(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

CORRECTED VERSION

G00002

(19) World Intellectual Property Organization
International Bureau

(43) International Publication Date
10 January 2002 (10.01.2002)

PCT

(10) International Publication Number
WO 02/003439 A3

(51) International Patent Classification[7]: H01L 21/311

(21) International Application Number: PCT/US01/41275

(22) International Filing Date: 5 July 2001 (05.07.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/610,049 5 July 2000 (05.07.2000) US

(71) Applicant: MICRON TECHNOLOGY, INC. [US/US]; 8000 South Federal Way, Boise, ID 83707-0006 (US).

(72) Inventors: KO, Kei-Yu; 4611 East Rockbury Court, Meridian, ID 83642 (US). LI, Li; 2790 North Oldstone Way, Meridian, ID 83642 (US). BLALOCK, Guy, T., 8101 Silkwood Court, Boise, ID 83704 (US).

(74) Agents: POWER, Brick, G. et al.; Traskbritt, Suite 300, 230 South 500 East, P.O. Box 2550, Salt Lake City, UT 84110 (US).

(81) Designated States *(national)*: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.


(84) Designated States *(regional)*: ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:
— *with international search report*

[Continued on next page]

(54) Title: PROCESS FOR SELECTIVELY ETCHING DOPED SILICON DIOXIDE OVER UNDOPED SILICON DIOXIDE AND SILICON NITRIDE

162162



(57) Abstract: An etchant including $C_2H_xF_y$, where x is an integer from two to five, inclusive, where y is an integer from one to four, inclusive, and where x plus y equals six. The etchant etches doped silicon dioxide with selectivity over both undoped silicon dioxide and silicon nitride. Thus, undoped silicon dioxide and silicon nitride may be employed as etch stops in dry etch processes which utilize the $C_2H_xF_y$-containing etchant $C_2H_xF_y$ may be employed as either a primary etchant or as an additive to another etchant or etchant mixture. Semiconductor devices (10) that include structures that have been patterned with an etchant of the present invention or in accordance with the method of the present invention are also disclosed. Specifically, the present invention includes semiconductor devices (10) including doped silicon oxide structures (24) with substantially vertical sidewalls (34) and adjacent undoped silicon oxide or silicon nitride structures (36) exposed adjacent the sidewall (34).

WO 02/003439 A3

(88) Date of publication of the international search report:
6 June 2002

(48) Date of publication of this corrected version:
4 July 2002

(15) Information about Correction:
see PCT Gazette No. 27/2002 of 4 July 2002, Section II

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette