

Description

RESIN MOLD, PRODUCTION METHOD THEREOF, AND USE THEREOF

TECHNICAL FIELD

5 [0001]

The present invention relates to a resin mold. More specifically, the present invention relates to a resin mold having superior releasability from a resin to be imprinted.

10 BACKGROUND ART

[0002]

Imprinting technology is a technology in which a mold for molding a depressions and protrusions pattern is pressed into a liquid resin or the like upon a substrate, and transfers the
15 pattern of the mold to the resin. Depressions and protrusions patterns exist at sizes ranging from nano-scale (10 nm level) to about 100 μm , and these patterns are used in various types of fields such as semiconductor materials, optical materials, recording media, micro machines, biotechnology, environment, or the like.

20 [0003]

Types of imprinting are exemplified by thermal imprinting, photo imprinting, or the like. Thermal imprinting presses a mold having a certain pattern formed in the surface thereof against a thermoplastic resin melted at a temperature greater than or equal

to the glass transition temperature, thermally imprints the surface pattern of the mold into the thermoplastic resin, and peels off the imprinted thermoplastic resin from the mold after cooling. Photo imprinting presses the same type of mold against a
5 photo-curable resin, causes curing of the photo-curable resin by ultraviolet radiation, and then peels the cured photo-curable resin from the mold.

[0004]

In order to prevent attachment of the resin to the mold
10 during imprinting, a release layer is arranged on the depressions and protrusions surface of the mold so as to impart releasability from the resin to the depressions and protrusions surface. However, there has been a problem in that, when the release layer adheres poorly to the mold, the release layer is shed due to
15 imprinting. Therefore in order to solve the aforementioned problem, a method is known that treats the surface of the mold by plasma treatment or a silane coupling agent treatment so as to cause an improvement of adhesion of the mold release agent to the mold (e.g. see Patent Document 1). Moreover, a method is known
20 that uses as the mold release agent a perfluoropolyether having functional groups that are chemically reactive with the material of the mold (e.g. see Patent Documents 2 and 3). These methods all relate to release treatment for molds of hard substances such as metal, silicon, glass, or the like.

[0005]

Resin molds are being used in recent years due to general versatility and cost. Mold release agents are being used even for resin molds. However, since the resin mold and the resin
5 to be imprinted are both resins, adhesion of the mold release agent is of a similar extent to both resins, and this results in a problem in that the release layer is transferred to the resin to be imprinted. Technology is desired for improving adhesion of the release layer to the resin mold.

10 [0006]

In order to solve the aforementioned problems, for example, an oxide layer composed of an inorganic oxide is formed on the surface of a replica mold, and shedding of the release layer from the surface of the replica mold is prevented. Although it is
15 possible to prevent shedding of the release layer from the oxide layer by formation of a release layer with this oxide layer interposed between the release layer and the mold, adhesion of this oxide film to the resin film is not necessarily good.

[0007]

20 Therefore, there is a problem in that, even when the release layer and the oxide film are integrated, there still may be transfer of the integrated release layer and oxide film to the surface of the imprinted resin film.

CITATION LIST

Patent Literatures

[0008]

Patent Document 1: Japanese Unexamined Patent Application

5 Publication No. 2010-5841

Patent Document 2: Japanese Patent No. 4154595

Patent Document 3: Japanese Unexamined Patent Application

Publication No. 2004-306030

10 SUMMARY

Problem to be Solved

[0009]

An object of the embodiments disclosed herein is to provide a resin mold for imprinting without transfer defects, that has excellent releasability from the resin to be imprinted, and that is free of shedding of the mold release agent when imprinting. Moreover, another object of the embodiments disclosed herein is to provide a resin mold that is capable of inexpensive mass production. Yet another object of the embodiments disclosed herein is to provide a resin mold that has flexibility and can be used by fixing to a roller or the like.

Solution to Problem

[0010]

25 [1] A resin mold comprising:

a substrate,

a resin layer formed upon the substrate and having a depressions and protrusions pattern formed on the surface of the resin layer,

5 and a release layer containing a mold release agent and being formed with uniform thickness on at least the surface of the depressions and protrusions pattern of said resin layer;


wherein said resin layer comprises a solvent soluble resin and an additive; the additive contains a substituent group capable
10 of coupling with said mold release agent and a substituent group having compatibility with said solvent soluble resin and has bleeding ability with respect to the solvent soluble resin;

said additive is localized in the vicinity of said resin layer surface and the substituent group capable of coupling with
15 the mold release agent contained in the additive bonds chemically with said mold release agent to couple together said resin layer and release layer.

[2] The resin mold according to [1]; where the pure water
20 contact angle of the aforementioned release layer surface is greater than or equal to 100 degrees.

[3] The resin mold according to [1] or [2]; where the aforementioned additive is a compound, or hydrolysate thereof, indicated by the below listed General Formula (1):

[0011]



In General Formula (1), Y is a methoxy or ethoxy group; X is an organic group including one type selected from the group consisting of an epoxy group, glycidoxy group, and optionally substituted phenyl group and amino group; and n is 0 or 1.

[4] The resin mold according to any one of [1] to [3]; where the content of the aforementioned additive within the aforementioned resin layer is from 1 to 13 percent by weight.

10 [5] The resin mold according to [3] or [4]; where the aforementioned solvent soluble resin has a constituent unit having a substituent group of the same type as X in the aforementioned General Formula (1).

15 [6] The resin mold according to [5]; where, in the aforementioned solvent soluble resin, the content of the constituent unit having the substituent group of the same type as X in the aforementioned General Formula (1) is from 1 to 15 percent by weight.

20 [7] The resin mold according to any one of [3] to [6]; where the aforementioned substituent group of the aforementioned additive having compatibility with the aforementioned solvent resin is the substituent group X in the aforementioned General Formula (1).

[8] The resin mold according to any one of [3] to [7]; where

the aforementioned substituent group of the aforementioned additive capable of coupling with the aforementioned mold release agent is the substituent group Y in the aforementioned General Formula (1) or a hydrolysate of such substituent group Y.

5 [9] The resin mold according to any one of [1] to [8]; where the aforementioned mold release agent is at least one type selected from the group consisting of fluorine-based silane coupling agents, mono-terminal aminated perfluoro (perfluoroether) compounds, and mono-terminal carboxylated perfluoro (perfluoroether)
10 compounds.

 [10] The resin mold according to any one of [1] to [9]; where the aforementioned substrate is a resin substrate, glass substrate, silicon substrate, sapphire substrate, carbon substrate, or GaN substrate.

15 [11] The resin mold according to [10]; where the aforementioned resin substrate is one type of resin selected from the group consisting of : polyethylene terephthalates, polycarbonates, polymethylmethacrylates, polyimides, polysulfones, polyether sulfones, cyclic polyolefins, and
20 polyethylene naphthalates.

 [12] The resin mold according to any one of [1] to [11]; where period of the depressions and protrusions pattern of the surface is from 10 nm to 50 μ m.

 [13] The resin mold according to any one of [1] to [12];

where shape of the depressions and protrusions pattern of the surface is linear shaped, columnar shaped, moth-eye-pattern shaped, or lens shaped.

[14] A method of production of a resin mold comprising steps

5 of:

(I) applying to a substrate a solution dissolving a solvent soluble resin and an additive in a solvent, and forming a resin solution layer on the substrate;

(II) removing the solvent from the aforementioned resin
10 solution layer and forming a resin layer upon the substrate;

(III) contacting a mold against the aforementioned resin layer, and transferring a depressions and protrusions pattern formed in the surface of the aforementioned mold to the surface of the aforementioned resin layer; and

15 (IV) coating a mold release agent on the surface of at least the depressions and protrusions pattern of the aforementioned resin layer, and forming a release layer of uniform thickness.

[15] A method of use of a resin mold comprising steps of: contacting the resin surface against the resin mold according to
20 any one of [1] to [13]; and peeling the aforementioned resin mold from the aforementioned resin.

[16] The method of use of a resin mold according to [15]; where the aforementioned resin is a photo-curable resin.

[17] The resin mold according to any one of [1] to [13];

where the resin mold is fixed to a roller.

[0011a]


In a first aspect, there is provided a resin mold comprising:

a substrate,

5 a resin layer formed upon the substrate and having a depressions and protrusions pattern formed on the surface of the resin layer,

and a release layer containing a mold release agent and being formed with uniform thickness on at least the surface of the
10 depressions and protrusions pattern of said resin layer;

wherein said resin layer comprises a solvent soluble resin and an additive; said additive is a compound, or hydrolysate thereof, of General Formula (1):



15 wherein Y is a methoxy or ethoxy group; X is an organic group including one type selected from the group consisting of an epoxy group, glycidoxy group, and optionally substituted phenyl group or amino group; and n is 0 or 1;

the solvent soluble resin has a constituent unit having a
20 substituent group of the same type as X in said General Formula (1); and

said additive is localized in the vicinity of said resin layer surface, the substituent group Y in said General Formula (1) of the additive, or a hydrolysate of such substituent group Y, bonding chemically with said mold release agent to couple together said resin layer and release layer.

[0011b]

In a second aspect, there is provided a method of production of a resin mold comprising steps of:


(I) applying to a substrate a solution dissolving a solvent soluble resin and an additive in a solvent, and forming a resin solution layer on the substrate;

(II) removing the solvent from said resin solution layer and forming a resin layer upon the substrate;

(III) contacting a mold against said resin layer, and transferring a depressions and protrusions pattern formed in the surface of said mold to the surface of said resin layer; and

(IV) coating a mold release agent on the surface of at least the depressions and protrusions pattern of said resin layer, and forming a release layer of uniform thickness;

wherein the additive is a compound, or hydrolysate thereof, of General Formula (1):



wherein Y is a methoxy or ethoxy group; X is an organic group including one type selected from the group consisting of an epoxy group, glycidoxy group, and optionally substituted phenyl group or amino group; and n

5 is 0 or 1,

and the solvent soluble resin has a constituent unit having a substituent group of the same type as X in said General Formula (1).

[0011c]

10 In a third aspect, there is provided a method of use of a resin mold comprising steps of:

contacting the resin surface against the resin mold as defined above;

and peeling said resin mold from said resin.

15

ADVANTAGEOUS EFFECTS

[0012]

The resin mold of the present disclosure has excellent releasability from the resin to be imprinted, and there is no shedding of mold release agent due to imprinting. Moreover, the
20 imprinted resin has no transfer defects.

[0013]

The resin mold of the present disclosure is mainly composed of resin, and thus inexpensive mass production is possible, and the resin mold is flexible.

5

BRIEF DESCRIPTION OF THE DRAWINGS

[0014]

FIG. 1 shows a resin mold of the present invention that has a quasi-4 layer structure.

10

FIG. 2 shows the method of production of the resin mold of the present invention that has a quasi-4 layer structure.

FIG. 3 shows the method of use of the resin mold of the present invention.

FIG. 4 shows the method of use of the roller type resin mold.

15

DESCRIPTION OF EMBODIMENTS

[0015]

The present invention will be explained concretely hereinafter.

[0016]

5 The present invention will be explained with reference to the schematic cross-sectional view of the resin mold of the present invention shown in FIG. 1.

[0017]

10 The present invention relates to a resin mold including:
a substrate, a resin layer formed upon the substrate and having a depressions and protrusions pattern formed in the surface thereof, and a release layer including a mold release agent and being formed of uniform thickness on at least the depressions and protrusions pattern of the aforementioned resin layer;

15 where the aforementioned resin layer has a solvent soluble resin, and the aforementioned resin layer further includes an additive that has bleeding ability with respect to the solvent soluble resin, has a substituent group capable of coupling with the aforementioned mold release agent, and has a substituent group
20 having compatibility with the aforementioned solvent soluble resin;

the aforementioned additive is localized in the vicinity of the aforementioned resin layer surface; and the group of the additive capable of coupling with the mold release agent bonds

chemically with the aforementioned mold release agent and couples together the aforementioned resin layer and release layer.

1. Method for Production of the Resin Mold

This resin mold is produced by the steps of:

5 (I) applying to a substrate a solution dissolving a solvent soluble resin and an additive in a solvent, and forming a resin solution layer on the substrate;

(II) removing the solvent from the aforementioned resin solution layer and forming a resin layer upon the substrate;

10 (III) contacting a mold against the aforementioned resin layer, and transferring a depressions and protrusions pattern formed in the surface of the aforementioned mold to the surface of the aforementioned resin layer; and

(IV) coating a mold release agent on the surface of at least
15 the depressions and protrusions pattern of the aforementioned resin layer, and forming a release layer of uniform thickness.
[0018]

The method of producing the quasi-4 layer structure resin mold will be described with reference to FIG. 2.

20 [0019]

A substrate 4 is prepared as shown in FIG. 2(a).

[0020]

Next, a resin solution is applied to the substrate 4 as shown in FIG. 2(b), and a resin solution layer 3' is produced.

[0021]

Next, the solvent is removed from the resin solution layer 3' as shown in FIG. 2(c), and a resin layer 3 is formed in which the additive 2 is localized in the vicinity of the surface above the substrate 4.

[0022]

Next, by contacting the mold against the aforementioned resin layer 3 as shown in FIG. 2(d), the depressions and protrusions pattern formed in the surface of this mold is transferred to the surface of the resin layer.

[0023]

Thereafter, as shown in FIG. 2(e), a release layer 1 of uniform thickness is formed on the surface of said resin layer 3 at least where the depressions and protrusions pattern is present.

<Step (I): Step of coating the solution dissolving solvent soluble resin and additive in a solvent on the substrate, and forming a resin solution layer>

In step (I), firstly the solvent soluble resin and the additive are uniformly dissolved in solvent to produce the resin solution.

[0024]

The solvent is a normal organic solvent, as exemplified by: aromatic type solvents such as benzene, toluene, xylene, or the

like; ketone type solvents such as acetone, methyl ethyl ketone, cyclohexanone, or the like; halogen type solvents such as methylene chloride, chloroform, carbon tetrachloride, ethylene chloride, tetrachloroethane, chlorobenzene, or the like; ether
5 type solvents such as tetrahydrofuran, dioxane, ethylene glycol diethyl ether, or the like; ester type solvents such as methyl acetate, ethyl acetate, ethyl cellosolve, propylene glycol methyl ester acetate, or the like; alcohol type solvents such as methanol, ethanol, isopropyl alcohol, or the like; as well as
10 dimethylformamide, dimethyl sulfoxide, diethyl formamide, or the like. From the standpoint of coating ability, the solvent is preferably an aromatic type solvent or ester type solvent. Moreover, propylene glycol methyl ether acetate and toluene are particularly preferred solvents.

15 [0025]

The additive which is possible to use, has a substituent group that is capable of coupling with the aforementioned mold release agent and has a substituent group that is compatible with the aforementioned solvent soluble resin and has bleeding ability
20 with respect to the solvent soluble resin.

[0026]

Examples of the additive include the compounds indicated by the below listed General Formula (1) and hydrolysates of such compounds.

[0027]



In General Formula (1), Y is a methoxy or ethoxy group; X is an organic group including one type selected from the group including an epoxy group, glycidoxy group, and optionally substituted phenyl group or amino group; and n is 0 or 1.

The organic group preferably has 1 to 9 carbon atoms, more preferably has 2 to 6 carbon atoms, and yet further preferably has 3 to 6 carbon atoms.

10 [0028]

Here, the Y group or the hydrolysate thereof is considered to be the group that has the ability to couple with the aforementioned mold release agent. X is considered to be the group that has compatibility with the aforementioned solvent soluble resin.

[0029]

Any resin may be used as the solvent soluble resin as long as resin that is soluble in the aforementioned solvent and there is no separation from the aforementioned additive. Examples of thermoplastic resins include acrylic type resins, methacrylic type resins, styrene type resins, epoxy type resins, polyester type resins, olefin type resins, polycarbonate type resins, and the like. When the additive is a compound as indicated in the aforementioned General Formula (1), from the standpoint of

compatibility with the additive, the solvent soluble resin is preferably the above mentioned thermoplastic resin that has a constituent unit that includes the same type of substituent group as X. The constituent unit having the same type of substituent
5 group as X is included (based on total constituent units of the resin) at a concentration that is preferably from 1 to 15 percent by weight, and more preferably from 2 to 10 percent by weight. When the aforementioned range is used, although there is no separation of the solvent soluble resin and the additive, both
10 components are not entirely miscible after removal of the solvent, and it is thought that the additive bleeds out toward the resin layer surface.

[0030]

When the solvent soluble resin and additive are added to
15 the aforementioned solvent, both components dissolve uniformly. Taking the total parts by weight of the solvent soluble resin and the additive to be 100 parts by weight, the added portion of the solvent soluble resin in the solvent is preferably from 87 to 99 parts by weight, and more preferably from 91 to 98 parts by weight,
20 and the added portion of the additive in the solvent is preferably from 1 to 13 parts by weight, and more preferably is from 2 to 9 parts by weight. The total added amount of the solvent soluble resin and additive in the solvent relative to the solvent is preferably 5 to 50 % by weight, and more preferably is 10 to 40 %

by weight.

[0031]

Thereafter, the solution containing the aforementioned solvent soluble resin and additive dissolved in solvent is coated
5 onto the substrate, and the resin solution layer is formed.

[0032]

Examples of the substrate include one type selected from among resin substrates, glass substrates, silicon substrates, sapphire substrates, carbon substrates, and GaN substrates. For
10 forming a flexible resin mold, the resin substrate is preferable, the substrate is exemplified by one type selected from the group including polyethylene terephthalate, polycarbonates, polymethylmethacrylates, polyimides, polysulfones, polyether sulfones, cyclic polyolefins, and polyethylene naphthalates.

15 [0033]

Examples of a coating method of the solution on the substrate include spin coating, spray coating, bar coating, lip coating, slit coating, or the like.

<(Step II): Step of removing the solvent from the aforementioned
20 resin solution layer and forming the resin layer upon the substrate>

Thereafter, the solvent is removed from the resin solution layer, and a resin layer is formed. The resin layer comprises the solvent soluble resin, and the additive which has a substituent

group capable of coupling with the aforementioned mold release agent, has a substituent group having compatibility with the aforementioned solvent soluble resin, and has bleeding ability relative to the solvent soluble resin.

5 [0034]

Examples of a removal method of the solvent include placing the resin solution layer on a hot plate or the like to cause drying. The temperature of drying is normally a temperature greater than or equal to the boiling point of the solvent, and this temperature
10 is a temperature that does not affect properties of the resin or the like.

[0035]

A thickness of the resin layer formed in this manner is normally from 50 nm to 30 μm , and preferably is from 500 nm to
15 10 μm . Such a thickness facilitates imprinting processing.

[0036]

Compatibility between the additive and solvent soluble resin is thought to change due to this drying step. Except for the substituent group having compatibility with the solvent
20 soluble resin, the additive is thought to not have good overall compatibility with the solvent soluble resin. As a result, when solvent is removed from the resin solution layer, only the substituent group having compatibility with the solvent soluble resin is thought to remain within the resin layer, and the

remaining constituent part of the additive is thought to protrude outside the resin layer, resulting in bleeding at the surface of the resin layer so that the additive becomes localized in the vicinity of the resin layer surface.

5 [0037]

Thus, if the additive is the compound indicated by the aforementioned General Formula (1), due to the solvent soluble resin having a constituent unit having a substituent group that is the same type as the substituent group X, the additive has partial compatibility with the solvent soluble resin, and it is thought that a structure does not result where the additive and the solvent soluble resin are separated. Since the non-X part of the additive does not have compatibility with the solvent soluble resin, the additive is thought to localize near the surface of the resin layer, resulting in bleeding out occurs. In this context, the expression "a substituent group that is the same type as the substituent group X" means a substituent group that has the same basic skeleton. For example, if X is the glycidoxy group, this means the substituent group having an epoxy structure. If X is an optionally substituted phenyl group, this means the substituent group having an aromatic ring.

[0038]

Taking the total percent by weight of the solvent soluble resin and additive to be 100 percent by weight, the resin layer

comprises the solvent soluble resin is preferably from 87 to 99 percent by weight, and more preferably from 91 to 98 percent by weight of the resin layer. The resin layer comprises the additive is preferably from 1 to 13 percent by weight, and more preferably
5 from 2 to 9 percent by weight, of the resin layer. When the proportions of the solvent soluble resin and additive are within the aforementioned range, the resin layer and release layer are bonded together with sufficient adhesiveness, and there is no shedding of the additive from the resin layer.

10 <(Step III): Step of contacting the mold against the aforementioned resin layer, and transferring the depressions and protrusions pattern formed in the surface of the mold to the surface of the aforementioned resin layer>

The surface geometry (i.e. depressions and protrusions
15 pattern) of the mold (i.e. quartz, metal, silicon, or the like normally used for imprinting) is copied (imprinted) to the surface of the aforementioned resin layer.

[0039]

Although no particular limitation is placed on the surface
20 geometry (depressions and protrusions pattern) of the mold, the surface geometry preferably has a period of 10 nm to 50 μm , a depth of 10 nm to 100 μm , and a transferring surface of 1.0 to $1.0 \times 10^6 \text{ mm}^2$. More preferably, the surface geometry has a period of 20 nm to 20 μm , a depth of 50 nm to 1 μm , and a transferring surface

of 1.0 to $0.25 \times 10^6 \text{ mm}^2$. Due to such surface geometry, it is possible to form a sufficient depressions and protrusions pattern in the resin layer. Examples of geometry include moth-eye pattern, linear, columnar, monolithic, conical, multi-sided pyramidal, and micro-lens shaped.

[0040]

The transferring (imprinting) is performed by thermal imprinting since the aforementioned resin layer is a thermoplastic resin.

10 [0041]

For the thermal imprinting to be performed using the operation normally used for thermal imprinting of a thermal plastic resin, a preferred thermal imprinting operation that may be cited is performed by maintaining the mold at a pressure of 0.5 to 50 MPa for 10 to 600 seconds against a resin heated to a temperature greater than or equal to the glass transition temperature (T_g), thereafter cooling the resin to a temperature less than or equal to the glass transition temperature (T_g), and then pulling apart the mold and resin layer. The depressions and protrusions pattern is formed in the surface of the resin layer by the thermal imprinting.

<(Step IV): Step of coating a mold release agent at least on the surface where the aforementioned resin layer has the depressions and protrusions pattern, and forming a release layer of uniform

thickness>

On at least the surface having the pattern of the
aforementioned resin layer, the release layer is formed by coating
the aforementioned mold release agent by a normal coating
5 operation such as dip coating, spin coating, vapor deposition,
spraying, or the like. Furthermore, the mold release agent may
be a mold release agent diluted by an organic solvent in which
the mold release agent dissolves.

[0042]

10 The mold release agent is preferably at least one type
selected from the group including fluorine-based silane coupling
agents, perfluoro compounds having an amino group or carboxyl
group, and perfluoro ether compounds having an amino group or
carboxyl group. More preferably, the mold release agent is at least
15 one type selected from the group including fluorine-based silane
coupling agents, mono-terminal aminated perfluoro
(perfluoroether) compounds, and mono-terminal carboxylated
perfluoro (perfluoroether) compounds, either as a single compound
or a mixture of single compound and multiple compounds.

20 [0043]

When the aforementioned type of compound is used as the mold
release agent, adhesion to the above mentioned resin layer is
excellent, and releasability from the imprinted resin is
excellent.

[0044]

After the aforementioned coating operation, rinse treatment of the surface of the mold release agent coating film is preferably performed using, for example, fluorine-based solvent such as perfluorohexane. Although the aforementioned rinse treatment is preferable in order to obtain a release layer of uniform thickness, it is permissible not to perform rinse treatment if it is possible to maintain uniform thickness of the release layer by the aforementioned mold release agent coating operation.

10 [0045]

Due to this process, a release layer is formed that preferably has a thickness of 0.5 to 20 nm, more preferably 0.5 to 10 nm, and most preferably 0.5 to 5 nm.

[0046]

15 The release layer is thought to bind to the aforementioned resin layer by chemical bonding between the mold release agent and the group capable of coupling with the mold release agent of the additive mainly present near the resin layer surface. The chemical bonding is thought to be due to condensation reaction.

20 [0047]

When the aforementioned additive is indicated by the aforementioned General Formula (1), the substituent group Y (or hydrolysate thereof) is thought to chemically bonded with a substituent group (including groups generated by hydrolysis) of

the mold release agent. The chemical bonding is thought to be due to condensation reaction.

[0048]

The aforementioned release layer is formed at uniform
5 thickness on at least the surface that has the depressions and protrusions pattern of the resin layer. The expression "uniform thickness" means substantially uniform thickness, and means a thickness that is uniform within a standard deviation of 0.1 to 10. Therefore, the surface of the release layer maintains the
10 depressions and protrusions shape of the resin layer surface geometry.

[0049]

The release layer contact angle for pure water on the release layer surface is preferably at least 100 degrees, more preferably
15 is from 100 to 130 degrees, and further preferably is from 100 to 120 degrees.

[0050]

Wetting ability is low when the contact angle is within the aforementioned range, and it is thus possible to suppress flow
20 of the resin of the release layer surface during coating of the liquid imprinting resin on the surface of the release layer. It is also thought that the imprinted resin becomes readily peeled from the release layer surface.

2. Resin Mold

The resin mold of the present invention is produced by the
aforementioned production method.

[0051]

The invention of the present application is a resin mold
5 that has a multi-layer structure.

[0052]

As shown in FIG. 1, the resin mold of the present invention
is a quasi-4 layer structure resin mold that has a substrate 4,
a resin layer 3 formed upon the aforementioned substrate and having
10 a depressions and protrusions pattern, the aforementioned
additive 2 mainly present near the resin layer surface, and a
release layer 1 formed of uniform thickness at least on the surface
of said resin layer 3 having the depressions and protrusions
pattern.

15 [0053]

The resin layer of the resin mold of the present invention
is the resin layer formed by steps (I) to (III) of the
aforementioned production method. Therefore, the solvent
soluble resin and additive composing the resin layer, the
20 dimensions of the resin layer, and the structure of the resin layer
are as explained above. The height "a" of the resin layer shown
in FIG. 1 (i.e. the height of the part lacking depressions and
protrusions shape) is preferably from 1 to 15 times height of "b"
shown in FIG. 1 (i.e. height of the depressions and protrusions

shape). Imprint processing may be performed without problem when this ratio is used.

[0054]

The release layer of the resin mold of the present invention
5 is the release layer formed by the step (IV) of the aforementioned production method. Therefore, the mold release agent composing the release layer and dimensions of the release layer are as described above.

[0055]

10 The aforementioned resin layer and the aforementioned release layer are thought to be bonded together by chemical bonding between the aforementioned additive and mold release agent. The mechanism thereof is as described above.

[0056]

15 The aforementioned resin mold has the desired geometry on the surface.

[0057]

The "desired geometry" is normally a depressions and protrusions pattern that has a fixed repeat frequency. That is
20 to say, this is a depressions and protrusions pattern that preferably has a frequency of 10 nm to 50 μm , a depth of 10 nm to 100 μm , and a transferring surface of 1.0 to $1.0 \times 10^6 \text{ mm}^2$.

[0058]

Specific examples of geometrics include moth-eye, linear,


columnar, monolithic, conical, multi-sided pyramidal, and micro-lens shaped.

[0059]

In other words, the resin mold of the present invention has
5 a resin layer having a depressions and protrusions pattern structure on the surface, and

has a release layer including a mold release agent formed of a uniform thickness on at least the surface having a depressions and protrusions pattern structure of the aforementioned resin
10 layer.

The above mentioned resin layer includes an additive (i.e. the compound indicated by the below listed General Formula (1) or a hydrolysate thereof)



15 (within the General Formula (1), Y is a methoxy or ethoxy group; X is an organic group including one type selected from the group including an epoxy group, glycidoxy group, and optionally substituted phenyl group or amino group; and n is 0 or 1)

and a solvent soluble resin having a substituent group that
20 is the same type as the substituent group X in the aforementioned General Formula (1).

The resin mold is characterized in that the aforementioned resin layer and release layer are bonded together due to chemical bonding between the mold release agent and the substituent group

Y of the aforementioned additive or hydrolysate group thereof.

[0060]

A roller type resin mold is cited as one aspect of the resin mold of the present invention.

5 [0061]

As shown in FIG. 4, a roller type resin mold is a mold of a configuration similar to the aforementioned resin mold where the mold in a form wound upon a roller or the like with the depressions and protrusions surface is oriented outwardly.

10 [0062]

In a preferred configuration of the roller type resin mold, the mold has a flexible structure of 30 to 300 μm thickness.

[0063]

3. Method of Use of the Resin Mold

15 (1) Normal Method of Use

The resin mold of the present invention is used with advantage for imprinting a thermoplastic resin, thermosetting resin, or photo-curable resin. More preferably the resin mold of the present invention is used with advantage for imprinting
20 a photo-curable resin. An embodiment of the method of use will be described using FIG. 3.

[0064]

Next, as shown in FIG. 3(a), the resin mold of the present invention is contacted against the resin 5 surface.

[0065]

Next, as shown in FIG. 3(b), the resin mold of the present invention is peeled away, and the resin 5 is obtained with a patterned surface.

5 [0066]

<Step of contacting the resin mold against the resin surface>

The resin 5 to be imprinted is normally a thermoplastic resin, thermosetting resin, or photo-curable resin, and the resin 5 to be imprinted is normally on a substrate 6.

10 [0067]

Any substrate may be used without limitation as the substrate 6 provided that it is a substrate normally used for imprinting, as exemplified by resins, glasses, silicon, sapphire, gallium nitride, carbon, silicon carbide, or the like.

15 [0068]

If a thermoplastic resin or thermosetting resin is used, it is possible to use the procedure used for normal thermal imprinting thermoplastic resin or thermosetting resin. However, processing is preferably performed by pressing the mold at a pressure of 0.5 to 50 MPa for a time of 10 to 600 seconds against the resin heated to a temperature greater than or equal to the glass transition temperature (T_g).

[0069]

Any generally used thermoplastic resin or thermosetting

resin may be used without limitation as the thermoplastic resin or thermosetting resin.

[0070]

If a photo-curable resin is used, it is possible to use the
5 operation normally used for photo imprinting of a photo-curable resin. However, the procedure is preferably performed, while maintaining contact of the mold against the resin at a pressure of 0.1 to 5 MPa for 1 to 600 seconds, by irradiation using energetic radiation (i.e. ultraviolet radiation, visible radiation,
10 infrared radiation, or electron beam radiation).

[0071]

In photo imprinting of the photo-curable resin, since greater pressure is not required than that for thermal imprinting in the above described manner, it is possible to appropriately
15 use various types of embodiments of the resin mold of the present invention. For example, a flexible embodiment of the resin mold or the like using a film or the like on the substrate may be used with advantage for photo imprinting of the photo-curable resin.

[0072]

20 Any general photo-curable resin may be used as the photo-curable resin without limitation.

[0073]

<Step of separating the resin and resin mold>

When a thermoplastic resin or thermosetting resin is used,

the resin is cooled to a temperature less than or equal to the glass transition temperature (T_g), and the resin layer and the mold are separated.

[0074]

5 When a photo-curable resin is used, the mold and resin layer are separated.

[0075]

(2) Method of Use As a Roller Type Resin Mold

10 The resin mold of the present invention may be used as a roller type resin mold by wrapping the resin mold upon a roller or the like.

[0076]

15 Use of the resin mold as a roller type resin mold is suitable for imprinting a photo-curable resin. As shown in FIG. 4, the aforementioned step of pressing the resin mold against the aforementioned resin surface is composed of pressing the resin mold wrapped upon a roller against the aforementioned resin surface and irradiating by ultraviolet radiation.

[0077]

20 4. Applications

 The resin mold of the present invention is used for imprinting a thermoplastic resin, thermosetting resin, or photo-curable resin.

[0078]

The various products obtained from the imprinted resin may be used for semiconductor materials, optical elements, prisms, micro lenses, memory media, holography, micro-machines, biotech products, environmental products, and electronic materials such as semiconductors, LEDs, hard discs, or the like.

[0079]

A surface pattern geometry period of 20 nm to 500 nm is preferred for use in semiconductor materials, media, optical elements, or the like. A surface pattern geometry period of 200 nm to 20 μ m is suitable for use in prisms, micro lenses, or the like.

[0080]

If the resin mold of the present invention is a roller type resin mold, the resin mold may be used for continuous molding, and such a roller type resin mold is preferably used for optically functional films such as a micro lens film, anti-reflective film, or the like.

EXAMPLES

[0081]

Although the present invention is explained below further based on examples, the present invention is not limited by these examples.

[0082]

In the specification of the present application and in the examples, various values were measured by the below described measurement methods.

[0083]

5 <Weight average molecular weight Mw>

Gel permeation chromatography (GPC) was used to determine weight average molecular weight (Mw) based on standard polystyrene.

Measurement Conditions

10 Equipment: HLC-8120 GPC (manufactured by Tosoh Corp.)

Column: The 5 columns listed below were used in series.

[0084].

TSK-GEL HXL-H (guard column, manufactured by Tosoh Corp.)

TSK-GEL G7000 HXL (manufactured by Tosoh Corp.)

15 TSK-GEL GMHXL (manufactured by Tosoh Corp.)

TSK-GEL GMHXL (manufactured by Tosoh Corp.)

TSK-GEL G2500 HXL (manufactured by Tosoh Corp.)

Sample concentration: diluted by tetrahydrofuran to reach a concentration of 1.0 mg/cm^3

20 Mobile phase solvent: tetrahydrofuran

Flow rate: $1.0 \text{ cm}^3/\text{minute}$

Column temperature: 40°C

<Thickness of the Resin Layer>

Thickness of the resin layer was taken to be the separation

between the resin layer bottom surface and the highest surface within the surface having the depressions and protrusions pattern.

[0085]

<Thickness of the Release Layer>

5 A thickness measurement device (model F20, manufactured by
Filmetrics Inc.) was used. Measurement was performed at 5
arbitrary locations within the surface, and the average value was
taken to be thickness of the release layer. Uniformity of
thickness was checked by the standard deviation of the
10 aforementioned 5 points.

[0086]

<Contact Angle of Pure Water against the Release Layer Surface>

The contact angle is measured in air by placing a minute
water droplet of about 1 μ L volume was placed on the sample
15 surface with a Kyowa Contact-Angle Meter model CA-D, manufactured
by Kyowa Interface Science Co., Ltd. Measurement conditions were
based on JIS R3257.

[0087]

The rate of change was found by the following formula:
20 ("pre-imprint release layer contact angle" - "post-imprint
release layer contact angle") $\div$ "pre-imprint release layer contact
angle" $\times$ 100 (percent).

[0088]

<Surface Geometry (Pattern)>

The period and line width were evaluated by SEM (S-4800, manufactured by Hitachi High Technologies Corp.), and depth (height) was evaluated using an AFM (L-Trace, manufactured by SII NanoTechnology, Inc.).

5 [0089]

<Imprinting Results>

Macro-evaluation: The transferring surface formed on the imprinted resin was observed at ×20 magnification using an optical microscope (ELIPSE LV100, manufactured by Nikon Corp.), and the
10 presence or absence of resin attachment to the mold was checked.

○ : There was no resin attachment. × : There was resin attachment.

SEM (period): The pattern formed in the imprinted resin was measured by SEM, and the evaluation was performed by determining
15 whether or not there was a change in the SEM measurement results for the pattern formed in the resin mold surface according to the below listed standards.

○ : The amount of change was less than 10 nm. × : The amount of change was greater than or equal to 10 nm.

20 AFM (depth): The pattern formed in the imprinted resin was measured by AFM. The presence or absence of change based on the AFM measurement results for the pattern formed in the surface of the resin mold was determined and evaluated according to the below listed standards.

o : The amount of change was less than 10 nm. × : The amount of change was greater than or equal to 10 nm.

Example 1

(i) Preparation of Resin (PMMA type) for the Resin Mold

5 95 parts by weight of methyl methacrylate (product name =
LIGHT ESTER M, manufactured by Kyoeisha Chemical Co., Ltd.), 5
parts by weight of glycidyl methacrylate (product name = LIGHT
ESTER G, manufactured by Kyoeisha Chemical Co., Ltd.), and 100
parts by weight of toluene were added to a flask equipped with
10 a stirrer device, nitrogen gas feed tube, thermometer, and tubular
refluxing condenser. Thereafter, while nitrogen gas was fed into
the flask, the contents of the flask were heated to 80°C, 0.5 parts
by weight of dimethyl 2,2'-azobis(2-methylpropionate) (product
name = V-601, manufactured by Wako Pure Chemical Industries, Ltd.)
15 as the initiator was added, and temperature was maintained at 80°C
for 8 hours. Thereafter, the flow of nitrogen gas was stopped,
100 parts by weight of toluene was added, and the reaction was
stopped by lowering temperature to obtain the resin for the resin
mold. Molecular weight of the obtained resin is shown in Table
20 1.

[0090]

(ii) Production of the Resin Mold

(ii-a) Production of the Resin Solution Layer and Resin Layer

The resin for the resin mold produced in (1) was diluted

10-fold using toluene, and then 5 parts by weight of
3-glycidoxypropyltrimethoxysilane (product name = KBM-403,
manufactured by Shin-Etsu Chemical Co., Ltd.) was added per 100
parts by weight of resin. Thereafter, this resin solution was
5 spin coated (2,000 rpm for 20 seconds) onto a polyethylene
terephthalate film (PET) (product name = LUMIRROR; manufactured
by Toray Industries, Inc.; 0.125 mm thick), and a hotplate was
used for drying for 15 minutes at 130°C. A resin layer of 1.2 μm
film thickness was produced.

10 [0091]

(ii-b) Forming the Depressions and protrusions Pattern of the
Resin Layer Surface

The laminate of the aforementioned film substrate and resin
layer was heated to 140°C, and a master mold (i.e. quartz mold
15 treated using release agent, transferring surface: 576 mm², 150
nm L/S (linear geometry), 300 nm period, 150 nm depth) (geometry
I) was pressed against the resin layer surface, and thermal
imprinting was performed at 140°C. The pressure of 20 MPa during
thermal imprinting was maintained for 5 minutes. Thereafter, the
20 laminate was cooled down to 80°C or less, the master mold was
removed, and the resin mold was obtained (transferring surface
of 576 mm², 150 nm L/S, 300 nm period, 150 nm depth). The period
and line width were evaluated using SEM (S-4800, manufactured by
Hitachi High Technologies Corp.). Depth (height) was evaluated

by AFM (L-trace, manufactured by SII Nanotechnology, Inc.).

[0092]

(ii-c) Production of the Release Layer

After the resin mold obtained during step (ii-b) was dipped
5 for 1 minutes in a perfluoro polyether type mold release agent
solution (product name = OPTOOL HD-1100, manufactured by Daikin
Industries, Ltd.), the resin mold was pulled up and placed for
1 hour in a warm and humid environment at 70°C and 90% relative
humidity. Thereafter, the resin mold was rinsed using a
10 fluorine-based solvent (product name = OPTOOL HD-TH, manufactured
by Daikin Industries, Ltd.), and the resin mold was left for 24
hours in a 23°C and 65% relative humidity environment. The pure
water contact angle was measured (Kyowa Contact-Angle Meter model
CA-D, manufactured by Kyowa Interface Science Co., Ltd.) as 110°C.
15 There were no defects or changes of geometry in the patterned part
(150 nm line width, 300 nm period, 150 nm depth).

[0093]

Measurement of contact angle for pure water was performed
in the air by placement of a minute droplet (about 1 μ L) on the
20 sample surface.

[0094]

(iii) Photo-nanoimprinting Using the Resin Mold

0.2 mL of a photo-curing resin (product name = PAK-02,
manufactured by Toyo Gosei Co., Ltd.) was dropped onto the resin

mold obtained during step (ii-c), the droplet was covered by a polycarbonate film (product name = Lexan, manufactured by Asahi Glass Co., Ltd.), and a photo-nano imprinter device (manufactured by Engineering System Co., Ltd.) was used to perform imprinting by pressing at 1.0 MPa and simultaneously irradiating ultraviolet radiation (10 mW/cm^2) for 2 seconds. Thereafter, the molded article was removed from the resin mold, and it was confirmed that there were no transfer defects in the molded article. Contact angle was measured by the same method as that of step (ii-c). It was confirmed that there was no change in contact angle. Furthermore, changes of geometry in the resin after imprinting was checked by SEM and AFM (148 nm line width, 298 nm period, 148 nm depth).

[0095]

This resin mold was used to perform 20 consecutive photo-nanoimprintings. It was possible to imprint without problems.

[0096]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 1.

[0097]

Example 2

Except for setting the added amount of 3-glycidoxypropyltrimethoxysilane in step (ii-a) of Example 1 to

10 parts by weight, a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0098]

5 Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 1.

[0099]

Example 3

Except for setting the added amount of
10 3-glycidoxypropyltrimethoxysilane in step (ii-a) of Example 1 to 1 part by weight, a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0100]

15 Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 1.

[0101]

Example 4

Except for use of 90 parts by weight of methyl methacrylate
20 and the use of 10 parts by weight of glycidyl methacrylate in step (i) of Example 1, a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0102]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 1.

[0103]

Example 5

5 Except for use of 99 parts by weight methyl methacrylate and 1 part by weight of glycidyl methacrylate in step (i) of Example 1, a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

10 [0104]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 1.

[0105]

Example 6

15 Except for use of 95 parts by weight of styrene (product name = Styrene Monomer, manufactured by Idemitsu Kosan Co., Ltd.) in place of the methyl methacrylate of step (i) of Example 1, a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in
20 the same manner as that of Example 1.

[0106]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 1.

[0107]

Example 7

Except for use of 95 parts by weight of isobornyl methacrylate (product name = Light Ester 1B-X, manufactured by Kyoeisha Chemical Co., Ltd.) in place of the methyl methacrylate of step (i) of Example 1, a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0108]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 1.

[0109]

Example 8

Except for use of 3-glycidoxypropyl methyldimethoxysilane (product name = Z-6044, manufactured by Dow Corning Toray Co., Ltd.) rather than the 3-glycidoxypropyltrimethoxysilane of step (ii-a) of Example 1, a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0110]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 2.

[0111]

Example 9

Except for use of 5 parts by weight of benzyl methacrylate

(product name = Light Ester BZ, manufactured by Kyoeisha Chemical Co., Ltd.) in place of the glycidyl methacrylate of step (i) of Example 1, and except for use of 5 parts by weight of phenyltrimethoxysilane (product name = KBM-103, manufactured by Shin-Etsu Silicone Co., Ltd.) in place of the 3-glycidoxypropyltrimethoxysilane of step (ii)-a of Example 1, a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

10 [0112]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 2.

[0113]

Example 10

15 Except for use of 5 parts by weight of dimethylaminoethyl methacrylate (product name = Light Ester DM, manufactured by Kyoeisha Chemical Co., Ltd.) in place of the glycidyl methacrylate of step (i) of Example 1, and except for use of 5 parts by weight of 3-aminopropyltrimethoxysilane (product name = KBM-903, 20 manufactured by Shin-Etsu Silicone Co., Ltd.) in place of the 3-glycidoxypropyltrimethoxysilane of step (ii)-a of Example 1, a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0114]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 2.

[0115]

5 Example 11

Except for use of perfluoro hexanoic acid rather than the perfluoro polyether type mold release agent of step (ii-c) of Example 1, a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform

10 photo-nanoimprinting in the same manner as that of Example 1.

[0116]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 1.

[0117]

15 Example 12

Except for use of 1H,1H-tridecafluoroheptylamine rather than the perfluoro polyether type mold release agent of step (ii-c) of Example 1, a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform

20 photo-nanoimprinting in the same manner as that of Example 1.

[0118]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 1.

[0119]

Example 13

Except for change of the master mold used in step (ii-b) of Example 1 to a master mold (geometry II) with 576 mm² transferring surface, 25 nm L/S, 50 nm period, and 150 nm depth (linear pattern), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0120]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 3.

[0121]

Example 14

Except for change of the master mold used in step (ii-b) of Example 1 to a master mold (geometry III) with 576 mm² transferring surface, 75 nm L/S, 150 nm period, and 150 nm depth (linear pattern), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0122]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 3.

[0123]

Example 15

Except for change of the master mold used in step (ii-b)

of Example 1 to a master mold (geometry IV) with 576 mm² transferring surface, 10,000 nm L/S, 20,000 nm period, and 300 nm depth (linear pattern), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform
5 photo-nanoimprinting in the same manner as that of Example 1.

[0124]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 3.

[0125]

10 Example 16

Except for change of the master mold used in step (ii-b) of Example 1 to a master mold (geometry V) with 576 mm² transferring surface, 200 nm hole diameter, 400 nm period, and 200 nm depth (columnar geometry), a resin mold was produced in the same manner
15 as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0126]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 3.

20 [0127]

Example 17

Except for change of the master mold used in step (ii-b) of Example 1 to a master mold (geometry VI) with 576 mm² transferring surface, 300 nm period, and 300 nm depth (moth-eye

geometry), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0128]

5 Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 3.

[0129]

Example 18

Except for change of the resin layer thickness of step (ii-a) of Example 1 to 6.4 μm , and except for change of the master mold used in step (ii-b) of Example 1 to a master mold (geometry VII) with 576 mm^2 transferring surface, 10,000 nm hole diameter, 20,000 nm period, and 4,000 nm depth (micro lens geometry), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0130]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 3.

20 [0131]

Example 19

Except for change of the polyethylene terephthalate film substrate of step (ii-a) of Example 1 to a soda glass substrate (1.1 mm thickness, manufactured by Asahi Glass Corp.), a resin

mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0132]

5 Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 4.

[0133]

Example 20

Except for change of the polyethylene terephthalate film
10 substrate of step (ii-a) of Example 1 to a silicon wafer substrate (0.5 mm thickness, manufactured by Covalent Materials Corp., usage grade = polished wafer grade), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example
15 1.

[0134]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 4.

[0135]

20 Example 21

Except for change of the polyethylene terephthalate film substrate of step (ii-a) of Example 1 to a sapphire substrate (0.5 mm thickness, manufactured by Orbe Pioneer, Ltd., semiconductor grade), a resin mold was produced in the same manner as Example

1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0136]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 4.

[0137]

Example 22

Except for change of the polyethylene terephthalate film substrate of step (ii-a) of Example 1 to a polysulfone substrate (0.12 mm thickness, product name = SUMILITE © FS-1200, manufactured by Sumitomo Bakelite Co., Ltd.), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0138]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 4.

[0139]

Example 23

Except for change of the polyethylene terephthalate film substrate of step (ii-a) of Example 1 to a polycarbonate substrate (0.12 mm thickness, product name = Lexan, Asahi Glass Corp.), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in

the same manner as that of Example 1.

[0140]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 4.

5 [0141]

Example 24

Except for change of the polyethylene terephthalate film substrate of step (ii-a) of Example 1 to a polyethylene naphthalate substrate (0.12 mm thickness, product name = TEONEX, manufactured
10 by Teijin Chemicals, Ltd.), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0142]

Nanoimprinting results and the obtained resin mold for
15 nanoimprinting are indicated in Table 4.

[0143]

Example 25

Except for change of the polyethylene terephthalate film substrate of step (ii-a) of Example 1 to a polyimide substrate
20 (0.3 mm thickness, product name = AURUM Film, manufactured by Mitsui Chemicals), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0144]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 4.

[0145]

Example 26

5 Except for change of the polyethylene terephthalate film substrate of step (ii-a) of Example 1 to a polymethylmethacrylate substrate (0.12 mm thickness, product name = ACRYPLEN, manufactured by Mitsubishi Rayon Co., Ltd.), a resin mold was produced in the same manner as Example 1. The obtained resin mold
10 was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0146]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 4.

15 [0147]

Example 27

 Except for change of the polyethylene terephthalate film substrate of step (ii-a) of Example 1 to diamond-like carbon surface-coated polyethylene terephthalate film substrate (0.12
20 mm thickness (1 μ m coating layer), product name = Geniuscoat DLC, manufactured by Nippon-ITF Inc.), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0148]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 4.

[0149]

5 Example 28

Except for change of the polyethylene terephthalate film substrate of step (ii-a) of Example 1 to glassy carbon (1 mm thickness, product name = SA-1, manufactured by Tokai Carbon Co., Ltd.), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0150]

Nanoimprinting results and the obtained resin mold for nanoimprinting are indicated in Table 4.

15 [0151]

Example 29

Except for change of the polyethylene terephthalate film substrate of step (ii-a) of Example 1 to a silicon carbide wafer (0.43 mm thickness, grade = 6NH-Type, manufactured by Tanke Blue Semiconductor Co., Ltd.), a resin mold was produced in the same manner as Example 1. The obtained resin mold was used to perform photo-nanoimprinting in the same manner as that of Example 1.

[0152]

Nanoimprinting results and the obtained resin mold for

nanoimprinting are indicated in Table 4.

[0153]

Comparative Example 1

When there was a change of the added amount of
5 3-glycidoxypropyltrimethoxysilane to 20 parts by weight during
step (ii-a) of Example 1, the 3-glycidoxypropyltrimethoxysilane
attached to the master mold during thermal nanoimprinting to the
resin layer of step (ii-b), and it was not possible to obtain a
resin mold.

10 [0154]

The results are shown in Table 1.

[0155]

Comparative Example 2

When the amount of added 3-glycidoxypropyltrimethoxysilane
15 was changed to 0.5 parts by weight for step (ii-a) of Example 1,
and when the peeling treatment of step (ii-c) was carried out,
the release layer was shed during the rinse step. It is thought
that this occurred since the required adhesivity between the resin
layer and release layer was not ensured.

20 [0156]

The results are shown in Table 1.

[0157]

Comparative Example 3

When the amount of the methyl methacrylate was changed to

80 parts by weight and the amount of glycidyl methacrylate was changed to 20 parts by weight for step (i) of Example 1, there was no bleeding out of additive to the surface of the resin layer formed in step (ii-a). Then during the rinse process of peeling treatment of step (ii-c), there was shedding of the mold release agent from the resin surface, and it was not possible to form a release layer. It is thought that this shedding occurred due to increased compatibility between the resin and additive.

[0158]

10 The results are shown in Table 1.

[0159]

Comparative Example 4

When the amount of methyl methacrylate was changed to 99.5 parts by weight and the amount of glycidyl methacrylate was changed to 0.5 parts by weight for step (i) of Example 1, during the rinse process of peeling treatment of step (ii-c), there was shedding of the mold release layer from the resin surface. It is thought that this occurred since the required adhesivity between the resin layer and release layer was not ensured.

20 [0160]

The results are shown in Table 1.

[0161]

Comparative Example 5

When 5 parts of benzyl methacrylate (product name = Light

Ester BZ, manufactured by Kyoeisha Chemical Co., Ltd.) was used instead of the glycidyl methacrylate in step (i) of Example 1, during the rinse process of peeling treatment of step (ii-c), there was shedding of the release layer. It is thought that this occurred since the required adhesivity between the resin layer and release layer was not ensured.

[0162]

The results are shown in Table 2.

[0163]

10 Reference Example 1

A polymer produced by the same method as that of step (i) of Example 1 was spin coated beforehand onto a glass substrate. The resin laminate was heated to 130°C, and an imprinting sheet was produced. Thermal imprinting was performed at 80°C by pressing the resin mold produced during Example 1 (576 mm² transferring surface, 150 nm L/S, 300 nm period, 150 nm depth) against this imprinting sheet. The pressure of 20 MPa was maintained for 5 minutes during thermal imprinting. Thereafter, the laminate was cooled to a temperature less than or equal to the T_g of the resin composing the resin layer, the resin mold was removed, and it was confirmed that there were no transfer defects. The results are shown in Table 5.

[0164]

Moreover, the present resin mold was used 20 times for

consecutive thermal nanoimprinting. Imprinting was possible without problems.

[0165]

The results are shown in Table 5.

5 [0166]

Reference Example 2

During step (iv) of Example 1, the resin mold obtained in step (ii-c) was wound upon a roll, and the Lexan film (imprinting region: 21 cm wide, 200 cm long) was pressed at 1.0 MPa. A
10 production line was run (1 m/min travel speed, handmade device) under conditions capable of uniform coating of PAK-02. Thereafter, ultraviolet radiation (70 mW/cm^2) was irradiated for 1 second while the line moved. While allowing the resin to cure, continuous roll imprinting was performed for 5 minutes to obtain
15 5 m of molded film. Thereafter, the resin mold was removed from the roll, and it was confirmed that there were no transfer defects in the mold. Moreover, contact angle was measured by the same method as that of step (iv), and it was confirmed that there was no change. Furthermore, it was confirmed by SEM and AFM that there
20 was no change of geometry in the resin after imprinting. The results are shown in Table 5.

[0167]

Abbreviations within the table have the below listed meanings.

PET: polyethylene terephthalate

Glass: soda glass

Si wafer: silicon wafer

PSF: polysulfone

5 PC: polycarbonate

PEN: polyethylene naphthalate

PMMA: polymethylmethacrylate

DLC: polyethylene terephthalate having a surface coating of
diamond-like carbon

10 GC: glassy carbon

SiC: silicon carbide wafer

HD-1100: perfluoropolyether type mold release agent liquid

15

20

[0168]

Table 1

					Example 1	Example 2	Example 3	Example 4
Master mold					I			
Mold	Substrate	Type			PET			
		Thickness (mm)			0.125			
	Resin layer	Composition	Constituent monomer of resin	Methyl methacrylate	95	95	95	90
				Styrene				
				Isobornyl methacrylate				
				Glycidyl methacrylate	5	5	5	10
		Additive	3-glycidoxyp pyltrimethoxys ilane	5	10	1	5	
			Thickness (μm)			1.2	1.2	1.2
		Weight average molecular weight (Mw)			8.3	8.3	8.3	8.5
		Release layer	Mold release agent			HD-1100	HD-1100	HD-1100
	Thickness (nm)			3	3	3	3	
	Standard deviation			0.43	0.43	0.43	0.43	
	Water contact angle (°)		Before imprinting	110	110	110	110	
			After imprinting	108	108	110	108	
			Rate of change after imprinting (%)	1.8	1.8	0.0	1.8	
	Results of imprinting		Macro inspection	o	o	o	o	
SEM (period)			o	o	o	o		
AFM (thickness)			o	o	o	o		

Table 1(Continued)

					Example 5	Example 6	Example 7	Example 11	Example 12
Master mold					I				
Mold	PET	Type			PET				
		Thickness (mm)			0.125				
	Resin layer	Composit ion	Constituent monomer of resin	Methyl methacrylate	99			95	95
				Styrene		95			
				Isobornyl methacrylate			95		
				Glycidyl methacrylate	1	5	5	5	5
		Additive	3-glycidoxypopylt rimethoxy silane	5	5	5	5	5	
			Thickness (μm)			1.2	1.2	1.2	1.2
		Weight average molecular weight (Mw)			8.2	8.5	8.3	8.3	8.3
		Releas e Layer	Mold release agent			HD-1100	HD-1100	HD-1100	a
	Thickness (nm)			3	3	3	3	3	
	Standard deviation			0.43	0.43	0.43	0.43	0.43	
	Water contact angle (°)			Before imprintin g	110	110	110	110	110
				After imprintin g	110	106	108	108	108
				Rate of change after imprintin g (%)	0.0	3.6	1.8	1.8	1.8
	Results of imprinting			Macro inspectio n	o	o	o	o	o
SEM (period)				o	o	o	o	o	
AFM (thicknes s)				o	o	o	o	o	

Table 1 (Continued)

					Comparative Example 1	Comparative Example 2	Comparative Example 3	Comparative Example 4
Master mold					I			
Mold	Substrate	Type			PET			
		Thickness (mm)			0.125			
	Resin layer	Composition	Constituent monomer of resin	Methyl methacrylate	95	95	80	99.5
				Styrene				
				Isobornyl methacrylate				
				Glycidyl methacrylate	5	5	20	0.5
		Additive	3-glycid oxypropyltrimethoxysilane	20	0.5	5	5	
			Thickness (μm)			1.2	1.2	1.2
		Weight average molecular weight (Mw)			8.3	8.3	8.8	8.5
		Release layer	Mold release agent			HD-1100	HD-1100	HD-1100
	Thickness (nm)			*1	*2	*2	*2	
	Standard deviation			-	-	-	-	
	Water contact angle (°)		Before imprinting	-	72	78	68	
			After imprinting	-	-	-	-	
			Rate of change after imprinting (%)	-	-	-	-	
	Results of imprinting		Macro inspection	-	-	-	-	
SEM (period)			-	-	-	-		
AFM (thickness)			-	-	-	-		

* 1: Thermal imprinting was not possible, and a resin mold could not be produced.

* 2: Unable to measure since there was shedding of the release agent during the rinse step after thermal imprinting.

mold release agent

a: perfluoro hexanoic acid

b: 1H, 1H,-tridecafluoroheptylamine

[0169]

Table 2. Combinations

					Example 1	Example 8	Example 9	Example 10	Comparative Example 5
Master mold					I				I
Mold	Substrate	Type			PET				PET
		Thickness (mm)			0.125				0.125
	Resin layer	Composition	Constituent monomer of resin	Methyl methacrylate	95	95	95	95	95
				Glycidyl methacrylate	5	5			
				Benzyl methacrylate			5		5
				Dimethyl aminoethyl methacrylate				5	
		Additive	3-glycidoxyp ropyltrimethoxysilane	5				5	
			3-glycidoxyp ropyl methyl dimethoxysilane		5				
			Phenyltrimethoxysilane			5			
			3-aminopropyl trimethoxysilane				5		
		Thickness (μm)			1.2	1.2	1.2	1.2	1.2
		Weight average molecular weight (Mw)			8.3	8.6	8.5	8.8	8.3
	Release layer	Mold release agent			HD-1100	HD-1100	HD-1100	HD-1100	HD-1100
		Thickness (nm)			3	3	3	3	*1
		Standard deviation			0.43	0.43	0.43	0.43	-
	Water contact angle (°)			Before imprinting	110	110	110	110	65
				After imprinting	108	108	108	110	-
				Rate of change after imprinting (%)	1.8	1.8	1.8	0.0	-
Results of imprinting			Macro inspection	○	○	○	○	-	
			SEM (period)	○	○	○	○	-	
			AFM (thickness)	○	○	○	○	-	

Master mold geometry: I, 576 mm² transferring surface, 150 nm L/S (linear geometry), 300 nm period, 150 nm depth.

5 *1: Unable to measure since the release layer could not be formed.

[0170]

Table 3. Shape of the master molds

					Example 1	Example 13	Example 14	Example 15
Master mold			Mold type		I	II	III	IV
			Period (nm)		300	50	150	20000
			Geometry		L/S	L/S	L/S	L/S
Mold	Substrate	Type			PET			
		Thickness (mm)			0.125			
	Resin layer	composition	Constituent monomer of resin	Methyl methacrylate	95			
				Glycidyl methacrylate	5			
			Additive	3-glycidoxypopyltrimethoxysilane	5			
		Weight average molecular weight (Mw)			8.3			
		Thickness (μm)			1.2			
	Release layer	Mold release agent			HD-1100			
		Thickness (nm)			3	3	3	3
		Standard deviation			0.43	0.43	0.43	0.43
	Water contact angle (°)			Before imprinting	110	110	110	110
				After imprinting	108	106	106	106
				Rate of change after imprinting (%)	1.8	3.6	3.6	3.6
Results of imprinting			Macro inspection	○	○	○	○	
			SEM (period)	○	○	○	○	
			AFM (thickness)	○	○	○	○	

Table 3 (Continued)

					Example 16	Example 17	Example 18	
Master mold			Mold type		V	VI	VII	
			Period (nm)		400	300	20000	
			Geometry		column	moth-eye	lens	
Mold	Substrate	Type			PET			
		Thickness (mm)			0.125			
	Resin layer	Composition	Constituent monomer of resin	Methyl methacrylate	95			
				Glycidyl methacrylate	5			
		Additive		3-glycidioxypropyltrimethoxysilane	5			
				Weight average molecular weight (Mw)			8.3	
		Thickness (μm)			1.2		6.4	
		Release layer		Mold release agent			HD-1100	
	Thickness (nm)			3	3	3		
	Standard deviation			0.43	0.43	0.43		
	Water contact angle (°)			Before imprinting	110	110	110	
				After imprinting	106	106	106	
				Rate of change after imprinting (%)	3.6	3.6	3.6	
	Results of imprinting			Macro inspection	○	○	○	
SEM (period)				○	○	○		
AFM (thickness)				○	○	○		

[0171]

Table 4

					Example 1	Example 19	Example 20
Master mold					I		
Mold	Substrate	Type			PET	glass	Si wafer
		Thickness (mm)			0.125	1.1	0.5
	Resin layer	Composition	Constituent monomer of resin	Methyl methacrylate	95		
				Glycidyl methacrylate	5		
			Additive	3-glycidoxyp ropyltrimethoxysilane	5		
		Weight average molecular weight (Mw)			8.3		
		Thickness (μm)			1.2		
	Release layer	Mold release agent			HD-1100		
		Thickness (nm)			3		
		Standard deviation			0.43		
	Water contact angle (°)			Before imprinting	110	110	110
				After imprinting	108	108	108
				Rate of change after imprinting (%)	1.8	1.8	1.8
	Results of imprinting			Macro inspection	○	○	○
SEM (period)				○	○	○	
AFM (thickness)				○	○	○	
					Example 24	Example 25	Example 26
Master mold					I		
Mold	Substrate	Type			PEN	polyimide	PMMA
		Thickness (mm)			0.12	0.3	0.12
	Resin layer	Composition	Constituent monomer of resin	Methyl methacrylate	95		
				Glycidyl methacrylate	5		
			Additive	3-glycidoxyp ropyltrimethoxysilane	5		
		Weight average molecular weight (Mw)			8.3		
		Thickness (μm)			1.2		
	Release layer	Mold release agent			HD-1100		
		Thickness (nm)			3		
		Standard deviation			0.43		
	Water contact angle (°)			Before imprinting	110	110	110
				After imprinting	108	108	108
				Rate of change after imprinting (%)	1.8	1.8	1.8
	Results of imprinting			Macro inspection	○	○	○
SEM (period)				○	○	○	
AFM (thickness)				○	○	○	

Table 4 (Continued)

					Example 21	Example 22	Example 23
Master mold					I		
Mold	Substrate	Type			sapphire	PSF	PC
		Thickness (mm)			0.5	0.12	0.12
	Resin layer	Composition	Constituent monomer of resin	Methyl methacrylate	95		
				Glycidyl methacrylate	5		
			Additive	3-glycidoxypopyltrimethoxysilane	5		
		Weight average molecular weight (Mw)			8.3		
		Thickness (μm)			1.2		
	Release layer	Mold release agent			HD-1100		
		Thickness (nm)			3		
		Standard deviation			0.43		
	Water contact angle (°)			Before imprinting	110	110	108
				After imprinting	108	107	106
				Rate of change after imprinting (%)	1.8	2.7	1.9
	Results of imprinting			Macro inspection	○	○	○
SEM (period)				○	○	○	
AFM (thickness)				○	○	○	
					Example 27	Example 28	Example 29
Master mold					I		
Mold	Substrate	Type			DLC	GC	SiC
		Thickness (mm)			0.12	1	0.43
	Resin layer	Composition	Constituent monomer of resin	Methyl methacrylate	95		
				Glycidyl methacrylate	5		
			Additive	3-glycidoxypopyltrimethoxysilane	5		
		Weight average molecular weight (Mw)			8.3		
		Thickness (μm)			1.2		
	Release layer	Mold release agent			HD-1100		
		Thickness (nm)			3		
		Standard deviation			0.43		
	Water contact angle (°)			Before imprinting	110	110	110
				After imprinting	107	108	108
				Rate of change after imprinting (%)	2.7	1.8	1.8
	Results of imprinting			Macro inspection	○	○	○
SEM (period)				○	○	○	
AFM (thickness)				○	○	○	

[0172]

Table 5. Examples of Use

					Example 1	Reference Example 1	Reference Example 2
Master mold					I		
Mold configuration	Substrate	Type			PET		
		Thickness (mm)			0.125		
	Resin layer	Composition	Constituent monomer of resin	Methyl methacrylate	95		
				Glycidyl methacrylate	5		
			Additive	3-glycidoxyp ropyltrimeth oxysilane	5		
		Weight average molecular weight (Mw)			8.3		
		Thickness (μm)			1.2		
	Release layer	Mold release agent			HD-1100		
		Thickness (nm)			3		
		Standard deviation			0.43		
	Water contact angle (°)			Before imprinting	110	110	110
				After imprinting	108	108	108
				Rate of change after imprinting (%)	1.8	1.8	1.8
	Nano printing method				UV / batch (sheet)	heat batch (sheet) /	UV / continuou s (roll)
	Results of imprinting			Macro inspection	o	o	o
				SEM (period)	o	o	o
				AFM (thickness)	o	o	o

POSSIBILITY OF INDUSTRIAL USE

5 [0173]

The resin mold of the present invention is used for imprinting of a thermoplastic resin, thermosetting resin, or photo-curable resin.

[0174]

10 The various products obtained from the imprinted resin may be used as semiconductor materials, optical elements, prisms, micro lenses, memory media, holography, micro machines,

biotechnology, environmental technology, and electronic materials such as semiconductors, LEDs, hard discs, or the like.

Description of Reference Characters

5 [0175]

1 release layer

2 additive mainly present near the resin layer surface

3 resin layer

3' resin solution layer

10 4 substrate

5 resin

6 substrate

7 roller type resin mold

8 light source

Claims

1. A resin mold comprising:


a substrate,

a resin layer formed upon the substrate and having a

5 depressions and protrusions pattern formed on the surface of the resin layer,

and a release layer containing a mold release agent and being formed with uniform thickness on at least the surface of the depressions and protrusions pattern of said resin layer;

10 wherein said resin layer comprises a solvent soluble resin and an additive; said additive is a compound, or hydrolysate thereof, of General Formula (1):



wherein Y is a methoxy or ethoxy group; X is an organic group
15 including one type selected from the group consisting of an epoxy group, glycidoxy group, and optionally substituted phenyl group or amino group; and n is 0 or 1;

the solvent soluble resin has a constituent unit having a substituent group of the same type as X in said General Formula

20 (1); and

said additive is localized in the vicinity of said resin layer surface, the substituent group Y in said General Formula (1) of the additive, or a hydrolysate of such substituent group Y, bonding chemically with said mold release agent to couple
5 together said resin layer and release layer.

2. The resin mold according to claim 1; wherein the pure water contact angle of said release layer surface is greater than or equal to 100 degrees.

3. The resin mold according to claim 1 or 2; wherein the content of said additive within said resin layer is from 1 to 13 percent by weight.

5 4. The resin mold according to claim 1; wherein, in said solvent soluble resin, the content of the constituent unit having the substituent group of the same type as X in said General Formula (1) is from 1 to 15 percent by weight.

5. The resin mold according to any one of claims 1 to 4;

wherein said mold release agent is at least one type selected from the group consisting of fluorine-based silane coupling agents, mono-terminal aminated perfluoro (perfluoroether) compounds, and
5 mono-terminal carboxylated perfluoro (perfluoroether) compounds.

6. The resin mold according to any one of claims 1 to 5;

wherein said substrate is a resin substrate, glass substrate,
10 silicon substrate, sapphire substrate, carbon substrate, or GaN substrate.

7. The resin mold according to claim 6; wherein said resin substrate is one type of resin selected from the group

consisting of: polyethylene terephthalate, polycarbonates, polymethylmethacrylates, polyimides, polysulfones, polyether sulfones, cyclic polyolefins, and polyethylene naphthalates.

5 8. A method of production of a resin mold comprising steps of:

(I) applying to a substrate a solution dissolving a solvent soluble resin and an additive in a solvent, and forming a resin solution layer on the substrate;

(II) removing the solvent from said resin solution layer
10 and forming a resin layer upon the substrate;


(III) contacting a mold against said resin layer, and transferring a depressions and protrusions pattern formed in the surface of said mold to the surface of said resin layer; and

(IV) coating a mold release agent on the surface of at least
15 the depressions and protrusions pattern of said resin layer, and

forming a release layer of uniform thickness;

wherein the additive is a compound, or hydrolysate thereof, of

General Formula (1):



5 wherein Y is a methoxy or ethoxy group; X is an organic group including one type selected from the group consisting of an epoxy group, glycidoxy group, and optionally substituted phenyl group or amino group; and n is 0 or 1,

10 and the solvent soluble resin has a constituent unit having a substituent group of the same type as X in said General Formula (1).

9. A method of use of a resin mold comprising steps of:
15 contacting the resin surface against the resin mold according to any one of claims 1 to 7;
and peeling said resin mold from said resin.

10. The method of use of a resin mold according to claim 9;
20 wherein said resin is a photo-curable resin.

11. The resin mold according to any one of claims 1 to 7;
wherein the resin mold is fixed to a roller.