

ABSTRACT

ACTIVATED EU-2 ZEOLITE AND USE THEREOF

5 Disclosed herein is an activated EU-2 zeolite, including: pores having a diameter of 30 to 40Å while maintaining the crystal structure of the EU-2 zeolite; and pores having a diameter of 40 to 200Å, wherein the volume of the pores having a diameter of 30 to 40Å is 0.01 to 0.06 cc/g, and the volume of the pores having a diameter of 40 to 200Å is 0.07 to 0.4 cc/g.

10 Figure 1