

**A CLEANING COMPOSITION FOR ELECTROCLEANING COLD-ROLLED
STEEL**

The present invention relates to a cleaning composition for electrocleaning, and particularly to a cleaning composition for electrolytically cleaning cold-rolled steel with high current density.

5 If it is intended that a thinner steel coil be manufactured, the steel work can be subjected to the treatment of cold-rolling. In doing this, a roll coolant must be added for dissipating the heat generated by mechanical rolling on the surface of the steel work.

10 Therefore, subsequent to the cold rolling operation, roll coolant which primarily includes animal oil or mineral oil together with other soils, such as iron smut, will be left on the surface of the cold-rolled steel. Before the cold-rolled steel work is subjected to annealing treatment,

15 such soils should be thoroughly removed from the surface. Otherwise the residual oil smudge will be cracked into carbon residue or a lower carbon compound which is deleterious to the quality of the surface of the resultant steel plate, and this problem manifests itself in a poor

20 finishing job, e.g. poor adherence in electroplating.

Due to its property of saponifying fats and oils to make water-soluble soaps, its capabilities of attacking organics and splitting esters, sodium or potassium hydroxide has been used as the most important alkali for

25 metal cleaning. Particularly, its highest conductivity

renders it an indispensable component in electrolytic cleaning composition.

5 It has been also described that when compounded with surfactants, silicates are the best emulsifying and deflocculating agents of all the alkali. Also their excellent buffer function in high basicity make them necessary for long-life electrocleaning compositions. On the other hand, silicates can be a possible source of trouble in subsequent plating operations and thus are
10 suggested not to be included in the cleaning compositions for some metal cleaning processes. Sodium orthosilicate has been reported as one silicate which is widely used in steel cleaners.

Chelating agents have acquired an important role in
15 conventional cleaning formulations in the case that little or no phosphate should be included. The most widely used chelating agents in metal cleaners are sodium gluconate, trisodium nitrilotriacetate and EDTA. These compounds can soften water and tie up many metal ions so as to enhance the cleaning effect of the cleaners.
20

Evidently, decreasing surface and interfacial tension will help in washing out the oil from the surface. However, specific selection of surfactants is important in electrolytic cleaning. Though nonionic surfactants have
25 been used in combination with anionics in soak and spray cleaners, they have not been positively disclosed or suggested to be used in electrocleaners. Only the anionic type of surfactants has been disclosed for the purpose of

electrocleaning. Finally, it is particularly desired in high-current-density electrocleaning to select a combination of surfactants which have good defoaming properties, because in electrocleaning with high current density, an enormous amount of hydrogen and oxygen evolves giving rise to voluminous foams which adversely cause current loss and affect the efficiency of the electrolysis.

It is known that hexamethylenetetramine can be used as a pickling inhibitor in hydrochloric and sulfuric acid. However, to the knowledge of the inventors, no literature has disclosed hexamethylenetetramine used in a formulation for electrolytic cleaning.

In view of the fact that conditions needed for conducting a electrolytic cleaning of a rolled metal sheet with high current density are very unique, to figure out a suitable cleaning formulation which can perform optimal cleaning function involves an enormous amount of experiments in light of the general teachings as discussed above.

In accordance with the present invention, a cleaning composition for electrolytically cleaning cold-rolled steelwork comprises an alkali metal hydroxide such as sodium or potassium hydroxide, a silicate, and a non-ionic surface-active agent that includes a major amount of lauryl polyethylene glycol ether with an average of 10 ethylene oxide units in the molecule, and a minor amount of nonyl phenyl ethylene glycol ether. By virtue of adding two non-ionic surface-active agents in such amounts, excellent defoaming can be obtained and the need of defoaming agent is greatly decreased. Preferably the silicate is sodium orthosilicate. It is especially preferred that the cleaning composition contain from 20 to 60 percent by weight of sodium hydroxide, from 20 to 60 percent by weight of sodium orthosilicate and from 0.1 to 20 percent by weight of non-ionic surface-active agent. The inclusion of sodium orthosilicate in the cleaning composition can not only increase the usable life of the cleaning solution, but also causes the formation of a thin layer of silicon dioxide which can effectively protect the surface of the cleaned steel sheet from scratching and sticking during the annealing procedure. (Such problems are encountered quite often with the use of conventional electrocleaning compositions.)

In accordance with another aspect of this invention, from 1 to 20 percent by weight of hexamethylenetetramine is added so as to inhibit

the phenomenon of overvoltage, which develops during electrolytic cleaning.

In accordance with a further aspect of this invention, from 1 to 20 percent by weight of a chelating agent can be added. The chelating agent is sodium gluconate, trisodium nitrilotriacetate or a mixture thereof. Owing to the incorporation of the chelating agent, calcium and magnesium, as well as other heavy metal ions, will be sequestered and prevented from contacting sodium orthosilicate and the stearates resulting from saponification. Therefore the formation of insoluble scum, which affects the conductivity of the electrocleaning solution and contaminates the surface of the steel sheet, will be substantially eliminated.

The following exemplary embodiments are provided for illustration of the present invention and should not be construed as limiting the scope of this invention.

150 kg sodium hydroxide, 200 kg sodium orthosilicate, 100 kg sodium gluconate, 100 kg trisodium nitrilotriacetate, 100 kg lauryl polyethylene glycol ether having the formula $C_{12}H_{25}-O-(CH_2CH_2O)_{10}-H$, 10 kg nonyl phenyl ethylene glycol ether, which has the formula $C_9H_{19}-C_6H_4-O-(CH_2CH_2O)-H$, and 10 kg hexamine are mixed to form a basic cleaning composition and pumped into a circulation tank. 21663 kg water is added to the basic cleaning composition to make up 3% by weight of the basic electrocleaning solution. The basic electrocleaning solution is used to wash the conveyed cold-rolled steel at the stage of brush scrubbing and is then sprayed into a high-current-density electrolytic cleaning tank for the electrocleaning process. In the electrocleaning the cold-rolled steel to be washed is made the cathode, while the inert anode is made of steel. Due to the evolution of copious gas at the surface of the cold-rolled steel, the mechanical action of the gas helps to dislodge the soil and simultaneously brings fresh solution up to the surface. No deposition on the steel anode appears even after a period of time; it is believed that this effect is due to the inclusion of hexamine. As a consequence, no light fault caused by overvoltage occurs when utilizing the electrocleaning solution according to this invention as opposed to an electrocleaning solution without hexamine. The advantage of the addition of hexamine in the electrocleaning solution will be

illustrated below. It is to be noted that adding lauryl polyethylene glycol ether having the formula $C_{12}H_{25}-O(CH_2CH_2O)_{10}-H$, and nonyl phenyl ethylene glycol ether, which has the formula $C_9H_{19}-C_6H_4-O-(CH_2CH_2O)-H$ as surface-active agents in such a proportion attains an excellent defoaming effect and has the desirable result of decreasing the consumption of defoaming agents. The effectiveness of the combination of these two surface-active agents will be illustrated below.

The used electrocleaning solution is collected and returned to the recirculation tank. The amount of electrocleaning solution consumed should be supplemented frequently before it is recirculated for the next use.

Subsequently, the cold-rolled steel plate is rinsed twice with hot water in the hot-rinse tank and then dried. The cleanliness of the surface of the resultant steel plate is assessed by the water-break test as very satisfactory.

In practice, it has been found that only 0.367 kg of the basic electrocleaning composition accompanied by 0.018 kg defoaming agent is needed for producing 1 ton of steel plate. At the same time, light fault on the anode develops rather slowly, so the average operation time can last for 172 hours. In view of the slow development of anodic overvoltage, consumption of electricity can be reduced. Furthermore, there is enough silicon dioxide left on the surface to efficiently alleviate the problem of sticking of the surface of the steelwork.

To show the excellent defoaming effect provided by a combination of a minor amount of nonyl phenyl ethylene glycol ether and a major amount of lauryl polyethylene glycol ether with 10 moles of ethylene oxide, two electrocleaning solutions, i.e. CTY410 and CTY412, are prepared for testing the defoaming effect. CTY412 is prepared by repeating the same procedure as for the preparation of the above-mentioned basic electrocleaning solution, except that no hexamine is included and water is added to make up 3% by weight of electrocleaning solution. CTY410 is prepared by repeating the same procedure for the preparation of CTY412 except that nonyl phenyl ethylene glycol ether is not included and water is added to make up 3% by weight of electrocleaning solution. In other words, adding about 0.01% by weight of nonyl phenol ethylene glycol ether to CTY410 will form electrocleaning solution CTY412. The test of the defoaming effect is

conducted for CTY412 and CTY410 according to the ASTM D1173 method. The height of foam in the respective solutions over a period of time is set out in Table I.

5

TABLE I

		CTY410	CTY412	CTY410*	CTY412*
	time (min)	height of foam (cm)	height of foam (cm)	height of foam (cm)	height of foam (cm)
10	0	3.5	1.2	12.0	3.5
	0.5	2.0	1.0	9.0	1.5
	1.0	1.5	0.8	2.0	1.2
15	1.5	1.2	0.7	1.0	1.0
	2.0	1.0	0.7	0.8	0.8
	3.0	0.7	0.3	0.7	0.7
	4.0	0.5	0.1	0.5	0.5
20	5.0	0.5	0.1	0.5	0.3

* To the electrocleaning solutions CTY410 and CTY412 are respectively added 0.5% by volume of rolling oil which comprises about 45% by weight of animal oil, such as tallow oil or lard oil, and 45% by weight of mineral oil as well as a slight amount of emulsifying agents and other additives. The rolling oil is left on the surface of cold-rolled steel after the cold-rolling treatment.

It can be noted from the lower height of the foam in testing CTY412 that inclusion of a slight amount of nonyl phenol ethylene glycol ether greatly enhances the defoaming effect. To demonstrate the excellent capability of hexamine of inhibiting overvoltage on the inert steel electrode, nine sample solutions as listed in Table II are prepared. For

35

simulating used electrocleaning solution which has been used for three days in electrocleaning the cold-rolled sheet as mentioned above, 70 ppm concentration of ferric ion is added to CTY412 to act as a control solution. The test results are tabulated in Table II.

TABLE II

	Sample No.	Added Fe conc. (ppm)	Electrolysis time	Voltage change (volt)	deposition on anode surface
10	control	70	2 min	12→20	Fe ₂ O ₃ +SiO ₂
	1	70	2 hrs	12→12	No
	2	70	2 hrs	12→12	No
	3	70	< 5 min	12→20	Fe ₂ O ₃ +SiO ₂
	4	70	< 5 min	12→20	Fe ₂ O ₃ +SiO ₂
15	5	70	< 5 min	12→20	Fe ₂ O ₃ +SiO ₂
	6	70	< 5 min	12→20	Fe ₂ O ₃ +SiO ₂
	7	70	< 5 min	12→20	Fe ₂ O ₃ +SiO ₂
	8	70	< 5 min	12→20	Fe ₂ O ₃ +SiO ₂
	9	70	< 5 min	12→20	Fe ₂ O ₃ +SiO ₂

NOTE:

1. Sample 1 is prepared by adding 0.1% by weight of hexamine to CTY412.
2. Sample 2 is prepared by adding 0.2% by weight of hexamine to CTY412
3. Sample 3 is prepared by adding 0.2% by weight of triethylamine to CTY412.
4. Sample 4 is prepared by adding 0.2% by weight of diphenylamine to CTY412.
5. Sample 5 is prepared by adding 0.2% by weight of

cyclohexylamine to CTY412.

6. Sample 6 is prepared by adding 0.2% by weight of n-propylamine to CTY412.

5 7. Sample 7 is prepared by adding 0.2% by weight of 2-butyn-1,4-diol to CTY412.

8. Sample 8 is prepared by adding 0.2% by weight of 2-mercaptobenzothiazole.

9. Sample 9 is prepared by adding 0.2% by weight of 1,2,3-benzothiazole.

10 It can be seen that inclusion of hexamethylenetetramine can inhibit to a surprising extent the deposition of ferric oxide and silicone oxide on the surface of the anode, which is believed to cause overvoltage during electrocleaning. Though some other pickling inhibitors,
15 such as 2-butyn-1,4-diol and cyclohexylamine as shown in Table II have been utilized for this purpose, no desirable effect can be obtained, as with hexamethylenetetramine. The mechanism of inhibition of deposition by using hexamethylenetetramine is not very clear to us. It is
20 believed that probably its high molecular weight and electron donor capability to the steel surface accounts for its excellent inhibition of deposition. In addition, hexamethylenetetramine is not easily oxidized.



CLAIMS

1. A cleaning composition for electrolytically cleaning cold-rolled steelwork comprising an alkali metal hydroxide, a silicate, and a non-ionic surface-active agent that includes a major amount of lauryl polyethylene glycol ether with an average of 10 ethylene oxide units in the molecule, and a minor amount of nonyl phenyl ethylene glycol ether.
2. A composition as claimed in Claim 1, containing from 20 to 60 percent by weight of the alkali metal hydroxide, from 20 to 60 percent by weight of the silicate, and from 0.1 percent to 20 percent by weight of the non-ionic surface-active agent.
3. A composition as claimed in Claim 1 or 2, in which the silicate is potassium orthosilicate or sodium orthosilicate and the alkali metal hydroxide is potassium hydroxide or sodium hydroxide.
4. A composition as claimed in any one of Claims 1 to 3, in which the weight ratio of the said lauryl polyethylene glycol ether to nonyl phenyl ethylene glycol is 9-10:1.
5. A composition as claimed in any one of Claims 1 to 4 that further comprises hexamethylenetetramine.
6. A composition as claimed in Claim 5, in which the amount of hexamethylenetetramine is from 1 to 20 percent by weight.
7. A composition as claimed in any one of Claims 1 to 6, further comprising from 1 to 20 percent by weight of a chelating agent.
8. A composition as claimed in Claim 7, in which the chelating agent is sodium gluconate, trisodium nitrilotriacetate or a mixture thereof.
9. A composition as claimed in Claim 1, substantially as hereinbefore described.