

ABSTRACT

The present invention provides a coating film remover composition comprising water, an alcohol having an aromatic group, an ether having an aromatic group, and at least one
5 cellulose derivative;

the coating film remover composition having a pH of 5 to 9, and satisfying all of the following (i) to (viii):

(i) the viscosity η_1 at 5°C and a shear rate of 0.1 s⁻¹ is in the range of 80,000 to 500,000 mPa·s;

10 (ii) the viscosity η_2 at 5°C and a shear rate of 1,000 s⁻¹ is in the range of 200 to 1,000 mPa·s;

(iii) the viscosity η_3 at 25°C and 0.1 s⁻¹ shear rate is in the range of 20,000 to 200,000 mPa·s;

(iv) the viscosity η_4 at 25°C and a shear rate of 1,000 s⁻¹ is in
15 the range of 200 to 1,000 mPa·s;

(v) the rate of change in temperature η_1/η_3 at a shear rate of 0.1 s⁻¹ is in the range of 1.5 to 5.0;

(vi) the rate of change in temperature η_2/η_4 at a shear rate of 1,000 s⁻¹ is in the range of 0.85 to 2.0;

20 (vii) the thixotropic ratio η_3/η_4 at 25°C is in the range of 50 to 1,000; and

(viii) the thixotropic ratio η_1/η_2 at 5°C is in the range of 100 to 1,000.