rates are constant until the operator manually alters the pump speed, and therefore the flow rate. In some cases, changes in flow rate will be made during upset conditions and left at the changed flow rate for an extended (i.e., excessive) period of time.

[0006] Another control method that is commonly utilized in brown stock washing processes is simple “pounds per ton” control, i.e., pounds of wash aid dosed per ton of dry pulp. For “pounds per ton” processes, the brown stock washing process control system calculates a pounds-of-wash-aid-per-ton-of-dry-pulp setpoint and then controls washing aid dosage based on the setpoint. “Pounds per ton” control does not base its wash aid dosage control on changes in either measured entrained air concentration data or changes in fiber characteristics that may impact drainage.

BRIEF SUMMARY

[0007] ~~A~~ According to a first aspect of the present invention, there is provided a method of treating brown stock in a brown stock washing process ~~is provided~~. The method includes measuring a refractive index of a brown stock; and dosing an additive to the brown stock according to at least the refractive index of the brown stock.

[0008] In some examples~~aspects~~, the method includes measuring a conductivity of the brown stock.

[0009] In some examples~~aspects~~, the method includes determining total dissolved solids from the refractive index of the brown stock.

[0010] In some examples~~aspects~~, the method includes determining a total black liquor carryover in the brown stock based on at least two variables: the refractive index of the brown stock and the conductivity of the brown stock.

[0011] In some examples~~aspects~~, the total black liquor carryover comprises an organic fraction and an inorganic fraction.

[0012] In some examples~~aspects~~, the organic fraction is determined using a formula that is a function of the conductivity of the brown stock and total dissolved solids in the brown stock.

[0013] In some examples~~aspects~~, the additive comprises a drainage aid.

[0014] In some examplesaspects, the drainage aid comprises a surfactant, a defoamer, a solvent, or combinations thereof.

[0015] In some examplesaspects, the additive comprises a defoamer.

[0016] In some examplesaspects, the defoamer comprises a hydrocarbon, an oil, a fatty alcohol, a fatty ester, a fatty acid, a poly(alkylene oxide), an organic phosphate, hydrophobic silica, a silicone-containing compound, and combinations thereof.

[0017] In some examplesaspects, the defoamer comprises a silicone-containing compound.

[0018] In some examplesaspects, the silicone-containing compound is a polydimethylsiloxane-containing compound.

[0019] In some examplesaspects, the method includes determining a chlorine dioxide dosage in a bleaching stage of a papermaking process based on the total black liquor carryover.

[0020] In some examplesaspects, the brown stock washing process comprises a plurality of washers arranged in series.

[0021] In some examplesaspects, the method includes measuring the conductivity and the refractive index of the brown stock being fed to a first washer in the plurality of washers and measuring the conductivity and the refractive index of washed pulp leaving a last washer in the plurality of washers.

[0022] A According to a second aspect of the present invention, there is provided a system for controlling dosing of an additive to a brown stock washing process is provided. The system includes a refractive index measurement device; a controller configured to receive data provided by the refractive index measurement device and transform the data into additive addition output instructions; and an additive delivery unit configured to receive and execute the additive addition output instructions from the controller.

[0023] In some examplesaspects, the system further comprises at least one of a vat level detector, a shower flow measurement device, a shower conductivity measurement device, a drum thickener electrical current relay, an entrained air and bubble size detector, and combinations thereof, in communication with the controller.

[0024] In some examplesaspects, the system includes a conductivity measurement device configured to measure conductivity of the brown stock.

[0025] In some examplesaspects, the controller is configured to determine a total black liquor carryover in the brown stock based on at least two variables: a refractive index of the brown stock and a conductivity of the brown stock.

[0026] In some examplesaspects, the additive delivery unit comprises a pump.

[0027] In some examplesaspects, the controller stores a formula that is a function of conductivity of the brown stock and total dissolved solids in the brown stock.

[0027a] According to a third aspect of the present invention, there is provided a use of the system defined in the second aspect for treating brown stock.

[0028] The foregoing has outlined rather broadly the features and technical advantages of the present disclosure in order that the detailed description that follows may be better understood. Additional features and advantages of the disclosure will be described hereinafter that form the subject of the claims of this application. It should be appreciated by those skilled in the art that the conception and the specific embodiments disclosed may be readily utilized as a basis for modifying or designing other embodiments for carrying out the same purposes of the present disclosure. It should also be realized by those skilled in the art that such equivalent embodiments do not depart from the spirit and scope of the disclosure as set forth in the appended claims.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[0029] A detailed description of the invention is hereafter described with specific reference being made to the drawings in which:

[0030] FIG. 1 shows a schematic for an embodiment of a system for treating and washing brown stock;

[0031] FIG. 2 shows conceptual schematic of using the refractive index to determine the total dissolved solids in the wash liquor;

[0032] FIG. 3 shows the predicted organic loading multiple regression model for the online measurements utilizing the total dissolved solids and conductivity measurements;

[0033] FIG. 4 shows a comparison of the predicted organic fraction to the lab result using gravimetric analysis;