

IMMOBILIZED 1,2-BENZISOTHIAZOLIN-3-ONE

5

BACKGROUND OF THE INVENTION

Field of the Invention

The present invention provides novel antimicrobial immobilized 1,2-
10 benzisothiazolin-3-one/zinc oxide complexes useful as preservatives because of
their resistance to being leached from the substrate to which they are attached. This
invention also provides substrates having antimicrobial protection including those
that require high temperatures in their processing such as, but not restricted to,
powder coatings, wood composites and plastics such as polyvinyl chloride (PVC),
15 low-density polyethylene (LDPE), low-density polyethylene foam, plastisols, and
polyurethane.

Description of the Related Art

20 Many materials that come into contact with moisture are prone to destructive
attacks by a variety of microorganisms including fungi, yeast, algae, and bacteria.
Consequently, there is a great need for an effective and economical means to
protect such materials from such destructive attacks for extended periods of time.
Commercial materials which usually require such protection include, for example,
25 plastics, wood, wood products, wood composites, plastic-wood composites, molded
plastics, building materials, paper, toys, coatings, protein-based materials, starch-
based compositions, inks, emulsions, resins, stucco, concrete, stone, wood
adhesives, caulking, sealants, leather, leather finishes, soap wrappers, packaging
materials, spin finishes, fabrics, cordage, carpet backings, electrical insulation,
30 medical devices, and the like.

In addition to protecting commercial materials from such destructive attacks, it
is also desirable to inhibit the growth of microorganisms on the surface of the
commercial materials to maintain hygienic conditions in, for example, hospitals,

nurseries, senior care institutions, food processing facilities, airplanes, trains, buses, and the like.

No single antimicrobial compound provides protection against all microorganisms or is suitable for all applications. In addition to limitations
5 concerning efficacy, other limitations include compound stability, physical properties, toxicological profile, regulatory considerations, economic considerations, and environmental concerns. Antimicrobials that are suitable in many applications may not be suitable in other applications. There is, therefore, a need to develop novel antimicrobial compositions that will provide protection in a variety of applications and
10 under a variety of conditions to protect commercial materials from destructive microorganism attacks and inhibit the growth of microorganisms on the surface of the commercial materials.

A widely used antimicrobial is 1,2-benzisothiazolin-3-one (BIT). BIT and its water-soluble alkali metal salts, are often the biocides of choice when an industrial
15 bactericide is needed to prevent microbial spoilage of water-based technical systems like mineral slurries, polymer emulsions, inks, paints, stucco, adhesives, and the like. (See, for example, W. Paulus "Dictionary of Microbicides for the Protection of Materials" pp. 664-666 (2005), Springer, Dordrecht.)

BIT and its salts are used primarily in liquid systems such as in the coatings
20 industry (paints, varnishes etc.). BIT, and its salts, are used almost exclusively as "in can" preservatives to protect a liquid paint while the paint is in the container before and during application. BIT is not used to protect the coating from microbial growth after it has been applied to the substrate since BIT readily leaches out of the dried coating film.

25 United States patent no. 3,065,123 discloses adding 1,2-benzisothiazolin-3-one to an aqueous media to protect the aqueous media from infection by microorganisms. United States patent no. 4,150,026 discloses metal salt complexes of 3-isothiazolones, which exhibit bactericidal, fungicidal, and algacidal properties. United States patent no. 4,188,376 discloses biocidal compositions suitable for
30 indirect food contact applications and in-can preservation of water-based paints comprising a solution of an alkali metal salt of 1,2-benzisothiazolin-3-one in an alcohol, glycol, or water solvent. United States patent no. 4,871,754 discloses the use of aqueous formulations of the lithium salt of 1,2-benzisothiazolin-3-one to

Antimicrobial compounds that are effective as film preservatives, such as Polyphase[®], a 3-iodo-2-propynyl butyl carbamate composition, remain in the dried coating and can thereby continue to protect the coating from microbial growth. Polyphase[®] is mainly effective against fungi and mildew. Accordingly, there is a
5 need for an antibacterial film preservative having the toxicological profile of BIT that will not lose its efficacy over time due to evaporation or leaching. (See W. Lindner in "Chemisch-physikalisches Verhalten von Konservierungsmittel in Beschichtungsstoffen" (1998) Expert Verlag, Bd 509, W. Lindner in "Directory of Microbicides for the Protection of Materials" (2005), W. Paulus (ed) Springer).

SUMMARY OF THE INVENTION

The present invention provides novel antimicrobial immobilized 1,2-benzisothiazolin-3-one/zinc oxide (BIT/ZnO) complexes useful as antimicrobial
15 agents that are resistant to being leached from the substrate to which they are attached. The present invention is also directed to methods for preparing the BIT/ZnO complexes, to BIT/ZnO complexes prepared by the novel methods, to methods for using the BIT/ZnO complexes to inhibit microbial growth or reduce the level of bacteria on the surface of a substrate, and to substrates protected from
20 microbial attack by being treated with the BIT/ZnO complexes. The present invention is further directed to compositions comprising 1,2-benzisothiazolin-3-one which has been immobilized with zinc oxide.

BRIEF DESCRIPTION OF THE DRAWINGS

25 Figure 1 is a graph showing the infrared spectrum of 1,2-benzisothiazolin-3-one (BIT).

Figure 2 is a graph showing the infrared spectrum of zinc oxide (ZnO).

30 Figure 3 is a graph showing the infrared spectrum of a BIT/ZnO complex.

Figure 4 is a graph showing the infrared spectrum of a BIT/Li salt.

DETAILED DESCRIPTION OF THE INVENTION

Applicants have discovered that the antimicrobial agent 1,2-benzisothiazolin-3-one (BIT) can be immobilized by admixing the antimicrobial agent with an immobilizing effective amount of zinc oxide (ZnO). While not wishing to be bound by theory, applicants believe that the antimicrobial agent and the immobilizing agent are subject to an attractive interaction, which assists in immobilizing the antimicrobial agent from the normally deleterious leaching effects from the substrates to which they are applied. BIT and zinc oxide may form an acid base complex and additional zinc oxide may deposit itself around the BIT/ZnO complex since higher ratios of ZnO to BIT results in a higher tendency of the BIT/ZnO complex to be immobilized. This immobilization retards or prevents leaching of the antimicrobial agent and results in greater retention of the antimicrobial protection in the final substrate than is the case when the immobilizing agent is not present. The combination of the antimicrobial agent and the immobilizing agent works in an unexpected manner to improve the immobilization of the antimicrobial agent on a substrate.

As set out in Figures 1-4, the structure of the immobilized BIT/ZnO complex has been analyzed by infrared spectra. Figure 1 is a graph showing the infrared spectrum of BIT with a strong carbonyl band at 1645 cm^{-1} . Figure 2 is a graph showing the infrared spectrum of ZnO. Figure 3 is a graph showing the infrared spectrum of a BIT/ZnO complex. Figure 4 is a graph showing the infrared spectrum of a BIT/Li salt. The infrared spectrum in Figure 3 clearly shows that the BIT/ZnO complex is not a physical mixture of BIT and ZnO because the carbonyl band of BIT at 1645 cm^{-1} (Figure 1) is missing. The immobilized BIT/ZnO complex is not an alkali salt, which is apparent by comparison with the infrared spectrum of a BIT/Li salt (Figure 4). The infrared spectra of the immobilized BIT/ZnO complex and the BIT/Li salt would be expected to be very similar since the same organic anion is involved. But the infrared spectra of the immobilized BIT/ZnO complex and the BIT/Li salt are different especially in the "fingerprint"-region of 700 cm^{-1} to 1400 cm^{-1} , which represents the combined resonances of the BIT molecule. In the BIT/Li salt, the bands of the BIT/ZnO complex at 910 , 899 , and 797 cm^{-1} are missing, while in the BIT/ZnO complex the bands of the BIT/Li salt at 1055 cm^{-1} and 880 cm^{-1} are missing. The infrared spectrum of ZnO (Figure 2) is void in the infrared range, the bands present are from humidity (approx 3300 cm^{-1}) or organic impurities at the high

concentration. The combination of the infrared spectra in Figures 1-4 together with the HPLC-analysis on methanol-extractable BIT and total BIT after hydrolysis (Examples 2-7) suggest that BIT must be complexed on the ZnO.

BIT may be immobilized on ZnO surfaces by precipitating water-soluble salts of BIT, especially alkali metal salts, onto ZnO. Non-limiting examples of water-soluble zinc salts of BIT include those formed with zinc chloride, zinc bromide, zinc acetate, zinc formate, and zinc nitrate. The procedure to prepare the immobilized BIT/ZnO complexes can vary widely. A water-soluble salt of BIT can be precipitated onto the surface of a preformed zinc oxide by neutralization of the solution. For example, an aqueous solution of BIT-potassium salt can be admixed with ZnO and ZnCl₂ and the BIT then precipitated onto ZnO by neutralizing the mixture. Alternatively, BIT and ZnO can be admixed directly to form the BIT/ZnO complex. Further zinc oxide can be precipitated on the preformed BIT/ZnO complexes. By choosing the precipitation conditions, the properties of the antimicrobial compound can be varied. The BIT/ZnO complexes may be prepared as solid materials or as dispersion concentrates using conventional dispersion technologies. The weight-to-weight ratio of BIT to ZnO in the complex may be adjusted to suit the particular application of the final product. The particle size of the BIT/ZnO complex and the viscosity of the BIT/ZnO complex in the dispersion concentrate may also be adjusted to suit the particular application of the final product. Higher weight to weight ratios of ZnO to BIT result in a higher tendency of the BIT/ZnO complex to be immobilized. The particle size of the BIT/ZnO complex can be adjusted by milling and can range from the nano scale (approximately 10nm) to several hundred microns. In general, the immobilized BIT/ZnO complex is precipitated in a particle size, which is sufficiently small to be used directly in a coating material. The viscosity of the BIT/ZnO complex dispersion concentrate may be adjusted by the addition of a viscosity-adjusting agent. Preferred reaction media are water, lower alcohols such as methanol, ethanol, isopropanol, n-propanol, n-butanol, *sec*-butanol, *tert*-butanol, and mixtures thereof. The immobilized BIT/ZnO complex can be isolated by the usual techniques such as filtration or spray drying. The immobilized BIT/ZnO complex can be combined with additional antimicrobial agents and fungicidal film preservatives such as carbendazim (methylbenzimidazol-2-ylcarbamate), 3-iodo-2-propynyl butyl carbamate, zinc pyrethrin, triclosan (5-chloro-2-(2,4-dichlorophenoxy)phenol), 2-n-octylisothiazolin-3-one, 4,5-dichloro-2-n-

octylisothiazolin-3-one, chlorthalonil (2,4,5,6,tetrachloroisophthalonitril), bethoxazin (3-benzo[*b*]thien-2-yl-5,6-dihydro-1,4,2-oxathiazine 4-oxide), ziram (zinc bis(dimethyldithiocarbamate), thiram (tetramethylthiuram disulfide), 2-n-butyl-benzisothiazolin-3-one, and silver and silver compounds such as coated silver on
5 zinc oxide AirQual AQ200, commercially available from AirQual, zinc silver zeolithe compounds, commercially available from Ciba, silver chloride on titanium dioxide commercially available from Clariant, and silver (nano-scale silver), commercially available from NANUX.

The antimicrobial immobilized BIT/ZnO complexes of the present invention
10 provide a complex wherein BIT is resistant to evaporation or leaching, or any other process, that would cause the BIT to be depleted from the surface of a substrate. The antimicrobial immobilized BIT/ZnO complexes also provide antibacterial hygienic coatings for surfaces such as in hospitals, senior homes, kindergartens, food producing units, and pharmaceutical facilities. Bacteria coming into contact with
15 such coatings are controlled by the presence of the immobilized antibacterial agent. Such permanent antimicrobial properties can supplement cleansing and disinfections procedures at difficult to reach surfaces. The antimicrobial immobilized complexes can also control biofilm formation on the surface of sealants such as in water supply systems. The antimicrobial immobilized complexes further provide an antimicrobial
20 compound suitable for use in hygienic surfaces that will not be burdened with undesirable properties characteristic of other antibacterial substances used for such purposes. Additional materials which may be coated with the antimicrobial immobilized BIT/ZnO complexes include coatings, plastics, wood products, wood composites, plastic-wood composites, molded plastics, building materials, paper,
25 starch-based compositions, adhesives, stucco, concrete, caulking, sealants, fabrics, and cordage.

In accordance with the present invention, a method is provided for making an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex comprising the steps of
30 (a) heating 1,2-benzisothiazolin-3-one and zinc chloride to reflux in a C₁-C₄ branched or unbranched alcohol to form a solution; (b) cooling the solution and adding an immobilizing effective amount of zinc oxide to the solution to form a mixture; (c) heating the mixture to reflux and then cooling the mixture to room temperature; (d) filtering the mixture to obtain the immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex. The method may further comprise washing the solid material with a C₁-C₄

branched or unbranched alcohol and drying the solid material under vacuum. The C₁-C₄ branched or unbranched alcohols may be selected from the group consisting of methanol, ethanol, n-propanol, *iso*-propanol, n-butanol, *sec*-butanol, and *tert*-butanol. Preferably, the C₁-C₄ branched or unbranched alcohols are selected from the group consisting of methanol, ethanol, n-propanol, and *iso*-propanol, more preferably, the alcohols are methanol or ethanol, and most preferably methanol.

In another embodiment, the present invention provides a method for making a dispersion concentrate of an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex comprising the steps of (a) forming an aqueous solution of 1,2-benzisothiazolin-3-one and potassium hydroxide having a pH from about 7 to about 8.5; (b) adding zinc chloride and an immobilizing effective amount of zinc oxide to the solution to form a mixture; and (c) milling the mixture to form the dispersion concentrate of immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex. The method may further comprise adding a dispersing agent to the mixture in step (b) and a defoaming agent to the mixture in step (c).

In yet another embodiment, the present invention provides a method for making a dispersion concentrate of an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex comprising the steps of (a) forming an aqueous mixture of 1,2-benzisothiazolin-3-one, zinc chloride, and an immobilizing effective amount of zinc oxide; (b) adjusting the pH of the mixture from about 7 to about 8.5; and (c) milling the mixture to form the dispersion concentrate of immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex. The method may further comprise adding a dispersing agent to the mixture in step (a) and a defoaming agent to the mixture in step (c).

In still yet another embodiment, the present invention provides a method for making a dispersion concentrate of an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex comprising the steps of (a) forming an aqueous mixture of 1,2-benzisothiazolin-3-one and an immobilizing effective amount of zinc oxide; and (b) milling the mixture to form the dispersion concentrate of immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex. The method may further comprise adding a dispersing agent to the mixture in step (a) and a defoaming agent to the mixture in step (b).

The present invention also provides an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex prepared by the methods set out above. The present invention further provides a method for protecting a substrate from antimicrobial

infestation which comprises treating the substrate with an antimicrobially effective amount of an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex prepared by the methods set out above. The present invention still further provides a composition comprising 1,2-benzisothiazolin-3-one, which has been immobilized with zinc oxide.

The antimicrobial agent used in the immobilized BIT/ZnO complexes of the present invention is commercially available 1,2-benzisothiazolin-3-one (1,2-benzisothiazolin-3(2*H*)-one, BIT), and the salts thereof. BIT has a molecular weight of 151.19, is soluble in hot water and forms water-soluble salts with alkali metals and amines, and is highly soluble in organic solvents especially alcohols and glycols. BIT, and its water-soluble alkali metal salts, are useful to prevent microbial spoilage of water-based technical systems like mineral slurries, polymer emulsions, inks, paints, stucco, adhesives, and the like. BIT is disclosed in United States patent no. 3,065,123, which disclosure is incorporated herein by reference.

The immobilizing agent used in the immobilized BIT/ZnO complexes of the present invention is commercially available zinc oxide (ZnO). Zinc oxide has a molecular weight of 81.38, exists as a white or yellowish-white, odorless powder, and is practically insoluble in water. Nanostructures of zinc oxide may also be employed. Nanostructures of zinc oxide are disclosed in detail in *Materialstoday*, June (2004), pp. 26-33, which disclosure is incorporated herein by reference.

In accordance with the present invention, an immobilizing effective amount of ZnO is admixed with BIT to form an immobilized BIT/ZnO complex. An immobilizing effective amount of ZnO is an amount effective to immobilize the antimicrobial agent BIT in the immobilized BIT/ZnO complex. An excess of immobilizing agent has been found to more efficiently immobilize the antimicrobial agent. The appropriate amount of immobilizing agent may depend upon a number of factors including the nature of the substrate to be protected and the conditions and duration of time under which the substrate is used. The appropriate amount of immobilizing agent for a particular purpose can be determined by routine testing of the immobilization of the antimicrobial agent with varying amounts of added immobilizing agent. Methods for assaying the immobility of the antimicrobial agent, such as by HPLC, are known and available to one skilled in the art, and are set out in the example section of this disclosure. Thus, depending on such factors, the weight-to-weight ratio of BIT:ZnO can be very broad. In general, the weight-to-weight ratio of BIT:ZnO will be from

about 1:20 to about 3:1. Preferably, the weight to weight ratio of BIT:ZnO will be from about 1:10 to about 3:1, more preferably from about 1:5 to about 1:1, and most preferably from about 1:3 to about 2:3.

For purposes of this invention, "immobilized BIT" and "free BIT" are defined in operational terms based on the fact that BIT *per se* is soluble in methanol at greater than 5%, i.e., 5 grams of pure BIT will be completely soluble in 100 ml of methanol. When a solid BIT/ZnO complex made in accordance with this invention is shaken at ambient (room) temperature with twenty (20) times its weight of methanol, any BIT that goes into solution, i.e. is not remain attached to the ZnO, is defined as "free" or "not immobilized" BIT while the BIT that remains attached to the ZnO as part of the solid, undissolved BIT/ZnO complex is defined as "immobilized BIT." Accordingly, the difference between the total amount of BIT in the BIT/ZnO complex and the amount of "free" BIT (that is, the amount of BIT soluble in a predetermined amount of methanol) is the amount of "immobilized BIT" in the BIT/ZnO complex.

The HPLC analytical methods described in the examples section of this disclosure provide a convenient way to analyze a BIT/ZnO complex to determine what amount of BIT therein is "free" and what amount of BIT therein is "immobilized". (For example, if a 500mg sample of a BIT/ZnO complex that was about 33% by weight of BIT shaken with 100 ml of methanol, such a sample would contain have less than 170 mg. of BIT, and if it were all free BIT it would all dissolve in the methanol forming a less than 0.2% solution. Since the solubility of BIT in methanol at ambient temperature is greater than 5%, such an analysis clearly illustrates any immobilization of the BIT in that any BIT that does not dissolve in the methanol is clearly immobilized in the BIT/ZnO complex.

In general, it is desirable to maximize the amount of BIT that is "immobilized BIT" in the BIT/ZnO complex and to minimize the amount of "free BIT" for the purposes of this invention, it being understood that for special circumstances it may be preferable to have mixtures as opposed to maximizing the "immobilized BIT" in the complex. A ZnO /BIT complex wherein from about 40% to about 100% of th BIT is immobilized would be suitable for many applications with about 50% to about 100% being preferable, with about 70% to about 100% being more preferable and with from about 90% to about 100% being most preferable.

In general, the immobilized BIT/ZnO complex is prepared by precipitation in a dispersion concentrate in a particle size, which is sufficiently small to be used directly in a coating material. The desired particle size of the BIT/ZnO complex may depend upon a number of factors including the nature of the substrate to be protected and the conditions and duration of time under which the substrate is used. The particle size of the BIT/ZnO complex can be adjusted by milling, such as in a pearl mill, and can range from the nano scale (approximately 10nm) to several hundred microns. The particle size of the BIT/ZnO complex may range from 0.8µm 50% / 10µm 95%. Preferably, the particle size of the BIT/ZnO complex may range from 1µm 50% / 8µm 95%, more preferably from 1.5µm 50% / 6µm 95%, and most preferably from 2.5µm 50% / 4µm 95%,

The viscosity of the BIT/ZnO complex dispersion concentrate may be adjusted to be used directly in a coating material. The viscosity of the BIT/ZnO complex may depend upon a number of factors including the nature of the coating and the substrate to be protected. The viscosity of the BIT/ZnO complex dispersion concentrate may be adjusted to suit the particular application of the final product. The viscosity of the BIT/ZnO complex dispersion concentrate may be adjusted by the addition of a viscosity-adjusting agent. A preferred viscosity-adjusting agent is xanthan gum (Kelzan®). The viscosity of the BIT/ZnO complex dispersion concentrate may range from about 400 to about 1200mPas, preferably from about 400 to about 1100mPas, more preferably from about 400 to about 1000mPas, and most preferably from about 400 to about 900mPas.

In accordance with the invention, the antimicrobial immobilized BIT/ZnO complex can be included in a final formulation for use in such end use applications as paints, coatings, plastics, wood products, wood composites, plastic-wood composites, molded plastics, building materials, paper, starch-based compositions, adhesives, stucco, concrete, caulking, sealants, fabrics, cordage, textiles, and the like, in a broad range from about 0.004% to 2.0% active concentration. Such compositions can be prepared from highly concentrated compositions of the immobilized complex by appropriate dilution. The optimum useful range is about 0.01 % to 1.0% of immobilized complex in the final formulations for such end use systems. With the use of such modified formulations in end use systems, it is possible to protect substrates for extended periods of time against growth from microorganisms.

Compositions of the present invention will generally be formulated by mixing or dispersing the immobilized complex in a selected proportion with a liquid vehicle for dissolving or suspending the active components. The vehicle may contain a diluent, an emulsifier and a wetting agent. Expected uses of the antimicrobial
5 immobilized complex include the protection of aqueous based paints and coatings, adhesives, joint cements, sealants, caulks, printing inks, metal working fluids, polymer emulsions, pigment dispersions, aqueous industrial products, lubricants, caulking, and the like. The antimicrobial immobilized complex may be provided as liquid mixtures, as wettable powders, dispersions, or in any other suitable product
10 type, which is desirable. In this regard, the composition of the present invention can be provided as a ready-for-use product in the form of aqueous dispersions, oil dispersions, or as a concentrate.

Useful solvents that can be used in the preparation of products comprising the antimicrobial immobilized complex are several glycol ethers and esters like
15 propylene glycol n-butyl ether, propylene glycol tert-butyl ether, 2-(2-methoxymethylethoxy)-tripropylene glycol methyl ether, propylene glycol methyl ether, dipropyleneglycol methyl ether, tripropylenelene glycol methyl ether, propylene glycol n-butyl ether and the esters of the previously mentioned compounds. Other useful solvents are n-methyl pyrrolidone, n-pentyl propionate and dibasic esters of
20 several dicarboxylic acids, and mixtures thereof. The preferred solvents for these products are propylene glycol n-butyl ether, 1-methoxy-2-propanol, and the dibasic isobutyl ester blend of succinic, glutaric and adipic acids.

When preparing formulations of the present invention for specific applications, the composition also will likely be provided with adjuvants conventionally employed
25 in compositions intended for such applications such as organic binding agents, additional antimicrobials, auxiliary solvents, processing additives, fixatives, plasticizers, UV-stabilizers or stability enhancers, water-soluble or water-insoluble dyes, color pigments, siccatives, corrosion inhibitors, antisetlement agents, anti-skinning agents and the like.

30 The immobilization of BIT on ZnO may be further controlled by adding to the complex basic salts of carboxylic acids, e.g. fatty acids. Preferred fatty acids are benzoic acid, octanoic acid, 2-ethylhexanoic acid, nonanoic acid, decanoic acid, undecanoic acid, decanoic acid, stearic acid, oleic acid, and mixtures thereof.

According to the present invention, substrates are protected from contamination by microorganisms simply by treating the substrate with a composition containing the antimicrobial immobilized BIT/ZnO complex of the present invention. Such treating may involve mixing the composition with the substrate, coating or
5 otherwise contacting the substrate with the composition and the like.

The following examples are presented to illustrate and explain the invention. Unless otherwise indicated, all references to parts and percentages here and throughout the application are based on weight.

10 EXAMPLES

Analytical Procedure For Determining the Amount of Immobilized BIT in a BIT/ZnO Complex

15 This analysis determines the total amount of BIT and the amount of "free" BIT in a BIT/ZnO complex. The difference between the total amount of BIT in the BIT/ZnO complex and the amount of "free" BIT (that is, the amount of BIT soluble in a predetermined amount of methanol) is defined as the amount of "immobilized BIT" in the BIT/ZnO complex.

20 1. Analysis of the Total Amount of BIT in a BIT/ZnO Complex.

To analyze the total amount of BIT in a BIT/ZnO complex, the BIT/ZnO complex must be hydrolyzed to liberate the BIT so that it can be analyzed by standard HPLC techniques.

25 Hydrolysis.

Approximately 200 mg of the immobilized BIT/ZnO complex is weighed exactly (exact weight may vary depending upon the expected total amount of BIT in the complex being analyzed) into a 100ml flask. A quantity of 20ml of methanol (HPLC-grade) and 5ml of hydrochloric acid (1 mol/l) is then added. The flask is
30 heated to about 50°C for 15 minutes. After being cooled to ambient temperature, the flask is filled with methanol up to the mark of 100 ml. The reaction mixture is then filtered over a 0.25µ membrane filter (e.g., Millipore) and is ready to be injected into an HPLC-column.

HPLC Conditions

Instrument	Apparatus Shimadzu A6
Column:	Nucleosil 100-5 C18 HD (Macherey-Nagel)
5 Solvent Gradient Flow:	.1.3ml/min
UV Detector wave length:	312nm
Eluent A:	water + 5% acetonitrile (vol:vol)
Eluent B:	acetonitrile

Flow time (min.)	Solvent Gradient*
0.1	10% Eluent B + 90% Eluent A
3.0	10% Eluent B + 90% Eluent A
8.0	70% Eluent B + 30% Eluent A
10.0	70% Eluent B + 30% Eluent A
11.0	90% Eluent B + 10% Eluent A
12.0	90% Eluent B + 10% Eluent A
13.0	10% Eluent B + 90% Eluent A
15.0	10% Eluent B + 90% Eluent A
17.0	stop

10 * = vol:vol

The total amount of BIT in the BIT/ZnO complex is then determined by comparison to an external standard (150mg BIT/1 liter methanol).

15 **2. Analysis of "free" BIT.**

BIT is very soluble in methanol and can be extracted from the BIT/ZnO complex to determine the amount of "free" BIT.

Approximately 500mg of the BIT/ZnO complex is weighed exactly (exact weight can vary depending upon the expected "free" BIT content of the complex being analyzed) into a 100ml flask. A quantity of 50ml of methanol (HPLC-grade) is added. The flask containing the mixture is then ultrasonicated in a water bath for about 15 minutes. After being cooled to ambient temperature, the flask is filled with

20

methanol up to the mark of 100ml. The reaction mixture is then filtered over a 0.25 μ membrane filter (e.g., Millipore) and is ready to be injected into an HPLC-column.

The HPLC-conditions for analysis of the "free" BIT is the same as set out above in part 1. The amount of "free" BIT in the BIT/ZnO complex is then

5 determined by comparison to an external standard (150mg BIT/1 liter methanol).

Example 1

Comparative Example

bis-(1,2-Benzisothiazolin-3-one)zinc(II)chloride

10

Bis-(1,2-benzisothiazolin-3-one)zinc(II)chloride was prepared according to example 53 of United States patent no. 4,150,026.

1.5g of 1,2-benzisothiazolin-3-one (analytical pure grade) was dissolved in 75ml of absolute methanol. A quantity of 0.68g zinc chloride was added to provide a
15 clear solution. The solvent was then evaporated under vacuum and the residue was dried. A quantity of 2.1g of bis-(1,2-benzisothiazolin-3-one)zinc(II)chloride was obtained. The molar ratio of BIT:Zn = 2:1.

The 1,2-benzisothiazolin-3-one was not immobilized as a bis-(1,2-benzisothiazolin-3-one)zinc(II)chloride salt complex because the complex is almost
20 completely soluble in methanol. HPLC analysis showed that 63% of the salt complex was 1,2-benzisothiazolin-3-one obtained from the methanol extract.

Example 2

Dispersion Concentrate of BIT/ZnO from BIT-Potassium salt

25

A quantity of 300g of tap water was admixed with 26.7g of potassium hydroxide prills and 74.1g of commercially available 1,2-benzisothiazolin-3-one (90%) (available from Aldrich) until a clear solution resulted. A quantity of 270g of tap water, 40g of Emulsogen TS 200 (a dispersing agent available from Clariant),
30 40g of Atlox® 4913 (a non-ionic dispersant available from Unigema), 155.7g of zinc oxide (available from Aldrich), and 30.1g of zinc chloride (available from Aldrich) were then added and the batch was milled in a pearl mill. The foam was controlled by adding 0.5g of Rhodorsil 416 (a silicon based defoamer available from Rhodia). The pH was 7. The mixture was passed 3 times through a pearl mill to reduce the

particle size. The product was adjusted to a viscosity of 420 mPas (Spindle 4, Brookfield) by addition and dispersion of 4g xanthan gum (Kelzan®) and 59g of tap water. The ZnO:BIT weight/weight ratio = 2.6:1 and the molar ratio BIT:Zn = 0.20.

A quantity of 1000g of (1,2-benzisothiazolin-3-one)zinc oxide was obtained.
5 Particle size distribution: 1.3 micrometer 50% / 5.5 micrometer 95%. Analysis: 6.7% total 1,2-benzisothiazolin-3-one by HPLC after acidic hydrolysis (decomposition in 10% hydrochloric acid, neutralize, dilute with methanol, HPLC analysis of BIT). Analysis of soluble BIT from methanol extract: 2.4%. (64% of the total BIT is fixed on the ZnO surface)

10

Example 3

Dispersion Concentrate of BIT/ZnO from BIT-ZnCl₂

A quantity of 90g of tap water was mixed with 22.2g of commercially available
15 1,2-benzisothiazolin-3-one (90%), 12g of Emulsogen TS 200, 12g of Atlox® 4913, 46.7g of zinc oxide, and 9.0g of zinc chloride. The batch was neutralized to pH 8.5 by slow addition with stirring of 16g of a 50% (w/w) potassium hydroxide solution. The batch was passed 3 times through a pearl mill to reduce the particle size. Foam was controlled by adding 0.5g of Rhodorsil 416. The product was then adjusted to a
20 viscosity of 720 mPas (Spindle 3, Brookfield, 100 rpm) by addition and dispersion of 1.6g of xanthan gum and 121g of tap water. The ZnO:BIT weight/weight ratio = 2.6:1 and the molar ratio BIT:Zn = 0.20.

A quantity of 400g of a dispersion concentrate of (1,2-benzisothiazolin-3-one)zinc oxide was obtained. Particle size distribution: 0.8 micrometer 50% / 3.5
25 micrometer 95%. Analysis: 6.7% total 1,2-benzisothiazolin-3-one by HPLC after acidic hydrolysis (decompose in 10% hydrochloric acid, neutralize, dilute with Methanol, HPLC analysis of BIT). Analysis of soluble BIT from methanol extract: 1.1%. (84% of the total BIT is fixed on the ZnO surface)

30

Example 4

Dispersion Concentrate of BIT/ZnO from BIT-ZnCl₂

A quantity of 90g of tap water was mixed with 22.2g of commercially available 1,2-benzisothiazolin-3-one (90%), 12g of Emulsogen TS 200, 12g of Atlox® 4913,

20.6g of zinc oxide, and 9.0g of zinc chloride. The batch was neutralized to pH 8.5 by admixing 16g of a 50% (w/w) potassium hydroxide solution. The batch was passed 3 times through a pearl mill to reduce the particle size. Foam was controlled by adding 0.2g of Rhodorsil 416. The product was then adjusted to a viscosity of 950 mPas (Spindle 3, Brookfield, 100 rpm) by addition and dispersion of 1.8g xanthan gum and 147g of tap water. The ZnO:BIT weight/weight ratio = 1.6:1 and the molar ratio BIT:Zn = 0.35)

A quantity of 400g of a dispersion concentrate of (1,2-benzisothiazolin-3-one)zinc oxide was obtained. Particle size distribution: 1.3 micrometer 50% / 6.0 micrometer 95%. Analysis: 6.7% total 1,2-benzisothiazolin-3-one by HPLC after acidic hydrolysis (decompose in 10% hydrochloric acid, neutralize, dilute with methanol, HPLC analysis of BIT). Analysis of soluble BIT from methanol extract: 1.6%. (76% of the total BIT is fixed on the ZnO surface).

Example 5

Dispersion Concentrate of BIT/ZnO By Direct Precipitation in a Pearl Mill

A quantity of 166.2g of tap water was mixed with 33.3g of commercially available 1,2-benzisothiazolin-3-one (90%), 3g of Emulsogen TS 200, 6g of Atlox® 4913, and 70.1g of zinc oxide. The batch was milled in a pearl mill for 30 minutes. Foam was controlled by adding 0.3g of Rhodorsil 416. The product was then adjusted to a viscosity of 1180 mPas (Spindle 3, Brookfield, 100 rpm) by addition of 0.6g xanthan gum and 21g of tap water. The ZnO:BIT weight/weight ratio = 2.3:1 and the molar ratio BIT:Zn = 0.24.

A quantity of 300g of a dispersion concentrate of (1,2-benzisothiazolin-3-one)zinc oxide was obtained. Particle size distribution: 2.4 micrometer 50% / 10 micrometer 95%. Analysis: 9.9% total 1,2-benzisothiazolin-3-one by HPLC after acidic hydrolysis (decompose in 10% hydrochloric acid, neutralize, dilute with methanol, HPLC analysis of BIT). Analysis of soluble BIT from methanol extract: 2.8%. (72% of the total BIT is fixed on the ZnO surface)

Example 6

Dispersion Concentrate of BIT/ZnO By Direct Precipitation in a Pearl Mill

The product from Example 5 was milled for 4 hours. A quantity of 300g of a
5 dispersion concentrate of (1,2-benzisothiazolin-3-one)zinc oxide was obtained.

Particle size distribution: 1.0 micrometer 50% / 4.5 micrometer 95%.
Analysis: 9.8% total 1,2-benzisothiazolin-3-one by HPLC after acidic hydrolysis
(decompose in 10% hydrochloric acid, neutralize, dilute with methanol, HPLC
analysis of BIT). Analysis of soluble BIT from methanol extract: 0.8%. (92% of the
10 total BIT is fixed on the ZnO surface)

Example 7

Dispersion Concentrate of BIT/ZnO By Direct Precipitation in a Pearl Mill

15 A quantity of 140g of tap water was mixed with 6.7g of commercially available
1,2-benzisothiazolin-3-one (90%), 3g of Emulsogen TS 200, 6g of Atlox 4913, and
134g of zinc oxide. The batch was milled in a pearl mill for 4 hours. Foam was
controlled by adding 0.1g of Rhodorsil 416. The product was then adjusted to a
viscosity of 1180 mPas (Spindle 3, Brookfield, 100 rpm) by addition of 0.6g xanthan
20 gum and 10g of tap water. The ZnO:BIT weight/weight ratio = 20:1 and the molar
ratio BIT:Zn = 0.028.

A quantity of 300g of a dispersion concentrate of (1,2-benzisothiazolin-3-
one)zinc oxide was obtained. Particle size distribution: 1.5 micrometer 50% / 7.7
micrometer 95%. Analysis: 2.0% total 1,2-benzisothiazolin-3-one by HPLC after
25 acidic hydrolysis (decompose in 10% hydrochloric acid, neutralize, dilute with
methanol, HPLC analysis of BIT). Analysis of soluble BIT from methanol extract:
0.1%. (95% of the total BIT is fixed on the ZnO surface)

Example 8

30 Solid Immobilized BIT/ZnO

A quantity of 30g (198 mmol) 1,2-benzisothiazolin-3-one and 15g (110 mmol)
of zinc chloride was heated to reflux in 250ml of methanol. The resulting clear
solution was cooled to approximately 50°C and 70g (860 mmol) of zinc oxide was

added. The mixture was then heated to reflux for 1 hour with stirring and then cooled to room temperature. The solid material was filtered off and washed with 250ml portions of methanol until no chloride could be detected in the filtrate by testing with silver nitrate in sulfuric acid. The BIT/ZnO complex was dried under vacuum to constant weight to yield 90g of a white powder. The ZnO:BIT weight/weight ratio = 2.57:1 and the molar ratio BIT:ZnO = 0.20.

The BIT/ZnO product was analyzed by heating 300mg at 60°C for 10 minutes with 50ml of a 5% solution of sodium hydroxide in methanol. Sufficient methanol was added to bring the solution to 100ml and the resulting solution was filtered through a 0.45 micron filter and injected into a RP-18 HPLC column (eluent was an acetonitrile/water mixture.) The amount of BIT was determined using an external standard and a UV detector operating at 310nm. A theoretical yield of 96% based upon BIT was achieved of a BIT/ZnO complex that was tested free of chloride. (96% of the total BIT is fixed on the ZnO surface)

Example 9

Dispersion Concentrate of Immobilized BIT/ZnO from BIT-Potassium salt

A quantity of 45g of potassium hydroxide prills, 125g of 1,2-benzisothiazolin-3-one (80% BIT, Mergal® BIT technical, commercially available from Troy GmbH), and 20g of Emulsogen TS 200 were mixed in 440g of tap water until a clear solution was obtained. 234g of zinc oxide was admixed and 12.5g of Emulsogen TS 200 was added. The foam was controlled by adding 0.5g of Rhodorsil 416. 45g of zinc chloride was then added and the temperature was raised to 40°C. The pH was adjusted to 8 by addition of 30g hydrochloric acid (16%). The mixture was passed 3 times through a pearl mill to reduce the particle size. The product was adjusted to a viscosity of 440 mPas (Spindle 4, Brookfield) by addition of 2g xanthan gum. The ZnO:BIT weight/weight ratio = 2.6:1 and the molar ratio BIT:ZnO = 0.20.

A quantity of 1000g of (1,2-benzisothiazolin-3-one)zinc oxide was obtained. Particle size distribution: 19 micrometer 50%/79 micrometer 95%. Analysis: 10.0% 1,2-benzisothiazolin-3-one by HPLC after alkaline hydrolysis.

Example 10
Infrared Spectrum of BIT

5 The BIT sample employed for the infrared spectrum analysis in Figure 1 was Mergal analytical standard (99.56%) from Troy Corporation. The sample was prepared according to standard procedures as a pressed (10-20%) KBr(99%)-pill using a Perkin-Elmer, System 2000 FT-IR Instrument.

10 **Example 11**
Infrared Spectrum of ZnO

The ZnO sample employed for the infrared spectrum analysis in Figure 2 was analytical grade (99+%). The procedure for conducting the infrared spectrum analysis is the same as set out in Example 10.

15 **Example 12**
Infrared Spectrum of BIT/ZnO complex

20 The BIT/ZnO sample employed for the infrared spectrum analysis in Figure 3 was the complex prepared in example 8. The procedure for conducting the infrared spectrum analysis is the same as set out in Example 10.

Example 13
Infrared Spectrum of BIT/Li Salt

25 The BIT/Li salt sample employed for the infrared spectrum analysis in Figure 4 was an analytical grade (99%) standard from Mergal. A quantity of 202g (1mol) of BIT (Proxel Press Paste, Arch) as a 75% wet cake (remainder water) and 45g (1.07mol) of lithium hydroxide-hydrate was heated to reflux for one hour in 700ml of methanol. The mixture was then cooled to ambient temperature to precipitate the BIT-lithium salt, which was isolated by filtration and dried to constant weight. The procedure for conducting the infrared spectrum analysis is the same as set out in Example 10.

Example 14

Activity of the Immobilized BIT/ZnO Complex in a Water-Based Flat Paint Against *Pseudomonas aeruginosa* Using a Modified Swiss Standard SNV195120 Test

5

The activity of the immobilized BIT/ZnO complex from Example 8 as a dry-film bactericide against *Pseudomonas aeruginosa* DSM 939 was determined in an ICI UK, Diamond Matt paint, a commercially available water-based interior flat paint (40% acrylic binder) according to the modified Swiss Standard SNV195120, which is
10 described below

Preparation of test specimen:

The immobilized BIT/ZnO complex from example 8 was incorporated into the
15 water-based interior flat paint at the levels shown in the Table below. The paints were allowed to equilibrate for one week at room temperature.

A quantity of 50mg of the BIT/ZnO complex was mixed with 100g of the paint (resulting in 0.05% of the specimen 1 in the table below, the other specimens were prepared accordingly). Round filter papers (5.5 cm diameter) were coated with the
20 test material to a thickness of 150g/m² wet and the resulting specimens dried at room temperature.

One half of the test specimen was leached by tap water (9 liters per m²) in a beaker. The specimens were dried at room temperature and sterilized by gamma radiation from a cobalt 60 source (25 kGy). In the microbiological test,
25 *Pseudomonas aeruginosa* DSM 939 was used as the bacteria source.

Liquid cultures of each bacterial strain were incubated over night at appropriate temperatures and then diluted 1:100,000 to result in a count of 10⁴ cfu per ml. 0.1ml of these diluted cultures were streaked onto bacterial nutrient in Petri dishes. The test specimens were placed coated side downwards on the inoculated
30 nutrient and incubated for 1 day at 29°C.

The growth of the bacteria on the agar under the test specimen was rated as follows:

- 0H No bacterial growth under the specimen, inhibition zone on the nutrient.
 5 0 No growth of bacteria under the specimen.
 G Growth of bacteria under the specimen.

Bacterial growth under the specimen was seen under the unprotected blank material. Bactericidal protection is provided if there is no growth of bacteria under
 10 the specimen.

Sample No	Sample indication	Antimicrobial Active Conc. %	Film weight (g/m ²)	Psa un-leached	Psa leached 24h	Remarks
1	Interior flat paint** + 0.05% of immobilized BIT / ex. 8	BIT * 0.016%	182	0	G	
2	Interior flat paint** + 0.1% of immobilized BIT / ex. 8	BIT* 0.032%	212	0	0	
3	Interior flat paint** + Thiram	Thiram 0.1%	223	0	G	Comparative Example
4	Interior flat paint** + Thiram	Thiram 0.2%	195	0	G	Comparative Example
5	Interior flat paint + Ziram	Ziram 0.1%	209	0	G	Comparative Example
6	Interior flat paint** + Ziram	Ziram 0.2%	186	0H	G	Comparative Example
7	Interior flat paint** – blank	none	255	G	G	Growth control

*BIT = 1,2-benzisothiazolin-3-one total concentration

**Interior flat paint = ICI UK, Diamond Matt

15 Thiram = tetramethylthiuram disulfide

Ziram = (T-4)-bis(dimethyldithio-carbamate-S,S')zinc)

This test demonstrated the efficacy of the immobilized BIT/ZnO complex from Example 8 in very low concentration against *Pseudomonas aeruginosa* in a water-based interior flat paint (40% acrylic binder) using the modified Swiss Standard SNV195120 Test. The effect was still present after an artificial aging process (24
 20 hours leached, submersed in water), demonstrating the durability of the antimicrobial substrate with immobilized 1,2-benzisothiazolin-3-one, while conventionally protected paint samples failed after leaching.

Example 15

**Activity of the Immobilized BIT/ZnO Complex in a Water-Based Eggshell Paint
Against *Pseudomonas aeruginosa* Using a
Modified Swiss Standard SNV195120 Test**

The activity of the immobilized BIT/ZnO complex from Example 8 as a dry-film bactericide against *Pseudomonas aeruginosa* DSM 939 was determined in a commercially available water-based interior eggshell paint (40% acrylic binder with an adhesion promoter) according to the modified Swiss Standard SNV195120. The composition of the paint, which is typically applied in wet rooms, is set out below.

Component	Amount
Water	16g
Hydroxymethylcellulose	0.2g
Calgon N	0.1g
Titanium dioxide (Rutil)	15g
Magnesium aluminum silicate	3g
China clay B	5g
Calcium carbonate Calcit	12.5g
Iron oxide	3g
Mowilith DM 772 (Polyacrylate dispersion Celanese (formerly Clariant)	40g
Texanol	4g
Mergal K14 (in-can preservative)	0.2g
pH was adjusted to 8.5 with Ammonium Hydroxide (25%)	

The microbiological test was performed according to the procedure described in Example 14.

Sample No	Sample indication	Antimicrobial Active Conc. %	Film weight (g/m ²)	Psa unleached	Psa leached 24h	Remarks
1	Interior Paint Eggshell + 0.05% of immobilized BIT / ex 8	BIT * 0.016%	229	G	0	Water-soluble growth supporting paint ingredients are washed out.
2	Interior Paint Eggshell + 0.1% of immobilized BIT / ex 8	BIT* 0.032%	231	0	0H	
3	Interior Paint Eggshell + Thiram	Thiram 0.1%	221	G	G	Comparative Example
4	Interior Paint Eggshell + Thiram	Thiram 0.2%	222	G	G	Comparative Example
5	Interior Paint Eggshell-blank		221	G	G	Growth control

*BIT = 1,2-benzisothiazolin-3-one total concentration

Thiram = tetramethylthiuram disulfide

5 This test demonstrated the efficacy of the immobilized BIT/ZnO complex from Example 8 in very low concentration against *Pseudomonas aeruginosa* in a water-based interior eggshell paint (40% acrylic binder with an adhesion promoter) using the modified Swiss Standard SNV195120 Test.

10

Example 16

Activity of the Immobilized BIT/ZnO Complex in a Water-Based Flat Paint Against *Escherichia coli* Using a JIS Z2801:2000 (E) Test

15 The activity of the immobilized BIT/ZnO complex from Example 9 as a dry-film bactericide against *Escherichia coli* was determined in ICI UK, Diamond Matt paint, a commercially available water-based interior flat paint (40% acrylic binder) according to the JIS Z2801:2000 (E) test (Japanese Industrial Standard Z2801:2000 (E) test, Antimicrobial products - Test for antimicrobial activity and efficacy).

20 The complex was coated on to Leneta Scrub Resistance test panels, with a dry film thickness of 200 micrometers, with a foam roller allowing a drying time of 18 hours between coats. The panels were equilibrated in the dark for 7 days. Subsamples were cut (each 50 mm x 50 mm). The samples were inoculated with a

suspension of the test bacteria and then incubated in chambers (1 per species) at 20°C and 65% relative humidity.

Swabs were employed for recovery of the bacteria. From the blank sample 1.8×10^5 cfu/cm² were recovered. This number was taken as the starting bacterial load on the surface.

Sample No	Sample indication	Antimicrobial Active Conc. %	Contact time hrs	Log (Cfu/cm ²)	Kill rate % related to blank paint	Remarks
1a	Interior Paint - blank	blank	0	5.26		Recovered inoculum
1b	Interior Paint - blank	blank	8	5.20	0%	control
2	Interior Paint + 0.15% of immobilized BIT /ex. 9	BIT * 0.05%	8	2.57	99.8%	
3	Interior Paint + 0.05% of ZPT	ZPT 0.05%	8	3.76	96.4%	Comparative Example
4	Interior Paint 2.5% of IPBC-dispersion	IPBC 1.0%	8	5.04	31.3%	Comparative Example

ZPT = Zinc Pyrithione

IPBC = dispersion: 40% 3-Iodopropoxy-buylacarbamate suspension concentrate

*BIT = 1,2-benzisothiazolin-3-one total concentration

This test demonstrated the efficacy of the immobilized BIT/ZnO complex from Example 9 in very low concentration against *Escherichia coli* in a water-based interior flat paint (40% acrylic binder) using the JIS Z2801:2000 (E) Test. The data show that *Escherichia coli* did survive for 8 hours on the water-based interior flat paint (40% acrylic binder) not treated with the immobilized BIT/ZnO complex. The immobilized BIT/ZnO complex reduced the bacteria level by 99.8% while the commercially available comparative materials were significantly inferior.

Example 17

Activity of the Immobilized BIT/ZnO Complex in a Water-Based Flat Paint Against *Pseudomonas aeruginosa* Using a JIS Z2801:2000 (E) Test

Sample No	Sample indication	Antimicrobial Active Conc. %	Contact time hrs	Log (Cfu/cm ²)	Kill rate % related to blank paint	Remarks
1a	Interior Paint - blank	blank	0	5.11	-	Recovered inoculum
1b	Interior Paint - blank	blank	8	4.69	0%	control
2	Interior Paint + 0.15% of immobilized BIT / ex 8	BIT * 0.05%	8	3.56	92.70%	
3	Interior Paint + 0.05% of ZPT	ZPT 0.05%	8	4.18	69.40%	Comparative Example
4	Interior Paint 2.5% of IPBC-dispersion *	IPBC 1.00%	8	4.53	30.60%	Comparative Example

The activity of the immobilized BIT/ZnO complex from Example 8 as a dry-film bactericide against *Pseudomonas aeruginosa* DSM 939 was determined in ICI UK, Diamond Matt paint, a commercially available water-based interior flat paint (40% acrylic binder) according to the JIS Z2801:2000 (E) test. The microbiological test was performed according to the procedure described in Example 16.

ZPT = Zinc Pyrithione

IPBC = dispersion: 40% 3-Iodopropoxy-buylacarbamate suspension concentrate

*BIT = 1,2-benzisothiazolin-3-one total concentration

This test demonstrated the efficacy of the immobilized BIT/ZnO complex from Example 8 in very low concentration against *Pseudomonas aeruginosa* in a water-based interior flat paint (40% acrylic binder) using the JIS Z2801:2000 (E) test.

Example 18

Activity of the Immobilized BIT/ZnO Complex in a Water-Based Flat Paint Against *Pseudomonas aeruginosa* Using a JIS Z2801 Test

Sample No	Sample indication	Antimicrobial Active Conc. %	Contact time hrs	Log (Cfu/cm ²)	Kill rate % related to blank paint	Remarks
1a	Interior wall paint - blank	Blank	0	4.18	-	Recovered inoculum
1b	Interior wall paint - blank	Blank	8	4.69	0%	control
2	Interior wall paint + 0.15% of immobilized BIT / ex 8	BIT * 0.05%	8	1.08	99.98%	
3	Interior wall paint + 0.05% of ZPT	ZPT 0.05%	8	4.66	39.5%	Comparative Example
4	Interior wall paint 0.25% of IPBC-dispersion *	IPBC 0.1%	8	4.34	71.1%	Comparative Example

The activity of the immobilized BIT/ZnO complex from Example 8 as a dry-film bactericide against *Pseudomonas aeruginosa* DSM 939 was determined in the paint described in example 15 according to the JIS Z2801 test. The microbiological test was performed according to the procedure described in Example 16.

ZPT = Zinc Pyrithione

IPBC = dispersion: 40% 3-Iodopropoxy-buylacarbamate suspension concentrate

*BIT = 1,2-benzisothiazolin-3-one total concentration

This test demonstrated the efficacy of the immobilized BIT/ZnO complex from Example 8 in very low concentration against *Pseudomonas aeruginosa* in an interior acrylic wall paint using the JIS Z2801.

Example 19

Activity of the Immobilized BIT/ZnO Complex in a Water-Based Flat Paint Against *Pseudomonas aeruginosa* Using a JIS Z2801 Test Simulating Severe Environmental Conditions

The activity of the immobilized BIT/ZnO complex from Example 8 as a dry-film bactericide after aging against *Pseudomonas aeruginosa* DSM 939 was determined in the paint described in example 15 according to the JIS Z2801 test. The

microbiological test was performed according to the procedure described in Example 16. After equilibration, the specimens were leached in water (24 hours) to simulate use conditions in a severe environment. The paint film was cleaned by water jet.

Sample No	Sample indication	Antimicrobial Active Conc. %	Contact time hrs	Log (Cfu/cm ²)	Kill rate % related to blank paint	Remarks
1a	Interior wall paint - blank	blank	0	4.18		Recovered inoculum
1b	Interior wall paint - blank	blank	24	3.88	0%	control
2	Interior wall paint + 0.15% of immobilized BIT /ex. 8	BIT * 0.05%	24	2.52	95.7%	
3	Interior wall paint + 0.05% of (ZPT)	ZPT 0.05%	24	3.04	85.5%	Comparative Example
4	Interior wall paint 0.25% of IPBC-dispersion *	IPBC 0.1%	24	3.76	25.0%	Comparative Example

ZPT = Zinc Pyrithione

IPBC = dispersion: 40% 3-Iodopropoxy-buylacarbamate suspension concentrate

*BIT = 1,2-benzisothiazolin-3-one total concentration

This test demonstrated the efficacy of the immobilized BIT/ZnO complex from Example 8 in very low concentration against *Pseudomonas aeruginosa* in an interior acrylic wall paint using the JIS Z2801 test simulating severe environmental conditions.

Example 20

Activity of the Immobilized BIT/ZnO Complex in a Water-Based Flat Paint Against *Escherichia coli* Using a JIS Z2801 Test Simulating Severe Environmental Conditions

The activity of the immobilized BIT/ZnO complex from Example 8 as a dry-film bactericide after artificial aging against *Escherichia coli* was determined in ICI UK, Diamond Matt paint, a commercially available water-based interior flat paint (40% acrylic binder) according to the JIS Z2801 test. The paint specimens were prepared

as described in example 19. The microbiological test was performed according to the procedure described in Example 16. After equilibration, the specimens were leached in water (24 hours) to simulate use conditions in a severe environment. The paint film was cleaned by water jet.

5

Sample No	Sample indication	Antimicrobial Active Conc. %	Contact time hrs	Log (Cfu/cm ²)	Kill rate % related to blank paint	Remarks
1a	Interior wall paint - blank	blank	0	3.04		Recovered inoculum
1b	Interior wall paint - blank	blank	24	3.30	0%	control
2	Interior wall paint + 0.15% of immobilized BIT / ex 8	BIT * 0.05%	24	2.73	73%	
3	Interior wall paint + 0.05% of ZPT	ZPT 0.05%	24	3.04	20%	Comparative Example
4	Interior wall paint 0.25% of IPBC-dispersion *	IPBC 0.1%	24	3.76	35%	Comparative Example

ZPT = Zinc Pyrithione

IPBC = dispersion: 40% 3-Iodopropoxy-buylacarbamate suspension concentrate

10 *BIT = 1,2-benzisothiazolin-3-one total concentration

This test demonstrated the efficacy of the immobilized BIT/ZnO complex from Example 8 in very low concentration against *Escherichia coli* in a water-based interior flat paint (40% acrylic binder) using the JIS Z2801 test simulating severe environmental conditions.

15

Example 21

20

Leaching of Immobilized BIT/ZnO Complex in a Water-Based VOC Paint

A water-based low-volatile organic compound (VOC) paint was prepared according to the following formula:

Ingredient:	% weight	comment
Water	21.75	
Walocel XM 30,000 PV	0.20	MHEC modified
Calgon N neu	0.20	Polyphosphate
Sodium hydroxide 25%	0.10	pH-regulator
Borchigel 76	0.25%	
Borchigen NA40	0.50%	
Kronos 2160	10.00%	Rutil pigment
Finntalc M 30 SL	5.00%	Extender
China Clay	4.00%	Extender
Omyacarb 10 GU	19.60%	Extender
Omyacarb 5 GU	10.00%	Extender
Mill base 30 min at 2000 cycles/min		
Mowilith LDM 1871	23.00%	Binder-Vinyl-Ethylene-copolymer
Water	5.40%	

Preparation of test specimen:

The immobilized BIT complex from example 9 (10% BIT) was incorporated as
 5 the last component in the paint at the levels indicated in the Table below. As a
 comparative compound, a commercially available solution of BIT-Lithium (Mergal®
 K10N) was incorporated into the paint (samples 2 and 4) in the same manner. The
 test paints were allowed to equilibrate for one week at room temperature. Round
 filter paper (5.5 cm diameter) was coated with the test paints and the resulting
 10 specimens dried at room temperature. The test specimens were leached by tap
 water (9 liters per m²) in a beaker. After the times indicated in the Table below, test
 specimens were taken and dried at room temperature. The total BIT concentration
 in the test paint films was analyzed by HPLC after an alkaline hydrolysis and
 extraction of the leached paint films.

Specimen No	Antimicrobial added to the paint	Antimicrobial active substance BIT wt-%/wt wet paint	8h Leach-% BIT*	24h Leach-% BIT*	Comment
1	0.3% of immobilized BIT ex. 9	0.03%	42	17	
2	0.3% of a water solution of 10% BIT lithium salt	0.03%	2	1	Comparative Example
3	0.5% of immobilized BIT ex. 9	0.05%	49	24	
4	0.5% of a water solution of 10% BIT lithium salt	0.05%	1	1	Comparative Example

The results are expressed as % of the amount found from the original ("unleached") paint sample. This eliminates the error from the variances in extraction method and recovery rates.

This example demonstrates the immobilization of the BIT/ZnO complex in a water-based VOC paint film.

Example 22

Leaching of the Immobilized BIT/ZnO Complex in an Alkyd-Acrylic Binder Paint

The test paint was commercially available Larco Type 147 (Denmark), a water reducible top coat for wooden surfaces based on an alkyd-acrylic hybrid binder. The immobilized BIT complex from example 9 was incorporated into the paint and the paint film test specimens were prepared as described in example 21. After equilibration, the paint specimens were leached as described in example 21. The leaching water was exchanged after 24 hours.

Specimen No	Antimicrobial	Antimicrobial active substance BIT wt-%/wt wet paint	24h Leach-% BIT*	48h Leach-% BIT*	Comment
1	0.3% of immobilized BIT ex. 9	0.03%	50	27	
2	0.3% as water solution of 10% BIT lithium salt	0.03%	7	0	Comparative Example
3	0.5% of immobilized BIT ex. 9	0.05%	47	36	
4	0.5% as water solution of 10% BIT lithium salt	0.05%	10	2	Comparative Example

This example demonstrates the immobilization of the BIT/ZnO complex in a commercially available water-reducible topcoat paint for wooden surfaces based on an alkyd-acrylic hybrid binder.

While the invention has been illustrated by reference to specific and preferred
5 embodiments, those skilled in the art will understand that variations and modifications may be made through routine experimentation and practice of the invention. Thus, the invention is intended not to be limited by the foregoing description, but to be defined by the appended claims and their equivalents.

CLAIMS

We claim:

- 5 1. A method for making an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex comprising the steps of:
- (a) heating 1,2-benzisothiazolin-3-one and zinc chloride to reflux in a C₁-C₄ branched or unbranched alcohol to form a solution;
- (b) cooling the solution from step (a) and adding an immobilizing effective
10 amount of zinc oxide to the solution to form a mixture;
- (c) heating the mixture from step (b) to reflux and then cooling the mixture to room temperature;
- (d) filtering the mixture from step (c) to obtain a solid material which is the immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.
- 15 2. The method of claim 1, further comprising washing the solid material from step (d) with a C₁-C₄ branched or unbranched alcohol and drying the solid material under vacuum.
- 20 3. The method of claim 1, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.
4. A method for making a dispersion concentrate of an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex comprising the steps of:
- 25 (a) forming an aqueous solution of 1,2-benzisothiazolin-3-one and potassium hydroxide having a pH from about 7 to about 8.5;
- (b) adding zinc chloride and an immobilizing effective amount of zinc oxide to the solution in step (a) to form a mixture; and
- (c) milling the mixture from step (b) to form the dispersion concentrate of
30 immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.
5. The method of claim 4, further comprising adding a dispersing agent to the mixture in step (b) and a defoaming agent to the mixture in step (c).

6. The method of claim 4, wherein the milling in step (c) provides an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex having a particle size distribution from about 0.8 μ m 50% / 10 μ m 95% and the viscosity of the mixture is adjusted from about 400 to about 1200mPas by admixing a viscosity adjusting agent.

5

7. The method of claim 4, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

8. A method for making a dispersion concentrate of an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex comprising the steps of:

10

(a) forming an aqueous mixture of 1,2-benzisothiazolin-3-one, zinc chloride, and an immobilizing effective amount of zinc oxide;

(b) adjusting the pH of the mixture in step (a) to from about 7 to about 8.5; and

(c) milling the mixture from step (b) to form the dispersion concentrate of immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.

15

9. The method of claim 8, further comprising adding a dispersing agent to the mixture in step (a) and a defoaming agent to the mixture in step (c).

20

10. The method of claim 8, wherein the milling in step (c) provides an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex having a particle size distribution from about 0.8 μ m 50% / 10 μ m 95% and the viscosity of the mixture is adjusted from about 400 to about 1200mPas by admixing a viscosity adjusting agent.

25

11. The method of claim 8, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

12. A method for making a dispersion concentrate of an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex comprising the steps of:

30

(a) forming an aqueous mixture of 1,2-benzisothiazolin-3-one and an immobilizing effective amount of zinc oxide; and

(b) milling the mixture from step (a) to form the dispersion concentrate of immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.

13. The method of claim 12, further comprising adding a dispersing agent to the mixture in step (a) and a defoaming agent to the mixture in step (b).

14. The method of claim 12 wherein the milling in step (b) provides an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex having a particle size distribution from about 0.8 μ m 50% / 10 μ m 95% and the viscosity of the mixture is adjusted from about 400 to about 1200mPas by admixing a viscosity adjusting agent.

15. The method of claim 12 wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

16. An immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex prepared by a method comprising the steps of:

(a) heating 1,2-benzisothiazolin-3-one and zinc chloride to reflux in a C₁-C₄ branched or unbranched alcohol to form a solution;

(b) cooling the solution from step (a) and adding an immobilizing effective amount of zinc oxide to the solution to form a mixture;

(c) heating the mixture from step (b) to reflux and then cooling the mixture to room temperature;

(d) filtering the mixture from step (c) to obtain a solid material which is the immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.

17. The method of claim 16, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

18. An immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex prepared by a method comprising the steps of:

(a) forming an aqueous solution of 1,2-benzisothiazolin-3-one and potassium hydroxide having a pH from about 7 to about 8.5;

(b) adding zinc chloride and an immobilizing effective amount of zinc oxide to the solution in step (a) to form a mixture; and

(c) milling the mixture from step (b) to form the dispersion concentrate of immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.

19. The method of claim 18, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

20. An immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex prepared
5 by a method comprising the steps of:

- (a) forming an aqueous mixture of 1,2-benzisothiazolin-3-one, zinc chloride, and an immobilizing effective amount of zinc oxide;
- (b) adjusting the pH of the mixture in step (a) to from about 7 to about 8.5; and
- (c) milling the mixture from step (b) to form the dispersion concentrate of
10 immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.

21. The method of claim 20, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

22. An immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex prepared
15 by a method comprising the steps of:

- (a) forming an aqueous mixture of 1,2-benzisothiazolin-3-one and an immobilizing effective amount of zinc oxide; and
- (b) milling the mixture from step (a) to form the dispersion concentrate of
20 immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.

23. The method of claim 22, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

24. A method for protecting a substrate from antimicrobial infestation which
25 comprises treating the substrate with an antimicrobially effective amount of an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex prepared by a method comprising the steps of:

- (a) heating 1,2-benzisothiazolin-3-one and zinc chloride to reflux in a C₁-C₄
30 branched or unbranched alcohol to form a solution;
- (b) cooling the solution from step (a) and adding an immobilizing effective amount of zinc oxide to the solution to form a mixture;
- (c) heating the mixture from step (b) to reflux and then cooling the mixture to room temperature;

(d) filtering the mixture from step (c) to obtain a solid material which is the immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.

25. The method of claim 24, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

26. A method for protecting a substrate from antimicrobial infestation which comprises treating the substrate with an antimicrobially effective amount of an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex prepared by a method comprising the steps of:

- (a) forming an aqueous solution of 1,2-benzisothiazolin-3-one and potassium hydroxide having a pH from about 7 to about 8.5;
- (b) adding zinc chloride and an immobilizing effective amount of zinc oxide to the solution in step (a) to form a mixture; and
- (c) milling the mixture from step (b) to form the dispersion concentrate of immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.

27. The method of claim 26, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

28. A method for protecting a substrate from antimicrobial infestation which comprises treating the substrate with an antimicrobially effective amount of an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex prepared by a method comprising the steps of:

- (a) forming an aqueous mixture of 1,2-benzisothiazolin-3-one, zinc chloride, and an immobilizing effective amount of zinc oxide;
- (b) adjusting the pH of the mixture in step (a) to from about 7 to about 8.5; and
- (c) milling the mixture from step (b) to form the dispersion concentrate of immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.

29. The method of claim 28, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

30. A method for protecting a substrate from antimicrobial infestation which comprises treating the substrate with an antimicrobially effective amount of an immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex prepared by a method comprising the steps of:

- 5 (a) forming an aqueous mixture of 1,2-benzisothiazolin-3-one and an immobilizing effective amount of zinc oxide; and
- (b) milling the mixture from step (a) to form the dispersion concentrate of immobilized 1,2-benzisothiazolin-3-one/zinc oxide complex.

10 31. The method of claim 30, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

32. An antibacterial composition that is suitable for providing antibacterial activity on the surface of a solid comprising 1,2-benzisothiazolin-3-one which has
15 been immobilized as part of a 1,2-benzisothiazolin-3-one/zinc oxide complex.

33. The composition of claim 32, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:20 to about 3:1.

20 34. The composition of claim 33, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:5 to about 1:1.

35. The composition of claim 34, wherein the weight to weight ratio of 1,2-benzisothiazolin-3-one:zinc oxide is from about 1:3 to about 2:3.

25