

THERMOPLASTIC RESIN COMPOSITION AND USE THEREOF

ABSTRACT

An object of the present invention is to obtain a
5 thermoplastic resin composition that is suitable for
obtaining a molded article that does not produce increased
hydrophilic properties, and that has a hard feel and a
texture closer to that of earthenware.

The thermoplastic resin composition of the present
10 invention is characterized in that it contains 10 to 50 parts
by mass of a thermoplastic resin (A), 50 to 90 parts by mass
of a metal oxide (B) [provided that the total amount of
(A)+(B) is 100 parts by mass], and an unmodified polyolefin-
based wax (C) in a range of 0.1 to 20 parts by mass per 100
15 parts by mass of the total amount of (A)+(B).

[No Available Figure]