PATENT SPECIFICATION

629,630

Convention Date (Canada): March 21, 1946.

Application Date (In United Kingdom): March 4, 1947. No. 6110/47.

Complete Specification Accepted: Sept. 23, 1949.

Index at acceptance:—Class 1(iii), D1, G50.

COMPLETE SPECIFICATION

Improvements in or relating to Separation of Alumina Values from Phosphorus-Contaminated Bauxite Material

We, ALUMINIUM LABORATORIES LIMITED, a corporation organised under the laws of the Dominion of Canada of 1800, Sun Life Building, Montreal 2, Canada, do hereby declare the nature of this invention and in what manner the same is to be performed, to be particularly described and ascertained in and by the following statement:—

This invention relates to the production of alumina from bauxite containing phosphorus.

The process most commonly resorted to for the production of alumina from bauxite is commonly known as the "Bayer" process, in which a more concentrated sodium aluminate solution is obtained by subjecting the bauxite to digestion with a less concentrated solution containing sodium hydroxide. In the ordinary operation of the process sodium carbonate is included in the liquor and calcium oxide or calcium hydroxide is added to the digester charge in order that losses of sodium hydroxide consumed in the course of the process of digestion may be replaced by reaction between them. With a good grade of bauxite, calcium hydroxide is consumed in a proportion of about 3 parts to 100 parts by weight of the bauxite treated, and 56 grams of calcium oxide may of course, if desired, be substituted for 74 grams of calcium hydroxide in the usual way.

It has been found that if the bauxite contains phosphorus this is dissolved therefrom during the process of digestion and that when the digest liquor is used repeatedly in the normal cyclic way for the digestion of fresh bauxite containing phosphorus, the concentration of phosphorus pentoxide in the sodium aluminate sometimes increases to an undesirable extent. For this no convenient remedy has heretofore been found.

It has been known for some time in the art that the concentration of phosphorus in the liquor can be controlled by the addition of considerable quantities of calcium oxide or of calcium hydroxide to the digester charge. However, when the phosphorus pentoxide content of the bauxite becomes sufficiently large, the quantity of calcium hydroxide necessary to control the concentration of phosphorus pentoxide in the liquor becomes so large that the solubility of alumina is adversely affected with consequent avoidable losses, and the quantity of sodium hydroxide present, which it is important to control, becomes excessive.

It has now been discovered that the undue concentration of phosphorus pentoxide can be overcome in part by extending the time of digestion and in part by adding calcium carbonate to the digester charge so as to insure the presence therein of at least a given molar ratio between the calcium carbonate and the phosphorus pentoxide. Although calcium carbonate appears to be essentially insoluble in the solution, it has been found that its incorporation, and consequent presence at the time of digestion, have the effect, in some way not yet fully understood, of depressing the solubility of phosphorus. At the same time even large amounts of the calcium carbonate do not seem to modify or disturb the proportions of sodium hydroxide and sodium carbonate in the liquor; the added material does not produce a causticization of sodium carbonate, and hence the optimum concentrations of total caustic and total alkali can be readily maintained in the solution. Tests have also revealed, as indicated above, that the time of digestion may be peculiarly significant in practical operation, for example in that useful economy of calcium carbonate can be achieved by extending the digestion time beyond the period which would ordinarily be deemed sufficient for a given set of conditions.

A further feature of the invention is

that the calcium hydroxide added for causticization represents another factor in determining the quantity of calcium carbonate necessary for optimum results in relation to a given phosphorus content of the bauxite. More specifically, the use of calcium hydroxide in the liquor has been found to permit a very considerable economy in the consumption of calcium carbonate for purposes of the invention. The precise extent of such economy depends on the amount of calcium hydroxide so used, which must vary as dictated by the composition of the solution when it returns from the precipitation stage. As explained above, however, calcium hydroxide by itself is either inadequate or undesirable for the control of substantial phosphorus concentrations; and to take advantage of the present discovery in avoiding the inadequacy or inefficiency of prior proposals, a significant quantity of calcium carbonate must be added.

With reference to commercial requirements of the usual sort, experience indicates that a certain phosphorus content in the produced alumina may be tolerated, and although special circumstances may require lower or permit higher values, it is at present considered that a concentration of 2 grams P_2O_5 per liter represents a significant maximum for the liquor, and thus indirectly represents a corresponding maximum tolerable phosphorus content in the precipitated alumina. In other words, if the phosphorus content of the solution exceeds a value of about 2 grams P_2O_5 per liter, the resulting alumina will also contain too much phosphorus for the standard adopted above. In carrying out the present procedure, a convenient measure of the minimum amount of calcium carbonate necessary to obtain the desired standard is the molar ratio between that material (i.e. calcium carbonate added as such) and the phosphorus in the bauxite, expressed as phosphorus pentoxide, e.g. the ratio $CaCO_3 : P_2O_5$ for the given amount of bauxite that is to be treated in, say, any one digestion period.

It will now be seen that under the selected circumstances, optimum conditions can be readily determined. The molar ratio required depends upon the time of digestion and upon the quantity of calcium hydroxide which is added to the digester charge for formation of fresh sodium hydroxide in the liquor. By way of illustration of the manner in which the ratio depends on such factors, there are set forth hereinbelow some particular conditions and ratios that may be taken to represent specific examples of the process, —it being understood that when carrying out the present method in actual production; the fundamental aspects of the Bayer process (e.g. caustic and alkali concentrations, temperatures, method of alumina precipitation, and manner of recycling) may be such as constitute known and accepted practice in the art.

Based correspondingly on actual tests employing such practice, the above mentioned examples of minimum values now preferred for the invention are as follows: If the time of digestion is 10 minutes, and if no calcium hydroxide is added to the digester charge, the molar ratio $CaCO_3 : P_2O_5$ should be at least 8:1. If the time of digestion is 10 minutes and calcium hydroxide is used in the proportion of 3 parts per 100 parts of bauxite by weight the molar ratio of $CaCO_3 : P_2O_5$ should be at least 2:1, but when the time of digestion is increased to 60 minutes, this ratio need only be 1.8:1, and for intermediate digestion times the ratio may be between these limits.

It will be seen that in a general sense, the greater the quantity of calcium hydroxide, the smaller is the amount of calcium carbonate required, and to a corresponding but lesser degree, the effect of increase of digestion time is also apparently such as to reduce the requirement of calcium carbonate. Ordinarily the minimum digestion time will be that needed for desired utilization of the Bayer process under the given circumstances, disregarding the problem of phosphorus contamination; in some cases the time preferred for the ordinary digestion procedure, without the present invention, may be as much as 30 minutes or more. To the extent that this time can be increased economically (with regard to other considerations of commercial operation), some saving of calcium carbonate may be effected.

As indicated above, the precise chemical or physical mechanism whereby calcium carbonate impedes the solution of phosphorus in the liquor is not understood, but tests have abundantly established the efficacy of the process, i.e. in that despite a high phosphorus content in the bauxite, the equilibrium value to which the phosphorus concentration in the solution rises can now be kept at or well below a tolerable minimum. Although the exact form of the calcium carbonate does not seem significant in other respects great convenience is served by having it in a fine state of subdivision, i.e. in order that it may act with practical rapidity. It is essentially insoluble in the aluminate solution, and in practice can be filtered off with the residue from digestion after serving its purpose. Then in repeating the process, calcium carbonate is added anew,

e.g. in a fresh quantity, for each cycle. According to present experience there is no harm, either to the recovery of alumina or the rejection of phosphorus, in using even a considerable excess of calcium carbonate over the requirements suggested above, but in most cases reasons of economy make it important to avoid a substantial excess.

Generally speaking, the chief criterion for the use of the process, and indeed, in the last analysis, for the amount of calcium carbonate to be employed in it, is the phosphorus content of the bauxite, which ordinarily determines the value to which the phosphorus concentration of the liquor may rise in the course of recycling and in the absence of added calcium carbonate,—i.e. the utimate equilibrium value. In turn, as stated above, the equilibrium value governs the phosphorus contamination of the precipitated alumina. If significant contamination is to be avoided, under ordinary circumstances a value of 2 grams P_2O_5 per liter seems an inherently appropriate maximum for the phosphorus in the liquor. Thus where we refer below to a specific phosphorus content of the bauxite as a limit upon the practical use of calcium hydroxide (alone) to prevent undue concentrations in the liquor, it will be understood that an undue concentration means one exceeding the above-selected value of 2 grams P_2O_5 per liter.

It will also be appreciated that wherever reference is made herein to calcium hydroxide as added to the digest liquor, such term is used generically (unless the contrary is stated) to include calcium oxide as an alternative, in the manner already mentioned. In naming a specific proportion of phosphorus in the bauxite, the figure given below represents phosphorus pentoxide. In point of fact the phosphorus occurs only in chemical combination in both the bauxite and the aluminate solution; but present inability to make a precise identification of the actual phosphorus compound or compounds in either body seems immaterial to this invention.

When the proportion of phosphorus (i.e. P_2O_5) in the bauxite does not exceed 0.6% by weight, undue concentrations in the digest liquor will, even when this is used repeatedly, be prevented by the presence of the amount of calcium hydroxide used to replace the sodium hydroxide consumed, but when this percentage is exceeded further amounts of calcium must be added. According to the invention, this additional calcium is added as calcium carbonate.

Having now particularly described and ascertained the nature of our said invention, and in what manner the same is to be performed, we declare that what we claim is:—

1. A process of separating alumina values from phosphorus-contaminated bauxite material which comprises digesting said material with sodium hydroxide, and impeding solution of phosphorus in said liquor by introducing calcium carbonate as such into the liquor and effecting said digestion in the presence of said calcium carbonate.

2. A process of separating alumina values from phosphorus-contaminated bauxite material, which comprises digesting said material with a liquor containing sodium hydroxide and sodium carbonate in a predetermined proportion, and impeding contamination of the liquor with phosphorus by introducing calcium carbonate into the liquor without thereby changing the aforesaid proportion and maintaining the presence of said calcium carbonate during the digestion.

3. A cyclic process according to claim 2, which comprises digesting successive quantities of said material with a correspondingly recycled liquor containing sodium hydroxide and sodium carbonate, wherein the alumina content of the liquor is reduced between successive digestions and the proportion of said hydroxide and carbonate is brought to a predetermined value for each digestion, and introducing the calcium carbonate into the liquor from time to time and suppressing solution of phosphorus from the bauxite by maintaining such calcium carbonate in the liquor during each digestion.

4. A cyclic process according to any of claims 1 to 3, in which the quantity of calcium carbonate added is such that between said calcium carbonate and the phosphorus pentoxide content of the bauxite there is maintained a molar ratio of at least 2:1 when the time of digestion is 10 minutes and when calcium hydroxide has been added to the digester charge in quantities sufficient to replace losses of sodium hydroxide in a preceding cycle, and a ratio between 2:1 and 1.8:1 for digestion times between 10 and 60 minutes, likewise when calcium hydroxide has been added as aforesaid, and a ratio of at least 8:1 when the process is carried out without calcium except in the form of calcium carbonate.

5. A process according to any of claims 1 to 4, in which the proportion of phosphorus pentoxide present in the liquor is maintained at a level not higher than 2 grams per litre.

6. A process according to any of claims 1 to 5, in which the bauxite material

e.g. in a fresh quantity, for each cycle. According to present experience there is no harm, either to the recovery of alumina or the rejection of phosphorus, in using even a considerable excess of calcium carbonate over the requirements suggested above, but in most cases reasons of economy make it important to avoid a substantial excess.

Generally speaking, the chief criterion for the use of the process, and indeed, in the last analysis, for the amount of calcium carbonate to be employed in it, is the phosphorus content of the bauxite, which ordinarily determines the value to which the phosphorus concentration of the liquor may rise in the course of recycling and in the absence of added calcium carbonate,—i.e. the utimate equilibrium value. In turn, as stated above, the equilibrium value governs the phosphorus contamination of the precipitated alumina. If significant contamination is to be avoided, under ordinary circumstances a value of 2 grams P_2O_5 per liter seems an inherently appropriate maximum for the phosphorus in the liquor. Thus where we refer below to a specific phosphorus content of the bauxite as a limit upon the practical use of calcium hydroxide (alone) to prevent undue concentrations in the liquor, it will be understood that an undue concentration means one exceeding the above-selected value of 2 grams P_2O_5 per liter.

It will also be appreciated that wherever reference is made herein to calcium hydroxide as added to the digest liquor, such term is used generically (unless the contrary is stated) to include calcium oxide as an alternative, in the manner already mentioned. In naming a specific proportion of phosphorus in the bauxite, the figure given below represents phosphorus pentoxide. In point of fact the phosphorus occurs only in chemical combination in both the bauxite and the aluminate solution; but present inability to make a precise identification of the actual phosphorus compound or compounds in either body seems immaterial to this invention.

When the proportion of phosphorus (i.e. P_2O_5) in the bauxite does not exceed 0.6% by weight, undue concentrations in the digest liquor will, even when this is used repeatedly, be prevented by the presence of the amount of calcium hydroxide used to replace the sodium hydroxide consumed, but when this percentage is exceeded further amounts of calcium must be added. According to the invention, this additional calcium is added as calcium carbonate.

Having now particularly described and ascertained the nature of our said invention, and in what manner the same is to be performed, we declare that what we claim is:—

1. A process of separating alumina values from phosphorus-contaminated bauxite material which comprises digesting said material with sodium hydroxide, and impeding solution of phosphorus in said liquor by introducing calcium carbonate as such into the liquor and effecting said digestion in the presence of said calcium carbonate.

2. A process of separating alumina values from phosphorus-contaminated bauxite material, which comprises digesting said material with a liquor containing sodium hydroxide and sodium carbonate in a predetermined proportion, and impeding contamination of the liquor with phosphorus by introducing calcium carbonate into the liquor without thereby changing the aforesaid proportion and maintaining the presence of said calcium carbonate during the digestion.

3. A cyclic process according to claim 2, which comprises digesting successive quantities of said material with a correspondingly recycled liquor containing sodium hydroxide and sodium carbonate, wherein the alumina content of the liquor is reduced between successive digestions and the proportion of said hydroxide and carbonate is brought to a predetermined value for each digestion, and introducing the calcium carbonate into the liquor from time to time and suppressing solution of phosphorus from the bauxite by maintaining such calcium carbonate in the liquor during each digestion.

4. A cyclic process according to any of claims 1 to 3, in which the quantity of calcium carbonate added is such that between said calcium carbonate and the phosphorus pentoxide content of the bauxite there is maintained a molar ratio of at least 2:1 when the time of digestion is 10 minutes and when calcium hydroxide has been added to the digester charge in quantities sufficient to replace losses of sodium hydroxide in a preceding cycle, and a ratio between 2:1 and 1.8:1 for digestion times between 10 and 60 minutes, likewise when calcium hydroxide has been added as aforesaid, and a ratio of at least 8:1 when the process is carried out without calcium except in the form of calcium carbonate.

5. A process according to any of claims 1 to 4, in which the proportion of phosphorus pentoxide present in the liquor is maintained at a level not higher than 2 grams per litre.

6. A process according to any of claims 1 to 5, in which the bauxite material

629630

treated does not contain less than 0.6% of phosphorus pentoxide.

7. A process of separating alumina values from phosphorus-contaminated bauxite material substantially as hereinbefore described.

8. Alumina values whenever obtained from phosphorus-contaminated bauxite material by the process according to any of claims 1 to 7.

Dated the 4th day of March, 1947.

For: ALUMINIUM LABORATORIES LIMITED,
Stevens, Langner, Parry & Rollinson,
Chartered Patent Agents,
5/9, Quality Court, Chancery Lane,
London, W.C.2, and at
120, East 41st Street, New York, 17,
New York, U.S.A.

Leamington Spa: Printed for His Majesty's Stationery Office, by the Courier Press.—1949.
Published at The Patent Office, 25, Southampton Buildings, London, W.C.2, from which copies, price 2s. 0d. each (inland) 2s. 1d. (abroad) may be obtained.





Stevens, Langner, Parry