

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau

(43) International Publication Date
18 March 2021 (18.03.2021)



(10) International Publication Number
WO 2021/050176 A1

(51) International Patent Classification:

C30B 15/00 (2006.01) C30B 15/22 (2006.01)
C30B 15/04 (2006.01) C30B 29/06 (2006.01)
C30B 15/20 (2006.01)

(21) International Application Number:

PCT/US2020/044844

(22) International Filing Date:

04 August 2020 (04.08.2020)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

16/569,949 13 September 2019 (13.09.2019) US
16/570,010 13 September 2019 (13.09.2019) US

(71) Applicant: **GLOBALWAFERS CO., LTD.** [CN/CN];
No. 8 Industrial East Road 2, Science-Based Industrial Park,
Hsinchu (TW).

(72) Inventors: **RYU, JaeWoo**; 501 Pearl Drive, St. Peters,
Missouri 63376 (US). **HUDSON, Carissima Marie**; 501
Pearl Drive, St. Peters, Missouri 63376 (US).

(74) Agent: **SCHUTH, Richard A.** et al.; ARMSTRONG
TEASDALE LLP, 7700 Forsyth Blvd., Suite 1800, St.
Louis, Missouri 63105 (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,
CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO,
DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,
HR, HU, ID, IL, IN, IR, IS, IT, JO, JP, KE, KG, KH, KN,
KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD,
ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO,

(54) Title: METHODS FOR GROWING A NITROGEN DOPED SINGLE CRYSTAL SILICON INGOT USING CONTINUOUS CZOCHRALSKI METHOD AND A SINGLE CRYSTAL SILICON INGOT GROWN BY THIS METHOD




FIG. 4A

(57) Abstract: A method for growing a single crystal silicon ingot by the continuous Czochralski method is disclosed. The melt depth and thermal conditions are constant during growth because the silicon melt is continuously replenished as it is consumed, and the crucible location is fixed. The critical v/G is determined by the hot zone configuration, and the continuous replenishment of silicon to the melt during growth enables growth of the ingot at a constant pull rate consistent with the critical v/G during growth of a substantial portion of the main body of the ingot. The continuous replenishment of silicon is accompanied by periodic or continuous nitrogen addition to the melt to result in a nitrogen doped ingot.

[Continued on next page]

WO 2021/050176 A1

NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW,
SA, SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))