

5 **MIDDLE DISTILLATE HYDROCRACKING CATALYST CONTAINING ZEOLITE
BETA WITH LOW OD ACIDITY AND LARGE DOMAIN SIZE**

10 This application is related to two co-filed applications titled “MIDDLE DISTILLATE
HYDROCRACKING CATALYST CONTAINING ZEOLITE USY, AND ZEOLITE BETA
WITH LOW ACIDITY AND LARGE DOMAIN SIZE” and “IMPROVED NOBLE METAL
ZEOLITE CATALYST FOR SECOND-STAGE HYDROCRACKING TO MAKE MIDDLE
DISTILLATE”, herein incorporated in their entireties.

TECHNICAL FIELD

15 This application is directed to a hydrocracking catalyst, a process for hydrocracking a
hydrocarbonaceous feedstock, and a method for making a hydrocracking catalyst.

BACKGROUND

20 Improved hydrocracking catalysts and processes for using them and making them are
needed. Earlier hydrocracking catalysts have not provided the desired levels of activity and
selectivity that are required to optimize the production of middle distillates.

SUMMARY

This application provides a hydrocracking catalyst comprising:

- 25 a. from 0.5 to 10 wt% zeolite beta having an OD acidity of 20 to 400 $\mu\text{mol/g}$ and
an average domain size from 800 to 1500 nm^2 ;
- b. from 0 to 5 wt% zeolite USY having an ASDI between 0.05 and 0.12; wherein
a wt% of the zeolite beta is greater than the wt% of the zeolite USY;
- c. a catalyst support; and
- 30 d. at least one metal selected from the group consisting of elements from Group
6 and Groups 8 through 10 of the Periodic Table.

 This application also provides a process for hydrocracking a hydrocarbonaceous
feedstock, comprising contacting the hydrocarbonaceous feedstock with a hydrocracking
catalyst under hydrocracking conditions to produce a hydrocracked effluent that comprises
35 middle distillates; wherein the hydrocracking catalyst comprises:

- a. from 0.5 to 10 wt% zeolite beta having an OD acidity of 20 to 400 $\mu\text{mol/g}$ and
an average domain size from 800 to 1500 nm^2 ;

- 5 b. from 0 to 5 wt% zeolite USY having an ASDI between 0.05 and 0.12; wherein the wt% of the zeolite beta is greater than the wt% of the zeolite USY;
- c. a catalyst support; and
- d. at least one metal selected from the group consisting of elements from Group 6 and Groups 8 through 10 of the Periodic Table.
- 10 This application also provides a method for making a hydrocracking catalyst, comprising:
- a. mixing together a zeolite beta having an OD acidity of 20 to 400 $\mu\text{mol/g}$ and an average domain size from 800 to 1500 nm^2 ; optionally, a zeolite USY having an ASDI between 0.05 and 0.12; a catalyst support; and enough liquid to form an extrudable paste;
- 15 wherein a wt% of the zeolite beta is greater than a second wt% of the zeolite USY;
- b. extruding the extrudable paste to form an extrudate base;
- c. impregnating the extrudate base with a metal impregnation solution containing at least one metal selected from the group consisting of elements from Group 6 and Group 8 through 10 of the Periodic Table to make a metal-loaded extrudate; and
- 20 d. post-treating the metal-loaded extrudate by subjecting the metal-loaded extrudate to drying and calcination; wherein the hydrocracking catalyst has improved selectivity for producing a hydrocracked effluent having a TBP of 380 -700 °F (193-371 °C).

The present invention may suitably comprise, consist of, or consist essentially of, the elements in the claims, as described herein.

25

BRIEF DESCRIPTION OF THE DRAWINGS

FIGURE 1 is a transmission electron microscopy (TEM) image showing the agglomerate crystals of the H-BEA-150 zeolite beta used in the preparation of the hydrocracking catalysts in the examples.

30

FIGURE 2 is a chart of the domain measurements made on two samples of zeolite beta.

FIGURE 3 is a chart of the average domain sizes of two samples of zeolite beta.

GLOSSARY

35

“Hydrocracking” refers to a process in which hydrogenation and dehydrogenation accompanies the cracking/fragmentation of hydrocarbons, e.g., converting heavier hydrocarbons into lighter hydrocarbons, or converting aromatics and/or cycloparaffins(naphthenes) into non-cyclic branched paraffins.

5 “Cut point” refers to the temperature on a True Boiling Point (“TBP”) curve at which a predetermined degree of separation is reached.

“TBP” refers to the boiling point of a hydrocarbonaceous feed or product, as determined by ASTM D2887-13.

10 “Hydrocarbonaceous” means a compound or substance that contains hydrogen and carbon atoms, and which can include heteroatoms such as oxygen, sulfur, or nitrogen.

“Distillates” include the following products:

Products	Typical Cut Points, °F (°C) for North American Market
Light Naphtha	C ₅ -180 (C ₅ – 82)
Heavy Naphtha	180-300 (82-149)
Jet	300-380 (149-193)
Kerosene	380-530 (193-277)
Diesel	530-700 (277-371)

“Middle distillates” include jet, kerosene and diesel products, as defined by their typical cut points, above.

“Heavy middle distillates” refers to products having a TBP of 380 -700 °F (193-371 °C).

15 “Finished catalyst” refers to the hydrocracking catalyst composition comprising all of its components and after all of the processing and any post-processing steps used to manufacture it.

“LHSV” means liquid hourly space velocity.

20 “SCF/B” refers to a unit of standard cubic foot of gas (e.g., nitrogen, hydrogen, air, etc) per barrel of hydrocarbonaceous feed.

“Zeolite beta” refers to zeolites having a 3-dimensional crystal structure with straight 12-membered ring channels with crossed 12-membered ring channels, and having a framework density of about 15.3 T/1000Å³. Zeolite beta has a BEA framework as described in Ch. Baerlocher and L.B. McCusker, Database of Zeolite Structures: [http://www.iza-](http://www.iza-structure.org/databases/)

25 [structure.org/databases/](http://www.iza-structure.org/databases/)

“SiO₂/Al₂O₃ mole ratio (SAR) is determined by ICP elemental analysis. A SAR of infinity means there is no aluminum in the zeolite, i.e., the mole ratio of silica to alumina is infinity. In that case, the zeolite is comprised of essentially all silica.

30 “Zeolite USY” refers to ultra-stabilized Y zeolite. Y zeolites are synthetic faujasite (FAU) zeolites having a SAR of 3 or higher. Y zeolite can be ultra-stabilized by one or more of hydrothermal stabilization, dealumination, and isomorphous substitution. Zeolite USY can be any FAU-type zeolite with a higher framework silicon content than a starting (as-synthesized) Na-Y zeolite precursor.

5 “Catalyst support” refers to a material, usually a solid with a high surface area, to which a catalyst is affixed.

 “Periodic Table” refers to the version of the IUPAC Periodic Table of the Elements dated June 22, 2007, and the numbering scheme for the Periodic Table Groups is as described in Chemical And Engineering News, 63(5), 27 (1985).

10 “OD acidity” refers to the amount of bridged hydroxyl groups exchanged with deuterated benzene at 80°C by Fourier transform infrared spectroscopy (FTIR). OD acidity is a measure of the Brønsted acid sites density in a catalyst. The extinction coefficient of OD signals was determined by analysis on a standard zeolite beta sample calibrated with ¹H magic-angle spinning nuclear magnetic resonance (MAS NMR) spectroscopy. A correlation between the
15 OD and OH extinction coefficients was obtained as following:

$$\epsilon_{(-OD)} = 0.62 * \epsilon_{(-OH)}.$$

 “Domain Size” is the calculated area, in nm², of the structural units observed and measured in zeolite beta catalysts. Domains are described by Paul A. Wright et. al., “Direct Observation of Growth Defects in Zeolite Beta”, JACS Communications, published on web
20 12/22/2004. The method used to measure the domain sizes of zeolite beta is further described herein.

 “Acid site distribution index (ASDI)” is an indicator of the hyperactive site concentration of a zeolite. In some embodiments, the lower the ASDI the more likely the zeolite will have a greater selectivity towards the production of heavier middle distillate products.

25 “Amorphous silica aluminate (ASA)” refers to a synthetic material having some of the alumina present in tetrahedral coordination as shown by nuclear magnetic resonance imaging. ASA can be used as a catalyst or catalyst support. Amorphous silica alumina contains sites which are termed Brønsted acid (or protic) sites, with an ionizable hydrogen atom, and Lewis acid (aprotic), electron accepting sites and these different types of acidic site can be
30 distinguished by the ways in which, say, pyridine attaches.

 “Pseudo-boehmite alumina refers to an aluminum compound with the chemical composition AlO(OH). Pseudo-boehmite alumina consists of finely crystalline boehmite with a higher water content than boehmite.

35 “API gravity” refers to the gravity of a petroleum feedstock or product relative to water, as determined by ASTM D4052-11.

 “Polycyclic index (PCI)” refers to a measure of the content of compounds having several aromatic rings. PCI is useful in evaluating feedstocks for hydroprocessing. PCI is measured using UV-spectroscopy and is calculated as follows:

- 5 $PCI = \{[Absorbance @385 \text{ nm} - (0.378 \times Absorbance @435 \text{ nm})]/115 \times c\} \times 1000$;
 where c is the original concentration of the sample in solvent in g/cm^3 .

DETAILED DESCRIPTION

- Without being bound by theory, it is believed that the unique combination of zeolite beta
 10 with a defined OD acidity and a defined average domain size, optionally combined with a
 zeolite USY with a defined acid site distribution index (ASDI); combined in a specified
 proportion provides a hydrocracking catalyst having much improved hydrocracking
 performance. The unique combination of these two zeolites in a hydrocracking catalyst gives
 improved selectivity for producing a hydrocracked effluent having a TBP of 380 – 700°F
 15 (193-371°C). The hydrocracking catalyst can also provide improved activity, such as from 1
 to 20°F at 60% conversion compared to other hydrocracking catalysts that do not have the
 unique combination of zeolites disclosed herein.

Hydrocracking Catalyst Composition – Zeolite Beta:

- 20 The zeolite beta has an OD acidity of 20 to 400 $\mu\text{mol/g}$ and an average domain size from
 800 to 1500 nm^2 . In one embodiment, the OD acidity is from 30 to 100 $\mu\text{mol/g}$.

In one embodiment the zeolite beta is synthetically manufactured using organic
 templates. Examples of three different zeolite betas are described in Table 1.

Table 1

Zeolite Betas	$\text{SiO}_2/\text{Al}_2\text{O}_3$ Molar Ratio (SAR)	OD Acidity, $\mu\text{mol/g}$
H-BEA-35	35	304
H-BEA-150 (ZE0090)	150	36
CP811C-300 (ZE0106)	300	Not measured

- 25 The total OD acidity was determined by H/D exchange of acidic hydroxyl groups by
 FTIR spectroscopy. The method to determine the total OD acidity was adapted from the
 method described in the publication by Emiel J.M. Hensen et. al., J.Phys. Chem., C2010, 114,
 8363-8374. Prior to FTIR measurement, the sample was heated for one hour at 400-450°C
 under vacuum $<1 \times 10^{-5}$ Torr. Then the sample was dosed with C_6D_6 to equilibrium at 80°C.
 30 Before and after C_6D_6 dosing, spectra were collected for OH and OD stretching regions.

The average domain size was determined by a combination of transmission electron
 (TEM) and digital image analysis, as follows:

I. Zeolite Beta Sample Preparation:

5 The zeolite beta sample was prepared by embedding a small amount of the zeolite beta in an epoxy and microtoming. The description of suitable procedures can be found in many standard microscopy text books.

Step 1. A small representative portion of the zeolite beta powder was embedded in epoxy. The epoxy was allowed to cure.

10 Step 2. The epoxy containing a representative portion of the zeolite beta powder was microtomed to 80-90 nm thick. The microtome sections were collected on a 400 mesh 3mm copper grid, available from microscopy supply vendors.

Step 3. A sufficient layer of electrically-conducting carbon was vacuum evaporated onto the microtomed sections to prevent the zeolite beta sample from charging under the electron
15 beam in the TEM.

II. TEM Imaging:

Step 1. The prepared zeolite beta sample, described above, was surveyed at low magnifications, e.g., 250,000 – 1,000,000x to select a crystal in which the zeolite beta channels can be viewed.

20 Step 2. The selected zeolite beta crystals were tilted onto their zone axis, focused to near Scherzer defocus, and an image was recorded $\geq 2,000,000\times$.

III. Image Analysis to Obtain Average Domain Size (nm²):

Step 1. The recorded TEM digital images described previously were analyzed using commercially available image analysis software packages.

25 Step 2. The individual domains were isolated and the domain sizes were measured in nm². The domains where the projection was not clearly down the channel view were not included in the measurements.

Step 3. A statistically relevant number of domains were measured. The raw data was stored in a computer spreadsheet program.

30 Step 4. Descriptive statistics, and frequencies were determined - The arithmetic mean (d_{av}), or average domain size, and the standard deviation (s) were calculated using the following equations:

$$\text{The average domain size, } d_{av} = (\sum n_i d_i) / (\sum n_i)$$

$$\text{The standard deviation, } s = (\sum (d_i - d_{av})^2 / (\sum n_i))^{1/2}$$

35 In one embodiment the average domain size is from 900 to 1250 nm², such as from 1000 to 1150 nm².

5 Hydrocracking Catalyst Composition – Zeolite USY:

When included in the hydrocracking catalyst composition, the zeolite USY has an acid site distribution index (ASDI) between 0.05 and 0.12. In one embodiment, the zeolite USY has an ASDI that favors the production of heavy middle distillates.

ASDI is determined by H/D exchange of acidic hydroxyl groups by FTIR spectroscopy, as described previously. Brönsted acid sites density was determined by using the integrated area of peak 2676 cm^{-1} as the first high frequency OD (HF), 2653 cm^{-1} as the 2nd high frequency OD (HF'), 2632 cm^{-1} and 2620 cm^{-1} as the first low frequency OD (LF) and 2600 cm^{-1} as the 2nd low frequency OD (LF'). The acid site distribution index factor was determined by the following equation: $\text{ASDI} = (\text{HF}' + \text{LF}')/(\text{HF} + \text{LF})$; which reflects the hyperactive acid sites content in the zeolite sample. In one embodiment the zeolite USY has a total Brönsted acid sites determined by FTIR after H/D exchange of 0.080 to 0.200 mmol/g.

In one embodiment, the wt% of the zeolite beta is greater than the wt% of the zeolite USY in the hydrocracking catalyst. For example, the wt% of the zeolite beta can be from 0.45 to 9.95 wt% greater than the wt% of the zeolite USY. In one embodiment, the wt% of the zeolite beta is from 1 to 5 wt% higher than the wt% of the zeolite USY. In one embodiment, the hydrocracking catalyst has a weight ratio of the zeolite USY to the zeolite beta that is less than 0.90, such as from 0.01 to 0.80, or from 0.02 to 0.48.

Hydrocracking Catalyst Composition – Catalyst Support:

The hydrocracking catalyst comprises a catalyst support. The catalyst support can be inert or can participate in the catalytic reactions performed by the hydrocracking catalyst. Typical catalyst supports include various kinds of carbon, alumina, and silica. In one embodiment, the catalyst support comprises an amorphous silica aluminate. In one embodiment, the catalyst support comprises an amorphous silica aluminate and a second support material.

In one embodiment, the amorphous silica aluminate (ASA) has greater thermal stability than high purity aluminas. Examples of suitable amorphous silica aluminates are SIRAL® ASAs, described below:

Table 2

Typical Properties		SIRAL 1	SIRAL 5	SIRAL 10	SIRAL 20	SIRAL 30	SIRAL 40
Al ₂ O ₃ + SiO ₂	%	75	75	75	75	75	75
Loss on Ignition (LOI)	%	25	25	25	25	25	25

Al ₂ O ₃ : SiO ₂	%	99:1	95:5	90:10	80:20	70:30	60:40
C	%	0.2	0.2	0.2	0.2	0.2	0.2
Fe ₂ O ₃	%	0.02	0.02	0.02	0.02	0.02	0.02
Na ₂ O	%	0.005	0.005	0.005	0.005	0.005	0.005
Loose bulk density	[g/l]	600-800	450-650	400-600	300-500	250-450	250-450
Particle size (d ₅₀)	[μ m]	50	50	50	50	50	50
Surface area (BET)*	[m ² /g]	280	370	400	420	470	500
Pore volume*	[ml/g]	0.50	0.70	0.75	0.75	0.80	0.90

* After activation at 550 °C for 3 hours.

5 SIRAL® is a registered trademark of SASOL.

Examples of the second support material, when used, can include kieselguhr, alumina, silica, and silica-alumina. Other examples of the second support material include alumina-boria, silica-alumina-magnesia, silica-alumina-titania and materials obtained by adding zeolites and other complex oxides thereto. In one embodiment, the second support material is porous, and comprises a natural clay or a synthetic oxide. The second support material can be selected to provide adequate mechanical strength and chemical stability at the reaction conditions under which the hydrocracking catalyst is employed.

In one embodiment, the second support material comprises a pseudo-boehmite alumina. Examples of pseudo-boehmite alumina are CATAPAL® high purity aluminas. CATAPAL® is a registered trademark of SASOL. Typical properties of the CATAPAL high purity aluminas are summarized below:

Table 3

Typical Properties	CATAPAL B	CATAPAL C1	CATAPAL D	CATAPAL 200
Al ₂ O ₃ , wt%	72	72	76	80
Na ₂ O, wt%	0.002	0.002	0.002	0.002
Loose Bulk Density, g/l	670-750	670-750	700-800	500-700
Packed Bulk Density, g/l	800-1100	800-1100	800-1100	700-800
Average Particle size (d ₅₀), μm	60	60	40	40
Surface Area* (BET), m ² /g	250	230	220	100
Pore Volume*, ml/g	0.50	0.50	0.55	0.70
Crystal size, nm	4.5	5.5	7.0	40

*Surface area and pore volume were determined after activation at 550°C for 3 hours.

5 Hydrocracking Catalyst Composition – Metal:

 The hydrocracking catalyst comprises at least one metal selected from the group consisting of elements from Group 6 and Groups 8 through 10 of the Periodic Table. In one embodiment, the hydrocracking catalyst comprises at least one Group 6 metal and at least one metal selected from Groups 8 through 10 of the Periodic Table. In one embodiment, each
10 metal is selected from the group consisting of nickel (Ni), palladium (Pd), platinum (Pt), cobalt (Co), iron (Fe), chromium (Cr), molybdenum (Mo), tungsten (W), and mixtures thereof. Exemplary mixtures of metals include Ni/Mo/W, Ni/Mo, Ni/W, Co/Mo, Co/W, Co/W/Mo, Ni/Co/W/Mo, and Pt/Pd. In another embodiment, the hydrocracking catalyst contains at least one Group 6 metal and at least one metal selected from Groups 8 through 10
15 of the periodic table. Exemplary metal combinations include Ni/Mo/W, Ni/Mo, Ni/W, Co/Mo, Co/W, Co/W/Mo and Ni/Co/W/Mo.

 In one embodiment, the at least one metal is a metal oxide. In one embodiment, the total amount of a metal oxide in the hydrocracking catalyst is from 0.1 wt. % to 90 wt. % based on the bulk dry weight of the finished hydrocracking catalyst. In one embodiment, the
20 hydrocracking catalyst contains from 2 wt. % to 10 wt. % of nickel oxide and from 8 wt. % to 40 wt. % of tungsten oxide based on the bulk dry weight of the finished hydrocracking catalyst.

 In one embodiment, the finished hydrocracking catalyst will have the following composition:

25 0.5 to 10 wt% zeolite beta having an OD acidity of 20 to 400 $\mu\text{mol/g}$ and an average domain size from 800 to 1500 nm^2 , 0 to 5 wt% zeolite USY having an ASDI between 0.05 and 0.12, with the wt% zeolite beta being greater than the wt% zeolite USY, 3 to 6 wt% nickel oxide, and from 15 to 35 wt% of tungsten oxide. Additionally, in one embodiment, the finished hydrocracking catalyst can contain an organic acid in an amount wherein the organic
30 acid/Ni molar ratio is from 0 to 2.

 The hydrocracking catalyst may additionally contain one or more promoters selected from the group consisting of phosphorous (P), boron (B), fluorine (F), silicon (Si), aluminum (Al), zinc (Zn), manganese (Mn), and mixtures thereof. The amount of promoter in the hydrocracking catalyst can be from 0 wt. % to 10 wt. % based on the bulk dry weight of the
35 finished hydrocracking catalyst. In one embodiment, the amount of promoter in the hydrocracking catalyst is from 0.1 wt. % to 5 wt. % based on the bulk dry weight of the finished hydrocracking catalyst.

5 In one embodiment, the hydrocracking catalyst is in the form of extruded pellets (extrudates) that have an extruded pellet diameter of 10 mm or less, such as from 1.0 to 5.0 mm. In one embodiment, the extruded pellet has a length-to-diameter ratio of 10 to 1. Examples of other types and sizes of pellets used for the hydrocracking catalysts are 1 to 10 mm diameter spheres; 1 to 10 mm diameter cylinders with a length-to-diameter ratio of 4 to 1; 1 to 10 mm asymmetric shapes (including quadrolobes), and up to 10 mm diameter hollow cylinders or rings.

Hydrocracking Catalyst Preparation

15 The hydrocracking catalyst can be prepared by: a) mixing the zeolite beta, the zeolite USY (when used), the catalyst support, and enough liquid to form an extrudable paste that forms an extrudate base; b) impregnating the extrudate base with a metal impregnation solution containing at least one metal to make a metal-loaded extrudate; and c) post-treating the metal-loaded extrudate by subjecting the metal-loaded extrudate to drying and calcination.

20 In one embodiment, the method for making a hydrocracking catalyst comprises:




- a. mixing together a zeolite beta having an OD acidity of 20 to 400 $\mu\text{mol/g}$ and an average domain size from 800 to 1500 nm^2 ; a zeolite USY having an ASDI between 0.05 and 0.12; a catalyst support; and enough liquid to form an extrudable paste; wherein a wt% of the zeolite beta is greater than a second wt% of the zeolite Y;
- 25 b. extruding the extrudable paste to form an extrudate base;
- c. impregnating the extrudate base with a metal impregnation solution containing at least one metal selected from the group consisting of elements from Group 6 and Group 8 through 10 of the Periodic Table to make a metal-loaded extrudate; and
- d. post-treating the metal-loaded extrudate by subjecting the metal-loaded extrudate to drying and calcination; wherein the hydrocracking catalyst has improved selectivity for producing a hydrocracked effluent having a TBP of 380 -700 °F (193-371 °C).

30 The liquid used in step a) can be water or a mild acid. In one embodiment the liquid used in step a) is a diluted HNO_3 acid aqueous solution with from 0.5 to 5 wt% HNO_3 .

Prior to impregnation, the extrudate base can be dried at a temperature between 35 90°C (194°F) and 150°C (302°F) for 30 minutes to 3 hours. The dried extrudate base can then be calcined at one or more temperatures between 350°C (662°F) and 700°C (1292°F).

In one embodiment, the metal impregnation solution is made by dissolving metal precursors in a solvent. Suitable solvents include water, C_1 - C_3 alcohols, ethers, and amines.

- 5 In one embodiment, the solvent is deionized water. The concentration of the impregnation solution can be determined by the pore volume of the catalyst support and by the selected metal loading. In one embodiment, the extrudate base is exposed to the impregnation solution for 0.1 to 10 hours. If the hydrocracking catalyst comprises two or more metals, these metals can be impregnated sequentially or simultaneously.
- 10 In one embodiment, impregnation of at least one of the metals is achieved in the presence of a modifying agent that can be selected from the group consisting of compounds represented by structures (1) through (4), including condensated forms thereof:



wherein:

(1) R₁, R₂ and R₃ are independently selected from the group consisting of hydrogen; hydroxyl; methyl; amine; and linear or branched, substituted or unsubstituted C1-C3 alkyl groups, C1-C3 alkenyl groups, C1-C3 hydroxyalkyl groups, C1-C3 alkoxyalkyl groups, C1-C3 aminoalkyl groups, C1-C3 oxoalkyl groups, C1-C3 carboxyalkyl groups, C1-C3 aminocarboxyalkyl groups and C1-C3 hydroxycarboxyalkyl groups;

(2) R₄ through R₁₀ are independently selected from the group consisting of hydrogen; hydroxyl; and linear or branched, substituted or unsubstituted C2-C3 carboxyalkyl groups;

and

5 (3) R11 is selected from the group consisting of linear or branched, saturated and unsaturated, substituted or unsubstituted C1-C3 alkyl groups, C1-C3 hydroxyalkyl groups, and C1-C3 oxoalkyl groups.

Representative examples of modifying agents useful in this embodiment include 2,3-dihydroxy-succinic acid, ethanedioic acid, 2-hydroxyacetic acid, 2-hydroxy-propanoic acid,
 10 2-hydroxy-1,2,3-propanetricarboxylic acid, methoxyacetic acid, cis-1,2-ethylene dicarboxylic acid, hydroethane-1,2-dicarboxylic acid, ethane-1,2-diol, propane-1,2,3-triol, propanedioic acid, and α -hydro- ω -hydroxypoly(oxyethylene).

In an alternate embodiment, deposition of at least one of the metals is achieved in the presence of a modifying agent selected from the group consisting of N,N'-bis(2-aminoethyl)-
 15 1,2-ethane-diamine, 2-amino-3-(1H-indol-3-yl)-propanoic acid, benzaldehyde, [[(carboxymethyl)imino]bis(ethylenenitrilo)]-tetra-acetic acid, 1,2-cyclohexanediamine, 2-hydroxybenzoic acid, thiocyanate, thiosulfate, thiourea, pyridine, and quinoline.

When used, the modifying agent can impede metal aggregation, thereby enhancing the activity and selectivity of the catalyst.

20 For each embodiment described herein, the amount of modifying agent in the pre-calcined hydrocracking catalyst can be from 0 wt% to 18 wt%, based on the bulk dry weight of the hydrocracking catalyst.

In one embodiment, the metal impregnation solution can additionally comprise a peptizing agent. Examples of peptizing agents are organic acids such as pyruvic acid,
 25 levulinic acid, acetic acid, 2-ketogulonic acid, keto-gluconic acid, thioglycolic acid, 4-acetylbutyric acid, 1,3-acetonedicarboxylic acid, 3-oxo propanoic acid, 4-oxo butanoic acid, 2,3-diethyl succinic acid, citric acid, 5-oxo pentanoic acid, 4-oxo pentanoic acid, formic acid, propionic acid, butyric acid, valeric acid, caproic acid, enanthic acid, caprylic acid, pelargonic acid, capric acid, undecylic acid, lauric acid, tridecylic acid, benzoic acid, salicylic
 30 acid, glutaric acid, adipic acid, pimelic acid, azelaic acid, phthalic acid, isophthalic acid, lactic acid, ethyl glyoxylate, glycolic acid, glucose, glycine, oxamic acid, glyoxylic acid, ethylenediaminetetraacetic acid (EDTA), nitrilotriacetic acid, N-methylaminodiacetic acid, iminodiacetic acid, diglycolic acid, malic acid, gluconic acid, acetylacetone, tartaric acid, aconitic acid, suberic acid, tricarballic acid, malonic acid, succinic acid, and glycolic acid.

35 In one embodiment the metal-loaded extrudate is dried at one or more temperatures in the range of 38°C (100°F) to 149°C (300°F) for 0.1 to 10 hours. The dried metal-loaded extrudate can be further calcined at one or more temperatures from 316°C (600°F) to 649°C (1200°F), with purging excess dry air, for 0.1 to 10 hours.

5

Hydrocracking Overview

The hydrocracking catalyst has improved selectivity for producing a hydrocracked effluent having a TBP of 380 -700 °F (193-371 °C) from a wide variety of hydrocarbonaceous feedstocks. Examples of hydrocarbonaceous feedstocks include those that could be considered disadvantaged feedstocks that would not normally be conducive for making a hydrocracked effluent having a TBP of 380 -700 °F (193-371 °C) using a conventional one- or two-stage hydrocracking process. Suitable hydrocarbonaceous feedstocks that can be used can include visbroken gas oils, heavy coker gas oils, gas oils derived from residue hydrocracking or residue desulfurization, other thermally cracked oils, de-asphalted oils, Fischer-Tropsch derived feedstocks, cycle oils from an FCC unit, heavy coal-derived distillates, coal gasification byproduct tars, heavy shale-derived oils, organic waste oils such as those from pulp or paper mills or from waste biomass pyrolysis units.

Table 4 lists some typical physical properties for a hydrocarbonaceous feedstock that can be used.

20

Table 4

Property	
API Gravity	13.5 – 30.0
N, ppm	0.5 – 2,000
S, wt%	0 – 5
Polycyclic Index (PCI)	1500 – 8000
TBP Range, °F (°C)	700-1200 °F (371-649°C)

Table 5 lists some typical hydrocracking process conditions that can be used.

Table 5

Property	
Liquid Hourly Space Velocity (LHSV), hr ⁻¹	0.1 - 5
H ₂ partial pressure, psig (kPa)	800 – 3,500 (5516-24,132)
H ₂ Consumption Rate, SCF/B	200 – 20,000
H ₂ Recirculation Rate, SCF/B	50 – 5,000
Operating Temperature	200 – 450°C (392 – 842°F)
Conversion (wt%)	30 - 90

Depending on the feedstock, target product slate and amount of available hydrogen, the catalyst described herein can be used alone or in combination with other conventional hydrocracking catalysts.

25

In one embodiment, the process for hydrocracking a hydrocarbonaceous feedstock comprises contacting the hydrocarbonaceous feedstock with a hydrocracking catalyst under hydrocracking conditions to produce a hydrocracked effluent that comprises middle distillates in either a single stage or a two stage hydroprocessing configuration. In one embodiment, the

5 catalyst is deployed in one or more fixed beds in a single stage hydrocracking unit, with recycle or without recycle (once-through). Optionally, the single-stage hydrocracking unit may employ multiple single-stage units operated in parallel.

In one embodiment, the catalyst is deployed in one or more beds or units in a two-stage hydrocracking unit, with and without intermediate stage separation, and with or without
10 recycle. Two-stage hydrocracking units can be operated using a full conversion configuration (meaning all of the hydrotreating and hydrocracking is accomplished within the hydrocracking loop via recycle). This embodiment may employ one or more distillation units within the hydrocracking loop for the purpose of stripping off product prior to the second stage hydrocracking step or prior to recycle of the distillation bottoms back to the first and/or
15 second stage.

Two stage hydrocracking units can also be operated in a partial conversion configuration (meaning one or more distillation units are positioned within hydrocracking loop for the purpose of stripping of one or more streams that are passed on for further hydroprocessing). Operation of the hydrocracking unit in this manner allows a refinery to hydroprocess highly
20 disadvantaged feedstocks by allowing undesirable feed components such as the polynuclear aromatics, nitrogen and sulfur species (which can deactivate hydrocracking catalysts) to pass out of the hydrocracking loop for processing by equipment better suited for processing these components, e.g., an FCC unit.

In one embodiment, the catalyst is used in the first stage and optionally the second stage
25 of a partial conversion, two-stage hydrocracking configuration which is well suited for making at least one middle distillate and a heavy vacuum gas fluidized catalytic cracking feedstock (HVGO FCC), by:

- (a) hydrocracking a hydrocarbonaceous feedstock to produce a first stage hydrocracked effluent;
- 30 (b) distilling the hydrocracked feedstock by atmospheric distillation to form at least one middle distillate fraction and an atmospheric bottoms fraction;
- (c) further distilling the atmospheric bottoms fraction by vacuum distillation to form a side-cut vacuum gas oil fraction and a heavy vacuum gas oil FCC feedstock;
- (d) hydrocracking the side-cut vacuum gas oil fraction to form a second stage
35 hydrocracked effluent; and
- (e) combining the second stage hydrocracked effluent with the first stage hydrocracked effluent.

5 The refinery configuration described above has several advantages over conventional two-stage hydrocracking schemes. First, in this configuration, the catalyst and operating conditions of the first stage are selected to yield a HVGO FCC stream having only the minimum feed qualities necessary to produce FCC products which meet the established commercial specifications. This is in contrast to a conventional two-stage hydrocracking
10 scheme where the first stage hydrocracking unit is operated at a severity necessary to maximize distillate yield which, in turn, requires the unit to be operated at more severe conditions (which requires more hydrogen and reduces the life of the catalyst).

 Second, in this optional configuration, the side-cut VGO sent to the second stage hydrocracker unit is cleaner and easier to hydrocrack than a conventional second stage
15 hydrocracker feed. Therefore, higher quality middle distillate products can be achieved using a smaller volume of second stage hydrocracking catalyst which, in turn, allows for the construction of a smaller hydrocracker reactor and consumption of less hydrogen. The second stage hydrocracking unit configuration reduces construction cost, lowers catalyst fill cost and operating cost.

20 Products Made by Hydrocracking

 The hydrocracking catalyst can produce significantly increased yields of middle distillates. In one embodiment, the hydrocracking catalyst can also provide reduced yields of products having a cut point below 380°F. In one embodiment, the hydrocracked effluent comprises from greater than 30 vol% to 50 vol% of a heavy middle distillate having a TBP
25 of 380 -700 °F (193-371 °C). In one embodiment, the hydrocracked effluent comprises at least 35 vol% to 50 vol% hydrocarbons having a TBP less than 700°F (371°C).

 In one embodiment, the hydrocracking catalyst produces light naphtha and heavy naphtha, but the yields of light naphtha and heavy naphtha can be reduced compared to earlier hydrocracking catalysts not comprising the zeolite beta having an OD acidity of 20 to
30 400 µmol/g and an average domain size from 800 to 1500 nm².

EXAMPLES

Example 1: Preparation of Catalyst Sample DJ-4

 Catalyst sample DJ-4 was prepared by combining 2.9 wt% H-BEA-150 zeolite, 1.1 wt% USY zeolite, 74.5 wt% amorphous silica alumina (ASA) powder, and 21.5 wt% pseudo-boehmite alumina; and mixing them well. The H-BEA-150 zeolite was a zeolite beta that
35 was obtained from SUD CHEMIE. The USY zeolite was obtained from Zeolyst. The USY zeolite had an acid site distribution index (ASDI) of 0.086. Additional properties of the USY zeolite are summarized in Table 6.

5

Table 6

Brönsted acid sites determined by FTIR after H/D exchange (mmol/g)	
HF(OD)	0.076
HF'(OD)	0.005
LF(OD)	0.034
LF'(OD)	0.003
Total	0.118
ASDI	0.086

The ASA powder was Siral-40 obtained from Sasol. The pseudo-boehmite alumina was CATAPAL B from Sasol.

To this mixture described above, a diluted HNO₃ acid aqueous solution (2 wt%) was added to form an extrudable paste. The extrudable paste was extruded into a 1/16" (1.59 mm) asymmetric quadrolobe shape, and dried at 248°F (120°C) for 1 hour. The dried extrudates were calcined at 1100°F (593°C) for 1 hour with purging excess dry air, and cooled down to room temperature.

Ni and W were impregnated onto the dried extruded catalyst using a solution containing ammonium metatungstate and nickel nitrate at concentrations to achieve the target metal loadings of 4.1 wt% NiO and 25.2 wt% WO₃, based on the bulk dry weight of the finished catalyst. The metal impregnated extruded catalyst was dried at 270°F (132°C) for 1 hour. The dried catalyst was then calcined at 950°F (510°C) for 1 hour with purging excess dry air, and cooled down to room temperature. The composition of this finished catalyst sample DJ-4 is shown in Table 7.

20 **Example 2:** Preparation of Catalyst Sample DJ-5

Catalyst sample DJ-5 was prepared similar to the process described in Example 1. 5.7 wt% H-BEA-150 zeolite, 2.1 wt% USY zeolite, 70.7 wt% ASA powder, and 21.5 wt% pseudo-boehmite alumina powder were combined and mixed well. To this mixture, a diluted HNO₃ acid aqueous solution (2 wt%) was added to form an extrudable paste. The extrudable paste was extruded into a 1/16" asymmetric quadrolobe shape, and dried at 248°F (120°C) for 1 hour. The dried extrudates were calcined at 1100°F (593°C) for 1 hour with purging excess dry air, and cooled down to room temperature.

Ni and W were impregnated onto the dried extruded catalyst using a solution containing ammonium metatungstate and nickel nitrate at concentrations to achieve the target metal loadings of 4.1 wt% NiO and 25.2 wt% WO₃, based on the bulk dry

5 weight of the finished catalyst. The metal impregnated extruded catalyst was dried at 270°F (132°C) for 1 hour. The dried catalyst was then calcined at 950°F (510°C) for 1 hour with purging excess dry air, and cooled down to room temperature. The composition of this finished catalyst sample DJ-5 is shown in Table 7.

Example 3: Preparation of Catalyst Sample YY-8

10 Catalyst sample YY-8 was prepared by combining 1.6 wt% H-BEA-150 zeolite, 58.4 wt% amorphous silica alumina (ASA) powder, and 40 wt% pseudo-boehmite alumina; and mixing them well. To this mixture, a diluted HNO₃ acid aqueous solution (2 wt%) was added to form an extrudable paste. The extrudable paste was extruded into a 1/16" asymmetric quadrolobe shape, and dried at 248°F (120°C) for 1 hour. The
15 dried extrudates were calcined at 1100°F (593°C) for 1 hour with purging excess dry air, and cooled down to room temperature.

Ni and W were impregnated onto the dried extruded catalyst using a solution containing ammonium metatungstate and nickel carbonate at concentrations to achieve the target metal loadings of 5 wt% NiO and 29 wt% WO₃, based on the bulk dry weight
20 of the finished catalyst. The solution additionally contained 12.7 grams of citric acid as a chelating agent. The metal impregnated extruded catalyst was dried at 212°F (100°C) for 2 hours. The dried catalyst was then calcined at 500°F (260°C) for 1 hour with purging excess dry air, and cooled down to room temperature. The composition of this finished comparative catalyst sample YY-8 is shown in Table 7.

25 **Example 4:** Preparation of Catalyst Sample YY-9

Catalyst sample YY-9 was prepared similar to the process described in Example 1. 7.1 wt% H-BEA-150 zeolite, 0.7 wt% USY zeolite, 70.7 wt% ASA powder, and 21.5 wt% pseudo-boehmite alumina powder were combined and mixed well. To this
30 mixture, a diluted HNO₃ acid aqueous solution (2 wt%) was added to form an extrudable paste. The extrudable paste was extruded into a 1/16" asymmetric quadrolobe shape, and dried at 248°F (120°C) for 1 hour. The dried extrudates were calcined at 1100°F (593°C) for 1 hour with purging excess dry air, and cooled down to room temperature.

Ni and W were impregnated onto the dried extruded catalyst using a solution
35 containing ammonium metatungstate and nickel nitrate at concentrations to achieve the target metal loadings of 4.1 wt% NiO and 25.2 wt% WO₃, based on the bulk dry weight of the finished catalyst. The metal impregnated extruded catalyst was dried at 270°F (132°C) for 1 hour. The dried catalyst was then calcined at 950°F (510°C) for 1 hour

- 5 with purging excess dry air, and cooled down to room temperature. The composition of this finished catalyst sample YY-9 is shown in Table 7.

5 **Example 5:** Preparation of Comparative Catalyst Sample

Comparative catalyst sample was prepared by combining 5.7 wt% USY zeolite, 71.3 wt% amorphous silica alumina (ASA) powder, and 23 wt% pseudo-boehmite alumina; and mixing them well.

10 To this mixture described above, a diluted HNO₃ acid aqueous solution (2 wt%) was added to form an extrudable paste. The extrudable paste was extruded into a 1/16" asymmetric quadrolobe shape, and dried at 248°F (120°C) for 1 hour. The dried extrudates were calcined at 1100°F (593°C) for 1 hour with purging excess dry air, and cooled down to room temperature.

15 Ni and W were impregnated onto the dried extruded catalyst using a solution containing ammonium metatungstate and nickel nitrate at concentrations to achieve the target metal loadings of 3.8 wt% NiO and 25.3 wt% WO₃, based on the bulk dry weight of the finished catalyst. The metal impregnated extruded catalyst was dried at 270°F (132°C) for 1/2 hour. The dried catalyst was then calcined at 950°F (510°C) for 1 hour with purging excess dry air, and cooled down to room temperature. The composition of this comparative catalyst sample
20 is shown in Table 7.

Table 7
Catalyst Compositions

Catalyst Component	Comparative Base Case	DJ-4	DJ-5	YY-8	YY-9
Zeolite beta, wt%	0	2	4	1	5
Zeolite USY, wt%	4	0.8	1.5	0	0.5
NiO, wt%	3.8	4.1	4.1	5	4.1
WO ₃ , wt%	25.2	25.2	25.2	29	25.2
Al ₂ O ₃	67.0	67.9	65.2	Bal.	65.7
Citric Acid/Ni	0	0	0	0.6	0
Weight ratio zeolite USY/zeolite beta	-	0.40	0.375	0	0.10

Example 6: Comparison of Catalyst Performance

The example catalysts described above were used to process a typical Middle Eastern
25 VGO feedstock. The example catalysts were not presulfided.

The properties of the Middle Eastern VGO feedstock are described in Table 8.

Table 8

API Gravity	21
N, ppm	1140
S, wt%	2.3
Polycyclic Index (PCI)	2333
TBP Range, °F (°C)	
5	708 (376)
10	742 (394)

30	810 (432)
50	861 (461)
70	913 (489)
90	981 (527)
95	1008 (542)
End point	1069 (576)

- 5 The hydrocracking runs were operated in a pilot plant unit under 2300 psig (18,858 kPa) total pressure, 1.0 to 2.0 LHSV, and 5000 SCF/B once through hydrogen gas. The test results are summarized below in Table 9.

Table 9

	Comparative Base Case	DJ-4	DJ-5	YY-8	YY-9
CAT, °F (60% conv.)	Base	-5	-8	0	-12
Yields Compared to Comparative Base Case, by cut point					
C ₄ gas, wt%	Base	-0.3	-0.2	-0.6	-0.6
C ₅ -180°F, vol%	Base	-0.6	0.1	-0.8	-0.8
180 – 380°F, vol%	Base	-6.7	-6.2	-7.5	-6.5
380 – 530°F, vol%	Base	1.6	0.8	1.9	1.2
530-700°F, vol%	Base	5.5	3.8	6.8	5.8
Heavy Middle distillates (380 – 700°F), vol%	Base	7.1	4.6	8.7	7.0

- 10 The catalyst samples DJ-4, DJ-5, YY-8 and YY-9 gave significantly increased yields of middle distillates and reduced yields of products having a cut point below 380°F compared to the commercial comparative catalyst sample. The catalyst examples containing similar total zeolite amounts of 4.0 to 5.5 wt% were 8 to 12°F more active than the commercial comparative catalyst sample.

- 15 It is believed that the hydrocracking catalyst samples comprising H-BEA-150, with the unique distribution of larger domain sizes (and thus fewer faults), reduced the unselective cracking that produces more gas. The combination with a zeolite USY having minimum hyper-active sites (i.e., having an ASDI between 0.05 and 0.12) also provided enhanced activity.

Example 7: Domain Size Analysis of Two Different Beta Zeolites

- 20 Domain size determinations were made on two samples of commercial zeolite beta. One sample was the same H-BEA-150 zeolite beta (ZE0090) used in the previous examples. The other sample was a comparison zeolite beta from Zeolyst International (CP811C-300, ZE0106) that had a higher SAR than H-BEA-150. The raw data and

- 5 statistical analysis of the data for the domain size analysis is summarized below, in Table 10.

Table 10

	Sample	
	ZE0090	ZE0106
Mean	1089.9	663.6
Standard Error	119.2	67.8
Median	907.2	530.2
Standard Deviation	715.5	454.8
Sample Variance	511881.8	206846.9
Kurtosis	1.2	7.8
Skewness	1.1	2.6
Range	2972.4	2358.0
Minimum	207.7	205.8
Maximum	3180.1	2563.8
Sum	39236.8	29862.5
Count	36.0	45.0
Count of Small Domains, 200 to 600 nm ²	8	20
Count of Large Domains, 1200 to 2000 nm ²	11	1
Count of Extra Large Domains, 1500 to 3200 nm ²	9	2

- The data from these domain size analyses were also charted and are shown in Figures 2 and 3. Figure 2 shows the differences in the frequency of the domain sizes between the two zeolite betas. Figure 3 shows that the domain sizes for the H-BEA-150 were larger and more broadly distributed than those shown for the comparison zeolite beta. The standard deviation for the domain sizes for the H-BEA-150 was greater than 700 nm², while the standard deviation for the domain sizes for the comparison zeolite beta was less than 500 nm². Also, the H-BEA-150 zeolite beta had more large domains that had a domain size from 1200 to 2000 nm² than small domains that had a domain size from 200 to 600 nm²; which is notably different than the distribution of the domain sizes in the comparison zeolite beta. The H-BEA-150 had a similar distribution (9 vs. 8) of extra large domains with a domain size from 1500 to 3200 nm² to small domains with a domain size from 200 to 600 nm². In this context, similar distribution means that the ratio of the count of domains in the two different domain size ranges is from 0.8:1 to 1.2:1.

The transitional term "comprising", which is synonymous with "including," "containing," or "characterized by," is inclusive or open-ended and does not exclude additional, unrecited elements or method steps. The transitional phrase "consisting of" excludes any element, step,

5 or ingredient not specified in the claim. The transitional phrase "consisting essentially of" limits the scope of a claim to the specified materials or steps "and those that do not materially affect the basic and novel characteristic(s)" of the claimed invention.

For the purposes of this specification and appended claims, unless otherwise indicated, all numbers expressing quantities, percentages or proportions, and other numerical values
10 used in the specification and claims, are to be understood as being modified in all instances by the term "about." Furthermore, all ranges disclosed herein are inclusive of the endpoints and are independently combinable. Whenever a numerical range with a lower limit and an upper limit are disclosed, any number falling within the range is also specifically disclosed. Unless otherwise specified, all percentages are in weight percent.

15 Any term, abbreviation or shorthand not defined is understood to have the ordinary meaning used by a person skilled in the art at the time the application is filed. The singular forms "a," "an," and "the," include plural references unless expressly and unequivocally limited to one instance.

All of the publications, patents and patent applications cited in this application are
20 herein incorporated by reference in their entirety to the same extent as if the disclosure of each individual publication, patent application or patent was specifically and individually indicated to be incorporated by reference in its entirety.

This written description uses examples to disclose the invention, including the best mode, and also to enable any person skilled in the art to make and use the invention. Many
25 modifications of the exemplary embodiments of the invention disclosed above will readily occur to those skilled in the art. Accordingly, the invention is to be construed as including all structure and methods that fall within the scope of the appended claims. Unless otherwise specified, the recitation of a genus of elements, materials or other components, from which an individual component or mixture of components can be selected, is intended to include all
30 possible sub-generic combinations of the listed components and mixtures thereof.

The invention illustratively disclosed herein suitably may be practiced in the absence of any element which is not specifically disclosed herein.

5 IT IS CLAIMED:

1. A hydrocracking catalyst comprising:
 - a. from 0.5 to 10 wt% zeolite beta having an OD acidity of 20 to 400 $\mu\text{mol/g}$ and an average domain size from 800 to 1500 nm^2 ;
 - 10 b. from 0 to 5 wt% zeolite USY having an ASDI between 0.05 and 0.12; wherein a wt% of the zeolite beta is greater than the wt% of the zeolite USY;
 - c. a catalyst support; and
 - d. at least one metal selected from the group consisting of elements from Group 6 and Groups 8 through 10 of the Periodic Table.
- 15 2. The hydrocracking catalyst of claim 1, wherein the zeolite beta has a $\text{SiO}_2/\text{Al}_2\text{O}_3$ mole ratio (SAR) from 50 to 200.
3. The hydrocracking catalyst of claim 1, wherein the OD acidity is from 30 to 100 $\mu\text{mol/g}$.
4. The hydrocracking catalyst of claim 1, wherein the average domain size is from 900
20 to 1250 nm^2 .
5. The hydrocracking catalyst of claim 1, wherein the zeolite beta has more large domains that have a domain size from 1200 to 2000 nm^2 than small domains that have the domain size from 200 to 600 nm^2 .
6. The hydrocracking catalyst of claim 1, wherein the zeolite beta has a standard deviation
25 for domain sizes greater than 700 nm^2 .
7. The hydrocracking catalyst of claim 1, wherein the wt% of the zeolite beta is from 1 to 5 wt% higher than the wt% of the zeolite USY.
8. The hydrocracking catalyst of claim 1, wherein a weight ratio of the zeolite USY to the zeolite beta is 0 to 0.48.
- 30 9. The hydrocracking catalyst of claim 1, wherein the zeolite USY has a total Brönsted acid sites determined by FTIR after H/D exchange of 0.080 to 0.200 mmol/g.

- 5 10. The hydrocracking catalyst of claim 1, comprising at least one Group 6 metal and at least one metal selected from Groups 8 through 10 of the Periodic Table.
11. A process for hydrocracking a hydrocarbonaceous feedstock, comprising contacting the hydrocarbonaceous feedstock with a hydrocracking catalyst under hydrocracking conditions to produce a hydrocracked effluent that comprises middle distillates;
10 wherein the hydrocracking catalyst comprises:
- a. from 0.5 to 10 wt% zeolite beta having an OD acidity of 20 to 400 $\mu\text{mol/g}$ and an average domain size from 800 to 1500 nm^2 ;
 - b. from 0 to 5 wt% zeolite USY having an ASDI between 0.05 and 0.12; wherein the wt% of the zeolite beta is greater than the wt% of the zeolite USY;
 - 15 c. a catalyst support; and
 - d. at least one metal selected from the group consisting of elements from Group 6 and Groups 8 through 10 of the Periodic Table.
12. The process of claim 11, wherein the hydrocarbonaceous feedstock has a TBP range within 700 to 1200 $^{\circ}\text{F}$ (371 to 649 $^{\circ}\text{C}$).
- 20 13. The process of claim 11, wherein the zeolite beta has a $\text{SiO}_2/\text{Al}_2\text{O}_3$ mole ratio (SAR) from 50 to 200.
14. The process of claim 11, wherein the OD acidity is from 30 to 100 $\mu\text{mol/g}$.
15. The process of claim 11, wherein the average domain size is from 900 to 1250 nm^2 .
- 25 16. The process of claim 11, wherein the zeolite beta has more large domains that have a domain size from 1200 to 2000 nm^2 than small domains that have the domain size from 200 to 600 nm^2 .
17. The process of claim 11, wherein the zeolite beta has a standard deviation for domain sizes greater than 700 nm^2 .
- 30 18. The process of claim 11, wherein the wt% of the zeolite beta is from 1 to 5 wt% higher than the wt% of the zeolite USY.

- 5 19. The process of claim 11, wherein a weight ratio of the zeolite USY to the zeolite beta is 0 to 0.48.
20. The process of claim 11, wherein the zeolite USY has a total Brönsted sites determined by FTIR after H/D exchange of 0.080 to 0.200 mmol/g.
- 10 21. The process of claim 11, comprising at least one Group 6 metal and at least one metal selected from Groups 8 through 10 of the Periodic Table.
22. The process of claim 11, wherein the hydrocracked effluent comprises from greater than 30 vol% to 50 vol% of a heavy middle distillate having a TBP of 380 -700 °F (193-371 °C).
23. A method for making a hydrocracking catalyst, comprising:
- 15 a. mixing together a zeolite beta having an OD acidity of 20 to 400 $\mu\text{mol/g}$ and an average domain size from 800 to 1500 nm^2 ; optionally, a zeolite USY having an ASDI between 0.05 and 0.12; a catalyst support; and enough liquid to form an extrudable paste; wherein a wt% of the zeolite beta is greater than a second wt% of the zeolite USY;
- 20 b. extruding the extrudable paste to form an extrudate base;
- c. impregnating the extrudate base with a metal impregnation solution containing at least one metal selected from the group consisting of elements from Group 6 and Group 8 through 10 of the Periodic Table to make a metal-loaded extrudate; and
- 25 d. post-treating the metal-loaded extrudate by subjecting the metal-loaded extrudate to drying and calcination; wherein the hydrocracking catalyst has improved selectivity for producing a hydrocracked effluent having a TBP of 380 -700 °F (193-371 °C).