Structure of package

BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to a wafer level package, and more particularly to a wafer level package structure, the wafer level package structure can avoid the open circuit caused by the solder ball cracking due to the temperature variation inducing the reinforcing stress between the solder balls and a print circuit board.

2. Description of the Prior Art

The earlier lead frame package technology is already not suitable for the advanced semiconductor dice due to the density of the terminals thereof is too high. Hence, a new package technology of BGA (Ball Grid Array) has been developed to satisfy the packaging requirement for the advanced semiconductor dice. The BGA package has an advantage of that the spherical terminals has a shorter pitch than that of the lead frame package, and the terminals of the BGA are unlikely to be damage and deform. In addition, the shorter signal transmitting distance benefits to raise the operating frequency to conform to the requirement of faster efficiency. Most of the package

technologies divide dice on a wafer into respective dice and then to package and test the die respectively. Another package technology, called "Wafer Level Package (WLP)", can package the dice on a wafer before dividing the dice into respective individual die. The WLP technology has some advantages, such as a shorter producing cycle time, lower cost, and no need to under-fill or molding.

Besides, a partial package structure using in the present marketing is shown as Fig. 1. The package structure comprises an isolation layer 103 and a passivation layer 102 of an IC device 100. The material of the isolation layer 103 may be a dielectric layer with a thickness of 5 micron such as BCB, polyimides etc.. The material of the passivation layer 102 is polyimides or SiN. The redistribution layer(RDL)104 is combined with the isolation layer 103, Al pads 101 of the IC device. The material of the redistribution layer(RDL)104 may be Cu/Ni/Au alloy with a thickness of 15 micron. Moreover, an isolation layer 105 covers the redistribution layer (RDL) 104. And, the redistribution layer (RDL) 104 has a plurality of openings. Each of the openings has a solder ball 106 to electrically couple with a print circuit board or external parts. The material of the isolation layer 105 may be a dielectric layer such as BCB, epoxy, or polyimides etc..

The aforementioned package structure generally needs an additional material to intensively fix the solder ball 106. It has a

drawback mentioned as follow: the adhesion between the redistribution layer (RDL) 104 and the isolation layer 105 is too strong, which is drawback to the solder ball. When the solder ball 106 joints to the print circuit board, the stress may be induced by temperature influence at the joint part between the solder ball 106 and the redistribution layer (RDL) 104, it is indicated by the area 107, the solder ball 106 will be cracked owing to reinforcing stress raised by temperature variation, thereby causing open circuit between the solder ball and pad.

In view of the aforementioned, the present invention provides an improved wafer level package structure to overcome the above drawback.

SUMMARY OF THE INVENTION

It is an objective of the present invention to provide a wafer level package structure. The wafer level package structure of the present invention can avoid open circuit due to solder ball cracking by reinforcing stress.

The present invention provides a wafer level package structure. The package structure comprises a first patterning isolation layer, a conductive layer and a second patterned isolation layer. The first

patterned isolation layer is provided adjacent to a passivation layer of an IC (Integrated Circuit) . The conductive layer is configured over the passivation layer and metal pads of the IC to have a curved or winding or zigzag conductive pattern. The second patterned isolation layer is formed over the conductive layer having a plurality of openings, and contact metal balls can be formed in the openings to electrically couple to a print circuit board.

The conductive layer will not directly stretch the metal pads when the contact metal ball joints to a print circuit board. The zigzag conductive layer creates buffer area, like a cushion to absorb the stress by poor adhesion between the curved or zigzag conductive layer pattern and the patterned first isolation layer.

BRIEF DESCRIPTION OF THE DRAWINGS

The above objects, and other features and advantages of the present invention will become more apparent after reading the following detailed description when taken in conjunction with the drawings, in which:

Fig. 1 is a schematic diagram of a conventional wafer level package structure.

FIG. 2 is a schematic diagram of one wafer level package structure according to the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENT

The present invention provides a backend structure of wafer level packaging, and the scope of the present invention is expressly not limited expect as specified in the accompanying claims. The present invention discloses a structure of package, comprising: a patterned isolation layer covering a partial region of a underlying layer; and a conductive layer configured on the patterned isolation layer to have a zigzag pattern to absorb stress due to the topography of the patterned isolation layer. Wherein the material for the isolation layer comprises BCB, SINR (Siloxane polymer), epoxy, polyimides or resin. The material for the conductive layer is metal alloy.

As shown in FIG. 2, it is a schematic diagram of one wafer level package structure according to the present invention. The wafer level packaging is expressly not limited expect as specified in the accompanying claims of the present invention. The present invention comprises a patterned isolation layer 203 covering a partial region of passivation layer 202 of a device 200. The material of the isolation layer 203 may be dielectric, such as BCB, SINR (Siloxane polymer), epoxy, polyimides or resin etc.. The patterned isolation layer 203 has a plurality of openings to expose the underlying passivation layer 202. The material of the passivation layer 202 comprises polyimide or SiN.

The area indicated by 207 will suffer the external force as shown in FIG. 2.

The redistribution layer(RDL)204 on the patterned isolation layer 203 is configured with a zigzag or winding conductive layer pattern owing to the pattern topography of the isolation layer. In one preferred embodiment, the material of the conductive layer includes Ti/Cu alloy or Cu/Ni/Au alloy with a thickness of 15 micron. The Ti/Cu alloy may be formed by sputtering technique, the Cu/Ni/Au alloy may be formed by electroplating. The material of the metal pads 201 may be Al or Cu or the combination.

Furthermore, an isolation layer 205 is formed on the conductive layer 204 and the isolation layer 205 have a plurality of openings. Each of the openings has a contact metal ball 206 to electrically couple to a print circuit board (PCB) or external parts (not shown). The contact metal ball 206 may be a conductive ball such as solder ball 206. The material of the isolation layer 205 may be formed of dielectric such as BCB, SINR (Siloxane polymer), epoxy, polyimides or resin etc..

The conductive layer 204 adjacent to the fixed area 210 of the package structure will not directly stretch the metal pads 201 of inter-connector of the IC device 200 due to the passivation layer 202 tightly "catches" the conductive layer 204 by the scheme disclosed by the present invention. The temperature influence will be reduced owing

to the conductive layer 204 directly joint to the passivation layer 202 when the solder ball 206 mounts to the print circuit board, it may induce thermal stress.

Besides, in the buffer area 209 of the package structure, the conductive layer 204 is partially attached to the passivation layer 202 and partially formed on the isolation layer 203 so that the conductive layer 204 is configured to have a curve or zigzag pattern. The stress generated by temperature variation will be distributed due to the shape of the conductive layer and the zigzag structure of the conductive layer acts as a cushion to release the thermal stress. The adhesion between the conductive layer 204 and the isolation layer 203 is poor, the conductive layer 204 will slightly peel from the surface of the isolation layer 203 when external force applied. The extension of the conductive layer will be increased owing to curved conductive layer pattern with zigzag scheme will slightly peel and absorbs the thermal stress. Therefore, the life time of the package structure will be increased. Especially, when the solder ball 206 is far away from the bonding pad.

The present invention also comprises a patterned isolation layer 208 formed between the isolation layer 203 and the conductive layer 204 to increase the zigzag level (namely, increase the number of the zigzag shape) of the conductive layer under the solder ball. The material of the isolation layer 208 comprises BCB, SINR (Siloxane

polymer), epoxy, polyimides or resin.

Hence, according to the present invention, the aforementioned package structure has the advantages list as follow: the wafer level package structure of the present invention can avoid open circuit of the solder ball cracking generated by reinforcing stress due to temperature variation after the solder balls solder joined on the print circuit board. Moreover, it does not need an additional material to intensively fix the solder ball.

Although specific embodiments have been illustrated and described, it will be obvious to those skilled in the art that various modifications may be made without departing from what is intended to be limited solely by the appended claims.

CLAIMS

What is claimed is:

1. A structure of package, comprising:

a patterned first isolation layer covering a partial region of a passivation layer;

a conductive layer formed on said patterned first isolation layer to form a zigzag conductive layer pattern due to the topography of said patterned first isolation layer, wherein said zigzag conductive layer pattern is partially attached on said passivation layer and partially attached on said first isolation layer;

a second isolation layer covering said conductive layer, said second isolation layer having a plurality of openings, each of said openings having a contact metal ball electrically coupling with an external part; and

the adhesion between said conductive layer and said isolation layer is poor, said conductive layer will slightly peel from the surface of said isolation layer.

2. The structure in claim 1, wherein said conductive layer at a fixed area of said structure of package will not directly stretch metal pads when said contact metal ball is placed on a print circuit board, said zigzag conductive layer acting as a buffer of said package to absorb the stress.

3. The structure in claim 1, further comprising a patterned third isolation layer formed between said patterned first isolation layer and

said conductive layer; wherein the material for said third isolation layer comprises BCB, SINR (Siloxane polymer), epoxy, polyimides or resin; wherein the material for said first isolation layer comprises BCB, SINR (Siloxane polymer), epoxy, polyimides or resin.

4. The structure in claim 1, wherein the material for said passivation layer is polyimides; wherein the material for said conductive layer is metal alloy; wherein said metal alloy comprises Ti/Cu alloy or Cu/Ni/Au alloy, said Ti/Cu alloy being formed by sputtering and said Cu/Ni/Au alloy being formed by electroplating; wherein the thickness of said metal alloy is around 10~20 micron.

5. The structure in claim 2, wherein the material of said metal pads comprises Al or Cu.

6. The structure in claim 1, wherein the material of said second isolation layer comprises BCB, SINR (Siloxane polymer), epoxy, polyimides or resin; wherein said contact metal ball is solder ball.

7. A structure of package, comprising:

a patterned isolation layer covering a partial region of a underlying layer; a conductive layer configured on said patterned isolation layer to have a zigzag pattern to absorb stress due to the topography of said patterned isolation layer;

and

the adhesion between said conductive layer and said isolation layer is poor, said conductive layer will slightly peel from the surface of said isolation layer.

8. The structure in claim 7, wherein the material for said isolation layer comprises BCB, SINR (Siloxane polymer), epoxy, polyimides or resin; wherein the material for said conductive layer is metal alloy.

9. The structure in claim 8, wherein said metal alloy comprises Ti/Cu alloy or Cu/Ni/Au alloy; wherein said Ti/Cu alloy is formed by sputtering; wherein said Cu/Ni/Au alloy is formed by electroplating.

10. The structure in claim 8, wherein the thickness of said metal alloy is around 10~20 micron.