We claim:

1. An article produced by additive manufacturing comprising a photopolymerization product of a precursor polymer and a photoinitiator, the precursor polymer includes a first repeat unit and a second repeat unit, wherein one or both of the first repeat unit and second repeat unit comprises polyester repeat units, ~~and~~ the first repeat unit includes at least one vinyl-terminated side-chain, and wherein the photopolymerization product comprises from 35% to 50% b/w vinyl-terminated sidechain functionalization.

2. The article according to claim 1 wherein the polymerization product further comprises an acrylate crosslinker.

3. The article according to claim 1 or claim 2, wherein the acrylate crosslinker includes alkylene oxide.

4. The article according to any one of claims 1-3, wherein the precursor polymer has the following structure:



wherein, independently for each occurrence, m and n are integers from 5 - 400, having an m:n ratio from 1:1 to 20:1, wherein x and y are each independently an integer from 1 - 10; and R^1 includes a vinyl terminated side-chain.

5. The article according to claim 4, wherein R1 has the following structure:



wherein z is an integer from 1 – 10.

6. The article according to any one of claims 2-5, wherein the alkylene oxide crosslinker has the following structure:



wherein w is an integer from 2 – 4, and p is an integer from 1 – 20.

7. The article according to claim 1, wherein the precursor polymer comprises at least one labile bond.

8. The article according to claim 7, wherein the labile bond is formed from the reaction of the precursor polymer with D,L-dithiolthreitol.

9. The article according to claim 2, wherein a labile bond is formed from the reaction of the acrylate crosslinker with D,L-dithiolthreitol.

10. The article according to claim 8 or claim 9, wherein the article having the labile bond is configured to degrade at a faster rate compared to the article ~~of claims 1-6~~without the labile bond.

11. An article produced by additive manufacturing comprising a photopolymerization product of a precursor polymer and a photoinitiator, the precursor polymer having the following structure:



wherein, independently for each occurrence, m and n are integers from 5- 400, and wherein the

m:n ratio is from 1:1 to 20:1, wherein the photopolymerization product comprises from 35% to 50 b/w vinyl-terminated sidechain functionalization.

12. The article according to claim 11, wherein the photopolymerization product further comprises an alkylene oxide crosslinker having the following structure:



wherein p is an integer from 1 – 20.

13. The article according to claim 11, wherein the precursor polymer comprises at least one labile bond.

14. The article according to claim 13, wherein the labile bond is formed from the reaction of the precursor polymer with D,L-dithiolthreitol.

15. The article according to claim 12, wherein a labile bond is formed from the reaction of the alkylene oxide crosslinker with D,L-dithiolthreitol, and wherein the alkylene oxide crosslinker reacted with D,L-dithiolthreitol has a molecular weight between 200 and 6000 daltons.

16. The article according to claim ~~14 or claim~~ 15, wherein the article having the labile bond is configured to degrade at a faster rate compared to the article ~~of claims 11-12~~without the labile bond.

17. A method of manufacturing an article via photopolymerization, the method comprising:

(i) providing a precursor solution, the precursor solution comprising a precursor polymer and photoinitiator; the precursor polymer including a first repeat unit and a second repeat unit, wherein one or both of the first repeat unit and second repeat unit comprises polyester repeat units, and the first repeat unit includes at least one vinyl-terminated side-chain, wherein the photopolymerization product comprises from 35% to 50 b/w vinyl-terminated sidechain functionalization.

(ii) exposing the precursor solution to an intensity and frequency of light to initiate photopolymerization of the precursor polymer to form a layer of the article;

(iii) repeating step (ii) a number of times to form the article in a layer-by-layer configuration via the process of additive manufacturing.

18. The method according to claim 17, wherein the precursor solution further comprises an acrylate crosslinker.

19. The method according to claim 17 or claim 18, wherein the method further comprises providing a manufacturing device and heating at least a portion of said manufacturing device to 20°c to 80°C.

20. The method according to any of claims 17-19, wherein the method further comprises exposing the article to DMSO at a temperature of between 40°C to 60°C for at least 1 hour.