

Refractory product having high zirconia content

Field of technology

The invention relates to a new fused cast refractory product having a high zirconia content.

Prior art

Among refractory products, a distinction is made between fused cast products, well known for the construction of glass melting furnaces, and sintered products.

In contrast to sintered products, the fused cast products most often comprise an intergranular vitreous phase binding crystalline grains. The problems posed by sintered products and by fused cast products, and the technical solutions adopted for solving them, are therefore generally different. A composition developed for making a sintered product is therefore not usable as such *a priori* for making a fused cast product, and vice versa.

The fused cast products, often called electrocast products, are obtained by melting a mixture of suitable raw materials in an electric arc furnace or by any other technique that is suitable for these products. The molten material is then cast in a mold, and the product obtained undergoes a controlled cooling cycle so that it reaches room temperature without cracking. This operation is called "annealing" by a person skilled in the art.

Among the fused cast products, the electrocast products with high zirconia content, i.e. having more than 85 wt.% of zirconia (ZrO_2), have a reputation for their quality of very high corrosion resistance without coloration of the glass produced and without generating defects.

Conventionally, the fused cast products with high zirconia content also comprise sodium oxide (Na_2O) to prevent the formation of zircon from the zirconia and silica present in the product. The formation of zircon is in fact harmful since it is accompanied by a decrease in volume of the order of 20%, thus creating mechanical stresses that cause cracking.

The product ER-1195 produced and marketed by Saint-Gobain SEFPRO and covered by patent EP-B-403 387 is now widely used in glass melting furnaces. Its chemical composition comprises about 94% zirconia, 4 to 5% silica, about 1% alumina, 0.3% sodium oxide and less than 0.05 wt.% P_2O_5 . It is typical of products with high zirconia content used for glass furnaces.

FR 2 701 022 describes fused cast products with high zirconia content that contain 0.05 to 1.0 wt.% of P_2O_5 and 0.05 to 1.0 wt.% of boron oxide B_2O_3 . These products have a high electrical resistivity. Advantageously, this makes it possible to stabilize the electric power consumption during electric melting of glass and in particular avoid any problem of short circuiting in the refractory products leading to their rapid degradation. In fact, during electric melting of glass, some of the electric current passes through the refractory products. The increase in the resistivity of these refractory products therefore makes it possible to reduce the amount of electric current able to pass through them.

WO 2009 027610 describes fused cast products with high zirconia content having a high electrical resistivity in the presence of at least one oxide selected from Nb_2O_5 and Ta_2O_5 for silica contents between 6 and 12%.

WO 2007 099253 describes fused cast products with high zirconia content having a high electrical resistivity in the presence of at least one oxide selected from CrO_3 , Nb_2O_5 , MoO_3 , Ta_2O_5 and WO_3 . These products contain less than 1.5 wt.% of B_2O_3 for alumina contents between 0.1 and 2.4%.

WO 2005 068393 describes fused cast products with high zirconia content having a high electrical resistivity while minimizing the contents of BaO , SrO , MgO , CaO , P_2O_5 , Na_2O and K_2O . These products contain 0.1 to 1.2 wt.% of B_2O_3 and between 0.8% and 2.5% of alumina. This document does not suggest adding Ta_2O_5 or B_2O_3 .

JP 63 285173 describes fused cast products with high zirconia content having a good electrical resistivity and resistance to cracking for silica contents less than 6.5%.

The current development of glasses of very high quality, in particular glasses for flat screens of the LCD type, increases the requirements for the refractory products of glass melting furnaces. In particular, there is a need for refractory products with improved electrical resistivity while having good resistance to corrosion by glass.

The present invention aims to satisfy this need.

Summary of the invention

More particularly, the invention relates to a fused cast refractory product comprising, in percentages by weight based on the oxides and for a total of 100% of the oxides:

$\text{ZrO}_2 + \text{Hf}_2\text{O}_3$: complement to 100%;

$4.0\% < \text{SiO}_2 < 6.5\%$

$\text{Al}_2\text{O}_3 \leq 0.75\%$

$0.2\% < \text{B}_2\text{O}_3 < 1.5\%$

$0.3\% < \text{Ta}_2\text{O}_5 < 1.5\%$

$\text{Nb}_2\text{O}_5 < 1.5\%$, preferably $\text{Ta}_2\text{O}_5 + \text{Nb}_2\text{O}_5 < 1.4\%$;

$\text{Na}_2\text{O} + \text{K}_2\text{O} < 0.2\%$

$\text{BaO} < 0.2\%$

$\text{P}_2\text{O}_5 < 0.15\%$

$\text{Fe}_2\text{O}_3 + \text{TiO}_2 < 0.55\%$

other oxide species: $< 1.5\%$

the ratio "A/B" of the contents by weight $\text{Al}_2\text{O}_3 / \text{B}_2\text{O}_3$ being less than 1.50.

As will be seen later, surprisingly, the inventors discovered that this composition allows the refractory product according to the invention to have a good electrical resistivity, for silica contents less than 6.5% enabling good corrosion resistance and a limited content of Nb_2O_5 and Ta_2O_5 to be maintained, notably making it possible to limit costs.

A refractory product according to the invention can then further comprise one or more of the following optional characteristics:

- The ratio A/B of the contents by weight $\text{Al}_2\text{O}_3 / \text{B}_2\text{O}_3$ is less than or equal to 1.40, preferably less than 1.30, or even less than 1.20, or even less than 1.10.
- The ratio A/B of the contents by weight $\text{Al}_2\text{O}_3 / \text{B}_2\text{O}_3$ is above 0.10, or even above 0.20, or even above 0.30.
- The content by weight of $\text{ZrO}_2 + \text{HfO}_2$ is less than 95.5%, or even less than 95.0%, or even less than 94.0% and/or above 87.0%, above 90.0%, above 91.0%, or even above 92.0%.
- The $\text{Al}_2\text{O}_3/\text{SiO}_2$ ratio is less than 0.20, preferably less than 0.15, preferably less than 0.13, preferably less than 0.10.
- The content by weight of silica SiO_2 is less than 6.3%, less than 6.0%, or even less than 5.8% or less than 5.6%.

- The content by weight of silica SiO_2 is above 4.2%, or even above 4.5%, or even above 4.8%, or even above 5.0%, or above 5.2%.
- The content by weight of alumina Al_2O_3 is less than 0.7%, less than 0.6%, or even less than 0.55%, or even less than 0.5%.
- Alumina Al_2O_3 is only present as impurities.
- The content by weight of Al_2O_3 is above 0.2%, or even above 0.25%.
- The content by weight of B_2O_3 is above 0.25%, above 0.30%, above 0.35%, or even above 0.4%.
- The content by weight of B_2O_3 is less than 1.2%, or even less than 1.0%, or even less than 0.80%, less than 0.7%, less than 0.6%, or even less than 0.55%.
- The total content by weight of $\text{Nb}_2\text{O}_5 + \text{Ta}_2\text{O}_5$ is above 0.4%, preferably above 0.5%, preferably above 0.6% and/or less than 1.3%, or even less than 1.2%.
- The content by weight of Ta_2O_5 is above 0.4%, preferably above 0.5%, preferably above 0.6% and/or less than 1.4%, or even less than 1.3%, or even less than 1.2.
- The content by weight of Nb_2O_5 is less than 1.0%, less than 0.6%, or even less than 0.40%.
- The weight ratio $\text{ZrO}_2 / (\text{Nb}_2\text{O}_5 + \text{Ta}_2\text{O}_5)$ is above 50, above 80 and/or less than 200, less than 150.
- The content by weight of $(\text{Na}_2\text{O} + \text{K}_2\text{O})$ is less than 0.1%, or even less than 0.05%.
- The content by weight of P_2O_5 is less than 0.05%.
- The oxides of iron and/or of titanium and/or of calcium and/or of strontium and/or of barium and/or of magnesium and/or of zinc and/or of phosphorus are only present as impurities.
- The content by weight of oxides of iron and/or of titanium, $\text{Fe}_2\text{O}_3 + \text{TiO}_2$, is less than 0.4%, preferably less than 0.3%, preferably less than 0.2%.
- The content by weight of oxide of calcium and/or of strontium and/or barium and/or of magnesium and/or of zinc is less than 0.15%, preferably less than 0.1%.
- The total content by weight of oxides of calcium and/or of strontium and/or barium and/or of magnesium and/or of zinc, $\text{CaO} + \text{SrO} + \text{BaO} + \text{MgO} + \text{ZnO}$, is less than 0.3%, preferably less than 0.2%, less than 0.1%, less than 0.05%.
- The total content by weight of the "other oxide species" is less than 1.0%, less than 0.6%, less than 0.5%, or even less than 0.3%.
- The "other oxide species" only consist of impurities and the total content by weight of the "other oxide species" is less than 0.6%, less than 0.5%, or even less than 0.3%.

- The content by weight of yttrium oxide Y_2O_3 is less than 1%, preferably less than 0.5%, more preferably less than 0.4%, or even less than 0.3%, or even less than 0.25%. In one embodiment, $Y_2O_3 < 0.15\%$, or even $Y_2O_3 < 0.05\%$, or the content of Y_2O_3 is zero.

According to a particular embodiment, the invention proposes a fused cast refractory product comprising, in percentages by weight based on the oxides:

$$92.0\% < ZrO_2 + Hf_2O < 94.7\%$$

$$4.5\% < SiO_2 < 6.5\%$$

$$Al_2O_3 < 0.7\%$$

$$0.3\% < B_2O_3 < 0.6\%$$

$$0.5\% < Ta_2O_5 < 1.4\%$$

$$Na_2O + K_2O < 0.05\%$$

$$CaO + SrO + MgO + ZnO + BaO < 0.2\%$$

other oxide species (other than ZrO_2 , Hf_2O , SiO_2 , Al_2O_3 , B_2O_3 , Ta_2O_5 , Na_2O , K_2O , CaO , SrO , MgO , ZnO , and BaO): complement to 100%,

the ratio "A/B" of the contents by weight Al_2O_3 / B_2O_3 being less than or equal to 1.2.

Preferably, the other oxide species represent less than 2.5%, less than 2.0%, less than 1.5%, less than 1.0%, less than 0.5%, or even less than 0.3%.

The invention also relates to a method for manufacturing a refractory product according to the invention, comprising the following successive steps:

- a) mixing raw materials so as to form an initial charge,
- b) melting said initial charge until a molten material is obtained,
- c) casting and solidification of said molten material, by cooling, so as to obtain a refractory product,

said method being characterized in that said raw materials are selected so that said refractory product is according to the invention.

Preferably, oxides for which a minimum content is required, notably ZrO_2 , SiO_2 , B_2O_3 , Ta_2O_5 or precursors of these oxides, are added systematically and methodically. In particular, Y_2O_3 is not added. Preferably, the contents of these oxides in the sources of the other oxides, where they are conventionally regarded as impurities, are taken into account.

Preferably, cooling is controlled, preferably so as to be carried out at a rate of less than 20°C per hour, preferably at a rate of about 10°C per hour.

The invention also relates to a glass melting furnace comprising a refractory product according to the invention, or a refractory product manufactured or that can be manufactured by a method according to the invention, in particular in a region intended to be in contact with molten glass. In a furnace according to the invention, the refractory product can advantageously form part of a tank for making glass by melting, notably by electric melting, where it may come in contact with molten glass at a temperature above 1200°C.

Definitions

The contents of oxides by weight refer to the total contents for each of the corresponding chemical elements, expressed in the form of the most stable oxide, according to the convention that is usual in the industry; therefore this includes the suboxides and optionally nitrides, oxynitrides, carbides, oxycarbides, carbonitrides, or even the metallic species of the aforementioned elements.

A "molten material" is a liquid mass which, to conserve its shape, must be contained in a container. It can contain some solid particles, but of an insufficient amount to be able to structure said mass.

"Impurities" means the inevitable constituents, introduced unintentionally and necessarily with the raw materials or resulting from reactions with these constituents. The impurities are not necessary constituents, but are merely tolerated. For example, the compounds included in the group of the oxides, nitrides, oxynitrides, carbides, oxycarbides, carbonitrides and metallic species of iron, titanium, vanadium and chromium are impurities.

Unless stated otherwise, all the contents of oxides in the products described and claimed are percentages by weight based on the oxides.

Detailed description of the invention

In a fused cast product according to the invention, high content of zirconia ZrO_2 makes it possible to meet the requirements of high corrosion resistance without coloration of the glass produced and without producing defects that impair the quality of said glass.

In a product obtained by melting, HfO_2 cannot be dissociated chemically from ZrO_2 . In the chemical composition of such a product, $\text{ZrO}_2 + \text{HfO}_2$ therefore denotes the total content of these two oxides. However, according to the present invention, HfO_2 is not added deliberately in the initial charge. HfO_2 therefore only denotes traces of hafnium oxide, this oxide always being naturally present in sources of zirconia at contents generally less than 2%. For clarity, the content of zirconia and traces of hafnium oxide can therefore be denoted either by $\text{ZrO}_2 + \text{HfO}_2$ or by ZrO_2 , or by "zirconia content".

The content of hafnium oxide HfO_2 in a product according to the invention is less than 5%, generally less than 2%.

The presence of silica SiO_2 notably permits the formation of an intergranular vitreous phase that can effectively accommodate the changes in volume of the zirconia during its reversible allotropic transformation, i.e. during transition from the monoclinic phase to the tetragonal phase.

However, addition of silica must be limited in order to obtain high corrosion resistance. Moreover, too high a content of silica might cause defects in the glass through detachment of stones (pieces of refractory product resulting from loss in cohesion of the product), which is regarded as poor behavior in application.

The presence of alumina promotes the formation of a stable vitreous phase and improves the castability of the products in the mold. An excessive content leads to instability of the vitreous phase (formation of crystals), which has an adverse effect on feasibility, in particular in the presence of boron oxide. The content by weight of alumina must therefore remain limited.

The presence of a content by weight of B_2O_3 in a proportion such that the ratio A/B of the contents by weight $\text{Al}_2\text{O}_3 / \text{B}_2\text{O}_3$ is less than 1.50 makes it possible to increase the electrical resistivity.

The oxides Ta_2O_5 and Nb_2O_5 have a favorable effect on electrical resistivity. The content by weight of Ta_2O_5 must in particular be above 0.3%.

In a product according to the invention, it is considered that the oxides Na_2O and K_2O have similar effects.

The oxides Na_2O and K_2O have an adverse influence on electrical resistivity. The content by weight of $\text{Na}_2\text{O} + \text{K}_2\text{O}$ must therefore be less than 0.2%.

According to the invention, the content by weight of $\text{Fe}_2\text{O}_3 + \text{TiO}_2$ is less than 0.55% and that of P_2O_5 is less than 0.15%, preferably less than 0.10%, more preferably less than 0.05%. In fact, these oxides are known to be harmful and their content must preferably be limited to traces introduced as impurities with the raw materials.

Unless stated otherwise, the "other oxide species" are the species that are not listed above, namely species other than ZrO_2 , Hf_2O , SiO_2 , Al_2O_3 , B_2O_3 , Ta_2O_5 , Nb_2O_5 , Na_2O , K_2O , BaO , P_2O_5 , Fe_2O_3 and TiO_2 . In one embodiment, the "other oxide species" are limited to species whose presence is not particularly desired and which are generally present as impurities in the raw materials.

Conventionally, in a fused cast product, the oxides represent more than 98.5%, more than 99%, or even roughly 100% of the mass of the product. It is the same in a product according to the invention.

A product according to the invention can be manufactured conventionally according to steps a) to c) described less than:

- a) mixing raw materials so as to form an initial charge,
- b) melting said initial charge until a molten material is obtained,
- c) solidification of said molten material, by cooling, so as to obtain a refractory product according to the invention.

In step a), the raw materials are selected so as to guarantee the contents of oxides in the finished product.

In step b), melting is preferably effected through the combined action of a fairly long electric arc, not causing reduction, and mixing which promotes reoxidation of the products.

To minimize the formation of nodules of a metallic appearance and prevent the formation of cracks or crazing in the final product, it is preferable to perform melting in oxidizing conditions.

The long-arc melting process described in French patent No. 1 208 577 and its additions No. 75893 and 82310 is preferably used.

This process consists of using an arc furnace whose arc is struck between the charge and at least one electrode some distance from said charge and adjusting the length of the arc so that its reducing action is minimized, while maintaining an oxidizing atmosphere above the molten bath and mixing said bath, either by the action of the arc itself, or by bubbling an oxidizing gas (air or oxygen, for example) in the bath or by adding substances that release oxygen, such as peroxides or nitrates, to the bath.

Melting can in particular take place at a temperature above 2300°C, preferably between 2400°C and 2500°C.

In step c), cooling is preferably carried out at a rate of less than 20°C per hour, preferably at a rate of about 10°C per hour.

A product of the invention manufactured in this way consists of grains of zirconia surrounded by a vitreous phase. The zirconia can be monoclinic to more than 80%, more than 90%, more than 99% or roughly 100%, as percentage by weight. The vitreous phase can comprise for example more than 50%, or even more than 70%, of silica, between 5% and 20% of B_2O_3 and between 1% and 20% of alumina, in percentages by weight based on the vitreous phase. The silica, B_2O_3 and alumina can represent more than 95%, more than 97%, or even roughly 100% of the weight of the vitreous phase.

Any conventional method of manufacturing fused products based on zirconia intended for applications in glass melting furnaces can be employed, provided that the composition of the initial charge allows products to be obtained having a composition according to that of a product according to the invention.

Examples

The following non-limiting examples are given for the purpose of illustrating the invention.

In these examples, the following raw materials were used:

- zirconia containing mainly, on average by weight, 98.5% ZrO_2 + HfO_2 , 0.2% SiO_2 and 0.02% Na_2O ,
- zircon sand at 33% silica,
- boron oxide of purity above 99%,
- niobium oxide and tantalum oxide of purity above 99%.

The raw materials were melted by the conventional process of arc furnace melting and then the molten material was cast to obtain blocks with the dimensions 220 mm x 450 mm x 150 mm.

Example 1 corresponds to the product ER1195, marketed by Saint-Gobain SEFPRO, and constitutes the reference.

For all the products obtained, crystallographic analysis reveals crystals of monoclinic zirconia surrounded by a vitreous phase typically having more than 70% of silica. All of the silica as well as the other oxide species with the exception of zirconia are in the vitreous phase.

The chemical analysis of the products obtained is given in Table 1; this is an average overall chemical analysis, given in percentages by weight.

In the following Table 1, * indicates that the example is outside of the invention, and an empty cell corresponds to a content less than or equal to 0.05 wt.%.

Cylindrical bars of product 30 mm in diameter and 30 mm high were extracted from the various examples of blocks produced. These bars were submitted to a potential difference of 1 volt at a frequency of 100 Hertz at 1500°C or 1600°C respectively for measuring the electrical resistivity, "R1500" and "R1600" respectively.

Table 1

Compositions by weight (as percentage based on oxides)										
	ZrO ₂	SiO ₂	B ₂ O ₃	Al ₂ O ₃	Ta ₂ O ₅	Nb ₂ O ₅	Na ₂ O	A/B	R1500 (Ω.cm)	R1600 (Ω.cm)
1*	Complement to 100%	4.0		1.20			0.3		70	
2*		4.5	0.40	0.80				2.00	110	80
3*		4.1	0.40	0.61				1.53	107	81
4*		4.9	0.36	0.74		0.69		2.06	181	134
5*		5.0	0.49	0.92	0.99			1.88	190	135
6*		5.1	0.38	0.83	0.56	0.40		2.18	197	140
7		5.0	0.52	0.75	1.03			1.44	280	190
8		5.1	0.50	0.52	1.02			1.04	450	275
9		5.3	0.27	0.26	0.71			0.96	453	283
10		6.0	0.49	0.51	1.02			1.04	410	250
11		4.6	0.47	0.54	1.00			1.15	340	212
12		4.8	0.36	0.44	0.86			1.22	254	165
13*		4.9	0.36	0.56	0.98			1.56	225	141

The results show that the products of the invention tested have improved electrical resistivity.

Comparison of examples 5* (or 6*) and then 13* with example 7, and then comparison of examples 5* (or 6*) and then 13* with example 8 shows, at roughly constant silica content and at roughly identical total contents of dopant, the very positive effect of a decrease in the ratio A/B. The same applies on comparing example 4* with example 12.

Examples 7 and 8 demonstrate, at roughly constant silica content, the very positive effect of a decrease in the ratio A/B between 1.44 and 1.04 and its synergistic effect with the dopant.

Comparison of examples 8 and 9 or of examples 9 and 10 shows that the performance can be maintained if the ratio A/B is maintained, despite a decrease in the contents of B₂O₃, Al₂O₃, and Ta₂O₅.

Finally, measurements showed that the resistance to corrosion by molten glass of the products of the invention is equivalent to that of the reference example 1*.

Of course, the present invention is not limited to the embodiments in the examples, which are given for purposes of illustration.

CLAIMS

1. A fused cast refractory product comprising, in percentages by weight based on the oxides and for a total of 100% of the oxides:

$\text{ZrO}_2 + \text{Hf}_2\text{O}_3$: complement to 100%

$4.0\% < \text{SiO}_2 < 6.5\%$

$\text{Al}_2\text{O}_3 \leq 0.75\%$

$0.2\% < \text{B}_2\text{O}_3 < 1.5\%$

$0.3\% < \text{Ta}_2\text{O}_5$

$\text{Nb}_2\text{O}_5 + \text{Ta}_2\text{O}_5 < 1.4\%$

$\text{Na}_2\text{O} + \text{K}_2\text{O} < 0.2\%$

$\text{BaO} < 0.2\%$

$\text{P}_2\text{O}_5 < 0.15\%$

$\text{Fe}_2\text{O}_3 + \text{TiO}_2 < 0.55\%$

other oxide species: $< 1.5\%$

the ratio "A/B" of the contents by weight $\text{Al}_2\text{O}_3 / \text{B}_2\text{O}_3$ being less than 1.50.

2. The product as claimed in the preceding claim, wherein the ratio A/B is less than 1.40.
3. The product as claimed in the preceding claim, wherein the ratio A/B is less than 1.30.
4. The product as claimed in the preceding claim, wherein the ratio A/B is less than 1.20.
5. The product as claimed in any one of the preceding claims, wherein $\text{Nb}_2\text{O}_5 + \text{Ta}_2\text{O}_5 > 0.5\%$.
6. The product as claimed in any one of the preceding claims, wherein $\text{Nb}_2\text{O}_5 + \text{Ta}_2\text{O}_5 < 1.2\%$.
7. The product as claimed in any one of the preceding claims, wherein the content by weight of silica SiO_2 is less than 6.0%.
8. The product as claimed in any one of the preceding claims, wherein the content by weight of silica SiO_2 is greater than 4.5%.
9. The product as claimed in any one of the preceding claims, wherein the content by weight of silica SiO_2 is greater than 4.8%.

10. The product as claimed in any one of the preceding claims, wherein the content by weight of B_2O_3 is less than 1.0%.
11. The product as claimed in the preceding claim, wherein the content by weight of B_2O_3 is less than 0.80%.
12. The product as claimed in any one of the preceding claims, wherein the content by weight of Al_2O_3 is less than 0.7%.
13. The product as claimed in any one of the preceding claims, wherein the content by weight of Al_2O_3 is less than 0.6%.
14. The product as claimed in any one of the preceding claims, wherein the content by weight of Al_2O_3 is less than 0.55%.
15. The product as claimed in any one of the preceding claims, wherein the content by weight of $Na_2O + K_2O$ is less than 0.1%.
16. The product as claimed in any one of the preceding claims, wherein the content by weight of $Na_2O + K_2O$ is less than 0.05%.
17. The product as claimed in any one of the preceding claims, comprising, in percentages by weight based on the oxides:
 - $92.0\% < ZrO_2 + Hf_2O < 94.7\%$
 - $4.5\% < SiO_2 < 6.5\%$
 - $Al_2O_3 < 0.7\%$
 - $0.3\% < B_2O_3 < 0.6\%$
 - $0.5\% < Ta_2O_5$
 - $Nb_2O_5 + Ta_2O_5 < 1.4\%$
 - $Na_2O + K_2O < 0.05\%$
 - $CaO + SrO + MgO + ZnO + BaO < 0.2\%$
 - oxide species other than ZrO_2 , Hf_2O , SiO_2 , Al_2O_3 , B_2O_3 , Ta_2O_5 , Na_2O , K_2O , CaO , SrO , MgO , ZnO , and BaO : complement to 100%,
 - the ratio "A/B" of the contents by weight Al_2O_3 / B_2O_3 being less than or equal to 1.2.
18. The product as claimed in any one of the preceding claims, wherein the content by weight of Y_2O_3 is less than 0.25%.
19. The product as claimed in any one of the preceding claims, wherein the content by weight of oxides of iron and/or of titanium, $Fe_2O_3 + TiO_2$, is less than 0.4%, the content by weight of P_2O_5 is less than 0.05%, the total content by weight of oxides

of calcium and/or of strontium and/or of barium and/or of magnesium and/or of zinc, $\text{CaO} + \text{SrO} + \text{BaO} + \text{MgO} + \text{ZnO}$, is less than 0.3%, and the total content by weight of "other oxide species" is less than 0.6%.

20. A glass melting furnace comprising a product as claimed in any one of the preceding claims in a region intended to be in contact with molten glass.