

ABSTRACT

The pressure sensitive adhesive sheet (5) has a haze of 1% or less, an adhesive strength of 2.0 N/10 mm or more to glass, a glass transition temperature of -3°C or lower, and a shear storage elastic modulus of 0.16 MPa or more at a temperature of 25°C. The pressure sensitive adhesive can be formed by, for example, applying a composition containing an acryl-based monomer and/or a partially polymerized product thereof and a urethane (meth)acrylate onto a substrate in a layer shape; and thereafter irradiating the composition with an active ray to photocure the composition.

FIG. 1