

WAFER PROCESSING METHOD

BACKGROUND OF THE INVENTION

Field of the Invention

The present invention relates to a wafer processing method for dividing a wafer along a plurality of division lines to obtain a plurality of individual device chips, the division lines being formed on the front side of the wafer to thereby define a plurality of separate regions where a plurality of devices are individually formed.

Description of the Related Art

In a fabrication process for device chips to be used in electronic equipment such as mobile phones and personal computers, a plurality of crossing division lines (streets) are first set on the front side of a wafer formed of a semiconductor, for example, thereby defining a plurality of separate regions on the front side of the wafer. In each separate region, a device such as an integrated circuit (IC), a large-scale integrated circuit (LSI), and a light emitting diode (LED) is next formed. Thereafter, a ring frame having an inside opening is prepared, in which an adhesive tape called a dicing tape is previously attached in its peripheral portion to the ring frame (the back side of the ring frame) so as to

close the inside opening of the ring frame. Thereafter, a central portion of the adhesive tape is attached to the back side of the wafer such that the wafer is accommodated in the inside opening of the ring frame. In this manner, the wafer, the adhesive tape, and the ring frame are united together to form a frame unit. Thereafter, the wafer included in this frame unit is processed to be divided along each division line, thereby obtaining a plurality of individual device chips including the respective devices.

For example, a cutting apparatus is used to divide the wafer. The cutting apparatus includes a chuck table for holding the wafer through the adhesive tape and a cutting unit for cutting the wafer. The cutting unit includes a cutting blade for cutting the wafer and a spindle for rotating the cutting blade. The cutting blade has a central through hole, and the spindle is fitted in this central through hole of the cutting blade, so that the cutting blade and the spindle are rotated as a unit. An annular abrasive portion is provided around the outer circumference of the cutting blade, so as to cut the wafer. In cutting the wafer by using this cutting apparatus, the frame unit is placed on the chuck table, and the wafer is held through the adhesive tape on the

upper surface of the chuck table. In this condition, the spindle is rotated to thereby rotate the cutting blade, and the cutting unit is next lowered to a predetermined height. Thereafter, the chuck table and the cutting unit are relatively moved in a direction parallel to the upper surface of the chuck table. Accordingly, the wafer is cut along each division line by the cutting blade being rotated, so that the wafer is divided.

Thereafter, the frame unit is transferred from the cutting apparatus to another apparatus for applying ultraviolet light to the adhesive tape to thereby reduce the adhesion of the adhesive tape. Thereafter, each device chip is picked up from the adhesive tape. As a processing apparatus capable of producing the device chips with high efficiency, there is a cutting apparatus capable of continuously performing the operation for dividing the wafer and the operation for applying ultraviolet light to the adhesive tape (see Japanese Patent No. 3076179, for example). Each device chip picked up from the adhesive tape is next mounted on a predetermined wiring substrate or the like.

SUMMARY OF THE INVENTION

The adhesive tape includes a base layer and an

adhesive layer formed on the base layer. In cutting the wafer by using the cutting apparatus, the cutting unit is positioned at a predetermined height such that the lower end of the cutting blade reaches a position lower than the lower surface (the back side) of the wafer, so as to reliably divide the wafer. Accordingly, the adhesive layer of the adhesive tape attached to the back side of the wafer is also cut by the cutting blade at the time the wafer is cut by the cutting blade. As a result, in cutting the wafer, cutting dust due to the wafer is generated, and cutting dust due to the adhesive layer is also generated. In cutting the wafer, a cutting water is supplied to the wafer and the cutting blade. The cutting dust generated in cutting the wafer is taken into the cutting water and then diffused on the front side of the wafer. However, the cutting dust due to the adhesive layer is apt to adhere again to the front side of each device. Furthermore, it is not easy to remove this cutting dust adhered to each device in a cleaning step to be performed after cutting the wafer. Accordingly, when the cutting dust due to the adhesive layer adheres to each device formed on the front side of the wafer, there arises a problem such that each device chip may be degraded in quality.

The present invention has been made in view of the above problem, and it is therefore an object of the present invention to provide a wafer processing method which can prevent the adherence of cutting dust to the front side of each device in cutting the wafer, thereby suppressing a degradation in quality of each device chip.

In accordance with an aspect of the present invention, there is provided a wafer processing method for dividing a wafer along a plurality of division lines to obtain a plurality of individual device chips, the division lines being formed on a front side of the wafer to thereby define a plurality of separate regions where a plurality of devices are individually formed. The wafer processing method includes a ring frame preparing step of preparing a ring frame having an inside opening for accommodating the wafer; a polyester sheet providing step of positioning the wafer in the inside opening of the ring frame and providing a polyester sheet on a back side of the wafer and on a back side of the ring frame; a uniting step of heating the polyester sheet as applying a pressure to the polyester sheet after performing the polyester sheet providing step, thereby uniting the wafer and the ring frame through the polyester sheet by thermocompression bonding to form a frame unit in a

condition where the front side of the wafer and the front side of the ring frame are exposed; a dividing step of cutting the wafer along each division line by using a cutting apparatus including a rotatable cutting blade after performing the uniting step, thereby dividing the wafer into the individual device chips; and a pickup step of picking up each device chip from the polyester sheet after performing the dividing step.

Preferably, the uniting step includes a step of applying infrared light to the polyester sheet, thereby performing the thermocompression bonding.

Preferably, the polyester sheet is larger in size than the ring frame, and the uniting step includes an additional step of cutting the polyester sheet after heating the polyester sheet, thereby removing a part of the polyester sheet outside the outer circumference of the ring frame.

Preferably, the pickup step includes a first step of expanding the polyester sheet to thereby increase a spacing between any adjacent ones of the device chips and a second step of pushing up each device chip through the polyester sheet after performing the first step.

Preferably, the polyester sheet is formed of a material selected from the group consisting of

polyethylene terephthalate and polyethylene naphthalate.

In the case that the polyester sheet is formed of polyethylene terephthalate, the polyester sheet is preferably heated in the range of 250°C to 270°C in the uniting step. In the case that the polyester sheet is formed of polyethylene naphthalate, the polyester sheet is preferably heated in the range of 160°C to 180°C in the uniting step.

Preferably, the wafer is formed of a material selected from the group consisting of silicon, gallium nitride, gallium arsenide, and glass.

In the wafer processing method according to a preferred embodiment of the present invention, the wafer and the ring frame are united by using the polyester sheet having no adhesive layer in place of an adhesive tape having an adhesive layer, thereby forming the frame unit composed of the wafer, the ring frame, and the polyester sheet united together. The uniting step of uniting the wafer and the ring frame through the polyester sheet is realized by thermocompression bonding. After performing the uniting step, the wafer is cut to be divided into the individual device chips by using the cutting blade. Thereafter, each device chip is picked up from the polyester sheet. Each device chip picked up is

next mounted on a predetermined wiring substrate or the like.

In cutting the wafer by using the cutting blade, the polyester sheet provided below the wafer is also cut by the cutting blade. That is, the wafer and the polyester sheet bonded to the back side of the wafer are cut together by the cutting blade in a condition where the front side of the wafer is oriented upward. Accordingly, cutting dust due to the polyester sheet is generated. This cutting dust is taken into cutting water supplied in cutting the wafer and then diffused on the front side of the wafer. However, since the polyester sheet has no adhesive layer, the cutting dust does not adhere to the wafer, so that the cutting dust can be removed more reliably in a cleaning step to be performed later. In this manner, according to the preferred embodiment of the present invention, the frame unit can be formed by thermocompression bonding using the polyester sheet having no adhesive layer. Accordingly, cutting dust due to an adhesive layer is not generated in cutting the wafer, so that it is possible to suppress a degradation in quality of each device chip due to such cutting dust having adhesion.

Thus, the wafer processing method according to the

preferred embodiment of the present invention can exhibit the effect that cutting dust does not adhere to the front side of each device in cutting the wafer and a degradation in quality of each device chip divided from the wafer can be suppressed.

The above and other objects, features, and advantages of the present invention and the manner of realizing them will become more apparent, and the invention itself will best be understood from a study of the following description and appended claims with reference to the attached drawings depicting a preferred embodiment of the invention.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic perspective view of a wafer;

FIG. 2 is a schematic perspective view depicting a manner of positioning the wafer and a ring frame on a holding surface of a chuck table;

FIG. 3 is a schematic perspective view depicting a polyester sheet providing step;

FIG. 4 is a schematic perspective view depicting a uniting step;

FIG. 5 is a schematic perspective view depicting a modification of the uniting step;

FIG. 6 is a schematic perspective view depicting another modification of the uniting step;

FIG. 7A is a schematic perspective view depicting a manner of cutting the polyester sheet after performing the uniting step;

FIG. 7B is a schematic perspective view of a frame unit formed by performing the step depicted in FIG. 7A;

FIG. 8 is a schematic perspective view depicting a dividing step;

FIG. 9 is a schematic perspective view depicting a manner of loading the frame unit to a pickup apparatus after performing the dividing step;

FIG. 10A is a schematic sectional view depicting a standby condition where the frame unit is fixed to a frame support table set at an initial position in a pickup step using the pickup apparatus depicted in FIG. 9; and

FIG. 10B is a schematic sectional view depicting a working condition where the frame support table holding the frame unit with the polyester sheet is lowered to expand the polyester sheet in the pickup step.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

A preferred embodiment of the present invention

will now be described with reference to the attached drawings. There will first be described a wafer to be processed by a processing method according to this preferred embodiment. FIG. 1 is a schematic perspective view of a wafer 1. The wafer 1 is a substantially disc-shaped substrate formed of a material such as silicon (Si), silicon carbide (SiC), gallium nitride (GaN), and gallium arsenide (GaAs). The wafer 1 may be formed of any other semiconductor materials. Further, the wafer 1 may be formed of a material such as sapphire, glass, and quartz. The wafer 1 has a front side 1a and a back side 1b. A plurality of crossing division lines 3 are formed on the front side 1a of the wafer 1 to thereby define a plurality of separate regions where a plurality of devices 5 such as ICs and LEDs are respectively formed. The crossing division lines 3 are composed of a plurality of parallel division lines 3 extending in a first direction and a plurality of parallel division lines 3 extending in a second direction perpendicular to the first direction. In the processing method for the wafer 1 according to this preferred embodiment, the wafer 1 is cut along the crossing division lines 3 and thereby divided into a plurality of individual device chips individually including the plural devices 5.

The wafer 1 is cut by using a cutting apparatus. Prior to loading the wafer 1 into the cutting apparatus, the wafer 1 is united with a polyester sheet 9 (see FIG. 3) and a ring frame 7 (see FIG. 3) to thereby form a frame unit. Thus, the wafer 1 is loaded in the form of such a frame unit into the cutting apparatus and then cut into the individual device chips in the cutting apparatus, in which each device chip is supported to the polyester sheet 9. Thereafter, the polyester sheet 9 is expanded to thereby increase the spacing between any adjacent ones of the device chips. Thereafter, each device chip is picked up by using a pickup apparatus. The ring frame 7 is formed of a rigid material such as metal, and it has a circular inside opening 7a having a diameter larger than that of the wafer 1. The outside shape of the ring frame 7 is substantially circular. The ring frame 7 has a front side 7b and a back side 7c. In forming the frame unit, the wafer 1 is accommodated in the inside opening 7a of the ring frame 7 and positioned in such a manner that the center of the wafer 1 substantially coincides with the center of the inside opening 7a.

The polyester sheet 9 is a flexible (expandable) resin sheet, and it has a flat front side and a flat back side. The polyester sheet 9 is a circular sheet having a

diameter larger than the outer diameter of the ring frame 7. The polyester sheet 9 has no adhesive layer. The polyester sheet 9 is a sheet of a polymer (polyester) synthesized by polymerizing dicarboxylic acid (compound having two carboxyl groups) and diol (compound having two hydroxy groups) as a monomer. Examples of the polyester sheet 9 include a polyethylene terephthalate sheet and polyethylene naphthalate sheet. The polyester sheet 9 is transparent or translucent to visible light. As a modification, the polyester sheet 9 may be opaque. Since the polyester sheet 9 has no adhesive property, it cannot be attached to the wafer 1 and the ring frame 7 at room temperature. However, the polyester sheet 9 is a thermoplastic sheet, so that, when the polyester sheet 9 is heated to a temperature near its melting point under a predetermined pressure in a condition where the polyester sheet 9 is in contact with the wafer 1 and the ring frame 7, the polyester sheet 9 is partially melted and thereby bonded to the wafer 1 and the ring frame 7. That is, by applying heat and pressure to the polyester sheet 9 in the condition where the polyester sheet 9 is in contact with the wafer 1 and the ring frame 7, the polyester sheet 9 can be bonded to the wafer 1 and the ring frame 7. Thusly, in the processing method for the wafer 1

according to this preferred embodiment, all of the wafer 1, the ring frame 7, and the polyester sheet 9 are united by thermocompression bonding as mentioned above, thereby forming the frame unit.

The steps of the processing method for the wafer 1 according to this preferred embodiment will now be described. Prior to uniting the wafer 1, the polyester sheet 9, and the ring frame 7, a polyester sheet providing step is performed by using a chuck table 2 having a holding surface 2a depicted in FIG. 2. FIG. 2 is a schematic perspective view depicting a manner of positioning the wafer 1 and the ring frame 7 on the holding surface 2a of the chuck table 2. That is, the polyester sheet providing step is performed on the holding surface 2a of the chuck table 2 as depicted in FIG. 2. The chuck table 2 has a circular porous member having a diameter larger than the outer diameter of the ring frame 7. The porous member constitutes a central upper portion of the chuck table 2. The porous member has an upper surface functioning as the holding surface 2a of the chuck table 2. A suction passage (not depicted) is formed in the chuck table 2, in which one end of the suction passage is connected to the porous member. Further, a vacuum source 2b (see FIG. 3) is connected to

the other end of the suction passage. The suction passage is provided with a selector 2c (see FIG. 3) for switching between an ON condition and an OFF condition. When the ON condition is established by the selector 2c, a vacuum produced by the vacuum source 2b is applied to a workpiece placed on the holding surface 2a of the chuck table 2, thereby holding the workpiece on the chuck table 2 under suction.

In the polyester sheet providing step, the wafer 1 and the ring frame 7 are first placed on the holding surface 2a of the chuck table 2 as depicted in FIG. 2. At this time, the front side 1a of the wafer 1 is oriented downward, and the front side 7b of the ring frame 7 is also oriented downward. In this condition, the wafer 1 is positioned in the inside opening 7a of the ring frame 7. Thereafter, as depicted in FIG. 3, the polyester sheet 9 is provided on the back side 1b (upper surface) of the wafer 1 and on the back side 7c (upper surface) of the ring frame 7. FIG. 3 is a schematic perspective view depicting a manner of providing the polyester sheet 9 on the wafer 1 and the ring frame 7. That is, as depicted in FIG. 3, the polyester sheet 9 is provided so as to fully cover the wafer 1 and the ring frame 7. In the polyester sheet providing step, the diameter of the polyester sheet

9 is set larger than the diameter of the holding surface 2a of the chuck table 2. Unless the diameter of the polyester sheet 9 is larger than the diameter of the holding surface 2a, there may arise a problem such that, when the vacuum from the vacuum source 2b is applied to the holding surface 2a of the chuck table 2 in a uniting step to be performed later, the vacuum may leak from any gap between the polyester sheet 9 and the holding surface 2a because the holding surface 2a is not fully covered with the polyester sheet 9, so that a pressure cannot be properly applied to the polyester sheet 9.

In the processing method for the wafer 1 according to this preferred embodiment, a uniting step is next performed in such a manner that the polyester sheet 9 is heated to unite the wafer 1 and the ring frame 7 through the polyester sheet 9 by thermocompression bonding. FIG. 4 is a schematic perspective view depicting the uniting step according to this preferred embodiment. As depicted in FIG. 4, the polyester sheet 9 transparent or translucent to visible light is provided so as to fully cover the wafer 1, the ring frame 7, and the holding surface 2a of the chuck table 2, which are all depicted by broken lines in FIG. 4. In the uniting step, the selector 2c is operated to establish the ON condition

where the vacuum source 2b is in communication with the porous member of the chuck table 2, i.e., the holding surface 2a of the chuck table 2, so that a vacuum produced by the vacuum source 2b is applied to the polyester sheet 9 provided on the chuck table 2. Accordingly, the polyester sheet 9 is brought into close contact with the wafer 1 and the ring frame 7 by the atmospheric pressure applied to the upper surface of the polyester sheet 9.

Thereafter, the polyester sheet 9 is heated in a condition where the polyester sheet 9 is sucked by the vacuum source 2b, thereby performing thermocompression bonding. In this preferred embodiment depicted in FIG. 4, for example, the heating of the polyester sheet 9 is effected by a heat gun 4 provided above the chuck table 2. The heat gun 4 includes heating means such as a heating wire and an air blowing mechanism such as a fan. Accordingly, the heat gun 4 can heat ambient air and blow the heated air. In a condition where the vacuum from the vacuum source 2b is applied to the polyester sheet 9, the heat gun 4 is operated to supply hot air 4a to the upper surface of the polyester sheet 9. Accordingly, when the polyester sheet 9 is heated to a predetermined temperature, the polyester sheet 9 is bonded to the wafer

1 and the ring frame 7 by thermocompression bonding.

Another method for heating the polyester sheet 9 may be adopted. For example, any member heated to a predetermined temperature may be pressed on the polyester sheet 9 against the wafer 1 and the ring frame 7. FIG. 5 is a schematic perspective view depicting such a modification of the uniting step. As depicted in FIG. 5, the polyester sheet 9 transparent or translucent to visible light is provided so as to fully cover the wafer 1, the ring frame 7, and the holding surface 2a of the chuck table 2, which are all depicted by broken lines in FIG. 5. In this modification depicted in FIG. 5, a heat roller 6 including a heat source is used. More specifically, the vacuum produced by the vacuum source 2b is first applied to the polyester sheet 9, so that the polyester sheet 9 is brought into close contact with the wafer 1 and the ring frame 7 by the atmospheric pressure applied to the upper surface of the polyester sheet 9.

Thereafter, the heat roller 6 is heated to a predetermined temperature, and next placed on the holding surface 2a of the chuck table 2 at one end lying on the outer circumference of the holding surface 2a as depicted in FIG. 5. Thereafter, the heat roller 6 is rotated about its axis to roll on the chuck table 2 through the

polyester sheet 9 from the above one end to another end diametrically opposite to the above one end. As a result, the polyester sheet 9 is bonded to the wafer 1 and the ring frame 7 by thermocompression bonding. In the case that a force for pressing the polyester sheet 9 is applied by the heat roller 6, the thermocompression bonding is effected at a pressure higher than atmospheric pressure. Preferably, a cylindrical surface of the heat roller 6 is coated with fluororesin. Further, the heat roller 6 may be replaced by any iron-like pressure member having a flat base plate and containing a heat source. In this case, the pressure member is heated to a predetermined temperature to thereby provide a hot plate, which is next pressed on the polyester sheet 9 held on the chuck table 2.

Still another method for heating the polyester sheet 9 may be adopted in the following manner. FIG. 6 is a schematic perspective view depicting such another modification of the uniting step. As depicted in FIG. 6, the polyester sheet 9 transparent or translucent to visible light is provided so as to fully cover the wafer 1, the ring frame 7, and the holding surface 2a of the chuck table 2, which are all depicted by broken lines in FIG. 6. In this modification depicted in FIG. 6, an

infrared lamp 8 is provided above the chuck table 2 to heat the polyester sheet 9. The infrared lamp 8 can apply infrared light 8a having an absorption wavelength to at least the material of the polyester sheet 9. Also in the modification depicted in FIG. 6, the vacuum produced by the vacuum source 2b is first applied to the polyester sheet 9, so that the polyester sheet 9 is brought into close contact with the wafer 1 and the ring frame 7 by the atmospheric pressure applied to the upper surface of the polyester sheet 9. Thereafter, the infrared lamp 8 is operated to apply the infrared light 8a to the polyester sheet 9, thereby heating the polyester sheet 9. As a result, the polyester sheet 9 is bonded to the wafer 1 and the ring frame 7 by thermocompression bonding.

When the polyester sheet 9 is heated to a temperature near its melting point by performing any one of the above methods, the polyester sheet 9 is bonded to the wafer 1 and the ring frame 7 by thermocompression bonding. After bonding the polyester sheet 9, the selector 2c is operated to establish the OFF condition where the communication between the porous member of the chuck table 2 and the vacuum source 2b is canceled. Accordingly, the suction holding by the chuck table 2 is canceled.

Thereafter, the polyester sheet 9 is circularly cut along the outer circumference of the ring frame 7 to remove an unwanted peripheral portion of the polyester sheet 9. FIG. 7A is a schematic perspective view depicting a manner of cutting the polyester sheet 9. As depicted in FIG. 7A, a disc-shaped (annular) cutter 10 is used to cut the polyester sheet 9. The cutter 10 has a central through hole 10a in which a rotating shaft 10b is fitted. Accordingly, the cutter 10 is rotatable about the axis of the rotating shaft 10b. First, the cutter 10 is positioned above the ring frame 7. At this time, the rotating shaft 10b is set so as to extend in the radial direction of the chuck table 2. Thereafter, the cutter 10 is lowered until the outer circumference (cutting edge) of the cutter 10 comes into contact with the polyester sheet 9 placed on the ring frame 7. That is, the polyester sheet 9 is caught between the cutter 10 and the ring frame 7, so that the polyester sheet 9 is cut by the cutter 10 to form a cut mark 9a. Further, the cutter 10 is rolled on the polyester sheet 9 along a circular line set between the inner circumference of the ring frame 7 (i.e., the periphery of the inside opening 7a of the ring frame 7) and the outer circumference of the ring frame 7, thereby circularly forming the cut mark 9a along the

above circular line. As a result, a predetermined central portion of the polyester sheet 9 is surrounded by the circular cut mark 9a. Thereafter, a remaining peripheral portion of the polyester sheet 9 outside the circular cut mark 9a is removed. That is, an unwanted peripheral portion of the polyester sheet 9 including an outermost peripheral portion outside the outer circumference of the ring frame 7 can be removed.

The cutter 10 may be replaced by an ultrasonic cutter for cutting the polyester sheet 9. Further, a vibration source for vibrating the cutter 10 at a frequency in an ultrasonic band may be connected to the cutter 10. Further, in cutting the polyester sheet 9, the polyester sheet 9 may be cooled to be hardened in order to facilitate the cutting operation. By cutting the polyester sheet 9 as mentioned above, a frame unit 11 depicted in FIG. 7B is formed, in which the frame unit 11 is composed of the wafer 1, the ring frame 7, and the polyester sheet 9 united together. That is, the wafer 1 and the ring frame 7 are united with each other through the polyester sheet 9 to form the frame unit 11 as depicted in FIG. 7B. FIG. 7B is a schematic perspective view of the frame unit 11 in a condition where the front side 1a of the wafer 1 and the front side 7b of the ring

frame 7 are exposed upward.

In performing the thermocompression bonding as mentioned above, the polyester sheet 9 is heated preferably to a temperature lower than or equal to the melting point of the polyester sheet 9. If the heating temperature is higher than the melting point of the polyester sheet 9, there is a possibility that the polyester sheet 9 may be melted to such an extent that the shape of the polyester sheet 9 cannot be maintained. Further, the polyester sheet 9 is heated preferably to a temperature higher than or equal to the softening point of the polyester sheet 9. If the heating temperature is lower than the softening point of the polyester sheet 9, the thermocompression bonding cannot be properly performed. Accordingly, the polyester sheet 9 is heated preferably to a temperature higher than or equal to the softening point of the polyester sheet 9 and lower than or equal to the melting point of the polyester sheet 9. Further, there is a case that the softening point of the polyester sheet 9 may be unclear. To cope with such a case, in performing the thermocompression bonding, the polyester sheet 9 is heated preferably to a temperature higher than or equal to a preset temperature and lower than or equal to the melting point of the polyester sheet

9, the preset temperature being lower by 20°C than the melting point of the polyester sheet 9.

In the case that the polyester sheet 9 is a polyethylene terephthalate sheet, for example, the heating temperature in the uniting step is preferably set in the range of 250°C to 270°C. Further, in the case that the polyester sheet 9 is a polyethylene naphthalate sheet, the heating temperature in the uniting step is preferably set in the range of 160°C to 180°C.

The heating temperature is defined herein as the temperature of the polyester sheet 9 to be heated in performing the uniting step. As the heat sources included in the heat gun 4, the heat roller 6, and the infrared lamp 8 mentioned above, some kind of heat source capable of setting an output temperature has been put into practical use. However, even when such a heat source is used to heat the polyester sheet 9, the temperature of the polyester sheet 9 does not reach the output temperature set above in some case. To cope with such a case, the output temperature of the heat source may be set to a temperature higher than the melting point of the polyester sheet 9 in order to heat the polyester sheet 9 to a predetermined temperature.

After performing the uniting step mentioned above,

a dividing step is performed in such a manner that the wafer 1 in the condition of the frame unit 11 is cut by a cutting blade to obtain individual device chips. The dividing step is performed by using a cutting apparatus 12 depicted in FIG. 8 in this preferred embodiment. FIG. 8 is a schematic perspective view depicting the dividing step. As depicted in FIG. 8, the cutting apparatus 12 includes a cutting unit 14 for cutting a workpiece and a chuck table (not depicted) for holding the workpiece. The cutting unit 14 includes a cutting blade 18 having an annular abrasive portion (cutting edge) for cutting the workpiece and a spindle (not depicted) for supporting the cutting blade 18 so as to rotate the cutting blade 18. The cutting blade 18 has a central through hole for mounting the front end of the spindle. The cutting blade 18 is composed of an annular base (hub) having the above-mentioned central through hole and an annular abrasive portion provided along the outer circumference of the annular base. The spindle is rotatably supported in a spindle housing 16, and the base end of the spindle is connected to a spindle motor (not depicted) accommodated in the spindle housing 16. Accordingly, the cutting blade 18 can be rotated by operating the spindle motor. The chuck table has an upper surface as a holding surface for

holding the wafer 1.

When the workpiece is cut by the cutting blade 18, heat is generated by the friction between the cutting blade 18 and the workpiece. Further, when the workpiece is cut by the cutting blade 18, cutting dust is generated from the workpiece. To remove such heat and cutting dust due to the cutting of the workpiece, cutting water such as pure water is supplied to the cutting blade 18 and the workpiece during the cutting of the workpiece.

Accordingly, the cutting unit 14 includes a pair of cutting water nozzles 20 for supplying cutting water to the cutting blade 18 and the workpiece, in which the pair of cutting water nozzles 20 are located so as to face both sides of the cutting blade 18. In FIG. 8, only one of the two cutting water nozzles 20 is depicted.

In cutting the wafer 1, the frame unit 11 is placed on the chuck table in the condition where the front side 1a of the wafer 1 is exposed upward. Accordingly, the wafer 1 is held through the polyester sheet 9 on the chuck table. Thereafter, the chuck table is rotated to make the division lines 3 extending in the first direction on the front side 1a of the wafer 1 parallel to a feeding direction in the cutting apparatus 12. Further, the chuck table and the cutting unit 14 are relatively

moved in a direction perpendicular to the feeding direction in a horizontal plane to thereby position the cutting blade 18 directly above an extension of a predetermined one of the division lines 3 extending in the first direction.

Thereafter, the spindle is rotated to thereby rotate the cutting blade 18. Thereafter, the cutting unit 14 is lowered to a predetermined height, and the chuck table and the cutting unit 14 are relatively moved in the feeding direction parallel to the upper surface of the chuck table. Accordingly, the abrasive portion of the cutting blade 18 being rotated comes into contact with the wafer 1 to thereby cut the wafer 1 along the predetermined division line 3 in the feeding direction. As a result, a cut mark 3a (groove) is formed along the predetermined division line 3 so as to fully cut the wafer 1 and the polyester sheet 9. After cutting the wafer 1 and the polyester sheet 9 along the predetermined division line 3, the chuck table and the cutting unit 14 are relatively moved in an indexing direction perpendicular to the feeding direction by the pitch of the division lines 3. Thereafter, the above cutting operation is similarly performed along the next division line 3 adjacent to the above predetermined division line

3. After similarly performing the cutting operation along all of the other division lines 3 extending in the first direction, the chuck table is rotated 90 degrees about its axis perpendicular to the holding surface, so that the other division lines 3 extending in the second direction perpendicular to the first direction become parallel to the feeding direction. Thereafter, the above cutting operation is similarly performed along all the other division lines 3 extending in the second direction. After performing the cutting operation along all the other division lines 3 extending in the second direction, the dividing step is finished.

The cutting apparatus 12 may include a cleaning unit (not depicted) provided in the vicinity of the cutting unit 14. That is, the wafer 1 cut by the cutting unit 14 may be transferred to the cleaning unit and then may be cleaned by the cleaning unit. For example, the cleaning unit includes a cleaning table having a holding surface for holding the frame unit 11 and a cleaning water nozzle adapted to be horizontally moved in opposite directions above the frame unit 11 held on the holding surface of the cleaning table. The cleaning water nozzle functions to supply cleaning water such as pure water to the wafer 1. The cleaning table is rotatable about its

axis perpendicular to the holding surface. In operation, the cleaning table is rotated about its axis and at the same time the cleaning water is supplied from the cleaning water nozzle to the wafer 1. During this supply of the cleaning water, the cleaning water nozzle is horizontally moved in opposite directions along a path passing through the position directly above the center of the holding surface of the cleaning table. Accordingly, the entire surface of the front side 1a of the wafer 1 can be cleaned by the cleaning water.

By performing the dividing step as mentioned above, the wafer 1 is divided into the individual device chips, which are still supported to the polyester sheet 9. In cutting the wafer 1, the cutting unit 14 is positioned at a predetermined height such that the lower end of the cutting blade 18 is lower in level than the back side 1b of the wafer 1, in order to reliably divide the wafer 1. Accordingly, when the wafer 1 is cut by the cutting blade 18, the polyester sheet 9 bonded to the back side 1b of the wafer 1 is also cut by the cutting blade 18, so that cutting dust due to the polyester sheet 9 is generated. In the case that an adhesive tape having an adhesive layer is used in the frame unit 11 in place of the polyester sheet 9, cutting dust due to the adhesive layer

of the adhesive tape is generated. In this case, the cutting dust is taken into the cleaning water supplied from the cutting water nozzles 20, and then diffused on the front side 1a of the wafer 1. The cutting dust due to the adhesive layer is apt to adhere again to the front side of each device 5. Furthermore, it is not easy to remove the cutting dust adhered to the front side of each device 5 in a cleaning step of cleaning the wafer 1 after the dividing step. When the cutting dust due to the adhesive layer adheres to each device 5, there arises a problem such that each device chip divided from the wafer 1 may be degraded in quality.

To the contrary, the processing method for the wafer 1 according to this preferred embodiment has the following advantage. In this preferred embodiment, the polyester sheet 9 having no adhesive layer is used in the frame unit 11 in place of an adhesive tape having an adhesive layer. Although the cutting dust due to the polyester sheet 9 is generated and then diffused on the front side 1a of the wafer 1 as being taken into the cleaning water, this cutting dust does not adhere to the wafer 1, but it is reliably removed in the subsequent cleaning step. Accordingly, it is possible to suppress a degradation in quality of each device chip due to the

cutting dust.

After performing the dividing step or the cleaning step, a pickup step is performed to pick up each device chip from the polyester sheet 9. The pickup step is performed by using a pickup apparatus 22 depicted in FIG. 9. FIG. 9 is a schematic perspective view depicting a manner of loading the frame unit 11 to the pickup apparatus 22. As depicted in FIG. 9, the pickup apparatus 22 includes a cylindrical drum 24 and a frame holding unit 26 having a frame support table 30 provided around the cylindrical drum 24. The cylindrical drum 24 has an inner diameter larger than the diameter of the wafer 1 and an outer diameter smaller than the inner diameter of the ring frame 7 (the diameter of the inside opening 7a). The frame support table 30 of the frame holding unit 26 is an annular table having a circular inside opening larger in diameter than the drum 24. That is, the frame support table 30 has an inner diameter larger than the outer diameter of the drum 24. Further, the frame support table 30 has an outer diameter larger than the outer diameter of the ring frame 7. The inner diameter of the frame support table 30 is substantially equal to the inner diameter of the ring frame 7. The frame support table 30 has an upper surface as a supporting surface for

supporting the ring frame 7 thereon through the polyester sheet 9. Initially, the height of the upper surface of the frame support table 30 is set equal to the height of the upper end of the drum 24 (see FIG. 10A). Further, the upper end portion of the drum 24 is surrounded by the inner circumference of the ring frame 7 in this initial stage.

A plurality of clamps 28 are provided on the outer circumference of the frame support table 30. Each clamp 28 functions to hold the ring frame 7 supported on the frame support table 30. That is, when the ring frame 7 of the frame unit 11 is placed through the polyester sheet 9 on the frame support table 30 and then held by each clamp 28, the frame unit 11 can be fixed to the frame support table 30. The frame support table 30 is supported by a plurality of rods 32 extending in a vertical direction. That is, each rod 32 is connected at its upper end to the lower surface of the frame support table 30. An air cylinder 34 for vertically moving each rod 32 is connected to the lower end of each rod 32. More specifically, the lower end of each rod 32 is connected to a piston (not depicted) movably accommodated in the air cylinder 34. Each air cylinder 34 is supported to a disc-shaped base 36. That is, the lower end of each air

cylinder 34 is connected to the upper surface of the disc-shaped base 36. Accordingly, when each air cylinder 34 is operated in the initial stage, the frame support table 30 is lowered with respect to the drum 24 fixed in position.

Further, a pushup mechanism 38 for pushing up each device chip supported to the polyester sheet 9 is provided inside the drum 24. That is, each device chip is adapted to be pushed up through the polyester sheet 9 by the pushup mechanism 38 located below the polyester sheet 9. Further, a collet 40 (see FIG. 10B) capable of holding each device chip under suction is provided above the drum 24. Both the pushup mechanism 38 and the collet 40 are movable in a horizontal direction parallel to the upper surface of the frame support table 30. The collet 40 is connected through a selector 40b (see FIG. 10B) to a vacuum source 40a (see FIG. 10B).

In the pickup step, each air cylinder 34 in the pickup apparatus 22 is first operated to adjust the height of the frame support table 30 such that the height of the upper end of the drum 24 becomes equal to the height of the upper surface of the frame support table 30. Thereafter, the frame unit 11 transferred from the cutting apparatus 12 is placed on the drum 24 and the

frame support table 30 in the pickup apparatus 22 in a condition where the front side 1a of the wafer 1 of the frame unit 11 is oriented upward. Thereafter, each clamp 28 is operated to fix the ring frame 7 of the frame unit 11 to the upper surface of the frame support table 30. FIG. 10A is a schematic sectional view depicting a standby condition where the frame unit 11 is fixed to the frame support table 30 set at the initial position. At this time, the plural cut marks 3a have already been formed in the wafer 1 in the dividing step, so that the wafer 1 has already been divided into a plurality of individual device chips 1c (see FIG. 10B).

Thereafter, each air cylinder 34 is operated to lower the frame support table 30 of the frame holding unit 26 with respect to the drum 24. As a result, the polyester sheet 9 fixed to the frame holding unit 26 by each clamp 28 is expanded radially outward as depicted in FIG. 10B. FIG. 10B is a schematic sectional view depicting a working condition where the frame support table 30 holding the ring frame 7 with the polyester sheet 9 is lowered to expand the polyester sheet 9. When the polyester sheet 9 is expanded radially outward as mentioned above, the spacing between any adjacent ones of the device chips 1c supported to the polyester sheet 9 is

increased as depicted in FIG. 10B. Accordingly, the contact between the adjacent device chips 1c can be suppressed, and each device chip 1c can be easily picked up. Thereafter, a target one of the device chips 1c is decided, and the pushup mechanism 38 is next moved to a position directly below this target device chip 1c as depicted in FIG. 10B. Furthermore, the collet 40 is also moved to a position directly above this target device chip 1c as depicted in FIG. 10B. Thereafter, the pushup mechanism 38 is operated to push up the target device chip 1c through the polyester sheet 9. Further, the selector 40b is operated to make the collet 40 communicate with the vacuum source 40a. As a result, the target device chip 1c is held under suction by the collet 40 and thereby picked up from the polyester sheet 9. Such a pickup operation is similarly performed for all the other device chips 1c. Thereafter, each device chip 1c picked up is mounted on a predetermined wiring substrate or the like for actual use.

In the wafer processing method according to this preferred embodiment mentioned above, the frame unit 11 including the wafer 1 can be formed without using an adhesive tape having an adhesive layer. Accordingly, in cutting the wafer 1, cutting dust due to the adhesive

layer of the adhesive tape is not generated, so that this cutting dust does not adhere to each device chip 1c. As a result, there is no possibility that each device chip 1c may be degraded in quality.

The present invention is not limited to the above preferred embodiment, but various modifications may be made within the scope of the present invention. For example, while the polyester sheet 9 is selected from a polyethylene terephthalate sheet and a polyethylene naphthalate sheet in the above preferred embodiment, this is merely illustrative. That is, the polyester sheet usable in the present invention may be formed of any other materials (polyesters) such as polytrimethylene terephthalate, polybutylene terephthalate, or polybutylene naphthalate.

The present invention is not limited to the details of the above described preferred embodiment. The scope of the invention is defined by the appended claims and all changes and modifications as fall within the equivalence of the scope of the claims are therefore to be embraced by the invention.

WHAT IS CLAIMED IS:

1. A wafer processing method for dividing a wafer along a plurality of division lines to obtain a plurality of individual device chips, the division lines being formed on the front side of the wafer to thereby define a plurality of separate regions where a plurality of devices are individually formed, the wafer processing method comprising:

a ring frame preparing step of preparing a ring frame having an inside opening for accommodating the wafer;

a polyester sheet providing step of positioning the wafer in the inside opening of the ring frame and providing a polyester sheet on a back side of the wafer and on a back side of the ring frame, without an adhesive provided between the polyester sheet and the back side of the ring frame, such that the polyester sheet is in direct contact with the back side of the ring frame;

a uniting step of heating the polyester sheet while applying a pressure to the polyester sheet after performing the polyester sheet providing step, thereby uniting the wafer and the ring frame through the polyester sheet by thermocompression bonding to form a frame unit in a condition where the front side of the

wafer and the front side of the ring frame are exposed;

a dividing step of cutting the wafer along each division line by using a cutting apparatus including a rotatable cutting blade after performing the uniting step, thereby dividing the wafer into the individual device chips; and

a pickup step of picking up each device chip from the polyester sheet after performing the dividing step.

2. The wafer processing method according to claim 1, wherein the uniting step includes a step of applying infrared light to the polyester sheet, thereby performing the thermocompression bonding.

3. The wafer processing method according to claim 1, wherein the polyester sheet is larger in size than the ring frame, and the uniting step includes an additional step of cutting the polyester sheet after heating the polyester sheet, thereby removing a part of the polyester sheet outside an outer circumference of the ring frame.

4. The wafer processing method according to claim 1, wherein the pickup step includes a first step of expanding the polyester sheet to thereby increase a spacing between any adjacent ones of the device chips and a second step of pushing up each device chip through the polyester sheet after performing the first step.

5. The wafer processing method according to claim 1, wherein the polyester sheet is formed of a material selected from the group consisting of polyethylene terephthalate and polyethylene naphthalate.

6. The wafer processing method according to claim 5, wherein the polyester sheet is formed of polyethylene terephthalate, and the polyester sheet is heated in the range of 250° C. to 270° C. in the uniting step.

7. The wafer processing method according to claim 5, wherein the polyester sheet is formed of polyethylene naphthalate, and the polyester sheet is heated in the range of 160° C. to 180° C. in the uniting step.

8. The wafer processing method according to claim 1, wherein the wafer is formed of a material selected from the group consisting of silicon, gallium nitride, gallium arsenide, and glass.

9. The wafer processing method according to claim 1, wherein the uniting step is performed while the ring frame, with the polyester sheet provided thereon, is seated on a holding surface of a porous member of a chuck table, and further wherein a vacuum from a vacuum source is applied to the holding surface of the porous member such that the polyester sheet is sucked by the vacuum source towards the holding surface, with the ring frame

therebetween.

10. The wafer processing method according to claim 9, wherein the diameter of the polyester sheet is larger than the diameter of the holding surface of the porous member.

11. The wafer processing method according to claim 3, wherein the step of cutting the polyester sheet results in a cut mark that is between an inner circumference of the ring frame and the outer circumference of the ring frame.

12. The wafer processing method according to claim 3, wherein the step of cutting the polyester sheet involves rolling a cutter on the polyester sheets along a circular line to produce a circular cut mark that is between an inner circumference of the ring frame and the outer circumference of the ring frame.