

Alkenyl(perfluoroalkyl)phosphinic acids

The invention relates to alkenyl(perfluoroalkyl)phosphinic acids, to the preparation and intermediates thereof, to the use thereof as monomers for the preparation of oligomers and/or polymers, to the corresponding oligomers/polymers, and to the use thereof as ion exchangers, catalysts, extraction media and the corresponding salts.

A multiplicity of symmetrical bis(perfluoroalkyl)phosphinic acids is known for a wide variety of uses. Peppard, D.F. et al., *Journal of Inorganic and Nuclear Chemistry* 1965, 27(9), 2065-73, describe, for example, the use of bis(n-octyl)phosphinic acid as selective extractant for metallic cations.

The only examples of classes of asymmetrical phosphinic acids containing perfluorinated groups are aryl(perfluoroalkyl)phosphinic acids, $R^F(\text{aryl})\text{-P}(\text{O})\text{OH}$ (aryl = 3- $\text{C}_6\text{H}_4\text{F}$, 4- $\text{C}_6\text{H}_4\text{F}$ or C_6H_5 and $R^F = \text{C}_3\text{F}_7$ [L. M. Yagupol'skii, N. V. Pavlenko, N. V. Ignat'ev, G. I. Matyushecheva, V. Y. Semeni, *J. Gen. Chem. U.S.S.R. Engl. Transl.* **1984**, 54, 297-302] or aryl = C_6H_5 and $R^F = \text{C}_n\text{F}_{2n+1}$ (n = 2, 4, 6, or 8) [A. I. Hosein, A. J. M. Caffyn, *Dalton Trans.* **2012**, 41, 13504 – 13508]) or asymmetrical phosphinic acids containing two different perfluoroalkyl groups [WO 2003/082884].

A multistep procedure has been used for the preparation of aryl(perfluoroalkyl)phosphinic acids. Aryl(heptafluoropropyl)phosphinic acids have been obtained by hydrolysis of aryl[bis(heptafluoropropyl)]phosphine oxides using aqueous sodium carbonate solution. The aryl[bis(heptafluoropropyl)]phosphine oxides themselves have been prepared using a multistep procedure beginning with the reaction of bis(heptafluoropropyl)chlorophosphine, $(\text{C}_3\text{F}_7)_2\text{PCl}$ (a non-commercially available substance), with arylmagnesium bromides, followed by chlorination to give $\text{XC}_6\text{H}_4(\text{C}_3\text{F}_7)_2\text{PCl}_2$ and hydrolysis using formic acid to give $\text{XC}_6\text{H}_4(\text{C}_3\text{F}_7)_2\text{P}=\text{O}$ (X = H or F). This

complex procedure is not suitable for the preparation of large amounts of aryl(perfluoroalkyl)phosphinic acids.

The phosphine oxides of the type $R(CF_3)_2P=O$ with mixed substituents have been obtained by an Arbuzov-type rearrangement of bis(trifluoromethyl)phosphinous acid esters, $(CF_3)_2P-OR$, under the action of CH_3I [J. F. Griffiths, A. B. Burg, *J. Am. Chem. Soc.* **1962**, *84*, 3442 – 3450].

WO 2003/082884 describes the preparation of asymmetrical bis(perfluoroalkyl)phosphinic acids by reaction of a perfluoroalkylphosphonic acid dichloride ($R_iP(O)Cl_2$) with perfluoroalkylmagnesium bromide to give an asymmetrically substituted bis(perfluoroalkyl)phosphinic acid chloride and subsequent hydrolysis to give the acid.

Corresponding asymmetrical alkenylperfluoroalkylphosphinic acids are, by contrast, not known compounds, even though unfluorinated asymmetrical phosphine oxides and asymmetrical dialkylphosphinic acids and dialkylphosphinic acid derivatives are typical reagents (ligands) for asymmetrical synthesis [L. D. Quin, G. S. Quin, *A Guide To Organophosphorus Chemistry*, Wiley-Interscience, **2000**, 282 – 306].


US 4,647,438 describes a process for the liquid-liquid extraction of rare-earth metals from aqueous solutions by an extraction medium comprising an organic phosphinic acid of the formula $R_1(R_2)P(O)(OX)$, where R_1 and R_2 may be identical or different and denote unsubstituted or substituted alkyl, cycloalkyl, alkoxyalkyl or alkylcycloalkyl and X denotes H or a cation. Possible substituents of the alkyl group are described as being OH or halogen atoms, for example F or Cl. R_1 and R_2 are preferably described as linear or branched alkyl group having at least 6 C atoms or as cycloalkyl group having at least 6 C atoms. An asymmetrical phosphinic acid mentioned is 2,4,4-trimethylpentylcyclohexylphosphinic acid. No fluorinated or perfluorinated phosphinic acids are described. In the examples, bis(2,4,4-trimethylpentyl)phosphinic acid is used.

US 7,691,478 describes thin films comprising, for example, a phosphinic acid, where the phosphinic acid is bonded to the substrate via the acid function. Diphenylphosphinic acid, phenylphosphinic acid and bis(perfluoroheptyl)phosphinic acid are described as representative. In Example 1, no phosphinic acid is used.

The object of the invention was the broadening of the range available to the person skilled in the art of polymerisable monomers which are suitable for the preparation of oligomers and polymers, and which have the functionality of a strong Brønsted acid. Both the monomers and also the corresponding oligomers/polymers are therefore suitable as ion exchanger or as extraction medium or as Brønsted acid catalysts and can be combined with a suitable support material. Further advantages of the present invention arise for the person skilled in the art from the following disclosure.

Surprisingly, the alkenyl(perfluoroalkyl)phosphinic acids of the formula I according to the invention achieve the object set in an excellent manner.

The invention accordingly relates firstly to the compounds of the formula I,



where

- R_f denotes a straight-chain or branched perfluoroalkyl group having 1 to 12 C atoms,
 A denotes H, F, Cl or a straight-chain or branched alkyl group having 1 to 12 C atoms,
 B denotes $-(\text{CR}_1\text{R}_2)_n-$, $[-(\text{CR}_1\text{R}_2)_m-\text{O}-(\text{CR}_1\text{R}_2)_{m1}-]_{m2}$, arylene or substituted arylene,
 X denotes H, F and/or Cl,

n denotes an integer from 0 to 20,

m denotes an integer from 1 to 20,

m₁ denotes an integer from 0 to 8,

m₂ denotes an integer from 1 to 20 and

5 R₁ or R₂ each, independently of one another, denote H, F, Cl or a straight-chain or branched alkyl group having 1 to 12 C atoms.

R₁ and R₂ may be identical or different. R₁ and R₂ are particularly preferably identical.

10

Straight-chain or branched perfluoroalkyl groups having 1 to 12 C atoms conform to the formula C_mF_{2m+1} where m = 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11 or 12. Preferred perfluoroalkyl groups are straight-chain or branched perfluoroalkyl groups having 1 to 8 C atoms.

15

The substituent R_f preferably stands for trifluoromethyl, pentafluoroethyl, heptafluoropropyl, straight-chain or branched nonafluorobutyl, straight-chain perfluorohexyl or straight-chain perfluorooctyl. The substituent R_f particularly preferably stands for pentafluoroethyl, heptafluoropropyl, linear or branched nonafluorobutyl. The substituent R_f very particularly preferably

20

Straight-chain or branched alkyl groups having 1 to 4, 1 to 6, 1 to 8 or 1 to 12 C atoms conform to the formula C_pH_{2p+1} where p = 1, 2, 3 or 4, or 1, 2, 3, 4, 5 or 6, or 1, 2, 3, 4, 5, 6, 7 or 8, or 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11 or 12, for example methyl, ethyl, i-propyl, propyl, butyl, i-butyl or tert-butyl, further-

25

more also pentyl, 1-, 2- or 3-methylbutyl, 1,1-, 1,2- or 2,2-dimethylpropyl, 1-ethylpropyl or hexyl, heptyl, octyl, furthermore also nonyl, decyl, undecyl or dodecyl.

If an alkyl group is not specified in greater detail, it is a straight-chain alkyl group.

30

An unsubstituted or substituted arylene is derived from an aryl group having 6 to 12 C atoms, for example from phenyl, naphthyl or anthryl. The unsubstituted or substituted arylene preferably corresponds to unsubstituted or substituted phenylene.

5

Substituted arylene denotes arylene which is substituted by C₁- to C₆-alkyl, C₂- to C₆-alkenyl, F, Cl, Br, OH, unfluorinated, partially fluorinated or perfluorinated C₁-C₆-alkoxy, where the substituents are each selected independently of one another. A preferred substituted arylene is tetrafluorophenylene, tetrachlorophenylene or trifluoromethylphenylene.

10

The variable n preferably stands for an integer from 1 to 12.

The variable m preferably stands for an integer from 1 to 12.

The variable m₁ preferably stands for an integer from 1 to 3, particularly preferably for 2.

15

The variable m₂ preferably stands for an integer from 1 to 3.

R₁ and/or R₂ preferably stand for H, F or Cl.

20

In compounds of the formula I, R_f is preferably a straight-chain or branched perfluoroalkyl group having 1 to 8 C atoms.

Accordingly, the invention preferably relates to compounds of the formula I, as described above, where R_f denotes a straight-chain or branched perfluoroalkyl group having 1 to 8 C atoms. R_f is particularly preferably a straight-chain or branched perfluoroalkyl group having 1 to 4 C atoms. R_f is very particularly preferably pentafluoroethyl.

25

In compounds of the formula I, B is preferably -(CR₁R₂)_n-, arylene or substituted arylene, where R₁, R₂, arylene and substituted arylene have a meaning indicated above.

30

Accordingly, the invention preferably relates to compounds of the formula I, as described above or described as preferred, where B denotes $-(CR_1R_2)_n-$, arylene or substituted arylene and where R_1 , R_2 , arylene and substituted arylene have a meaning indicated above.

5

In an embodiment of the invention, compounds of the formula I are preferred if A and X have the same meaning. In this embodiment, A and X are preferably H, F or Cl, particularly preferably H or F, very particularly preferably F.

10

Accordingly, the invention preferably relates to compounds of the formula I, as described above or described as preferred, where A and X are identical. In this embodiment, if A and X are identical, B is preferably $-(CR_1R_2)_n-$, arylene or substituted arylene, as described above. In this embodiment, R_1 and R_2 are preferably identical and correspond to H, F or Cl, particularly preferably H or F, very particularly preferably H. If A and X are preferably H and B denotes $-(CR_1R_2)_n-$, R_1 and R_2 are preferably H. If A and X preferably F and B denotes $-(CR_1R_2)_n-$, R_1 and R_2 are preferably F or H, particularly preferably H. If A and X are preferably H and B denotes arylene, the corresponding arylene is preferably employed in unsubstituted form. If A and X are preferably F and B denotes arylene, the corresponding F-substituted or unsubstituted arylene is preferably employed. If A and X are preferably Cl and B denotes arylene, the corresponding unsubstituted arylene is preferably employed.

15

20

25

In another embodiment of the invention, compounds of the formula I are preferred if A corresponds to a straight-chain or branched alkyl group having 1 to 12 C atoms.

Accordingly, the invention likewise relates to compounds of the formula I, as described above or described as preferred, where A denotes a straight-chain or branched alkyl group having 1 to 12 C atoms. In this embodiment, A and X are not identical.

30

In this embodiment, if A and X are not identical, A is preferably methyl or ethyl and X, R₁ and R₂ are preferably, independently of one another, H, F or Cl. In this embodiment, A is particularly preferably methyl and X, R₁ and R₂ are particularly preferably H, F or Cl, very particularly preferably H or F and
5 very particularly preferably H. In this embodiment, B is preferably
-(CR₁R₂)_n-, arylene or substituted arylene, as described above. If X is preferably H and B denotes arylene, the corresponding arylene is preferably employed in unsubstituted form. If X is preferably F and B denotes arylene, the corresponding F-substituted or unsubstituted arylene is preferably
10 employed. If X is preferably Cl and B denotes arylene, the corresponding unsubstituted arylene is preferably employed.


In an embodiment of the invention, particular preference is given to compounds of the formula I, as described above, in which B denotes
15 -(CR₁R₂)_n-. In particularly preferred compounds of this embodiment, the variable n stands for 1, 2, 4 or 9.

Very particularly preferred compounds of the formula I are
allylpentafluoroethylphosphinic acid,
20 allylnonafluorobutylphosphinic acid,
pentafluoroethyl(but-3-en-1-yl)phosphinic acid,
nonafluorobutyl(but-3-en-1-yl)phosphinic acid,
pentafluoroethyl(undec-10-en-1-yl)phosphinic acid,
nonafluorobutyl(undec-10-en-1-yl)phosphinic acid,
25 pentafluoroethyl-4-styrylphosphinic acid,
nonafluorobutyl-4-styrylphosphinic acid,
pentafluoroethyl(3,4,4-trifluorobut-3-en-1-yl)phosphinic acid
nonafluorobutyl(3,4,4-trifluorobut-3-en-1-yl)phosphinic acid,
nonafluorobutyl(1,2,2-trifluorovinyl)phosphinic acid,
30 pentafluoroethyl(1,2,2-trifluorovinyl)phosphinic acid.


The present invention likewise relates to processes for the preparation of compounds of the formula I, as described above or described as preferred.

5 The invention therefore relates to a process for the preparation of compounds of the formula I, as described above or described as preferred, characterised in that

a) a compound of the formula II




10 where R_f , A, B and X have one of the meanings indicated above or indicated as preferred and x denotes 1 or 2, is hydrolysed, giving an intermediate compound of the formula IIIa as intermediate,



15

where R_f , A, B and X have a meaning indicated in formula II, or


b) a compound of the formula II



20

where R_f , A, B and X have one of the meanings indicated above or indicated as preferred and x denotes 1, 2 or 3, is reacted with a hexaalkyldisiloxane without or in the presence of a catalytic amount of water, where the alkyl groups of the hexaalkyldisiloxane each, independently of one another, denote a straight-chain or branched alkyl group having 1 to 4 C atoms, giving an intermediate compound of the formula III,

25



30

where R_f , A, B and X have a meaning indicated in formula II, which is subsequently hydrolysed.

The compounds of the formula II, as described above, can be prepared, for example, by reacting a phosphorane, selected from the group difluorotris-(perfluoroalkyl)phosphorane, trifluorobis(perfluoroalkyl)phosphorane or tetra-
5 fluoro(perfluoroalkyl)phosphorane, under inert-gas conditions with an alkenylmagnesium bromide ($A-CX=CX-B-MgBr$) or an alkenylmagnesium chloride ($A-CX=CX-B-MgCl$) or an alkenyllithium ($A-CX=CX-B-Li$) or with di(alkenyl)zinc [$(A-CX=CX-B)_2Zn$] or
10 with alkenylzinc chloride ($A-CX=CX-B-ZnCl$).

The perfluoroalkyl group, A, X and B in the formulae indicated have a meaning as described above for the formula I.

15 The choice of the organic metal compound required depends on the reactivity, stability and steric hindrance of the alkenyl group $A-CX=CX-B-$ used, as described above.

Inert-gas conditions in the sense of the invention mean that working is carried out in the presence of an inert gas, for example nitrogen, dried nitrogen, dried argon or argon.

20 The synthesis of the phosphoranes via electrochemical fluorination is described, for example, in WO 00/21969. Alternatively, for example, a bis(perfluoroalkyl)trifluorophosphorane can be prepared by reaction of tetrafluorobis(perfluoroalkyl)phosphate salts with SbF_5 or $SbCl_5$, as
25 described in WO 2005/049628.



Hexaalkyldisiloxanes are in some cases commercially available or can be prepared analogously by known processes. Suitable alkyl groups are preferably identical and are preferably selected from methyl, ethyl, propyl or
30 butyl. Hexamethyldisiloxane is preferably used.

The hydrolysis of the compounds of the formula II, as described above as process variant a), is preferably carried out at a temperature of 0°C to 100°C. The reaction may be exothermic. The final temperature for complete reaction is preferably 60 to 80°C. The speed of the hydrolysis is dependent on the length of the perfluoroalkyl group R_f and the steric size of the alkenyl group -B-CX=CXA in the phosphorane of the formula II.

The alternative reaction of the compounds of the formula II, as described above, with a hexaalkyldisiloxane, in process variant b) as described above, is preferably carried out without solvent at temperatures of 0°C to 120°C, particularly preferably at 80°C to 100°C, if X denotes H and particularly preferably at 0°C to 60°C if X denotes F.


Alternatively, the reaction can also be carried out in the presence of a solvent. Suitable solvents are n-hexane, 1,4-dioxane, benzene or toluene.

Both in the case of hydrolysis and also in the case of reaction with a hexaalkyldisiloxane to give the compounds of the formula I, the corresponding alkenylbis(perfluoroalkyl)phosphine oxides of the formula III or IIIa,



where R_f , A, B and X have a meaning indicated above or a meaning preferably indicated, form as intermediate compounds.

Owing to its reactivity, the compound of the formula III formed as intermediate is generally not isolated. However, isolation is possible if it desired to characterise the specific compound of the formula IIIa,




5 Suitable measures would be extraction and/or distillative separation.

In process variant b), the intermediate compound of the formula III formed can, if this conforms to the formula IIIa, as described above, be isolated and purified before the further hydrolysis is carried out. However, this is likewise
 10 not absolutely necessary. Process variant b) can also be carried out as a one-pot variant in which the two reaction steps are carried out successively.

The hydrolysis of the compounds of the formula III or of the formula IIIa, as described above, is preferably carried out at temperatures of 30 to 100°C, particularly preferably at 40°C to 60°C, with a reaction duration of several
 15 hours. The hydrolysis can alternatively preferably be carried out at temperatures of 80°C to 120°C, preferably at 100°C, with a reaction duration of 1 to 10 hours.

The hydrolysis can alternatively also be carried out in the presence of a solvent. Suitable solvents are acetonitrile, propionitrile, dioxane, dimethoxyethane, dimethyl sulfoxide, dimethylformamide, or alcohols, for example
 20 methanol, ethanol or isopropanol, or mixtures of the said solvents.

The invention accordingly furthermore also relates to the compounds of the
 25 formula IIIa,



30 where

R_f denotes a straight-chain or branched perfluoroalkyl group having 1 to 12 C atoms,

A denotes H, F, Cl or a straight-chain or branched alkyl group having 1 to 12 C atoms,

B denotes $-(CR_1R_2)_n-$, $[-(CR_1R_2)_m-O-(CR_1R_2)_{m1-}]_{m2}$, arylene or substituted arylene,

5 X denotes H, F and/or Cl,

n denotes an integer from 0 to 20,

m denotes an integer from 1 to 20,

m_1 denotes an integer from 0 to 8,


m_2 denotes an integer from 1 to 20 and

10 R_1 or R_2 each, independently of one another, denote H, F, Cl or a straight-chain or branched alkyl group having 1 to 12 C atoms.

The description of the meanings or of the preferred meanings of R_f , A, B and X in compounds of the formula I also applies correspondingly to the intermediate compounds of the formula III or the intermediate compounds of the formula IIIa.

The invention accordingly furthermore likewise relates to a process for the preparation of compounds of the formula IIIa, as described above, characterised in that

20 a compound of the formula II




where R_f , A, B and X have one of the meanings indicated above or indicated as preferred and x denotes 1 or 2, is hydrolysed by reaction with water in an organic solvent.

Suitable solvents are, for example, acetonitrile, propionitrile, dioxane, dimethoxyethane, dimethyl sulfoxide, dimethylformamide, or alcohols, for example methanol, ethanol or isopropanol, or mixtures of the said solvents.

The yield of compounds of the formula IIIa is dependent on the solvent used and the amount of water.

5 The invention furthermore likewise relates to a process for the preparation of compounds of the formula IIIa, as described above, characterised in that a compound of the formula II



10 where R_f , A, B and X have one of the meanings indicated above or indicated as preferred and x denotes 1 or 2, is reacted with alkaline-earth metal oxides, alkaline-earth metal carbonates, zinc oxide, copper(I) oxide, copper(II) oxide, silver oxide, mercury(II) oxide, cadmium oxide or cadmium carbonate.

15 In principle, all alkaline-earth metal oxides or alkaline-earth metal carbonates can be employed in the process according to the invention. As is known, alkaline-earth metals are magnesium, calcium, strontium and barium. Commercially interesting alkaline-earth metal oxides or alkaline-earth metal carbonates are, for example, calcium oxide (CaO), calcium carbonate (CaCO₃), magnesium oxide (MgO) or barium carbonate (BaCO₃).
20 The said metal oxides or metal carbonates, as described above, can be used in equimolar amount or up to a two-fold excess.

25 For the synthesis of the compounds of the formula IIIa, as described above, preference is given to an embodiment of the invention in which alkaline-earth metal oxides or alkaline-earth metal carbonates are employed. The invention therefore relates to a process, as described above, characterised in that alkaline-earth metal oxides or alkaline-earth metal carbonates are used. These are preferably selected from CaO, CaCO₃, MgO or BaCO₃.
30

Calcium oxide is very particularly preferably used.

The solids employed in the process according to the invention should preferably be employed in the ground state in order that the largest possible surface area is present for the reaction.

5

Any type of grinding is possible, for example grinding by means of a ball mill.

10

Another alternative is the use of metal oxides in the form of fine particles having a diameter of 10 nm to 0.1 mm, which are preferably employed in freshly prepared form in the process according to the invention. The preparation of such highly active metal oxides from corresponding precursor materials is known to the person skilled in the art and can be carried out by methods which are known in the literature. For example, highly active metal oxides of this type can be prepared by sol-gel processes in which a suitable precursor compound, for example a corresponding metal acetate, is hydrolysed in alcohol or an alcohol/water mixture.

15

20

In the case of the alkaline-earth metal oxides or alkaline-earth metal carbonates, it is preferred to dry the solids in advance. In general, however, a proportion of at most 10 mol% of water is tolerated in the process according to the invention. In exceptional cases, such as, for example, on use of copper(I) oxide, the proportion of water described even results in an acceleration of the reaction.

25

The reaction can in principle be carried out at temperatures between 15°C and 200°C. If lower reaction temperatures are selected, the corresponding reaction time is longer.

30

The invention therefore also relates to a process, as described above, characterised in that the reaction is carried out at temperatures between 15°C and 200°C.

The reaction is preferably carried out at room temperature if long reaction times in the order of days are desired.

5 The reaction is preferably carried out at reaction temperatures of 50°C to 150°C, particularly preferably at reaction temperatures of 70°C to 130°C.

The reaction can be carried out in a glass apparatus or in an apparatus made from plastic (such as, for example, Teflon) or steel.


10 The reaction in the plastic apparatus or in the steel apparatus generally takes longer

The reaction is preferably carried out without solvents. However, it is also possible to carry out the reaction in the presence of solvents which are inert to the compounds employed, for example dialkyl ethers containing alkyl groups having 2 to 4 C atoms, for example diethyl ether, diisopropyl ether, 15 dipropyl ether, dibutyl ether.

The metal fluorides formed are virtually insoluble and can easily be separated off, for example, by filtration or decantation.

20 The reaction conditions in this embodiment are derived from the reaction conditions described in WO 2011/110281, in particular from Examples 1 to 5.

25 The invention furthermore likewise relates to a process for the preparation of compounds of the formula IIIa, as described above, characterised in that a compound of the formula II



30 where R_f, A, B and X have one of the meanings indicated above or indicated as preferred and x denotes 1 or 2, with non-metal oxides, semimetal oxides or organic compounds containing basic oxygen residues.

In principle, all non-metal oxides, semimetal oxides or organic compounds containing basic oxygen residues can be employed in the process according to the invention for the preparation of the compounds of the formula IIIa. Non-metal oxides are, as is known, oxides of carbon, nitrogen, phosphorus or sulfur, but also selenium, semimetal oxides are oxides of boron, silicon, arsenic or tellurium. Economically interesting non-metal oxofluorides are COF_2 , $\text{P}(\text{O})\text{F}_3$, $\text{S}(\text{O})\text{F}_2$. The said organic oxo compounds, as well as the non-metal or semimetal oxides, as described above, can be used in equimolar amount or large excess.

Non-metal oxides preferably used are SO_2 , POCl_3 , P_4O_{10} , CO_2 , SeO_2 , in particular SO_2 , CO_2 and SeO_2 .

A semimetal oxide which is preferably used is SiO_2 .

Organic compounds containing basic oxygen residues which are preferably used are triphenylphosphine oxide (Ph_3PO), ethylene carbonate or dimethyl carbonate, in particular ethylene carbonate.

For the synthesis of the compounds of the formula IIIa, as described above, preference is given to an embodiment of the invention in which the non-metal oxides and semimetal oxides are employed, in particular the compounds mentioned as preferred. The invention therefore relates to a process, as described above, characterised in that non-metal oxides and semimetal oxides are used. Particular preference is given to the use of silicon dioxide, selenium dioxide or sulfur dioxide.

The reaction times can be reduced significantly if small amounts of water are added. Water can be added here in a molar proportion of 0.01 to 0.8 equivalents. 0.1 to 0.5 equivalents of water are preferably added. Due to the addition of larger amounts of water, preferably 0.5 to 1.0 equivalents of water, some of the product reacts further to give the corresponding phos-

phinic acids of the formula I and liberated HF forms the corresponding (per-fluoroalkyl) fluorophosphate with some of the starting material.

5 The solids employed in this process should preferably be employed in the ground state in order that the largest possible surface area is present for the reaction. Any type of grinding is possible, for example grinding by means of a ball mill.

10 The solids do not require any type of drying. In general, the proportion of water described results in an acceleration of the reaction.

The reaction can in principle be carried out at temperatures between 80°C and 200°C. If low reaction temperatures are selected, the corresponding reaction time is longer. The invention therefore also relates to a process, as
15 described above, characterised in that the reaction is carried out at temperatures between 25°C and 200°C.

The reaction is preferably carried out at room temperature if long reaction times in the order of days are desired.

20 The reaction is preferably carried out at reaction temperatures of 50°C to 180°C, particularly preferably at reaction temperatures of 80°C to 150°C.

The reaction can be carried out in a glass apparatus or in an apparatus
25 made from plastic (such as, for example, Teflon) or steel.

The reaction in the plastic apparatus or in the steel apparatus generally takes longer

The reaction is preferably carried out without solvents. However, it is also possible to carry out the reaction in the presence of solvents which are inert
30 to the compounds employed, for example dialkyl ethers containing alkyl groups having 2 to 4 C atoms, for example diethyl ether, diisopropyl ether, dipropyl ether, methyl butyl ether.

The by-products formed are gaseous and can easily be separated off. Reactions in which solids were used can easily be separated off, for example, by filtration or decantation or condensed off or distilled off in vacuo.

5


Isolation of the products is not necessary in the case of gaseous reactants. The by-products are discharged continuously on use of cooling above the boiling point of the by-products. The residue is principally product. However, the compounds of the formula IIIa or I can also be separated off by condensation or distillation from solid by-products formed.

10

The reaction conditions in this embodiment are derived from the reaction conditions described in WO 2014/005668, in particular from Examples 1 to 9.

15

The invention furthermore likewise relates to a process for the preparation of compounds of the formula IIIa, as described above, characterised in that a compound of the formula II



20

where R_f , A, B and X have one of the meanings indicated above or indicated as preferred and x denotes 1 or 2, is reacted with a hexaalkyldisiloxane without or in the presence of a catalytic amount of water, where the alkyl groups of the hexaalkyldisiloxane each, independently of one another, denote a straight-chain or branched alkyl group having 1 to 4 C atoms.


25

The compounds of the formula I, as described above, can alternatively be prepared by hydrolysis of the intermediate compounds of the formula III if the intermediate compounds of the formula III are accessible by a route other than via reaction of a compound of the formula II, as described above.

30

The invention accordingly furthermore likewise relates to a process for the preparation of compounds of the formula I, as described above or preferably described, characterised in that a compound of the formula III is hydro-

5



10

where R_f, A, B and X have one of the meanings indicated above or preferred meanings.

15

The compound of the formula I prepared by the said processes is preferably purified by conventional methods. Suitable purification steps include separating off readily volatile components by distillation or condensation, extraction with an organic solvent or a combination of these methods. Any known separation method can be used or combined for this purpose.

20

The invention furthermore relates to the use of the compounds of the formula I, as described above or described as preferred, for the preparation of oligomers or polymers.

25

The term "polymer" generally denotes a molecule having a high relative molecular weight whose structure essentially comprises the multiple repetition of units which are actually or conceptually derived from molecules having a low relative molecular weight (PAC, 1996, 68, 2291). The term "oligomer" generally denotes a molecule having a moderate relative molecular weight whose structure essentially comprises a small number of units which are actually or conceptually derived from molecules having a lower relative molecular weight (PAC, 1996, 68, 2291). In a preferred meaning in accordance with the present invention, a polymer denotes a compound having > 1, preferably ≥ 5 repeating units, and an oligomer denotes a compound having > 1 and < 10, preferably < 5 repeating units. The number of

30

monomer units in a macromolecule is also called degree of polymerisation.

Unless indicated otherwise, the molecular weight indicated is the number average molecular weight M_n or weight average molecular weight M_w , which is determined by gel permeation chromatography (GPC) against polystyrene standards in eluting solvents, such as tetrahydrofuran, trichloromethane (TCM, chloroform), chlorobenzene or 1,2,4-trichlorobenzene. The degree of polymerisation (n) denotes the number average degree of polymerisation, given by

$n = M_n/M_U$, in which M_U is the molecular weight of the individual repeating unit, as described in J. M. G. Cowie, *Polymers: Chemistry & Physics of Modern Materials*, Blackie, Glasgow, 1991.

The terms "repeating unit" and "monomer unit" denote the basic repeating unit (constitutional repeating unit - CRU), which is the smallest basic unit whose repetition represents a regular macromolecule, a regular oligomer molecule, a regular block or a regular chain (PAC, 1996, 68, 2291). The term "unit" denotes a structural unit which may itself be a repeating unit or can form a repeating unit together with other units.

The oligomer or polymer, as described above, may, besides the polymerised compounds of the formula I, as described above or described as preferred, also contain alternative polymerised monomer units. In a preferred embodiment of the invention, the polymers are homopolymers. In a homopolymer, the polymer consists of the polymerised compounds of the formula I, as described above, as monomer unit.

The invention accordingly furthermore relates to an oligomer or polymer containing the polymerised compounds of the formula I, as described above or described as preferred, as monomer unit.

The invention accordingly furthermore relates to an oligomer or polymer consisting of polymerised compounds of the formula I, as described above or described as preferred, as monomer unit.

5 The invention accordingly furthermore relates to a homooligomer or homopolymer consisting of polymerised compounds of the formula I, as described above or described as preferred, as monomer unit.

10 The oligomers or polymers or homooligomers or homopolymers, as described above, may furthermore be linear or crosslinked.

The choice of crosslinking agents or crosslinking agent here is not limited. Suitable crosslinking agents are known to the person skilled in the art in the area of polymer chemistry and are described below.

15 The invention furthermore relates to a process for the preparation of oligomers or polymers, as described above, characterised in that compounds of the formula I, as described above or described as preferred, are polymerised, optionally together with further monomers and optionally in the presence of a crosslinking agent.

20 The invention furthermore relates to a process for the preparation of homooligomers or homopolymers, as described above, characterised in that compounds of the formula I, as described above or described as preferred, are polymerised, optionally in the presence of a crosslinking agent. A homopolymer is preferably prepared.

25 The type of polymerisation is not limited. The polymerisation can be anionic, cationic or free-radical. Living polymerisation is also suitable. Graft polymerisation onto a support material is also suitable.

30

In the case of graft polymerisation, the polymerisation in accordance with the invention is carried out with the aid of cerium(IV) ions.

5 The invention furthermore relates to the process for the preparation of oligomers or polymers, as described above, where the graft polymerisation is carried out with the aid of cerium(IV) ions.

In accordance with the invention, free-radical polymerisation is preferred. The invention furthermore relates to the process for the preparation of oligomers or polymers, as described above, where the polymerisation is
10 carried out by means of free radicals.

The free-radical polymerisation is preferably carried out with exclusion of oxygen.

15 The free-radical polymerisation can be initiated by a free-radical initiator, for example by AIBN (2,2'-azobis(2-methylpropionitrile)) or V65 (2,2'-azobis-(2,4-dimethylvaleronitrile)), or by a photoinitiator.

20 The free-radical initiator is employed, for example, in 0.01 to 15% by weight, based on the totality of monomers. The free-radical initiator is preferably employed in 0.1 to 5% by weight.

In the case of a photopolymerisation initiator, the polymerisation process is initiated by irradiation of the initiator/monomer mixture, where energy
25 beams of light, electrons or γ rays can be used for this purpose. The photopolymerisation generally results in a rapidly crosslinked end product. The irradiation is preferably carried out with UV light.

30 The choice of photoinitiator is not limited. Suitable photoinitiators for irradiation with UV light are, for example, 2-hydroxy-2-methyl-1-phenylpropan-1-one, marketed under the trade name Darocur® 1173 from BASF, or 1-hydroxycyclohexyl phenyl ketone,

marketed, for example, under the trade name Irgacure® 184 by BASF (Ciba).

5 A photoinitiator is employed, for example, in 0.1 to 5% by weight, based on the totality of monomers. A photoinitiator is preferably employed in 1% by weight.

10 In the case of graft polymerisation, the polymerisation process is initiated by cerium(IV) ions, where the compound $[\text{NH}_4]_2\text{cerium}[\text{NO}_3]_6$ in an aqueous HNO_3 solution is preferably used.

15 In an embodiment of the invention, the monomers of the formula I or a monomer mixture comprising a compound of the formula I, as described above, are polymerised by means of free radicals in the presence of a crosslinking agent.

Suitable crosslinking agents are, for example, hexadiol diacrylate, divinylbenzene, tripropylene glycol diacrylate, butanediol diacrylate, trimethylol propane triacrylate, dipropylene glycol diacrylate or mixtures thereof. The crosslinking agent used is preferably tripropylene glycol diacrylate (TPGDA).

20

25 The crosslinking agent(s) is preferably employed in an amount of 3 to 10 mol%, particularly preferably in 5 mol%, based on the totality of monomers.

In a preferred embodiment of the invention, the polymerisation is carried out without crosslinking agents.

30 The invention accordingly furthermore relates to process for the preparation of oligomers or polymers or homooligomers or homopolymers, as described above, characterised in that the polymerisation is carried out without crosslinking agents.

In a alternative preferred embodiment of the invention, the polymerisation is carried out with crosslinking agents.

5 In a further preferred embodiment of the invention, in particular for industrial use, as described below, the polymerisation is carried out in, on or at a support material.

10 The invention accordingly furthermore relates to a process for the preparation of oligomers or polymers or homooligomers or homopolymers, as described above, characterised in that the polymerisation is carried out in, on or at a support material.

15 The free-radical polymerisation is preferably carried out at temperatures of 0°C to 80°C. The polymerisation is particularly preferably carried out at room temperature. The polymerisation is particularly preferably carried out at 60°C to 70°C if the polymerisation is carried out onto a porous silica support material.

20 The graft polymerisation is preferably carried out at temperatures of 20°C to 60°C. The polymerisation is particularly preferably carried out at 40°C.

25 In the polymers in accordance with the present invention, the total number of monomer units n is preferably ≥ 50 , very preferably ≥ 100 , particularly preferably ≥ 500 , and preferably up to 5000, very preferably up to 50,000, particularly preferably up to 200,000, including any desired combinations of the above-mentioned lower and upper limits for n .

30 M_w is preferably at least 5,000, preferably at least 28,000, particularly preferably at least 150,000 and preferably up to 3,000,000, particularly preferably up to 110,000,000.

The polymers according to the invention preferably have an average degree of polymerisation of 25 to 400,000, preferably of 351,600. The average degree of polymerisation is determined via the weight average molecular weight M_w and the polydispersity by means of GPC. The polydispersity, also known as nonuniformity U , is a measure of the width of the distribution.

The oligomers or polymers containing polymerised compounds of the formula I as monomer unit or consisting of polymerised compounds of the formula I as monomer unit, as described above, are preferably used, for example, as ion exchanger or as Brønsted acid catalyst.

Due to the phosphinic acid acidic protons present, both the compounds of the formula I and also the corresponding polymers and oligomers, as described above, are capable of effecting ion exchange or effecting catalysis.

The invention therefore furthermore relates to the use of the compounds of the formula I, as described above or described as preferred, or the use of the oligomers/polymers, as described above, or also of the composite materials comprising compounds of the formula I or the oligomers/polymers according to the invention, as described below, as ion exchanger or as Brønsted acid catalyst.

An alternative use, besides the use as ion exchanger, is, for example, the use in organic catalysis for chemical reactions.

A further alternative use of the compounds of the formula I according to the invention, as described above or described as preferred, or the use of the oligomers/polymers, as described above, or also composite materials comprising compounds of the formula I or the oligomers/polymers according to the invention is, for example, the use as catalysts for the generation of gasoline components for increasing the octane number or for the adduction of water onto olefins for the generation of simple alcohols.


The suitability of the oligomers/polymers, as described above, as ion exchanger can be determined by determination of the ion exchange capacity IEC. For this purpose, the corresponding compound is, for example, suspended in aqueous sodium hydroxide solution (0.1 M NaOH) and stirred vigorously at room temperature for 24 h. The resultant supernatant basic solution is subsequently titrated with hydrochloric acid (0.1 M). Further details on this determination are explained in Example 26.

The suitability of the polymers, as described above, as ion exchanger can likewise be confirmed by titration of the polymer material with a caustic lye, for example a sodium hydroxide solution.

Due to the ion exchange, salts of the compounds of the formula I, as described above or described as preferred, and ionic polymers/oligomers containing polymerised salts of the compounds of the formula I as monomer units, on a support material or without a support material, as described above or below, are formed.

The compound of the formula I is a strong acid which is particularly suitable for the preparation of salts of the formula IV.

The invention furthermore likewise relates to the salts of the compounds of the formula I, corresponding to the formula IV,



or the corresponding ionic polymers/oligomers, as described above, on a support material or without a support material, where the cations of the salts or of the ionic polymers/oligomers Kt^+ are an inorganic or organic

cation and where R_f, A, B and X have one of the meanings indicated above or meanings preferably indicated.

5 In relation to the choice of the inorganic or organic cation of the salts of the formula IV or of the ionic polymers or oligomers containing polymerised salts of the formula IV as monomeric units on a support material or without a support material, in accordance with the present invention, there are no restrictions per se.

10 The inorganic cations are preferably the group of cations selected from a cation of an element from group 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11 and/or 12 of the Periodic Table.

15 Salts of this type with inorganic cations, for example K⁺ or Na⁺, are suitable, in particular, for the preparation of salts of the formula IV or ionic polymers containing polymerised salts of the formula IV with organic cations or alternative inorganic cations.

20 The organic cations are preferably organic cations selected from the group comprising ammonium, sulfonium, oxonium, phosphonium, iodonium, tritylium, uronium, thiouronium, guanidinium cations or heterocyclic cations. Examples of organic cations are also polyammonium ions having a degree of charging of 4.

25 Compounds of the formula IV with organic cations, as described above, then form so-called polymerisable ionic liquids. The uses of ionic liquids are adequately known to the person skilled in the art.

30 Particularly suitable organic cations are selected from the group tetraalkylammonium, tetraalkylphosphonium, 1,1-dialkylpyrrolidinium, 1-alkyl-1-alkoxyalkylpyrrolidinium or 1,3-dialkylimidazolium, where the alkyl groups or the alkoxy group in the alkoxyalkyl group each have, independently of one

another, 1 to 10 C atoms. Very particularly preferably, the alkyl groups have 1 to 6 C atoms and the alkoxy group has 1 to 3 C atoms.

The alkyl groups in tetraalkylammonium or in tetraalkylphosphonium may therefore be identical or different. Preferably, three alkyl groups are identical and one alkyl group is different or two alkyl groups are identical and the other two are different. Preferred tetraalkylammonium cations are, for example, trimethyl(ethyl)ammonium, triethyl(methyl)ammonium, tripropyl(methyl)ammonium, tributyl(methyl)ammonium, tripentyl(methyl)ammonium, trihexyl(methyl)ammonium, triheptyl(methyl)ammonium, trioctyl(methyl)ammonium, trinonyl(methyl)ammonium, tridecyl(methyl)ammonium, trihexyl(ethyl)ammonium, ethyl(trioctyl)ammonium, propyl(dimethyl)ethylammonium, butyl(dimethyl)ethylammonium, methoxyethyl(dimethyl)ethylammonium, methoxyethyl(diethyl)methylammonium, methoxyethyl(dimethyl)propylammonium, ethoxyethyl(dimethyl)ethylammonium.

Particularly preferred quaternary ammonium cations are propyl(dimethyl)ethylammonium, tributyl(methyl)ammonium and/or methoxyethyl(dimethyl)ethylammonium.

Preferred tetraalkylphosphonium cations are, for example, trimethyl(ethyl)phosphonium, triethyl(methyl)phosphonium, tripropyl(methyl)phosphonium, tributyl(methyl)phosphonium, tripentyl(methyl)phosphonium, trihexyl(methyl)phosphonium, triheptyl(methyl)phosphonium, trioctyl(methyl)phosphonium, trinonyl(methyl)phosphonium, tridecyl(methyl)phosphonium, trihexyl(ethyl)phosphonium, ethyl(trioctyl)phosphonium, propyl(dimethyl)ethylphosphonium, butyl(dimethyl)ethylphosphonium, methoxyethyl(dimethyl)ethylphosphonium, methoxyethyl(diethyl)methylphosphonium, methoxyethyl(dimethyl)propyl phosphonium, ethoxyethyl(dimethyl)ethyl phosphonium. Particularly preferred quaternary phosphonium cations are propyl(dimethyl)ethyl phosphonium and/or methoxyethyl(dimethyl)ethylphosphonium.

Preferred 1,1-dialkylpyrrolidinium cations are, for example, 1,1-dimethylpyrrolidinium, 1-methyl-1-ethylpyrrolidinium, 1-methyl-1-propylpyrrolidinium, 1-methyl-1-butylpyrrolidinium, 1-methyl-1-pentylpyrrolidinium, 1-methyl-1-hexylpyrrolidinium, 1-methyl-1-heptylpyrrolidinium, 1-methyl-1-octylpyrrolidinium, 1-methyl-1-nonylpyrrolidinium, 1-methyl-1-decylpyrrolidinium, 1,1-diethylpyrrolidinium, 1-ethyl-1-propylpyrrolidinium, 1-ethyl-1-butylpyrrolidinium, 1-ethyl-1-pentylpyrrolidinium, 1-ethyl-1-hexylpyrrolidinium, 1-ethyl-1-heptylpyrrolidinium, 1-ethyl-1-octylpyrrolidinium, 1-ethyl-1-nonylpyrrolidinium, 1-ethyl-1-decylpyrrolidinium, 1,1-dipropylpyrrolidinium, 1-propyl-1-methylpyrrolidinium, 1-propyl-1-butylpyrrolidinium, 1-propyl-1-pentylpyrrolidinium, 1-propyl-1-hexylpyrrolidinium, 1-propyl-1-heptylpyrrolidinium, 1-propyl-1-octylpyrrolidinium, 1-propyl-1-nonylpyrrolidinium, 1-propyl-1-decylpyrrolidinium, 1,1-dibutylpyrrolidinium, 1-butyl-1-methylpyrrolidinium, 1-butyl-1-pentylpyrrolidinium, 1-butyl-1-hexylpyrrolidinium, 1-butyl-1-heptylpyrrolidinium, 1-butyl-1-octylpyrrolidinium, 1-butyl-1-nonylpyrrolidinium, 1-butyl-1-decylpyrrolidinium, 1,1-dipentylpyrrolidinium, 1-pentyl-1-hexylpyrrolidinium, 1-pentyl-1-heptylpyrrolidinium, 1-pentyl-1-octylpyrrolidinium, 1-pentyl-1-nonylpyrrolidinium, 1-pentyl-1-decylpyrrolidinium, 1,1-dihexylpyrrolidinium, 1-hexyl-1-heptylpyrrolidinium, 1-hexyl-1-octylpyrrolidinium, 1-hexyl-1-nonylpyrrolidinium, 1-hexyl-1-decylpyrrolidinium, 1,1-diheptylpyrrolidinium, 1-heptyl-1-octylpyrrolidinium, 1-heptyl-1-nonylpyrrolidinium, 1-heptyl-1-decylpyrrolidinium, 1,1-dioctylpyrrolidinium, 1-octyl-1-nonylpyrrolidinium, 1-octyl-1-decylpyrrolidinium, 1,1-dinonylpyrrolidinium, 1-nonyl-1-decylpyrrolidinium or 1,1-didecylpyrrolidinium. Very particularly preference is given to 1-butyl-1-methylpyrrolidinium or 1-propyl-1-methylpyrrolidinium.

Preferred 1-alkyl-1-alkoxyalkylpyrrolidinium cations are, for example, 1-methoxyethyl-1-methylpyrrolidinium, 1-methoxyethyl-1-ethylpyrrolidinium, 1-methoxyethyl-1-propylpyrrolidinium, 1-methoxyethyl-1-butylpyrrolidinium,

1-ethoxyethyl-1-methylpyrrolidinium, 1-ethoxymethyl-1-methylpyrrolidinium. Very particular preference is given to 1-methoxyethyl-1-methylpyrrolidinium.

5 Preferred 1,3-dialkylimidazolium cations are, for example, 1-ethyl-3-methylimidazolium, 1-methyl-3-propylimidazolium, 1-butyl-3-methylimidazolium, 1-methyl-3-pentylimidazolium, 1-ethyl-3-propylimidazolium, 1-butyl-3-ethylimidazolium, 1-ethyl-3-pentylimidazolium, 1-butyl-3-propylimidazolium, 1,3-dimethylimidazolium, 1,3-diethylimidazolium, 1,3-dipropylimidazolium, 1,3-dibutylimidazolium, 1,3-dipentylimidazolium, 1,3-diethylimidazolium, 1,3-diheptylimidazolium, 1,3-dioctylimidazolium, 1,3-dinonylimidazolium, 1,3-didecylimidazolium, 1-hexyl-3-methylimidazolium, 1-heptyl-3-methylimidazolium, 1-methyl-3-octylimidazolium, 1-methyl-3-nonylimidazolium, 1-decyl-3-methylimidazolium, 1-ethyl-3-hexylimidazolium, 1-ethyl-3-heptylimidazolium, 1-ethyl-3-octylimidazolium, 1-ethyl-3-nonylimidazolium or 15 1-decyl-3-ethylimidazolium. Particularly preferred cations are 1-ethyl-3-methylimidazolium, 1-butyl-3-methylimidazolium or 1-methyl-3-propylimidazolium.

20 Particularly preferred organic cations of the compounds of the formula IV for industrial applications of ionic liquids are accordingly 1-butyl-1-methylpyrrolidinium, 1-ethyl-3-methylimidazolium, 1-ethyl-2,3-dimethylimidazolium, 1-butyl-2,3-dimethylimidazolium, 1-(2-methoxyethyl)-3-methylimidazolium, 1-butyl-3-methylimidazolium, tributylmethylammonium, tetra-*n*-butylammonium, tributylmethylphosphonium, tetraphenylphosphonium, tetra-25 butylphosphonium, diethylmethylsulfonium, S-ethyl-N,N,N',N'-tetramethylisothiuronium, 1-allyl-3-methylimidazolium, 1-allyl-2,3-dimethylimidazolium, 1-cyanomethyl-3-methylimidazolium, 1-(2-cyanoethyl)-3-methylimidazolium, 1-methyl-3-propynylimidazolium, 1-butyl-4-methylpyridinium, 1,1-dimethylpyrrolidinium.

30

A particular form of ion exchange is the exchange of protons by cations of the rare earths. There continues to be a demand for alternative compounds

for the extraction of cations of the rare earths from solutions, preferably from aqueous solutions, particularly preferably from aqueous acidic solutions.

5 Particularly preferred inorganic cations of the compounds of the formula IV or of the ionic polymers/oligomers containing polymerised compounds of the formula IV or of the composite materials comprising compounds of the formula IV or ionic polymers/oligomers containing polymerised compounds of the formula IV are the cations of the rare earths.

10 In a preferred embodiment of the invention, cations of the rare earths are selected from the group Sc, Y, Lu, La, Ce, Pr, Nd, Pm, Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm and Yb.

As is known, rare-earth metal cations can have a valency of 2, 3 or 4. The
15 valency of the corresponding cation is preferably 3 ($z = 3$).

In a particularly preferred embodiment of the invention, cations of the rare earths from the group Y, La, Ce, Pr, Nd, Sm, Eu, Gd and Tm are extracted.

20 The invention therefore furthermore relates to the use of the compounds of the formula I described above or of the corresponding polymers/oligomers containing polymerised compounds of the formula I on a support material or without a support material for the extraction of cations of the rare earths from solutions, preferably from aqueous solutions, particularly preferably from aqueous acidic solutions.

25 The source of the corresponding solution is not restricted. It may be a corresponding solution which forms during the work-up of commercially available rare-earth minerals, for example during the work-up of bastnesite, monazite or xenotime. However, it may also be a solution which forms as
30 intermediate during the processing of rare-earth metals or rare-earth metal solutions or a solution from waste water or a solution which forms during the recycling of industrial equipment.

The solution can contain one or more rare-earth metal cation(s).

The pH of these solutions is preferably pH 0 to 7.

5 The proportion of the corresponding cations of the rare-earth metals in the solution is preferably ≤ 10 per cent by weight.

The aqueous acidic solutions contain, for example, chloride anions, sulfate anions, nitrite anions or nitrate anions or a mixture of the said anions. The
10 aqueous solution preferably contains chloride anions or a mixture of chloride and nitrate anions.

The invention accordingly furthermore also relates to a process for the extraction of cations of the rare earths from solutions, preferably aqueous
15 solutions, particularly preferably from aqueous acidic solutions, using a compound of the formula I, as described above, or a polymer/oligomer containing polymerised compounds of the formula I, as described above, or a composite material comprising a polymer/oligomer comprising or consisting of polymerised monomer units of the formula I, as described below.

20

The extraction according to the invention is preferably carried out by

a) providing the solution containing the cations of the rare earths,

b) mixing the aqueous solution from a) with

b1) at least one compound of the formula I, as described above,

25 b2) a polymer or oligomer containing polymerised compounds of the formula I, as described above, or

b3) a composite material comprising a support material and either a compound of the formula I or a polymer or oligomer containing polymerised compounds of the formula I, as described below,

30 so that at least some of the acidic protons of the phosphinic acid function are replaced by the cations of the rare earths in order to extract these

cations from the solution, where corresponding salts or ionic polymers/oligomers form,

c) separating off the salts of the compounds of the formula I or of the ionic polymers or oligomers containing polymerised salts of the compounds of the formula I or of the composite material from the aqueous solution and optionally

d) regenerating to form compounds of the formula I or to form polymers or oligomers containing polymerised compounds of the formula I or of the composite material.

The extraction can be carried out discontinuously in a batch process or continuously in through-flow, for example as co-current or countercurrent process.

The regeneration of the compounds of the formula I, as described above, of the polymers or oligomers containing polymerised compounds of the formula I, as described above, or of the composite material comprising a compound of the formula I or a polymer or oligomer containing polymerised compounds of the formula I, as described below, is carried out, for example, by exchange of the cation of the rare-earth metal by an acid. Suitable acids for the regeneration are hydrochloric acid, sulfuric acid or nitric acid or a mixture of the said acids.

If a liquid-phase extraction is carried out, firstly a phase separation is carried out and then the cations of the rare earths are separated off, where rinsing is carried out, for example, with an aqueous acid. Suitable acids are listed above. The further work-up of the aqueous solution containing the cations of the rare earths is then dependent on the corresponding application.

In a preferred embodiment of the invention, a polymer containing polymerised compounds of the formula I, as described above or described as preferred, is employed as extraction medium.

5 In a alternative preferred embodiment of the invention, a polymer containing polymerised compounds of the formula I, as described above or described as preferred, combined with a support material is employed. In this embodiment of a composite material, the separation from the aqueous solution is the simplest.

10 The polymerisation can take place within the support material or merely at the surface of the support material. The polymer formed containing the polymerised monomer units of the formula I or consisting of the polymerised monomer units of the formula I can covalently bond to the support
15 material. However, the invention also encompasses support materials comprising oligomers/polymers containing or consisting of polymerised monomer units of the formula I which are merely adsorbed at the surface or in the pores or in which the polymerisation takes place in the pores.

20 The invention furthermore relates to a composite material comprising a support material and at least one compound of the formula I, as described above, or a support material and a polymer or oligomer containing polymerised compounds of the formula I, as described above or described as an alternative or preferred, or a corresponding salt or polymerised salts of the
25 formula IV after successful ion exchange.

The composite material preferably comprises a support material and a polymer containing polymerised compounds of the formula I, as described above or described as preferred.

30 The composite material preferably comprises a support material and a polymer consisting of polymerised compounds of the formula I, as described above or described as preferred.

The composite material may comprise or contain, essentially consist of or consist of the said requisite or optional constituents. All compounds or components which can be used in the composite material are either known and commercially available, can be synthesised by known processes or are as described above or below.

A suitable support material is any form of a matrix, for example a porous material, a film, a fibre or a hollow fibre. The porous material can be a particle or a monolithic shaped body.

Suitable as support material are inorganic materials, organic materials or a composite material comprising inorganic and organic materials.


Suitable support materials are, for example, polymer support materials, which may likewise be porous.

Suitable support materials are polysulfones, polyether sulfones, polyphenyl sulfones, polyimides, polyamides, polyvinylidene fluoride (PVDF), polyacrylonitriles, polyacrylamides, polyacrylates, polyaniline, polyether-imides, polyvinyl ethers, polystyrenes or cellulose acetate.

A preferred polyvinyl ether is a hydrophilically crosslinked polyvinyl ether.

A particularly preferred polymer as support material is a hydrophilic crosslinked polymer based on a copolymer at least of

a) at least one hydrophilically substituted alkyl vinyl ether of the formula 1



where R1, R2, R3, independently of one another, can be H or C1 to C6 alkyl, preferably H or -CH₃


and R4 is a radical which carries at least one hydroxyl group and

5

b)

at least one crosslinking agent conforming to formula 2 and/or 3 and/or 4, with

10




2

15

where X in the formula 2 is a divalent alkyl radical having 2 to 5 C atoms, preferably 2 or 3 C atoms, in which one or more non-adjacent methylene groups which are not located in the direct vicinity of N may be replaced by O, C=O, S, S=O, SO₂, NH, NOH or N and one or more H atoms of the methylene groups may be substituted, independently of one another, by hydroxyl groups, C1-C6-alkyl, halogen, NH₂, C5-C10-aryl, NH-(C1-C8)-alkyl, N-(C1-C8)-alkyl₂, C1-C6-alkoxy or C1-C6-alkyl-OH, and


20



25

3

30



4

where Y₁ and Y₂ in formula 3 and 4 are, independently of one another, C1 to C10 alkyl or cycloalkyl, where one or more non-adjacent methylene groups or methylene groups which are not located in the direct vicinity of N may be replaced by O, C=O, S, S=O, SO₂, NH, NOH or N and one or more
5 H of the methylene groups may be substituted, independently of one another, by hydroxyl groups, C1-C6-alkyl, halogen, NH₂, C5-C10-aryl, NH(C1-C8)alkyl, N(C1-C8)alkyl₂, C1-C6-alkoxy or C1-C6-alkyl-OH,

or are C6 to C18 aryl, where one or more H in the aryl system may be
10 substituted, independently of one another, by hydroxyl groups, C1-C6-alkyl, halogen, NH₂, NH(C1-C8)alkyl, N(C1-C8)alkyl₂, C1-C6-alkoxy or C1-C6-alkyl-OH and

A in this formula 3 is a divalent alkyl radical having 2 to 5 C atoms, preferably 2 or 3 C atoms, in which one or more non-adjacent methylene groups or methylene groups which are not located in the direct vicinity of N may be replaced by O, C=O, S, S=O, SO₂, NH, NOH or N and one or more
15 H of the methylene groups may be substituted, independently of one another, by hydroxyl groups, C1-C6-alkyl, halogen, NH₂, C5-C10-aryl, NH(C1-C8)alkyl, N(C1-C8)alkyl₂, C1-C6-alkoxy or C1-C6-alkyl-OH, as
20 described in WO 2007/014591.

In a particularly preferred embodiment, the hydrophilically substituted alkyl vinyl ether employed is 1,2-ethanediol monovinyl ether, 1,3-propanediol
25 monovinyl ether, 1,4-butanediol monovinyl ether, 1,5-pentanediol monovinyl ether, 1,6-hexanediol monovinyl ether or diethylene glycol monovinyl ether and the cycloaliphatic vinyl ether employed is cyclohexanedimethanol monovinyl ether.

30 in a further preferred embodiment, the crosslinking agent employed is divinylethyleneurea (1,3-divinylimidazolin-2-one) or divinylpropyleneurea (1,3-divinyltetrahydropyrimidin-2-one).

In another preferred embodiment, the polymer is porous having pore sizes between 2 and 200 nm.

5 In another embodiment, the polymer is in the form of particles having a diameter between 3 and 300 μm .

The oligomers/polymers according to the invention can preferably be applied to this polymer material by graft polymerisation, for example by
10 graft polymerisation with cerium(IV)catalysis, as described in Example 29.

Further preferred embodiments of this polymer material as support material and the preparation of this polymer material are described in WO 2007/
15 014591, in particular in Example 1.

Suitable natural support materials are carbohydrate polymers, such as, for example, agarose, cellulose, dextran and chitosan (A. Jungbauer, G. Carta, in: Protein Chromatography, Process Development and Scale-Up; WILEY-VCH Verlag, Weinheim (Germany) 2010).

20 Suitable inorganic support materials are metal oxides, for example SiO_2 , including silicates and silica gel, TiO_2 , ZrO_2 , Al_2O_3 , ZnO or mixtures thereof, where the inorganic surfaces must have corresponding free edge groups which allow the binding of the monomer unit of the formula I. Corresponding
25 free edge groups are, for example, the OH group or the SH group. In Example 30, for example, the graft polymerisation is carried out on a mercapto-silica gel.

The term inorganic support materials also encompasses ceramic support materials, in which, for example, a mixture of inorganic metal oxides is
30 used, where the mixture also encompasses a sequence of different layers of metal oxides on a metal oxide as substrate.

Suitable inorganic support materials are likewise support materials based on activated carbon.

5 Suitable support materials are likewise porous glasses having pore diameters of about 50 to 300 microns, which are optionally functionalised by a polymer material, as described above, and which carry reactive groups on which or with which the polymerisation with the monomer units of the formula I according to the invention can take place. Porous glasses of this type are of called "controlled pore glass" (CPG).

10

The support materials, preferably the porous support materials, can be in particulate or monolithic form.

15

Monolithic support materials have a porous body in which channels are present which arise through the connection of cavities from one end to the other end of the inorganic support material. The cavities contain a macropore and a mesopore, which forms on the inside surface of the macropore. In general, the mesopores have a pore size of 6 to 100 nm. Further details on monolithic support materials are described, for example, in US 2011/0094955 in paragraphs [0019] to [0029].

20

Preferred suitable support materials are porous materials in the pores of which the ion exchange or extraction takes place, preferably particulate materials.

25

Particularly preferred support materials are particulate.

30

Even without further comments, it will be assumed that a person skilled in the art is able to utilise the above description in the broadest scope. The preferred embodiments and examples should therefore merely be regarded as descriptive disclosure which is absolutely not limiting in any way.

The following examples demonstrate syntheses of compounds of the formula I and use thereof for polymerisation processes, examples of the preparation of polymers and composite materials and examples of ion exchangers and examples of the use as extraction medium.

5

Apparatuses and materials

Gaseous or readily volatile substances are handled in grease-free glass vacuum lines. Moisture-sensitive solids are stored and handled in a dry box (Jacomex with the P(SYS)-II-P inert-gas purification module, argon atmosphere; H₂O and O₂ range < 0.5 ppm). Organic solvents are purified and dried in accordance with the current standard literature, for example as described in Wilfred L.F. Armarego, Christina L.L. Chai, *Purification of Laboratory Chemicals*, 5th ed.; Butterworth-Heinemann, Elsevier Science, 2003.

15

NMR spectroscopy: NMR samples are measured at 25°C either in a 5 mm (Ø_o) glass NMR tube or in a 3.7 mm (Ø_o) FEP inliner. In the case of measurements in FEP, the inliner is introduced into a 5 mm (Ø_o) precision thin-glass NMR tube (Wilmad 537). The lock substance, CD₃CN, is thus located between glass and FEP inliner in the glass NMR tube and is characterised below using film measurement or solvent film. The measurements are carried out in a 400 MHz Bruker Avance III spectrometer with a 9.3980 T cryomagnet and a 5 mm BBFO sample head. ¹H NMR spectra are measured in the ¹H/¹⁹F channel at 400.17 MHz. ¹³C, ¹⁹F and ³¹P NMR spectra are measured in the broad-band channel at 100.62, 376.54 and 161.99 MHz. The ¹H NMR chemical shifts are relative to tetramethylsilane (TMS) and arise for the solvents D₂O (4.81 ppm), CDCl₃ (7.24 ppm) and CD₃CN (1.96 ppm). The ¹³C NMR chemical shifts are likewise relative to TMS and arise for the solvents CDCl₃ (77.2 ppm) and CD₃CN (118.7 ppm). The ¹⁹F NMR chemical shifts are relative to CFC₃ and arise for the internal standards C₆F₆ (−162.9 ppm) or C₆H₅CF₃ (−63.9 ppm). The ³¹P NMR chemical shifts are relative to H₃PO₄ (85%).

30

The ^{19}F NMR spectra of the asymmetrical alkenebis(pentafluoroethyl)-phosphinic acids are higher order spectra (AA'BB'). The analysis therefore does not allow direct assignment of the resonance frequencies, which are determined directly as the centre of the AA' or BB' part, or of the coupling constants J and J' or J_A and J_B . The line assignment made is checked by calculation of a sample spectrum with the aid of the gNMR program [Version 5.0.6.0; P. H. M. Budzelaar, IvorySoft], taking into account the experimentally determined values from the ^{31}P NMR spectra, in order in this way to avoid possible misassignments by precise frequency and intensity comparison with the experiment. The chemical shifts were determined by iterative approximations of the parameters.

Fluorescence spectroscopy

Fluorescence spectroscopic measurements are carried out using a HITACHI F-2700 fluorescence spectrophotometer. The band pass for excitation the emission is 5 nm.

GPC analysis

Working conditions:

Apparatus:	Hitachi Elite LaChrom
Eluent:	DMF Art. 1.03053 batch K44604953
Sample solvent:	ID2013-10-31_KB01
Flow rate:	1.0 ml/min
Pressure:	72 bar
Injection:	100 μL
Separating column:	1 x PSS GRAM 100A 8 x 300mm SN 3090514 + 2 x PSS GRAM 3000A 8 x 300mm SN 3082811 + 3082814

Column temperature: 40°C

Detector: RI Hitachi L-2490 cell temp. 40°C, polarity +

Evaluation method: PSS WINGPC Unity

EZChrom method: PMMA.met

5 EZChrom sequence: POLOXAMER.seq

WINGPC method: POLOXAMER.met

Internal standard: 200 µl of ethylene glycol Art. 109621 batch K38533121
ad 200 ml of eluent = ID2013-10-31_KB01

10 **Sample preparation:**

20 – 25 mg of the sample are dissolved in 10 ml of sample solvent in a thermoshaker, cooled to room temperature and injected twice each. Before and after the sample injections, sample solvent was injected twice in each case.

15

Performance of the analyses:

The standard and sample solutions were each injected twice. Sample solvent was in each case injected twice before, between and after the standard and sample injections.

20

PMMA standard solution:

As calibration solutions, 20 - 25 mg of PSS PMMA calibration standards Mp 410 mmg14064, Mp 1.020 mmg19113, Mp 1.960 mmg23084, Mp 4.250 mmg24042, Mp 14.300 mmg20124, Mp 23.500 mmg15087, Mp 67.000 mmg2096, Mp 128.000 mmbs15, Mp 263.000 mml19095, Mp 579.000 mm6086, Mp 898.000 mm1086 and Mp 2.740.000 mm7086 were weighed out accurately into a 20 ml volumetric flask, dissolved with sample solvent in the thermomixer and made up to the calibration mark with sample solvent, analysed analogously and a calibration curve was drawn up with poly-


25

30 nome 3 as fit.

Evaluation:

Any elution time shifts are corrected via the internal standard.

Example 1. Synthesis of allylfluorotris(pentafluoroethyl)phosphorane by reaction of difluorotris(pentafluoroethyl)phosphorane and allyl-magnesium bromide



15 Difluorotris(pentafluoroethyl)phosphorane, $(\text{C}_2\text{F}_5)_3\text{PF}_2$ (82.8 g, 194 mmol), is initially introduced in a 500 ml round-bottomed flask, cooled (0°C) and emulsified in diethyl ether (100 ml). Allylmagnesium bromide, $\text{CH}_2=\text{CHCH}_2\text{MgBr}$ (100 ml of a 1 mol/l solution in diethyl ether; 100 mmol), is added to this emulsion over the course of one hour. A white solid precipitates out, and the reaction mother liquor becomes a yellow colour. The suspension is

20 stirred at 0°C for 1 hour and at room temperature for 1 hour. The reaction suspension is subsequently filtered, and the solid is washed twice with diethyl ether (25 ml each time). The ether phases are combined and ether and excess $(\text{C}_2\text{F}_5)_3\text{PF}_2$ are condensed off at 0°C in vacuo (10^{-1} mbar). The yellow liquid remaining consists principally of product, $(\text{C}_2\text{F}_5)_3\text{PF}-$

25 $(\text{CH}_2\text{CH}=\text{CH}_2)$, and small amounts of $(\text{C}_2\text{F}_5)_3\text{PF}_2$ and $(\text{C}_2\text{F}_5)_3\text{P}=\text{O}$. Pure allylfluorotris(pentafluoroethyl)phosphorane, $(\text{C}_2\text{F}_5)_3\text{PF}(\text{CH}_2\text{CH}=\text{CH}_2)$ (37.1 g, 83 mmol), can be isolated as a clear and colourless liquid with a yield of 83% by condensation at 30°C in vacuo (10^{-3} mbar). The isolated product is characterised by means of ^1H , ^{19}F and ^{31}P NMR spectra.

30

NMR (lock substance: CD_3CN film; δ in ppm):


^1H NMR: 3.56 m (2H), 5.32 m (2H), 5.71 m (1H)

^{19}F NMR: -7.3^* d, $^1J_{\text{F,P}} = 827$ Hz (1F), -81.9^* m (9F), -122.0^* d, $^2J_{\text{F,P}} = 80$ Hz (6F)

^{31}P NMR: -42.0 d, sep, t, d, $^1J_{\text{P,F}} = 822$ Hz, $^2J_{\text{P,F}} = 78$ Hz, $^2J_{\text{P,H}} = 14$ Hz, $^3J_{\text{P,H}} = 5$ Hz (1P)

5 * signals broadened

Example 2. Synthesis of allylpentafluoroethylphosphinic acid by hydrolysis of allylfluorotris(pentafluoroethyl)phosphorane in water




15 Clear and colourless allylfluorotris(pentafluoroethyl)phosphorane, $(\text{C}_2\text{F}_5)_3\text{PF}(\text{CH}_2\text{CH}=\text{CH}_2)$ (33.7 g, 75.2 mmol), is initially introduced in a 100 ml PFA round-bottomed flask, cooled (0°C), and water (10 ml, ~555 mmol) is slowly added. The reaction is very exothermic and is cooled if necessary using ice (0°C). The emulsion is stirred at 0°C to 18°C for

20 1 hour, at 35°C for 1.5 hours, at 50°C for 1.5 hours and finally at 80°C for 3 hours. Evolution of gas can be observed constantly. Excess water is subsequently condensed off at 50°C to 65°C in vacuo (10^{-3} mbar). The crude product remaining is transferred quantitatively into a 100 ml glass

25 flask and condensed at 100°C in vacuo (10^{-3} mbar). Allylpentafluoroethylphosphinic acid, $(\text{C}_2\text{F}_5)(\text{CH}_2\text{CH}=\text{CH}_2)\text{P}(\text{O})\text{OH}$ (14.2 g, 63.5 mmol), can be isolated as a clear and colourless liquid with a yield of 84%. The isolated product is characterised by means of ^1H , ^{19}F and ^{31}P NMR spectra.

30 NMR (lock substance: CD_3CN film; δ in ppm)


^1H NMR: **2.24** m (2H), **4.74** m (2H), **5.14** m (1H).



^{19}F NMR: -81.9 m (3F), -128.4 d, $^2J_{\text{F,P}} = 73$ Hz (2F).

^{31}P NMR: 25.4 t, t, d $^2J_{\text{P,F}} = 83$ Hz, $^2J_{\text{P,H}} = 18$ Hz, $^3J_{\text{P,H}} = 5$ Hz (1P).

Example 3. Synthesis of allylbis(pentafluoroethyl)phosphine oxide by hydrolysis of allylfluorotris(pentafluoroethyl)phosphorane in water



Clear and colourless allylfluorotris(pentafluoroethyl)phosphorane, $(\text{C}_2\text{F}_5)_3\text{PF}(\text{CH}_2\text{CH}=\text{CH}_2)$ (11.45 g, 25.5 mmol), is initially introduced in a 23 mm (internal diameter) FEP reactor, cooled (0°C), and water (1.7 ml, 94 mmol) is added. Two phases form and evolution of gas can be observed. The reaction emulsion is stirred at 0°C for 1.5 hours and at room temperature for 30 minutes. A conversion of 79% to allylbis(pentafluoroethyl)phosphine oxide, $(\text{C}_2\text{F}_5)_2\text{P}(\text{O})(\text{CH}_2\text{CH}=\text{CH}_2)$, can be detected. Secondary compounds are $[\text{H}(\text{H}_2\text{O})_n][(\text{C}_2\text{F}_5)_3\text{PF}_3]$ (21%) and traces of bis(pentafluoroethyl)phosphinic acid, $(\text{C}_2\text{F}_5)_2\text{P}(\text{O})\text{OH}$. The compounds can easily be separated from one another using methods which are known to the person skilled in the art. The mixture can be used without further purification for the further hydrolysis (Example 2). The product is characterised by means of ^1H , ^{19}F and ^{31}P NMR spectra.

25

NMR (lock substance: CD_3CN film; δ in ppm)

^1H NMR: 3.40 m (2H), 5.56 m (2H), 5.80 m (1H).


^{19}F NMR: -81.9 m (6F), -122.1 d, m $^2J_{\text{FA,P}} = 79$ Hz,

$^2J_{\text{FB,P}} = 71$ Hz, $J_{\text{FA,FB}} = 341$ Hz (2FA), -124.1 d, m, $^2J_{\text{FA',P}} =$


$= 79$ Hz, $^2J_{\text{FB',P}} = 71$ Hz, $J_{\text{FA',FB'}} = 310$ Hz (2FB).

^{31}P NMR: 36.4 t, t $^2J_{\text{P,FA}} = ^2J_{\text{P,FA'}} = 79$ Hz, $^2J_{\text{P,FB}} =$

$^2J_{\text{P,FB'}} = 71$ Hz (1P).



30

Example 4. Synthesis of but-3-en-1-ylmagnesium bromide

Magnesium turnings (15.81 g, 650 mmol) in diethyl ether (300 ml) are initially introduced in a 500 ml glass round-bottomed flask, and 4-bromo-1-butene (96.20 g, 713 mmol) is added over the course of 2 hours at room temperature. The brown suspension is stirred at room temperature for a further 30 minutes and subsequently filtered. But-3-en-1-ylmagnesium bromide (91%, ~592 mmol) in diethyl ether can be obtained as a brown solution. The only by-product is 1,7-octadiene (9%). This solution is used without further purification. The product is characterised by means of ^1H and ^{13}C NMR spectra.

10

15

NMR (lock substance: CD_3CN film; δ in ppm)


^1H NMR: **-0.57** t $^3J_{\text{H,H}} = 8$ Hz (2H^{a}), **2.15** t, d, d, d $^3J_{\text{H,H}} = 8$ Hz, $^3J_{\text{H,H}} = 7$ Hz, $^4J_{\text{H,H}} = 1.5$ Hz, $^4J_{\text{H,H}} = 1.1$ Hz (2H^{b}), **4.52** d, d, t $^3J_{\text{H,H}} = 10$ Hz, $^2J_{\text{H,H}} = 3$ Hz, $^4J_{\text{H,H}} = 1.1$ Hz (1H^{e}), **4.72** d, d, t $^3J_{\text{H,H}} = 17$ Hz, $^2J_{\text{H,H}} = 3$ Hz, $^4J_{\text{H,H}} = 1.5$ Hz (1H^{d}), **5.85** d, d, t $^3J_{\text{H,H}} = 17$ Hz, $^3J_{\text{H,H}} = 10$ Hz, $^3J_{\text{H,H}} = 7$ Hz (1H^{c})

^{13}C NMR: **7.5** t, m $^1J_{\text{C,H}} = 108$ Hz, (1C^{a}), **34.1** t, d, d, d $^1J_{\text{C,H}} = 123$ Hz, $^2J_{\text{C,H}} = 5$ Hz, $^3J_{\text{C,H}} = 5$ Hz, $^3J_{\text{C,H}} = 5$ Hz (1C^{b}), **108.7** d, d, t $^1J_{\text{C,H}} = 155$ Hz, $^1J_{\text{C,H}} = 152$ Hz, $^3J_{\text{C,H}} = 6$ Hz (1C^{d}), **148.3** d, t, m $^1J_{\text{C,H}} = 148$ Hz, $^2J_{\text{C,H}} = 6$ Hz (1C^{c}).


20

25

30




Example 5. Synthesis of di(but-3-en-1-yl)zinc by reaction of but-3-en-1-ylmagnesium bromide and zinc chloride



10 Zinc chloride (37.14 g, 272 mmol) is suspended in diethyl ether (500 ml) in a 100 ml glass round-bottomed flask, and the but-3-en-1-ylmagnesium bromide solution (592 mmol in diethyl ether (300 ml)) described in Example 4 is added over the course of 4 hours. A bulky pale-grey precipitate precipitates out. The suspension is stirred at room temperature for 12 h and then filtered. The grey residue is washed with diethyl ether (60 ml). The yellow filtrate and the wash solution are combined, and the majority of the ether is condensed off at 0°C in vacuo (10⁻³ mbar). The product is condensed out of the suspension at 30°C to 40°C in vacuo (10⁻³ mbar) into a cooled (-196°C) trap. Residues of diethyl ether and 1,7-octadiene can be removed in a further condensation at -20°C to -15°C in vacuo (10⁻³ mbar). Further purification can be achieved by re-condensation of the product at 40°C in vacuo (10⁻³ mbar). Di(but-3-en-1-yl)zinc (40.59 g, 231 mmol) can be isolated as a clear and colourless liquid with a yield of 85% and a purity of 99%. The isolated product is characterised by means of ¹H and ¹³C NMR spectra.


25 NMR (lock substance: CD₃CN film; δ in ppm)

¹H NMR: **0.40** t ³J_{H,H} = 8 Hz (4H^a), **2.24** t, d, d, d ³J_{H,H} = 8 Hz, ³J_{H,H} = 6 Hz, ⁴J_{H,H} = 1.7 Hz, ⁴J_{H,H} = 1.2 Hz (4H^b), **4.84** d, d, t ³J_{H,H} = 10 Hz, ²J_{H,H} = 1.8 Hz, ⁴J_{H,H} = 1.2 Hz (2H^c), **4.94** d, d, t ³J_{H,H} = 17 Hz, ²J_{H,H} = 1.8 Hz, ⁴J_{H,H} = 1.7 Hz (2H^d), **5.92** d, d, t ³J_{H,H} = 17 Hz, ³J_{H,H} = 10 Hz, ³J_{H,H} = 6 Hz (2H^e).



¹³C NMR: **15.9** t, t, d, t ¹J_{C,H} = 121.3 Hz, ²J_{C,H} = 4.1 Hz, ²J_{C,H} = 4.0 Hz, ³J_{C,H} = 1.0 Hz (2C^a), **31.3** t, m ¹J_{C,H} = 121.3 Hz (2C^b), **113.1** d, d, t, m ¹J_{C,H} = 157.5 Hz, ¹J_{C,H} = 152.3 Hz, ³J_{C,H} = 6.1 Hz (2C^d), **145.0** d, t, d, d, m ¹J_{C,H} = 121.3 Hz, ²J_{C,H} = 6.2 Hz, ²J_{C,H} = 6.2 Hz, ²J_{C,H} = 5.8 Hz (2C^c).

Example 6. Synthesis of bis(pentafluoroethyl)trifluorophosphorane




Pale-yellow hexylmethylimidazolium bis(pentafluoroethyl)tetrafluorophosphate, [C₆MIM][C₂F₅)₂PF₄] (203.0 g, 396 mmol), is initially introduced in a 500 ml glass round-bottomed flask, warmed (100°C), and freshly distilled yellow SbCl₅ (137.7 g; 460 mmol) is added dropwise over the course of 2.5 h. Bis(pentafluoroethyl)trifluorophosphorane, (C₂F₅)₂PF₃, (bp 46°C), formed is condensed directly into a cooled (−78°C) 300 ml Young U-trap. After a further 30 min at 100°C and 15 min at 150°C, bis(pentafluoroethyl)trifluorophosphorane, (C₂F₅)₂PF₃ (122.1 g; 375 mmol), can be isolated in the trap as a pale-yellow liquid in a yield of 95% (purity 98%). The phosphorane can be used without further purification for subsequent experiments. The isolated product is characterised by means of ¹⁹F and ³¹P NMR spectra.

NMR (lock substance: CD₃CN film; δ in ppm)


¹⁹F NMR: **−55.2** d, qui, sep ¹J_{F,P} = 1145 Hz, ³J_{F,F} = 11 Hz, ⁴J_{F,F} = 7 Hz (3F), **−84.1** q, d ⁴J_{F,F} = 7 Hz, ³J_{F,P} = 2 Hz (6F), **−119.8** d, q ²J_{F,P} = 127 Hz, ³J_{F,F} = 11 Hz (4F)

³¹P NMR: **−40.1** q, qui, sep ¹J_{P,F} = 1145 Hz, ²J_{P,F} = 127 Hz, ³J_{P,F} = 2.0 Hz (1P).



Example 7. Synthesis of bis(pentafluoroethyl)(but-3-en-1-yl)difluorophosphorane by reaction of bis(pentafluoroethyl)trifluorophosphorane and di(but-3-en-1-yl)zinc

5



10


Di(but-3-en-1-yl)zinc (24.27 g, 138 mmol) is dissolved in *n*-pentane (350 ml) in a 1000 ml glass round-bottomed flask, and bis(pentafluoroethyl)trifluorophosphorane, (C₂F₅)₂PF₃ (76.4 g, 234 mmol), is added over the course of 7.5 hours at room temperature. A white solid precipitates out. The suspension is stirred at room temperature for 1.5 hours, and *n*-pentane is subsequently condensed off at −40°C to −25°C in vacuo (10^{−3} mbar). The product which remains is condensed at room temperature in vacuo (10^{−3} mbar). Bis(pentafluoroethyl)(but-3-en-1-yl)difluorophosphorane, (C₂F₅)₂PF₂-(CH₂CH₂CH=CH₂) (82.08 g, 227 mmol), can be isolated as a clear and colourless liquid with a yield of 97% and a purity of 91%. Bis(pentafluoroethyl)-difluorocyclopropylmethylphosphorane, (C₂F₅)₂PF₂(CH₂-c-C₃H₅) (6%) and di(but-3-en-1-yl)zinc (3%) are detected as by-products. This mixture is used without further purification. The impurities can be separated using methods which are known to the person skilled in the art. The product is character-

25 ised by means of ¹H, ¹⁹F, ¹³C and ³¹P NMR spectra.

NMR (lock substance: CD₃CN film; δ in ppm)


¹H NMR: **2.35** m (2H^a), **2.47** m (2H^b), **5.02** d, m ³J_{H,H} = 10 Hz (1H^e), **5.05** d, m ³J_{H,H} = 17 Hz (1H^d), **5.71** d, d, t ³J_{H,H} = 17 Hz, ³J_{H,H} = 10 Hz, ³J_{H,H} = 6 Hz (1H^c)

30



¹³C NMR: **25.8** t, d, t, m ¹J_{C,H} = 133 Hz, ³J_{C,F} = 8 Hz, ²J_{C,P} = 4 Hz (1C^b),
29.0 t, d, t, m ¹J_{C,H} = 123 Hz, ¹J_{C,P} = 108 Hz, ²J_{C,F} = 17 Hz (1C^a), **113.3** t, d,
 q, m ¹J_{C,F} = 284 Hz, ¹J_{C,P} = 86 Hz, ²J_{C,F} = 42 Hz (2CF₂), **116.0** d, d, t, d, m
¹J_{C,H} = 159 Hz, ¹J_{C,H} = 154 Hz, ³J_{C,H} = 6 Hz, ⁴J_{C,P} = 1.5 Hz (1C^d), **118.4** q, t,
 5 d, m ¹J_{C,F} = 286 Hz, ²J_{C,F} = 32 Hz, ²J_{C,P} = 27 Hz (2CF₃), **134.6** d, d, m ¹J_{C,H} =
 156 Hz, ³J_{C,P} = 21 Hz (1C^c)
¹⁹F NMR: **-49.7** d, t, q, m ¹J_{F,P} = 876 Hz, ³J_{F,F} = 14 Hz, ⁴J_{F,F} = 11 Hz
 (2F), **-83.6** t ⁴J_{F,F} = 11 Hz (6F), **-118.0** d, t ²J_{F,P} = 112 Hz, ³J_{F,F} = 14 Hz (4F)
³¹P NMR: **-31.5** t, qui, t, t ¹J_{P,F} = 876 Hz, ²J_{P,F} = 112 Hz, ²J_{P,H} = 18 Hz ,
 10 ³J_{P,H} = 13 Hz (1P).

**Example 8. Synthesis of bis(pentafluoroethyl)(but-3-en-1-yl)phosphine
 oxide by reaction of bis(pentafluoroethyl)(but-3-en-1-yl)difluoro-
 phosphorane and hexamethyldisiloxane using catalytic amounts of
 H₂O**




Hexamethyldisiloxane (76.2 g, 469 mmol) and H₂O (619 mg; 34.4 mmol)
 are added to bis(pentafluoroethyl)(but-3-en-1-yl)difluorophosphorane,
 (C₂F₅)₂PF₂(CH₂CH₂CH=CH₂), from Example 7 (151.4 g, 418 mmol), con-
 taining bis(pentafluoroethyl)difluorocyclopropylmethylphosphorane,
 25 (C₂F₅)₂PF₂(CH₂-c-C₃H₅) (5%) and di(but-3-en-1-yl)zinc (3%)] in a 250 ml
 glass round-bottomed flask, and the mixture is stirred at 100°C for 3.5
 hours with evolution of gas. The product is subsequently condensed at
 room temperature to 30°C in vacuo (10⁻³ mbar). Bis(pentafluoroethyl)(but-
 3-en-1-yl)phosphine oxide, (C₂F₅)₂P(O)(CH₂CH₂CH=CH₂) (131.2 g;
 30 386 mmol), can be isolated as a clear and colourless liquid with a yield of
 92%. By-products are bis(pentafluoroethyl)cyclopropylmethylphosphine

oxide, $(\text{C}_2\text{F}_5)_2\text{P}(\text{O})(\text{CH}_2\text{-c-C}_3\text{H}_5)$ (5%, 6.8 g; 20 mmol), trimethylfluorosilane and hexamethyldisiloxane (13.7 g). This mixture is used without further purification. The compounds can be separated using methods which are known to the person skilled in the art.

5

The product, bis(pentafluoroethyl)(but-3-en-1-yl)-phosphine oxide, $(\text{C}_2\text{F}_5)_2\text{P}(\text{O})(\text{CH}_2\text{CH}_2\text{CH}=\text{CH}_2)$, is characterised by means of ^1H , ^{13}C , ^{19}F and ^{31}P NMR spectra.

10

15

NMR (lock substance: CDCl_3 ; δ in ppm)

^1H NMR: **2.44** m (2H^a), **2.56** m (2H^b), **5.13** d, d, t $^3J_{\text{H,H}} = 10$ Hz, $^2J_{\text{H,H}} = 1.2$ Hz, $^4J_{\text{H,H}} = 1.0$ Hz (1H^e), **5.16** d, t, d $^3J_{\text{H,H}} = 17$ Hz, $^4J_{\text{H,H}} = 1.5$ Hz, $^2J_{\text{H,H}} = 1.2$ Hz (1H^d), **5.86** d, d, t $^3J_{\text{H,H}} = 17$ Hz, $^3J_{\text{H,H}} = 10$ Hz, $^3J_{\text{H,H}} = 6$ Hz (1H^c)


^{13}C NMR: **23.8** t, d, t, m $^1J_{\text{C,H}} = 133$ Hz, $^1J_{\text{C,P}} = 64$ Hz, $^2J_{\text{C,H}} = 6$ Hz (1C^a), **24.1** t, t, d, m $^1J_{\text{C,H}} = 132$ Hz, $^2J_{\text{C,H}} = 6$ Hz, $^2J_{\text{C,H}} = 5$ Hz (1C^b), **112.9** d, d, d, q, m $^1J_{\text{C,FA}} = ^1J_{\text{C,FA'}} = 286$ Hz, $^1J_{\text{C,FB}} = ^1J_{\text{C,FB'}} = ^1J_{\text{C,P}} = 88$ Hz, $^2J_{\text{C,F}} = 41$ Hz (2CF_2), **117.3** d, d, t, d, m $^1J_{\text{C,H}} = 160$ Hz, $^1J_{\text{C,H}} = 154$ Hz, $^3J_{\text{C,H}} = 6$ Hz, $^4J_{\text{C,P}} = 0.9$ Hz (1C^d), **118.4** q, d, d, d, m $^1J_{\text{C,F}} = 287$ Hz, $^2J_{\text{C,FA}} = ^2J_{\text{C,FA'}} = 31$ Hz, $^2J_{\text{C,FB}} = ^2J_{\text{C,FB'}} = 30$ Hz, $^2J_{\text{C,P}} = 17$ Hz (2CF_3), **134.9** d, d, t, d, d $^1J_{\text{C,H}} = 156$ Hz, $^3J_{\text{C,P}} = 16$ Hz, $^2J_{\text{C,H}} = 6$ Hz, $^2J_{\text{C,H}} = 3$ Hz, $^2J_{\text{C,H}} = 3$ Hz (1C^c)

^{19}F NMR: **-80.3** d, m $^3J_{\text{F,P}} = 1.2$ Hz (6F), **-121.7** d, m $^2J_{\text{FA,P}} = 77$ Hz, $^2J_{\text{FB,P}} = 69$ Hz, $^2J_{\text{FA,FB}} = 340$ Hz (2F_A), **-123.6** d, m $^2J_{\text{FA',P}} = 77$ Hz, $^2J_{\text{FB',P}} = 69$ Hz, $^2J_{\text{FA',FB'}} = 310$ Hz (2F_B)

^{31}P NMR: **37.8** t, t, t, t, sep $^2J_{\text{P,FA}} = ^2J_{\text{P,FA'}} = 77$ Hz, $^2J_{\text{P,FB}} = ^2J_{\text{P,FB'}} = 69$ Hz, $^2J_{\text{P,H}} = 10$ Hz, $^3J_{\text{P,H}} = 10$ Hz, $^3J_{\text{P,F}} = 1.2$ Hz (1P).

30

Example 9. Synthesis of (but-3-en-1-yl)(pentafluoroethyl)phosphinic acid by hydrolysis of bis(pentafluoroethyl)(but-3-en-1-yl)phosphine oxide




10 Bis(pentafluoroethyl)(but-3-en-1-yl)phosphine oxide, $(\text{C}_2\text{F}_5)_2\text{P}(\text{O})-(\text{CH}_2\text{CH}_2\text{CH}=\text{CH}_2)$ (130.3 g, 383 mmol), from Example 8 is emulsified with water (100 ml) in a 250 ml glass round-bottomed flask and warmed (50°C). The emulsion is stirred at 50°C for 17 hours with constant evolution of gas. All volatile constituents are subsequently condensed off at room temperature in vacuo (10^{-3} mbar). The product which remains is distilled at 130°C in vacuo (10^{-3} mbar). (Pentafluoroethyl)(but-3-en-1-yl)phosphinic acid, $(\text{C}_2\text{F}_5)-(\text{CH}_2\text{CH}_2\text{CH}=\text{CH}_2)\text{P}(\text{O})\text{OH}$ (89.7 g; 375 mmol), can be isolated as a clear and colourless liquid (94.0 g) with a yield of 93%. The only by-product is pentafluoroethyl(cyclopropylmethyl)phosphinic acid, $(\text{C}_2\text{F}_5)(\text{CH}_2\text{-c-C}_3\text{H}_5)\text{-P}(\text{O})\text{OH}$ (4.3 g; 18 mmol), which results from bis(pentafluoroethyl)cyclopropylmethylphosphine oxide in the starting material. The two compounds can be separated using methods which are known to the person skilled in the art. The isolated product is characterised by means of ^1H , ^{13}C , ^{19}F and ^{31}P NMR spectra.

25

NMR (lock substance: CDCl_3 ; δ in ppm)

30 ^1H NMR: **2.02** m (2H^a), **2.41** m (2H^b), **5.06** d, t, d $^3J_{\text{H,H}} = 10$ Hz, $^4J_{\text{H,H}} = 1.4$ Hz, $^2J_{\text{H,H}} = 1.1$ Hz (1H^e), **5.10** d, t, d $^3J_{\text{H,H}} = 17$ Hz, $^4J_{\text{H,H}} = 1.4$ Hz, $^2J_{\text{H,H}} = 1.2$ Hz (1H^d), **5.83** d, d, t $^3J_{\text{H,H}} = 17$ Hz, $^3J_{\text{H,H}} = 10$ Hz, $^3J_{\text{H,H}} = 6$ Hz (1H^c), **10.86** s $\Delta\nu_{1/2} = 7$ Hz (1OH)




^{13}C NMR: **24.5** t, d, m $^1J_{\text{C,H}} = 129$ Hz, $^2J_{\text{C,P}} = 5$ Hz (1C^{b}), **25.1** t, d, m $^1J_{\text{C,H}} = 129$ Hz, $^1J_{\text{C,P}} = 102$ Hz (1C^{a}), **111.6** t, d, q $^1J_{\text{C,F}} = 276$ Hz, $^1J_{\text{C,P}} = 127$ Hz, $^2J_{\text{C,F}} = 40$ Hz, (1CF_2), **116.5** d, d, t $^1J_{\text{C,H}} = 159$ Hz, $^1J_{\text{C,H}} = 154$ Hz, $^3J_{\text{C,H}} = 6$ Hz (1C^{d}), **119.0** q, t, d $^1J_{\text{C,F}} = 286$ Hz, $^2J_{\text{C,F}} = 31$ Hz, $^2J_{\text{C,P}} = 16$ Hz (1CF_3), **136.3** d, d, t, d, d $^1J_{\text{C,H}} = 155$ Hz, $^3J_{\text{C,P}} = 17$ Hz, $^2J_{\text{C,H}} = 6$ Hz, $^2J_{\text{C,H}} = 3$ Hz, $^2J_{\text{C,H}} = 3$ Hz (1C^{c})

^{19}F NMR: **-80.8** s $\Delta\nu_{1/2} = 5$ Hz (3F), **-121.5** d $^2J_{\text{F,P}} = 81$ Hz (2F)

^{31}P NMR: **34.5** t $^2J_{\text{P,F}} = 81$ Hz (1P).

Example 10. Synthesis of undec-10-en-1-ylmagnesium bromide by reaction of 11-bromo-1-undecene and magnesium




Magnesium turnings (0.53 mg, 21.6 mmol) in diethyl ether (20 ml) are initially introduced in a 100 ml glass round-bottomed flask, and 11-bromo-1-undecene (5.25 g, 22.5 mmol) in diethyl ether (20 ml) is added over the course of 1 hour. The yellow suspension is stirred at room temperature for 30 minutes and subsequently filtered. Undec-10-en-1-ylmagnesium bromide (83%, ~18 mmol) in diethyl ether can be obtained as a yellow solution. By-product is 1,21-docosadiene (11 mol%). This solution is used without further purification. The isolated product is characterised by means of ^1H and ^{13}C NMR spectra.

NMR (lock substance: CD_3CN film; δ in ppm)

^1H NMR: **-0.54** t $^3J_{\text{H,H}} = 8$ Hz (2H^{a}), **1.26-1.29** t $^3J_{\text{H,H}} = 7$ Hz ($10\text{H}^{\text{c-g}}$), **1.36** t, t $^3J_{\text{H,H}} = 7$ Hz, $^3J_{\text{H,H}} = 7$ Hz (2H^{h}), **1.50** t, t

$^3J_{\text{H,H}} = 7$ Hz, $^3J_{\text{H,H}} = 7$ Hz (2H^{b}), **2.01** t, d, t $^3J_{\text{H,H}} = 7$ Hz, $^3J_{\text{H,H}} = 7$ Hz, $^4J_{\text{H,H}} =$




1 Hz (2Hⁱ), **4.86** d, d, t, t ³J_{H,H} = 10 Hz, ²J_{H,H} = 2 Hz, ⁴J_{H,H} = 1 Hz, ⁵J_{H,H} = 1 Hz (1H^m), **4.93** d, d, t ³J_{H,H} = 17 Hz, ²J_{H,H} = 2 Hz, ⁴J_{H,H} = 2 Hz (1H^l), **5.75** d, d, t ³J_{H,H} = 17 Hz, ³J_{H,H} = 10 Hz, ³J_{H,H} = 7 Hz (1H^k)

¹³C{¹H} NMR: **8.5** (1C^a), **29.7** (1C^{b,d-h}), **29.9** (1C^{b,d-h}), **30.3**^o (1C^{b,d-h}), **30.4**^o (1C^{b,d-h}), **30.4**^o (1C^{b,d-h}), **30.6** (1C^{b,d-h}), **34.5** (1Cⁱ), **39.0** (1C^c), **114.2** (1C^j), **139.4** (1C^k).

^o signals superimposed

Example 11. Synthesis of bis(undec-10-en-1-yl)zinc by reaction of undec-10-en-1-ylmagnesium bromide and zinc chloride




Zinc chloride, ZnCl₂ (2.99 g, 21.9 mmol), is suspended in diethyl ether (40 ml) in a 250 ml glass round-bottomed flask, and a solution of undec-10-en-1-ylmagnesium bromide (45.2 mmol, contains 17 mol% of 1,21-docosadiene) in diethyl ether (120 ml) is added over the course of 45 minutes. A bulky white solid rapidly precipitates out. The suspension is filtered under inert gas, and the residue is washed with diethyl ether (10 ml). The pale-yellow filtrate is evaporated together with the wash solution at room temperature in vacuo (10⁻³ mbar). The bulky suspension formed is extracted three times with *n*-pentane (20 ml each time) and filtered under inert conditions. The *n*-pentane phases are subsequently combined, and *n*-pentane is condensed off at 40°C in vacuo (10⁻³ mbar). Di(undec-10-en-1-yl)zinc (6.17 g, 16.6 mmol) can be isolated as a clear and yellow liquid with a yield of 76%. The only by-product is 1,21-docosadiene (3.18 g, 10.4 mmol, 39 mol%). The two compounds can be separated using methods which are known to the person skilled in the art. This solution is used without further

purification. The product, di(undec-10-en-1-yl)zinc, is characterised by means of ^1H and ^{13}C NMR spectra.

NMR (lock substance: CD_3CN film; δ in ppm)

- 5 ^1H NMR: **0.39** t $^3J_{\text{H,H}} = 8$ Hz (4H^{a}), **1.26-1.28** $^\circ$ t $^3J_{\text{H,H}} = 7$ Hz ($20\text{H}^{\text{c-g}}$), **1.36** $^\circ$ t, t $^3J_{\text{H,H}} = 7$ Hz, $^3J_{\text{H,H}} = 7$ Hz (4H^{h}), **1.55** t, t $^3J_{\text{H,H}} = 7$ Hz, $^3J_{\text{H,H}} = 7$ Hz (4H^{b}), **2.00** t, d $^3J_{\text{H,H}} = 7$ Hz, $^3J_{\text{H,H}} = 7$ Hz (4H^{i}), **4.87** d, d, t $^3J_{\text{H,H}} = 10$ Hz, $^2J_{\text{H,H}} = 2$ Hz, $^4J_{\text{H,H}} = 1$ Hz (2H^{m}), **4.93** d, d, t $^3J_{\text{H,H}} = 17$ Hz, $^2J_{\text{H,H}} = 2$ Hz, $^4J_{\text{H,H}} = 2$ Hz (2H^{l}), **5.73** d, d, t $^3J_{\text{H,H}} = 17$ Hz, $^3J_{\text{H,H}} = 10$ Hz, $^3J_{\text{H,H}} = 7$ Hz (2H^{k})
- 10 ^{13}C NMR: **16.8** t, m $^1J_{\text{C,H}} = 120$ Hz (2C^{a}), **26.9** t, m $^1J_{\text{C,H}} = 124$ Hz (2C^{b}), **29.5** $^\circ$ t, m $^1J_{\text{C,H}} = 126$ Hz ($2\text{C}^{\text{d-h}}$), **29.8** $^\circ$ t, m $^1J_{\text{C,H}} = 126$ Hz ($2\text{C}^{\text{d-h}}$), **30.2** $^\circ$ t, m $^1J_{\text{C,H}} = 126$ Hz ($2\text{C}^{\text{d-h}}$), **30.3** $^\circ$ t, m $^1J_{\text{C,H}} = 126$ Hz ($2\text{C}^{\text{d-h}}$), **30.4** $^\circ$ t, m $^1J_{\text{C,H}} = 126$ Hz ($2\text{C}^{\text{d-h}}$), **34.4** t, m $^1J_{\text{C,H}} = 126$ Hz (2C^{j}), **37.1** t, m $^1J_{\text{C,H}} = 124$ Hz (2C^{c}), **114.6** d, d, t $^1J_{\text{C,H}} = 157$ Hz, $^1J_{\text{C,H}} = 153$ Hz, $^3J_{\text{C,H}} = 6$ Hz (2C^{l}), **139.0** d, d, d, t $^1J_{\text{C,H}} = 150$ Hz, $^2J_{\text{C,H}} = 6$ Hz, $^2J_{\text{C,H}} = 6$ Hz, $^2J_{\text{C,H}} = 6$ Hz (2C^{k}).
- * signals broadened
- 20 $^\circ$ signals superimposed

Example 12. Synthesis of bis(pentafluoroethyl)difluoro(undec-10-en-1-yl)phosphorane by reaction of di(undec-10-en-1-yl)zinc and bis(pentafluoroethyl)trifluorophosphorane



- 30 Di(undec-10-en-1-yl)zinc (2.39 g, 6.43 mmol; additionally contains 1.53 g of 1,21-docosadiene) is dissolved in *n*-pentane (40 ml) in a 100 ml glass

round-bottomed flask. Bis(pentafluoroethyl)trifluorophosphorane, $(\text{C}_2\text{F}_5)_2\text{PF}_3$ (2.54 g, 7.79 mmol), is added to this solution over the course of 10 minutes. The solution is stirred at room temperature for 30 minutes. A suspension forms. The conversion (96%, 7.48 mmol) to bis(pentafluoroethyl)difluoro(undec-10-en-1-yl)phosphorane, $(\text{C}_2\text{F}_5)_2\text{PF}_2(\text{C}_9\text{H}_{18}\text{CH}=\text{CH}_2)$, is virtually quantitative. The only by-product formed besides ZnF_2 is bis(pentafluoroethyl)(cyclopropyloctyl)difluorophosphorane, $(\text{C}_2\text{F}_5)_2\text{PF}_2(\text{C}_8\text{H}_{16}\text{-cyclo-C}_3\text{H}_5)$ (4%). In addition, 1,21-docosadiene from the starting material (see Example 10) are also in the suspension. The compounds can be separated using methods which are known to the person skilled in the art. The suspension is used here without further purification. The product is characterised by means of ^1H , $^{13}\text{C}\{^1\text{H}\}$, ^{19}F and ^{31}P NMR spectra.


NMR (lock substance: CD_3CN film; δ in ppm)

^1H NMR: **1.28-1.31°** s (10 $\text{H}^{\text{c-g}}$), **1.37°** t, t $^3J_{\text{H,H}} = 7$ Hz, $^3J_{\text{H,H}} = 7$ Hz (2 H^{h}), **1.66** d, t, t $^3J_{\text{H,P}} = 13$ Hz, $^3J_{\text{H,H}} = 7$ Hz, $^3J_{\text{H,H}} = 7$ Hz (2 H^{b}), **2.02** t, d, t, d $^3J_{\text{H,H}} = 7$ Hz, $^3J_{\text{H,H}} = 7$ Hz, $^4J_{\text{H,H}} = 1.6$ Hz, $^4J_{\text{H,H}} = 1.2$ Hz (2 H^{i}), **2.37** d, t, t $^2J_{\text{H,P}} = 18$ Hz, $^3J_{\text{H,F}} = 17$ Hz, $^3J_{\text{H,H}} = 7$ Hz (2 H^{a}), **4.87** d, d, t, t $^3J_{\text{H,H}} = 10$ Hz, $^2J_{\text{H,H}} = 1.9$ Hz, $^4J_{\text{H,H}} = 1.2$ Hz, $^5J_{\text{H,H}} = 0.9$ Hz (1 H^{m}), **4.94** d, d, t $^3J_{\text{H,H}} = 17$ Hz, $^2J_{\text{H,H}} = 1.9$ Hz, $^4J_{\text{H,H}} = 1.6$ Hz (1 H^{l}), **5.74** d, d, t $^3J_{\text{H,H}} = 17$ Hz, $^3J_{\text{H,H}} = 10$ Hz, $^3J_{\text{H,H}} = 7$ Hz (1 H^{k})

$^{13}\text{C}\{^1\text{H}\}$ NMR: **22.1** t, d $^3J_{\text{C,F}} = 7$ Hz, $^2J_{\text{C,P}} = 6$ Hz (1 C^{b}), **29.0** d $^3J_{\text{C,P}} = 1.7$ Hz (1 C^{c}), **29.3** (1 $\text{C}^{\text{d-h}}$), **29.5°** (1 $\text{C}^{\text{d-h}}$), **29.5°** (1 $\text{C}^{\text{d-h}}$), **30.0°** d, t $^1J_{\text{C,P}} = 91$ Hz, $^2J_{\text{C,F}} = 17$ Hz (1 C^{a}), **30.0°** (1 $\text{C}^{\text{d-h}}$), **30.1°** (1 $\text{C}^{\text{d-h}}$), **34.1** (1 C^{j}), **114.0** (1 C^{l}), **138.7** (1 C^{k}), **n.b.** (2 C_2F_5)


^{19}F NMR: **-49.4** d, t, qui, sep $^1J_{\text{F,P}} = 875$ Hz, $^3J_{\text{F,H}} = 17$ Hz, $^3J_{\text{F,F}} = 14$ Hz, $^4J_{\text{F,F}} = 11$ Hz (2F), **-82.7** t $^4J_{\text{F,F}} = 11$ Hz (6F), **-117.5** d, t $^2J_{\text{F,P}} = 111$ Hz, $^3J_{\text{F,F}} = 14$ Hz (4F)

^{31}P NMR: **-30.9** t, qui, t, t $^1J_{\text{P,F}} = 875$ Hz, $^2J_{\text{P,F}} = 111$ Hz, $^2J_{\text{P,H}} = 18$ Hz, $^3J_{\text{P,H}} = 13$ Hz (1P).



° signals superimposed

Example 13. Synthesis of bis(pentafluoroethyl)(undec-10-en-1-yl)-phosphine oxide by reaction of bis(pentafluoroethyl)(undec-10-en-1-yl)difluorophosphorane and hexamethyldisiloxane



The suspension from Example 12 consisting of bis(pentafluoroethyl)(undec-10-en-1-yl)difluorophosphorane, $(\text{C}_2\text{F}_5)_2\text{PF}_2(\text{C}_9\text{H}_{18}\text{CH}=\text{CH}_2)$ (7.48 mmol) in *n*-pentane (40 ml) (additionally contains bis(pentafluoroethyl)(cycloprop-8-yloctyl)difluorophosphorane, $(\text{C}_2\text{F}_5)_2\text{PF}_2(\text{C}_8\text{H}_{16}\text{-cyclo-C}_3\text{H}_5)$ (4%) and ZnF_2) is initially introduced in a 100 ml glass round-bottomed flask, and *n*-pentane is distilled off at 80°C. Hexamethyldisiloxane (2.32 g, 14.3 mmol) and water (2 g, 110 mmol) is subsequently added and stirred at room temperature for 45 minutes. A conversion of 88% to bis(pentafluoroethyl)(undec-10-en-1-yl)phosphine oxide, $(\text{C}_2\text{F}_5)_2\text{P}(\text{O})(\text{C}_9\text{H}_{18}\text{CH}=\text{CH}_2)$, can be detected in the yellow mother liquor. By-products are bis(pentafluoroethyl)(cycloprop-8-yloctyl)phosphine oxide, $(\text{C}_2\text{F}_5)_2\text{P}(\text{O})(\text{C}_8\text{H}_{16}\text{-cyclo-C}_3\text{H}_5)$ (4 mol%), which results from bis(pentafluoroethyl)(cycloprop-8-yloctyl)difluorophosphorane in the starting material, and (pentafluoroethyl)(undec-10-en-1-yl)phosphinic acid, $(\text{C}_2\text{F}_5)(\text{C}_9\text{H}_{18}\text{CH}=\text{CH}_2)\text{P}(\text{O})\text{OH}$ (8 mol%). In addition, undecene, ZnF_2 and 1,21-docosadiene are also from the starting material (see Example 11). The compounds can be separated using methods which are known to the person skilled in the art. The suspension is used here without further purification. The product is characterised by means of ^1H , $^{13}\text{C}\{^1\text{H}\}$, ^{19}F and ^{31}P NMR spectra.

NMR (lock substance: CD₃CN film, δ in ppm)


¹H NMR: **1.28-1.30**^o s (8H^{d-g}), **1.38**^o t, t ³J_{H,H} = 7 Hz, ³J_{H,H} = 7 Hz (2H^h), **1.47** t, t ³J_{H,H} = 7 Hz, ³J_{H,H} = 6 Hz, (2H^c), **1.78** d, t, t ³J_{H,P} = 10 Hz, ³J_{H,H} = 8 Hz, ³J_{H,H} = 8 Hz (2H^b), **2.02** t, d, t, d ³J_{H,H} = 7 Hz, ³J_{H,H} = 7 Hz, ⁴J_{H,H} = 1 Hz, ⁴J_{H,H} = 1 Hz (2Hⁱ), **2.29** d, t ²J_{H,P} = 11 Hz, ³J_{H,H} = 8 Hz (2H^a), **4.87** d, d, t, t ³J_{H,H} = 10 Hz, ²J_{H,H} = 2 Hz, ⁴J_{H,H} = 1 Hz, ⁵J_{H,H} = 1 Hz (1H^m), **4.94** d, d, t ³J_{H,H} = 17 Hz, ²J_{H,H} = 2 Hz, ⁴J_{H,H} = 2 Hz (1H^l), **5.74** d, d, t ³J_{H,H} = 17 Hz, ³J_{H,H} = 10 Hz, ³J_{H,H} = 7 Hz (1H^k)

¹³C{¹H} NMR: **20.1** d ²J_{C,P} = 5 Hz (1C^b), **24.1** d ¹J_{C,P} = 61 Hz (1C^a), **29.1** d ⁴J_{C,P} = 0.8 Hz (1C^d), **29.2** (1C^{e-h}), **29.6** (1C^{e-h}), **30.0**^o (1C^{e-h}), **30.1**^o (1C^{e-h}), **30.9** d ³J_{C,P} = 15 Hz (1C^c), **34.1** (1C^l), **112.9** t, m ¹J_{C,F} = 286 Hz (2CF₂), **114.3** (1C^l), **118.4** q, m ¹J_{C,F} = 287 Hz (2CF₃), **138.6** (1C^k)


¹⁹F NMR: **-80.0** d ³J_{F,P} = 3 Hz (6F), **-121.5** d, m ²J_{FA,P} = 75 Hz, ²J_{FB,P} = 66 Hz, ²J_{FA,FB} = 340 Hz (2F_A), **-123.5** d, m, ²J_{FA',P} = 75 Hz, ²J_{FB',P} = 66 Hz, ²J_{FA',FB'} = 310 Hz (2F_B)

³¹P NMR: **37.6** t, t, t, t ²J_{P,FA} = ²J_{P,FA'} = 75 Hz, ²J_{P,FB} = ²J_{P,FB'} = 66 Hz, ²J_{P,H} = 11 Hz, ³J_{P,H} = 10 Hz (1P).

^o signals superimposed



Example 14. Synthesis of pentafluoroethyl(undec-10-en-1-yl)phosphinic acid by hydrolysis of bis(pentafluoroethyl)(undec-10-en-1-yl)-phosphine oxide



Water (7 g, 390 mmol) is added to the suspension from Example 13, bis-(pentafluoroethyl)(undec-10-en-1-yl)phosphine oxide, $(\text{C}_2\text{F}_5)_2\text{P}(\text{O})-(\text{C}_9\text{H}_{18}\text{CH}=\text{CH}_2)$ [besides undecene, ZnF_2 and 1,21-docosadiene, additionally contains bis(pentafluoroethyl)(cycloprop-8-yloctyl)phosphine oxide, $(\text{C}_2\text{F}_5)_2\text{P}(\text{O})(\text{C}_8\text{H}_{16}-\text{c}-\text{C}_3\text{H}_5)$ (4 mol%), and pentafluoroethyl(undec-10-en-1-yl)phosphinic acid, $(\text{C}_2\text{F}_5)(\text{C}_9\text{H}_{18}\text{CH}=\text{CH}_2)\text{P}(\text{O})\text{OH}$ (8 mol%)], in a 250 ml glass round-bottomed flask and warmed (50°C). This emulsion is stirred at 50°C for 21 hours and at 100°C for 1 hour. The emulsion is subsequently extracted with hot *n*-pentane (60 ml) and *n*-hexane (60 ml) under reflux.

The organic phases are combined and washed with water (10 ml). All volatile constituents from the organic phase are removed at room temperature to 90°C in vacuo (10^{-3} mbar). Pentafluoroethyl(undec-10-en-1-yl)phosphinic acid, $(\text{C}_2\text{F}_5)(\text{C}_9\text{H}_{18}\text{CH}=\text{CH}_2)\text{P}(\text{O})\text{OH}$ (2.32 g, 6.9 mmol), can be isolated as a yellow solid with a yield of 88%. By-products are pentafluoroethyl(cycloprop-8-yloctyl)phosphinic acid, $(\text{C}_2\text{F}_5)(\text{C}_8\text{H}_{16}-\text{cyclo}-\text{C}_3\text{H}_5)\text{P}(\text{O})\text{OH}$ (4%), and 1,21-docosadiene from Example 12. The compounds can be removed using methods which are known to the person skilled in the art. The product is characterised by means of ^1H , $^{13}\text{C}\{^1\text{H}\}$, ^{19}F and ^{31}P NMR spectra.

NMR (lock substance: toluene- d_8 ; δ in ppm)

^1H NMR: **1.27-1.32°** s

($10\text{H}^{\text{c-g}}$), **1.36°** t $^3J_{\text{H,H}} = 7$ Hz

(2H^{h}), **1.83°** s (2H^{b}), **1.99°** t,

d, t, $^3J_{\text{H,H}} = 7$ Hz, $^3J_{\text{H,H}} =$

7 Hz, $^4J_{\text{H,H}} = 1$ Hz (2H^{i}), **2.05°** d, t $^2J_{\text{H,P}} = 12$ Hz, $^3J_{\text{H,H}} = 7$ Hz (2H^{a}), **4.97** d,

d, t $^3J_{\text{H,H}} = 10$ Hz, $^2J_{\text{H,H}} = 2$ Hz, $^4J_{\text{H,H}} = 1$ Hz (1H^{m}), **5.02** d, d, t $^3J_{\text{H,H}} = 17$ Hz,


$^2J_{\text{H,H}} = 2$ Hz, $^4J_{\text{H,H}} = 2$ Hz (1H^{l}), **5.78** d, d, t $^3J_{\text{H,H}} = 17$ Hz, $^3J_{\text{H,H}} = 10$ Hz, $^3J_{\text{H,H}}$

$= 7$ Hz (1H^{k}), **13.01** s (1H^{n})

$^{13}\text{C}\{^1\text{H}\}$ NMR: **23.6°** (1C^{b}), **25.9°** d $^1J_{\text{C,P}} = 103$ Hz (1C^{a}), **29.8°** d $^4J_{\text{C,P}} =$

0.9 Hz (1C^{d}), **29.8°** ($1\text{C}^{\text{e-h}}$), **29.9** ($1\text{C}^{\text{e-h}}$), **30.1** ($1\text{C}^{\text{e-h}}$), **30.3** ($1\text{C}^{\text{e-h}}$), **31.2** d

$^3J_{\text{C,P}} = 16$ Hz (1C^{c}), **34.7** (1C^{i}), **114.9** (1C^{l}), **139.5** (1C^{k}), **n.b.** ($1\text{C}_2\text{F}_5$)



^{19}F NMR: **-80.5** s (3F), **-127.3** d $^2J_{\text{F,P}} = 79$ Hz (2F)


^{31}P NMR: **-35.7** t, t, t $^2J_{\text{P,F}} = 79$ Hz, $^2J_{\text{P,H}} = 12$ Hz, $^3J_{\text{P,H}} = 12$ Hz (1P).

* signals broadened

° signals superimposed

5

Example 15. Synthesis of 4-styrylmagnesium chloride by reaction of 4-chlorostyrene and magnesium




Magnesium turnings (1.78 g, 73.2 mmol) are suspended in tetrahydrofuran (20 ml) in a 100 ml glass round-bottomed flask and activated using bromoethane, $\text{C}_2\text{H}_5\text{Br}$ (1.16 g, 10.6 mmol). After 10 minutes, the THF mother liquor is decanted. The activated magnesium turnings (1.52 g, 62.6 mmol) are re-suspended in THF (60 ml), 4-chlorostyrene (7.24 g, 52.2 mmol) is added and warmed (70°C). After 1 hours at 70°C , a brown-black suspension can be obtained. The conversion to 4-styrylmagnesium chloride is 98%. The brown-black THF mother liquor can be stored cooled (0°C) for some time. The product is characterised by ^1H and ^{13}C NMR spectra.


NMR (lock substance: CD_3CN film; δ in ppm)

25 ^1H NMR: **4.96** d, d $^3J_{\text{H,H}} = 11$ Hz, $^2J_{\text{H,H}} = 1.6$ Hz (1H^g), **5.62** d, d $^3J_{\text{H,H}} = 18$ Hz, $^2J_{\text{H,H}} = 1.6$ Hz (1H^f), **6.62** d, d $^3J_{\text{H,H}} = 18$ Hz, $^3J_{\text{H,H}} = 11$ Hz (1H^e), **7.10** d $^3J_{\text{H,H}} = 8$ Hz (2H^c), **7.71** d $^3J_{\text{H,H}} = 8$ Hz (2H^b)

30 ^{13}C NMR: **108.7** d, d $^1J_{\text{C,H}} = 159$ Hz, $^1J_{\text{C,H}} = 154$ Hz (1C^f), **123.4** d, d, d, d, m $^1J_{\text{C,H}} = 151$ Hz, $^3J_{\text{C,H}} = 5$ Hz, $^3J_{\text{C,H}} = 4$ Hz, $^4J_{\text{C,H}} = 4$ Hz (2C^c), **133.1** m (1C^d), **139.6** d, t, d, m $^1J_{\text{C,H}} = 150$ Hz, $^3J_{\text{C,H}} = 5$ Hz, $^2J_{\text{C,H}} = 3$ Hz (1C^e), **140.8** d, d, m $^1J_{\text{C,H}} = 151$ Hz, $^2J_{\text{C,H}} = 12$ Hz (2C^b), **172.2** m (1C^a).




Example 16. Synthesis of di(4-styryl)zinc by reaction of 4-styryl-magnesium chloride and zinc chloride




4-Styrylmagnesium chloride (51.2 mmol) in tetrahydrofuran (60 ml) from Example 15 is initially introduced in a 100 ml glass round-bottomed flask and cooled (0°C). Zinc chloride, ZnCl₂ (3.35 g, 24.6 mmol), is added to this THF solution. The suspension is stirred at 0°C for 2.5 hours and subsequently centrifuged. The yellow mother liquor is decanted into a 100 ml glass round-bottomed flask and THF is condensed off at 0°C in vacuo (10⁻³ mbar). A white solid remains behind. This is extracted three times with toluene (50 ml each time). Toluene is condensed off from the combined toluene phases at 0°C in vacuo (10⁻³ mbar) in a 250 ml glass round-bottomed flask. Since THF can still be detected in the resultant white solid, the solid is suspended two further times in toluene (20 ml each time). All volatile compounds are subsequently condensed off again at 0°C in vacuo (10⁻³ mbar). Distyrylzinc·3THF (6.84 g, 14.0 mmol) can be isolated as a white solid with a yield of 57%. The isolated product is characterised by means of ¹H and ¹³C NMR spectra.

NMR (lock substance: CD₃CN; δ in ppm)

25 ¹H NMR: **5.11** d ³J_{H,H} = 11 Hz (2H^g), **5.73** d ³J_{H,H} = 18 Hz (2H^f), **6.71** d, d ³J_{H,H} = 18 Hz, ³J_{H,H} = 11 Hz (2H^e), **7.25** d ³J_{H,H} = 8 Hz (4H^c), **7.59** d ³J_{H,H} = 8 Hz (4H^b)



30 ¹³C NMR: **111.7** d, d ¹J_{C,H} = 159 Hz, ¹J_{C,H} = 155 Hz (2C^f), **125.0** d ¹J_{C,H} = 153 Hz (4C^c), **133.9** m (2C^d), **139.2** d ¹J_{C,H} = 152 Hz (2C^e), **139.6** d, d ¹J_{C,H} = 156 Hz, ²J_{C,H} = 11 Hz (4C^b), **160.5** m (2C^a).

Example 17. Synthesis of pentafluoroethyl)tetrafluorophosphorane


5

Pale-yellow hexylmethylimidazolium pentafluoroethylpentafluorophosphate, $[\text{C}_6\text{MIM}][\text{C}_2\text{F}_5\text{PF}_5]$ (10.52 g, 25.52 mmol), is initially introduced in a 10 ml glass reactor with J. Young tap, cooled (-78°C), and antimony pentafluoride, SbF_5 (6.88 g, 31.74 mmol) is added. The reaction solution is warmed (RT), during which an emulsion forms. After 1.5 h at RT, pentafluoroethyltetrafluorophosphorane, $\text{C}_2\text{F}_5\text{PF}_4$, is formed quantitatively as a very volatile clear and colourless liquid. The product is used directly without purification for subsequent experiments. Isolated product can be characterised by means of ^{19}F and ^{31}P NMR spectra.

10

15

NMR (lock substance: CD_3CN film; δ in ppm)


^{19}F NMR: -60.1 d, t, q $^1J_{\text{F,P}} = 1090$ Hz, $^3J_{\text{F,F}} = 8$ Hz, $^4J_{\text{F,F}} =$  6 Hz (4F), -84.7 qui, d $^4J_{\text{F,F}} = 6$ Hz, $^3J_{\text{F,P}} = 4$ Hz (3F), -120.7 d, qui $^2J_{\text{F,P}} = 125$ Hz, $^3J_{\text{F,F}} = 8$ Hz (2F)

20

^{31}P NMR: -61.2 qui, t $^1J_{\text{P,F}} = 1091$ Hz, $^2J_{\text{P,F}} = 125$ Hz (1P).

Example 18. Synthesis of pentafluoroethyl-(4-styryl)trifluorophosphorane by reaction of di(4-styryl)zinc and pentafluoroethyltetrafluorophosphorane

25



30

Di(4-styryl)zinc·3THF (6.60 g, 13.5 mmol) is suspended in *n*-pentane (100 ml) in a 250 ml glass round-bottomed flask with subsequent cooled (-80°C) condenser and cooled (0°C). Pentafluoroethyltetrafluorophosphorane, $\text{C}_2\text{F}_5\text{PF}_4$ (5.06 g, 22.4 mmol), is condensed into this suspension over the course of 15 minutes. The yellow suspension is stirred at 0°C for a

further 15 min and, when conversion is complete, warmed to room temperature. The suspension is subsequently centrifuged, and the pink-coloured mother liquor is decanted. The yield of pentafluoroethyl-(4-styryl)-trifluorophosphorane, $C_2F_5PF_3(C_6H_4CH=CH_2)$, in *n*-pentane is 49%. The product is characterised in *n*-pentane by means of 1H , ^{13}C , ^{19}F and ^{31}P NMR spectra.

NMR (lock substance: CD_3CN film; δ in ppm)


1H NMR: **5.41** d $^3J_{H,H} = 11$ Hz ($1H^g$), **5.88** d $^3J_{H,H} = 18$ Hz ($1H^f$), **6.70** d, d $^3J_{H,H} = 18$ Hz, $^3J_{H,H} = 11$ Hz ($1H^e$), **7.47** d, d $^3J_{H,H} = 8$ Hz, $^4J_{H,P} = 6$ Hz ($2H^c$), **8.04** d, d, m $^3J_{H,P} = 15$ Hz, $^3J_{H,H} = 8$ Hz ($2H^b$)

^{13}C NMR: **118.5** d, d $^1J_{C,H} = 162$ Hz, $^1J_{C,H} = 155$ Hz ($1C^f$), **127.3** d, d, d, d $^1J_{C,H} = 161$ Hz, $^3J_{C,P} = 19$ Hz, $^2J_{C,H} = 6$ Hz, $^3J_{C,H} = 6$ Hz ($2C^e$), **136.0** d, m $^1J_{C,H} = 157$ Hz ($1C^e$), **138.8** d, d, q, m $^1J_{C,H} = 166$ Hz, $^2J_{C,P} = 15$ Hz, $^3J_{C,F} = 7$ Hz ($2C^b$), **145.8** m ($1C^d$), **n.d.** ($1C^a$), **n.d.** ($1C_2F_5$)


^{19}F NMR: **-70.5*** s (3F), **-82.3** t, d, q $^4J_{F,F} = 7$ Hz, $^3J_{F,P} = 7$ Hz, $^3J_{F,F} = 2$ Hz (3F), **-118.6** d, q, q $^2J_{F,P} = 116$ Hz, $^3J_{F,F} = 12$ Hz, $^3J_{F,F} = 2$ Hz (2F)

^{31}P NMR: **-40.5** q, t, t, t, $^1J_{P,F} = 965$ Hz, $^2J_{P,F} = 116$ Hz, $^3J_{P,H} = 15$ Hz, $^4J_{P,H} = 6$ Hz (1P).

* signals broadened



Example 19. Synthesis of pentafluoroethyl-(4-styryl)phosphinic acid by hydrolysis of pentafluoroethyl-(4-styryl)trifluorophosphorane using hexamethyldisiloxane and water



Hexamethyldisiloxane (7.35 g, 45.3 mmol) and water (1.02 g, 56.6 mmol) are added to pentafluoroethyl-(4-styryl)trifluorophosphorane, (C₂F₅)-(4-C₆H₄CH=CH₂)PF₃ (11.2 mmol), in *n*-pentane (100 ml) from Example 18 in a 250 ml glass round-bottomed flask. A colourless emulsion resulted. After 2.5 hours at room temperature, the upper *n*-pentane phase contained neither (C₂F₅)-(4-C₆H₄CH=CH₂)PF₃ nor product. The *n*-pentane phase was decanted, the lower phase was suspended in water (10 ml) and washed twice with *n*-pentane (10 ml each time). The small proportion of solid is filtered off and all volatile constituents of the mother liquor are condensed off at room temperature in vacuo (10⁻³ mbar). Pentafluoroethyl-(4-styryl)-phosphinic acid, (C₂F₅)(CH₂=CH-C₆H₄)P(O)OH·0.5H₂O (3.32 g, 11.2 mmol), can be isolated as a beige tacky solid with quantitative yield. The isolated product is characterised by means of ¹H and ¹³C NMR spectra.

NMR (lock substance: CD₃CN; δ in ppm)


¹H NMR: **5.49** d ³J_{H,H} = 11 Hz (1H^g), **6.00** d

³J_{H,H} = 18 Hz (1H^f), **6.83** d, d ³J_{H,H} = 18 Hz,

³J_{H,H} = 11 Hz (1H^e), **7.63** d, d ³J_{H,H} = 8 Hz,

⁴J_{H,P} = 4 Hz (2H^c), **7.84** d, d, m ³J_{H,P} = 13 Hz,

³J_{H,H} = 8 Hz (2H^b), **9.51** s (OH)



¹³C NMR: **112.6** t, d, q ¹J_{C,F} = 276.6 Hz, ¹J_{C,P} = 136.7 Hz, ²J_{C,F} = 38.7 Hz

(1CF₂), **118.8** d, d ¹J_{C,H} = 161 Hz, ¹J_{C,H} = 155 Hz (1C^f), **120.0** q, t, d ¹J_{C,F} =

285.9 Hz, ²J_{C,F} = 31.1 Hz, ²J_{C,P} = 16.5 Hz (1CF₃), **124.9** d, t, m ¹J_{C,P} =

150.8 Hz, ³J_{C,H} = 7.6 Hz (1C^a) **127.6** d, d, d, d, m ¹J_{C,H} = 161.5 Hz, ³J_{C,P} =

14.7 Hz, ²J_{C,H} = 5.8 Hz, ³J_{C,H} = 5.6 Hz (1C^c), **134.5** d, d, d, m ¹J_{C,H} =

167.0 Hz, ²J_{C,P} = 11.1 Hz, ²J_{C,H} = 6.8 Hz (1C^b), **136.6** d, d, d, d, m ¹J_{C,H} =


156.9 Hz, ³J_{C,H} = 4.4 Hz, ³J_{C,H} = 4.4 Hz, ⁵J_{C,P} = 1.5 Hz (1C^e), **144.6** m (1C^d)

¹⁹F NMR: **-80.9** t, d ³J_{F,F} = 1.8 Hz, ³J_{F,P} = 1.0 Hz (3F), **-127.1** d, q ²J_{F,P} =

80.0 Hz, ³J_{F,F} = 1.8 Hz (2F)

³¹P NMR: **17.5** t, t, t ²J_{P,F} = 79.9 Hz, ³J_{P,H} = 12.4 Hz, ⁴J_{P,H} = 3.7 Hz (1P).

Example 20. Synthesis of bis(pentafluoroethyl)difluoro-3,4,4-trifluorobut-3-en-1-ylphosphorane from bis(pentafluoroethyl)trifluorophosphorane and 3,4,4-trifluorobut-3-en-1-ylmagnesium bromide




A cold (-50°C) yellow diethyl ether solution of 3,4,4-trifluorobut-3-en-1-ylmagnesium bromide, $\text{CF}_2=\text{CFCH}_2\text{CH}_2\text{MgBr}$ (33 mmol in 50 ml, additionally contains 1,1,2,7,8,8-hexafluoroocta-1,7-diene and 1,1,2-trifluorobut-1-ene), is reacted with bis(pentafluoroethyl)trifluorophosphorane, $(\text{C}_2\text{F}_5)_2\text{PF}_3$ (9.40 g, 28.8 mmol), in a 100 ml glass round-bottomed flask. A white solid precipitates out. The suspension is stirred at -50°C to -40°C for 1 hour. The reaction suspension is subsequently filtered at -30°C , the solid is washed with diethyl ether (5 ml) and subsequently condensed over at RT in vacuo (10^{-3} mbar). Bis(pentafluoroethyl)difluoro-3,4,4-trifluorobut-3-en-1-ylphosphorane, $(\text{C}_2\text{F}_5)_2(\text{CF}_2=\text{CFCH}_2\text{CH}_2)\text{PF}_2$ (17.4 mmol), can be isolated as a clear and colourless diethyl ether solution with a yield of 60%.

NMR (lock substance: CD_3CN film; δ in ppm)

^1H -NMR: **2.70** d, d, m $^3J_{\text{H,F}} = 20$ Hz, $^3J_{\text{H,P}} = 18$ Hz (2H^b), **2.89** d, m $^2J_{\text{H,P}} = 18$ Hz (2H^a).

^{19}F -NMR: **-49.1** d, t, q, m $^1J_{\text{F,P}} = 880$ Hz, $^3J_{\text{F,F}} = 14$ Hz, $^4J_{\text{F,F}} = 10$ Hz (2F), **-82.6** t $^4J_{\text{F,F}} = 10$ Hz (6F), **-105.4** d, d, t, m $^2J_{\text{F,F}} = 83$ Hz, $^3J_{\text{F,F}} = 34$ Hz, $^4J_{\text{F,H}} = 3$ Hz (1F^e), **-117.4** d, t $^2J_{\text{F,P}} = 113$ Hz, $^3J_{\text{F,F}} = 14$ Hz (4F), **-123.6** d, d, t, m $^3J_{\text{F,F}} = 115$ Hz, $^2J_{\text{F,F}} = 83$ Hz, $^4J_{\text{F,H}} = 3$ Hz




(1F^d), **-179.3** d, d, t, m ³J_{F,F} = 115 Hz, ³J_{F,F} = 34 Hz, ³J_{F,H} = 20 Hz (1F^c).

³¹P-NMR: **-31.5** t, qui, t, t ¹J_{P,F} = 880 Hz, ²J_{P,F} = 113 Hz, ²J_{P,H} = 18 Hz, ³J_{P,H} = 18 Hz (1P).

5

Example 21. Synthesis of bis(pentafluoroethyl)-3,4,4-trifluorobut-3-en-1-ylphosphine oxide by reaction of bis(pentafluoroethyl)difluoro-3,4,4-trifluorobut-3-en-1-ylphosphorane and hexamethyldisiloxane with catalytic amounts of H₂O

10



15

A clear and colourless ether solution with bis(pentafluoroethyl)difluoro-3,4,4-trifluorobut-3-en-1-ylphosphorane, (C₂F₅)₂(CF₂=CFCH₂CH₂)PF₂ (17.4 mmol, additionally contains 1,1,2,7,8,8-hexafluoroocta-1,7-diene and 1,1,2-trifluorobut-1-ene), from Example 1 is stirred with hexamethyldisiloxane, ((CH₃)₃Si)₂O (5.75 g, 35.4 mmol), and water (2 mg, 0.11 mmol) at RT for 0.5 hours in a 100 ml glass round-bottomed flask with evolution of gas. The volatile constituents are removed at -40 to -10°C in vacuo (10⁻³ mbar). Bis(pentafluoroethyl)-3,4,4-trifluorobut-3-en-1-ylphosphine oxide (6.42 g, 16.3 mmol) can be isolated as a pale-yellow liquid with a yield of 94% and a purity of 99%.


25

NMR (lock substance: CDCl₃; δ in ppm)

¹H-NMR: **2.57** d, t ²J_{H,P} = 10 Hz, ³J_{H,H} = 6 Hz (2H^a), **2.77** d, d, t, d, d ³J_{H,F} = 19 Hz, ³J_{H,P} = 19 Hz, ³J_{H,H} = 6 Hz, ⁴J_{H,F} = 3 Hz, ⁴J_{H,F} = 3 Hz (2H^b).

30

¹³C-NMR: **17.5** t, d, m ¹J_{C,H} = 133 Hz, ²J_{C,P} =




23 Hz ($1C^b$), **20.5** t, d, m $^1J_{C,H} = 132$ Hz, $^1J_{C,P} = 62$ Hz ($1C^a$), **112.8** d, d, d, q, m $^1J_{C,F_A} = ^1J_{C,F_B} = 288$ Hz, $^1J_{C,F_{A'}} = ^1J_{C,F_{B'}} = 283$ Hz $^1J_{C,P} = 92$ Hz, $^2J_{C,F} = 42$ Hz ($2CF_2$), **118.3** q, t, d, m $^1J_{C,F} = 286$ Hz, $^2J_{C,F} = 30$ Hz, $^2J_{C,P} = 17$ Hz ($2CF_3$), **126.4** d, d, d, d, t, t $^1J_{C,F} = 234$ Hz, $^2J_{C,F} = 54$ Hz, $^2J_{C,F} = 18$ Hz $^3J_{C,P} = 16$ Hz, $^2J_{C,H} = 7$ Hz $^3J_{C,H} = 3$ Hz ($1C^c$), **153.3** d, d, d, d, t, d $^1J_{C,F} = 288$ Hz, $^1J_{C,F} = 275$ Hz, $^2J_{C,F} = 45$ Hz, $^3J_{C,H} = 3$ Hz, $^4J_{C,P} = 1.3$ Hz ($1C^d$).

^{19}F -NMR: **-80.9** m (6F), **-104.3** d, d, t $^2J_{F,F} = 83$ Hz, $^3J_{F,F} = 33$ Hz, $^4J_{F,H} = 3$ Hz ($1F^e$), **-122.1** d, m $^2J_{F_A,F_B} = 340$ Hz ($2F_A$), $^2J_{F_A,P} = 79$ Hz, $^2J_{F_B,P} = 70$ Hz, **-122.8** d, d, t $^3J_{F,F} = 115$ Hz, $^2J_{F,F} = 83$ Hz, $^4J_{F,H} = 3$ Hz ($1F^d$), **-124.2** d, m $^2J_{F_{A'},F_{B'}} = 342$ Hz, $^2J_{F_{A'},P} = 79$ Hz, $^2J_{F_{B'},P} = 70$ Hz, **-179.0** d, d, t, m $^3J_{F,F} = 115$ Hz, $^3J_{F,F} = 34$ Hz, $^3J_{F,H} = 19$ Hz ($1F^c$).

^{31}P -NMR: **36.1** t, t, t, t $^2J_{P,F_A} = ^2J_{P,F_{A'}} = 79$ Hz, $^2J_{P,F_B} = ^2J_{P,F_{B'}} = 70$ Hz, $^2J_{P,H} = 19$ Hz, $^3J_{P,H} = 10$ Hz ($1P$).

Example 22. Synthesis of pentafluoroethyl-3,4,4-trifluorobut-3-en-1-ylphosphinic acid by hydrolysis of bis(pentafluoroethyl)-3,4,4-trifluorobut-3-en-1-ylphosphine oxide




Pale-yellow bis(pentafluoroethyl)-3,4,4-trifluorobut-3-en-1-ylphosphine oxide, $(C_2F_5)_2(CF_2=CFCH_2CH_2)P=O$ (5.75 g, 14.6 mmol) from Example 2, is emulsified in water (5 ml) in a 25 ml glass round-bottomed flask and warmed ($50^\circ C$). The emulsion is stirred at $50^\circ C$ for 4 h. All volatile constituents are subsequently removed at RT to $50^\circ C$ in vacuo (10^{-3} mbar). Pentafluoroethyl-3,4,4-trifluorobut-3-en-1-ylphosphinic acid (4.12 g,

14.1 mmol) can be isolated as a pale-yellow liquid with a yield 97% and a purity of 99%.

NMR (lock substance: CDCl₃; δ in ppm)

5 ¹H-NMR: **2.25** d, t ²J_{H,P} = 13 Hz, ³J_{H,H} = 8 Hz (2H^a), **2.72** d, d, t, d, d ³J_{H,F} = 20 Hz, ³J_{H,P} = 12 Hz, ³J_{H,H} = 8 Hz, ⁴J_{H,F} = 4 Hz, ⁴J_{H,P} = 2 Hz (2H^b), **13.26** s $\Delta\nu_{1/2}$ = 2 Hz (1OH).




10 ¹³C-NMR: **17.8** t, d, m ¹J_{C,H} = 133 Hz, ²J_{C,P} = 23 Hz (1C^b), **21.8** t, d, m ¹J_{C,H} = 131 Hz, ¹J_{C,P} = 104 Hz (1C^a), **111.1** t, d, q, m ¹J_{C,F} = 277 Hz, ¹J_{C,P} = 133 Hz, ²J_{C,F} = 40 Hz (CF₂), **118.5** q, t, d, m ¹J_{C,F} = 286 Hz, ²J_{C,F} = 31 Hz, ²J_{C,P} = 17 Hz (CF₃), **126.7** d, d, d, d, m ¹J_{C,F} = 235 Hz, ²J_{C,F} = 53 Hz, ²J_{C,P} = 17 Hz ³J_{C,P} = 16 Hz (1C^c), **153.0** d, d, d, t ¹J_{C,F} = 288 Hz, ¹J_{C,F} = 275 Hz, ²J_{C,F} = 46 Hz, ³J_{C,H} = 3 Hz (1C^d).

15 ¹⁹F-NMR: **-80.7** s $\Delta\nu_{1/2}$ = 4 Hz (3F), **-103.0** d, d, t, m ²J_{F,F} = 83 Hz, ³J_{F,F} = 33 Hz, ⁴J_{F,H} = 2 Hz (1F^e), **-121.9** d, d, t ³J_{F,F} = 115 Hz, ²J_{F,F} = 83 Hz, ⁴J_{F,H} = 4 Hz (1F^d), **-127.3** d ²J_{F,P} = 84 Hz (2F), **-176.9** d, d, t ³J_{F,F} = 115 Hz, ³J_{F,F} = 33 Hz, ³J_{F,H} = 20 Hz (1F^c).

20 ³¹P-NMR: **33.8** t, t, t ²J_{P,F} = 84 Hz, ²J_{P,H} = 13 Hz, ³J_{P,H} = 12 Hz (1P).

Example 23. Synthesis of bis(pentafluoroethyl)difluoro-1,2,2-trifluorovinylphosphorane from bis(pentafluoroethyl)trifluorophosphorane and 1,2,2-trifluorovinylzinc chloride

25




30 A cold (0°C) dark-brown solution of trifluorovinylzinc chloride, CF₂=CFZnCl (795 mg; 4.37 mmol, additionally contains 1.46 mmol of Et₂O and 2.24 mmol of C₆H₅CF₃ as internal standard), in toluene (10 ml) is reacted

with bis(pentafluoroethyl)trifluorophosphorane, $(\text{C}_2\text{F}_5)_2\text{PF}_3$ (1.46 g; 4.48 mmol), over the course of 15 min in a 25 ml glass round-bottomed flask. The conversion to $(\text{C}_2\text{F}_5)_2(\text{CF}_2=\text{CF})\text{PF}_2$ (714 mg; 1.84 mmol) is calculated as 42% with the aid of the internal standard. The brown-black suspension is firstly condensed over at RT and the condensate is subsequently condensed over at -40°C to -25°C in vacuo (10^{-3} mbar). The resultant colourless condensate contains the product in toluene (10 ml) and 1.72 mmol of $\text{C}_6\text{H}_5\text{CF}_3$. This clear and colourless liquid is used without further purification.


NMR (lock substance: CD_3CN ; δ in ppm)

^{19}F -NMR: -55.8 d, d, qui, d, hep, d $^1J_{\text{F,P}} = 920$ Hz, $^4J_{\text{F,F}} = 54$ Hz, $^3J_{\text{F,F}} = 14$ Hz, $^4J_{\text{F,F}} = 11$ Hz, $^4J_{\text{F,F}} = 9$ Hz, $^3J_{\text{F,F}} = 5$ Hz (2F), -58.8 d, d, d, t $^3J_{\text{F,F}} = 40$ Hz, $^3J_{\text{F,P}} = 22$ Hz, $^2J_{\text{F,F}} = 17$ Hz, $^4J_{\text{F,F}} = 11$ Hz (1F^a), -81.6 d, t, d, d $^3J_{\text{F,F}} = 113$ Hz, $^4J_{\text{F,F}} = 54$ Hz, $^2J_{\text{F,F}} = 17$ Hz, $^3J_{\text{F,P}} = 16$ Hz (1F^b), -82.4 t $^4J_{\text{F,F}} = 9$ Hz (6F), -117.2 d, t $^2J_{\text{F,P}} = 120$ Hz, $^3J_{\text{F,F}} = 14$ Hz (4F), -185.5 d, d, d, t $^3J_{\text{F,F}} = 113$ Hz, $^2J_{\text{F,P}} = 83$ Hz, $^3J_{\text{F,F}} = 40$ Hz, $^3J_{\text{F,F}} = 5$ Hz (1F^c).

^{31}P -NMR: -54.1 t, qui, d, d, d $^1J_{\text{P,F}} = 920$ Hz, $^2J_{\text{P,F}} = 120$ Hz, $^2J_{\text{P,F}} = 83$ Hz, $^3J_{\text{P,F}} = 22$ Hz, $^3J_{\text{P,F}} = 16$ Hz (1P).



Example 24. Synthesis of bis(pentafluoroethyl)(1,2,2-trifluorovinyl)-phosphine oxide from bis(pentafluoroethyl)difluoro-1,2,2-trifluorovinylphosphorane and hexamethyldisiloxane



A colourless solution of bis(pentafluoroethyl)difluorotrifluorovinyl-phosphorane, $(C_2F_5)_2(CF_2=CF)PF_2$ (714 mg; 1.84 mmol), in toluene (10 ml), contains 1.72 mmol of $C_6H_5CF_3$ as internal standard) from Example 4 is reacted with hexamethyldisiloxane, $((CH_3)_3Si)_2O$ (620 mg; 3.82 mmol) in a 25 ml glass round-bottomed flask. The reaction solution is stirred at RT for 30 min. After 30 min at RT, the conversion is quantitative. The amount of bis(pentafluoroethyl)trifluorovinylphosphine oxide (655 mg, 1.79 mmol) is determined with the aid of the internal standard, and the solution is used without further purification.

NMR (lock substance: CD_3CN ; δ in ppm)

^{19}F -NMR: -63.6 d, d, d $^3J_{F,F} = 29$ Hz, $^3J_{F,P} = 11$ Hz

($1F^a$), $^2J_{F,F} = 7$ Hz, -80.4 s $\Delta\nu_{1/2} = 6$ Hz (6F),

-93.7 d, d, d $^3J_{F,F} = 121$ Hz, $^3J_{F,P} = 15$ Hz, $^2J_{F,F}$

$= 7$ Hz ($1F^b$), -121.1 d, m $^2J_{FA,FB} = 327$ Hz,


$^2J_{FA,P} = ^2J_{FB,P} = 83$ Hz ($2FA$), -122.9 d, m $^2J_{FA',FB'} = 340$ Hz, $^2J_{FA',P} =$

$^2J_{FB',P} = 83$ Hz ($2FB$), -199.4 d, d, d $^3J_{F,F} = 121$ Hz, $^2J_{F,P} = 44$ Hz,


$^3J_{F,F} = 29$ Hz ($1F^c$).

^{31}P -NMR: 7.7 t, t, d, d, d $^2J_{P,FA} = ^2J_{P,FB} = 83$ Hz, $^2J_{P,FA'} = ^2J_{P,FB'} = 83$ Hz,

$^2J_{P,F} = 44$ Hz, $^3J_{P,F} = 15$ Hz, $^3J_{P,F} = 11$ Hz (1P).



Example 25. Synthesis of pentafluoroethyl-1,2,2-trifluorovinyl-phosphinic acid from bis(pentafluoroethyl)(1,2,2-trifluorovinyl)-phosphine oxide and water



A colourless solution of bis(pentafluoroethyl)trifluorovinylphosphine oxide, $(\text{C}_2\text{F}_5)_2(\text{CF}_2=\text{CF})\text{P}=\text{O}$ (655 mg, 1.79 mmol), in toluene (10 ml, also contains $\text{C}_6\text{H}_5\text{CF}_3$, $((\text{CH}_3)_3\text{Si})_2\text{O}$ and $(\text{CH}_3)_3\text{SiF}$) is emulsified in water (15 ml) in a 25 ml glass round-bottomed flask and warmed (50°C). The emulsion is stirred at 50°C for 3 h. After 3 h at RT, the conversion is quantitative. All volatile constituents are removed at RT in vacuo (10^{-3} mbar). Pentafluoroethyltrifluorovinylphosphinic acid (410 mg, 1.76 mmol) can be isolated as a colourless liquid with the yield of 98%.

NMR (solvent: CD_3CN ; δ in ppm)

^1H -NMR: **13.00** s $\Delta\nu_{1/2} = 7$ Hz (1OH)

^{19}F -NMR: **-75.9** d, d, d $^3J_{\text{F},\text{F}} = 30$ Hz, $^2J_{\text{F},\text{F}} = 24$ Hz,


$^3J_{\text{F},\text{P}} = 15$ Hz (1F^a), **-81.9** s $\Delta\nu_{1/2} = 6$ Hz (3F), **-97.4**

d, d, d $^3J_{\text{F},\text{F}} = 120$ Hz, $^2J_{\text{F},\text{F}} = 24$ Hz, $^3J_{\text{F},\text{P}} = 15$ Hz


(1F^b), **-128.9** d $^2J_{\text{F},\text{P}} = 90$ Hz (2F), **-195.0** d, d, d $^3J_{\text{F},\text{F}} = 120$ Hz, $^2J_{\text{F},\text{P}}$

= 65 Hz, $^3J_{\text{F},\text{F}} = 30$ Hz (1F^c)

^{31}P -NMR: **0.6** t, d, d, d $^2J_{\text{P},\text{F}} = 90$ Hz, $^2J_{\text{P},\text{F}} = 65$ Hz, $^3J_{\text{P},\text{F}} = 15$ Hz, $^3J_{\text{P},\text{F}} = 15$ Hz (1P).



Example 26. Polymerisation of pentafluoroethyl-(4-styryl)phosphinic acid with AIBN



Pentafluoroethyl-(4-styryl)phosphinic acid, $(\text{C}_2\text{F}_5)(4\text{-styryl})\text{P}(\text{O})\text{OH}\cdot 0.5\text{H}_2\text{O}$ (1.12 g; 3.79 mmol) is dissolved in CH_3CN (20 ml) with azobisisobutyronitrile (AIBN) (50 mg; 0.30 mmol) in a 25 ml glass round-bottomed flask with vigorous stirring and warmed (75°C). Cloudiness can immediately be observed. After 1.5 h at 75°C , the milky-cloudy suspension is transferred into a 100 ml glass round-bottomed flask with CH_3CN (5 ml). All volatile substances are removed at RT in vacuo (10^{-3} mbar), and the white pulverulent solid is dried for a further 2 h. Polymeric material can be isolated

as a white powder with a yield of 96%. The polymer also contains 0.3 equivalent of CH₃CN and 0.1 equivalent of H₂O (elemental analysis) and also about 5 mol% of unpolymerised (C₂F₅)(4-styryl)P(O)OH (NMR). The average degree of polymerisation (351600 formula units) was determined via the weight average molecular weight and the polydispersity by means of GPC.

Impurities, such as CH₃CN, can be removed on drying (50-60°C) in a high vacuum for 1 day.

Analytical result (GPC):

	Mw	Mp	D
Poly(pentafluoroethyl-4-styrylphosphinic acid)	94,522,300	5,143,990	4,338.20
	100,648,000	5,179,390	2,905.77

Notes: entire polymer distribution evaluated

	Mw	Mp	D
Poly(pentafluoroethyl-4-styrylphosphinic acid)	17,487,700	5,143,990	2.92
	17,387,700	5,179,390	2.80

Notes: only maximum evaluated

Mw is the weight average molecular weight, calculated over the entire peak.

Mp is the molecular weight at the peak maximum.


D (polydispersity) is an indication of the width of the weight distribution of the peak. The higher this value, the broader the weight distribution.

The analysis shows a very broad weight distribution with a maxima at ~5,200,000 Da.

The following experiment demonstrates the applicability thereof.

Determination of the ion exchange capacity (IEC):

The polymer $[(C_2F_5)(4\text{-styryl})P(O)OH]_n$ (214 mg; 0.748 mmol) is suspended in 0.1 M $NaOH_{(aq)}$ (10 ml, titre: 1.0019) in a glass round-bottomed flask (25 ml) and stirred vigorously at RT for 24 h. The resultant solution is titrated with 0.1 M $HCl_{(aq)}$ (titre: 1.0185). The consumption of 0.1 M $HCl_{(aq)}$ at the equivalence point is 2.752 ml. Taking into account the titre, this results in an amount of 0.720 mmol of acidic protons in the polymeric material. A value of 3.36 meq/g (theor.: 3.49 meq/g) thus arises for the IEC. Taking into account the impurities, such as CH_3CN , the measured ion exchange capacity IEC of the polymer is >99% of the theoretical value.


Example 27. Extraction of europium chloride using polypentafluoroethyl-4-styrylphosphinic acid

Polypentafluoroethyl-4-styrylphosphinic acid, $[(C_2F_5)(4\text{-styryl})-$

$P(O)OH \cdot 0.5H_2O]_n$ (210 mg; 0.712 mmol), is added to a solution of $EuCl_3$ (159 mg; 0.616 mmol) in H_2O (2 ml) in an FEP reactor ($\varnothing_i = 8$ mm), and the mixture is stirred at RT. After 20 h, the pale-yellow suspension with fine precipitate (**A**) is centrifuged, the mother liquor is decanted and the white solid (**A**) is washed with H_2O (3 x 2 ml). The combined mother liquors are evaporated at RT in vacuo (10^{-3} mbar), and the resultant white and solid residue (**B**) (157 mg) is dried at RT in vacuo (10^{-3} mbar) for a further 5 h. The white solid (**B**) fluoresced intensely red ($EuCl_3$) on irradiation with UV light ($\lambda = 366$ nm). The water content of the solid was determined as 45 mg (2.5 mmol) by means of Karl Fischer titration. Elemental analysis of the solid shows little contamination by CH_3CN (3 mg; 0.07 mmol) from the starting material. No chloride was detected in the polymer (**A**) by X-ray fluorescence analysis. The ratio of europium to phosphorus is 0.30 to 1.00.

EuCl₃ (157 mg – 45 mg (H₂O) – 3 mg (CH₃CN) = 109 mg (0.422 mmol)) can be recovered as white solid (**A**). Eu³⁺ (0.194 mmol) in the polymer are replaced by H⁺. The ratio of europium to phosphorus is thus 0.272 to 1.00, which corresponds to replacement of 82% of the acidic protons in the polymer (**A**). On irradiation with UV light at $\lambda = 366$ nm, the polymer exhibits a pale orange fluorescence, whereas it fluoresces intensely pink at $\lambda = 254$ nm. A quantum yield of 3.6% is determined with the aid of fluorescence spectroscopy. Excitation at $\lambda = 250.0$ nm causes maximum absorption with emission maxima at $\lambda = 590.0$ nm ($\Delta\nu_{1/2} = 9.8$ nm) and 610.5 nm ($\Delta\nu_{1/2} = 9.7$ nm).

Example 28. Extraction of terbium chloride using polypentafluoroethyl-4-styrylphosphinic acid



Polypentafluoroethyl-4-styrylphosphinic acid, [(C₂F₅)(4-styryl)-


P(O)OH·0.5H₂O]_n (52 mg; 0.176 mmol), is added to a solution of TbCl₃ (55 mg; 0.207 mmol) in H₂O (1 ml) in an FEP reactor ($\varnothing_i = 8$ mm), and the mixture is stirred at RT. After 22 h, the white suspension with bulky precipitate (**A**) is centrifuged, the mother liquor is decanted and the white solid (**A**) is washed with H₂O (2 x 1 ml). The combined mother liquors are evaporated at RT in vacuo (10⁻³ mbar), and the resultant white and solid residue (**B**) (62 mg) is dried at RT in vacuo (10⁻³ mbar) for a further 2 h. The white solid (**B**) fluoresced yellow-green (TbCl₃) on irradiation with UV light ($\lambda = 254$ nm). Analogously to the experiment with europium (Example 6), the residue here can again be assumed to be a hexaaqua complex, [Tb(H₂O)₆]Cl₃. The water content is estimated as 18 mg (1.0 mmol). Elemental analysis of the solid shows little contamination by CH₃CN (1 mg; 0.02 mmol) from the starting material. No chloride was detected in the

polymer (A) by X-ray fluorescence analysis. The ratio of terbium to phosphorus is 0.33 to 1.00. TbCl_3 (62 mg – 18 mg (H_2O) – 1 mg (CH_3CN) = 43 mg (0.162 mmol)) can be isolated as white solid (A). Tb^{3+} (0.045 mmol) in the polymer are replaced by H^+ . The ratio of terbium to phosphorus is thus 0.26 to 1.00, which corresponds to replacement of 77% of the acidic protons in the polymer (A). On irradiation with UV light at $\lambda = 254$ nm, the polymer (A) likewise fluoresces yellow-green.

Example 29. Graft polymerisation of $(\text{C}_2\text{F}_5)(\text{CH}_2=\text{CHCH}_2\text{CH}_2)\text{P}(\text{O})\text{OH}$ on a porous polymer support (hydrophilic crosslinked polyvinyl ether) using $[\text{NH}_4]_2\text{cerium}[\text{NO}_3]_6$ in H_2O at 40°C

White and solid polymer gel (~20 g) (filtered out of H_2O suspension) is initially introduced in a 500 ml 3-necked round-bottomed flask with reflux condenser, dropping funnel and precision glass stirrer, and an aqueous $(\text{C}_2\text{F}_5)(\text{CH}_2=\text{CHCH}_2\text{CH}_2)\text{P}(\text{O})\text{OH}$ solution (18.77 g in 100 ml of water) is added. As initiator, an aqueous $[\text{NH}_4]_2\text{cerium}[\text{NO}_3]_6$ (2.41 g)/ HNO_3 (65%, 1.44 g) solution (20 ml) is placed in the dropping funnel. The entire apparatus is degassed in a membrane-pump vacuum (100 mbar) and flooded with N_2 . The reaction suspension is warmed (40°C) and the initiator substance is subsequently added. The now-yellow suspension is stirred at 40°C for 22 h. The mixture is subsequently filtered, and the filter cake is washed with water (2 x 100 ml). The pale-yellow polymer material is washed with water (3 x 100 ml) and an H_2SO_4 (concentrated, 25 g)/ascorbic acid (17.6 g) solution (500 ml)(5 x 100 ml). The mixture is subsequently washed neutral several times more with an $\text{NaHPO}_4/\text{NaOH}$ buffer solution (pH 7, 50 mM) and water (in total 1000 ml). The slightly beige-coloured polymer material is stored in the refrigerator at 0°C under Millipur water. A polymer material forms in which 0.9 g of the phosphinic acid employed is bonded to 1 g of polymer.

The polymer material obtained is in addition investigated by solid-state and liquid NMR spectroscopy. The signals detected are comparable with those of but-3-en-1-ylpentafluoroethylphosphinic acid and can be assigned to the structural unit



Example 30. Polymerisation in the presence of a silica-gel support material

Step 1: Preparation of mercapto-silica gel

Object: Synthesis of LiChroprep Mercapto from LiChroprep Si 100; 15µm - 25µm. LiChroprep Si 100 as an average pore size of 10 nm.

LiChroprep Si 100 is a traditionally prepared irregular SiO₂ sorbent (silica gel) having an average pore size of 10 nm and an average particle size of 15µm to 25µm. LiChroprep Si is merely a trade name. Silica gels of this type are prepared in accordance with the prior art and are known to the person skilled in the art.

Equipment : 1l 3-necked flask, precision glass stirrer, reflux condenser, oil-bath heating 90°C, nitrogen feed, 50 ml dropping funnel, 1x stirrer, 2x glass suction filters 1l Por. 4

1x 2000 ml three-necked flask, 2x 2l suction bottle, 1x porcelain dish

Table 1: Chemicals used:

Amount	Chemical	Art. No.	Batch	Property
100.1g	LiChroprep Si 100 (15-25µm)		F553395	S _{BET} =282.2 m ² /g
4.1086 g	Sodium acetate	1.06268	A0472968 322	0.1M

5	43.1 g 43.1 ml	Mercapto- propylmethyl- dimethoxysilane w=95%	AB111217 ABCR	1068410	180.34 g/mol
		Dist. water	-----	-----	
	1.3 l	Methanol	1.06009.5000	1734309416	

Procedure:

100.1 g of LiChroprep Si100 are initially introduced in a 1000 ml three-necked flask and suspended in 0.1 molar sodium acetate solution at 250 rpm.

The mercaptopropylmethyldimethoxysilane should be added dropwise over the course of 10 to 15 minutes with stirring.

The suspension is heated under reflux (90°C) for 3 hours.

After heating for 3 hours, the suspension is slowly cooled to room temperature with stirring.

The gel is then filtered off with suction on a 1 l Por4 frit, suspended again with 1 l of deionised water and filtered off with suction. The gel is transferred into a 2l three-necked flask, and 1 l of methanol is added.

The suspension is heated at 65-69°C for 30 minutes. After cooling to room temperature, the reaction mixture is filtered off with suction on a 1l Por4 frit, rinsed twice with 100 ml of methanol and dried over vacuum for 1 hour.

The product is left to stand overnight in the fume hood without vacuum and next day dried again for 3 hours in vacuo.

Elemental analysis: C = 6.3%, S = 4.0%

2nd step Addition of but-3-en-1-yl(pentafluoroethyl)phosphinic acid

Product batch: ScW14FE002

Equipment:

- 2x 250 ml three-necked flasks
- condenser

- precision glass stirrer and stirrer sleeve
- hotplate
- thermometer and oil bath
- 1000µl Eppendorf pipette equi No.: 70221348
- 5 - analytical balance equ No.: 70081915
- 125 ml Por.4 frit

Table 2: Chemicals:

10		Chemical	Article number/ batch	Molar amount	EQUIVA- LENCE mmol	Weight/ volume
		Mercapto-silica gel	ScW14FE001	1.2699mmol /g 5.77mmol	4.5µmol/m ²	4.4990 g
		But-3-en-1-yl- (pentafluoro-ethyl)phos- phinic acid		13.71 mmol	2.4	3.2562 g
15		Glacial acetic acid	K28057163032 1.00063.1000	9 mmol	2mmol / g of silica	0.540g 0.515 ml
		V65		1.1142 mmol	20%mol	0.2836g
		Methanol	I734309416 1.06009.5000			90 ml

20

Procedure:

The mercapto-silica gel (ScW14FE001) was initially introduced in a three-necked flask with 40ml of methanol and suspended under nitrogen. The 3-butenylpentafluoroethylphosphinic acid, the glacial acetic acid and the V65 were then added. The vessels in which the weighed amounts were located were rinsed twice with a small amount of methanol. The reaction mixture was boiled at a bath temperature of 67°C for 6h under nitrogen. The lukewarm reaction solution was filtered off with suction via a 125 ml Por.4 frit.

25 The gel was transferred into another 250 ml three-necked flask, boiled with about 50 ml of methanol for 5min with stirring and filtered off with suction. This washing step was repeated 3 times.

30

The gel was dried firstly in a fume hood overnight and then at 30°C in a vacuum drying cabinet for 16 hours.

Elemental analysis:

5 **3. Determination of the terbium chloride binding capacity**

Equipment:

- 10, 25 and 100 ml volumetric flasks
- Ultrospec 4000 UV spectrometer, Pharmacia Biotech, Inv. No. 59485
- ultrasound bath
- 10 - Sartorius BP221 F analytical balance Equ Nr:70098279
- Eppendorf 5804 centrifuge, Equ No.: EM 2363

Table 3: chemicals used

15	Chemical	Article number/ batch	Molecular weight or S _{BET}
	Terbium chloride hexahydrate (TbCl ₃ *6 H ₂ O)	1315353	265.29
	LiChroprep Si 100, 15-25 µm	F553395	
	Mercapto-silica gel	ScW14FE001	
	Silica gel from step 2	ScW14FE002	
20	Water, MilliQ		

A calibration curve of the adsorption of terbium chloride hexahydrate in water at 220 nm in the range from 0.018 to 1.832 mg/ml is recorded. The line of best fit followed the line equation $y = 0.8502 x + 0.009$ where $R^2 = 0.999$.

- 25 In each case 10 ml of a stock solution of 0.521 mg of TbCl₃ * 6 H₂O in water are added to about 200 mg (weighed precisely) of the respective silica gel, as indicated in Table 4,, in a sealed glass vessel and left in the ultrasound bath in parallel for 10 min. In each case 5 ml of the solution are subsequently centrifuged at 5000 rpm for 5 min and the adsorption of the super-
- 30 natant at 220 nm is measured.

Table 4: Results:


Sample	Adsorption (220 nm) of the supernatant
Stock solution (0.521 mg of $\text{TbCl}_3 \cdot 6 \text{H}_2\text{O}$ in water)	0.437
Silica gel LiChroprep Si 100, 15-25 μm	0.401
Silica gel from step 2	0.148

Measurement of the TbCl_3 adsorption shows a decrease of 70%, which corresponds to the amount of Tb cations bound.

Patent Claims

1. Compounds of the formula I

5



where

- R_f denotes a straight-chain or branched perfluoroalkyl group having 1 to 12 C atoms,
- A denotes H, F, Cl or a straight-chain or branched alkyl group having 1 to 12 C atoms,
- B denotes $-(\text{CR}_1\text{R}_2)_n-$, $[-(\text{CR}_1\text{R}_2)_m\text{O}-(\text{CR}_1\text{R}_2)_{m1}-]_{m2}$, arylene or substituted arylene,
- X denotes H, F and/or Cl,
- n denotes an integer from 0 to 20,
- m denotes an integer from 1 to 20,
- m_1 denotes an integer from 0 to 8,
- m_2 denotes an integer from 1 to 20 and
- R_1 or R_2 each, independently of one another, denote H, F, Cl or a straight-chain or branched alkyl group having 1 to 12 C atoms.


2. Compounds according to Claim 1, characterised in that R_f denotes a straight-chain or branched perfluoroalkyl group having 1 to 8 C atoms.

3. Compounds according to Claim 1 or 2, characterised in that A and X are identical.


4. Compounds according to one or more of Claims 1 to 3, characterised in that B denotes $-(\text{CR}_1\text{R}_2)_n-$, arylene or substituted arylene.

5. Process for the preparation of compounds of the formula I according to one of Claims 1 to 4, characterised in that

a) a compound of the formula II




where R_f , A, B and X have a meaning indicated in one or more of Claims 1 to 4 and x denotes 1 or 2, is hydrolysed, giving an intermediate compound of the formula IIIa as intermediate,




where R_f , A, B and X have a meaning indicated in formula II, or

b) a compound of the formula II




where R_f , A, B and X have a meaning indicated in one or more of Claims 1 to 4 and x denotes 1, 2 or 3, is reacted with a hexaalkyldisiloxane without or in the presence of a catalytic amount of water, where the alkyl groups of the hexaalkyldisiloxane each, independently of one another, denote a straight-chain or branched alkyl group having 1 to 4 C atoms, giving an intermediate compound of the formula III,



where R_f , A, B and X have a meaning indicated in formula II, which is subsequently hydrolysed.

6. Compounds of the formula IIIa,




where R_f , A, B and X have a meaning indicated in one of Claims 1 to 4.

7. Use of compounds of the formula I according to one or more of Claims 1 to 4 for the preparation of oligomers or polymers.
- 5 8. Oligomer or polymer containing polymerised compounds of the formula I, according to one or more of Claims 1 to 4, as monomer units.
9. Process for the preparation of oligomers or polymers according to Claim 8, characterised in that compounds of the formula I, as described in one or more of Claims 1 to 4, are polymerised, optionally together with further monomers and optionally in the presence of a crosslinking agent.
- 10 10. Process according to Claim 9, characterised in that the polymerisation is carried out by means of free radicals
- 15 11. Process according to Claim 9 or 10, characterised in that a homopolymer is prepared.
12. Process according to one or more of Claims 9 to 11, characterised in that the polymerisation is carried out without crosslinking agents.
- 20 13. Process according to one or more of Claims 9 to 12, characterised in that the polymerisation is carried out in, on or at a support material.
14. Composite material comprising a support material and at least one compound according to Claim 1 or compounds according to Claim 8.
- 25 15. Use of the compounds according to one or more of Claims 1 to 4, according to Claim 6, according to Claim 8 or according to Claim 14 as ion exchanger or as Brønsted acid catalyst.
- 30

16. Use of the compounds according to one or more of Claims 1 to 4, according to Claim 6, according to Claim 8 or according to Claim 14 for the extraction of cations of the rare earths from solutions.

5 17. Salts of the compounds according to Claim 1 of the formula I corresponding to the formula IV,



10 or ionic compounds according to Claim 8 containing polymerised salts of the formula IV or ionic compounds according to Claim 14 containing a support material and at least one salt of the formula IV or ionic polymers or oligomers containing polymerised salts of the formula IV, where the
 15 cations Kt^+ in formula IV denote an inorganic or organic cation and where R_f , A, B and X have a meaning indicated in one of Claims 1 to 4.

20

25

30