REDUCED METAL PIPE FORMATION IN METAL SILICIDE CONTACTS

ABSTRACT

Formation of metal pipes resulting from formation of metal silicide contacts are reduced or avoided. To reduce formation of metal pipes, an epitaxial layer is formed over the diffusion region on which the metal silicide contact is formed. The epitaxial layer reduces defects which enhances diffusion of metal atoms or molecules.

Figure 2