

THIS SHEET HAS BEEN
REPLACED

ABSTRACT

PROCESS FOR PRODUCING METHACRYLIC POLYMER

5

The present invention provides a process for
producing a methacrylic polymer which comprises bulk
or solution polymerization a methacrylic monomer (a)
to obtain a liquid polymer composition (b) containing
10 an unreacted methacrylic monomer and separating a
volatile component (c) containing said unreacted
monomers to obtain said polymer (d), wherein said
volatile component (c) containing said unreacted
monomer is treated with a compound having a sulphonic
15 acid group and then with an amine, and is recycled to
the polymerizing step.

20

This Sheet Has Been Replaced



25

30

35