

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
26 October 2006 (26.10.2006)

PCT

(10) International Publication Number
WO 2006/111829 A1

(51) International Patent Classification:
C21D 7/04 (2006.01) **B23K 31/00** (2006.01)

(21) International Application Number:
PCT/IB2006/000928

(22) International Filing Date: 19 April 2006 (19.04.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
20051913 19 April 2005 (19.04.2005) NO

(71) Applicant (for all designated States except US): **VETCO AIBEL AS** [NO/NO]; Bergerveien 12, P.O. Box 81, 1375 Billingstad (NO).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **FREDBORG, Andreas** [NO/NO]; øvre Høn Terrasse 18, 1384 Asker (NO).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD FOR OBTAINING ENHANCED FATIGUE STRENGTH IN WELDED METAL JOINTS AND HAMMER HEAD FOR USE AT COLD WORKING



(57) Abstract: A method for obtaining enhanced fatigue strength in welded metal joints and -components comprising a weld toe (9) subjected to cold working such that a visible and/or measurable indentation at the weld toe (9) is produced. The cold working is carried out by means of a power driven hammer head, which has a slightly convex, elongated contact surface (3) in the length direction for contact with the weld toe (9). Hereby, the geometry of the weld toe (9) is strongly improved at the same time as residual stresses after the welding are eliminated and advantageous compressive stresses are established.