

WAFER PROCESSING METHOD

BACKGROUND OF THE INVENTION

Field of the Invention

The present invention relates to a wafer processing method of processing a wafer to form a 5S molded package.

Description of the Related Art

As a structure for realizing miniaturization and higher density of various devices such as large-scale integrated circuits (LSIs) and NAND type flash memories, for example, a chip size package (CSP) in which device chips are packaged in chip size has been put to practical use and widely used for mobile phones, smart phones, and the like. Furthermore, in recent years, of the CSP, a CSP in which not only a front surface but also all side surfaces of a chip are sealed with a sealing material, that is, a so-called 5S molded package has been developed and put to practical use.

The conventional 5S molded package is manufactured by the following steps.

(1) Forming devices (circuits) and external connection terminals called bumps on a front surface of a semiconductor wafer (hereinafter sometimes referred to simply as a wafer).

(2) Cutting the wafer along division lines from a front

surface side of the wafer to form cut grooves each having a depth corresponding to a finished thickness of each of the device chips.

(3) Sealing the front surface of the wafer with a carbon black-containing sealing material.

(4) Grinding a back surface side of the wafer to the finished thickness of each of the device chips to expose the sealing material in the cut grooves.

(5) Performing alignment in which, since the front surface of the wafer is sealed with the carbon black-containing sealing material, the sealing material at a peripheral portion of the front surface of the wafer is removed to expose alignment marks such as target patterns, and the division line to be cut is detected based on the alignment marks.

(6) Cutting the wafer along the division lines from the front surface side of the wafer based on the alignment, and dividing the wafer into 5S molded packages each of which has its front surface and all side surfaces sealed with the sealing material.

Since the front surface of the wafer is sealed with the carbon black-containing sealing material as described above, the devices and the like formed in the front surface of the wafer are not at all visible to the naked eye. To enable alignment by solving this problem, the

present inventor has developed a technique in which, as described in the above paragraph (5), the sealing material at the peripheral portion of the front surface of the wafer is removed to expose the alignment marks such as the target patterns, and based on these alignment marks, the division line to be cut is detected, so that alignment is performed (see Japanese Patent Laid-open No. 2013-074021 and Japanese Patent Laid-open No. 2016-015438).

SUMMARY OF THE INVENTION

However, according to the alignment method described in the above-mentioned patent documents, a step of removing the sealing material at the peripheral portion of the wafer with a large-width cutting blade for edge trimming mounted to a spindle in place of a cutting blade for dicing is needed, and it is laborious to replace the cutting blade and to remove the sealing material at the peripheral portion by edge trimming, thereby causing poor productivity.

It is therefore an object of the present invention to provide a wafer processing method in which an alignment step can be performed through a carbon black-containing sealing material applied to coat a front surface of a wafer.

In accordance with an aspect of the present invention, there is provided a wafer processing method of processing a wafer in which each of devices having a plurality of bumps is formed in each of regions of a front surface partitioned by a plurality of division lines formed in an intersecting manner. The wafer processing method includes: a cut groove forming step of forming cut grooves each having a depth corresponding to a finished thickness of each of device chips by a cutting blade along the division lines from a front surface side of the wafer; a sealing step of sealing the front surface of the wafer including the cut grooves with a sealing material, after the cut groove forming step is performed; an alignment step of detecting an alignment mark through the sealing material by visible light imaging means from the front surface side of the wafer, and detecting the division line to be laser processed based on the alignment mark, after the sealing step is performed; a modified layer forming step of emitting a laser beam of such a wavelength as to pass through the sealing material along the division lines from the front surface side of the wafer, with a focal point of the laser beam being positioned inside the sealing material in the cut grooves, to form modified layers inside the sealing material in the cut grooves, after the alignment step is performed; a

grinding step of grinding the wafer from a back surface side of the wafer to the finished thickness of each of the device chips to expose the sealing material in the cut grooves, after the modified layer forming step is performed; and a dividing step of applying an external force to the sealing material in the cut grooves, and dividing the wafer, with the modified layers serving as starting points of division, into individual device chips each of which has its front surface and four side surfaces surrounded by the sealing material, after the grinding step is performed. The alignment step is performed while obliquely irradiating a region to be captured by the visible light imaging means with light by oblique light means.

According to the wafer processing method of the present invention, while obliquely irradiating the wafer with light by the oblique light means, the alignment mark formed in the wafer is detected through the sealing material by the visible light imaging means, and the alignment can be performed based on the alignment mark. Therefore, the alignment step can be easily performed without removing the sealing material at a peripheral portion of the front surface of the wafer as in the related art.

Accordingly, by emitting the laser beam of such a

wavelength as to pass through the sealing material from the front surface side of the wafer, with the focal point of the laser beam being positioned inside the sealing material in the cut grooves, it is possible to form the modified layers inside the sealing material, and then, by grinding the wafer from a back surface side of the wafer to the finished thickness of each of the device chips to expose the sealing material in the cut grooves, and by applying an external force to the sealing material, it is possible to divide the wafer, with the modified layers serving as starting points of division, into individual device chips each of which has its front surface and four side surfaces surrounded by the sealing material.

The above and other objects, features and advantages of the present invention and the manner of realizing them will become more apparent, and the invention itself will best be understood from a study of the following description and appended claims with reference to the attached drawings showing a preferred embodiment of the invention.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a perspective view of a semiconductor wafer;

FIG. 2 is a perspective view depicting a cut groove

forming step;

FIG. 3 is a perspective view depicting a sealing step;

FIG. 4 is a sectional view depicting an alignment step;

FIG. 5A is a sectional view depicting a modified layer forming step;

FIG. 5B is a partial enlarged sectional view of a wafer after the modified layer forming step is performed;

FIG. 6 is a sectional view depicting a grinding step;

FIG. 7 is a perspective view of a dividing apparatus;

FIG. 8A is a sectional view depicting a dividing step;

FIG. 8B is a sectional view depicting the dividing step; and

FIG. 9 is a partial enlarged sectional view of the wafer after the dividing step is performed.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

An embodiment of the present invention will be described in detail below with reference to the drawings. Referring to FIG. 1, there is depicted a perspective view of a front surface side of a semiconductor wafer

(hereinafter sometimes referred to simply as a wafer) 11 suitable for being processed by a processing method of the present invention. In a front surface 11a of the semiconductor wafer 11, a plurality of division lines (streets) 13 are formed in a grid pattern, and a device 15 such as an integrated circuit (IC) or an LSI is formed in each of regions partitioned by the division lines 13 intersecting orthogonally.

Each device 15 has a plurality of electrode bumps (hereinafter sometimes referred to simply as bumps) 17 on its front surface, and the wafer 11 includes, on the front surface thereof, a device region 19 in which a plurality of devices 15 each having the plurality of bumps 17 are formed and a peripheral marginal region 21 surrounding the device region 19.

In a wafer processing method according to an embodiment of the present invention, first, a cut groove forming step of forming cut grooves each having a depth corresponding to a finished thickness of each of device chips by a cutting blade along the division lines 13 from the front surface side of the wafer 11 is performed as a first step. The cut groove forming step will be described with reference to FIG. 2.

A cutting unit 10 includes a cutting blade 14 detachably mounted to a tip portion of a spindle 12, and

an alignment unit 16 having visible light imaging means (visible light imaging unit) 18. The visible light imaging unit 18 has a microscope and a camera which capture in visible light.

Before performing the cut groove forming step, alignment is performed in which the front surface of the wafer 11 is first captured in visible light by the visible light imaging unit 18, alignment marks such as target patterns formed in each device 15 are detected, and the division line 13 to be cut is detected based on the alignment marks.

After the alignment is performed, the cut groove forming step is performed in which the cutting blade 14 rotated at high speed in a direction of an arrow R1 is made to cut into the wafer 11 to a depth corresponding to a finished thickness of each of device chips along the division line 13 from the front surface 11a side of the wafer 11, and a chuck table (not depicted) with the wafer 11 sucked and held thereon is fed for processing in a direction of an arrow X1, whereby a cut groove 23 is formed along the division line 13.

The cut groove forming step is performed sequentially along the division lines 13 extending in a first direction, while the cutting unit 10 is put into indexing feeding in a direction orthogonal to the

direction X1 of feeding for processing by the pitch of the division lines 13. Next, the chuck table (not depicted) is rotated by 90°, and then, the same cut groove forming step as above is performed sequentially along the division lines 13 extending in a second direction orthogonal to the first direction.

After the cut groove forming step is performed, a sealing step is performed in which, as depicted in FIG. 3, a sealing material 20 is applied to the front surface 11a of the wafer 11 to seal the front surface 11a of the wafer 11 including the cut grooves 23 with the sealing material. Since the sealing material 20 has fluidity, when the sealing step is performed, the cut grooves 23 are filled with the sealing material 20.

As the sealing material 20, a composition containing 10.3% of epoxy resin or epoxy resin plus phenolic resin, 85.3% of silica filler, 0.1% to 0.2% of carbon black, and 4.2% to 4.3% of the other constituents in mass % is adopted. Examples of the other constituents include metal hydroxides, antimony trioxide, silicon dioxide, and the like.

When the front surface 11a of the wafer 11 is covered with the sealing material 20 having such a composition and sealed, the carbon black contained in an extremely small amount in the sealing material 20 makes

the sealing material 20 black, and accordingly, it is normally difficult to see the front surface 11a of the wafer 11 through the sealing material 20.

Here, the carbon black is mixed in the sealing material 20 mainly for preventing electrostatic breakdown of the device 15, and at present, no sealing material that does not contain carbon black is commercialized. The method of applying the sealing material 20 is not particularly limited; however, it is desirable to apply the sealing material 20 to a height of each of the bumps 17, and then, the sealing material 20 is subjected to etching to expose head portions of the bumps 17.

After the sealing step is performed, an alignment step is performed in which the front surface 11a of the wafer 11 is captured through the sealing material 20 by visible light imaging means from the front surface 11a side of the wafer 11, at least two alignment marks such as target patterns formed in the front surface 11a of the wafer 11 are detected, and the division line 13 to be laser processed is detected based on these alignment marks.

The alignment step will be described in detail with reference to FIG. 4. Before performing the alignment step, the back surface 11b side of the wafer 11 is adhered to a dicing tape T whose outer peripheral portion is attached

to an annular frame F. In the alignment step, as depicted in FIG. 4, the wafer 11 is sucked and held by a chuck table 40 of a laser processing apparatus through the dicing tape T, and the sealing material 20 sealing the front surface 11a of the wafer 11 is exposed upward. Then, the annular frame F is fixed by clamping it with clamps 42.

In the alignment step, the front surface 11a of the wafer 11 is captured by an imaging element such as a charge coupled device (CCD) of a visible light imaging unit 18A of a laser processing apparatus similar to the visible light imaging unit 18 of the cutting apparatus. However, since such constituents as silica filler and carbon black are contained in the sealing material 20 and further, a front surface of the sealing material 20 is uneven, even if the front surface 11a of the wafer 11 is captured through the sealing material 20 by vertical illumination of the visible light imaging unit 18A, the captured image becomes out of focus, making it difficult to detect the alignment marks such as target patterns.

In view of this, in the alignment step of the present embodiment, by obliquely irradiating a region to be captured with light from oblique light means 31 in addition to the vertical illumination of the visible light imaging unit 18A, the out-of-focus problem of the

captured image can be improved, thereby enabling detection of the alignment marks.

The light irradiated from the oblique light means 31 is preferably white light, and an incident angle to the front surface 11a of the wafer 11 is preferably in a range of 30° to 60°. Preferably, the visible light imaging unit 18A includes an exposure controller by which exposure time or the like can be adjusted. Next, the chuck table 40 is rotated by θ such that a straight line connecting these alignment marks will be parallel to the direction X1 of feeding for processing, and further, the cutting unit 10 depicted in FIG. 2 is moved in the direction orthogonal to the direction X1 of feeding for processing by a distance between the alignment mark and the center of the division line 13, whereby the division line 13 to be laser processed is detected.

After the alignment step is performed, a modified layer forming step is performed in which, as depicted in FIG. 5A, a laser beam LB of such a wavelength (for example, 1,064 nm) as to pass through the sealing material 20 is irradiated from a laser head (light collector) 46 of the laser processing apparatus along the division line 13 from the front surface 11a side of the wafer 11, with a focal point of the laser beam LB being positioned inside the sealing material 20 in the cut

groove 23, and the chuck table 40 is fed for processing in the direction of the arrow X1 to form a modified layer 25 depicted in FIG. 5B inside the sealing material 20 in the cut groove 23.

This modified layer forming step is performed sequentially along the division lines 13 extending in a first direction, after which the chuck table 40 is rotated by 90°, and the modified layer forming step is then performed sequentially along the division lines 13 extending in the second direction orthogonal to the first direction.

After the modified layer forming step is performed, a grinding step is performed in which the wafer 11 is ground from the back surface 11b side of the wafer 11 to a finished thickness of each of the device chips to expose the sealing material 20 in the cut grooves 23.

This grinding step will be described with reference to FIG. 6. A surface protective tape 22 is adhered to the front surface 11a of the wafer 11, and the wafer 11 is sucked and held by a chuck table 24 of a grinding apparatus through the surface protective tape 22.

A grinding unit 26 includes a spindle 30 rotatably accommodated in a spindle housing 28 and rotationally driven by a motor which is not depicted, a wheel mount 32 fixed to a tip of the spindle 30, and a grinding wheel 34

detachably mounted to the wheel mount 32. The grinding wheel 34 is composed of an annular wheel base 36, and a plurality of grindstones 38 secured to an outer periphery of a lower end of the wheel base 36.

In the grinding step, while the chuck table 24 is rotated in a direction of an arrow a at, for example, 300 rpm, the grinding wheel 34 is rotated in a direction of an arrow b at, for example, 6,000 rpm, and a grinding unit feeding mechanism (not depicted) is driven to bring the grindstones 38 of the grinding wheel 34 into contact with the back surface 11b of the wafer 11.

Then, the back surface 11b of the wafer 11 is ground while the grinding wheel 34 is put into grinding feeding by a predetermined amount downward at a predetermined grinding feeding speed. While a thickness of the wafer 11 is measured by a thickness measuring gauge of a contact type or non-contact type, the wafer 11 is ground to a predetermined thickness, for example, 100 μm , thereby exposing the sealing material 20 filled in the cut grooves 23.

After the grinding step is performed, a dividing step is performed in which an external force is applied to the wafer 11 by use of a dividing apparatus 50 depicted in FIG. 7 to divide the wafer 11 into individual device chips 27. The dividing apparatus 50 depicted in

FIG. 7 includes frame holding means 52 holding the annular frame F, and tape expanding means 54 expanding the dicing tape T attached to the annular frame F held by the frame holding means 52.

The frame holding means 52 includes an annular frame holding member 56, and a plurality of clamps 58 as fixing means disposed at an outer periphery of the frame holding member 56. An upper surface of the frame holding member 56 forms a mount surface 56a on which to mount the annular frame F, and the annular frame F is mounted on the mount surface 56a.

Then, the annular frame F mounted on the mount surface 56a is fixed to the frame holding member 56 by the clamps 58. The frame holding means 52 configured in this way is supported to be movable in a vertical direction by the tape expanding means 54.

The tape expanding means 54 has an expanding drum 60 disposed inside the annular frame holding member 56. An upper end of the expanding drum 60 is closed with a lid 62. The expanding drum 60 has an inner diameter which is smaller than an inner diameter of the annular frame F and is larger than an outer diameter of the wafer 11 adhered to the dicing tape T attached to the annular frame F.

The expanding drum 60 has a support flange 64

integrally formed at a lower end thereof. The tape expanding means 54 further has driving means 66 moving the annular frame holding member 56 in the vertical direction. The driving means 66 is composed of a plurality of air cylinders 68 disposed on the support flange 64, and piston rods 70 thereof are connected to a lower surface of the frame holding member 56.

The driving means 66 composed of the plurality of air cylinders 68 moves the annular frame holding member 56 in the vertical direction between a reference position in which the mount surface 56a is at substantially the same height as a front surface of the lid 62 serving as the upper end of the expanding drum 60 and an expanding position which is by a predetermined amount lower than the upper end of the expanding drum 60.

The dividing step for the wafer 11 performed by use of the dividing apparatus 50 configured as above will be described with reference to FIGS. 8A and 8B. As depicted in FIG. 8A, the annular frame F supporting the wafer 11 through the dicing tape T is mounted on the mount surface 56a of the frame holding member 56, and is fixed to the frame holding member 56 by the clamps 58. In this instance, the frame holding member 56 is positioned in the reference position where the mount surface 56a thereof is at substantially the same height as the upper

end of the expanding drum 60.

Next, the air cylinders 68 are driven to lower the frame holding member 56 to the expanding position depicted in FIG. 8B. Accordingly, the annular frame F fixed on the mount surface 56a of the frame holding member 56 is lowered, and as a result, the dicing tape T attached to the annular frame F abuts on an upper end edge of the expanding drum 60 and is expanded mainly in a radial direction.

As a result, pulling forces are radially applied to the wafer 11 adhered to the dicing tape T. When the pulling forces are thus radially applied to the wafer 11, the wafer 11 is divided along the modified layers 25 formed in the sealing material 20 in the cut groove 23 along the division lines 13, with the modified layers 25 serving as starting points of division, as depicted in the enlarged view of FIG. 9, whereby the wafer 11 is divided into individual device chips 27 each of which has its front surface and four side surfaces surrounded by the sealing material 20.

The present invention is not limited to the details of the above described preferred embodiment. The scope of the invention is defined by the appended claims and all changes and modifications as fall within the equivalence of the scope of the claims are therefore to be embraced

by the invention.

WHAT IS CLAIMED IS:

1. A wafer processing method of processing a wafer in which each of devices having a plurality of bumps is formed in each of regions of a front surface partitioned by a plurality of division lines formed in an intersecting manner, the wafer processing method comprising:

a cut groove forming step of forming cut grooves each having a depth corresponding to a finished thickness of each of device chips by a cutting blade along the division lines from a front surface side of the wafer;

a sealing step of sealing the front surface of the wafer including the cut grooves with a sealing material, after the cut groove forming step is performed;

an alignment step of detecting an alignment mark through the sealing material by visible light imaging means from the front surface side of the wafer, and detecting the division line to be laser processed based on the alignment mark, after the sealing step is performed;

a modified layer forming step of emitting a laser beam of such a wavelength as to pass through the sealing material along the division lines from the front surface side of the wafer, with a focal point of the laser beam being positioned inside the sealing material in the cut

grooves, to form modified layers inside the sealing material in the cut grooves, after the alignment step is performed;

a grinding step of grinding the wafer from a back surface side of the wafer to the finished thickness of each of the device chips to expose the sealing material in the cut grooves, after the modified layer forming step is performed; and

a dividing step of applying an external force to the sealing material in the cut grooves, and dividing the wafer, with the modified layers serving as starting points of division, into individual device chips each of which has its front surface and four side surfaces surrounded by the sealing material, after the grinding step is performed,

wherein the alignment step is performed while obliquely irradiating a region to be captured by the visible light imaging means with light by oblique light means.