

PH BUFFERED COMPOSITIONS FOR CLEANING SEMICONDUCTOR SUBSTRATES

Field of the Invention

The present invention relates to a semi-aqueous cleaning formulation for use in producing semiconductor devices and a process for producing semiconductor devices using the cleaning formulation. More particularly, the present invention relates to a semi-aqueous cleaning formulation useful for cleaning organic materials, organometallic residues, organosilicon residues, sidewall polymers and inorganic residues from a semiconductor substrate.

Background of the Invention

The process of wafer fabrication includes a series of putting down layers. Each layer involves a series of steps, which may comprise all or some of photolithography, etch, strip, diffusion, ion implant, deposition, and chemical mechanical polishing.

Photolithography is the process through which images are transferred to the surface of a wafer by means of a light sensitive polymeric film layer (photoresist). The image is transferred from a mask to the photoresist layer by a developing process, which includes exposing regions of the film to a light/UV source, which are not blocked by the mask, resulting in a pattern on the wafer.

Figures 1(a)-1(d) depict four key photolithographic steps for an exemplary photoresist process. In Figure 1a, photoresist (10) is deposited on a silicon dioxide, dielectric, hard mask, etch stop, and/or barrier layer (12) on silicon substrate (14). A light source (16) (as indicated by the down ward facing arrows) exposes the resist (10) not blocked by mask (18). The exposed resist (20), (the areas where the down arrows penetrate the resist layer), is dissolved in a developing solution, leaving a resist pattern identical to the mask (18). Figure 1(b) depicts the resist pattern (22) on silicon dioxide layer (12) after dissolution of the exposed resist. In Figure 1(c), the silicon dioxide layer (12) is then put into a plasma etch process or wet etch process typically using a fluorinated compound to remove the oxide in areas not protected by resist (22), to create a patterned silicon dioxide layer of vias and/or trenches. At this point, the photoresist has served its useful purpose and must be removed by an ashing and/or wet stripping step. The resist must be entirely removed since it is an organic material, which, if left on the wafer surface, would cause defects.

The plasma etch process used to remove the silicon dioxide or other substrate material requires exposing the substrate surface to UV radiation. The radiation tends to cross link the photoresist material making it more difficult to remove in the subsequent ashing or wet stripping step.

Ashing is a general term used for a process, which includes removing a photoresist coating by exposing the photoresist-coated wafer to an oxygen or hydrogen plasma in order to burn the resist film from the substrate surface. Alternatively, wet stripping typically involves contacting the photoresist-covered substrate with a stripper solution consisting primarily of an organic solvent and an amine. Of the two, plasma ashing is the more popular method for removing photoresist because it is less susceptible to contamination, as the process is carried out in a vacuum. Figure 1(d) shows a patterned silicon dioxide layer (12), on the silicon substrate (14) after plasma ashing removal of the photoresist layer having particles and residues (24) left behind from the ashing process.

Prior to trench or via fill, the wafer surface must be cleaned of particles and residues left behind from the plasma etch and resist removal processes. The deposits may vary, but will most likely include at least an etching gas component, a component of the film being patterned by etching, and photoresist. If left in place, the deposits would cause a significant deterioration in the reliability of the semiconductor device. Accordingly, the wafer surface must be sufficiently cleaned of such deposits.

As fabs work to integrate new materials such as copper, and low dielectric constant materials, a need emerges for new cleaning techniques for post etch and post ash residue removal, where long trenches and narrow vias trap particles. Integration of low-dielectric constant materials with $k < 3.0$ with existing aluminum or new copper damascene processes has been difficult to overcome.

Low- dielectric constant films such as carbon-doped oxide (OSG) comprise Si-O, Si-H and Si-C linkages. The film structure is preferably porous, whereby the porous nature of the film is due to the loss of volatile organic species or the inherent structure of the precursor material(s). In the presence of highly acidic or alkaline aqueous formulations, the Si-O and Si-H links are converted to OH groups, destroying the integrity of the Si-O link and increasing the dielectric of the low-k film.

One useful carbon-doped oxide (OSG) is a low-k material having a dielectric constant in the range of 2.7-3.0. The trend to single wafer tools for photoresist removal and post plasma/ash residual removal has mandated a short cleaning time to maintain wafer throughput. At the same time the introduction of organosilica glass (OSG) dielectrics has made the alkaline strippers and post-ash

residual removers less viable since they attack OSG. The solution to high cleaning rate and compatibility with OSG requires new chemistries, which are formulated in such a way as to clean and remove particles without corroding the substrate surface.

Prior art cleaning formulations including highly-acidic, hydrofluoric acid are effective when the wafer substrate is made of a material, such as silicon, silicon dioxide, tungsten, tungsten-titanium alloys or titanium nitride. Such materials are relatively resistant to corrosion by a hydrofluoric acid. However, when made of materials, such as aluminum, aluminum alloys containing copper, copper or carbon-doped oxide, which are relatively less resistant to corrosion by the fluorine compound, the cleaning agent significantly corrodes and dissolves the conductive line pattern and/or dielectric.

Other prior art cleaning formulations have used alkanolamines to remove resist residues. However, if water is present during use, the alkanolamine dissociates and creates an alkaline solution that accelerates the corrosion of metals and dielectrics.

Other prior art cleaning formulations used organic solvents, which are no longer compatible with the new low-k dielectrics as they react with the organic and hydrogen substituents to produce a chemically altered dielectric material.

Hence, there is a need for an improved cleaning formulation that removes organic materials, organometallic residues, organosilicon residues, sidewall polymers and inorganic residues from a semiconductor wafer surface and inside and around via holes when low dielectric constant films and conductive lines containing aluminum and/or copper are exposed to plasma etch and resist ash conditions.

Further, there is a need for a cleaning formulation that is not effected by small changes in the concentration of acidic and/or basic components.

Therefore, it is one object of the present invention to provide an improved cleaning formulation that removes organic materials, organometallic residues, organosilicon residues, sidewall polymers and inorganic residues from a semiconductor wafer surface when low dielectric constant films and conductive lines containing aluminum and/or copper are exposed to plasma etch and resist ash conditions

It is a further object of the present invention to produce a cleaning formulation having a pH in a range that does not corrode metal and/or dielectric films and that is not effected by small changes in the concentration of acidic and or basic components.

A still further object of the present invention is to provide a cleaning agent for use in producing semiconductor devices, which meets the above objects.

A still further object of the present invention is to provide a process for producing semiconductor devices, which comprises a step of cleaning a wafer surface with a cleaning formulation that removes organic materials, organometallic residues, organosilicon residues, sidewall polymers and inorganic residues from a semiconductor wafer surface when low dielectric constant films and conductive lines containing aluminum and/or copper are exposed to plasma etch and resist ash conditions.

Summary of the Invention

The present invention relates to a semi-aqueous cleaning formulation for semiconductor devices comprising a buffering system, and a low temperature process for cleaning a semiconductor substrate using the semi-aqueous formulation.

In one aspect, the present invention relates to a semi aqueous cleaning formulation comprising a buffering system.

In a further aspect, the present invention relates to a semi-aqueous cleaning formulation comprising a buffering system, a fluoride salt and a polar organic solvent and water.

In a still further aspect the present invention relates to a method of removing particles from a semiconductor substrate which includes, providing a semi-aqueous cleaning formulation comprising a buffering system and contacting the wafer surface with the cleaning formulation for a time sufficient to effect the removal of at least of portion of the particles.

Brief Description of the Drawings

Figure 1(a)-1(d) shows four key photolithographic steps for an exemplary photoresist process.

Figure 2 shows an aluminum metal line having residue, prior to chemical processing.

Figure 3 shows the aluminum metal line of **Figure 2**, after chemical processing.

Figure 4 shows a via structure having residue, prior to chemical processing.

Figure 5 shows the via structure of **Figure 4**, after chemical processing.

Detailed Description of the Invention and Preferred Embodiments Thereof

The present invention relates to a semi-aqueous cleaning formulation for semiconductor wafers that provides for simultaneous cleaning and/or removal of particles from a wafer surface, while maintaining a fixed pH, thus avoiding unnecessary corrosion of the substrate.

The present formulations provide effective cleaning of the substrates, which means more effective residue removal, which in turn means that higher product yields can be obtained from the substrates being cleaned.

In one embodiment, the present invention relates to a semi-aqueous cleaning formulation comprising a buffering system, wherein said buffering system comprises at least one organic acid, the salt of the organic acid or other conjugate base, and water, such that the buffer system provides a buffering capacity of from about 100 to 1000 mM to change the pH one unit. The buffering capacity is measured by a solution of the buffer only. Preferably the water used in the formulation is high purity de-ionized water, present in an amount of from about 0 to 70.0% weight by volume of the total formulation, more preferably from about 5.0 to 25.0% weight by volume, and most preferably from about 8.0 to 15.0% weight by volume.

As used herein, the term "semi-aqueous" refers to a mixture of water and organic components.

The buffering system of the present invention should comprise from about 1.0 to 70% weight by volume, and more preferably from about 5.0 to 45% weight by volume of the total composition. The pH of the present solution should be maintained within the range of 3.0 to 8.0, more preferably about 4 to 7 and, most preferably about 4.0 to 6.5. The term "buffer system" refers to a combination of compounds that provide a buffering system in solution that exhibits buffering capacity, that is, the capacity to neutralize within limits, either acids or bases (alkali) with relatively little or no change in the original pH. The buffering system of the present invention serves to maintain the pH of the instant formulation to within a pH of ± 1 , and as such the potential for oxide etching and/or metal corrosion is limited.

As used herein, the term "buffering capacity" is defined as the millimoles (mM) of strong acid or base (or respectively, hydrogen or hydroxide ions) required to change the pH by one unit when added to one liter (a standard unit) of the buffer solution. The buffering capacity will depend on the kind and concentration of the buffer components.

Organic acids useful in the buffering system of the instant invention include but are not limited to: formic acid, trifluoroacetic acid, propionic acid, butyric acid, valeric acid, heptanoic acid, lactic acid, oxalic acid, malic acid, malonic acid, succinic acid, fumaric acid, adipic acid, benzoic acid, phthalic acid and citric acid. Conjugate bases useful in the buffering system of the present invention include but are not limited to: a salt of the organic acid, ammonia, tetramethylammonium hydroxide, tetraalkylammonium hydroxide, 2-(methylamino)ethanol, monoisopropanolamine, diglycolamine, N,N-dimethyl-2-(2-aminoethoxy)ethanol, 1-(2-aminoethyl)piperidine, 1-(2-hydroxyethyl)piperazine, 1-(2-aminoethyl)piperazine, 1-(3-aminopropyl)-imidazole, 1,8-diazabicyclo[5.4.0]undec-7-ene, N,N,N'-trimethylaminoethanolamine, pentamethyldiethylenetriamine, ethylmorpholine, hydroxyethylmorpholine, aminopropylmorpholine, triethanolamine, and methyldiethanolamine. In a preferred embodiment, the buffering system of the present invention, comprises lactic acid and ammonium lactate.

In one embodiment, the cleaning formulation of the present invention comprises a multi-component buffering system, such as a lactic acid/lactate and citric acid/citrate buffering system.

In a further embodiment, the present invention relates to a semi-aqueous cleaning formulation comprising a buffering system, and optionally a fluoride source. Preferably, the fluoride source is present in an amount ranging from about 0 to 25.0% weight by volume, more preferably from about 0 to 8.0 % weight by volume and most preferably from about 0 to 1.0 percent weight by volume. Suitable fluoride compounds are ammonium fluoride and derivatives thereof, including but not limited to:

- ammonium fluoride;
- ammonium bifluoride;
- tetraalkylammonium fluorides, wherein each alkyl group may be same or different and is selected from the group consisting of C₁ to C₄, such as
- tetramethylammonium fluoride (TMAF); and
- amine fluoride salts, such as,
- methyldiethanolammonium fluoride (MDEAF);
- triethanolammonium fluoride (TEAF);
- diglycolammonium fluoride (DGAF);
- triethylamine tris (hydrogen fluoride) (TREAT-HF).

In a further embodiment, the present invention relates to a semi-aqueous cleaning formulation useful for removing particles from a semiconductor substrate, wherein said formulation comprises a buffer system, and optionally, a fluoride source and an organic solvent system. Preferably, the organic solvent system is soluble in water. Preferably the organic solvent system comprises at least one polar solvent component. The cleaning formulation may comprise from about 0-95% weight by volume of the solvent system, more preferably between 0 and 80% weight by volume and most preferably between 0 and 70% weight by volume of the organic solvent system. Preferably, at least one component of the organic solvent system comprises an amide or ether functional group. Preferred solvents include but are not limited formamides amide glycol ethers, to N,N-dimethylacetamide, N,N-dimethylformamide, 1-cyclohexyl-2-pyrrolidinone, N-methylpyrrolidone, N-cyclohexylpyrrolidone, N-hydroxyethylpyrrolidone, N-octylpyrrolidone, 1,3-dimethylpiperidone, ethylene glycol, propylene glycol, phenoxyethanol, sulfolane, gamabutyrolactone, butyrolactone, 1,4-butanediol, N,N-dimethylacetoacetamide, N-cyclohexylpyrrolidone, N-octylpyrrolidone, 1-phenoxy-2-propanol, phenoxyethanol, dimethylsulfoxide, diethyleneglycol monobutylether, diethyleneglycol monomethylether, diethylene glycol monoethylether, diethylene glycol monopropyl ether, 1,3-dimethyl-2-imidazolidinone and mixtures thereof.

In a further embodiment, the semi-aqueous cleaning formulation of the present invention may further and optionally comprise a corrosion inhibitor and/or a cleaning agent. The cleaning agent may be present in a concentration ranging from about 0 to 5.0% weight by volume of the total cleaning formulation, preferably 0 to 2% weight by volume of the total cleaning formulation and most preferably from about 0 to 2.0% weight by volume of the total cleaning formulation. The corrosion inhibitor may be present in a concentration ranging from about 0 to 2.5% weight by volume of the total cleaning formulation, preferably 0 to 1.0% weight by volume of the total cleaning formulation and most preferably about 0 to 0.5% weight by volume of the total cleaning formulation.

The corrosion inhibitor serves to react with the substrate surface, which may be metal or non-metal, to passivate the surface and prevent excessive etching during cleaning. The cleaning agent is a substance that chelates to specific metal or non-metal components to be removed, leading to soluble components that can be readily removed during polishing. The corrosion inhibitor and cleaning agent for the instant invention are preferably a carboxylic acid. More specifically, the carboxylic acid may be chosen from, but not limited to glycine, oxalic acid, malonic acid, succinic

acid, citric acid, tartaric acid, gluconic acid, nitrilotriacetic acid, their salts and mixtures thereof. Alternatively, the carboxylic acid may be a di, tri or tetra carboxylic acid that preferentially has a nitrogen containing functional group. In the most preferred form, the corrosion inhibitor and the cleaning agent are iminodiacetic acid. Other substances useful as corrosion inhibitors and/or cleaning agents include but are not limited to ethylene-diaminetetraacetic acid (EDTA), benzotriazole (BTA), tolytriazole, BTA derivatives, such as BTA carboxylic acids, boric acid, fluoroboric acid, cystine, haloacetic acids, glucose, dodecyl mercaptan and mixtures thereof.

In a still further embodiment, the present invention may further and optionally comprise at least one surfactant. Suitable surfactants include but are not limited to amphoteric, cationic, anionic, and nonionic, which may be present individually or in combination in amounts up to 0.5%, preferably up to 0.1% and more preferably up to 0.05% weight by volume. Specific non-limiting examples of surfactants are Surfynol®, Triton®, Tergitol®, and Tween ®.

In one embodiment, the present invention relates to a cleaning formulation comprising at least one bi-functional component, wherein at least one component serves as both, a component of the buffering system and/or solvent system as well as at least one of, a chelating agent, surfactant, corrosion inhibitor and/or stabilizer.

In one embodiment, the semi-aqueous cleaning formulation of the present invention comprises:

<u>Component</u>	<u>Percent weight by volume</u>
a buffer system comprising:	
organic acid	0.1 to 35.0;
salt of organic acid or conjugate base	0.1 to 40.0;
water	1.0 to 70.0; and
organic solvent system	0 to 95.0; and
fluoride salt	0 to 25.0.

In one embodiment, the present invention relates to a semi-aqueous cleaning formulation comprising: a lactic acid, ammonium lactate and water buffer system; a 1-cyclohexyl-2-pyrrolidinone and N,N-dimethylacetamide solvent system; and ammonium fluoride.

In a more preferred embodiment, the semi-aqueous cleaning formulation of the present invention comprises:

<u>Component</u>	<u>Percent weight by volume</u>
a buffer system comprising:	
lactic acid	8.14-13.26;
ammonium lactate	13.25-16.95;
water	8.2-10; and
organic solvent system: comprising:	
1-cyclohexyl-2-pyrrolidinone	29.1-31.5;
N,N-dimethylacetamide	34.0-36.8; and
ammonium fluoride	0.27-0.33.

Other exemplary formulations of the instant invention include but are not limited to:

<u>Component</u>	<u>Percent weight by volume</u>
a buffer system comprising:	
formic acid	26.2;
1-(2-aminoethyl)piperazine (AEP)	37.0;
water	32.8; and
corrosion inhibitor: comprising:	
iminodiacetic acid	3.5
ammonium fluoride	0.5.

<u>Component</u>	<u>Percent weight by volume</u>
a buffer system comprising:	
formic acid	28.7;
1-(2-aminoethyl)piperazine (AEP)	37.0;

water	33.8; and
ammonium fluoride	0.5.

<u>Component</u>	<u>Percent weight by volume</u>
a buffer system comprising:	
formic acid	26.4;
1-(2-aminoethyl)piperazine (AEP)	37.6;
water	32.5; and
corrosion inhibitor: comprising:	
iminodiacetic acid	3.5

<u>Component</u>	<u>Percent weight by volume</u>
a buffer system comprising:	
formic acid	31.0;
1-(2-aminoethyl)piperazine (AEP)	36.1;
water	32.9

The cleaning formulation of the instant invention may have multiple cleaning uses and is not limited to post etch and resist residue removal. For example, the cleaning formulation of the instant invention when diluted with water in a ratio of from about 1 part formulation to 12 parts water, is useful for post chemical mechanical polishing cleaning.

The cleaning formulation is useful in cleaning wafer surfaces of multiple particle residues, particularly post etch and post ash residues from a carbon doped dielectric thin film. In one embodiment, the instant invention relates to a method of removing particles from a semiconductor substrate. Representative particle compositions include positive photoresists, electron beam resists, X-ray resists, ion beam resists, and the like. Examples of plasma processing residue sidewall polymers include among others, metal-organic complexes and /or inorganic salts, oxides, hydroxides or complexes of the organic polymer resins of a photoresist.

In a further embodiment, the present invention relates to a method for removing particles from a semiconductor wafer surface, said method includes providing a semi-aqueous cleaning formulation

comprising a buffering system and contacting the wafer surface with said cleaning formulation for a time sufficient to effect the removal of at least of portion of the particles.

The method of cleaning a wafer surface using the cleaning compositions of the present invention involves contacting a substrate having residue thereon, particularly organometallic or metal oxide residue, with a cleaning composition of the present invention for a time and at a temperature sufficient to remove the residue. Stirring, agitation, circulation, sonication or other techniques as are known in the art optionally may be used. The substrate is generally immersed in the cleaning composition. The time and temperature are determined based on the particular material being removed from a substrate. Generally, the temperature is in the range of from about ambient or room temperature to 45°C., and the contact time is from about 30 seconds to 60 minutes. The preferred temperature and time of contact for this invention is 20 to 45° C. and from about 1 to 10 minutes. The formulation may be removed from the wafer by any method readily know to those skilled in the art. However, preferably, the formulation is removed by spin-drying. Generally, the wafer is preferably rinsed with a solvent such as ethanol or deionized water to complete the cleaning process.

In one embodiment, the present invention relates to a method of removing particles from a semiconductor substrate comprising a step of forming an insulation film on a semiconductor substrate, a step of dry-etching the insulation film into a prescribed pattern and a step of cleaning the resultant product with a semi-aqueous cleaning formulation comprising a buffer system, an organic solvent system and a fluoride source.

In a further embodiment, the present invention relates to a method of removing particles from a semiconductor substrate comprising a step of forming a conductive line pattern from a metal material or a semiconducting material on a semiconductor substrate, a step of forming an insulation film on the conductive line pattern, a step of forming a via hole in the insulation film by dry etching and a step of cleaning the resultant product with a semi-aqueous cleaning formulation comprising a buffer system, an organic solvent system and a fluoride source.

In a still further embodiment, the present invention relates to a method of removing particles from a semiconductor substrate comprising a step of forming a film of a metal material or a semiconducting material on a semiconductor substrate, a step of dry-etching the film into a

conductive line pattern and a step of cleaning the resultant product with a semi-aqueous cleaning formulation comprising a buffer system, an organic solvent system and a fluoride source.

In a further embodiment, the method of the instant invention may further comprise an agitating means, wherein the wafer is contacted with the cleaning formulation and agitated by means of shaking, megasonic or ultrasonic to aid in freeing particles adhering to the substrate surface or trapped in vias or trenches.

The present invention is not limited to the particular embodiments shown and described herein, but that various changes and modifications may be made without departing from the scope and spirit of the invention.

The features, aspects and advantages of the present invention are further shown with reference to the following non-limiting example relating to the invention.

Example

Example 1: Metal Etch rates at 100%

Formulation:

pH of approximately 6

Component

Percent weight by volume

a buffer system comprising:

boric acid

5.0;

formic acid

19.0

1-(2-aminoethyl) piperazine (AEP)

26.0;

water

48.6; and

corrosion inhibitor: comprising:

citric acid

0.4; and

ammonium fluoride

1.0

Recommended Process Conditions:

Time: 10 Minutes
Process Temperature: 40°C
DI H2O Rinse: 3 Minutes

Table 1:

Film	Etch rate @ 100%
AlCu	1-8 Å/min
Cu	1.2-4.1 Å/min
TaN	13.6 Å/min
Ti	0.55 Å/min
W	0.2 Å/min
TiN	5.6 Å/min
Thermal Ox	3.0 Å/min
Poly Si	0.6 Å/min

Example 2: Cleaning of Metal Lines

The same formulation as used in Example 1, was used to clean aluminum/copper metal lines:

Figure 2 and Figure 3 show the aluminum/copper metal lines before (Figure 2) and after (Figure 3) cleaning with the above formulation. Experimental conditions included a processing temperature of 40°C for a time of 10 minutes, followed by a deionized (DI) water rinse.

Example 3: Cleaning of Via Structure

The same formulation as used in Example 1 was used to clean a via structure:

Figure 4 and Figure 5 show a via structure comprising silicon dioxide, before (Figure 4) and after (Figure 5) cleaning with the above formulation. Experimental conditions included a processing temperature of 40°C for a time of 10 minutes, followed by a deionized (DI) water rinse.

Although the present invention has been described in detail, it should be understood that various changes, substitutions and alterations can be made hereto without departing from the spirit and scope of the invention as described by the appended claims.

The Claims

What is claimed is:

1. A semi-aqueous cleaning formulation for semiconductor devices comprising a buffering system.
2. The semi-aqueous cleaning formulation of claim 1, further comprising a polar organic solvent.
3. The semi-aqueous cleaning formulation of claim 1, further comprising a fluoride source.
4. The semi-aqueous cleaning formulation of claim 1, wherein said buffering system comprises at least one organic acid.
5. The semi-aqueous cleaning formulation of claim 1, wherein said buffering system comprises at least one organic acid and the salt of the organic acid.
6. The semi-aqueous cleaning formulation of claim 1, wherein said buffering system comprises at least one organic acid, at least one conjugate base and water.
7. The semi-aqueous cleaning formulation of claim 1, comprising from about 1.0 to 75.0% weight by volume buffering system.
8. The semi-aqueous cleaning formulation of claim 1, comprising a pH in a range for from about 4 to 7.
9. The semi-aqueous cleaning formulation of claim 1, having a buffering capacity of 100 to 1000 mM.
10. The semi-aqueous cleaning formulation of claim 1, wherein said buffering system comprises an organic acid selected from the group consisting of: formic acid, trifluoroacetic acid, propionic acid, butyric acid, valeric acid, heptanoic acid, lactic acid, oxalic acid, malic acid, malonic acid, succinic acid, fumaric acid, adipic acid, benzoic acid, phthalic acid and citric acid.
11. The semi-aqueous cleaning formulation of claim 1, wherein said buffering system comprises a salt of an organic acid, wherein said organic acid is selected from the group consisting of: formate,

trifluoroacetate, propionate, butyrate, valerate, heptanoate, lactate, oxalate, malate, malonate, succinate, fumarate, adiptate, benzoate, phthalate and citrate.

12. The semi-aqueous cleaning formulation of claim 1, wherein said buffering system comprises a conjugate base selected from the group consisting of: ammonia, tetramethylammonium hydroxide, tetraalkylammonium hydroxide, 2-(methylamino)ethanol, monoisopropanolamine, diglycolamine, N,N-dimethyl-2-(2-aminoethoxy)ethanol, 1-(2-aminoethyl)piperidine, 1-(2-hydroxyethyl)piperazine, 1-(2-aminoethyl)piperazine, 1-(3-aminopropyl)imidazole, 1,8-diazabicyclo[5.4.0]undec-7-ene, N.N.N'-trimethylaminoethanolamine, pentamethyldiethylenetriamine, ethylmorpholine, hydroxyethylmorpholine, aminopropylmorpholine, triethanolamine, and methyldiethanolamine.

13. The semi-aqueous cleaning formulation of claim 1, wherein said buffering system comprises lactic acid, ammonium lactate and water.

14. The semi-aqueous cleaning formulation of claim 1, wherein said cleaning formulation further comprises a polar organic solvent system.

15. The semi-aqueous cleaning formulation of claim 1, wherein said cleaning formulation further comprises a polar organic solvent system, wherein at least one component of the organic solvent system is selected from the group consisting of: N,N-dimethylacetamide, N,N-dimethylformamide, 1-cyclohexyl-2-pyrrolidinone, N-methylpyrrolidone, N-cyclohexylpyrrolidone, N-hydroxyethylpyrrolidone, N-octylpyrrolidone, 1,3-dimethylpiperidone, ethylene glycol, propylene glycol, phenoxyethanol, sulfolane, gamma-butyrolactone, 1,4-butanediol, N,N-dimethylacetoacetamide, N-cyclohexylpyrrolidone, N-octylpyrrolidone, 1-phenoxy-2-propanol, phenoxyethanol, dimethylsulfoxide, diethyleneglycol monobutylether, diethyleneglycol monomethylether, diethylene glycol monoethylether, diethylene glycol monopropyl ether, 1,3-dimethyl-2-imidazolidinone and mixtures thereof.

16. The semi-aqueous cleaning formulation of claim 14, wherein said polar organic solvent is soluble in water.

17. The semi-aqueous cleaning formulation of claim 14, comprising from about 10.0 to 95.0% weight by volume solvent system.

18. The semi-aqueous cleaning formulation of claim 14, wherein said polar organic solvent system comprises at least one component having an amide functional group.
19. The semi-aqueous cleaning formulation of claim 1, further comprising a fluoride source.
20. The semi-aqueous cleaning formulation of claim 1, further comprising a polar organic solvent system and a fluoride source.
21. The semi-aqueous cleaning formulation of claim 1, further comprising from about 0.1 to 25.0% weight by volume fluoride source.
22. The semi-aqueous cleaning formulation of claim 19, wherein said fluoride source is selected from the group consisting of: ammonium fluoride and derivatives thereof.
23. The semi-aqueous cleaning formulation of claim 19, wherein said fluoride source is selected from the group consisting of:
- ammonium fluoride;
 - ammonium bifluoride;
 - tetraalkylammonium fluorides, wherein each alkyl group may be same or different and is selected from the group consisting of C₁ to C₄, such as
 - tetramethylammonium fluoride (TMAF); and
 - amine fluoride salts, such as,
 - methyldiethanolammonium fluoride (MDEAF);
 - triethanolammonium fluoride (TEAF);
 - diglycolammonium fluoride (DGAF); and
 - triethylamine tris (hydrogen fluoride) (TREAT-HF).
24. The semi-aqueous cleaning formulation of claim 1, further comprising a corrosion inhibitor.
25. The semi-aqueous cleaning formulation of claim 1, further comprising a cleaning agent.
26. The semi-aqueous cleaning formulation of claim 24, wherein said corrosion inhibitor is a carboxylic acid.