

Description

Background of the Invention

This invention is directed toward the preparation of stabilized, rare earth metal-doped cadmium halide glasses exhibiting excellent transmission far into the infrared region of the electromagnetic radiation spectrum.

Glasses transmitting in the infrared portion of the radiation spectrum have long been of interest as potential candidates for ultra-low loss optical fibers. More recently it has been recognized that these same materials, when doped with rare earth metals, can demonstrate properties rendering them eminently suitable for making efficient lasers, amplifiers, and upconverters.

The peculiar characteristic of a material that imparts the ability to transmit radiation far into the infrared region is the same one which makes the material a good host of rare earth metals for the three above-mentioned applications. That singular property comprises a low fundamental vibrational frequency (phonon energy) which is typically associated with the strongest chemical bond of the material matrix. For example, the more ionic metal fluorine bond in a fluoride material is weaker than the more covalent metal oxygen bond in an oxide material which, in turn, results in the fluoride material exhibiting superior infrared transmission. Moreover, in a given class of materials, bonds are weaker and, hence, infrared transmission is improved, when the component ions are heavy and/or have low valence. Thus, within the particular class of halide glasses, the cadmium-based glasses have more extended transmission of infrared radiation than the well known glasses based on either BeF_2 or ZrF_4 .

Radiative emission of rare earth metal-doped materials is based upon electronic transitions between atomic-like 4f levels that are localized on the rare earth metal ions. From a particular level radiative emissions compete with non-radiative emissions. Often the dominant non-radiative process is the emission of one or more phonons. The probability of this non-radiative process is known to decrease exponentially with the number of phonons required to bridge the energy gap of the transition. Therefore, materials with low-phonon energies will require more phonons to bridge that gap and, hence, will have less competitive non-radiative emission processes and higher radiative efficiencies, thereby enhancing any process which depends upon fluorescence between rare earth metal levels.

Three basic devices can be made with rare earth metal-doped materials, viz., lasers, amplifiers, and upconverters. Lasers demand good radiative efficiency for the laser transition. Amplifier efficiency is similarly directly tied to radiative efficiency. In fact, only those transitions separated by more than twice the phonon energy of the host material can be made to lase or amplify. Consequently, the lower the material phonon energy, the larger the number of transitions that can be made to lase or amplify. In an upconversion device light is converted from a longer wavelength, e.g., in the infrared, to a short wavelength, e.g., in the visible. Such a process can be used both for detecting long wavelength light and as a source of short wavelength light. The simplest upconversion process is generally a two-step process, first involving the absorption of a long wavelength photon followed by the promotion of an electron to an intermediate level. From this intermediate level the electron is further promoted to a higher level through the absorption of a second photon (so-called excited state absorption) or through the exchange of energy with another excited rare earth metal ion (so-called energy transfer upconversion). Clearly, the efficiency of emission from the final state will be positively correlated with the radiative efficiency of the transition from the upper state. In addition, the efficiency will also be positively correlated with the lifetime of the electrons in the intermediate state. The longer the lifetime (before the electron decays back towards the ground state), the longer a given electron will be available for excited state absorption energy transfer upconversion and, therefore, the greater the probability of such a promotion. Accordingly, as the probability of the non-radiative processes is reduced in a material with a lower phonon energy, the excited state lifetimes are longer, thereby rendering the multi-step upconversion process more efficient.

Cadmium halide-containing glasses comprise one class of glasses with very low phonon energies. The cations present in those glasses are monovalent and/or divalent. Moreover, the most stable cadmium halide glasses contain a mixture of light (fluoride) and heavier (chloride) anions. As a result, these glasses have more extended transmissions in the infrared than do other halide glasses based upon zirconium, hafnium, uranium, indium, and/or aluminum fluorides.

Nevertheless, unlike heavy metal fluoride glasses, the cadmium halide glasses become less stable with the addition of trivalent cations, such as the rare earth metals. For example, the addition of as little as 0.1 mole percent of praseodymium halide is sufficient to convert an otherwise stable and clear cadmium chloride-containing glass into an opaque, partially devitrified material. This behavior was observed by Jha and Parker in "Preparation of Infrared Transmitting CdF_2 Based Mixed Halide Glasses", Physics and Chemistry of Glasses, 32, No. 1, February 1991, pages 1-12. Thus, at page 7 the author stated:

Our results indicate that trivalent fluorides cannot be incorporated into mixed halide glasses as they can into heavy metal fluoride glasses. LaF_3 and YF_3 caused crystallization while AlF_3 dissolves to a limited extent, but at the expense of the infrared cutoff edge (see next section) and even in this case only 2 mol % could be added without significant crystallization. Similarly, BiCl_3 cannot be incorporated in these glasses, which seems to suggest that it is either the chemical nature or the size of these trivalent halides that decides their solubility.

The primary objective of the present invention was to discover means for producing stable, transparent cadmium halide glasses containing trivalent rare earth metal cations, which glasses exhibit excellent transmission far into the infrared portion of the radiation spectrum, thereby commending their utility in the fabrication of efficient lasers, amplifiers, and upconverters.

Summary of the Invention

We have found that the above objective can be achieved through the addition of small amounts of halide (X), customarily a fluoride, chloride, and/or bromide, of relatively light monovalent and divalent cations, such as Li^+ , Be^{2+} , Mg^{2+} , Mn^{2+} , Co^{2+} , and Zn^{2+} , in order to suppress the tendency of cadmium halide (CdX) glass compositions doped with a trivalent rare earth metal to crystallize and/or to opalize. Thus, as was observed above, the incorporation of only 0.1 mole percent of PrCl_3 into a cadmium halide-containing glass caused the development of extensive devitrification therein, the crystals being tentatively identified as CdCl_2 . The inclusion of 3 mole percent LiF yielded a clear, homogeneous glass. Laboratory investigations have indicated that rare earth metal-doped, CdX -containing glasses can be stabilized to exhibit excellent transparency both in the visible and infrared regimes of the radiation spectrum through the inclusion of about 1-5 mole percent of a stabilizing halide. Greater amounts of a stabilizing halide may be included, e.g., up to 10 mole percent, but with no apparent substantive advantage. Those investigations have led to the appreciation that, although the effect is not expressly limited thereto, the following cations demonstrate a superior action and, hence, are preferred: Li^+ , Be^{2+} , Mg^{2+} , Mn^{2+} , Co^{2+} , and Zn^{2+} .

We have found that lead halides in amounts up to 12 mole percent, preferably up to 10 mole percent, and thallium halides in amounts up to 7%, preferably up to 5 mole percent, exert a similar, albeit less pronounced, stabilizing effect on rare earth metal-doped, CdX -containing glasses. The addition of lead and/or thallium halides to the base glass compositions can provide the further advantage of raising the refractive index of the glass. For example, a cadmium halide-containing glass composition incorporating about 10 mole percent of a lead halide can exhibit a refractive index of up to 1.668. In contrast, lead-free glasses of the same base composition will exhibit a refractive index of about 1.613. The inclusion of a lithium halide can lower the refractive index of the glass. Those circumstances strongly recommend the use of the inventive glasses as transparent glass core portions for optical waveguide structures.

Thus, as is well recognized in the art, an optical waveguide consists of a transparent glass core portion enveloped within a transparent compatible glass cladding layer which exhibits a lower refractive index than the core glass. The term "compatible" indicates the essential absence of any deleterious reaction taking place at the interface between the core and cladding glasses.

Accordingly, the inventive rare earth metal-doped glasses can comprise the core glass with a compatible glass demonstrating a lower refractive index constituting the cladding glass. To assure a high refractive index, a lead halide and/or a thallium halide will be included in the composition. In general, the core glass will contain up to 10% total of 1-10% PbX_2 and/or 1-5% TiX_3 . For example, a praseodymium-doped, lead and/or thallium-containing glass exhibiting a high refractive index would be especially desirable as the core composition for a waveguide structure with an undoped, lead and thallium-free glass serving as the cladding.

We have found that the following base glass compositions, expressed in terms of mole percent, when stabilized with up to 12 mole percent, preferably 1-5 mole percent, of a stabilizing halide and doped with at least 0.005 mole percent, preferably 0.05-0.5 mole percent, of at least one rare earth metal halide selected from the lanthanide series of rare earth metals (ReX_3), display properties strongly recommending them for use in lasers, amplifiers, and upconverters.

The base glass compositions consist essentially, expressed in terms of mole percent, of 42-55% CdF_2 and/or CdCl_2 , 30-40% NaF and/or NaCl , 2-20% total of BaF_2 and/or BaCl_2 + KF and/or KCl , consisting of 0-15% BaF_2 and/or BaCl_2 and 0-7% KF and/or KCl , wherein up to about 10 mole % total of at least one metal selected from the group consisting of Cd , Ba , Na , and K can be incorporated as a bromide. In the preferred compositions at least 2% each of BaF_2 and/or BaCl_2 and KF and/or KCl will be present. Levels of rare earth metal halide dopant in excess of 0.5 mole percent are operable, but with no substantive advantage. The lanthanide series of rare earth metals includes La , Ce , Pr , Nd , Pm , Sm , Eu , Gd , Tb , Dy , Ho , Er , Tm , Yb , and Lu .

We have found that up to 2.5 mole percent total of non-essential, but useful, metal halides, such as AlX_3 , GaX_3 , and InX_3 , wherein X is selected from the group of fluoride, chloride, and bromide, may be included to modify the proportions of the base glass, most generally to adjust the refractive index thereof. Individual additions will consist of up to 1.5% AlX_3 , up to 1.5% GaX_3 , and up to 2% InX_3 . In the preferred glasses the AlX_3 concentration will not exceed 1%, the GaX_3 concentration will not exceed 1%, the InX_3 concentration will not exceed 1.5%, and the total of all such additions will not exceed 2%.

Prior Art

In addition to the Jha and Parker journal article briefly discussed above, the following literature references are of interest:

J. L. Mouric et al. in PROGRESS IN CADMIUM HALIDE GLASSES, Materials Science Forum, Volume 5, pp. 135-144 (1985), describe their laboratory work in preparing glasses within the following four systems:

CdCl_2 - CdF_2 - NaCl or NaF

CdF_2 - NaCl - BaCl_2 or BaF_2

BaCl_2 - NaF - CdCl_2 or CdF_2

BaF_2 - NaF - CdCl_2 or CdF_2

There is no discussion of doping those glasses with rare earth metals such that the authors were unaware of the glass stability problem giving rise to the present invention.

M. Matecki et al. in ALKALI CADMIUM HALIDE GLASSES, Fourth International Symposium on Halide Glasses, January 26-29, 1987, pages 470-476, reviewed their investigations of glass forming compositions within the following ternary systems:

CdCl_2 - CdF_2 - KF

CdCl_2 - CdF_2 - KCl

CdCl_2 - CdF_2 - KBr

CdCl_2 - CdF_2 - KI

CdCl_2 - NaF - KF

CdCl_2 - NaF - KCl

CdCl_2 - NaF - KBr

CdCl_2 - NaF - KI

No mention is made of doping those glasses with rare earth metals.

M. Matecki et al. in COMPOSITION ADJUSTMENTS IN CADMIUM FLUOROCHLORIDE GLASSES, Journal of Non-Crystalline Solids, 140, pages 82-86 (1992) disclose their laboratory work in evaluating the utility of adding SrF_2 , InF_3 , or KF to cadmium fluorochloride glasses containing Na and Ba. No reference is made of doping cadmium halide-containing glasses with rare earth metals.

U. S. Patent No. 4,647,545 (Lucas et al.) is also of interest in that it discloses in very general and broad terms the formation of glasses containing at least one member of the group of cadmium halide, manganese halide, and zinc halide. Whereas the patentees refer to possible glass forming composition areas in very broad terms, including the possibility of incorporating rare earth metals in those compositions, there is no apparent recognition of the lack of glass stability problem when a rare earth metal is included in the composition, much less providing a solution to that problem. That is, the heart of the present invention resides in the finding of metal chlorides, bromides, and fluorides which, when incorporated into the base cadmium halide-containing composition, will so stabilize the glass that the inclusion of a rare earth metal will not result in devitrification of the glass. Lucas et al. make no mention of the problem and do not provide a working example having a composition coming within the ranges of the present invention such as to constitute an accidental disclosure.

Description of Preferred Embodiments

Table I records a group of glass compositions, expressed in terms of mole percent, illustrative of the inventive glasses. The glasses were prepared by compounding the batch ingredients, thoroughly mixing the ingredients together to assist in achieving a homogeneous melt, and then charging the batch mixtures into vitreous carbon crucibles. The crucibles were introduced into a dry glove box under a nitrogen atmosphere. The crucibles were heated to 800°C and, after a period of 30 minutes, the temperature was reduced to 700°C and the crucibles were maintained at that temperature for 15 minutes to assure a minimum water content in the resultant glasses. The melts were poured into steel molds to form cylindrical rods having a diameter of 4 mm and a length of 50 mm which were transferred immediately to an annealer

operating at about 125°C.

TABLE I

	1	2	3	4	5	6	7
CdF ₂	16.5	16.5	17.0	17.0	17.0	17.0	16.0
CdCl ₂	30.1	30.1	33.0	33.0	33.0	33.0	33.5
BaF ₂	5.8	5.8	10.0	10.0	10.0	10.0	2.5
NaF	32.0	32.0	34.0	34.0	34.0	34.0	29.0
KF	2.9	2.9	3.0	3.0	3.0	3.0	6.0
LiF	--	--	3.0	--	--	--	--
MnCl ₂	2.9	--	--	--	--	--	--
ZnCl ₂	--	2.9	--	3.0	3.0	3.0	3.0
PbF ₂	3.9	3.9	--	--	--	--	7.0
PbCl ₂	3.9	3.9	--	--	--	--	--
PbBr ₂	1.9	1.9	--	--	--	--	3.0
PrCl ₃	0.05	0.05	0.05	0.05	0.1	0.15	0.05
	8	9	10	11	12	13	14
CdF ₂	45.5	17.0	17.0	17.0	50.0	17.0	45.5
CdCl ₂	4.3	33.0	28.0	33.0	--	33.0	4.5
BaF ₂	7.0	12.0	13.0	10.0	--	10.0	--
BaCl ₂	--	--	--	--	10.0	--	10.0
NaF	33.8	34.0	34.0	34.0	--	34.0	--
NaCl	--	--	--	--	34.0	--	34.0
KF	2.4	3.0	3.0	3.0	--	3.0	--
KCl	--	--	--	--	3.0	--	3.0
BeF ₂	--	0.5	5.0	--	--	--	--
MgF ₂	--	0.5	--	--	--	--	--
ZnCl ₂	3.0	--	--	--	3.0	3.0	3.0
CoCl ₂	--	--	--	3.0	--	--	--
PrCl ₃	0.05	0.1	0.1	0.1	0.05	--	--
NdF ₃	--	--	--	--	--	0.05	--
ErF ₃	--	--	--	--	--	--	0.10
TlCl	4.0	--	--	--	--	--	--

TABLE I (Continued)

	15	16	17	18	19	20
CdF ₂	45.5	45.5	48.5	48.5	48.5	17.0
CdCl ₂	4.5	4.5	1.5	1.5	1.5	33.0
BaCl ₂	9.6	8.5	11.0	11.0	13.0	--
NaF	--	--	--	--	--	34.0
NaCl	34.0	34.0	34.0	34.0	35.0	--
KF	--	--	--	--	--	3.0
KCl	3.0	3.0	--	--	--	--
ZnCl ₂	3.0	3.0	2.0	2.0	2.0	--
LiF	--	--	--	--	--	3.0
TlCl	--	--	3.0	--	--	--
PbCl ₂	--	--	--	3.0	--	10.0
PrCl ₃	0.05	0.05	0.05	0.05	0.05	0.10
InF ₃	0.4	1.5	--	--	--	--

It has proven to be possible to optically evaluate the inventive glasses for their suitability as hosts for rare earth metal dopants. To illustrate, in the case of the inventive glasses doped with praseodymium, which glasses are of particular interest for use as single mode optical fiber amplifiers operating at 1.3 μm , the glasses have been characterized by measuring the decay of the 1.3 μm fluorescence. Results of those measurements are recorded below in Table II in terms of microseconds. Table II indicates that the inventive glasses can have fluorescence lifetimes that are as long as about 300 μsec and, consequently, represent a significant improvement over the lifetimes of the current benchmark, viz., ZBLAN glasses exhibiting lifetimes of about 110 μsec .

TABLE II

	1	2	3	4	5	6	8
μsec	246	276	200	268	240	212	230
	10	15	16	17	18	19	
μsec	262	270	262	264	272	290	

In the case of erbium-doped glasses, illustrated in Example 14, the glasses exhibited a strong emission of green light, peaking at about 523 nm, 542 nm, and 551 nm, when pumped with 800 nm light, indicating their potential utility as an upconversion source.

The more preferred inventive compositions consist essentially, in mole percent, of 44-52% CdF₂ and/or CdCl₂, 4-11% BaF₂ and/or BaCl₂, 30-35% NaF and/or NaCl, and 2-6% KF and/or KCl, wherein up to 7% total of at least one metal selected from the group of Cd, Ba, Na, and K can be incorporated as a bromide, along with 1-5% total of at least one stabilizing metal halide selected from the group consisting of LiX, BeX₂, MgX₂, MnX₂, CoX₂, and ZnX₂, wherein X is at least one halide selected from the group consisting of fluoride, chloride, and bromide, optionally up to 10% of a lead halide selected from the group of PbF₂, PbCl₂, and PbBr₂, optionally up to 5% TlF, TlCl, and TlBr, and 0.025-0.25% ReX₃, wherein Re is at least one rare earth metal selected from the lanthanide series of rare earth metals and X is a

halide selected from the group consisting of fluoride, chloride, and bromide. No more than a total of 1.5% of non-essential metal halides will be included.

Example 2 is the most preferred composition.

Claims

1. A transparent glass exhibiting excellent transmission far into the infrared region of the electromagnetic radiation spectrum consisting essentially, expressed in terms of mole percent, of 42-55% CdF_2 and/or CdCl_2 , 30-40% NaF and/or NaCl , 2-20% total of BaF_2 and/or BaCl_2 + KF and/or KCl , consisting of 0-15% BaF_2 and/or BaCl_2 and 0-7% KF and/or KCl , 1-12% total of at least one stabilizing metal halide in the indicated proportion selected from the group consisting of 0-10% LiX , 0-10% BeX_2 , 0-10% MgX_2 , 0-10% MnX_2 , 0-12% PbX_2 , 0-10% CoX_2 , 0-7% TiX , and 0-10% ZnX_2 , wherein X is at least one halide selected from the group consisting of fluoride, chloride, and bromide, and 0.005-0.5% ReX_3 , wherein Re is at least one rare earth metal selected from the lanthanide series of rare earth metals and X is at least one halide selected from the group consisting of fluoride, chloride, and bromide, and wherein up to 10% total of at least one metal selected from the group consisting of Cd, Ba, Na, and K can be incorporated as a bromide.
2. A transparent glass according to claim 1 also containing up to 2% each of BaF_2 and/or BaCl_2 and KF and/or KCl .
3. A transparent glass according to claim 1 also containing up to 2.5% total of at least one metal halide in the indicated proportion selected from the group consisting of 0-1.5% AlX_3 , 0-1.5% GaX_3 , and 0-2% InX_3 , wherein X is at least one halide selected from the group consisting of fluoride, chloride, and bromide.
4. A transparent glass according to claim 1 consisting essentially of 44-52% CdF_2 and/or CdCl_2 , 4-11% BaF_2 and/or BaCl_2 , 30-35% NaF and/or NaCl , 2-6% KF and/or KCl , 1-5% total of at least one stabilizing metal halide selected from the group consisting of LiX , BeX_2 , MgX_2 , MnX_2 , CoX_2 and ZnX_2 , wherein X is at least one halide selected from the group consisting of fluoride, chloride, and bromide, up to 10% total of a lead halide selected from the group consisting of PbF_2 , PbCl_2 , and PbBr_2 , up to 5% total of a thallium halide selected from the group consisting of TlF , TlCl , and TlBr , and wherein up to 7% total of at least one metal selected from the group consisting of Ca, Ba, Na, and K can be incorporated as a bromide.
5. A transparent glass according to claim 4 also containing up to 2% total of at least one metal halide in the indicated proportions selected from the group consisting of 0-1% AlX_3 , 0-1% GaX_3 , and 0-1.5% InX_3 , wherein X is selected from the group consisting of fluoride, chloride, and bromide.
6. An optical amplifier with an amplification medium fabricated from a transparent glass according to claims 1, 2, 3, 4 or 5.
7. An optical amplifier according to claim 6 which amplifies light at about $1.31\mu\text{m}$ with an amplification medium consisting of a single mode optical fiber fabricated from a transparent glass wherein ReX_3 consists of 0.01-0.5% PrX_3 .
8. A laser with a gain medium fabricated from a transparent glass according to claims 1, 2, 3, 4, or 5.
9. An upconversion source or laser with an upconversion medium fabricated from a transparent glass according to claims 1, 2, 3, 4, or 5.
10. An optical waveguide consisting of a transparent glass core portion enveloped within a transparent compatible glass cladding layer which exhibits a lower refractive index than said core glass, said core and/or said cladding consisting of a glass according to claims 1, 2, 3, 4, or 5.
11. An optical waveguide according to claim 10 wherein said core glass contains up to 10% total of at least one metal halide in the indicated proportion of 1-10% PbX_2 and 1-5% TiX .

Patentansprüche

1. Transparentes Glas mit einer ausgezeichneten Transmission bis weit in den Infrarotbereich des elektromagnetischen Strahlungsspektrums, bestehend im wesentlichen, ausgedrückt in Mol-%, aus 42 - 55 % CdF_2 und/oder CdCl_2 , 30 - 40 % NaF und/oder NaCl , insgesamt 2 - 20 % BaF_2 und/oder BaCl_2 + KF und/oder KCl , bestehend aus 0 - 15 % BaF_2 und/oder BaCl_2 und 0-7 % KF und/oder KCl , insgesamt 1 - 12 % wenigstens eines stabilisierenden Metallha-

halide selected from the group consisting of fluoride, chloride, and bromide. No more than a total of 1.5% of non-essential metal halides will be included.

Example 2 is the most preferred composition.

Claims

1. A transparent glass exhibiting excellent transmission far into the infrared region of the electromagnetic radiation spectrum consisting essentially, expressed in terms of mole percent, of 42-55% CdF_2 and/or CdCl_2 , 30-40% NaF and/or NaCl , 2-20% total of BaF_2 and/or BaCl_2 + KF and/or KCl , consisting of 0-15% BaF_2 and/or BaCl_2 and 0-7% KF and/or KCl , 1-12% total of at least one stabilizing metal halide in the indicated proportion selected from the group consisting of 0-10% LiX , 0-10% BeX_2 , 0-10% MgX_2 , 0-10% MnX_2 , 0-12% PbX_2 , 0-10% CoX_2 , 0-7% TiX , and 0-10% ZnX_2 , wherein X is at least one halide selected from the group consisting of fluoride, chloride, and bromide, and 0.005-0.5% ReX_3 , wherein Re is at least one rare earth metal selected from the lanthanide series of rare earth metals and X is at least one halide selected from the group consisting of fluoride, chloride, and bromide, and wherein up to 10% total of at least one metal selected from the group consisting of Cd, Ba, Na, and K can be incorporated as a bromide.
2. A transparent glass according to claim 1 also containing up to 2% each of BaF_2 and/or BaCl_2 and KF and/or KCl .
3. A transparent glass according to claim 1 also containing up to 2.5% total of at least one metal halide in the indicated proportion selected from the group consisting of 0-1.5% AlX_3 , 0-1.5% GaX_3 , and 0-2% InX_3 , wherein X is at least one halide selected from the group consisting of fluoride, chloride, and bromide.
4. A transparent glass according to claim 1 consisting essentially of 44-52% CdF_2 and/or CdCl_2 , 4-11% BaF_2 and/or BaCl_2 , 30-35% NaF and/or NaCl , 2-6% KF and/or KCl , 1-5% total of at least one stabilizing metal halide selected from the group consisting of LiX , BeX_2 , MgX_2 , MnX_2 , CoX_2 and ZnX_2 , wherein X is at least one halide selected from the group consisting of fluoride, chloride, and bromide, up to 10% total of a lead halide selected from the group consisting of PbF_2 , PbCl_2 , and PbBr_2 , up to 5% total of a thallium halide selected from the group consisting of TlF , TlCl , and TlBr , and wherein up to 7% total of at least one metal selected from the group consisting of Ca, Ba, Na, and K can be incorporated as a bromide.
5. A transparent glass according to claim 4 also containing up to 2% total of at least one metal halide in the indicated proportions selected from the group consisting of 0-1% AlX_3 , 0-1% GaX_3 , and 0-1.5% InX_3 , wherein X is selected from the group consisting of fluoride, chloride, and bromide.
6. An optical amplifier with an amplification medium fabricated from a transparent glass according to claims 1, 2, 3, 4 or 5.
7. An optical amplifier according to claim 6 which amplifies light at about $1.31\mu\text{m}$ with an amplification medium consisting of a single mode optical fiber fabricated from a transparent glass wherein ReX_3 consists of 0.01-0.5% PrX_3 .
8. A laser with a gain medium fabricated from a transparent glass according to claims 1, 2, 3, 4, or 5.
9. An upconversion source or laser with an upconversion medium fabricated from a transparent glass according to claims 1, 2, 3, 4, or 5.
10. An optical waveguide consisting of a transparent glass core portion enveloped within a transparent compatible glass cladding layer which exhibits a lower refractive index than said core glass, said core and/or said cladding consisting of a glass according to claims 1, 2, 3, 4, or 5.
11. An optical waveguide according to claim 10 wherein said core glass contains up to 10% total of at least one metal halide in the indicated proportion of 1-10% PbX_2 and 1-5% TiX .

Patentansprüche

1. Transparentes Glas mit einer ausgezeichneten Transmission bis weit in den Infrarotbereich des elektromagnetischen Strahlungsspektrums, bestehend im wesentlichen, ausgedrückt in Mol-%, aus 42 - 55 % CdF_2 und/oder CdCl_2 , 30 - 40 % NaF und/oder NaCl , insgesamt 2 - 20 % BaF_2 und/oder BaCl_2 + KF und/oder KCl , bestehend aus 0 - 15 % BaF_2 und/oder BaCl_2 und 0-7 % KF und/oder KCl , insgesamt 1 - 12 % wenigstens eines stabilisierenden Metallha-



logenids im angegebenen Anteil, ausgewählt aus der Gruppe, bestehend aus 0 - 10 % LiX, 0 - 10 % BeX₂, 0 - 10 % MgX₂, 0 - 10 % MnX₂, 0 - 12 % PbX₂, 0 - 10 % CoX₂, 0 - 7 % TiX und 0 - 10 % ZnX₂, wobei X wenigstens ein Halogenid ist, ausgewählt aus der Gruppe, bestehend aus Fluorid, Chlorid und Bromid, darstellt, und 0,005 - 0,5 % ReX₃, wobei Re wenigstens ein Seltenerdmetall ist, ausgewählt aus der Lanthanidenreihe der Seltenerdmetalle und X wenigstens ein Halogenid ist, ausgewählt aus der Gruppe, bestehend aus Fluorid, Chlorid und Bromid, und wobei bis zu insgesamt 10 % wenigstens eines Metalls, ausgewählt aus der Gruppe, bestehend aus Cd, Ba, Na und K als Bromid eingebaut werden können.

2. Transparentes Glas nach Anspruch 1, das weiterhin bis zu je 2 % BaF₂ und/oder BaCl₂ und KF und/oder KCl enthält.

3. Transparentes Glas nach Anspruch 1, das weiterhin bis zu insgesamt 2,5 % wenigstens eines Metallhalogenids im angegebenen Anteil, ausgewählt aus der Gruppe, bestehend aus 0 - 1,5 % AlX₃, 0 - 1,5 % GaX₃ und 0 - 2 % InX₃ enthält, wobei X wenigstens ein Halogenid ist, ausgewählt aus der Gruppe, bestehend aus Fluorid, Chlorid und Bromid.

4. Transparentes Glas nach Anspruch 1, bestehend im wesentlichen aus 44 - 52 % CdF₂ und/oder CdCl₂, 4 - 11 % BaF₂ und/oder BaCl₂, 30 - 35 % NaF und/oder NaCl, 2 - 6 % KF und/oder KCl, insgesamt 1 - 5 % wenigstens eines stabilisierenden Metallhalogenids, ausgewählt aus der Gruppe, bestehend aus LiX, BeX₂, MgX₂, MnX₂, CoX₂ und ZnX₂, wobei X wenigstens ein Halogenid ist, ausgewählt aus der Gruppe, bestehend aus Fluorid, Chlorid und Bromid, bis zu insgesamt 10 % eines Bleihalogenids, ausgewählt aus der Gruppe bestehend aus PbF₂, PbCl₂ und PbBr₂, bis zu insgesamt 5 % eines Thalliumhalogenids, ausgewählt aus der Gruppe, bestehend aus TlF, TlCl und TlBr, und wobei bis zu insgesamt 7 % wenigstens eines Metalls, ausgewählt aus der Gruppe, bestehend aus Ca, Ba, Na und K als ein Bromid eingebaut werden können.

5. Transparentes Glas nach Anspruch 4, das weiterhin bis zu insgesamt 2 % wenigstens eines Metallhalogenids in den angegebenen Anteilen enthält, ausgewählt aus der Gruppe, bestehend aus 0 - 1 % AlX₃, 0 - 1 % GaX₃ und 0 - 1,5 % InX₃, wobei X aus der Gruppe, bestehend aus Fluorid, Chlorid und Bromid ausgewählt ist.

6. Optischer Verstärker mit einem Verstärkungsmedium, hergestellt aus einem transparenten Glas nach einem der Ansprüche 1, 2, 3, 4 oder 5.

7. Optischer Verstärker nach Anspruch 6, der Licht bei etwa 1,31 µm mit einem Verstärkungsmedium, bestehend aus einer optischen Monomode-Faser, hergestellt aus einem transparenten Glas, wobei ReX₃ aus 0,01 - 0,5 % PrX₃ besteht, verstärkt.

8. Laser mit einem Verstärkungsmedium, hergestellt aus einem transparenten Glas nach einem der Ansprüche 1, 2, 3, 4 oder 5.

9. Eine Hochwandlerquelle oder ein Laser mit einem Hochwandlungsmedium, hergestellt aus einem transparenten Glas nach einem der Ansprüche 1, 2, 3, 4 oder 5.

10. Optischer Wellenleiter, bestehend aus einem transparenten Kernanteil aus Glas, umhüllt mit einer transparenten, kompatiblen Mantelschicht aus Glas, die einen niedrigeren Brechungsindex aufweist als das Kernglas, wobei der Kern und/oder der Mantel aus einem Glas nach einem der Ansprüche 1, 2, 3, 4 oder 5 bestehen.

11. Optischer Wellenleiter nach Anspruch 10, wobei das Kernglas bis zu insgesamt 10 % wenigstens eines Metallhalogenids im angegebenen Anteil von 1 - 10 % PbX₂ und 1 - 5 % TiX enthält.

Revendications

1. Verre transparent présentant une excellente transmission jusque dans le domaine infrarouge du spectre de rayonnement électromagnétique, constitué essentiellement, exprimé en termes de pourcentage molaire, de 42 à 55% de CdF₂ et/ou de CdCl₂, de 30 à 40% de NaF et/ou de NaCl, de 2 à 20% au total de BaF₂ et/ou de BaCl₂ + KF et/ou de KCl, constitué de 0 à 15% de BaF₂ et/ou de BaCl₂ et de 0 à 7% de KF et/ou de KCl, 1 à 12% au total d'au moins un halogénure de métal stabilisant, dans la proportion indiquée, choisi dans le groupe constitué par 0 à 10% de LiX, 0 à 10% de BeX₂, 0 à 10% de MgX₂, 0 à 10% de MnX₂, 0 à 12% de PbX₂, 0 à 10% de CoX₂, 0 à 7% de TiX et 0 à 10% de ZnX₂, dans lequel X est au moins un halogénure choisi dans le groupe constitué par le fluorure, le chlorure et le bromure, et de 0,005 à 0,5% de ReX₃, dans lequel Re est au moins un métal terreux rare choisi parmi les lanthanides de métaux terreux rares et X est au moins un halogénure choisi dans le groupe constitué par



le fluorure, le chlorure et le bromure, et dans lequel jusqu'à 10% au total d'au moins un métal choisi dans le groupe constitué par Cd, Ba, Na et K peut être incorporé en tant que bromure.

2. Verre transparent selon la revendication 1, contenant également jusqu'à 2% de chacun des corps suivants : BaF_2 et/ou BaCl_2 et KF et/ou KCl.
3. Verre transparent selon la revendication 1, contenant également jusqu'à 2,5% au total d'au moins un halogénure de métal, dans la proportion indiquée, choisi dans le groupe constitué par 0 à 1,5% de AlX_3 , 0 à 1,5% de GaX_3 et 0 à 2% de InX_3 , dans lequel X est au moins un halogénure choisi dans le groupe constitué par le fluorure, le chlorure et le bromure.
4. Verre transparent selon la revendication 1, constitué essentiellement de 44 à 52% de CdF_2 et/ou de CdCl_2 , de 4 à 11% de BaF_2 et/ou BaCl_2 , de 30 à 35% de NaF et/ou de NaCl, de 2 à 6% de KF et/ou de KCl, de 1 à 5% au total d'au moins un halogénure de métal stabilisant choisi dans le groupe constitué par LiX , BeX_2 , MgX_2 , MnX_2 , CoX_2 et ZnX_2 dans lequel X est au moins un halogénure choisi dans le groupe constitué par le fluorure, le chlorure et le bromure, de jusqu'à 10% au total d'un halogénure de plomb choisi dans le groupe constitué par PbF_2 , PbCl_2 et PbBr_2 , de jusqu'à 5% au total d'un halogénure de thallium choisi dans le groupe constitué par TlF , TlCl et TlBr et dans lequel jusqu'à 7% au total d'au moins un métal choisi dans le groupe constitué par Ca, Ba, Na et K peut être incorporé en tant que bromure.
5. Verre transparent selon la revendication 4, contenant également jusqu'à 2% au total d'au moins un halogénure de métal, dans les proportions indiquées, choisi dans le groupe constitué par 0 à 1% de AlX_3 , 0 à 1% de GaX_3 et 0 à 1,5% de InX_3 , dans lequel X est choisi dans le groupe constitué par le fluorure, le chlorure et le bromure.
6. Amplificateur optique comportant un milieu d'amplification fabriqué à partir d'un verre transparent selon l'une quelconque des revendications 1 à 5.
7. Amplificateur optique selon la revendication 6 qui amplifie de la lumière d'environ $1,31 \mu\text{m}$ et qui comporte un milieu d'amplification constitué d'une fibre optique monomode fabriquée à partir d'un verre transparent dans lequel ReX_3 est constitué de 0,01 à 0,5% de PrX_3 .
8. Laser comportant un milieu de gain fabriqué à partir d'un verre transparent selon l'une quelconque des revendications 1 à 5.
9. Source ou laser de transposition de fréquence comportant un milieu de transposition de fréquence fabriqué à partir d'un verre transparent selon l'une quelconque des revendications 1 à 5.
10. Guide d'onde optique constitué par une partie de noyau en verre transparent enfermée à l'intérieur d'une couche de revêtement en verre transparent compatible qui présente un indice de réfraction plus faible que celui du verre du noyau, ledit noyau et/ou ledit revêtement étant constitué d'un verre selon l'une quelconque des revendications 1 à 5.
11. Guide d'onde optique selon la revendication 10, dans lequel ledit verre du noyau contient jusqu'à 10% au total d'au moins un halogénure de métal, dans la proportion indiquée, de 1 à 10% de PbX_2 et de 1 à 5% de TlX .

