

ABSTRACT

1

Hydrophilic contact lens molds are transiently modified to provide a water dynamic contact angle equal to or less than 100° by treatment with a wetting agent which may be water or a surfactant composition which provides a mold surface having a water wetting force of at least 70 mg to afford a reduction in lens hole defects in hydrophilic contact lens manufacture.

10

15

This Sheet Has Been Replaced



20

25

30

35