

Method for repairing gas turbine components made of ceramic composite materials and device for carrying out said method

5 The present invention relates to a method for repairing gas turbine components made of ceramic composite material comprising the features of the preamble of claim 1, and a device for carrying out said method comprising the features of the preamble of claim 8.

10

There will be an increased use of ceramic components in gas turbines in the future. Due to higher gas temperatures or component temperatures, higher efficiencies of the engines can be achieved with these components. However, it is a general problem of ceramic components that they have a lower ductility
15 than comparable metal components. This goes hand in hand with low fracture toughness, and thus a high risk of fracture. To prevent this problem, ceramics can be reinforced, for example by fibers or particles. Such ceramic composite materials, in particular fibrous composite materials, also called CMC or fiber ceramics, provide a number of advantages. Compared to conventional technical ceramics they have a significantly higher fracture strain, a higher crack resistance and a very high thermal shock resistance. Alternatively, also a composite of
20 ceramics and particles, in addition to fibers, can be used to increase for example the abrasion strength, thermal shock resistance or fracture strength. They generally are well-suited for various applications in aeronautics due to their high temperature stability and their low density. Combinations of fibrous materials / particle materials / matrix materials made
25 of the following materials and combinations thereof can be given as examples for common ceramic fibrous composite materials and particle composite materials: silicon carbide/silicon,

30

silicon carbide/silicon nitride, silicon carbide/carbon, carbon/carbon, aluminum oxide/aluminum.

5 The repair of components or component sections made of ceramic composite materials raises a problem, as hitherto existing repair methods require many process steps and time-consuming furnace treatments of the components to be repaired.

10 A repair method for ceramic fibrous composite materials is presented in Patent Specification US 6 820 334 B2. To repair the components, cut-to-size tapes of ceramic fibrous composite materials are positioned next to a pre-processed spot to be repaired, the component as a whole subsequently is autoclaved in a vacuum bag and is then subjected to a first heat treatment at approximately 750°C and a second heat treatment at approximately 1425°C in a vacuum furnace.

20 Another solution is known from EP 1 559 499 A1. Here, the component made of a ceramic fibrous composite material first is processed mechanically to form a depression or to wear out the matrix of the composite material, to then repair the component by locally reconstructing the ceramic matrix plus sintering and/or new infiltration using CVD (Chemical Vapor Deposition) methods at 700°C up to 1100°C.

25

What both methods have in common is that a component section needs to be processed with a plurality of process steps. Material partly needs to be pre-deposited, which is time-consuming, besides there are several basic problems with processing fibers and aggregates in a furnace, a mold or by the use of a pre-deposited tape: the first problem is that for bigger components accordingly big furnaces need to be available to make repair possible in the first place. In the case of small com-

30

ponents, the furnace size is a problem insofar as there often is a large number of small components, and accordingly many furnace cycles generally also need to be completed for repairing the large number of small components, while it is barely possible to meet the individual requirements (for example temperatures, pressures, etc.) of all components. The second problem is that due to the long-time acting heat of the molten mass or furnace there is a risk of decomposition of fibers and/or damage of the component to be repaired and/or damage of the spot to be repaired. A high stress caused by the thermal influence and the applied materials further needs to be compensated when treating large surfaces. Furthermore, the use of methods requiring a casting mold is limited, in particular in the case of free formed surfaces of the gas turbine section, like for example airfoils, as individual damaging mechanisms and individual deformations due to manufacture and operation imply an enormous number of different pre-molds. Since gas turbine components are subjected to a plurality of actions by corrosive substances, oxidizing atmospheres, high temperatures or even foreign objects, damages to the components are practically unavoidable, justifying the demand for cost-effective repair methods in particular in view of the high costs of the new parts.

It therefore is the object of the invention to provide a low-cost method for repairing generic gas turbine components and a corresponding device for carrying out said method.

The invention solves the object with a method comprising the features of claim 1 and a device comprising the features of claim 10. Further preferred embodiments of the invention can be learned from the sub claims and the related descriptions and drawings.

For the solution of the object, the invention proposes a method for repairing a gas turbine component, the gas turbine component at least at the spot to be repaired consisting of a ceramic composite material, and during which the gas turbine component is locally heated in a zone by an energy beam, and one or more auxiliary materials and optionally fibers and/or particles are fed to this zone, with a ceramic being generated in the melting zone through this auxiliary material or these auxiliary materials, which together with the fed fibers and/or particles forms a ceramic fibrous composite material. The inventive process of bonding the generated ceramic to the ceramic present in the component essentially is possible in two ways, in each of which the component is thermally activated. The first way includes incipiently melting the present ceramic and bonding it to the fed materials. Due to possibly occurring shrinkages, this way is suited for certain components only. The second way is carried out by way of a heating-coating-reaction. Bonding the present material to fed material at the boundary surface includes three steps. In the first step, a zone of the component is heated by an energy beam or by the molten mass of the fed materials. In the second step, the present ceramic boundary surface is coated by the fed materials, for example by fusible silicon or aluminum. In the third step, the molten metals partially or completely react to metal-non-metal-compounds (ceramic).

The inventive method for repairing the gas turbine component enables the local generation of a ceramic composite material, without the need for time-consuming furnace treatments. If specifically required, the component can be subjected to a furnace treatment, for example a stress-relief annealing, but normally this is not necessary, as due to the very high tem-

peratures during operation low stresses in the components repaired according to the invention are quickly relieved anyway. A special advantage of the developed method is that shrinkage stresses, which are practically unavoidable when using standard methods (for example sintering) for generating ceramic composite materials, can be reduced. The inventive method generally is easy to carry out, as only the damaged area is actually repaired, and not the component as a whole needs to be subjected to a sintering process or casting process. The component also does not have to be newly infiltrated, as the ceramic composite material can directly be generated locally by inventively feeding the fibers to the melting zone, where the ceramic is formed.

Preferably, the fed auxiliary material or the fed auxiliary materials completely or partially react to a ceramic in a chemical reaction in the melting zone. The components required therefor, for example a metal like silicon and a non-metal like carbon, are fed to the melting zone as auxiliary materials in a stoichiometric ratio and then react to the desired ceramic, in this case silicon carbide. A metal proportion which is 20 to 40 % higher than it would be required for stoichiometric reasons is preferably provided to have all of the non-metal react completely. The reason for this is the aim that the carbon reacts completely and does not remain elementally in the fusion zone due to local lack of silicon. A left-over of silicon is approvingly accepted, as this may even have positive effects on the material properties, as many finely dispersed silicon inclusions in the matrix of the ceramic can have a positive effect on the ductility and fracture toughness of the fusion zone. While the auxiliary materials react, they ideally equally enclose the non-melted fibers and/or particles of the base material exposed in the molten mass and the addi-

tionally fed fibers and/or particles, so that after the chemical reaction the new material is firmly bonded to the base material. It is a specific advantage that not only a compound between two matrix materials is obtained, but that old and new
5 fibers and/or particles extend into the molten bath reacting to ceramic, by which a compound of particularly high quality is generated according to the invention. A matrix generally characterizes a continuous material or phase containing non-continuous other phases and/or particles and/or fibers of the
10 same or another material.

The fed auxiliary material or the fed auxiliary materials preferably can already contain the ceramic to be generated. The auxiliary material or the auxiliary materials fed to the melting zone are completely or partially heated beyond the melting point by the energy beam. The molten bath generated thereby due to its liquid nature is able to flow around the fibers and/or particles of the base material and the newly fed fibers and/or particles and, after becoming solid, to bond the
20 base material to the additionally fed materials. Preferably, the fed auxiliary material and the additionally fed fibers and/or particles consist of the same material combination as the base material, i.e. the auxiliary material or the auxiliary materials and/or the fibers and/or the particles are chosen
25 in such a way that they generate the same ceramic composite material, of which the gas turbine component also mainly consists. Due to the similar compound partners, the resulting compound is particularly easy to realize (identical properties like for example the melting point facilitate the process),
30 and the compound further is of particularly high quality. For example, identical coefficients of thermal expansion are very advantageous in order to minimize thermal stresses of the com-

pound, being of overriding importance for applications in the turbine section.

The fed auxiliary material or the fed auxiliary materials
5 and/or the fibers and/or the particles are preferably pre-deposited and/or are fed to the reaction energy via one or more feeders. In some cases, pre-depositing the auxiliary materials and/or the fibers and/or the particles at the spot to be repaired can provide advantages, but normally the auxiliary materials and/or the fibers and/or the particles are preferably
10 fed via a feeder which is coaxial or lateral to the energy beam. This provides the advantage that all layers can be processed, and with a controlled feeding the auxiliary materials and/or fibers and/or particles can be fed to the fusion zone in a defined manner. This can be carried out in a particularly defined and controlled manner, if a flux cored wire is provided for feeding the auxiliary materials and/or the fibers and/or the particles. This flux cored wire contains the required materials in a suitable amount and composition. A flux
15 cored wire provides the advantage that it is possible to feed all required components via one single feeder. Depending on the needs, the flux cored wire for example contains silicon and carbon as well as silicon carbide fibers and is used to repair a component made of a ceramic silicon carbide composite material. Even very small fibers, which due to their pulmonary intrusion usually can only be fed involving difficulties and effort, can be fed easily, but also continuous fibers can be fed without any difficulties, as the length of the flux cored wire is not limited. Such a defined feeding of fibers of any
20 length and diameter for repairing ceramic fibrous composite materials by the use of reacting filler materials provides miscellaneous repair options. Thus, it is also possible to close cracks in gas turbine components made of ceramic fibrous

composite materials with the inventive method and to reinforce such a weak spot for example by several layers on top of each other. It is also possible to join two components together for example by arranging the melting zone and thus the fusion zone
5 right in the area, where the components contact each other.

The design of the flux cored wire is preferably chosen in such a way that the flux cored wire comprises an outer sheath, the material of the outer sheath itself possibly containing one or
10 more auxiliary materials, and the outer sheath encloses an interior, auxiliary materials and/or fibers and/or particles being provided in the interior. Such a flux cored wire provides the advantage that the outer sheath does not only serve as a structural element, but at the same time can assume the role
15 of the auxiliary materials. Thereby, material is saved and no impurities, which would have occurred by the use of a flux cored wire without filler material outer sheath, are leftover in the component. The interior of the flux cored wire is filled with the various auxiliary materials and fibers, the
20 auxiliary materials for example being present in the form of sheet metal, powder, paste or fibers. The amount and kind of the filler materials is adjusted to the respective need and it is ensured that a constant amount of filler materials and/or fibers and/or particles is continuously fed to the melting
25 zone, which for example cannot always be guaranteed by pre-deposition, as in this case the components locally are not always available in the desired ratio. Pre-deposited material is fed to the molten bath by the molten bath generated by the energy beam together with the energy beam being guided across
30 the gas turbine component along a pre-defined path and material being pre-deposited on this path, which is melted by the energy beam and is thereby fed to the molten bath. When using such a pre-deposition it may happen that fibers and/or parti-

cles are not evenly dispersed in the pre-deposited fiber/powder mixture, but accumulate in an area (for example due to differences in density or agglomeration effects), and that the ceramic composite material formed from such a mixture then accordingly does not all over have the desired material properties, i.e. it could have weak spots.

A gas stream is preferably provided in the interior of the flux cored wire, which is preferably used to provide a protective gas and/or reactant gas for the repair method. Depending on the material of the component and the ceramic to be generated, it can be necessary or helpful to provide a protective gas or a reactant gas. For example, argon as a protective gas could shield the fusion zone from atmospheric oxygen or, in another case, could be used together with methane for depositing carbon.

The energy beam is preferably realized as a laser beam. The advantage of a laser beam is that the process does not have to be carried out in a vacuum and the melting zone due to the slight scattering of the laser beam can be formed in a highly defined manner. The energy beam preferably can also be realized as an electron beam, which can be advantageous for certain applications. Furthermore, the energy beam preferably can also be realized as an induction field. In this case the energy beam is induced in the component by the induction field, which is suitable in particular for ceramic composite materials containing conductive fibers or particles.

In the following, the invention is described in more detail on the basis of specific embodiments with the aid of figures. The figures show in detail:

Fig. 1: a schematic illustration of the inventive device.

Fig. 2: representation of an inventive repair of a gas turbine component made of ceramic fibrous composite material.

Fig. 3: cut AA of the gas turbine component from Fig. 2.

Fig. 4: schematic design of the inventive flux cored wire design.

Fig. 5: cut BB of the flux cored wire from Fig. 4.

Fig. 1 shows the inventive device for carrying out the method. An energy beam 1 can be seen, which is directed onto a base material surface 5 which is to be processed. Thereby, the base material is thermally activated locally in a zone, which here is realized as a melting zone 4, i.e. it is heated and/or melted, so that a coating by molten masses or molten products can be effected. Material is fed to this melting zone 4 via a lateral feeder 3 and/or via a symmetric or coaxial feeder 2. Optionally, this material can also be fed to the melting zone 4 in addition or exclusively via a pre-deposition 16. A process gas 15 (for example oxygen, methane, argon) can also be fed to the melting zone 4, optionally also the present surrounding atmosphere (for example atmospheric oxygen and/or atmospheric nitrogen) can be used to benefit the process (for example for oxide/nitride formation). The aim is to provide a ceramic fibrous composite material 6 by feeding material, optionally in combination with feeding gas, to repair for example the gas turbine component 7 illustrated in Fig. 2.

The gas turbine component 7 illustrated in Fig. 2 can be for example a single blade with blade root or also a blade on an integral component (blisk or vane cluster). As a result of operation, the gas turbine component 7 is torn and damaged on the stream inlet side, so that using the inventive repair method a ceramic fibrous composite material 6 has been applied onto the base body 8 of the gas turbine component 7 for reinforcement, to restore the initial blade geometry. For the purpose of clarification, Fig. 3 shows a cut AA through the gas turbine component 7.

Fig. 3 particularly clearly shows how the present base body 8 adjoins the newly applied ceramic fibrous composite material 6. With the inventive method it is possible to repair torn gas turbine components made of ceramic fibrous composite materials. The major advantage of the inventive method is that it is comparatively easy and low-priced, as only the damaged area is actually repaired and the gas turbine component 7 as a whole does not have to be subjected to a sintering process or casting process. The gas turbine component 7 also does not have to be newly infiltrated. Instead, it is possible to locally re-build the ceramic in the original composition and condition or in alternative qualities by inventively feeding the fibers 12 to the melting zone 4, so that the ceramic fibrous composite material 6 can directly be generated locally. Thereby, in certain cases a repair can also be carried out "on-wing", i.e. without the need for removing gas turbine components 7 from the gas turbine. Owing to this extremely reduced process effort, the described method is much more cost-effective than well-known repair methods of ceramic fibrous composite materials.

Fig. 4 shows the design of the inventive flux cored wire 14. The marked cut BB is shown in Fig. 5. The flux cored wire 14 contains fibers 12 and auxiliary materials 13 which can be available in different shapes, sizes and amounts. Particles
5 are not shown, but according to the invention they can also be contained in the flux cored wire, preferably if a particle-reinforced ceramic composite material is repaired. The fibers 12 can have a length of for example a few micrometers, or alternatively they can have any length (so-called continuous fi-
10 bers). The auxiliary materials 13 can be available in the form of small metal sheets, as powder or pastes. The interior 9, in which most of the fibers 12 and auxiliary materials 13 are provided, is enclosed by an outer sheath 10 which himself can also be an auxiliary material 13. In addition, a gas stream 11
15 can also be provided in the interior 9, via which protective gases and/or process gases 15 can be carried to the spot to be repaired via the flux cored wire 14.

By feeding the auxiliary materials 13 to the melting zone 4
20 generated by the energy beam 1, a ceramic is generated in the melting zone, which together with additionally fed fibers 12 forms a ceramic fibrous composite material 6. The components required therefor, for example a metal like silicon and a non-metal like carbon, are fed to the melting zone 4 as auxiliary
25 materials 13 in a stoichiometric ratio and then react to the desired ceramic, in this case silicon carbide. A silicon proportion optionally increased by 20 to 40 % ensures a complete reaction of the carbon, which cannot always be achieved with an absolutely stoichiometric ratio, as in this case it cannot
30 be assumed that for the total amount of carbon also silicon is available nearby for reaction. The leftover silicon ideally remains in finely dispersed silicon inclusions and thereby can

further help improve the ductility of the generated ceramic fibrous composite material 6.

The inventive flux cored wire 14 provides a number of options
5 for repairing gas turbine components. Depending on the needs,
the flux cored wire 14 can have an individual design to thus
comply with the different requirements of the different fiber
combinations and matrix combinations. This option for indivi-
dual composition, for choosing the amount of the auxiliary ma-
10 terials 13, of the fibers and also of the protective gas and
process gas 15 allows for the easy application and adaption of
the inventive method and the inventive device to existing and
future gas turbine components made of ceramic fibrous compo-
site materials.

Reference numerals:

- 1 energy beam
- 2 coaxial feeder
- 5 3 lateral feeder
- 4 melting zone
- 5 base material surface
- 6 ceramic fibrous composite material
- 7 gas turbine component
- 10 8 base body
- 9 interior
- 10 outer sheath
- 11 gas stream
- 12 fibers
- 15 13 auxiliary materials
- 14 flux cored wire
- 15 process gas
- 16 pre-deposition

Claims:

1. Method for repairing a gas turbine component (7), which at least at the spot to be repaired consists of a ceramic composite material, characterized in that an energy beam (1) locally heats the gas turbine component (7) in a zone, and that one or more auxiliary materials (13) and optionally fibers (12) and/or particles are fed to this zone, wherein a ceramic is generated in the melting zone (4) through this auxiliary material (13) or these auxiliary materials (13), which together with the fed fibers (12) and/or particles forms a ceramic composite material (6).
2. Method according to claim 1, characterized in that the fed auxiliary material (13) or the fed auxiliary materials (13) completely or partially react to a ceramic in a chemical reaction in said zone.
3. Method according to claim 2, characterized in that the auxiliary materials (13) include a metal and a non-metal, which in the chemical reaction react to a ceramic, and wherein the proportion of the metal is higher, preferably 20 to 40 %, than the proportion of the non-metal.
4. Method according to claim 1, characterized in that the fed auxiliary material (13) or the fed auxiliary materials (13) contain the ceramic to be generated.
5. Method according to any one of the preceding claims, characterized in that the auxiliary material (13) or the auxiliary materials (13) and/or the fibers (12) and/or the particles are chosen in such a way that they generate

the same ceramic composite material (6), of which the gas turbine component (7) also mainly consists.

- 5 6. Method according to any one of the preceding claims, characterized in that the fed auxiliary material (13) or the fed auxiliary materials (13) and/or the fibers (12) and/or the particles are pre-deposited and/or are fed via one or more feeders (2, 3).
- 10 7. Method according to any one of the preceding claims, characterized in that the energy beam (1) is realized as a laser beam.
- 15 8. Method according to any one of the preceding claims, characterized in that the energy beam (1) is realized as an electron beam.
- 20 9. Method according to any one of the preceding claims, characterized in that the energy beam (1) is realized as an induction field.
- 25 10. Device for carrying out a method according to any one of the preceding claims, characterized in that a flux cored wire (14) is provided for feeding the auxiliary materials (13) and/or the fibers (12).
- 30 11. Device according to claim 10, characterized in that the flux cored wire (14) comprises an outer sheath (10), wherein the material of the outer sheath (10) itself can include one or more auxiliary materials (13), and the outer sheath (10) encloses an interior (9), wherein auxiliary materials (13) and/or fibers (12) and/or particles are provided in the interior (9).

12. Device according to claim 10 or 11, characterized in that a gas stream (11) is provided in the interior (9) of the flux cored wire (14), which is preferably used to provide a protective gas and/or reactant gas (15) for the repair method.