

ABSTRACT

Provided is a pressure-sensitive adhesive sheet that is not to be photocured after bonding to an adherend, and can achieve both level difference followability and dimensional stability. The pressure-sensitive adhesive sheet (5) is composed of a pressure sensitive adhesive that contains a base polymer having a crosslinked structure and is formed into a sheet shape, and has a shear storage elastic modulus of 0.16 MPa or more at a temperature of 25°C, and a loss tangent of 0.25 or more at a temperature of 70°C. A glass transition temperature of the pressure sensitive adhesive sheet is preferably -3°C or lower. A gel fraction of the pressure sensitive adhesive is preferably 30 to 80%, and a polymerization ratio (nonvolatile content) of the pressure sensitive adhesive is preferably 95% or ore.

Figure 1