

ABRASIVE ARTICLE AND METHOD OF FORMING

TECHNICAL FIELD

The following is directed to methods of forming abrasive articles, and particularly, single-layered abrasive articles.

5 BACKGROUND ART

A variety of abrasive tools have been developed over the past century for various industries for the general function of removing material from a workpiece, including for example, sawing, drilling, polishing, cleaning, carving, and grinding. In particular reference to the electronics industry, abrasive tools suitable for slicing
10 single crystal ingots of material to form wafers is particularly pertinent. As the industry continues to mature, the ingots have increasingly larger diameters, and it has become acceptable to use loose abrasives and wire saws for such works due to yield, productivity, affected layers, dimensional constraints and other factors.

Generally, wire saws are abrasive tools that include abrasive particles attached
15 to a long length of wire that can be spooled at high speeds to produce a cutting action. While circular saws are limited to a cutting depth of less than the radius of the blade, wire saws can have greater flexibility allowing for cutting of straight or profiled cutting paths.

Various approaches have been taken in conventional fixed abrasive wire saws,
20 such as producing these articles by sliding steel beads over a metal wire or cable, wherein the beads are separated by spacers. These beads may be covered by abrasive particles which are commonly attached by either electroplating or sintering. However, electroplating and sintering operations can be time consuming and thus costly ventures, prohibiting rapid production of the wire saw abrasive tool. Most of
25 these wire saws have been used in applications, where kerf loss is not so dominating as in electronics applications, often to cut stone or marble. Some attempts have been made to attach abrasive particles via chemical bonding processes, such as brazing, but such fabrication methods reduce the tensile strength of the wire saw, and the wire saw

becomes susceptible to breaking and premature failure during cutting applications under high tension. Other wire saws may use a resin to bind the abrasives to the wire. Unfortunately, the resin bonded wire saws tend to wear quickly and the abrasives are lost well before the useful life of the particles is realized, especially when cutting
5 through hard materials.

Accordingly, the industry continues to need improved abrasive tools, particularly in the realm of wire sawing.

SUMMARY

According to one aspect, an abrasive article includes a substrate, a tacking
10 film overlying the substrate, abrasive particles comprising a coating layer overlying the abrasive particle bonded to the tacking film, wherein a bond between the coating layer and the tacking film defines a metallic bonding region, and a bonding layer overlying the abrasive particles and the tacking film.

According to another aspect, an abrasive article includes a substrate
15 comprising an elongated body having an aspect ratio of length:width of at least about 10:1, a tacking film overlying the substrate comprising a solder material having a melting point of not greater than about 450°C, abrasive particles bonded to the tacking film, and a bonding layer overlying the abrasive particles and tacking film.

In yet another aspect, a method of forming an abrasive article includes
20 providing a substrate, forming a tacking film overlying a surface of the substrate, the tacking film comprising a solder material, placing abrasive particles comprising a coating layer on the tacking film, and treating the tacking film to bind the coating layer and the tacking film to each other. The method further includes forming a bonding layer over the tacking film and the abrasive particles.

25 According to still another aspect, a method of forming an abrasive article includes providing a substrate comprising an elongated body having an aspect ratio of length:width of at least about 10:1, forming a tacking film comprising a metal overlying a surface of the substrate, the tacking film having melting point of not

greater than about 450°C, placing abrasive particles in the tacking film, and forming a bonding layer over the tacking film and the abrasive particles.

Another aspect includes a method of forming an abrasive article including providing a substrate comprising a wire, forming a tacking film comprising a metal material overlying a surface of the substrate, placing abrasive particles in the tacking film, treating the tacking film to form a metallic bonding region between the abrasive particles and the tacking film, and forming a bonding layer over the tacking film and the abrasive particles

BRIEF DESCRIPTION OF THE DRAWINGS

The present disclosure may be better understood, and its numerous features and advantages made apparent to those skilled in the art by referencing the accompanying drawings.

FIG. 1 includes a flow chart providing a process for forming an abrasive article in accordance with an embodiment.

FIG. 2 includes a cross-sectional illustration of a portion of an abrasive article in accordance with an embodiment.

FIG. 3 includes a magnified image of an abrasive article formed according to an embodiment.

FIG. 4 includes a magnified image of an abrasive article formed according to another embodiment.

FIG. 5 includes a magnified image of an abrasive article formed according to another embodiment.

FIG. 6 includes a magnified image of an abrasive article formed according to yet another embodiment.

FIG. 7 includes a magnified image of an abrasive article formed according to still another embodiment.

FIG. 8 includes a magnified image of an abrasive article formed according to another embodiment.

The use of the same reference symbols in different drawings indicates similar or identical items.

5 DETAILED DESCRIPTION

The following is directed to abrasive articles, and particularly abrasive articles suitable for abrading and sawing through workpieces. In particular instances, the abrasive articles herein can form wire saws, which may be used in processing of sensitive, crystalline materials in the electronics industry, optics industry, and other
10 associated industries.

FIG. 1 includes a flow chart providing a process of forming an abrasive article in accordance with an embodiment. The process can be initiated at step 101 by providing a substrate. The substrate can provide a surface for affixing abrasive materials thereto, thus facilitating the abrasive capabilities of the abrasive article.

15 In accordance with an embodiment, the process of providing a substrate can include a process of providing a substrate in the form of a wire. In fact, the wire substrate may be connected to a spooling mechanism. For example, the wire can be fed between a feed spool and a receiving spool. The translation of the wire between the feed spool and the receiving spool can facilitate processing, wherein the wire is
20 translated through desired forming processes to form the component layers of the finally-formed abrasive article while being translated from the feed spool to the receiving spool.

In accordance with an embodiment, the substrate can be an elongated member having an aspect ratio of length:width of at least 10:1. In other embodiments the
25 substrate can have an aspect ratio of at least about 100:1, such as at least 1000:1, or even at least about 10,000:1. The length of the substrate is the longest dimension measured along a longitudinal axis of the substrate. The width is a second longest (or in some cases smallest) dimension of the substrate measured perpendicular to the longitudinal axis.

Furthermore, the substrate in the form of elongated member can have a length of at least about 50 meters. In fact, other substrates can be longer, having an average length of at least about 100 meters, such as at least about 500 meters, at least about 1,000 meters, or even 10,000 meters.

5 Furthermore, the substrate can have a width that may not be greater than about 1 cm. In fact, the substrate can be an elongated member having an average width of not greater than about 0.5 cm, such as not greater than about 1 mm, not greater than about 0.8 mm, or even not greater than about 0.5 mm. Still, the substrate can have an average width of at least about 0.01 mm, such as at least about 0.03 mm. It will be
10 appreciated that the substrate can have an average width within a range between any of the minimum and maximum values noted above. Moreover, in the case that a substrate is a wire having a generally circular cross-sectional shape, it will be appreciated that reference to width is reference to a diameter.

In accordance with an embodiment, the substrate can include an inorganic
15 material, such as a metal or metal alloy material. Some substrates can include a transition metal element as recognized in the Periodic Table of Elements. For example, the substrate may incorporate elements of iron, nickel, cobalt, copper, chromium, molybdenum, vanadium, tantalum, tungsten, and the like. In accordance with a particular embodiment, the substrate can include iron, and more particularly
20 maybe steel.

In certain embodiments, the substrate can be an elongated member, such as a wire, that may include a plurality of filaments braided together. That is, the substrate can be formed of many smaller wires wound around each other, braided together, or fixed to another object, such as a central core wire. Certain designs may utilize piano
25 wire as a suitable structure for the substrate.

In further reference to the process of providing a substrate, it will be appreciated that the substrate can be spooled from a feed spool to a receiving spool at a particular rate to facilitate processing. For example, the substrate can be spooled at a rate of not less than about 5 m/min from the feed spool to the receiving spool. In
30 other embodiments, the rate of spooling can be greater, such that it is at least about 8 m/min, at least about 10 m/min, at least about 12 m/min, or even at least about 14

m/min. In particular instances, the spooling rate may be not greater than about 200 m/min, such as not greater than about 100 m/min. The rate of spooling can be within a range between any of the minimum and maximum values noted above. It will be appreciated the spooling rate can represent the rate at which the finally-formed
5 abrasive article can be formed.

After providing a substrate at step 101, the process can continue at step 102 by forming a tacking film overlying a surface of the substrate. The process of forming a tacking film can include a deposition process, including for example, spraying, printing, dipping, die coating, plating, electroplating and a combination thereof. The
10 tacking film can be bonded directly to the external surface of the substrate. In fact, the tacking film can be formed such that it overlies a majority of the external surface of the substrate, and more particularly, can overlie essentially the entire external surface of the substrate.

The tacking film may be formed such that it is bonded to the substrate in a
15 manner that it defines a bonding region. The bonding region can be defined by an interdiffusion of elements between the tacking film and the substrate. It will be appreciated that formation of the bonding region may not necessarily be formed at the moment when the tacking film is deposited on the surface of the substrate. For example, the formation of a bonding region between the tacking film and the substrate
20 may be formed at a later time during processing, such as during a heat treatment process to facilitate bonding between the substrate and other component layers formed on the substrate.

In accordance with an embodiment, the tacking film can be formed from a metal, metal alloy, metal matrix composite, and a combination thereof. In one
25 particular embodiment, the tacking film can be formed of a material including a transition metal element. For example, the tacking film can be a metal alloy including a transition metal element. Some suitable transition metal elements can include, for example, lead, silver, copper, zinc, tin, titanium, molybdenum, chromium, iron, manganese, cobalt, niobium, tantalum, tungsten, palladium, platinum, gold,
30 ruthenium, and a combination thereof. According to one particular embodiment, the tacking film can be made of a metal alloy including tin and lead, such as a 60/40 tin/lead composition. In another embodiment the tacking film can be made of a

material having a majority content of tin. In fact, in certain abrasive articles, the tacking film comprises a material consisting essentially of tin.

The tin can have a purity of at least about 99%. Further, the tin can have a purity of at least about 99.1%, at least about 99.2%, at least about 99.3%, at least
5 about 99.4%, at least about 99.5%, at least about 99.6%, at least about 99.7%, at least about 99.8%, or at least about 99.9%. In another aspect, the tin can have a purity of at least about 100%.

In accordance with an embodiment, the tacking film can be a solder material. It will be appreciated that a solder material includes a material having a particular
10 melting point, such as not greater than about 450°C. Solder materials are distinct from braze materials in that the braze materials generally have significantly higher melting points than solder materials, such as greater than 450°C, and more typically, greater than 500°C. Furthermore, brazing materials may have different compositions. Still, in accordance with an embodiment, the tacking film of the embodiments herein
15 may be formed of a material having a melting point of not greater than about 400°C, such as not greater than about 375°C, not greater than about 350°C, not greater than about 300°C, or not greater than about 250°C. Still, the tacking film may have a melting point of at least about 100°C, such as at least about 125°C, at least about 150°C, or even at least about 175°C. It will be appreciated that the tacking film can
20 have a melting point within a range between any of the minimum and maximum temperatures noted above.

Formation of the tacking film can include formation of additional layers overlying the tacking film. For example, in one embodiment, the formation of the tacking film includes formation of an additional layer overlying the tacking film to
25 facilitate further processing. The overlying film can be a flux material, which facilitates melting of the material of the tacking film and further facilitates attachment of abrasive particles on the tacking film. The flux material can be in the form of a generally uniform layer overlying the tacking film, and more particularly in direct contact with the tacking film. The flux material can be in the form of a liquid or
30 paste. According to one embodiment, the flux material can be applied to the tacking film using a deposition process such as spraying, dipping, painting, printing, brushing, and a combination thereof.

The additional layer in the form of a flux material can comprise a majority content of flux material. In certain instances, essentially all of the additional layer can consist of the flux material.

After forming the tacking film at step 102, the process can continue at step 5 103 by placing the abrasive particles on the tacking film. In some instances, depending upon the nature of the process, the abrasive particles can be in direct contact with the tacking film. More particularly, the abrasive particles can be in direct contact with an additional layer, such as a layer comprising a flux material, overlying the tacking film. In fact, the additional layer of material comprising the flux material 10 can have a natural viscosity and adhesive characteristic that facilitates holding the abrasive particles in place during processing, until further processes are conducted to permanently bond the abrasive particles in place relative to the tacking film.

Suitable methods of providing the abrasive particles on the tacking film, and more particularly, on the additional layer comprising the flux material, can include 15 spraying, gravity coating, dipping, die coating, electrostatic coating, and a combination thereof. Particularly useful methods of applying the abrasive particles can include a spraying process, conducted to apply an substantially uniform coating of abrasive particles onto the additional layer comprising the flux material.

In an alternative embodiment, the process of providing the abrasive particles 20 can include the formation of a mixture comprising a flux material and the abrasive particles. The mixture can be formed and deposited directly on the tacking film, as opposed to utilizing a two-step process of first coating with a tacking film and then applying the abrasive particles. Mixing the abrasive particles with the flux and then applying that mixture to the wire can allow relatively high concentrations of single 25 layers of abrasive particles per unit of wire to be achieved. For example, a wire saw having up to and including 600 abrasive particles per millimeter of wire can be made using this process. The abrasive particles can be disposed on the wire in substantially a single layer with agglomeration of abrasive particles or multiple layers of abrasive particles.

30 The abrasive particles can include materials such as oxides, carbides, nitrides, borides, oxynitrides, oxyborides, diamond, and a combination thereof. In certain

embodiments, the abrasive particles can incorporate a superabrasive material. For example, one suitable superabrasive material includes diamond. In particular instances, the abrasive particles can consist essentially of diamond.

In one embodiment, the abrasive particles can include a material having a
5 Vickers hardness of at least about 10 GPa. In other instances, the abrasive particles
can have a Vickers hardness of at least about 25 GPa, such as at least about 30 GPa, at
least about 40 GPa, at least about 50 GPa, or even at least about 75 GPa. Still,
abrasive particles for use in the embodiments herein can have a Vickers hardness that
is not greater than about 200 GPa, such as not greater than about 150 GPa, or even not
10 greater than about 100 GPa. It will be appreciated that the abrasive particles can have
a Vickers hardness within a range between any of the minimum and maximum values
noted above.

The abrasive particles can have an average particle size that is determined in
part by the desired end use of the abrasive article. In certain instances, the abrasive
15 particles can have an average size that is not greater than about 500 microns. In other
instances, the average particle size of the abrasive particles can be smaller, such that
the average particle size is not greater than about 300 microns, not greater than about
250 microns, not greater than about 200 microns, not greater than about 150 microns,
or even not greater than about 100 microns. In accordance with an embodiment, the
20 average particle size of the abrasive particles can be at least about 0.1 microns, such
as at least about 0.5 microns, or even at least about 1 micron. It will be appreciated
that the abrasive particles can have an average particle size within a range between
any of the minimum and maximum values noted above.

The abrasive particles may include a coating layer over the exterior surfaces of
25 the abrasive particles. Suitable coating layer materials can include metal or metal
alloy materials. In accordance with one particular embodiment, the coating layer can
include a transition metal element, such as titanium, vanadium, chromium,
molybdenum, iron, cobalt, nickel, copper, silver, zinc, manganese, tantalum, tungsten,
and a combination thereof. Certain coating layers can include nickel, such as a nickel
30 alloy, and even alloys have a majority content of nickel, as measured in weight
percent as compared to other species present within the coating layer composition. In

more particular instances, the coating layer can include a single metal species. For example, the coating layer can consist essentially of nickel.

The abrasive particles can be formed such that the coating layer can overlie at least about 50% of the exterior surface area of the abrasive particle. In other
5 embodiments, the coverage of the coating layer for each abrasive particle can be greater, such that the coating layer overlies at least about 75%, at least about 80%, at least about 90%, at least about 95%, or essentially the entire exterior surface of the abrasive particle.

After placing the abrasive particles on the tacking film at step 103, the process
10 can continue at step 104 by treating the tacking film to bind the abrasive particles in the tacking film. Treating may include processes such as heating, curing, drying, and a combination thereof. In one particular embodiment, treating includes a thermal process, such as heating the tacking film to a temperature sufficient to induce melting of the tacking film, while avoiding excessive temperatures to limit damage to the
15 abrasive particles and substrate. For example, treating can include heating the substrate, tacking film, and abrasive particles to a temperature of not greater than about 450°C. Notably, the process of treating can be conducted at a treating temperature that is less, such as not greater than about 375°C, not greater than about 350°C, not greater than about 300°C, or even not greater than about 250°C. In other
20 embodiments, the process of treating can include heating the tacking film to a melting point of at least about 100°C, at least about 150°C, or even at least about 175°C.

It will be appreciated that the heating process can facilitate melting of materials within the tacking film and additional layers comprising the flux material to bond the abrasive particles to the tacking film and the substrate. The heating process
25 can facilitate the formation of a particular bond between the abrasive particle and the tacking film. Notably, in the context of coated abrasive particles, a metallic bonding region can be formed between the coating material of the abrasive particles and the tacking film material. The metallic bonding region can be characterized by diffusion bond region having an interdiffusion between at least one chemical species of the
30 tacking film and at least one species of the coating layer overlying the abrasive particles, such that the metallic bonding region comprises a mixture of chemical species from the two component layers.

After treating the tacking film at step 104, the process can continue at step 105, by forming a bonding layer over the tacking film and abrasive particles. Formation of the bonding layer can facilitate formation of an abrasive article having improved wear resistance. Furthermore, the bonding layer can enhance abrasive particle retention for the abrasive article. In accordance with an embodiment, the process of forming the bonding layer can include deposition of the bonding layer on the external surface of the article defined by the abrasive particles and the tacking film. In fact, the bonding layer can be bonded directly to the abrasive particles and the tacking film.

The formation of the bonding layer can include processes such as plating, spraying, dipping, printing, and a combination thereof. In accordance with one particular embodiment, the bonding layer can be formed by a plating process. Notably, formation of the bonding layer can include a multi-step process wherein the substrate with tacked abrasive particles from step 104 can be first cleaned or rinsed prior to formation of the bonding layer to remove unwanted materials (e.g., residual flux material from the additional layer).

The bonding layer can be formed such that it overlies at least 90% of the exposed surfaces of the abrasive particles and tacking film. In other embodiments, the coverage of the bonding layer can be greater, such that it overlies at least about 92%, at least about 95%, or even at least about 97% of the exposed surfaces of the abrasive particles and tacking film. In one particular embodiment, the bonding layer can be formed such that it overlies essentially all the exposed surfaces of the abrasive particles and tacking film and completely covers the component layers and defines the exterior surface of the abrasive article.

The bonding layer can be made of a material such as an organic material, inorganic material, and a combination thereof. Some suitable organic materials can include polymers such as UV curable polymer, thermosets, thermoplastics, and a combination thereof. Some other suitable polymer materials can include urethanes, epoxies, polyimides, polyamides, acrylates, polyvinyls, and a combination thereof.

Suitable inorganic materials for use in the bonding layer can include metals, metal alloys, cermets, ceramics, composites, and a combination thereof. In one

particular instance, the bonding layer can be formed of a material having at least one transition metal element, and more particularly a metal alloy containing a transition metal element. Some suitable transition metal elements for use in the bonding layer can include lead, silver, copper, zinc, tin, titanium, molybdenum, chromium, iron,
5 manganese, cobalt, niobium, tantalum, tungsten, palladium, platinum, gold, ruthenium, and a combination thereof. In certain instances, the bonding layer can include nickel, and may be a metal alloy comprising nickel, or even a nickel-based alloy. In still other embodiments, the bonding layer can consist essentially of nickel.

In accordance with one embodiment, the bonding layer can be made of a
10 material, including for example composite materials, having a hardness that is greater than a hardness of the tacking film. For example, the bonding layer can have a Vickers hardness that is at least about 5% harder than a Vickers hardness of the tacking film. In fact, in other embodiments, the Vickers hardness of the bonding layer can be at least about 10%, such as at least about 20%, at least about 30%, at least
15 about 40%, at least about 50%, at least about 75%, or even at least about 100% harder as compared to a Vickers hardness of the tacking film.

Additionally, the bonding layer can have a fracture toughness (K1c) as measured by indentation methods, that is at least about 5% greater than an average fracture toughness of the tacking film. In particular embodiment, the bonding layer
20 can have a fracture toughness (K1c) that is at least about 8% greater, at least about 10% greater, at least about 15% greater, at least about 20% greater, at least about 25% greater, at least about 30% greater, or even at least about 40% greater than a fracture toughness of the tacking film.

Optionally, the bonding layer can include a filler material. The filler can be
25 various materials suitable for enhancing performance properties of the finally-formed abrasive article. Some suitable filler materials can include abrasive particles, pore-formers such as hollow sphere, glass spheres, bubble alumina, natural materials such as shells and/or fibers, metal particles, and a combination thereof.

In one particular embodiment, the bonding layer can include a filler in the
30 form of abrasive particles. The abrasive particles of the filler can be significantly different than the abrasive particles, particularly with regard to size, such that in

certain instances the abrasive grain filler can have an average grain size that is substantially less than the average size of the abrasive particles bonded to the tacking film. For example, the abrasive grain filler can have an average grain size that is at least about 2 times less than the average particle size of the abrasive particles. In fact, 5 the abrasive filler may have an average grain size that is even smaller, such as on the order of at least 3 times less, such as at least about 5 times less, at least about 10 times less, and particularly within a range between about 2 times and about 10 times less than the average particle size of the abrasive particles placed in the tacking film.

The abrasive grain filler within the bonding layer can be made from a material 10 such as carbides, carbon-based materials (e.g. fullerenes), borides, nitrides, oxides, oxynitrides, oxyborides, and a combination thereof. In particular instances, the abrasive grain filler can be a superabrasive material such as diamond, cubic boron nitride, or a combination thereof. It will be appreciated that the abrasive grain filler can be the same material as that of the abrasive particles bonded to the tacking film. 15 In other instances, the abrasive grain filler can include a different material than the material of the abrasive particles bonded to the tacking film.

FIG. 2 includes a cross-sectional illustration of a portion of an abrasive article in accordance with an embodiment. As illustrated, the abrasive article 200 can include a substrate 201, which is in the form of an elongated member such as a wire. 20 As further illustrated, the abrasive article can include a tacking film 202 disposed over the entire external surface of the substrate 201. Furthermore, the abrasive article 200 can include abrasive particles 203 including a coating layer 204 overlying the abrasive particles 203. The abrasive particles 203 can be bonded to the tacking film 202. In particular, the abrasive particles 203 can be bonded to the tacking film 202 at the 25 interface 206, wherein a metallic bonding region can be formed as described herein.

The abrasive article 200 can include a coating layer 204 overlying the external surfaces of the abrasive particles 203. Notably, the coating layer 204 can be in direct contact with the tacking film 202. As described herein, the abrasive particles 203, and more particularly, the coating layer 204 of the abrasive particles 203, can form a 30 metallic bonding region at the interface between the coating layer 204 and the tacking film 202.

According to one embodiment, the tacking film 202 can have a particular thickness as compared to the average particle size of the abrasive particles 203. For example, the tacking film 202 can have an average thickness that is not greater than about 80% of the average particle size of the abrasive particles 203. In other abrasive articles, the tacking film 202 can have an average thickness of not greater than about 70%, such as not greater than about 60%, not greater than about 50%, not greater than about 40%, or even not greater than about 30% of the average particle size of the abrasive particles 203. Still, in certain instances the average thickness of the tacking film 202 can be at least about 3%, such as at least about 5%, at least about 8%, or even at least about 10% of the average particle size of the abrasive particles 203. It will be appreciated that the tacking film 202 can have an average thickness within a range between any of the minimum and maximum percentages noted above.

In alternative terms, according to certain abrasive articles, the tacking film 202 can have an average thickness that is not greater than about 25 microns. In still other embodiments, the tacking film 202 can have an average thickness that is not greater than about 20 microns, such as not greater than about 15 microns, not greater than about 12 microns, or even not greater than about 10 microns. In accordance with an embodiment, the tacking film 202 can have an average thickness that is at least about 0.05 microns, such as at least about 0.1 microns, at least about 0.5 micron, or even at least about 1 microns. It will be appreciated that the tacking film 202 can have an average thickness within a range between any of the minimum and maximum values noted above.

In certain aspects, depending on the size of the abrasive particles, the thickness of the tacking film 202 can affect the performance of the abrasive article. For example, for a particular particle size, if the tacking film 202 is too thin, the abrasive particles may not bond to the substrate 201. Further, if the tacking film 202 is too thick, the abrasive particles become too deeply embedded within the tacking film 202 and after the coating layer 204 is deposited over the abrasive particles 203 and the tacking film 202, the abrasive particles 202 do not substantially protrude from the substrate 201.

For nickel coated abrasive particles having an average particle size within a range of about 10-20 microns, the thickness of the tacking film can be at least about 1

micron. Further, the thickness can be at least about 1.25 microns, or at least about 1.75 microns. The thickness can be limited, however, such that the thickness is not greater than about 3.0 microns, not greater than about 2.75 microns, not greater than 2.5 microns, not greater than 2.25 microns, or not greater than 2.0 microns. For
5 abrasive particles having an average particle size within a range of 10 and 20 microns, the tacking film 202 can have a thickness within a range between and including any of minimum and maximum thickness values noted above.

For nickel coated abrasive particles having an average particle size within a range of about 40-60 microns, the thickness of the tacking film can be at least about 1
10 micron. Further, the thickness can be at least about 1.25 microns, at least about 1.75 microns, at least about 2.0 microns, at least about 2.25 microns, at least about 2.5 microns, at least about 2.75 microns, or at least about 3.0 microns. The thickness can be limited, however, such that the thickness is not greater than about 5.0 microns, not greater than about 4.75 microns, not greater than 4.5 microns, not greater than 4.25
15 microns, not greater than 4.0 microns, not greater than 3.75 microns, not greater than 3.5 microns, not greater than 3.25 microns, or not greater than 3.0 microns. For abrasive particles having an average particle size within a range of 40 and 60 microns, the tacking film 202 can have a thickness within a range between and including any of minimum and maximum thickness values noted above.

20 As further illustrated, the bonding layer 205 can be directly overlying and directly bonded to the abrasive particles 203 and the tacking film 202. According to an embodiment, the bonding layer 205 can be formed to have a particular thickness. For example, the bonding layer 205 can have an average thickness of at least about 10% of the average particle size of the abrasive particles 203. In other embodiments,
25 the average thickness of the bonding layer 205 can be greater, such as at least about 20%, at least about 30%, at least about 40%, or even at least about 50%. Still, the average thickness of the bonding layer 205 can be limited, such that it is not greater than about 130%, such as not greater than about 110%, not greater than about 100%, not greater than about 95%, or even not greater than about 90% of the average particle
30 size of the abrasive particles 203. It will be appreciated that the bonding layer 205 can have an average thickness within a range between any of the minimum and maximum percentages noted above.

In more particular terms, the bonding layer 205 can be formed to have an average thickness that is at least 2 microns. For other abrasive articles, the bonding layer 205 can have a greater average thickness, such as at least about 5 microns, at least about 10 microns, at least about 15 microns, or even at least about 20 microns.

5 Particular abrasive articles can have a bonding layer 205 having an average thickness that is not greater than about 100 microns, such as not greater than about 90 microns, not greater than about 80 microns, or not greater than about 70 microns. It will be appreciated that the bonding layer 205 can have an average thickness within a range between any of the minimum and maximum values noted above.

10 In a particular aspect, the abrasive article can include an abrasive grain concentration of at least about 60 particles per mm of wire. Further, the abrasive grain concentration can be at least about 100 particles per mm of wire, at least about 150 particles per mm of wire, at least about 200 particles per mm of wire, at least about 250 particles per mm of wire, or at least about 300 particles per mm of wire. In
15 another aspect, the abrasive grain concentration may be no greater than about 750 particles per mm of wire, no greater than about 700 particles per mm of wire, no greater than about 650 particles per mm of wire, or no greater than about 600 particles per mm of wire. In another aspect, the abrasive particle concentration can be within a range between and including any of these abrasive concentration values.

20 In another aspect, the abrasive article can include an abrasive grain concentration of at least about 0.5 carats of diamond per meter of wire. Further, the abrasive grain concentration can be at least about 1.0 carats per meter of wire, at least about 1.5 carats per meter of wire, at least about 2.0 carats per meter of wire, at least about 3.0 carats per meter of wire, at least about 4.0 carats per meter of wire, or at
25 least about 5.0 carats per meter of wire. The concentration, however, may be limited. For example, the concentration may not be greater than 15.0 carats per meter of wire, not greater than 14.0 carats per meter, not greater than 13.0 carats per meter, not greater than 12.0 carats per meter, not greater than 11.0 carats per meter, or not greater than 10.0 carats per meter. The concentration can be within a range between
30 and including any of these minimum and maximum abrasive concentration values.

EXAMPLE 1:

A length of high strength carbon steel wire is obtained as a substrate. The high strength carbon steel wire has an average diameter of approximately 125 microns. A tacking film is formed on the external surface of the substrate via electroplating. The electroplating process forms a tacking film having an average
5 thickness of approximately 4 microns. The tacking film is formed of a 60/40 tin/lead soldering composition.

After forming the tacking film, the wire is spooled into a bath containing a liquid flux material commercially available as Stay Clean ® Liquid Soldering Flux from Harris Products Group and the treated wire is then sprayed with nickel-coated
10 diamond abrasive particles having an average particle size of between 20 to 30 microns. Thereafter, the substrate, tacking film, and abrasive particles are heat treated to a temperature to approximately 190°C. The abrasive pre-form is then cooled and rinsed. The process of bonding the nickel coated diamond to the tacking film is conducted at an average spooling rate of 15 m/min.

15 Thereafter, the abrasive pre-form is washed using 15% HCl followed by a rinse with de-ionized water. The rinsed article is electroplated with nickel to form a bonding layer directly contacting and overlying the abrasive particles and tacking film. FIG. 3 includes a magnified image of a portion of the abrasive article formed from the process of Example 1.

20 EXAMPLE 2

A length of high strength carbon steel wire is obtained as a substrate. The high strength carbon steel wire has an average diameter of approximately 125 microns. A tacking film is formed on the external surface of the substrate via electroplating. The electroplating process forms a tacking film having an average
25 thickness of approximately 6 microns. The tacking film is formed of a 60/40 tin/lead soldering composition.

After forming the tacking film, the wire is spooled into a bath containing a liquid flux material commercially available as Stay Clean ® Liquid Soldering Flux from Harris Products Group and the treated wire is then sprayed with nickel-coated
30 diamond abrasive particles having an average particle size of between 15 to 25

microns. Thereafter, the substrate, tacking film, and abrasive particles are heat treated to a temperature to approximately 190°C. The abrasive pre-form is then cooled and rinsed. The process of bonding the nickel coated diamond to the tacking film is conducted at an average spooling rate of 15 m/min.

5 Thereafter, the abrasive pre-form is washed using 15% HCl followed by a rinse with de-ionized water. The rinsed article is electroplated with nickel to form a bonding layer directly contacting and overlying the abrasive particles and tacking film. FIG. 4 illustrates the resulting article. As indicated in FIG. 4, the tin/lead tacking film 402 having a thickness of approximately 6 microns allows the Ni coated
10 diamond 404 to be relatively deeply embedded in the tacking film 402 on the wire 406. However, after the final layer of nickel 408 is electroplated onto the Ni coated diamond 404 and the tacking film 402, the Ni coated diamond 404 exhibits poor protrusion from the surface of the wire 406 and is not useful for cutting.

EXAMPLE 3

15 A length of high strength carbon steel wire is obtained as a substrate. The high strength carbon steel wire has an average diameter of approximately 120 microns. A tacking film is formed on the external surface of the substrate via electroplating. The electroplating process forms a tacking film having an average thickness of approximately 2 microns. The tacking film is formed of a high purity tin
20 soldering composition.

After forming the tacking film, the wire is spooled into a bath containing a liquid flux material commercially available as Stay Clean ® Liquid Soldering Flux from Harris Products Group and the treated wire is then sprayed with nickel-coated diamond abrasive particles having an average particle size of between 10 to 20
25 microns. Thereafter, the substrate, tacking film, and abrasive particles are heat treated to a temperature to approximately 250°C. The abrasive pre-form is then cooled and rinsed. The process of bonding the nickel coated diamond to the tacking film is conducted at an average spooling rate of 15 m/min.

Thereafter, the abrasive pre-form is washed using 15% HCl followed by a
30 rinse with de-ionized water. The rinsed article is electroplated with nickel to form a

bonding layer directly contacting and overlying the abrasive particles and tacking film.

EXAMPLE 4

5 A length of high strength carbon steel wire is obtained as a substrate. The high strength carbon steel wire has an average diameter of approximately 120 microns. A tacking film is formed on the external surface of the substrate via electroplating. The electroplating process forms a tacking film having an average thickness of approximately 2 microns. The tacking film is formed of a high purity tin
10 soldering composition.

 After forming the tacking film, the wire is spooled into a bath containing a liquid flux material commercially available as Stay Clean ® Liquid Soldering Flux from Harris Products Group and nickel-coated diamond abrasive particles having an average particle size of between 10 to 20 microns are mixed with the flux. Thereafter,
15 the substrate, tacking film, and abrasive particles are heat treated to a temperature to approximately 250°C. The abrasive pre-form is then cooled and rinsed. The process of bonding the nickel coated diamond to the tacking film is conducted at an average spooling rate of 15 m/min.

 Thereafter, the abrasive pre-form is washed using 15% HCl followed by a
20 rinse with de-ionized water. The rinsed article is electroplated with nickel to form a bonding layer directly contacting and overlying the abrasive particles and tacking film.

 By controlling the concentration of nickel-coated diamond abrasive particles within the flux, diamond concentrations on the wire are obtained with a range that
25 includes 60 particles per millimeter of wire and 600 particles per millimeter of wire. This corresponds to about 0.6 to 6.0 carats per meter of 120 micron steel wire. FIG. 5 depicts a wire 500 with a concentration of approximately 60 particles 502 per millimeter of wire and FIG. 6 depicts a wire 600 with a concentration of approximately 600 particles 602 per millimeter of wire. The particles 502, 602 on

each of these wires 500, 600 are arranged in substantially single layer without any agglomeration or stacking (i.e., multiple layers).

CUTTING TEST

5 Twelve 100 mm square bricks of silicon are provided as workpieces. 365 meters of wire produced in accordance with EXAMPLE 4 is provided. The wire includes an abrasive particle concentration of about 1.0 carats per meter of wire. The wire includes a wire tension of approximately 14 Newtons and operates at a speed of 9 meters per second. The cutting time is 120 minutes. The wire successfully cut
10 through the workpieces and produced 12 wafers with a single cut.

EDS ANALYSIS

An EDS analysis of the wire of EXAMPLE 4 shows no indication of intermetallic compounds formed on the wire. Referring to FIG. 7, the results of the EDS analysis shows the steel wire 702 and a layer of tin 704 is disposed on the steel
15 wire 702. Further, a layer of nickel is disposed on the tin 704. In FIG. 8, the results of the EDS analysis also indicates a nickel layer 802 is formed around the diamond 804 such that the diamond 804 is nearly completely coated with the nickel layer 802. Further, the nickel layer 802 forms an interface with the tin layer 806 that is deposited on the steel core 808.

20 EXAMPLE 5

A length of high strength carbon steel wire is obtained as a substrate. The high strength carbon steel wire has an average diameter of approximately 120 microns. A tacking film is formed on the external surface of the substrate via dip coating. The dip coating process forms a tacking film having an average thickness of
25 approximately 2 microns. The tacking film is formed of a high purity tin soldering composition.

After forming the tacking film, the wire is spooled into a bath containing a liquid flux material commercially available as Stay Clean ® Liquid Soldering Flux from Harris Products Group and the treated wire is then sprayed with nickel-coated

diamond abrasive particles having an average particle size of between 10 to 20 microns. Unfortunately, for reasons not quite understood, the abrasive particles do not adhere to the tacking film formed via dip coating and the remaining process steps are not performed.

- 5 Due to a lack of abrasive particles on the substrate, an abrasive article formed in a manner similar to EXAMPLE 5 would lack a usable amount of abrasive particles and the abrasive article would be untenable as an abrasive cutting tool.

 The above-disclosed subject matter is to be considered illustrative, and not restrictive, and the appended claims are intended to cover all such modifications, enhancements, and other embodiments, which fall within the true scope of the present
10 invention. Thus, to the maximum extent allowed by law, the scope of the present invention is to be determined by the broadest permissible interpretation of the following claims and their equivalents, and shall not be restricted or limited by the foregoing detailed description.

- 15 The Abstract of the Disclosure is provided to comply with Patent Law and is submitted with the understanding that it will not be used to interpret or limit the scope or meaning of the claims. In addition, in the foregoing Detailed Description of the Drawings, various features may be grouped together or described in a single embodiment for the purpose of streamlining the disclosure. This disclosure is not to
20 be interpreted as reflecting an intention that the claimed embodiments require more features than are expressly recited in each claim. Rather, as the following claims reflect, inventive subject matter may be directed to less than all features of any of the disclosed embodiments. Thus, the following claims are incorporated into the Detailed Description of the Drawings, with each claim standing on its own as defining
25 separately claimed subject matter.

WHAT IS CLAIMED IS:

1. An abrasive article comprising:

a substrate;

a tacking film overlying the substrate;

abrasive particles comprising a coating layer overlying the abrasive particles

bonded to the tacking film, wherein a bond between the coating layer

and the tacking film defines a metallic bonding region; and

a bonding layer overlying the abrasive particles and the tacking film.

2. An abrasive article comprising:

a substrate comprising an elongated body having an aspect ratio of

length:width of at least about 10:1;

a tacking film overlying the substrate comprising a solder material having a

melting point of not greater than about 450°C;

abrasive particles bonded to the tacking film; and

a bonding layer overlying the abrasive particles and tacking film.

3. An abrasive article for cutting a workpiece formed by a process comprising:

providing a wire substrate;

forming a tacking film comprising a metal material overlying a surface of the wire substrate;

placing abrasive particles in the tacking film;

treating the tacking film to form a metallic bonding region between the

abrasive particles and the tacking film; and

forming a bonding layer over the tacking film and the abrasive particles.

4. An abrasive article for cutting a workpiece formed by a process comprising:

providing a wire substrate;

forming a tacking film comprising a metal material overlying a surface of the wire substrate;

applying a flux material to the tacking film, wherein the flux material comprises abrasive particles mixed therein;
treating the tacking film to form a metallic bonding region between the abrasive particles and the tacking film; and
forming a bonding layer over the tacking film and the abrasive particles.

5. The abrasive article of any of claims 1, 2, 3, or 4, wherein the substrate comprises an inorganic material.
6. The abrasive article of claim 5, wherein the substrate comprises a material selected from the group of materials consisting of metals, metal alloys, and a combination thereof.
7. The abrasive article of claim 6, wherein the substrate comprises a metal comprising a transition metal element.
8. The abrasive article of claim 7, wherein the substrate comprises steel.
9. The abrasive article of any of claims 1, 2, 3, or 4, wherein the substrate comprises an elongated member having an aspect ratio of length:width of at least about 10:1, at least about 100:1, or at least about 10000:1.
10. The abrasive article of any of claims 1, 2, 3, or 4, wherein the substrate comprises an average length of at least about 50 m.
11. The abrasive article of claim 12, wherein the substrate comprises an average length of at least about 100 m, at least about 500 m, or at least about 1000 m.
12. The abrasive article of any of claims 1, 2, 3, or 4, wherein the substrate comprises an average width of not greater than about 1 cm.

13. The abrasive article of claim 12, wherein the substrate comprises an average width of not greater than about 1 mm, not greater than about 0.8 mm, not greater than about 0.5 mm. at least about 0.03 mm, or at least about 0.01 mm.

14. The abrasive article of any of claims 1, 2, 3, or 4, wherein the substrate comprises a wire.

15. The abrasive article of any of claims 1, 2, 3, or 4, wherein the substrate comprises a plurality of filaments braided together.

16. The abrasive article of any of claims 1, 2, 3, or 4, wherein the tacking film is in direct contact with a surface of the substrate.

17. The abrasive article of claim 16, wherein the tacking film is bonded directly to a surface of the substrate.

18. The abrasive article of any of claims 1, 2, 3, or 4, wherein the tacking film overlies a majority of an external surface of the substrate.

19. The abrasive article of claim 18, wherein the tacking film overlies essentially the entire external surface of the substrate

20. The abrasive article of any of claims 1, 2, 3, or 4, wherein the tacking film comprises a material selected from the group of materials consisting of metal, metal alloys, metal matrix composites, and a combination thereof.

21. The abrasive article of any of claims 1, 2, 3, or 4, wherein the tacking film comprises a transition metal element.

22. The abrasive article of claim 21, wherein the tacking film comprises an alloy of transition metal elements.

23. The abrasive article of claim 21, wherein the tacking film comprises a metal selected from the group of metals consisting of lead, silver, copper, zinc, tin, titanium, molybdenum, chromium, iron, manganese, cobalt, niobium, tantalum, tungsten, palladium, platinum, gold, ruthenium, and a combination thereof.

24. The abrasive article of claim 21, wherein the tacking film comprises a metal alloy of tin and lead.

25. The abrasive article of claim 21, wherein the tacking film comprises tin.

26. The abrasive article of claim 25, wherein the tacking film consists essentially of tin.

27. The abrasive article of any of claims 1, 2, 3, or 4, wherein the tacking film comprises a solder material.

28. The abrasive article of any of claims 1, 2, 3, or 4, wherein the tacking film has a melting point of not greater than about 450°C.

29. The abrasive article of any of claims 1, 2, 3, or 4, wherein the tacking film has a melting point of not greater than about 400°C.

30. The abrasive article of claim 29, wherein the tacking film has a melting point of not greater than about 375°C, not greater than about 350°C, not greater than about 300°C, or not greater than about 250°C.

31. The abrasive article of claim 28, wherein the tacking film comprises a material having melting point of at least about 100°C, at least about 125°C, or at least about 150°C.

32. The abrasive article of any of claims 1, 2, 3, or 4, wherein the tacking film comprises an average thickness of not greater than about 80% of an average particle size of the abrasive particles.

33. The abrasive article of claim 32, wherein the average thickness of the tacking film is not greater than about 70% of an average particle size of the abrasive particles, not greater than about 60% of an average particle size of the abrasive particles, not greater than about 50% of an average particle size of the abrasive particles, not greater than about 40% of an average particle size of the abrasive particles, or not greater than about 30% of an average particle size of the abrasive particles.

34. The abrasive article of any of claims 1, 2, 3, or 4, wherein the abrasive particles comprise a material selected from the group of materials consisting of oxides, carbides, nitrides, borides, oxynitrides, oxyborides, diamond, and a combination thereof.

35. The abrasive article of any of claims 1, 2, 3, or 4, wherein the abrasive particles comprise a superabrasive material.

36. The abrasive article of any of claims 1, 2, 3, or 4, wherein the abrasive particles comprise diamond.

37. The abrasive article of claim 36, wherein the abrasive particles consist essentially of diamond.

38. The abrasive article of any of claims 1, 2, 3, or 4, wherein the abrasive particles comprise a Vickers hardness of at least about 10 GPa.

39. The abrasive article of any of claims 1, 2, 3, or 4, wherein the abrasive particles comprise an average particle size of not greater than about 500 microns.

40. The abrasive article of claim 39, wherein the abrasive particles comprise an average particle size of not greater than about 300 microns, not greater than about 250 microns, not greater than about 200 microns, not greater than about 150 microns, or not greater than about 100 microns.

41. The abrasive article of claim 39, wherein the abrasive particles comprise an average particle size of at least about 0.1 microns, at least about 0.5 microns, or at least about 1 micron.

42. The abrasive article of any of claims 1, 2, 3, or 4, wherein the coating layer comprises a material selected from the group of materials consisting of metals, metal alloys, and a combination thereof.

43. The abrasive article of claim 42, wherein the coating layer comprises a transition metal element.

44. The abrasive article of claim 43, wherein the coating layer comprises a metal selected from the group of metals consisting of titanium, vanadium, chromium, molybdenum, iron, cobalt, nickel, copper, silver, zinc, manganese, tantalum, tungsten, and a combination thereof.

45. The abrasive article of claim 44, wherein the coating layer comprises a majority content of nickel.

46. The abrasive article of claim 45, wherein the coating layer consists essentially of nickel.

47. The abrasive article of claim 42, wherein the coating layer overlies at least about 50% of the exterior surface area of the abrasive particle, at least about 75% of the exterior surface area of the abrasive particle, or at least about 90% of the exterior surface area of the abrasive particle.

48. The abrasive article of claim 47, wherein the coating layer overlies essentially the entire exterior surface area of the abrasive particle.
49. The abrasive article of any of claims 1, 2, 3, or 4, wherein the metallic bonding region comprise a diffusion bond region characterized by a region of interdiffusion between at least one chemical species of the coating layer and one chemical species of the tacking film.
50. The abrasive article of any of claims 1, 2, 3, or 4, wherein the bonding layer is bonded directly to a coating layer overlying the abrasive particles.
51. The abrasive article of any of claims 1, 2, 3, or 4, wherein the bonding layer is bonded directly to a portion of the tacking film.
52. The abrasive article of any of claims 1, 2, 3, or 4, wherein the bonding layer overlies at least about 90% of the surfaces of the abrasive particles and tacking film.
53. The abrasive article of claim 52, wherein the bonding layer overlies essentially all of the surfaces of the abrasive particles and tacking film.
54. The abrasive article of any of claims 1, 2, 3, or 4, wherein the bonding layer comprises a material selected from the group of materials consisting of metals, metal alloys, cermets, ceramics, composites, and a combination thereof.
55. The abrasive article of claim 54, wherein the bonding layer comprises a transition metal element.
56. The abrasive article of claim 55, wherein the bonding layer comprises an alloy of transition metal elements.

57. The abrasive article of claim 54, wherein the bonding layer comprises a metal selected from the group of metals consisting of lead, silver, copper, zinc, tin, titanium, molybdenum, chromium, iron, manganese, cobalt, niobium, tantalum, tungsten, palladium, platinum, gold, ruthenium, and a combination thereof.

58. The abrasive article of claim 54, wherein the bonding layer comprises nickel.

59. The abrasive article of claim 58, wherein the bonding layer consists essentially of nickel.

60. The abrasive article of any of claims 1, 2, 3, or 4, wherein the bonding layer comprises an average thickness of at least about 10% of an average particle size of the abrasive particles.

61. The abrasive article of claim 60, wherein the bonding layer comprises an average thickness of at least about 20% of the average particle size of the abrasive particles, at least about 30% of the average particle size of the abrasive particles, at least about 40% of the average particle size of the abrasive particles, or at least about 50% of the average particle size of the abrasive particles.

62. The abrasive article of claim 60, wherein the bonding layer comprises an average thickness of not greater than about 130% of the average particle size of the abrasive particles, not greater than about 110% of the average particle size of the abrasive particles, not greater than about 100% of the average particle size of the abrasive particles, not greater than about 95% of the average particle size of the abrasive particles, or not greater than about 90% of the average particle size of the abrasive particles.

63. The abrasive article of any of claims 1, 2, 3, or 4, wherein the bonding layer comprise an average thickness of at least about 2 microns.

64. The abrasive article of claim 63, wherein the bonding layer comprise an average thickness of at least about 5 microns, at least about 10 microns, at least about 15 microns, or at least about 20 microns.

65. The abrasive article of claim 63, wherein the bonding layer comprise an average thickness of not greater than about 100 microns, not greater than about 90 microns, not greater than about 80 microns, or not greater than about 70 microns.

66. The abrasive article of any of claims 1, 2, 3, or 4, further comprising an abrasive grain concentration of at least about 60 particles per mm of wire.

67. The abrasive article of claim 66, wherein the abrasive grain concentration is at least about 100 particles per mm of wire, at least about 150 particles per mm of wire, at least about 200 particles per mm of wire, at least about 250 particles per mm of wire, or at least about 300 particles per mm of wire.

68. The abrasive article of claim 66, wherein the abrasive grain concentration is not greater than about 750 particles per mm of wire, not greater than about 700 particles per mm of wire, not greater than about 650 particles per mm of wire, or not greater than about 600 particles per mm of wire.

69. The abrasive article of any of claims 1, 2, 3, or 4, further comprising an abrasive grain concentration of at least about 0.5 carats of diamond per meter of wire.

70. The abrasive article of claim 69, further comprising an abrasive grain concentration of at least about 1.0 carats of diamond per meter of wire, at least about 1.5 carats of diamond per meter of wire, at least about 2.0 carats of diamond per meter of wire, at least about 3.0 carats of diamond per meter of

wire, at least about 4.0 carats of diamond per meter of wire, or at least about 5.0 carats of diamond per meter of wire.

71. The abrasive article of claim 69, further comprising an abrasive grain concentration of not greater than about 15.0 carats of diamond per meter of wire, not greater than about 14.0 carats of diamond per meter of wire, not greater than about 13.0 carats of diamond per meter of wire, not greater than about 12.0 carats of diamond per meter of wire, not greater than about 11.0 carats of diamond per meter of wire, or not greater than about 10.0 carats of diamond per meter of wire.

72. A method of forming an abrasive article comprising:
providing a substrate;
forming a tacking film overlying a surface of the substrate, the tacking film comprising a solder material;
placing abrasive particles comprising a coating layer on the tacking film;
treating the tacking film to bind the coating layer and the tacking film to each other; and
forming a bonding layer over the tacking film and the abrasive particles.

73. A method of forming an abrasive article comprising:
providing a substrate comprising an elongated body having an aspect ratio of length:width of at least about 10:1;
forming a tacking film comprising a metal overlying a surface of the substrate, the tacking film having melting point of not greater than about 450°C;
placing abrasive particles in the tacking film; and
forming a bonding layer over the tacking film and the abrasive particles.

74. A method of forming an abrasive article comprising:
providing a substrate comprising a wire;
forming a tacking film comprising a metal material overlying a surface of the substrate;
placing abrasive particles in the tacking film;

treating the tacking film to form a metallic bonding region between the abrasive particles and the tacking film; and forming a bonding layer over the tacking film and the abrasive particles.

75. The method of any of claims 72, 73, or 74, wherein providing a substrate comprises providing a wire connected to a feed spool and a receiving spool.

76. The method of claim 75, wherein providing a substrate comprises spooling the wire at a rate of not less than about 5 m/min from the feed spool to the receiving spool.

77. The method of any of claims 72, 73, or 74, wherein the substrate comprises an elongated body having an aspect ratio of length:width of at least about 10:1.

78. The method of any of claims 72, 73, or 74, wherein forming a tacking film comprises a method selected from the group consisting of deposition, spraying, printing, dipping, die coating, electroplating, and a combination thereof.

79. The method of any of claims 72, 73, or 74, wherein the tacking film is bonded directly to a surface of the substrate.

80. The method of any of claims 72, 73, or 74, wherein the tacking film is bonded to the substrate at a bonding region defined by interdiffusion of elements of the tacking film and the substrate.

81. The method of any of claims 72, 73, or 74, wherein the tacking film overlies a majority of an external surface of the substrate.

82. The method of claim 81, wherein the tacking film overlies essentially the entire external surface of the substrate.

83. The method of any of claims 72, 73, or 74, wherein the tacking film comprises a material selected from the group of materials consisting of metal, metal alloys, metal matrix composites, and a combination thereof.

84. The method of claim 83, wherein the tacking film comprises a transition metal element.

85. The method of claim 84, wherein the tacking film comprises a metal alloy of tin and lead.

86. The method of claim 84, wherein the tacking film comprises tin.

87. The method of any of claims 72, 73, or 74, wherein the tacking film has a melting point of not greater than about 450°C.

88. The method of claim 87, wherein the tacking film has a melting point of not greater than about 250°C.

89. The method of any of claims 72, 73, or 74, wherein the tacking film comprises an average thickness of not greater than about 80% of an average particle size of the abrasive particles.

90. The method of any of claims 72, 73, or 74, wherein the tacking film comprises an average thickness of not greater than about 25 microns.

91. The method of any of claims 72, 73, or 74, wherein placing the abrasive particles on the tacking film comprises placing the abrasive particles directly in contact with the tacking film to bind the abrasive particles to the tacking film.

92. The method of any of claims 72, 73, or 74, wherein placing the abrasive particles on the tacking film comprises a process selected from the

group consisting of spraying, gravity coating, dipping, die coating, electrostatic coating, and a combination thereof.

93. The method of any of claims 72, 73, or 74, wherein placing the abrasive particles on the tacking film can include placing the abrasive particles on an additional layer overlying the tacking film.

94. The method of claim 93, wherein placing an additional layer comprises a flux material.

95. The method of claim 93, wherein the additional layer is a coating overlying essentially all of the surface of the tacking film.

96. The method of claim 93, wherein the additional layer is formed through a deposition process.

97. The method of any of claims 72, 73, or 74, wherein treating comprises a process selected from the group consisting of heating, curing, drying, and a combination thereof.

98. The method of any of claims 72, 73, or 74, wherein treating comprises heating the tacking film to a temperature of not greater than about 450°C.

99. The method of any of claims 72, 73, or 74, wherein treating comprises heating the tacking film to melt the tacking film and form a metallic bonding region between the tacking film and the coating layer.

100. The method of any of claims 72, 73, or 74, wherein forming a bonding layer comprises a process of coating the bonding layer directly on the abrasive particles and the tacking film.

101. The method of any of claims 72, 73, or 74, wherein the process of forming the bonding layer comprises a process selected from the group of

processes including plating, spraying, printing, dipping, and a combination thereof.

102. The method of any of claims 72, 73, or 74, wherein the bonding layer comprises a material selected from the group of materials consisting of organic materials, inorganic materials, and a combination thereof.

103. The method of any of claims 72, 73, or 74, wherein the bonding layer comprises fillers.

104. The method of claim 103, wherein the fillers comprise secondary abrasive particles.