

CLAIMS

1. A method of fabricating a membrane comprising proteoliposomes having protein water channels, the method comprising:
5 providing a porous substrate;
depositing a solution on the porous substrate, wherein the solution comprises the proteoliposomes; and
contacting the porous substrate with an aqueous monomer solution and an organic monomer solution to form a selective layer on the porous substrate
10 embedding the proteoliposomes, wherein the solution is deposited prior to contacting the porous substrate with the aqueous monomer solution and the organic monomer solution.
2. The method of claim 1, wherein depositing the solution comprises moving the
15 porous substrate unidirectionally under a discharge module which deposits the solution on the porous substrate.
3. The method of claim 1 or 2, wherein the porous substrate is formed of a polymer comprising polyetherimide, cellulose ester, polyacrylonitrile, polysulfone,
20 polyethersulfone, polyvinylidene fluoride, cellulose acetate, or a derivative thereof.
4. The method of claim 1 or 2, wherein the porous substrate is formed of an inorganic material comprising carbon, titanium, aluminum oxide, or ceramic.
- 25 5. The method of any one of claims 1 to 4, wherein depositing the solution comprises spraying the solution to cover a surface of the porous substrate with the proteoliposomes.
6. The method of any one of claims 1 to 5, wherein the solution comprises the
30 proteoliposomes in a concentration ranging from 1 mg/ml to 100 mg/ml.

7. The method of any one of claims 1 to 6, wherein the solution further comprises a (i) surfactant and/or (ii) a salt, wherein the surfactant comprises n-octyl-P-D-glucoside, n-octanoylsucrose, n-nonanoylsucrose, n-decanoylsucrose, n-undecyl-P-D-glucopyranoside, n-undecyl-P-D-thioglucoside, n-undecyl- β -O-thiomaltoside, n-undecyl-P-D-thiomaltopyranoside, n-undecyl- β -O-thiogluco-
pyranoside, or a combination thereof, wherein the salt comprises sodium chloride, magnesium chloride, monosodium phosphate, or a combination thereof.
8. The method of claim 7, wherein the surfactant is present in the solution at a concentration ranging from 0.0002 wt% to 2 wt%.
9. The method of claim 7 or 8, wherein the salt is present in the solution at a concentration ranging from 0.001 M to 0.5 M.
10. The method of any one of claims 1 to 9, wherein contacting the porous substrate with the aqueous monomer solution and the organic monomer solution comprises soaking the porous substrate in the aqueous monomer solution prior to soaking the porous substrate in the organic monomer solution.
11. The method of any one of claims 1 to 10, wherein contacting the porous substrate with an aqueous monomer solution and an organic monomer solution comprises
- (i) dissolving a polyfunctional amine in an aqueous solution to form the aqueous monomer solution; and
 - (ii) dissolving a polyfunctional acyl chloride or a polyfunctional sulfonyl chloride in an organic solvent to form the organic monomer solution.
12. The method of claim 11, wherein the polyfunctional amine comprises o-phenylenediamine, m-phenylenediamine, or piperazine.

13. The method of claim 11 or 12, wherein the polyfunctional acyl chloride comprises trimesoyl chloride, isophthaloyl chloride (IPC), 5-isocyanato-isophthaloyl chloride (ICIC), or 5-chloroformyloxy-isophthaloyl chloride (CFIC).
- 5 14. The method of claim 11 or 12, wherein the polyfunctional sulfonyl chloride comprises 1,5-naphthalene-bisulfonyl chloride, 1,3-dimethyl 2-imidazolidinone, or 1,3-dioxo-1,3-dihydroisobenzofuran-5-sulfonyl chloride.
- 10 15. The method of any one of claims 1 to 14, further comprising drying the porous substrate having the solution deposited thereon before contacting the porous substrate with the aqueous monomer solution and the organic monomer solution.
16. A method of fabricating a membrane comprising proteoliposomes having protein water channels, the method comprising:
- 15 providing a porous substrate;
contacting the porous substrate with an aqueous monomer solution;
depositing a solution on the porous substrate, wherein the solution comprises the proteoliposomes; and
contacting the porous substrate with an organic monomer solution to form a
- 20 selective layer on the porous substrate embedding the proteoliposomes, wherein the solution is deposited after contacting the porous substrate with the aqueous monomer solution but prior to contacting the porous substrate with the organic monomer solution.
- 25 17. The method of claim 16, wherein depositing the solution comprises moving the porous substrate unidirectionally under a discharge module which deposits the solution on the porous substrate.
- 30 18. The method of claim 16 or 17, wherein the porous substrate is formed of a polymer comprising polyetherimide, cellulose ester, polyacrylonitrile, polysulfone, polyethersulfone, polyvinylidene fluoride, cellulose acetate, or a derivative thereof.

19. The method of claim 16 or 17, wherein the porous substrate is formed of an inorganic material comprising carbon, titanium, aluminum oxide, or ceramic.

20. The method of any one of claims 16 to 19, wherein depositing the solution
5 comprises spraying the solution to cover a surface of the porous substrate with the proteoliposomes.

21. The method of any one of claims 16 to 20, wherein the solution comprises the proteoliposomes in a concentration ranging from 1 mg/ml to 100 mg/ml.

10

22. The method of any one of claims 16 to 21, wherein the solution further comprises a (i) surfactant and/or (ii) a salt, wherein the surfactant comprises n-octyl-P-D-glucoside, n-octanoylsucrose, n-nonanoylsucrose, n-decanoylsucrose, n-undecyl-P-D-glucopyranoside, n-undecyl-P-D-thioglucoside, n-undecyl- β -O-thiomaltoside, n-
15 undecyl-P-D-thiomaltopyranoside, n-undecyl- β -O-thioglucopyranoside, or a combination thereof, wherein the salt comprises sodium chloride, magnesium chloride, monosodium phosphate, or a combination thereof.

23. The method of claim 22, wherein the surfactant is present in the solution at a
20 concentration ranging from 0.0002 wt% to 2 wt%.

24. The method of claim 22 or 23, wherein the salt is present in the solution at a concentration ranging from 0.001 M to 0.5 M.

25. The method of any one of claims 16 to 24, wherein contacting the porous
25 substrate with the aqueous monomer solution comprises dissolving a polyfunctional amine in an aqueous solution to form the aqueous monomer solution.

26. The method of claim 25, wherein the polyfunctional amine comprises o-
30 phenylenediamine, m-phenylenediamine, or piperazine.

27. The method of any one of claims 16 to 26, wherein contacting the porous substrate with the organic monomer solution comprises dissolving a polyfunctional acyl chloride or a polyfunctional sulfonyl chloride in an organic solvent to form the organic monomer solution.

5

28. The method of claim 27, wherein the polyfunctional acyl chloride comprises trimesoyl chloride, isophthaloyl chloride (IPC), 5-isocyanato-isophthaloyl chloride (ICIC), or 5-chloroformyloxy-isophthaloyl chloride (CFIC).

10 29. The method of claim 27, wherein the polyfunctional sulfonyl chloride comprises 1,5-naphthalene-bisulfonyl chloride, 1,3-dimethyl 2-imidazolidinone, or 1,3-dioxo-1,3-dihydroisobenzofuran-5-sulfonyl chloride.

15 30. The method of any one of claims 16 to 29, further comprising drying the porous substrate having the solution deposited thereon before contacting the porous substrate with the organic monomer solution.

31. A membrane comprising:
a porous substrate comprising proteoliposomes deposited thereon, wherein the
20 proteoliposomes have protein water channels incorporated therein; and
a selective layer formed on the porous substrate, wherein the proteoliposomes are embedded in the selective layer.

32. The membrane of claim 31, wherein the porous substrate is formed of a
25 polymer comprising polyetherimide, cellulose ester, polyacrylonitrile, polysulfone, polyethersulfone, polyvinylidene fluoride, cellulose acetate, or a derivative thereof.

33. The membrane of claim 31, wherein the porous substrate is formed of an inorganic material comprising carbon, titanium, aluminum oxide, or ceramic.

30

34. The membrane of any one of claims 31 to 33, wherein each of the proteoliposomes comprises a ratio of protein water channels to lipids ranging from 1:100 to 1:1000.

5 35. The membrane of any one of claims 31 to 34, wherein the proteoliposomes have an average diameter ranging from 50 nm to 400 nm.

36. The membrane of any one of claims 31 to 35, wherein the proteoliposomes deposited on the porous substrate are present in an amount ranging from 0.8 mg/m² to
10 1000 mg/m².

37. The membrane of any one of claims 31 to 36, wherein the protein water channels comprise aquaporins, aquaglyceroporins, ion channel proteins, or analogues thereof.

15

38. The membrane of any one of claims 31 to 37, wherein the selective layer has a thickness ranging from 50 nm to 1500 nm.

39. The membrane of any one of claims 31 to 38, wherein the selective layer
20 comprises a polyamide.

40. The membrane of any one of claims 31 to 39, wherein the membrane is a flat sheet membrane or a spiral wound membrane.

25 41. A system for fabricating a membrane comprising proteoliposomes having protein water channels, the system comprising:

a plurality of rollers operable to receive and move the porous substrate under a discharge module operable to deposit a solution on the porous substrate, wherein the solution comprises the proteoliposomes; and

30 a contact module operable to have the porous substrate contact an aqueous monomer solution and an organic monomer solution to form a selective layer on the porous substrate.

42. The system of claim 41, wherein the plurality of rollers are arranged to receive the porous substrate at a first position and a second position, wherein the first position and the second position are arranged away from the discharge module, and wherein
5 the plurality of rollers are operable to move the porous substrate under the discharge module from the first position to the second position.

43. The system of claim 41 or 42, wherein the discharge module comprises one or more nozzles arranged to have a surface of the porous substrate covered with the
10 proteoliposomes when the solution is sprayed from the one or more nozzles on the porous substrate moving under the discharge module.

44. The system of any one of claims 41 to 43, wherein the contact module is operable to have the porous substrate contact the aqueous monomer solution prior to
15 (i) contacting the organic monomer solution or (ii) contacting the solution.

45. The system of any one of claims 41 to 44, further comprising a casting module operable to form the porous substrate, wherein the casting module comprises a reservoir designed to contain a coagulation liquid which renders formation of the
20 porous substrate from a polymer solution.