

**SO₂ ADSORPTION MATERIAL, PREPARATION METHOD
THEREFOR AND APPLICATION THEREOF, AND METHOD
FOR REMOVING SO₂ FROM FLUE GAS CONTAINING SO₂**

CROSS REFERENCE TO RELATED APPLICATIONS

[0001] The present disclosure claims the rights and interests of the Chinese patent application number 201911048429.7, filed on October 31, 2019, which is herein specifically and entirely incorporated by reference.

FIELD

[0002] The present disclosure relates to the field of desulfurization, in particular to a SO₂ adsorption material, a method for preparing the SO₂ adsorption material, the SO₂ adsorption material prepared with the method, a use of the SO₂ adsorption material in the field of desulfurization, and a method for removing SO₂ from a flue gas containing SO₂.

BACKGROUND

[0003] Fossil fuels (e.g., coal, oil) contain a large amount of sulfur, and the direct combustion thereof leads to high levels of SO₂ in the flue gas. The excessive emission of SO₂ causes a number of environmental problems, the formation of acid rain and photochemical smog has brought

forth serious hazards to production and daily life of human being.

[0004] The most widely used methods for removing SO_2 at present can be categorized into the wet method desulfurization technology and the dry method desulfurization technology. Among them, the wet method desulfurization is mainly carried out by contacting an alkaline solution with the flue gas, converting SO_2 into the sulfite and sulfate through the chemical reactions and dissolving the sulfite and sulfate in water, and further treating the sulfate-containing solution thereby fulfilling the purpose of desulfurization. Among the industrially applied wet method desulfurization technologies, SO_2 in the flue gas can be absorbed by a sodium sulfite solution. In the dry method desulfurization technologies, SO_2 is separated from an exhaust gas by using the adsorption property of the porous materials, the SO_2 is adsorbed to a saturated state and then subjected to desorption and regeneration, or oxidization to SO_3 which is further subjected to elution. In the dry method flue gas desulfurization modes which are industrially and widely applied, SO_2 is removed by adsorption-oxidation-sulfation-alkaline washing process by using an activated carbon material as an adsorption oxidant.

[0005] The S-Zorb flue gas in the petroleum refining industry has a volume concentration of SO_2 large than 1%, given that the SO_2 content of the flue gas is relatively high, it is more suitable to adsorb SO_2 and prepare sulfur by desorbing and recycling the SO_2 , thereby performing

recycle and reuse of SO₂. However, a majority of the adsorption materials applied in the conventional desulfurization process has an oxidation property, which is prone to oxidize SO₂ to SO₃, thus the adsorption materials are not suitable for recycling and reusing the SO₂ in the S-Zorb flue gas through the adsorption-desorption process. In addition, the S-Zorb flue gas has a low content of O₂ (the volume concentration is typically less than 0.1%), thus the treatment mode of oxidizing SO₂ into SO₃ is not feasible. In addition, with respect to the S-Zorb flue gas containing water vapor, the existing adsorption material has a low physical adsorption capacity for SO₂, it cannot meet the requirement of practical use.

[0006] Therefore, it is of important and practical significance to provide a novel SO₂ adsorption material having a high physical adsorption capacity for SO₂.

SUMMARY

[0007] The present disclosure aims to overcome the defects of the prior art that the adsorption capacity of the SO₂ adsorption material is prone to attenuate and the physical adsorption capacity thereof is poor in the presence of water vapor.

[0008] The inventors of the present disclosure have discovered that although the metal organic framework (MOF) materials have an abundant

microporous structure and a high specific surface area, the materials comprise metal oxides with metal element as the central node, and the materials are prone to carry out chemical reactions while adsorbing SO₂, thus the materials have poor physical adsorption capacity for SO₂, which is not conducive to adsorption-desorption and recycle of SO₂. Although the carbonized metal organic framework material obtained after the carbonization process is capable of performing physical adsorption-desorption for SO₂, its SO₂ adsorption capacity will attenuate in the presence of water vapor, particularly for S-Zorb flue gas containing water vapor, thus the physical adsorption capacity is not desirable.

[0009] The inventors of the present disclosure have performed extensive inventive researches and found that a composite material obtained by loading sulfite (e.g., sodium sulfite) on a carbonized metal organic framework material can achieve high capacity physical adsorption of SO₂ through synergy between the sulfite and the carbonized metal organic framework material, overcoming the defect that the SO₂ adsorption capacity is vulnerable to attenuate in the presence of water vapor, and the produced adsorption material can be desorbed and regenerated for reuse, and exhibit excellent recycle performance, such that the present disclosure is accomplished based on the finding.

[0010] In order to fulfill the above purpose, a first aspect of the present disclosure provides a SO₂ adsorption material, wherein the SO₂

adsorption material comprises a carbonized metal organic framework material and a sulfite loaded on the carbonized metal organic framework material, the carbonized metal organic framework material is a carbonized material obtained by subjecting a metal organic framework material to a carbonization treatment;

[0011] The loading amount of sulfite is not higher than 10 wt%, on the basis of the total weight of the SO₂ adsorption material.

[0012] A second aspect of the present disclosure provides a method for preparing a SO₂ adsorption material, wherein the method comprises the following steps:

[0013] (1) subjecting the metal organic framework material to a carbonization treatment to remove at least a portion of the metal elements contained in the metal organic framework material, so as to obtain a carbonized metal organic framework material;

[0014] (2) loading sulfite on the carbonized metal organic framework material to prepare the SO₂ adsorption material;

[0015] said carbonized metal organic framework material and said sulfite are used in an amount such that the loading amount of sulfite is not higher than 10 wt%, on the basis of the total weight of the SO₂ adsorption material.

[0016] A third aspect of the present disclosure provides a SO₂ adsorption material prepared with the method of the second aspect.

[0017] A fourth aspect of the present disclosure provides an application of the SO₂ adsorption material of the first aspect or the third aspect in the field of desulfurization.

[0018] A fifth aspect of the present disclosure provides a method for removing SO₂ from a flue gas containing SO₂, wherein the method comprises the following steps:

[0019] Contacting the SO₂ adsorption material with the SO₂-containing flue gas to be treated for adsorption treatment, wherein said SO₂ adsorption material is the SO₂ adsorption material of the first aspect or the third aspect.

[0020] The present disclosure has at least the following advantages over the prior art:

[0021] (1) The SO₂ adsorption material provided by the present disclosure has an excellent SO₂ adsorption capacity, which is higher than that of the commercially available activated carbon and MOF materials under the same adsorption conditions within the penetration time.

[0022] (2) The SO₂ adsorption material provided by the present disclosure also exhibits excellent physical adsorption capability in the presence of water vapor, its adsorption capacity does not obviously attenuate in the presence of water vapor; in addition, the SO₂ adsorption material provided by the present disclosure can be recycled and reused through desorption and regeneration, and the SO₂ adsorption capacity still

remains at a relatively high level after multiple cycles of adsorption-desorption, thus the material has important significance for solving the problem of adsorbing and recycling SO₂ from the flue gas of the petroleum refining industry.

[0023] The other characteristics and advantages of the present disclosure will be specified in the following content of the detailed description of the preferred embodiments.

BRIEF DESCRIPTION OF THE DRAWINGS

[0024] FIG. 1 illustrates a diagram comparing the test results of 30 cycles of adsorption-desorption tests among the MOF-5, the SO₂ adsorption material L1 prepared in Example 1, and the SO₂ adsorption material D1 prepared in Comparative example 1.

DETAILED DESCRIPTION

[0025] The terminals and any value of the ranges disclosed herein are not limited to the precise ranges or values, such ranges or values shall be comprehended as comprising the values adjacent to the ranges or values. As for numerical ranges, the endpoint values of the various ranges, the endpoint values and the individual point value of the various ranges, and the individual point values may be combined with one another to produce one or more new numerical ranges, which should be deemed have been

specifically disclosed herein.

[0026] As previously mentioned, a first aspect of the present disclosure provides a SO₂ adsorption material, wherein the SO₂ adsorption material comprises a carbonized metal organic framework material and a sulfite loaded on the carbonized metal organic framework material, the carbonized metal organic framework material is a carbonized material obtained by subjecting a metal organic framework material to a carbonization treatment;

[0027] The loading amount of sulfite is not higher than 10 wt%, on the basis of the total weight of the SO₂ adsorption material.

[0028] In order to obtain a higher SO₂ adsorption capacity, it is preferable that the loading amount of sulfite is within a range of 2-7 wt%, on the basis of the total weight of the SO₂ adsorption material.

[0029] In the present disclosure, the metal organic framework material is an organic-inorganic hybrid material having an infinite topological regular pore structure, which is formed from an organic ligand and metal ions through coordination-bonding of the coordinate bonds.

[0030] According to the present disclosure, it is preferable that the metal organic framework material is a zinc-based metal organic framework material, the zinc-based metal organic framework material refers to that a metal element in the metal organic framework material is a zinc element.

[0031] Preferably, the metal organic framework material is at least one

selected from the group consisting of MOF-5, MOF-74, ZIF-8, ZIF-7 and ZIF-20 having a specific surface area of 800-1,800 m²/g and a pore volume of 0.8-1.2 cm³/g. Thus the cooperation of the resulting carbonized metal organic framework material with sulfites enables to obtain the more desired effect of physical adsorption-desorption of SO₂, facilitates adsorption and recycle of SO₂.

[0032] Preferably, the metal organic framework material is MOF-5 having a specific surface area within a range of 1,500-1,700 m²/g and a pore volume within a range of 1-1.15 cm³/g.

[0033] Preferably, the metal organic framework material contains a metal element in an amount of 20-35 wt%.

[0034] The present disclosure does not impose specific limitation in regard to the source of the metal organic framework material, which is commercially available, or may be obtained by a method of preparing the metal organic framework material in the prior art.

[0035] In the present disclosure, the carbonized metal organic framework material is a carbonized material obtained by subjecting a metal organic framework material to a carbonization treatment. The carbonization treatment process serves to reduce the content of the metal elements in the metal organic framework material, and increase the specific surface area and the pore volume of the material. The carbonized metal organic framework material obtained through the carbonization treatment

maintains the advantages of regular porous cage-like topological structure, large specific surface area, and advanced pore structure of the metal organic framework material.

[0036] For example, a MOF-5 material is a porous three-dimensional material with an infinite and regular topological structure formed by assembling of the metals Zn and terephthalic acid, the material has a porosity within a range of 70%-80%, the secondary structure units are cubic crystals having $a = 25.6690 \text{ \AA}$, $V = 16913.2 \text{ \AA}^3$, an inner diameter of $15.2 \text{ \AA}$, and a window size of $7.8 \text{ \AA}$. With respect to the MOF-5 having an average pore size of $1.45\text{-}1.5 \text{ nm}$, the regular porous cage-like topological structure and high porosity of MOF-5 are retained after the carbonization process, and the pore volume ratio for the different pore sizes is macropores (pore size larger than 50 nm): mesopores (pore size within a range of $2\text{-}50 \text{ nm}$): micropores (pore size smaller than 2 nm) = $1: (13\text{-}15): (5\text{-}6)$, and the porosity is within a range of 80%-85%.

[0037] In another example, ZIF-8 is a porous three-dimensional material formed by assembling Zn and dimethyl imidazole, the material has a topological structure of SOD configuration, an internal pore size of $11.6 \text{ \AA}$, a window of $3.4 \text{ \AA}$, and a porosity of 35-40%. In regard to the ZIF-8 having a mean pore size of $1.07\text{-}1.15 \text{ nm}$, the regular porous cage-like topological structure of ZIF-8 is retained after the carbonization process, the pore volume ratio for the different pore sizes is macropores (pore size

larger than 50nm): mesopores (pore size within a range of 2-50nm): micropores (pore size smaller than 2nm) =1: (2-3): (16-18), and the porosity is within a range of 50-55%.

[0038] Preferably, said carbonized metal organic framework material has a regular, porous and cage-like topological structure with a bulk density of 0.2-0.35 g/cm³, a specific surface area of 1,000-2,700 m²/g, a pore volume of 1-3.8 cm³/g, and (macropore volume + mesopore volume)/micropore volume =0.16-3.5.

[0039] More preferably, said carbonized metal organic framework material has a regular, porous and cage-like topological structure with a bulk density of 0.22-0.33 g/cm³, a specific surface area of 1,025-2,650 m²/g, a pore volume of 1.06-3.7 cm³/g, and (macropore volume + mesopore volume)/micropore volume =2.3-3.5.

[0040] In the present disclosure, the macropores refer to the pores with a pore diameter greater than 50nm, the mesopores refer to the pores with a pore diameter within a range of 2-50nm, and the micropores refer to the pores with a pore diameter less than 2 nm.

[0041] Preferably, the content of metal elements in the carbonized metal organic framework material is within a range of 0-0.06 wt%, preferably 0-0.02 wt%; more preferably, the carbonized metal organic framework material obtained after the carbonization treatment does not contain metal element, but the content of metal elements in the carbonized metal

organic framework material is lower than the lower limit of the analytical detection due to an inevitable measuring error.

[0042] In the present disclosure, the content of the metal element is determined through the Inductively Coupled Plasma (ICP) analytic test.

[0043] Preferably, the carbonization treatment is carried out in a protective atmosphere under a carbonization temperature of 900-1,150°C for a carbonization time of 5-10h.

[0044] Preferably, the SO₂ adsorption material has a bulk density of 0.2-0.39 g/cm³, a specific surface area of 1,000-2,700 m²/g, a pore volume of 1-3.7 cm³/g, and (macropore volume + mesopore volume)/micropore volume = 0.21-3.5.

[0045] More preferably, the SO₂ adsorption material has a bulk density of 0.21-0.35 g/cm³, a specific surface area of 2,000-2,650 m²/g, a pore volume of 2.8-3.7 cm³/g, preferably 2.86-3.62 cm³/g, and (macropore volume + mesopore volume)/micropore volume = 2.3-3.5.

[0046] Preferably, the content of metal element introduced by the carbonized metal organic framework material in the SO₂ adsorption material is 0-0.06 wt%, preferably 0-0.02 wt%, based on the weight of the carbonized metal organic framework material in the SO₂ adsorption material; more preferably, the SO₂ adsorption material does not contain metal element contained in the metal organic framework material (e.g., zinc element in zinc-based metal organic framework material), but the

content of metal element may be lower than the lower limit of analytical detection due to an inevitable measuring error.

[0047] In the present disclosure, the specific surface area, porosity, pore volume and pore volume distribution ratio of the materials are all determined by an analytic detection of the adsorption-desorption curve with the N₂ adsorption meter.

[0048] Preferably, the sulfite is sodium sulfite and/or potassium sulfite, since the inventors have found that the use of sodium sulfite and/or potassium sulfite loaded on the carbonized metal organic framework material, the synergy of sulfite and the carbonized metal organic framework material can produce a superior SO₂ physical adsorption effect, particularly in the presence of water vapor, the resultant adsorption material also exhibits superior adsorption effect.

[0049] The SO₂ adsorption material provided by the present disclosure can be recycled and reused after the desorption treatment, the present disclosure does not impose particular limitation on the conditions of desorption treatment, however, in order to enable the desorbed SO₂ adsorption material to retain a desired adsorption effect, it is preferable that the conditions of desorption treatment comprise: the desorption treatment is carried out at a temperature of 110-120°C under a nitrogen gas atmosphere.

[0050] The present disclosure provides a SO₂ adsorption material having

a higher SO₂ adsorption capacity, particularly in the presence of water vapor, the SO₂ adsorption material also can produce an excellent physical adsorption-desorption effect on the flue gas containing water vapor; the SO₂ adsorption capacity of the SO₂ adsorption material provided in the present disclosure is higher than that of the commercially available activated carbon and MOF materials under the same adsorption conditions within the penetration time; the SO₂ adsorption material provided by the present disclosure can be recycled and reused through desorption and regeneration, and the SO₂ adsorption capacity still remains at a relatively high level after multiple cycles of adsorption-desorption.

[0051] As previously mentioned, a second aspect of the present disclosure provides a method for preparing a SO₂ adsorption material, wherein the method comprises the following steps:

[0052] (1) subjecting the metal organic framework material to a carbonization treatment to remove at least a portion of the metal elements contained in the metal organic framework material, so as to obtain a carbonized metal organic framework material;

[0053] (2) loading sulfite on the carbonized metal organic framework material to prepare the SO₂ adsorption material;

[0054] said carbonized metal organic framework material and said sulfite are used in an amount such that the loading amount of sulfite is not higher than 10 wt%, on the basis of the total weight of the SO₂ adsorption

material.

[0055] In the method according to the second aspect of the present disclosure, in order to obtain a higher SO₂ adsorption capacity, it is preferable that the carbonized metal organic framework material and the sulfite are used in an amount such that the loading amount of sulfite in the SO₂ adsorption material is within a range of 1-7 wt%, on the basis of the total weight of the SO₂ adsorption material.

[0056] According to the present disclosure, it is preferable that varying loading amount of the sulfite is achieved by adjusting the concentration of the sulfite solution.

[0057] According to the method of the second aspect of the present disclosure, it is preferable that the carbonization treatment in step (1) is carried out in a protective atmosphere under a carbonization temperature of 900-1,150°C for a carbonization time of 5-10h. Under this condition, 99.94-100 wt% of the metal element in the metal organic framework material can be removed; more preferably, the carbonized metal organic framework material after the carbonization treatment does not contain metal element.

[0058] According to the method of the second aspect of the present disclosure, the carbonization treatment has the same function as that of the previously described first aspect, and the obtained properties of the carbonized metal organic framework material (e.g., the content of

metallic elements, the specific surface area, the pore volume) are correspondingly identical to those of the carbonized metal organic framework material described above in connection with the first aspect, and the content will not be repeated here.

[0059] According to the method of the second aspect of the present disclosure, it is preferable that the protective atmosphere is provided by at least one substance selected from the group consisting of nitrogen gas, argon gas, helium gas and neon gas.

[0060] According to a preferred embodiment of the present disclosure, the modes of loading sulfite on the carbonized metal organic framework material in step (2) comprise impregnating the carbonized metal organic framework material with a sulfite solution, and drying the impregnated carbonized metal organic framework material to remove the solvent.

[0061] Preferably, the sulfite solution has a mass concentration less than 6%, more preferably within a range of 1.2-4%; the inventors have discovered that a more desired loading effect can be obtained by loading the carbonized metal organic framework material with sulfite solution having a mass concentration within the range.

[0062] Preferably, the impregnation time is 1-5h.

[0063] In order to obtain a SO₂ adsorption material with better adsorptive properties, preferably the impregnation is an equal volume impregnation.

[0064] Preferably, the drying is carried out in an inert atmosphere, the

drying temperature is within a range of 100-120°C, and the drying time is within a range of 6-10h.

[0065] According to the disclosure, the inert atmosphere comprises nitrogen gas and an inert gas; the inert atmosphere is preferably provided by at least one substance selected from the group consisting of nitrogen gas, argon gas, helium gas and neon gas.

[0066] According to the method of the second aspect of the present disclosure, the sulfite is preferably sodium sulfite and/or potassium sulfite.

[0067] According to the method of the second aspect of the present disclosure, it is preferable that the metal organic framework material is selected from zinc-based metal organic framework materials.

[0068] According to the method of the second aspect of the present disclosure, it is more preferable that the metal-organic framework material is at least one selected from the group consisting of MOF-5, MOF-74, ZIF-8, ZIF-7 and ZIF-20 having a specific surface area of 800-1,800 m²/g and a pore volume of 0.8-1.2 cm³/g. Thus the cooperation of the resulting carbonized metal organic framework material with sulfites enables to obtain the more desired effect of physical adsorption-desorption of SO₂, facilitates adsorption and recycle of SO₂.

[0069] According to the method of the second aspect of the present disclosure, it is further preferred that the metal organic framework

material is MOF-5 having a specific surface area within a range of 1,500-1,700 m²/g and a pore volume within a range of 1-1.15 cm³/g.

[0070] The present disclosure provides a method for obtaining a SO₂ adsorption material having an excellent physical adsorption effect of SO₂ by loading sulfite on the carbonized metal organic framework material, and the operations of preparation method are simple, thus the method is of important significance for solving the problem of adsorbing and recycling SO₂ from the flue gas of the petroleum refining industry.

[0071] As previously mentioned, a third aspect of the disclosure provides a SO₂ adsorption material prepared with the method of the second aspect.

[0072] The SO₂ adsorption material prepared with the method of the present disclosure has a high SO₂ adsorption capacity, particularly in the presence of water vapor, and has an excellent SO₂ adsorption capacity for SO₂-containing flue gas including water vapor; the material exhibits a higher SO₂ adsorption capacity than the commercial activated carbon and the MOF materials under the same adsorption conditions within the penetration time; in addition, the SO₂ adsorption material provided by the present disclosure can be regenerated by heating and desorption, and the adsorption capacity still remains at a relatively high level after multiple cycles of adsorption-desorption.

[0073] As previously described, a fourth aspect of the present disclosure provides an application of the SO₂ adsorption material of the first aspect

or third aspect in the field of desulfurization.

[0074] The present disclosure does not impose special limitation to the particular operation of the application, the operation may be carried out by using the existing operation of removing SO₂ in the art, and those skilled in the art should not be construed as limitation in regard to the present disclosure.

[0075] As previously mentioned, a fifth aspect of the present disclosure provides a method for removing SO₂ from a flue gas containing SO₂, wherein the method comprises the following steps:

[0076] Contacting the SO₂ adsorption material with the SO₂-containing flue gas to be treated for adsorption treatment, wherein said SO₂ adsorption material is the SO₂ adsorption material of the first aspect or the third aspect.

[0077] In the fifth aspect of the disclosure, the SO₂ adsorption material has the same properties as the aforementioned SO₂ adsorption material, and the present disclosure will not repeatedly explain the properties of the SO₂ adsorption material, such as specific surface area and pore volume.

[0078] Preferably, the conditions of the adsorption treatment comprise an adsorption temperature within a range of 5-25°C, an adsorption volumetric hourly space velocity of 100-1,000h⁻¹, and an adsorption pressure within a range of 0-0.3MPa, more preferably 0.1-0.3MPa.

[0079] In the present disclosure, the adsorption volumetric hourly space

velocity refers to the amount (volume) of adsorbed gas (SO_2 -containing flue gas) passed per unit volume of adsorbent in a unit time.

[0080] Preferably, the SO_2 -containing flue gas to be treated has a volumetric content of SO_2 more than 1%, more preferably 1-5%; the water vapor has a volumetric content of 1-4%.

[0081] Preferably, the SO_2 -containing flue gas is the S-Zorb flue gas from the petrochemical refining industry.

[0082] The present disclosure provides a desulfurization method having high adsorption capacity for SO_2 in the flue gas by employing the SO_2 adsorption material of the present disclosure, which is effective for physically removing SO_2 in the flue gas, and can subject to cyclic adsorption and desorption, thus it is of significant importance in the adsorption and recycle of SO_2 from flue gas in the petroleum refining industry.

[0083] Unless otherwise specified in the present disclosure, the pressure refers to the gauge pressure, and the normal pressure is 0MPa.

[0084] The present disclosure will be described in detail with reference to examples.

[0085] In the following examples, the raw materials used were commercially available products unless otherwise specified.

[0086] The metal organic framework materials MOF-5, ZIF-8 and MOF-74 are all self-made according to the methods disclosed in the prior

literature (*Microporous Mesoporous mater.* 84 (2005) 97-104; *ACS Catal.* 2011, 1, 120-127; *J. Am. Chem. Soc.* 2005, 127, 5, 1504-1518).

[0087] In the following examples, the relevant properties were obtained by the following method:

[0088] (1) specific surface area, pore volume, and pore volume distribution ration of the material were determined by an analytic detection of the adsorption-desorption curve with the N₂ adsorption meter;

[0089] (2) the content of metal element was determined through the ICP analytic test;

[0090] (3) SO₂ content in the gas was measured by Emerson X-STREAM instrument analysis;

[0091] (4) measurement of the loading amount was obtained through conversion of the content of Na element in the adsorption material determined through the ICP analytic test.

[0092] (5) in the following example, the penetration time was set when the concentration of SO₂ at the adsorption outlet reached 50mg/ m³, and the SO₂ adsorption capacity was calculated based on the following

$$Q = \frac{\sum_{i=1}^n [q \times \int_0^t (C_0 - C_i) dt] \times 10^{-3}}{m}$$

formula:

[0093] wherein Q denoted sulfur capacity (SO₂ adsorption capacity), mg/g; q denoted total flow rate of the mixed gas at an inlet, L/min; C₀ denoted the SO₂ concentration at an inlet, mg/L; C_i denoted the SO₂

concentration at an outlet for the i^{th} sampling, mg/L; t denoted the i^{th} sampling time, min; n denoted the sampling number when adsorption reached saturation or a specified penetration time; m denoted the loading amount of said adsorption material, g;

[0094] (6) bulk density: calculated and obtained by measuring the volume per unit mass of adsorption material.

[0095] Example 1

[0096] The material MOF-5 having a specific surface area of $1,655 \text{ m}^2/\text{g}$ and a pore volume of $1.13 \text{ cm}^3/\text{g}$ and a Zn element content of 31.2 wt% was used as a matrix.

[0097] (1) The MOF-5 matrix was subjected to carbonizing at $1,000^\circ\text{C}$ for 6h in the presence of nitrogen gas, so as to obtain a carbonized metal organic framework material, having a bulk density of $0.22 \text{ g}/\text{cm}^3$, a specific surface area of $2,650 \text{ m}^2/\text{g}$, a pore volume of $3.7 \text{ cm}^3/\text{g}$, a content of Zn element being 0 wt%, and (macropore volume + mesopore volume)/micropore volume = 3.2.

[0098] (2) The carbonized metal organic framework material was placed in a sodium sulfite solution having a mass concentration of 3%, and subjected to an equivalent-volume impregnation for 1h, the impregnated material was subjected to drying under a nitrogen gas atmosphere at 120°C for 6h, so as to prepare the SO_2 adsorption material L1.

[00099] Upon measurement, the prepared SO₂ adsorption material L1 had a loading amount of sodium sulfite of 5 wt%, a bulk density of 0.231 g/cm³, a specific surface area of 2,426 m²/g, a pore volume of 3.27 cm³/g, (macropore volume + mesopore volume)/micropore volume =3.1, and a content of Zn element being 0 wt%.

[00100] Example 2

[00101] The SO₂ adsorption material was prepared with a similar manner as that in Example 1, except that in step (2), the carbonized metal organic framework material was placed in a sodium sulfite solution having a mass concentration of 1.2%, and subjected to an equivalent-volume impregnation, so as to prepare the SO₂ adsorption material L2.

[00102] Upon measurement, the prepared SO₂ adsorption material L2 had a loading amount of sodium sulfite of 1 wt%, a bulk density of 0.222 g/cm³, a specific surface area of 2,615 m²/g, a pore volume of 3.62 cm³/g, (macropore volume + mesopore volume)/micropore volume =3.2, and a content of Zn element being 0 wt%.

[00103] Example 3

[00104] The SO₂ adsorption material was prepared with a similar manner as that in Example 1, except that in step (2), the carbonized metal organic framework material was placed in a sodium sulfite solution having a mass concentration of 4%, and subjected to an

equivalent-volume impregnation, so as to prepare the SO₂ adsorption material L3.

[00105] Upon measurement, the prepared SO₂ adsorption material L3 had a loading amount of sodium sulfite of 7 wt%, a bulk density of 0.235 g/cm³, a specific surface area of 2,320 m²/g, a pore volume of 3.05 cm³/g, (macropore volume + mesopore volume)/micropore volume = 3.35, and a content of Zn element being 0 wt%.

[00106] Example 4

[00107] The SO₂ adsorption material was prepared with a similar manner as that in Example 1, except that in step (2), the carbonized metal organic framework material was placed in a sodium sulfite solution having a mass concentration of 5.8%, and subjected to an equivalent-volume impregnation, so as to prepare the SO₂ adsorption material L4;

[00108] Upon measurement, the prepared SO₂ adsorption material L4 had a loading amount of sodium sulfite of 10 wt%, a bulk density of 0.242 g/cm³, a specific surface area of 2,110 m²/g, a pore volume of 2.86 cm³/g, (macropore volume + mesopore volume)/micropore volume = 3.4, and a content of Zn element being 0 wt%.

[00109] Example 5

[00110] The material ZIF-8 having a specific surface area of 1,150 m²/g and a pore volume of 0.82 cm³/g and a Zn element content of 30.7

wt% was used as a matrix.

[00111] (1) The ZIF-8 matrix was subjected to carbonizing at 1,150°C for 5h in the presence of nitrogen gas, so as to obtain a carbonized metal organic framework material, the obtained carbonized metal organic framework material had a bulk density of 0.28 g/cm³, a specific surface area of 1,290 m²/g, a pore volume of 1.27 cm³/g, a content of Zn element being 0 wt%, and (macropore volume + mesopore volume)/micropore volume =0.25.

[00112] (2) The carbonized metal organic framework material was placed in a sodium sulfite solution having a mass concentration of 3%, and subjected to an equivalent-volume impregnation for 1h, the impregnated material was subjected to drying under a nitrogen gas atmosphere at 120°C for 6h, so as to prepare the SO₂ adsorption material L5.

[00113] Upon measurement, the prepared SO₂ adsorption material L5 had a loading amount of sodium sulfite of 5 wt%, a bulk density of 0.294 g/cm³, a specific surface area of 1,225 m²/g, a pore volume of 1.24 cm³/g, (macropore volume + mesopore volume)/micropore volume =0.255, and a content of Zn element being 0 wt%.

[00114] Example 6

[00115] The material MOF-74 having a specific surface area of 852 m²/g and a pore volume of 1.02 cm³/g and a Zn element content of 29.2

wt% was used as a matrix.

[00116] (1) The MOF-74 matrix was subjected to carbonizing at 900°C for 10h in the presence of nitrogen gas, so as to obtain a carbonized metal organic framework material, the obtained carbonized metal organic framework material had a bulk density of 0.33 g/cm³, a specific surface area of 1,080 m²/g, a pore volume of 1.06 cm³/g, a content of Zn element being 0 wt%, and (macropore volume + mesopore volume)/micropore volume =0.22.

[00117] (2) The carbonized metal organic framework material was placed in a sodium sulfite solution having a mass concentration of 3%, and subjected to an equivalent-volume impregnation for 1h, the impregnated material was subjected to drying under a nitrogen gas atmosphere at 120°C for 6h, so as to prepare the SO₂ adsorption material L6;

[00118] Upon measurement, the prepared SO₂ adsorption material L6 had a loading amount of sodium sulfite of 5 wt%, a bulk density of 0.346 g/cm³, a specific surface area of 1,025 m²/g, a pore volume of 1 cm³/g, (macropore volume + mesopore volume)/micropore volume =0.226, and a content of Zn element being 0 wt%.

[00119] Comparative example 1

[00120] The material MOF-5 having a specific surface area of 1,655 m²/g and a pore volume of 1.13 cm³/g and a Zn element content of 31.2

wt% was used as a matrix.

[00121] The MOF-5 matrix was subjected to carbonizing at 1,000°C for 6h in the presence of nitrogen gas, so as to obtain the SO₂ adsorption material D1.

[00122] Upon measurement, the prepared material D1 had a bulk density of 0.22 g/cm³, a specific surface area of 2,650 m²/g, a pore volume of 3.7 cm³/g, (macropore volume + mesopore volume)/micropore volume =3.2, and a content of Zn element being 0 wt%.

[00123] Comparative example 2

[00124] The commercially available activated carbon material (with a bulk density 0.62 g/cm³, a specific surface area of 865 m²/g, a pore volume of 0.52 cm³/g) was placed in a sodium sulfite solution having a mass concentration of 3%, and subjected to an equivalent-volume impregnation for 1h, the impregnated material was subjected to drying under a nitrogen gas atmosphere at 120°C for 6h, so as to prepare the SO₂ adsorption material D2.

[00125] Upon measurement, the prepared SO₂ adsorption material D2 had a loading amount of sodium sulfite of 5 wt%, a bulk density of 0.65 g/cm³, a specific surface area of 820 m²/g, a pore volume of 0.5 cm³/g, and (macropore volume + mesopore volume)/micropore volume =0.2.

[00126] Comparative example 3

[00127] The SO₂ adsorption material was prepared with a similar

manner as that in Example 1, except that in step (2), the carbonized metal organic framework material was placed in a sodium sulfite solution having a mass concentration of 6.5%, and subjected to an equivalent-volume impregnation, so as to prepare the SO₂ adsorption material D3.

[00128] Upon measurement, the prepared material D3 had a loading amount of sodium sulfite of 13.2 wt%, a bulk density of 0.25 g/cm³, a specific surface area of 1,245 m²/g, a pore volume of 1.08 cm³/g, (macropore volume + mesopore volume)/micropore volume = 3.55, and a content of Zn element being 0 wt%.

[00129] Comparative example 4

[00130] The material MOF-5 was directly placed in a sodium sulfite solution having a mass concentration of 3%, and subjected to an equivalent-volume impregnation for 1h without subjected to the carbonization treatment, but the material MOF-5 was structurally decomposed and collapsed after being placed in the sodium sulfite solution, an adsorption material cannot be prepared and the subsequent operation cannot be performed.

[00131] Test example 1

[00132] The adsorption properties of the SO₂ adsorption materials prepared in the Examples and Comparative Examples were tested respectively.

[00133] Wherein the SO₂-containing flue gas to be treated was the S-Zorb flue gas comprising water vapor, wherein the SO₂ content was 3% by volume and the water vapor content was 3% by volume.

[00134] The SO₂-containing flue gas to be treated as described above was subjected to adsorption treatment by using the SO₂ adsorption materials MOF-5, ZIF-8, MOF-74, activated carbon, and the SO₂ adsorption materials prepared in the Examples and Comparative Examples.

[00135] The conditions of the adsorption treatment included an adsorption temperature of 20°C, an adsorption volumetric hourly space velocity of 800h⁻¹, and an adsorption pressures were normal pressure and 0.2MPa respectively.

[00136] The penetration time was set when the concentration of SO₂ at the adsorption outlet reached 50mg/ m³, the specific measurement results were shown in Table 1.

[00137] Table 1: adsorption capacities of different SO₂ adsorption materials

Adsorption materials	Matrix (framework Material)	Loading amount/wt %	Adsorption capacity (mg/g)	
			Condition of normal pressure	0.2MPa
MOF-5	—	—	34	80
ZIF-8	—	—	33	77
MOF-74	—	—	31	72
Activated carbon	—	—	30	70
Example 1	MOF-5	5	70	195

Comparative example 1	MOF-5	—	51	145
Comparative example 2	Activated carbon	5	35	105
Example 2	MOF-5	1	55	150
Example 3	MOF-5	7	68	190
Example 4	MOF-5	10	60	160
Example 5	ZIF-8	5	50	145
Example 6	MOF-74	5	46	135
Comparative example 3	MOF-5	13.2	28	65
Comparative example 4	MOF-5	—	—	—

[00138] As can be seen from Table 1, the SO₂ adsorption materials provided by the present disclosure have high SO₂ adsorption capacity; and their SO₂ adsorption capacity is higher than that of the commercially available activated carbon and MOF materials under the same adsorption conditions within the penetration time; in particular, wherein a portion of the adsorption materials have the SO₂ adsorption capacity which is 2.3 times or more of the commercially available activated carbon, or 2 times or more of the MOF materials.

[00139] In particular, as illustrated by a comparison between the Examples 1-4 and the Comparative example 3, the SO₂ adsorption capacity is significantly decreased when the loading amount of sulfite exceeds 10 wt%; it is particularly preferred that the SO₂ adsorption material has a higher adsorption capacity when the loading amount of sulfite (e.g., sodium sulfite) is 2-7 wt%.

[00140] Test example 2

[00141] The adsorption properties of the SO₂ adsorption materials

prepared in the Examples and Comparative Examples under different pressure and temperature conditions were tested respectively.

[00142] Wherein the SO₂-containing flue gas to be treated was the S-Zorb flue gas comprising water vapor, wherein the SO₂ content was 2% by volume and the water vapor content was 4% by volume.

[00143] The conditions of the adsorption treatment comprised: an adsorption volumetric hourly space velocity of 1,000h⁻¹, and the adsorption temperatures and pressures were specifically illustrated in Table 2 below.

[00144] The penetration time was set when the concentration of SO₂ at the adsorption outlet reached 50 mg/m³. The present disclosure exemplarily provided the test results for the SO₂ adsorption materials prepared in Example 1 and Comparative example 2, the specific test results were shown in Table 2 and Table 3, respectively.

[00145] Table 2: SO₂ adsorption capacity for L1 under various temperatures and pressures

Material type	Temperature	Adsorption capacity (mg/g)			
		Normal pressure	0.1MPa	0.2MPa	0.3MPa
L1	5°C	75	130	205	265
	15°C	72	125	195	245
	25°C	70	123	192	238

[00146] Table 3: SO₂ adsorption capacity for D2 under various temperatures and pressures

Material type	Temperature	Adsorption capacity (mg/g)			
		Normal pressure	0.1MPa	0.2MPa	0.3MPa

D2	5°C	40	90	115	168
	15°C	38	85	110	152
	25°C	35	82	107	145

[00147] As can be seen from a comparison of the results in Table 2 and Table 3, the SO₂ adsorption materials provided by the present disclosure have a high SO₂ adsorption capacity.

[00148] Moreover, as illustrated in Table 2, the SO₂ adsorption capacity of the adsorption material provided by the present disclosure can be increased by 1.7-3.5 times under the conditions consisting of the same temperature and the pressurized condition, while the temperature within a range of 5-25°C under the same pressure condition does not impose an obvious influence on the SO₂ adsorption capacity of the adsorption material.

[00149] Test example 3

[00150] The cyclic adsorption-desorption properties of the adsorption materials prepared in the Examples and Comparative Examples were measured.

[00151] Wherein the SO₂-containing flue gas to be treated was the S-Zorb flue gas comprising water vapor, wherein the SO₂ content was 5% by volume and the water vapor content was 4% by volume.

[00152] The conditions of the adsorption treatment comprised: an adsorption temperature of 20°C, an adsorption volumetric hourly space velocity of 400h⁻¹, and an adsorption pressure of 0.2MPa.

[00153] The penetration time was set when the concentration of SO₂ at

the adsorption outlet reached 50 mg/m³.

[00154] The SO₂ adsorption materials followed the adsorption treatment were subjected to desorption treatment at 120°C under the nitrogen gas atmosphere, and 30 cycles of adsorption-desorption tests were carried out.

[00155] The present disclosure exemplarily provides test results of cyclic adsorption-desorption of the material MOF-5, the adsorption material L1 prepared in Example 1, and the adsorption material D1 prepared in Comparative example 1, the specific results were shown in FIG. 1.

[00156] As can be seen from FIG. 1, the SO₂ adsorption materials provided by the present disclosure have excellent SO₂ adsorption capacity, its adsorption capacity does not obviously attenuate in the presence of water vapor, and exhibits an excellent recycling performance, and the SO₂ adsorption capacity can maintain 85 wt.% or more of the initial adsorption capacity after 30 cycles of adsorption-desorption tests. In contrast, the SO₂ adsorption capacities of both the material MOF-5 and the adsorption material D1 prepared in Comparative example 1 are remarkably and significantly reduced during the cyclic tests.

[00157] To sum up, the SO₂ adsorption materials provided by the present disclosure have excellent SO₂ adsorption capacity, particularly under the condition of the flue gas containing water vapor, its adsorption

capacity does not obviously attenuate in the presence of water vapor, and exhibit desirable physical adsorption effect on the SO₂ in the flue gas containing water vapor; the SO₂ adsorption capacity is higher than that of the commercially available activated carbon and MOF materials under the same adsorption conditions within the penetration time; in addition, the SO₂ adsorption materials provided by the present disclosure can be regenerated by heating and desorption, and the adsorption capacity still remains at a relatively high level after multiple cycles of adsorption-desorption, for example, the SO₂ adsorption capacity can maintain 85 wt.% or more of the initial adsorption capacity after 30 cycles of adsorption-desorption tests, thus the SO₂ adsorption materials have a widespread application prospect.

[00158] The above content describes in detail the preferred embodiments of the present disclosure, but the present disclosure is not limited thereto. A variety of simple modifications can be made in regard to the technical solutions of the present disclosure within the scope of the technical concept of the present disclosure, including a combination of individual technical features in any other suitable manner, such simple modifications and combinations thereof shall also be regarded as the content disclosed by the present disclosure, each of them falls into the protection scope of the present disclosure.

Claims

1. A SO₂ adsorption material comprising a carbonized metal organic framework material and a sulfite loaded on the carbonized metal organic framework material, the carbonized metal organic framework material is a carbonized material obtained by subjecting a metal organic framework material to a carbonization treatment;
a loading amount of sulfite is not higher than 10 wt%, on the basis of a total weight of the SO₂ adsorption material.
2. The SO₂ adsorption material of claim 1, wherein the loading amount of sulfite is within a range of 2-7 wt%, on the basis of the total weight of the SO₂ adsorption material;
preferably, the sulfite is sodium sulfite and/or potassium sulfite.
3. The SO₂ adsorption material of claim 1 or 2, wherein said carbonized metal organic framework material has a regular, porous and cage-like topological structure with a bulk density of 0.2-0.35 g/cm³, a specific surface area of 1,000-2,700 m²/g, a pore volume of 1-3.8 cm³/g, and (macropore volume + mesopore volume)/micropore volume = 0.16-3.5;
preferably, said carbonized metal organic framework material has a regular, porous and cage-like topological structure with a bulk density of 0.22-0.33 g/cm³, a specific surface area of 1,025-2,650 m²/g, a pore

volume of 1.06-3.7 cm³/g, and (macropore volume + mesopore volume)/micropore volume =2.3-3.5.

4. The SO₂ adsorption material of any of claims 1 to 3, wherein the SO₂ adsorption material has a bulk density of 0.2-0.39 g/cm³, a specific surface area of 1,000-2,700 m²/g, a pore volume of 1-3.7 cm³/g, and (macropore volume + mesopore volume)/micropore volume =0.21-3.5; preferably, the SO₂ adsorption material has a bulk density of 0.21-0.35 g/cm³, a specific surface area of 2,000-2,650 m²/g, a pore volume of 2.8-3.7 cm³/g, and (macropore volume + mesopore volume)/micropore volume =2.3-3.5.

5. The SO₂ adsorption material of any of claims 1 to 4, wherein the metal organic framework material is a zinc-based metal organic framework material; preferably, the metal organic framework material is at least one selected from the group consisting of MOF-5, MOF-74, ZIF-8, ZIF-7 and ZIF-20; preferably, the metal organic framework material is MOF-5 having a specific surface area within a range of 1,500-1,700 m²/g and a pore volume within a range of 1-1.15 cm³/g.

6. The SO₂ adsorption material of any of claims 1 to 5, wherein the

carbonization treatment is carried out in a protective atmosphere under a carbonization temperature of 900-1,150°C for a carbonization time of 5-10h.

7. The SO₂ adsorption material of any of claims 1 to 6, wherein the metal organic framework material contains a metal element in an amount of 20-35 wt%.

8. The SO₂ adsorption material of any of claims 1 to 7, wherein the content of metal elements in the carbonized metal organic framework material is within a range of 0-0.06 wt%, preferably 0-0.02 wt%.

9. A method for preparing a SO₂ adsorption material, wherein the method comprises the following steps:

(1) subjecting a metal organic framework material to a carbonization treatment to remove at least a portion of the metal elements contained in the metal organic framework material, so as to obtain a carbonized metal organic framework material;

(2) loading sulfite on the carbonized metal organic framework material to prepare the SO₂ adsorption material;

said carbonized metal organic framework material and said sulfite are used in an amount such that a loading amount of sulfite is not higher than

10 wt%, preferably 2-7 wt%, on the basis of a total weight of the SO₂ adsorption material.

10. The method of claim 9, wherein the carbonization treatment in step (1) is carried out in a protective atmosphere under a carbonization temperature of 900-1,150°C for a carbonization time of 5-10h.

11. The method of claim 10, wherein the protective atmosphere is provided by at least one substance selected from the group consisting of nitrogen gas, argon gas, helium gas and neon gas.

12. The method of any one of claims 9 to 11, wherein the modes of loading sulfite on the carbonized metal organic framework material in step (2) comprise impregnating the carbonized metal organic framework material with a sulfite solution, and drying the impregnated carbonized metal organic framework material to remove the solvent;
preferably, the sulfite solution has a mass concentration less than 6%;
preferably, the drying is carried out in an inert atmosphere, the drying temperature is within a range of 100-120°C, and the drying time is within a range of 6-10h.

13. The method of any of claims 9 to 12, wherein the sulfite is sodium

sulfite and/or potassium sulfite.

14. The method of any of claims 9 to 13, wherein the metal organic framework material is selected from zinc-based metal organic framework materials;

preferably, the metal organic framework material is at least one selected from the group consisting of MOF-5, MOF-74, ZIF-8, ZIF-7 and ZIF-20;
preferably, the metal organic framework material is MOF-5 having a specific surface area within a range of 1,500-1,700 m²/g and a pore volume within a range of 1-1.15 cm³/g.

15. The method of claim 12, wherein impregnating the carbonized metal organic framework is carried out for a time in the range of 1-5h.

16. The method of claim 12, wherein the sulfite solution has a mass concentration within a range of 1.2-4%.

17. The method of any one of claims 9 to 16, wherein the sulfite is sodium sulfite and/or potassium sulfite.

18. Use of a SO₂ adsorption material in the field of desulfurization, wherein the SO₂ adsorption material comprises a carbonized metal organic framework material and a sulfite loaded on the carbonized metal

organic framework material, and the carbonized metal organic framework material is a carbonized material obtained by subjecting a metal organic framework material to a carbonization treatment; and
a loading amount of sulfite is not higher than 10 wt%, on the basis of a total weight of the SO₂ adsorption material.

19. A method for removing SO₂ from a SO₂-containing flue gas containing SO₂, comprising a step of contacting a SO₂ adsorption material with the SO₂-containing flue gas to be treated for adsorption treatment, wherein said SO₂ adsorption material comprises a carbonized metal organic framework material and a sulfite loaded on the carbonized metal organic framework material, and the carbonized metal organic framework material is a carbonized material obtained by subjecting a metal organic framework material to a carbonization treatment; and
a loading amount of sulfite is not higher than 10 wt%, on the basis of a total weight of the SO₂ adsorption material.

20. The method of claim 19, wherein the conditions of the adsorption treatment comprise: an adsorption temperature of 5-25°C, an adsorption volumetric hourly space velocity of 100-1,000h⁻¹, and an adsorption pressure of 0-0.3MPa;

preferably, the SO₂-containing flue gas to be treated comprises SO₂ in a

volume content of 1-5% and water vapor in an volume content of 1-4%.