


9704752-6
1P08**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C08F 297/00, 4/40, 4/44	A1	(11) International Publication Number: WO 96/30421 (43) International Publication Date: 3 October 1996 (03.10.96)
(21) International Application Number: PCT/US96/03302 (22) International Filing Date: 19 March 1996 (19.03.96) (30) Priority Data: 08/414,415 31 March 1995 (31.03.95) US (71)(72) Applicants and Inventors: MATYJASZEWSKI, Krzysztof [US/US]; Carnegie-Mellon University, Dept. of Chemistry, 4400 Fifth Avenue, Pittsburgh, PA 15213 (US). WANG, Jin-Shan [CN/US]; 1611 Westminister Drive #106, Naperville, IL 60563 (US). (74) Agents: SCHWARTZ, Timothy, R. et al.; Oblon, Spivak, McClelland, Maier & Neustadt, P.C., Crystal Square Fire, 4th floor, 1755 Jefferson Davis Highway, Arlington, VA 22202 (US).	(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BE, BF, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> 	

(54) Title: NOVEL (CO)POLYMERS AND A NOVEL POLYMERIZATION PROCESS BASED ON ATOM (OR GROUP) TRANSFER RADICAL POLYMERIZATION**(57) Abstract**

A new polymerization process (atom transfer radical polymerization, or ATRP) based on a redox reaction between a transition metal (e.g., Cu(I)/Cu(II)), provides "living" or controlled radical polymerization of styrene, (meth)acrylates, and other radically polymerizable monomers. Using various simple organic halides as model halogen atom transfer precursors (initiators) and transition metal complexes as a model halogen atom transfer promoters (catalysts), a "living" radical polymerization affords (co)polymers having the predetermined number average molecular weight by $\Delta[M]/[I]_0$ (up to $M_n > 10^5$) and a surprisingly narrow molecular weight distribution (M_w/M_n), as low as 1.15. The participation of free radical intermediates in ATRP is supported by end-group analysis and stereochemistry of the polymerization. In addition, polymers with various topologies (e.g., block, random, star, end-functional and in-chain functional copolymers [for example, of styrene and methyl (meth)acrylate]) have been synthesized using the present process. The polymeric products encompassed by the present invention can be widely used as plastics, elastomers, adhesives, emulsifiers, thermoplastic elastomers, etc.

**THIS SHEET HAS BEEN
REPLACED**

This Sheet Has Been Replaced

