

DESCRIPTION

METHOD FOR PRODUCING POLYMER AND LIVING RADICAL POLYMERIZATION

INITIATOR

Technical Field

[0001]

The present invention relates to a method for producing a polymer used for living radical polymerization initiator and a polymerization initiator.

Background Art

[0002]

As a method for obtaining a vinyl polymer based on polymerization of a vinyl monomer, a radical polymerization method is conventionally known. The radical polymerization method has a disadvantage that it is generally difficult to control the molecular weight of a vinyl polymer to be obtained.

[0003]

Furthermore, there is also a disadvantage that, as the vinyl polymer to be obtained is a mixture of compounds with various molecular weights, it is difficult to obtain a vinyl polymer with narrow molecular weight distribution.

[0004]

Specifically, even when the reaction is controlled, the ratio (M_w/M_n) between weight average molecular weight (M_w) and number average molecular weight (M_n) can be only reduced to 2

to 3 or so.

[0005]

As a method for overcoming the above disadvantages, a living radical polymerization method has been developed since 1990. Namely, according to the living radical polymerization method, it is possible to control the molecular weight and also possible to obtain a polymer with narrow molecular weight distribution.

[0006]

Specifically, since it is possible to obtain easily a polymer which has M_w/M_n of 2 or less, the method receives great attention as a method for producing a polymer that is used for a cutting edge field like nano technology (see, Patent Literature 1, for example).

Citation List

Patent Literature

[0007]

Patent Literature 1: JP 2009-203359 A

Summary of Invention

Technical Problem

[0008]

Meanwhile, the conventional radical polymerization method described above involves with a reaction system in which

the polymerization reaction progresses for one initiating group of a polymerization initiator. However, it would be preferable to have a reaction system in which a different polymerization reaction is carried out for a plurality of initiating groups.

[0009]

Accordingly, the present invention is devised in view of the problems described above, and an object of the present invention is to provide a living radical polymerization initiator which has two halogen atoms different from each other in reactivity and enables different polymerization reactions to proceed in two directions by having each of the halogen atoms as a initiating group, a method for producing a polymer, and a polymer produced by using them.

Solution to Problem

[0010]


To solve the problems described above, the inventors of the present invention invented a living radical polymerization initiator which has two halogen atoms different from each other in reactivity and enables different polymerization reactions to proceed in two directions by having each of the halogen atoms as a initiating group, a method for producing a polymer, and a polymer produced by using them.

[0011]

A method for producing a polymer according to a first

invention is a method for producing a polymer by using a living radical polymerization initiator which consists of the following general formula (1):

[Chemical Formula 1]



in the formula, R¹ represents an organic group which is linkable with two or more other organic groups, and is selected from an aliphatic group having 1 to 12 carbon atoms, an aromatic group, an alkylcarbonyl group having 1 to 12 carbon atoms, an alkoxy carbonyl group having 1 to 12 carbon atoms, an aminocarbonyl group, an alkylaminocarbonyl group having 1 to 12 carbon atoms, a dialkylaminocarbonyl group having 1 to 12 carbon atoms, an arylcarbonyl group, an alkylsulfonyl group having 1 to 12 carbon atoms, an arylsulfonyl group, and an organic group in which two or more of those groups are combined,

R², R³, R⁴ and R⁵ are a hydrogen atom or an organic group selected from an aliphatic group having 1 to 12 carbon atoms, an aromatic group, an alkylcarbonyl group, an alkoxy carbonyl group, an aminocarbonyl group, an alkylaminocarbonyl group, a dialkylaminocarbonyl group having 1 to 12 carbon atoms, an arylcarbonyl group, a carboxy group, an alkylsulfonyl group having 1 to 12 carbon atoms, and an aryl sulfonyl group,

X and Y are a halogen atom,
m and n are an integer of 1 or more, and
the X and Y are in a state in which they are different
from each other in reactivity with a monomer,

a first polymerization step in which, for only one halogen
atom of the X or Y of the living radical polymerization initiator,
a living radical polymerization reaction in which the living
radical polymerization reaction initiator is mixed with a monomer
with unsaturated bond and the reaction is carried out at a reaction
condition depending on a type of the monomer one or more times
while changing in order the type of the monomer to be mixed to
obtain a first product; and

a second polymerization step in which, for both halogen
atoms of the X and Y contained in the first product, at least
one type of the monomer is subjected to a living radical
polymerization reaction in order at a reaction condition
depending on a type of the monomer to obtain a final product.

[0012]

In the method for producing a polymer according to a second
invention, in the first invention, the halogen atom is iodide,
chloride, or bromide.

[0013]

In the method for producing a polymer according to a third
invention, in the first invention or the second invention, the

first polymerization step and the second polymerization step are carried out by using a catalyst and the first polymerization step and the second polymerization step are carried out such that at least one of reaction temperature and type of the catalyst is changed depending on the type of the monomer.

[0014]

In the method for producing a polymer according to a fourth invention, in the third invention, the catalyst is a transition metal complex-based catalyst which is used for an atom transfer radical polymerization, a catalyst consisting of a compound containing at least one center element selected from phosphorus, nitrogen, carbon, oxygen, germanium, tin, and antimony and a halogen atom bound to the center element, which is used for reversible chain transfer catalyst polymerization, an organic amine compound catalyst used for reversible complexation mediated polymerization, or a catalyst in which, as a non-metal compound having an ionic bond with a halide ion, a non-metal atom in the non-metal compound is in a cation state and forms an ionic bond with the halide ion.

[0015]

In the method for producing a polymer according to a fifth invention, in any one of the first to fourth invention, the first polymerization step and the second polymerization step are carried out at 180°C or lower.


[0016]

In the method for producing a polymer according to a sixth invention, in any one of the first to fifth invention, the first polymerization step and the second polymerization step are carried out for reaction time of 30 minutes or longer and 24 hours or shorter.

[0017]

A living radical polymerization initiator according to a seventh invention is a living radical polymerization initiator by using the method for producing a polymer according to any one of claims 1 to 6, represented by the following general formula (1):

[Chemical Formula 1]



in the formula, R^1 represents an organic group which is linkable with two or more other organic groups, and is selected from an aliphatic group having 1 to 12 carbon atoms, an aromatic group, an alkylcarbonyl group having 1 to 12 carbon atoms, an alkoxycarbonyl group having 1 to 12 carbon atoms, an aminocarbonyl group, an alkylaminocarbonyl group having 1 to 12 carbon atoms, a dialkylaminocarbonyl group having 1 to 12 carbon atoms, an arylcarbonyl group, an alkylsulfonyl group having 1 to 12 carbon atoms, an arylsulfonyl group, and an organic group in which two or more of those groups are combined,

R^2 , R^3 , R^4 and R^5 are a hydrogen atom or an organic group selected from an aliphatic group having 1 to 12 carbon atoms, an aromatic group, an alkylcarbonyl group, an alkoxy carbonyl group, an aminocarbonyl group, an alkylaminocarbonyl group, a dialkylaminocarbonyl group having 1 to 12 carbon atoms, an arylcarbonyl group, a carboxy group, an alkylsulfonyl group having 1 to 12 carbon atoms, and an aryl sulfonyl group,

X and Y are a halogen atom,

m and n are an integer of 1 or more, and

the X and Y are in a state in which they are different from each other in reactivity with a monomer.

In the living radical polymerization initiator according to an eighth invention, in the seventh invention, the halogen atom is iodide, chloride, or bromide.

Advantageous Effects of Invention

[0018]

According to the present invention consisting of the above constitutions, it is possible to provide a method for producing a polymer by using a living radical polymerization initiator which has two halogen atoms different from each other in reactivity and enables different polymerization reactions to proceed in two directions by having each of the halogen atoms as a initiating group.

Brief Description of Drawings

[0019]

Fig. 1 is a schematic diagram illustrating a basic reaction in a method for producing a polymer according to an embodiment of the present invention.

Fig. 2 is a schematic diagram illustrating a process for having a polymer with regard to a method for producing a polymer according to Example.

Fig. 3 is a ^1H -NMR chart of a living radical polymerization initiator and each polymer obtained by the method for producing a polymer according to Example, in which (a) represents a structural formula of alkyl iodide as a living radical polymerization initiator, (b) represents a ^1H -NMR chart of the living radical polymerization initiator, (c) represents a ^1H -NMR chart of a polymer P, (d) represents a ^1H -NMR chart of a polymer Q, and (e) represents a ^1H -NMR chart of a polymer R.

Description of Embodiments

[0020]

Hereinbelow, a living radical polymerization initiator according to an embodiment of the present invention and a method for producing a polymer by using it are described in detail.

[0021]


[Living radical polymerization initiator]

(1) Chemical formula of living radical polymerization initiator

The living radical polymerization initiator according to this embodiment has a structure represented by the chemical formula (1), and it has two halogen atoms different from each other in reactivity.

[0022]

[Chemical Formula 1]



[0023]

In the above chemical formula (1), R¹ is an organic group with valency of two or more, i.e., an organic group which is linkable with two or more other organic groups, and examples thereof include an aliphatic group having 1 to 12 carbon atoms, an aromatic group, an alkylcarbonyl group having 1 to 12 carbon atoms, an alkoxycarbonyl group having 1 to 12 carbon atoms, an aminocarbonyl group, an alkylaminocarbonyl group having 1 to 12 carbon atoms, a dialkylaminocarbonyl group having 1 to 12 carbon atoms, an arylcarbonyl group, an alkylsulfonyl group having 1 to 12 carbon atoms, an arylsulfonyl group, and an organic group in which two or more of those groups are combined.

[0024]

Furthermore, each of R², R³, R⁴ and R⁵ is a hydrogen atom or an organic group selected from an aliphatic group having 1 to 12 carbon atoms, an aromatic group, an alkylcarbonyl group

having 1 to 12 carbon atoms, an alkoxycarbonyl group having 1 to 12 carbon atoms, an aminocarbonyl group, an alkylaminocarbonyl group having 1 to 12 carbon atoms, a dialkylaminocarbonyl group having 1 to 12 carbon atoms, an arylcarbonyl group, an alkylsulfonyl group having 1 to 12 carbon atoms, and an aryl sulfonyl group, X and Y are a halogen atom, and m and n are an integer of 1 or more. The left and right structures of the linking group R^1 in the chemical formula (1) are non-symmetrical so that the halogen atoms X and Y are given with different reactivity.

[0025]

(2) Linking group

The linking group R^1 is not particularly limited as long as it is an organic group which is linkable with two or more other organic groups. Specific examples thereof include an aliphatic group, an aromatic group, an alkylcarbonyl group having 1 to 12 carbon atoms, an alkoxycarbonyl group having 1 to 12 carbon atoms, an aminocarbonyl group, an alkylaminocarbonyl group having 1 to 12 carbon atoms, a dialkylaminocarbonyl group having 1 to 12 carbon atoms, an arylcarbonyl group, an alkylsulfonyl group having 1 to 12 carbon atoms, an aryl sulfonyl group, and an organic group in which two or more of those groups are combined.

[0026]

The linking group R^1 may have a substituent group, and in a case in which it has a substituent group, number of the

substituent group is not particularly limited as long as the substitution can be made, and the number is 1 or more.

[0027]

As for the group which may be substituted on the linking group R^1 , a halogen atom, a linear or non-linear alkyl group having 1 to 12 carbon atoms which may be substituted, an aromatic group which may be substituted, a non-aromatic heterocyclic group which may be substituted, a carboxy group, a linear or non-linear alkoxy group having 1 to 12 carbon atoms, a cyano group, a nitro group, and the like can be mentioned.

[0028]

As for the aliphatic group, a linear or non-linear alkyl group having 1 to 12 carbon atoms which may be substituted can be mentioned.

[0029]

In a case in which the aliphatic group is substituted, number of the substituent group is not particularly limited, and it is 1 or more.

[0030]

Furthermore, as for the group which may be substituted on the aliphatic group, a halogen atom, a linear or non-linear alkyl group having 1 to 12 carbon atoms which may be substituted, an aromatic group which may be substituted, a non-aromatic heterocyclic group which may be substituted, a linear or non-linear alkoxy group having 1 to 12 carbon atoms, a cyano

group, a nitro group, and the like can be mentioned.

[0031]

As for the aromatic group, an aromatic hydrocarbon cyclic group or an aromatic heterocyclic group can be mentioned, and specific examples thereof include a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a binaphthyl group, an azulenyl group, an anthracenyl group, a phenanthrenyl group, a furarenyl group, a furyl group, a thienyl group, a pyrrolyl group, a pyrazolyl group, an imidazolyl group, an isoxazolyl group, a thiazolyl group, a triazolyl group, a pyridyl group, a benzofuranyl group, an indolyl group, a benzothiazolyl group, and a carbazolyl group.

[0032]

The aromatic group may be substituted, and in that case, number of the substituent group is not particularly limited as long as the substitution can be made, and it is 1 or more.

[0033]

Furthermore, as for the group which may be substituted on the aromatic group, a halogen atom, a linear or non-linear alkyl group having 1 to 12 carbon atoms which may be substituted, an aromatic group which may be substituted, a non-aromatic heterocyclic group which may be substituted, a carboxy group, a linear or non-linear alkoxy group having 1 to 12 carbon atoms, a cyano group, a nitro group, and the like can be mentioned.

[0034]

(3) R^2 to R^5

As for the aliphatic group, a linear or non-linear alkyl group having 1 to 12 carbon atoms which may be substituted can be mentioned.

[0035]

In a case in which the aliphatic group is substituted, number of the substituent group is not particularly limited as long as the substitution can be made, and it is 1 or more.

[0036]

Furthermore, as for the group which may be substituted on the aliphatic group, a halogen atom, a linear or non-linear alkyl group having 1 to 12 carbon atoms which may be substituted, an aromatic group which may be substituted, a non-aromatic heterocyclic group which may be substituted, a linear or non-linear alkoxy group having 1 to 12 carbon atoms, a cyano group, a nitro group, and the like can be mentioned.

[0037]

As for the aromatic group, an aromatic hydrocarbon cyclic group or an aromatic heterocyclic group can be mentioned, and specific examples thereof include a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a binaphthyl group, an azulenyl group, an anthracenyl group, a phenanthrenyl group, a furarenyl group, a furyl group, a thienyl group, a pyrrolyl group, a pyrazolyl group, an imidazolyl group, an isoxazolyl group, a thiazolyl group, a tetrazolyl group, a

pyridyl group, a benzofuranyl group, an indolyl group, a benzothiazolyl group, and a carbazolyl group.

[0038]

The aromatic group may be substituted, and in that case, number of the substituent group is not particularly limited as long as the substitution can be made, and it is 1 or more.

[0039]

Furthermore, as for the group which may be substituted on the aromatic group, a halogen atom, a linear or non-linear alkyl group having 1 to 12 carbon atoms which may be substituted, an aromatic group which may be substituted, a non-aromatic heterocyclic group which may be substituted, a carboxy group, a linear or non-linear alkoxy group having 1 to 12 carbon atoms, a cyano group, a nitro group, and the like can be mentioned.

[0040]

Furthermore, as for the arylcarbonyl group, a benzoyl group, a 1-naphthoyl group, a 2-naphthoyl group, a 2-pyridylcarbonyl group, a 3-pyridylcarbonyl group, a 4-pyridylcarbonyl group, and the like can be mentioned.

[0041]

Furthermore, as for the aryl sulfonyl group, a benzene sulfonyl group, a toluene sulfonyl group, and the like can be mentioned.

[0042]

Furthermore, X and Y in the chemical formula (1) represent

a halogen atom, and they are preferably chloride, bromide, or iodide, and more preferably iodide.

[0043]

Since the aforementioned living radical polymerization initiator according to the present invention has two halogen atoms that are different from each other in reactivity as an initiating group, by suitably adjusting the reaction conditions, the living radical polymerization reaction different for each initiating group is allowed to occur.

[0044]

[Method for producing polymer]

Next, descriptions are given for the method for producing a polymer of a radical polymerizable monomer which is obtained by carrying out living radical polymerization by using the aforementioned living radical polymerization initiator.

[0045]

(1) Basic reaction

The method for producing a polymer according to this embodiment is achieved by performing a basic reaction illustrated in Fig. 1 with use of the aforementioned living radical polymerization initiator. Fig. 1 is a schematic diagram illustrating a basic reaction in a method for producing a polymer according to an embodiment of the invention. a, b, and c each represent a radical reactive polymerizable monomer having an unsaturated bond, and each of them may be a different monomer

or the same monomer. Furthermore, A, B, and C each represent a polymer block.

[0046]

According to the basic reaction illustrated in Fig. 1, as a first step, the polymerization reaction of a radical polymerizable monomer is carried out one or more times by having one of the halogen atoms as an initiating group while the type of a monomer to be mixed is changed in order, and then as a second step, the polymerization reaction is carried out to produce a polymer by using the other halogen atom remaining in the skeleton of an initiator as an initiator.

[0047]

Herein, the halogen atom Y in the living radical polymerization initiator of Fig. 1 is designed such that it has higher reactivity than the halogen atom X.

[0048]

Furthermore, since each of the reaction conditions 1 to 4 has a different reaction condition, one or more of the reaction temperature, reaction time, presence or absence of the catalyst, and type of the catalyst is different.

[0049]

According to the reaction of Fig. 1, the monomer a and the living radical polymerization initiator are first reacted with each other at reaction condition 1. The reaction condition 1 is set such that the living radical polymerization progresses

only with the halogen atom Y which has higher reactivity among the living radical polymerization initiators.

[0050]

Accordingly, polymer A in which a plurality of the monomers A are polymerized to the halogen atom Y of the living radical polymerization initiator is produced.

[0051]

The polymer A is then subjected to living radical polymerization reaction with the monomer b. By changing the reaction condition, a different polymer can be obtained.

[0052]

Specifically, by reacting the polymer A with the monomer b under the reaction condition 2 in which the reaction is allowed to occur not only with the halogen atom Y having high reactivity but also with the halogen atom X having low reactivity, polymer BAB in which a plurality of the monomers b are polymerized at each side of the halogen atom X and the halogen atom Y of the polymer A is generated.

[0053]

Incidentally, by reacting the polymer A with the monomer b under the reaction condition 3 in which the reaction is allowed to occur only with the halogen atom Y having high reactivity, polymer AB in which a plurality of the monomers b are polymerized at the halogen atom Y side of the polymer A is generated.

[0054]

As described above, according to the aforementioned basic reaction, any one halogen atom remains unreacted in the first step of the reaction, and by varying the reaction temperature or adding a different catalyst in the second step and the third step, the remaining halogen atom reacts as an initiating group with the monomer.

[0055]

It is also possible to carry out an additional living radical polymerization reaction for the polymer BAB or the polymer AB which is obtained as described above.

[0056]

For example, by reacting the polymer AB with the monomer c under the reaction condition 4 in which both the halogen atom X and the halogen atom Y react, polymer CABC in which a plurality of the monomers c are polymerized at each side of the halogen atom X and the halogen atom Y of the polymer AB is generated. It is evident that the polymer ABC can be obtained by carrying out the reaction under the reaction condition in which the monomer c reacts with the halogen atom Y side of the polymer AB and a different living polymerization reaction is allowed to proceed additionally with the polymer CABC or the polymer ABC.

[0057]

(2) Radical polymerizable monomer

The radical polymerizable monomer used for the aforementioned reaction is a monomer having an unsaturated bond

which allows radical polymerization in the presence of an organic radical. The unsaturated bond may be a triple bond other than a double bond. Namely, for the method for producing a polymer according to the present embodiment, any one of conventionally known monomers allowing living radical polymerization can be used.

[0058]

Such radical polymerizable monomer is specifically a monomer which is referred to as a vinyl monomer. The vinyl monomer is a general name of monomers that are represented by general formula " $\text{CH}_2 = \text{CR}^6\text{R}^7$ ".

[0059]

With regard to the above general formula, a monomer in which R^6 is methyl and R^7 is carboxylate is referred to as a methacrylate-based monomer, and it can be desirably used in the present invention,

[0060]

Specific examples of the methacrylate-based monomer include methyl methacrylate, ethyl methacrylate, propyl methacrylate, n-butyl methacrylate, t-butyl methacrylate, hexyl methacrylate, 2-ethylhexyl methacrylate, nonyl methacrylate, benzyl methacrylate, glycidyl methacrylate, cyclohexyl methacrylate, lauryl methacrylate, n-octyl methacrylate, 2-methoxyethyl methacrylate, butoxyethyl methacrylate, methoxytetraethylene glycol methacrylate,

2-hydroxyethyl methacrylate, 2-hydroxypropyl methacrylate, 3-chloro-2-hydroxypropyl methacrylate, tetrahydrofurfuryl methacrylate, 2-hydroxy3-phenoxypropyl methacrylate, diethylene glycol methacrylate, polyethylene glycol methacrylate, and 2-(dimethylamino)ethyl methacrylate.

[0061]

Furthermore, methacrylic acid can be also used.

[0062]

Furthermore, methacrylate with ion liquid property like 2-(N,N-diethyl-N-methylamino)ethyl methacrylate+/trifluorosulfonyl iminium ($\text{N}(\text{CF}_3\text{SO}_2)^{2-}$) salt, 2-(N-ethyl-N-methyl-N-hydrogenated amino)ethyl methacrylate+/trifluorosulfonyl iminium ($\text{N}(\text{CF}_3\text{SO}_2)^{2-}$) salt, 1-ethyl-3-methylimidazolium methacrylate+/fluorohydrogenation ($(\text{FH})\text{nF}^-$) salt, and N-ethyl-N-methylpyrrolidinium methacrylate+/fluorohydrogenation ($(\text{FH})\text{nF}^-$) salt can be used.

[0063]

With regard to the above general formula of vinyl monomer, a monomer in which R^6 is hydrogen and R^7 is carboxylate is referred to as an acrylate-based monomer, and it can be desirably used in the present invention.

[0064]

Specific examples of the acrylate-based monomer include methyl acrylate, ethyl acrylate, propyl acrylate, n-butyl

acrylate, t-butyl acrylate, hexyl acrylate, 2-ethylhexyl acrylate, nonyl acrylate, benzyl acrylate, glycidyl acrylate, cyclohexyl acrylate, lauryl acrylate, n-octyl acrylate, 2-methoxyethyl acrylate, butoxyethyl acrylate, methoxytetraethylene glycol acrylate, 2-hydroxyethyl acrylate, 2-hydroxypropyl acrylate, 3-chloro-2-hydroxypropyl acrylate, tetrahydrofurfuryl acrylate, 2-hydroxy-3-phenoxypropyl acrylate, diethylene glycol acrylate, polyethylene glycol acrylate, and 2-(dimethylamino)ethyl acrylate.

[0065]

Furthermore, acrylic acid can be also used.

[0066]

Furthermore, acrylate with ion liquid property like 2-(N,N-diethyl-N-methylamino)ethyl acrylate+/trifluorosulfonyl iminium ($\text{N}(\text{CF}_3\text{SO}_2)^{2-}$) salt, 2-(N-ethyl-N-methyl-N-hydrogenated amino)ethyl acrylate+/trifluorosulfonyl iminium ($\text{N}(\text{CF}_3\text{SO}_2)^{2-}$) salt, 1-ethyl-3-methylimidazolium acrylate+/fluorohydrogenation ($(\text{FH})\text{nF}^-$) salt, and N-ethyl-N-methylpyrrolidinium acrylate+/fluorohydrogenation ($(\text{FH})\text{nF}^-$) salt can be used.

[0067]

Controlling the living radical polymerization of acrylate is difficult in general. However, the control can be made according to the present invention. When a phosphorus-based catalyst is used, in particular, the polymerization of an

acrylate can be desirably controlled.

[0068]

With regard to the above general formula of vinyl monomer, a monomer in which R^6 is hydrogen and R^7 is phenyl corresponds to styrene and it can be desirably used in the present invention.

[0069]

Furthermore, a monomer in which R^7 is phenyl or a phenyl derivative corresponds to a styrene derivative and it can be desirably used in the present invention. Specific examples thereof include o-, m-, p-methoxystyrene, o-, m-, p-styrene sulfonic acid, and the like.

[0070]

Furthermore, vinyl naphthalene in which R^7 is an aromatic can be also mentioned.

[0071]

With regard to the above general formula of vinyl monomer, a monomer in which R^6 is hydrogen and R^7 is alkyl corresponds to alkylene and it can be desirably used in the present invention.

[0072]

For the present invention, a monomer having two or more vinyl groups can be also used. Specific examples thereof include a diene-based compound (for example, butadiene and isoprene), a compound with two allyl groups (for example, diallyl phthalate), dimethacrylate with two methacryls (for example, ethylene glycol dimethacrylate), and diacrylate with two acryls (for example,

ethylene glycol diacrylate).

[0073]

For the present invention, a vinyl monomer other than those described above can be also used. Specific examples thereof include vinyl esters (for example, vinyl acetate, vinyl propionate, vinyl benzoate, and vinyl acetate), a styrene derivative other than those described above (for example, α -methylstyrene), vinyl ketones (for example, vinyl ethyl ketone, vinyl hexyl ketone, and methyl isopropenyl ketone), an N-vinyl compound (for example, N-vinyl pyrrolidone, N-vinyl pyrrole, N-vinyl carbazole, and N-vinyl indole), (meth)acrylamide and a derivative thereof (for example, N-isopropyl acrylamide, N-isopropyl methacrylamide, N,N-dimethyl acrylamide, N,N-dimethyl methacrylamide, N-methylol acrylamide, and N-methylolmethacrylamide), acrylonitrile, methacrylonitrile, maleic acid and a derivative thereof (for example, maleic anhydride), vinyl halides (for example, vinyl chloride, vinylidene chloride, tetrachloroethylene, hexachloropropylene, and vinyl fluoride), and olefins (for example, ethylene, propylene, 1-hexene, and cyclohexene).

[0074]

Those monomers may be used either singly or in combination of two or more types. Furthermore, two or more types of a monomer may be added simultaneously at the time of initiating the reaction of the first step, or they may be added to each step of the reaction.

[0075]

(3) Catalyst

For a monomer which is arbitrarily selected, an arbitrarily selected catalyst of the present invention may be added, if necessary. It is possible not to have any catalyst. However, by adding the catalyst, the reaction progresses more favorably. Combination of the type of the monomer and the type of the catalyst of the present invention is not particularly limited.

[0076]

Examples of the catalyst include a transition metal complex-based catalyst which is used for an atom transfer radical polymerization (ATRP method), a catalyst consisting of a compound containing at least one center element selected from phosphorus, nitrogen, carbon, oxygen, germanium, tin, and antimony and a halogen atom bound to the center element, which is used for reversible chain transfer catalyst polymerization (RTCP method), an organic amine compound used for reversible complexation mediated polymerization (RCMP), and a catalyst in which, as a non-metal compound having an ionic bond with a halide ion, a non-metal atom in the non-metal compound is in a cation state and forms an ionic bond with the halide ion.

[0077]

As for the transition metal complex-based catalyst, a metal complex formed of a metal with low atomic valency such as Group 7, Group 8, Group 9, Group 10, or Group 11 of the Periodic Table

and an organic ligand or a metal complex formed of a metal with low atomic valency such as Group 7, Group 8, Group 9, Group 10, or Group 11 of the Periodic Table, a metal with high atomic valency, and an organic ligand (see, JP 2002-249505 A) can be used.

[0078]

Examples of the metal with low atomic valency include cuprous chloride, cuprous bromide, cuprous iodide, cuprous cyanide, cuprous oxide, ferrous chloride, ferrous bromide and ferrous iodide, and examples of the metal with high atomic valency include ferric chloride, ferric bromide, ferric iodide, ruthenium dichloride, ruthenium dibromide, and ruthenium diiodide.

[0079]

Furthermore, examples of the organic ligand include pyridines, bipyridines, polyamines, and phosphines, and specific examples thereof include 2,2'-bipyridyl and a derivative thereof, 1,10-phenanthroline and a derivative thereof, tetramethylethylene diamine, pentamethyldiethylene triamine, tris(dimethylaminoethyl)amine, triphenylphosphine, and tributylphosphine.

[0080]

Examples of the catalyst which has an element selected from germanium, tin, and antimony as a center element include a compound which contains at least one center element selected from germanium, tin, and antimony and at least one halogen atom

bound to the center element, and specific examples thereof include germanium (II) iodide, germanium (IV) iodide, tin (II) iodide, and tin (IV) iodide (see, JP 2007-92014 A).

[0081]

As for the catalyst in which nitrogen or phosphorus is contained as a center element, a compound having at least one center element selected from nitrogen and phosphorus and at least one halogen atom bound to the center element can be mentioned. Specific examples thereof include phosphorus halide, phosphine halide, nitrogen halide, phosphorus acid halide, amine halide, and imide halide derivative (see, WO 2008/139980 A).

[0082]

Specific examples of the organic amine compound catalyst include triethylamine, tributylamine, 1,1,2,2-tetrakis(dimethylamino)ethene, 1,4,8,11-tetramethyl-1,4,8,11-tetraazacyclotetradecane, ethylenediamine, tetramethylethylenediamine, tetramethyldiaminomethane, tris(2-aminoethyl)amine, tris(2-(methylamino)ethyl)amine, and hematoporphyrin (see, WO 2011/016166 A).

[0083]

Specific examples of the catalyst in which, as a non-metal compound having an ionic bond with a halide ion, a non-metal atom in the non-metal compound is in a cation state and forms an ionic bond with the halide ion include ammonium salt,

imidazolium salt, pyridinium salt, phosphonium salt, sulfonium salt, and iodonium salt. More specific examples thereof include tetrabutyl ammonium iodide, tetrabutyl ammoniumtri iodide, tetrabutyl ammoniumbromo diiodide, 1-methyl-3-methyl-imidazolium iodide, 1-ethyl-3-methylimidazolium bromide, 2-chloro-1-methylpyridinium iodide, hexaphenyldiphosphagenium chloride, methyltributyl phosphonium iodide, tetraphenyl phosphonium iodide, tributylsulfonium iodide, and diphenyliodonium iodide (see, WO 2013/027419 A).

[0084]

(4) Reaction temperature

The reaction temperature is not particularly limited. It is preferably 0°C to 180°C, and more preferably 30°C to 120°C.

[0085]

(5) Reaction time

The reaction time can be suitably selected within a range of 30 minutes to 24 hours such that is it suitable for each reaction.

[0086]

(6) Reaction solvent

The reaction can be carried out in the absence of a solvent. However, it is also possible to use a solvent. The reaction solvent is not particularly limited as long as the reaction is

not inhibited by it. However, it is preferable to use acetonitrile, methylene chloride, tetrahydrofuran, toluene, xylene, acetone, methyl ethyl ketone, ethanol, isopropanol, ethyl acetate, butyl acetate, ethyl cellosolve, or the like.

Examples

[0087]

Hereinbelow, the present invention is described in greater detail in view of the Examples. However, it is evident that the present invention is not limited to the Examples at all.

[0088]


<Preparation of living radical polymerization initiator>

(Example 1) Preparation of methyl

2-iodo-2-(4'-(2''-iodopropionyloxy)phenyl)acetate

[0089]

[Chemical Formula 2]



[0090]

To a mixture solution of 25.00 g (150.4 mmol) of methyl 4-hydroxyphenylacetate, 47.60 g (601.7 mmol) of pyridine, and 100 mL of diethyl ether, 50 mL diethyl ether solution of 38.97

g (180.5 mmol) of 2-bromopropionyl bromide was added at 0°C.

[0091]

After that, the reaction mixture was stirred for 30 minutes at room temperature and then washed with 5% hydrogen bromide, a saturated aqueous solution of sodium carbonate, a saturated aqueous solution of sodium sulfite, and water followed by extraction of an organic layer. The extracted solution was dried over anhydrous sodium sulfate, and according to concentration under reduced pressure, 42.91 g (yield: 95%) of methyl 2-(4'-(2''-bromopropionyloxy)phenyl)acetate was obtained.

[0092]

Next, to 66 mL dichloroethane solution of 9.94 g (33.00 mmol) of methyl 2-(4'-(2''-bromopropionyloxy)phenyl)acetate, 7.05 g (39.60 mmol) of N-bromosuccinimide was added at room temperature, and stirred under reflux for 5 hours while being illuminated with an LED light.

[0093]

The obtained reaction mixture was washed with a saturated aqueous solution of sodium sulfite and water followed by extraction of an organic layer. The extracted solution was dried over anhydrous sodium sulfate, and according to concentration under reduced pressure, 11.67 g (yield: 93%) of methyl 2-bromo-2-(4'-(2''-bromopropionyloxy)phenyl)acetate was obtained.

[0094]

To 55 mL acetonitrile solution of 10.37 g (27.23 mmol) of methyl 2-bromo-2-(4'-(2''-bromopropionyloxy)phenyl)acetate, 16.35 g (109.11 mmol) of sodium iodide was added at 0°C and then stirred at the same temperature for 1.5 hours.

[0095]

The obtained reaction mixture was added with dichloromethane and then washed with a saturated aqueous solution of sodium sulfite and water followed by extraction of an organic layer.

[0096]


The extracted solution was dried over anhydrous sodium sulfate and then concentrated under reduced pressure, and according to purification by silica gel column chromatography, 5.80 g (yield: 45%) of methyl 2-iodo-2-(4'-(2''-iodopropionyloxy)phenyl)acetate was obtained. ¹H NMR (CDCl₃): = 2.04 (d, 3H), 3.76 (s, 3H), 4.68 (q, 1H), 5.52 (s, 1H), 7.07 (d, 2H), 7.63 (d, 2H).

[0097]

(Example 2) Preparation of 4-iodobutyl 2-iodoisobutyrate

[0098]

[Chemical Formula 3]



[0099]

4.5 g (20 mmol) of 2-bromoisobutyric acid bromide and 9.0 g (60 mmol) of sodium iodide were admixed with each other under light-shielded condition, and after adding 4.8 mL (60 mmol) of tetrahydrofuran thereto, they were stirred for 2 hours at 25°C and subsequently for 30 minutes at 50°C.

[0100]

Next, the obtained reaction mixture was added with dichloromethane and then washed with a saturated aqueous solution of sodium sulfite. After drying over anhydrous sodium sulfate followed by concentration under reduced pressure, 20 mL of acetonitrile was added and then 6.0 g (40 mmol) of sodium iodide was added. After the reaction for 7 hours at 80°C, 9.0 g (60 mmol) of sodium iodide was added followed by further reaction for 7 hours.

[0101]

After that, the precipitates were separated by filtration followed by concentration under reduced pressure. Dichloromethane was then added and washing with a saturated aqueous solution of sodium sulfite was carried out. After drying over anhydrous sodium sulfate, concentration under reduced

pressure was carried out.

[0102]


Then, by purifying the obtained crude product by silica gel column chromatography, 4.4 g (yield: 68%) of (4-iodobutyl)2-iodoisobutyric acid was obtained. ^1H NMR (CDCl_3): δ = 4.17 (t, 2H), 3.22 (t, 2H), 2.06 (s, 6H), 1.98-1.90 (m, 2H), 1.83-1.77 (m, 2H).

[0103]

(Example 3) Preparation of methyl 2-iodo-2-(4'-(4''-iodobutanoyloxy)phenyl)acetate

[0104]

[Chemical Formula 4]



[0105]

To a mixture solution of 20.00 g (120.36 mmol) of methyl 4-hydroxyphenylacetate, 22.11 g (132.39 mmol) of 4-bromobutyric acid, and 60 mL of benzene, 16.69 g (108.32 mmol) of phosphoryl chloride was added at room temperature.

[0106]

After that, it was stirred for 5.5 hours at 80°C and the reaction mixture was added to 100 mL of water to extract an organic layer. The extracted solution was washed with a saturated

aqueous solution of sodium sulfite and water followed by drying over anhydrous sodium sulfate, and according to concentration under reduced pressure, 34.37 g (yield: 91%) of methyl 2-(4'-(4''-bromobutanoyloxy)phenyl)acetate was obtained.

[0107]

To 85 mL dichloroethane solution of 26.31 g (83.48 mmol) of methyl 2-(4'-(4''-bromobutanoyloxy)phenyl)acetate, 22.29 g (125.22 mmol) of N-bromosuccinimide was added at room temperature.

[0108]

Next, stirring under reflux was carried out for 6.5 hours while being illuminated with an LED light. The obtained reaction mixture was washed with a saturated aqueous solution of sodium sulfite and water followed by extraction of an organic layer.

[0109]

Next, the extracted solution was dried over anhydrous sodium sulfate followed by concentration under reduced pressure. By purifying the obtained crude product by silica gel column chromatography, 7.29 g (yield: 22%) of methyl 2-bromo-2-(4'-(4''-bromobutanoyloxy)phenyl)acetate was obtained.

[0110]

Next, to 20 mL acetone solution of 6.92 g (17.56 mmol) of methyl 2-bromo-2-(4'-(4''-bromobutanoyloxy)phenyl)acetate, 6.32 g (42.14 mmol) of sodium iodide was added at room temperature

and then stirred for 0.5 hour at 40°C.

[0111]

Next, the obtained reaction mixture was added with dichloromethane and washed with a saturated aqueous solution of sodium sulfite and water followed by extraction of an organic layer.

[0112]


Then, the extracted solution was dried over anhydrous sodium sulfate followed by concentration under reduced pressure. The obtained crude product was purified by silica gel column chromatography to obtain 2.50 g (yield: 30%) of methyl 2-iodo-2-(4'-(4''-iodobutanoyloxy)phenyl)acetate. ¹H NMR (CDCl₃): = 2.17-2.21 (m, 2H), 2.66-2.69 (t, 2H), 3.25-3.28 (t, 2H), 3.73 (s, 3H), 5.53 (s, 1H), 7.02-7.04 (m, 2H), 7.59-7.61 (m, 2H).

[0113]

(Example 4) Preparation of 4-iodobutyl 2-iodophenylacetate

[0114]

[Chemical Formula 5]



[0115]

6.5 g (30 mmol) of 2-bromophenylacetic acid was mixed with

4.2 mL (60 mmol) of thionyl chloride, and under light-shielded condition, they were stirred for 50 minutes at 80°C.

[0116]

Subsequently, after removing volatile components under reduced pressure, 8 mL (100 mmol) of THF was added and 18.0 g (120 mmol) of sodium iodide was added under light-shielded condition. After stirring for 2 hours at 27°C, 4.5 g (30 mmol) of sodium iodide was added and stirred for 5 hours at the same condition.

[0117]

Next, the obtained reaction mixture was added with dichloromethane and washed with 10 mL of an aqueous solution of sodium sulfite. Furthermore, the aqueous phase was extracted with 20 mL of dichloromethane and the organic layer was combined. After drying over anhydrous sodium sulfate, concentration under reduced pressure was carried out.

[0118]


Then, the obtained crude product was purified by silica gel column chromatography to obtain 4.1 g (yield: 31%) of 4-iodobutyl 2-iodophenyl acetate. ^1H NMR (CDCl_3): δ = 7.59-7.57 (m, 2H), 7.33-7.27 (m, 3H), 5.18 (s, 1H), 4.21-4.14 (m, 2H), 3.18 (t, 3H), 1.92-1.86 (m, 2H), 1.81-1.76 (m, 2H).

[0119]

(Example 5) Preparation of 2-(iodoacetoxy)ethyl
2-iodo-2-phenylacetate

[0120]

[Chemical Formula 6]



[0121]

To 25.00 g (114.66 mmol) of 2-bromophenyl acetic acid, 27.28 g (229.32 mmol) of thionyl chloride was added followed by stirring under reflux of 1 hour.

[0122]

After that, the remaining thionyl chloride was removed under reduced pressure, and then added to a mixture of 284.67 g (4586.32 mmol) of ethylene glycol and 9.52 g (120.39 mmol) of pyridine at room temperature.

[0123]

After stirring at the same temperature for 1 hour, diethyl ether was added and washing was carried out with 1 N hydrochloric acid, a saturated aqueous solution of sodium carbonate and water.

[0124]

After drying over anhydrous sodium sulfate, 23.61 g (yield: 80%) of 2-hydroxyethyl 2-bromo-2-phenylacetate was obtained.

[0125]

To a mixture of 5.00 g (19.30 mmol) 2-hydroxyethyl

2-bromo-2-phenylacetate, 1.60 g (20.26 mmol) of pyridine, and 20 mL of diethyl ether, 10 mL diethyl ether solution of 4.09 g (20.26 mmol) of 2-bromopropionyl bromide was added at room temperature.

[0126]

After stirring at the same temperature for 1 hour, the obtained reaction mixture was washed with 5% hydrogen bromide, a saturated aqueous solution of sodium carbonate and water to extract an organic layer.

[0127]

The extracted solution was dried over anhydrous sodium sulfate followed by concentration under reduced pressure. The obtained crude product was purified by silica gel column chromatography to obtain 4.41 g (yield: 60%) of 2-(bromoacetoxy)ethyl 2-bromo-2-phenyl acetate.

[0128]

To 22 mL acetone solution of 4.25 g (11.18 mmol) of 2-(bromoacetoxy)ethyl 2-bromo-2-phenyl acetate, 4.02 g (26.83 mmol) of sodium iodide was added at 0°C followed by stirring at the same temperature for 30 minutes.

[0129]

After that, the precipitates were separated by filtration followed by concentration under reduced pressure. Dichloromethane was then added and washing with a saturated aqueous solution of sodium sulfite and water was carried out

and an organic layer was extracted.

[0130]

Then, the extracted solution was dried over anhydrous sodium sulfate followed by concentration under reduced pressure. The obtained crude product was purified by silica gel column chromatography to obtain 2.52 g (yield: 48%) of 2-(iodoacetoxy)ethyl 2-iodo-2-phenylacetate. ^1H NMR (CDCl_3): = 3.66 (s, 2H), 4.34-4.38 (m, 4H), 5.55 (s, 1H), 7.28-7.33 (m, 3H), 7.58-7.60 (m, 2H).

[0131]

<Production of polymer>

Based on the basic reaction described above, production of a living radical polymer was carried out under the following specific reaction conditions. Fig. 2 is a schematic diagram illustrating a process for having a polymer with regard to a method for producing a polymer according to Example. Fig. 3 is a ^1H -NMR chart of a living radical polymerization initiator and each polymer obtained by the method for producing a polymer according to Example, in which (a) represents a structural formula of alkyl iodide as a living radical polymerization initiator, (b) represents a ^1H -NMR chart of the living radical polymerization initiator, (c) represents a ^1H -NMR chart of a polymer P, (d) represents a ^1H -NMR chart of a polymer Q, and (e) represents a ^1H -NMR chart of a polymer R.

[0132]

In the method for producing a polymer according to this Example, all the polymerization reactions were carried out under argon gas atmosphere.

[0133]

To 20 mL (8 M) of butyl methacrylate (BMA), methyl 2-iodo-2-(4'-(2''-iodopropionyloxy)phenyl)acetate (160 mM) and tributylmethyl phosphonium iodide (80 mM) were added and then stirred under heating for 8 hours at 60°C. The polymerization rate (i.e., monomer conversion rate) was 55%.

[0134]

To chilled hexane, the reaction solution was added and the polymer was isolated by re-precipitation. The isolated polymer P has $M_n = 3,900$ and $PDI = 1.15$. According to the NMR measurement, the iodophenyl acetyl part had undergone almost 100% initiation of the polymerization to have a grown polymer. On the other hand, 96% of the iodopropionyl part had no initiation and almost selective growth of a polymer of BMA from the iodophenyl acetyl part was shown.

[0135]

To the polymer P (160 mM), 20 mL (8 M) of methyl methacrylate (MMA) and tributylmethyl phosphonium iodide (80 mM) were added and then stirred under heating for 8 hours at 60°C. The polymerization rate (i.e., monomer conversion rate) of MMA was 30%.

[0136]

To chilled hexane, the reaction solution was added and the polymer was isolated by re-precipitation. The isolated polymer Q has $M_n = 5,800$ and $PDI = 1.24$. According to the NMR measurement, 90% of the iodopropionyl part had no initiation and a block polymer (BMA and MMA) was almost selectively produced from the iodophenyl acetyl part.

[0137]

Furthermore, to the polymer Q (160 mM) obtained in the second reaction step, 20 mL (8 M) of n-butyl acrylate (BA) and tetrabutyl ammonium iodide (320 mM) were added and then stirred under heating for 24 hours at 110°C. The polymerization rate (i.e., monomer conversion rate) of BA was 32%. To chilled hexane, the reaction solution was added and the polymer was isolated by re-precipitation.

[0138]

The isolated polymer R has $M_n = 8,000$ and $PDI = 1.33$. According to the NMR measurement, the polymerization was initiated almost 100% from of the iodopropionyl part. Accordingly, together with growth of a homopolymer of BA, a triblock polymer (BMA, MMA, and BA) was grown from iodophenyl acetyl part.

[0139]

Accordingly, it was possible to synthesize a non-symmetric multi-block polymer of CAB type in which A chain is BMA, B chain is MMA, and C chain is BA.

[0140]

¹H-NMR chart of the polymer P, Q, and R which have been obtained in each step is as shown in (c) to (e) of Fig. 3, respectively.

[0141]

Incidentally, "M" with regard to the concentration indicates mole number based on 1 liter of a monomer. For example, 8 M means that 8 moles are included in 1 liter of a monomer. Incidentally, in case of MMA, 1 liter of a monomer (in bulk) is 8 moles at room temperature.

[0142]

Furthermore, "mM" with regard to the concentration indicates millimole number based on 1 liter of a monomer. For example, 80 mM means that 80 millimoles are included in 1 liter of a monomer.

[0143]

Furthermore, "Mn" indicates number average molecular weight of an obtained polymer.

[0144]

Furthermore, "PDI" indicates the ratio of Mw/Mn.

[0145]

According to the method for producing a polymer of the present invention described in the above, since a living radical polymerization initiator which has, as an initiating group for reaction, two halogen atoms different from each other in

reactivity is used, it is possible to proceed with a different living radical polymerization reaction for each initiating group by suitably adjusting the reaction conditions.

Reference Signs List

[0146]

R¹ Linking group

R² Any one of a halogen atom, an aromatic group, an aliphatic group, and an acyloyl group


X, Y Halogen atom

CLAIMS

[Claim 1]

A method for producing a polymer by using a living radical polymerization initiator represented by the following general formula (1):

[Chemical Formula 1]



in the formula, R^1 represents an organic group which is linkable with two or more other organic groups, and is selected from an aliphatic group having 1 to 12 carbon atoms, an aromatic group, an alkylcarbonyl group having 1 to 12 carbon atoms, an alkoxy carbonyl group having 1 to 12 carbon atoms, an aminocarbonyl group, an alkylaminocarbonyl group having 1 to 12 carbon atoms, a dialkylaminocarbonyl group having 1 to 12 carbon atoms, an arylcarbonyl group, an alkylsulfonyl group having 1 to 12 carbon atoms, an arylsulfonyl group, and an organic group in which two or more of those groups are combined,

R^2 , R^3 , R^4 and R^5 are a hydrogen atom or an organic group selected from an aliphatic group having 1 to 12 carbon atoms, an aromatic group, an alkylcarbonyl group, an alkoxy carbonyl group, an aminocarbonyl group, an alkylaminocarbonyl group, a dialkylaminocarbonyl group having 1 to 12 carbon atoms, an arylcarbonyl group, a carboxy group, an alkylsulfonyl group

having 1 to 12 carbon atoms, and an aryl sulfonyl group,
X and Y are a halogen atom,
m and n are an integer of 1 or more, and
the X and Y are in a state in which they are different
from each other in reactivity with a monomer;

a first polymerization step in which, for only one halogen
atom of the X or Y of the living radical polymerization initiator,
a living radical polymerization reaction in which the living
radical polymerization reaction initiator is mixed with a monomer
with unsaturated bond and the reaction is carried out at a reaction
condition depending on a type of the monomer one or more times
while changing in order the type of the monomer to be mixed to
obtain a first product; and

a second polymerization step in which, for both halogen
atoms of the X and Y contained in the first product, at least
one type of the monomer is subjected to a living radical
polymerization reaction in order at a reaction condition
depending on a type of the monomer to obtain a final product.

[Claim 2]

The method for producing a polymer according to claim 1,
wherein the halogen atom is iodide, chloride, or bromide.

[Claim 3]

The method for producing a polymer according to claim 1

or 2, wherein the first polymerization step and the second polymerization step are carried out by using a catalyst and the first polymerization step and the second polymerization step are carried out such that at least one of reaction temperature and type of the catalyst is changed depending on the type of the monomer.

[Claim 4]

The method for producing a polymer according to claim 3, wherein the catalyst is a transition metal complex-based catalyst which is used for an atom transfer radical polymerization, a catalyst consisting of a compound containing at least one center element selected from phosphorus, nitrogen, carbon, oxygen, germanium, tin, and antimony and a halogen atom bound to the center element, which is used for reversible chain transfer catalyst polymerization, an organic amine compound catalyst used for reversible complexation mediated polymerization, or a catalyst in which, as a non-metal compound having an ionic bond with a halide ion, a non-metal atom in the non-metal compound is in a cation state and forms an ionic bond with the halide ion.

[Claim 5]

The method for producing a polymer according to any one of claims 1 to 4, wherein the first polymerization step and the

second polymerization step are carried out at 180°C or lower.


[Claim 6]

The method for producing a polymer according to any one of claims 1 to 5, wherein the first polymerization step and the second polymerization step are carried out for reaction time of 30 minutes or longer and 24 hours or shorter.

[Claim 7]

A living radical polymerization initiator by using the method for producing a polymer according to any one of claims 1 to 6, represented by the following general formula (1):

[Chemical Formula 1]



in the formula, R¹ represents an organic group which is linkable with two or more other organic groups, and is selected from an aliphatic group having 1 to 12 carbon atoms, an aromatic group, an alkylcarbonyl group having 1 to 12 carbon atoms, an alkoxycarbonyl group having 1 to 12 carbon atoms, an aminocarbonyl group, an alkylaminocarbonyl group having 1 to 12 carbon atoms, a dialkylaminocarbonyl group having 1 to 12 carbon atoms, an arylcarbonyl group, an alkylsulfonyl group having 1 to 12 carbon atoms, an arylsulfonyl group, and an organic

group in which two or more of those groups are combined,

R^2 , R^3 , R^4 and R^5 are a hydrogen atom or an organic group selected from an aliphatic group having 1 to 12 carbon atoms, an aromatic group, an alkylcarbonyl group, an alkoxy carbonyl group, an aminocarbonyl group, an alkylaminocarbonyl group, a dialkylaminocarbonyl group having 1 to 12 carbon atoms, an arylcarbonyl group, a carboxy group, an alkylsulfonyl group having 1 to 12 carbon atoms, and an aryl sulfonyl group,

X and Y are a halogen atom,

m and n are an integer of 1 or more, and

the X and Y are in a state in which they are different from each other in reactivity with a monomer.

[Claim 8]

The living radical polymerization initiator according to claim 7, wherein the halogen atom is iodide, chloride, or bromide.