

DEVICES AND METHODS FOR PATTERN GENERATION BY INK LITHOGRAPHY

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims the benefit of priority to U.S. provisional Patent
5 Application 60/863,248 filed October 27, 2006 and U.S. nonprovisional Patent
Application 11/675,659 filed February 16, 2007, which are hereby incorporated by
reference in their entirety.

BACKGROUND OF THE INVENTION

[0002] The design and fabrication of micrometer sized structures and devices have had
10 an enormous impact on a number of important technologies including microelectronics,
optoelectronics, microfluidics and microsensing. The ability to make micro-sized
electronic devices, for example, has revolutionized the electronics field resulting in faster
and higher performing electronic components requiring substantially less power. As
these technologies continue to rapidly develop, it has become increasingly apparent that
15 additional gains are to be realized by developing the ability to manipulate and organize
matter on the scale of nanometers. Advances in nanoscience and technology promise
to dramatically impact many areas of technology ranging from materials science to
applied engineering to biotechnology.

[0003] Fabrication of devices having nanoscale dimensions is not merely a natural
20 extension of the concept of miniaturization, but a fundamentally different regime in which
physical and chemical behavior deviates from larger scale systems. For example, the
behavior of nanoscale assemblies of many materials is greatly influenced by their large
interfacial volume fractions and quantum mechanical effects due to electronic
confinement. The ability to make structures having well-defined features on the scale of
25 nanometers has opened up the possibility of making devices based on properties and
processes only occurring at nanometer dimensions, such single-electron tunneling,
Coulomb blockage and quantum size effect. The development of commercially practical
methods of fabricating sub-micrometer sized structures from a wide range of materials,
however, is critical for continued advances in nanoscience and technology.

[0004] Photolithography is currently the most prevalent method of microfabrication, and
30 nearly all integrated electronic circuits are made using this technique. In conventional

projection mode photolithography, an optical image corresponding to a selected two dimensional pattern is generated using a photomask. The image is optically reduced and projected onto a thin film of photoresist spin coated onto a substrate. Alternatively, in Direct Write to Wafer photolithographic techniques, a photoresist is directly exposed to laser light, an electron beam or ion beam without the use of a photomask. Interaction between light, electrons and/or ions and molecules comprising the photoresist chemically alters selected regions of the photoresist in a manner enabling fabrication of structures having well defined physical dimensions. Photolithography is exceptionally well suited for generating two-dimensional distributions of features on flat surfaces. In addition, photolithography is capable of generating more complex three dimensional distributions of features on flat surfaces using additive fabrication methods involving formation of multilayer stacks.

[0005] Recent advances in photolithography have extended its applicability to the manufacture of structures having dimensions in the submicron range. For example, nanolithographic techniques, such as deep UV projection mode lithography, soft X-ray lithography, electron beam lithography and scanning probe methods, have been successfully employed to fabricate structures with features on the order of 10s to 100s of nanometers. Although nanolithography provides viable methods of fabricating structures and devices having nanometer dimensions, these methods have certain limitations that hinder their practical integration into commercial methods providing low cost, high volume processing of nanomaterials. First, nanolithographic methods require elaborate and expensive steppers or writing tools to direct light, electrons and/or ions onto photoresist surfaces. Second, these methods are limited to patterning a very narrow range of specialized materials, and are poorly suited for introducing specific chemical functionalities into nanostructures. Third, conventional nanolithography is limited to fabrication of nanosized features on small areas of ultra-flat, rigid surfaces of inorganic substrates and, thus is less compatible with patterning on glass, carbon and plastic surfaces. Finally, fabrication of nanostructures comprising features having selectable lengths in three dimensions is difficult due to the limited depth of focus provided by nanolithographic methods, and typically requires labor intensive repetitive processing of multilayers.

[0006] The practical limitations of photolithographic methods as applied to nanofabrication have stimulated substantial interest in developing alternative, non-photolithographic methods for fabricating nanoscale structures. In recent years, new

techniques based on molding, contact printing and embossing collectively referred to as soft lithography have been developed,. These techniques use a conformable patterning device, such as a stamp, a mold or mask, having a transfer surface comprising a well defined relief pattern. Microsized and nanosized structures are formed by material processing involving conformal contact on a molecular scale between the substrate and the transfer surface of the patterning device. Patterning devices used in soft lithography typically comprise elastomeric materials, such as poly(dimethylsiloxane) (PDMS), and are commonly prepared by casting prepolymers against masters generated using conventional photolithography. The mechanical characteristics of the patterning devices are critical to the fabrication of mechanically robust patterns of transferred materials having good fidelity and placement accuracy.

[0007] Soft lithographic methods capable of generating microsized and/or nanosized structures include nanotransfer printing, microtransfer molding, replica molding, micromolding in capillaries, near field phase shift lithography, and solvent assisted micromolding. Conventional soft lithographic contact printing methods, for example, have been used to generate patterns of self assembled monolayers of gold having features with lateral dimensions as small as about 250 nm. Structures generated by soft lithography have been integrated into a range of devices including diodes, photoluminescent porous silicon pixels, organic light emitting diodes and thin-film transistors. Other applications of this technology generally include the fabrication of flexible electronic components, microelectromechanical systems, microanalytical systems and nanophotonic systems.

[0008] Soft lithographic methods for making nanostructures provide a number of benefits important to fabricating nanoscale structures and devices. First, these methods are compatible with a wide range of substrates, such as flexible plastics, carbonaceous materials, ceramics, silicon and glasses, and tolerate a wide range of transfer materials, including metals, complex organic compounds, colloidal materials, suspensions, biological molecules, cells and salt solutions. Second, soft lithography is capable of generating features of transferred materials both on flat and contoured surfaces, and is capable of rapidly and effectively patterning large areas of substrate. Third, soft lithographic techniques are well-suited for nanofabrication of three dimensional structures characterized by features having selectably adjustable lengths in three-dimensions. Finally, soft lithography provides low cost methods which are potentially adaptable to existing commercial printing and molding techniques.

[0009] Although conventional PDMS patterning devices are capable of establishing reproducible conformal contact with a variety of substrate materials and surface contours, use of these devices for making features in the sub-100 nm range are subject to problems associated with pressure induced deformations due to the low modulus (3MPa) and high compressibility (2.0 N/mm^2) of conventional single layer PDMS stamps and molds. First, at aspect ratios less than about 0.3, conventional PDMS patterning devices having wide and shallow relief features tend to collapse upon contact with the surface of the substrate. Second, adjacent features of conventional single layer PDMS patterning devices having closely spaced ($< \text{about } 200 \text{ nm}$), narrow ($< \text{about } 200 \text{ nm}$) structures tend to collapse together upon contact with a substrate surface. Finally, conventional PDMS stamps are susceptible to rounding of sharp corners in transferred patterns when a stamp is released from a substrate due to surface tension. The combined effect of these problems is to introduce unwanted distortions into the patterns of materials transferred to a substrate. To minimizing pattern distortions caused by conventional single layer PDMS patterning devices, composite patterning devices comprising multilayer stamps and molds have been examined as a means of generating structures having dimensions less than 100 nm.

[0010] Michel and coauthors report microcontact printing methods using a composite stamp composed of a thin bendable layer of metal, glass or polymer attached to an elastomeric layer having a transfer surface with a relief pattern. [Michel et al. Printing Meets Lithography: Soft Approaches to High Resolution Patterning, IBM J. Res. & Dev., Vol. 45, No. 5, pgs 697 – 719 (Sept. 2001). These authors also describe a composite stamp design consisting of a rigid supporting layer and a polymer backing layer comprising a first soft polymer layer attached to a second harder layer having a transfer surface with a relief pattern. The authors report that the disclosed composite stamp designs are useful for “large area, high-resolution printing applications with feature sizes as small as 80 nm.”

[0011] Odom and coauthors disclose a composite, two layer stamp design consisting of a thick ($\approx 3 \text{ mm}$) backing layer of 184 PDMS attached to a thin (30 – 40 microns), layer of *h*-PDMS having a transfer surface with relief patterns . [Odem et al., Langmuir, Vol. 18, pgs 5314 – 5320 (2002). The composite stamp was used in this study to mold features having dimensions on the order of 100 nm using soft lithography phase shifting photolithography methods. The authors report that the disclosed composite stamp

exhibits increase mechanical stability resulting in a reduction in sidewall buckling and sagging with respect to conventional low modulus, single layer PDMS stamps.

[0012] Although use of conventional composite stamps and molds have improved to some degree the capabilities of soft lithography methods for generating features having dimensions in the sub-100 nm range, these techniques remain susceptible to a number of problems which hinder their effective commercial application for high throughput fabrication of micro-scale and nanoscale devices. First, some conventional composite stamp and mold designs have limited flexibility and, thus, do not make good conformal contact with contoured or rough surfaces. Second, relief patterns of conventional, multimaterial PDMS stamps are susceptible to undesirable shrinkage during thermal or ultraviolet curing, which distort the relief patterns on their transfer surfaces. Third, use of conventional composite stamps comprising multilayers having different thermal expansion coefficients can result in distortions in relief patterns and curvature of their transfer surfaces induced by changes in temperature. Fourth, use of stiff and/or brittle backing layers, such as glass and some metal layers, prevents easy incorporation of conventional composite stamps into preexisting commercial printer configurations, such as rolled and flexographic printer configurations. Finally, use of composite stamps having transfer surfaces comprising high modulus elastomeric materials impede formation of conformal contact between a transfer surface and a substrate surface necessary for high fidelity patterning.

[0013] It will be appreciated from the foregoing that there is currently a need in the art for methods and devices for fabricating high resolution patterns of structures having features on the scale of 10s to 100s of nanometers. Specifically, soft lithography methods and patterning devices are needed which are capable of fabricating patterns of nanoscale structures having high fidelity, good mechanical robustness and good placement accuracy. In addition, patterning devices are needed that minimize pattern distortions, for example by reducing relief pattern shrinkage during thermal or ultraviolet curing and/or minimizing temperature induced distortions as compared to conventional patterning devices. Finally, soft lithography methods and devices are needed that are compatible with and can be easily integrated into preexisting high speed commercial printing and molding systems.

[0014] Optical lithography, also commonly referred to as photolithography, is a widely used technique for patterning substrate surfaces with micro- and nano-sized structures,

such as functional materials (e.g. semiconductors, conductors and dielectrics) for electronic device components. Application of this technique in the field of microelectronics has been successfully implemented over the past several decades for the manufacture of microchips, integrated electronic circuits and printed circuit boards.

5 Optical lithography has also been applied to making structures useful for a diverse range of other technologies, including macroelectronics; microfluidics; microelectromechanical systems (MEMS) and nanoelectromechanical systems (NEMS); photovoltaics; and biological sensors and microarrays.

[0015] Conventional optical lithography involves selectively patterned illumination of specific regions of a photoresist layer deposited on a substrate surface. In this technique, selectively patterned illumination of the photoresist is accomplished using a photomask, commonly referred to as a photoretic, in combination with an appropriate optical source, such that the photoresist is exposed to visible and/or ultraviolet electromagnetic radiation having a selected two-dimensional spatial distribution.

15 Commonly used photomasks for manufacture of semiconductor devices are transparent fused quartz substrates having a pattern of thin metal films which is capable of generating transmitted or reflected electromagnetic radiation having a well defined, selected two dimensional spatial distribution of intensities corresponding to a desired device geometry. The composition of the photoresist is selected such that it undergoes chemical and/or physical changes confined to regions exposed to electromagnetic radiation from the photomask. After exposure, photoresist processing (or development) removes photoresist material so as to generate patterns in the photoresist corresponding to regions of the photoresist exposed (or not exposed) to electromagnetic radiation. Photoresists are commonly referred to as "positive" or "negative" depending on whether photoresist remains after developing in a masked region. In some device fabrication applications, patterns generated in the photoresist expose the underlying substrate, thereby allowing localized access to regions of the substrate for subsequent processing, for example via etching, deposition and/or doping steps.

20

25

[0016] Optical sources, photomasks and resist materials have evolved tremendously over the last several decades such that optical lithography currently provides a robust, versatile and high-throughput manufacturing platform critical to a large number of micro- and nanofabrication applications. Despite widespread acceptance and implementation of this technique, optical lithography is susceptible to a number of limitations arising from the mechanical and optical properties of conventional photomasks. First, many

30

conventional photomasks are only capable of photoresist illumination that is described as "black-and-white," wherein the optical properties of the photomask are selected to provide selected regions of the photoresist with uniform intensities of electromagnetic radiation and to substantially prevent exposure of other regions to electromagnetic radiation. This "all-or-none" exposure generates patterns of uniform height (or depth) in the photoresist. To generate features having varying height (or depth) requires multiple photoresist deposition, exposure and alignment steps. Accordingly, there is currently a need in the field of optical lithography for methods capable of generating complex three-dimensional patterns in a one-step process that is relatively simple while ensuring high pattern fidelity and feature accuracy. Second, many conventional photomasks are made up of mechanically rigid materials, such as borosilicate glass and fused silica. As these photomasks are often provided in planar configurations, they are not compatible with patterning substrates having nonplanar (e.g., curved) and/or rough surfaces.

[0017] There have been a number of approaches for "gray-scale" pattern generation using scanning lasers, micromirror projection displays, high-energy beam-sensitive glass photomasks (U.S. Pat. No. 6,524,756), ultra-high-resolution halftone photomasks, and metal-on-glass photomasks. Those techniques, however, are relatively complicated and/or costly and can add significant increases in manufacturing process time while permitting only limited gray-scale pattern generation.

[0018] The present invention combines soft lithography techniques with a radiation-absorbing patterning agent (e.g., an "ink") to obtain gray-scale pattern generation that is particularly compatible with developed photolithographic tools and processes used by most of the microelectronics industry. Soft lithography uses soft elastomers, molds or phase masks to form reversible, non-destructive conformal contact to affect pattern transfer (see U.S. Pub. No. 2005/0238967). Relief structures on the elastomer surface are used for printing, molding, and transferring material to form target shapes. Conformal contact of elastomer relaxes the requirement of ultraflat surface for patterning and allows precise transfer of relief shape. Ink lithography makes the best use of conventional photolithography and soft lithography to form a binary amplitude mask which has conformal contact and is deformable (e.g., stretchable, compressible) to ideally fit a flat and/or non-flat substrate for photolithography.

[0019] Gray-scale photolithography using a microfluidic photomask has been generally described. Chen et al., PNAS 100(4) 1499-1504 (2003). Chen et al., however, suffers

from being a relatively complex system to employ, requiring additional steps and equipment not required by the present invention, and so is less compatible with preexisting photolithography processes.

[0020] The ink lithography process can compliment some of the weaknesses associated with conventional photolithography. One advantage of ink lithography is that it is compatible with the developed photolithographic tools and processes adopted by most of the microelectronics industry. The invention is also useful for generating and/or placing electronic components on flexible and bendable plastic substrates. The conformal contact promises precise patterning on this class of substrate. Moreover, the stretchability of an elastomer mask with an embedded lock and key features permits alignment of pre-existing patterns. Especially after complex processing on plastic substrate, unexpected misfit due to thermal expansion or residual strain makes it impossible to align precisely. Uniform plastic elongation, however, can give some degree of self-alignment by anchoring elastomer mask to pre-patterned substrate. Low viscosity ink facilitates filling of deformed pockets on the three-dimensional surface of an elastomer mask. The ink itself can be a lubricant in its lock and key aligning process. Multilevel mask modulating thickness of trapped ink which can control the level of transmission allows generation of complex 3D structures with a single exposure.

[0021] Ink lithography has the advantage of conformality and stretchability without the requirement of an ultraflat surface. A relatively cheap elastomer mask can generate hundreds of identical replicas over a large area from a single master pattern. Trapped ink in relief structures offers intensity contrast enough for patterning arbitrary shapes as with conventional photolithography. Also, free flow of ink can fill deformed relief shapes fully. This aspect forms a fully stretchable binary amplitude mask that cannot be realized with other techniques.

SUMMARY OF THE INVENTION

[0022] The present invention provides methods, devices and device components for fabricating patterns on substrate surfaces, particularly patterns comprising structures having microscaled and/or nanosized features of selected lengths in one, two or three dimensions. Specifically, the present invention provides stamps, molds and photomasks used in soft lithography fabrication methods for generating high resolution patterns of structures on flat and contoured surfaces, including surfaces having a large radius of curvature on a wide variety of substrates, including flexible plastic substrates.

It is an object of the present invention to provide methods and devices for fabricating three-dimensional structures having well defined physical dimensions, particularly structures comprising well defined features having physical dimensions on the order of 10s of nanometers to 1000s of nanometers. It is another object of the present invention to provide methods, devices and device components for fabricating patterns of structures characterized by high fidelity over large substrate surface areas and good placement accuracy. It is further an object of the present invention to provide composite patterning devices which exhibit better thermal stability and resistance to curing induced pattern distortion than conventional single layer or multilayer stamps, molds and photomasks. It is another object of the present invention to provide soft lithography methods, devices and device components that are compatible with existing high speed commercial printing, molding and embossing techniques, devices and systems.

[0023] In one aspect, the present invention provides patterning devices comprising a plurality of polymer layers each having selected mechanical properties, such as Young's Modulus and flexural rigidity, selected physical dimensions, such as thickness, surface area and relief pattern dimensions, and selected thermal properties, such as coefficients of thermal expansion, to provide high resolution patterning on a variety of substrate surfaces and surface morphologies. Patterning devices of this aspect of the present invention include multilayer polymer stamps, molds and photomasks useful for a variety of soft lithographic patterning applications including contact printing, molding and optical patterning. In one embodiment, discrete polymer layers having different mechanical properties, physical dimensions and thermal properties are combined and/or matched to provide patterning devices having cumulative mechanical and thermal properties providing enhanced pattern resolution and fidelity, and improved thermal stability over conventional soft lithography devices. In addition, patterning devices of the present invention comprising a combination of discrete polymer layers tolerate a wide variety of device configurations, positions and orientations without fracture which make them more easily integrated into existing commercial printing, molding and optical patterning systems than conventional single layer or multiple layer stamps, molds and photomasks.

[0024] In one embodiment, the present invention provides a composite patterning device comprising a first polymer layer having a low Young's modulus and a second polymer layer having a high Young's modulus. The first polymer layer comprises a selected three-dimensional relief pattern having at least one contact surface disposed thereon and has an internal surface opposite the contact surface. The second polymer

layer has an external surface and an internal surface. First and second polymer layers are arranged such that a force applied to the external surface of the second polymer layer is transmitted to the first polymer layer. For example, first and second polymer layers may be arranged such that a force applied to the external surface of the second layer is transmitted to at least a portion of the contact surface(s) of the first polymer layer. In an embodiment, the internal surface of the first polymer layer is operationally coupled to the internal surface of the second polymer layer. For example, the internal surface of the first polymer layer may be in physical contact with the internal surface of the second polymer layer. Alternatively, the first polymer layer and the second polymer layer may be connected by one or more connecting layers, such as thin metal layers, polymer layers or ceramic layers, positioned between the internal surface of the first polymer layer and the internal surface of the second polymer layer.

[0025] Composite patterning devices of this aspect of the present invention are capable of establishing conformal contact between at least a portion of the contact surface(s) of the first polymer layer and the substrate surface undergoing patterning. Optionally, the second polymer layer may be operationally coupled to an actuator, such as a stamping, printing or molding device, capable of providing an external force to the external side of the second polymer layer so as to bring the patterning device into conformal contact with the substrate surface undergoing patterning. Optionally, the substrate may be operationally coupled to an actuator, capable of bringing the substrate into conformal contact with the patterning device.

[0026] Selection of the physical dimensions and Young's modulus of polymer layers in composite patterning devices of the present invention establishes the overall mechanical properties of the composite patterning device, such as the net flexural rigidity and conformability of the patterning device. In an embodiment of the present invention useful for soft lithographic contact printing and molding applications, including but not limited to soft ink lithographic contact printing and molding applications, the first polymer layer is characterized by a Young's modulus selected over the range of about 1 MPa to about 10 MPa and a thickness selected over the range of about 1 micron to about 100 microns, and the second polymer layer is characterized by a Young's modulus selected over the range of about 1 GPa to about 10 GPa and a thickness selected over the range of about 10 microns to about 100 microns. Composite patterning devices of the present useful for soft lithographic contact printing applications also include embodiments wherein the ratio of the thickness of the first polymer layer

and the thickness of the second polymer layer is selected from the range of about 1 to about 10, preferably equal to about 5 for some applications. In one embodiment, the first polymer is an elastomeric layer, such as a PDMS or h-PDMS layer, the second polymer layer is a thermoplastic or thermoset layer, such as a polyimide layer, and the composite patterning device has a net flexural rigidity selected from the range of about 1×10^{-7} Nm to about 1×10^{-5} Nm.

[0027] Use of a low modulus first polymer layer, such as an elastomer layer, is beneficial in the present invention because it provides patterning devices having the capability to establish conformal contact with large areas (up to several m^2) of smooth surfaces, flat surfaces, rough surfaces, particularly surfaces having roughness amplitudes up to about 1 micron, and contoured surfaces, preferably surfaces having radii of curvature up to about 25 microns. In addition, use of a low modulus first polymer layer allows conformal contact to be established between the contact surface(s) and large areas of substrate surface using relative low pressures (about 0.1 kN m^{-2} to about 10 kN m^{-2}) applied to the external surface of the second polymer layer. For example, a low modulus first polymer layer comprising a PDMS layer having a thickness greater than or equal to about 5 microns establishes reproducible conformal contact over substrate surface areas as large as 250 cm^2 upon application of external pressures less than or equal to about 100 N m^{-2} . In addition, incorporation of a low modulus first polymer layer into patterning devices of the present invention allows conformal contact to be established in a gradual and controlled manner, thus, avoiding the formation of trapped air pockets between the contact surface of the first layer and a substrate surface. Further, incorporation of a low modulus first polymer layer provides good release characteristics of contact surfaces from substrate surfaces and the surfaces of master relief patterns used to make composite patterning devices of the present invention.

[0028] Use of a high modulus second polymer layer in patterning devices of the present invention is beneficial because it provides patterning devices having a net flexural rigidity large enough to minimize distortions of the relief pattern which may occur upon formation of conformal contact between the contact surface(s) and a substrate surface. First, incorporation of a high modulus second polymer layer into patterning devices of the present invention minimizes distortions of the relief pattern in planes parallel to a plane containing the contact surface, such as distortions characterized by the collapse of narrow relief features of patterns having high aspect ratios. Second,

incorporation of a high modulus second polymer layer minimizes distortions of the relief pattern in planes which intersect a plane containing the contact surface, such as distortions characterized by sagging of recessed regions of a relief pattern. This reduction in relief pattern distortion provided by incorporation of a high modulus second polymer layer allows patterns of small structures comprising well defined features having physical dimensions as small as 50 nanometers to be fabricated using patterning devices and methods of the present invention.

[0029] Use of a high modulus second polymer layer in patterning devices of the present invention is also beneficial because it allows for easy handling and incorporation of patterning devices of the present invention into printing, embossing and molding machines. This attribute of the present invention facilitates mounting, remounting, orienting, maintaining and cleaning of the present patterning devices. Incorporation of a high modulus second polymer layer also improves the accuracy in which patterning devices of the present invention may be brought into contact with a selected region of a substrate surface by a factor of 25 with respect to conventional single layer PDMS stamps, molds and photomasks. For example, incorporation of a 25 micron thick second polymer layer having a Young's modulus equal to or greater than 5 GPa, such as a polyimide layer, allows patterning devices of the present invention to be brought into contact with a substrate surface with a placement accuracy equal to about 1 micron over a substrate area equal to about 232 cm². Further, use of a flexible and resilient, high modulus second polymer layer allows patterning devices of the present invention to be operated in a range of device configurations and easily integrated into conventional printing and molding systems. For example, use of a second polymer layer having a flexural rigidity of about 7×10^{-6} Nm allows integration of patterning devices of the present invention into conventional roller and flexographic printing systems.

[0030] In an alternative embodiment, a patterning device of the present invention comprises a unitary polymer layer. The unitary polymer layer comprises a three-dimensional relief pattern having at least one contact surface disposed thereon and a base having an external surface positioned opposite to the contact surface. The contact surface is oriented orthogonal to a layer alignment axis extending through the polymer layer, and the Young's modulus of the polymer layer varies continuously along the layer alignment axis from the contact surface to the external surface of the base. In one embodiment, the Young's modulus of the polymer layer varies continuously along the layer alignment axis from a low value at the contact surface to a high value at the mid

point between the contact surface and the external surface along the layer alignment axis. In another embodiment, the Young's modulus of the polymer layer varies continuously from a high modulus value at the mid point between the contact surface and the external surface along the layer alignment axis to a low modulus value at the external surface of the base. Optionally, the polymer layer may also have a substantially symmetrical distribution of the coefficients of thermal expansion about the center of the patterning device along the layer alignment axis. Variation of the Young's modulus in the polymer layer may be achieved by any means known in the art including methods wherein the extent of cross linking in the unitary polymer layer is selectively varied to achieve control of the Young's modulus as a function of position along the layer alignment axis.

[0031] Three-dimensional relief patterns useable in the present invention may comprise a singular continuous relief feature or a plurality of continuous and/or discrete relief features. In the present invention, selection of the physical dimensions of relief features or their arrangement in a relief pattern is made on the basis of the physical dimensions and relative arrangements of the structures to be generated on a substrate surface. Relief patterns useable in composite patterning devices of the present invention may comprise relief features having physical dimensions selected over the range of about 10 nanometers to about 10,000 nanometers, preferably selected over the range of about 50 nanometers to about 1000 nanometers for some applications. Relief patterns useable in the present invention may comprise symmetrical patterns of relief features or asymmetrical patterns of relief features. Three-dimensional relief patterns may occupy a wide range of areas, and relief areas selected over the range of about 10 cm² to about 260 cm² are preferred for some micro- and nanofabrication applications.

[0032] In another embodiment, a composite patterning device of the present invention further comprises a third polymer layer having an internal surface and an external surface. In this three layer embodiment, the first, second and third polymer layers are arranged such that a force applied to the external surface of the third polymer layer is transmitted to the first polymer layer. For example, first, second and third polymer layers may be arranged such that a force applied to the external surface of the third layer is transmitted to at least a portion of the contact surface(s) of the first polymer layer. In an embodiment, the external surface of the second polymer layer is operationally coupled to the internal surface of the third polymer layer. For example, the external surface of the second polymer layer may be in physical contact with the internal

surface of the third polymer layer. Alternatively, the second polymer layer and the third polymer layer may be connected by one or more connecting layers, such as thin metal layers, polymer layers or ceramic layers, positioned between the external surface of the second polymer layer and the internal surface of the third polymer layer. Optionally, the third polymer layer may be operationally coupled to an actuator capable of providing an external force to the external side of the third polymer layer so as to bring the contact surface(s) of the patterning device into conformal contact with the substrate surface undergoing patterning. Incorporation of a third polymer layer may also provide a means of handing, positioning, orienting, mounting, cleaning and maintaining composite patterning devices of the present invention.

[0033] Incorporation of a third polymer layer having a low young's modulus into composite patterning devices of the present invention is beneficial for some soft lithography applications. First, use of a low Young's modulus third polymer layer allows the force applied to the patterning device to be applied in a gradual and controlled manner, facilitating generation of conformal without formation of trapped air bubbles. Second, integration of a low Young's modulus third polymer layer provides an effective means of uniformly distributing a force applied to the patterning device to the contact surface(s) of the first polymer layer. Uniform distribution of the force applied to the patterning device to the contact surface(s) promotes formation of conformal contact over large areas of the substrate surface and enhances the fidelity of patterns generated on a substrate surface. In addition, uniform distribution of the force applied to the patterning device to the contact surface(s) improves the overall efficiency and energy consumption of the patterning process. An exemplary third polymer layer has a thickness which is several times thicker than the roughness and/or radius of curvature of the substrate surface.

[0034] In another aspect, the present invention provides thermally stable composite patterning devices that undergo less thermal induced pattern distortion than conventional single layer and multiple layer stamps, molds and photomasks. Some materials having a low Young's modulus are also characterized by a large coefficient of thermal expansion. For example, PDMS has a Young's modulus of 3 MPa and a coefficient of thermal expansion equal to about 260 ppm. Increases or decreases of temperature, therefore, can result in substantial distortions in relief patterns comprising these materials, particularly for patterning devices having large area relief patterns. Relief pattern distortions caused by changes in temperature may be especially

problematic for applications involving fabrication of patterns of structures having features with very small dimensions, such as submicron sized structures, over large areas of substrate

[0035] In one aspect of the present invention, a plurality of layers having different mechanical properties and/or thermal expansion coefficients are combined and matched in a manner providing patterning devices exhibiting high thermal stability. In another aspect of the present invention, a plurality of layers are combined such that the net thermal expansion properties of the patterning device is matched to the thermal expansion properties of the substrate, preferably matched to within 10% or better for some applications. In the context of the present description, "high thermal stability" refers to patterning devices exhibiting minimal pattern distortions upon changes in temperature. Composite patterning devices of the present invention having high thermal stability exhibit reduced deformation of relief patterns and contact surfaces caused by stretching, bowing, buckling, expansion and compression induced by changes in temperature, as compared to conventional single layer and multilayer stamps, molds and photomasks. In one embodiment, a high modulus second polymer layer having a low coefficient of thermal expansion, such as a polyimide layer, is operationally coupled to the internal surface of a low modulus first polymer layer having a large coefficient of thermal expansion, such as a PDMS layer or a h-PDMS layer. In this arrangement, integration of a second polymer layer having a high modulus and low coefficient of thermal expansion constrains expansion or contraction of the first polymer layer and, therefore, significantly decreases the extent of stretching or compression of the contact surface(s) and three-dimensional relief pattern induced by increases or decreases in temperature. In one embodiment of this aspect of the present invention, the second polymer layer has a coefficient of thermal expansion less than or equal to about 14.5 ppm and, optionally a thickness that is about five times larger than the thickness of the first layer.

[0036] In the present invention, good thermal stability may also be achieved by incorporation of a discontinuous low modulus first layer operationally coupled to a high modulus second layer, preferably a high modulus layer having a low thermal expansion coefficient. In one embodiment, the discontinuous low modulus layer is a three dimensional relief pattern comprising a plurality of discrete relief features. Discrete relief features comprising the low modulus layer are not in contact with each other but are each operationally coupled to the high modulus layer. For example, the pattern of

discrete relief features may comprise a pattern of individual islands of low modulus material on the internal surface of the high modulus layer. Incorporation of a first low modulus layer comprising a plurality of discrete relief features into composite patterning devices of the present invention is beneficial because it decreases the extent of the mismatch between thermal expansion properties of the low modulus and high modulus layers. In addition, use of a discontinuous low modulus layer decreases the net amount of material having a high coefficient of thermal expansion, which decreases the net extent of expansion or contraction induced by a change in temperature. In an exemplary embodiment, the discontinuous low modulus layer comprises an elastomer, such as PDMS or h-PDMS, and the high modulus layer comprises polyimide.

[0037] In another embodiment of the present invention providing patterning devices having good thermal stability, a plurality of layers are arranged so as to provide a substantially symmetrical distribution of coefficients of thermal expansion, thicknesses or both about the center of the patterning device along a layer alignment axis extending through the patterning device, for example a layer alignment axis positioned orthogonal to the contact surface. In an alternative embodiment also exhibiting good thermal stability, a temperature compensated patterning device of the present invention comprises a unitary polymer layer having a substantially symmetrical distribution of coefficients of thermal expansion about the center of the patterning device along a layer alignment axis extending through the patterning device, for example positioned orthogonal to the contact surface.

[0038] The symmetrical distribution of coefficients of thermal expansion, thicknesses or both in these configurations provides a means of compensating for the thermal expansion or compression of one or more layers. The result of this compensation scheme is to minimize buckling, bowing, elongation and compression of the relief pattern induced by changes in temperature. Particularly, a symmetrical distribution of coefficients of thermal expansion and layer thicknesses generates opposing forces having approximately the same magnitude but opposite directions upon a change in temperature. Accordingly, this temperature compensation scheme is used to minimize the magnitude of forces generated upon a change in temperature which act on the contact surface, relief features and three-dimensional relief pattern of the first layer.

[0039] An exemplary temperature compensated patterning device of the present invention comprises three layers having mechanical and physical properties selected to

provide a substantially symmetrical distribution of thermal expansion coefficients about the center of the device. The first layer comprises a three-dimensional relief pattern having at least one contact surface disposed thereon and an internal surface positioned opposite the contact surface. The first layer also has a low Young's modulus, for example ranging from about 1 MPa to about 10 MPa. The second layer has an internal surface and an external surface, and a high Young's modulus, for example ranging from about 1 GPa to about 10 GPa. The third layer has an internal surface and an external surface. In this three layer embodiment, the first, second and third layers are arranged such that a force applied to the external surface of the third layer is transmitted to the contact surface of the first layer. The thicknesses and thermal expansion coefficients of the first and third layers may be selected to provide a substantially symmetrical distribution of the coefficients of thermal expansion about the center of the patterning device along a layer alignment axis extending through said patterning device, such as a layer alignment axis positioned orthogonal to a plane encompassing at least one contact surface.

[0040] An exemplary three layer composite patterning device exhibiting high thermal stability comprises a PDMS first layer, a polyimide second layer and a PDMS third layer. In this embodiment, the thickness of first and third PDMS layers may be substantially equal, for example within 10% of each other, to provide a substantially symmetrical distribution of coefficients of thermal expansion about the center of the device along a layer alignment axis extending orthogonal to the contact surface. In this embodiment, pattern distortions across a 1 cm² relief pattern less than 150 nanometers for a change in temperature of 1 K are observed for three layer patterning devices of the present invention having first and third PDMS layers comprising the same material, having thicknesses equal to about 5 microns and separated by an approximately 25 micron thick polyimide layer. In an embodiment of the present invention having matched first and third layers providing a substantially symmetrical distribution of coefficients of thermal expansion, the ratio of the relief depth to the thickness of the first layer is kept small (e.g. less than or equal to 0.10) to avoid unwanted temperature induced thermal expansion or contraction corresponding to thermal coefficient mismatching in recessed regions of the relief pattern.

[0041] In another aspect, the present invention provides composite patterning devices that undergo less pattern distortion caused by polymerization and curing during fabrication than conventional single layer and multiple layer stamps, photomasks and

molds. Many polymers, such as PDMS, undergo a significant decrease in their physical dimensions upon polymerization. As relief patterns used in patterning devices are typically fabricated by initiating polymerization of a prepolymer in contact with a master relief surface, such as a master relief surface generated by conventional photolithography methods, this shrinkage may significantly distort the physical dimensions of relief patterns and contact surfaces of patterning devices comprising polymeric materials, particularly elastomers.

[0042] The present invention provides multilayer stamp designs that are less susceptible to deformations caused by polymerization and curing during fabrication.

Composite patterning devices of the present invention having decreased susceptibility to curing induced deformations of relief patterns and contact surfaces exhibit less stretching, bowing, buckling, expansion and compression induced by polymerization reactions during fabrication, as compared to conventional single layer and multilayer stamps, molds and photomasks. In one embodiment, a plurality of polymer layers having specific mechanical and thermal expansion characteristics are combined and/or matched in a manner decreasing the net extent of pattern distortion generated upon polymerization and curing during fabrication.

[0043] A composite patterning device of the present invention having decreased sensitivity to curing induced deformations of relief patterns and contact surfaces further comprises third and fourth polymer layers, each have internal surfaces and external surfaces. In this four layer embodiment, the first, second, third and fourth polymer layers are arranged such that a force applied to the external surface of the fourth polymer layer is transmitted to the contact surface of the first polymer layer. For example, first, second, third and fourth polymer layers may be arranged such that a force applied to the external surface of the fourth layer is transmitted to at least a portion of the contact surfaces of the first polymer layer. In an embodiment, the external surface of the second polymer layer is operationally coupled to the internal surface of the third polymer layer and the external surface of the third polymer layer is operationally coupled to the internal surface of the fourth polymer layer. Improved resistance to curing and/or polymerization induced distortion may be provided by matching the thicknesses, coefficients of thermal expansion and Young's modulus of the first and third layers and by matching the thicknesses, coefficients of thermal expansion and Young's modulus of the second and fourth layers. The net result of this matched multilayer design is to decrease the extent of curing induced distortions by a factor of

about 10 relative to conventional single layer or double layer stamps, molds and photomasks.

[0044] Patterning devices (including composite patterning devices) of the present invention may be fully optically transmissive or partially optically transmissive, particularly with respect to electromagnetic radiation having wavelengths in the ultraviolet and/or visible regions of the electromagnetic spectrum. Patterning devices which transmit visible light are preferred for some applications because they can be visually aligned with a substrate surface. Patterning devices of the present invention may transmit one or more patterns of electromagnetic radiation onto the substrate surface characterized by selected two dimensional distributions of intensities, wavelengths, polarization states or any combination of these. The intensities and wavelengths of electromagnetic radiation transmitted by patterning devices of the present invention may be controlled by introduction of materials into the polymer layers having selected absorption properties, scattering properties and/or reflection properties. In an exemplary embodiment, the patterning device is a partially transparent optical element characterized by a selected two dimensional distribution of absorption coefficients, extinction coefficients, reflectivities or any combination of these parameters. An advantage of this design is that it results in a selected two dimensional distribution of the intensities and wavelengths electromagnetic radiation transmitted to the substrate upon illumination by an optical source, such as a broad band lamp, atomic lamp, blackbody source or laser. In an embodiment, the selected two dimensional distribution is generated by the presence of a patterning agent localized to recess features on the three-dimensional polymer surface.

[0045] In one embodiment, the present invention comprises an optically transmissive mold capable of transmitting electromagnetic radiation for inducing polymerization reactions in a transfer material or a patterning agent disposed between the relief pattern of the first layer of the patterning device and the substrate surface. In another embodiment, the present invention comprises an optically transmissive photomask capable of transmitting a pattern of electromagnetic radiation on to a substrate surface in conformal contact with the contact surface of the first layer of the patterning device. In another embodiment, the present invention comprises an optically transmissive stamp capable of illuminating materials transferred to the surface of a substrate.

[0046] The present invention provides highly versatile patterning devices that may be used in a wide range of soft lithography methods, microfabrication methods and nanofabrication methods. Exemplary fabrication methods compatible with the patterning devices of the present invention include, but are not limited to, nanotransfer and/or microtransfer printing, nanotransfer and/or microtransfer molding, replica molding, nanomolding and micromolding in capillaries, near field phase shift lithography, and solvent assisted nanomolding and micromolding. In addition, patterning devices of the present invention are compatible with a wide variety of contact surface orientations including but not limited to planar, contoured, convex and concave contact surface configurations, which allow their integration into many different printing, molding and masking systems. In some applications, the coefficient of thermal expansion and thickness of polymer layers comprising a patterning device of the present invention are selected such that the net thermal expansion properties of the patterning device matches the thermal expansion properties of the substrate undergoing patterning. Matching thermal properties of the patterning device and the substrate is beneficial because it results in improved placement accuracy and fidelity of patterns fabricated on substrate surfaces.

[0047] In another aspect, the present invention provides methods of generating one or more patterns on a substrate surface by contact printing a transfer material, including methods of microtransfer contact printing and nanotransfer contact printing. In one embodiment, a transfer material is deposited onto the contact surface of a composite patterning device of the present invention, thereby generating a layer of transfer material on the contact surface. Deposition of transfer material onto the contact surface may be achieved by any means known in the art including, but not limited to, vapor deposition, sputtering deposition, electron beam deposition, physical deposition, chemical deposition dipping and other methods which involve bringing the contact surface into contact with a reservoir of transfer material. The patterning device is contacted to the substrate surface in a manner establishing conformal contact between at least a portion of the contact surface and the substrate surface. Establishing conformal contact exposes at least a portion of the layer of transfer material to the substrate surface. To generate a pattern on the substrate surface, the patterning device is separated from the substrate surface, thus transferring at least a portion of the transfer material to the substrate surface. The present invention also includes fabrication methods wherein these steps are sequentially repeated to construct complex structures comprising patterned multilayer stacks.

[0048] In another aspect, the present invention provides methods of generating one or more patterns on a substrate surface by molding a transfer material, such as micromolding and nanomolding methods. In one embodiment, a composite patterning device of the present invention is brought into contact with a substrate surface in a manner establishing conformal contact between at least a portion of the contact surface and the substrate surface. Conformal contact generates a mold comprising the space separating the three-dimensional relief pattern and the substrate surface. A transfer material, such as a prepolymer, is introduced into the mold. To generate a pattern on the substrate surface, the patterning device is separated from the substrate surface, thus transferring at least a portion of the transfer material onto the substrate surface. Optionally, methods of the present invention may further comprise the steps of heating the transfer material in the mold, exposing the transfer material in the mold to electromagnetic radiation or adding a polymerization activator to the transfer material in the mold to initiate chemical changes such as polymerization and/or cross linking chemical reactions.

[0049] In another aspect, the present invention provides methods of generating one or more patterns on a substrate surface by contact photolithography. In one embodiment, a composite patterning device of the present invention is brought into contact with a substrate surface comprising one or more radiation sensitive materials in a manner establishing conformal contact between at least a portion of the contact surface and the substrate surface. Electromagnetic radiation is directed through the patterning device and onto the surface of the substrate, thereby generating a pattern of electromagnetic radiation on the substrate surface having selected two dimensional distributions of intensities, wavelengths and/or polarization states. Interactions between electromagnetic radiation and radiation sensitive materials of the substrate generate chemically and/or physically modified regions of the substrate surface, thereby generating one or more patterns on the substrate surface. Optional, methods of the present invention may further comprise the steps of removing at least a portion of the chemically modified regions of the substrate surface or removing at least a portion of the substrate surface which is not chemically modified. Material removal in this aspect of the present invention may be achieved by any means known in the art of photolithography, including but not limited to, chemical etching and exposure to chemical agents, such as solvents.

[0050] The methods, devices and device components of the present invention are capable of generating patterns on the surfaces of a wide variety of substrates including but not limited to, plastics, glasses, carbonaceous surfaces, metals, textiles, ceramics or composites of these materials. The methods, devices and device components of the present invention are also capable of generating patterns on substrate surfaces having a wide range of surface morphologies, such as rough surfaces, smooth surfaces, contoured surfaces and flat surfaces. Important in fabricating high resolution patterns characterized by good placement accuracy and high fidelity is the use of conformable contact surfaces that support strong associations between the molecules comprising a substrate surface and molecules of the contact surface. For example, PDMS contact surfaces undergo strong Vander Waals interactions with many substrate surfaces including surfaces comprised of plastics, polyimide layers, glasses, metals, metalloids, silicon and silicon oxides, carbonaceous materials, ceramics, textiles and composites of these materials.

[0051] The methods of the present invention are capable of fabricating microscale and nanoscale structures having a wide variety of physical dimensions and relative arrangements. Symmetrical and asymmetrical three-dimensional structures may be fabricated by the present methods. The present methods, devices and device components may be used to generate patterns comprising one or more structures having features with dimensions ranging from about 10 nanometers to about 100 microns or more preferably for some applications ranging from about 10 nanometer to about 10 microns. Structures generated by the present methods, devices and device components may have selectable lengths in two or three physical dimensions, and may comprise patterned multilayer stacks. The present methods may also be used to generate structures comprising self assembled monolayers and structures. The methods, devices and device components of the present invention are capable of generating patterns comprising a wide range of materials including, but not limited to, metals, organic compounds, inorganic compounds, colloidal materials, suspensions, biological molecules, cells, polymers, microstructures, nanostructures and salt solutions.

[0052] In another aspect, the present invention comprises methods of making composite patterning devices. An exemplary method of making a composite patterning device comprises the steps of: (1) providing a master relief pattern having a selected three-dimensional relief pattern; (2) contacting the master relief pattern with a prepolymer of a low modulus polymer; (3) contacting the prepolymer material with an

high modulus polymer layer; (4) polymerizing the prepolymer, thereby generating a low modulus polymer layer in contact with the high modulus polymer layer and in contact with the master relief pattern; the low modulus layer having a three-dimensional relief pattern and (5) separating the low modulus layer from the master relief pattern, thereby making the composite patterning device. Master relief patterns useable in the present methods include relief patterns prepared using photolithography methods. In the present invention, polymerization may be initiated using any method known in the art including, but not limited to, thermal induced polymerization methods and electromagnetic radiation induced polymerization methods.

[0053] Conventional photolithography generally uses amplitude or amplitude and phase masks directly in contact with a layer of resist or as part of an optical projection system. The masks are usually made on substrates of glass or quartz or other rigid transparent material. It is difficult to generate gray-scale patterns using conventional photolithography, requiring multiple steps and accurate alignment systems that drive up the costs. The ink-based soft lithographic technique presented herein combines the best features of conventional photolithography (i.e. widespread industry acceptance, well developed technology) and soft lithography (suited for unusual applications in plastic electronics, microfluidics and other areas). A particularly important aspect of this invention is for patterning structures in plastic electronics, in which the flexible plastic substrate can deform in an uncontrolled manner during processing. The stamp and ink combination disclosed herein is a deformable amplitude mask that can be stretched to match the distortions in the substrate. In this manner, accurate multilevel feature registration is possible on plastic substrates and even complex curved or rough surfaces.

[0054] The methods and devices presented herein have applications as an amplitude photomask useful in generating patterns having features with different depths/heights and individual features with continuously varying depth/height and/or step-wise change in depth/height. In general, a method is provided for processing a substrate surface by establishing conformal contact between the substrate surface and a corresponding three-dimensional pattern surface on the elastomeric patterning device. The conformal contact facilitates filling of the recess features of the relief features of the pattern by patterning agent. Localization of patterning agent to the relief features processes the surface by formation of a pattern of substrate surface that is not covered or underneath a patterning agent-filled recess feature. Subsequent exposure of the surface substrate

to electromagnetic radiation, wherein the patterning agent is capable of modulating an optical property of electromagnetic radiation, results in patterning of the optical property on the substrate surface. In this aspect, a substrate surface that comprises a photosensitive material results in a pattern of physical property, chemical and/or phase changes to the substrate surfaces. The particular pattern on the surface substrate is selected by varying the geometry of the patterning device three-dimensional pattern, by selecting one or more patterning agents having different modulating characteristics, and/or providing modulating capability to the elastomeric patterning device.

[0055] Alternatively, the method and devices presented herein have applications as a mold by using a patterning agent that at least partially fills the patterning device recess features, wherein the patterning agent is modified in response to a signal. After exposure to the signal that causes a change to the patterning agent, the patterning device is separated from the substrate surface to reveal a pattern of relief features embossed on the substrate surface. This pattern of embossed features can itself be a photomask capable of optical modulation for generating patterns in photosensitive materials. The term "signal" is used broadly to refer to an interaction capable of causing a physical or chemical change to the patterning agent, and includes a chemical that can cause a polymerizing reaction or phase change, an optical property associated with electromagnetic radiation or heat.

[0056] Further control of surface processing is obtained by patterned application of the patterning agent by, for example, in one or more discrete droplets in a pattern. Each or any one or more of the droplets can be addressable by, for example, having discrete regions on the substrate surface or patterning device three-dimensional surface that are hydrophobic or hydrophilic. In an embodiment, the invention further comprises means for aligning the patterning device and surface substrate such as an optical waveguide and/or lock-and-key registration features.

[0057] Additional control of surface processing is obtained by modifying the optical properties of selected stamp regions to provide regions having spatially distinct and selected modulating properties. For example, the stamp having recessed features for receiving a patterning agent can have a selected index of refraction for phase modulation, absorption properties for wavelength dependent optical modulation and/or polarization properties for modulating the polarization state of incident electromagnetic radiation. The index of refraction or polarization properties of the stamp can be selected

by incorporating particles or thin films within or on the exterior of the stamp that are phase-modulating and/or polarization-modulating. The effect of the patterning agent can be further enhanced by coating recessed or relief regions with a thin layer of film of material having optically modulating properties, such as a thin (e.g., 20 to 500
5 nanometers) dielectric, metallic and/or semiconductor film. The stamp top surface on the opposite side of the patterned recessed features and in the path of the incident electromagnetic radiation is optionally patterned with a material, including a thin film layer or discrete particles, to provide controlled optical modulation.

[0058] The present invention provides methods, devices and device components for
10 fabricating patterns on substrate surfaces, particularly patterns comprising three-dimensional relief features, wherein the features can have complex geometry such as different features having different heights or an individual feature having a variable height. Specifically, the present invention provides stamps, molds and photomasks used in ink soft lithography fabrication methods for generating high resolution patterns of
15 structures on flat and contoured surfaces, including surfaces having a large radius of curvature on a wide variety of substrates, including flexible plastic substrates. It is an object of the present invention to provide one-step methods and devices for fabricating three-dimensional gray-scale structures having well-defined physical dimensions. The features can have a size ranging from the tens of nanometers scale to the hundreds of
20 microns and more scale. It is another object of the present invention to provide methods, devices and device components for fabricating patterns of structures characterized by high fidelity over large substrate surface areas and good placement accuracy. It is another object of the present invention to provide methods, devices and device components for fabricating patterns on substrates that tend to deform during
25 processing. It is another object of the present invention to provide soft lithography methods, devices and device components that are compatible with existing high speed commercial printing, molding and embossing techniques, devices and systems.

[0059] In an embodiment, the present invention provides a patterning device for generating a pattern on a substrate surface comprising a patterning device having a
30 three-dimensional relief and recess pattern on an elastomeric surface. This three dimensional surface has a contact surface that is capable of conformal contact with a substrate surface. To facilitate pattern generation, a patterning agent is located between the contact surface and the substrate surface such that when contact is established, the patterning agent can fill at least a portion of the recess features of the

three-dimensional pattern. The patterning agent can be placed on a portion of the substrate surface, patterning device three-dimensional pattern face, or both. The patterning agent is capable of effecting pattern generation by any one of a number of mechanisms. In an embodiment, the patterning agent is capable of generating a relief pattern on the substrate surface upon exposure to a signal. The signal is a physical interaction capable of effecting a change in the patterning agent including a change in state or a change in chemical properties. Commonly used signals include, but are not limited to, electromagnetic radiation such as UV light, and pulsed high-energy sources.

[0060] In an embodiment, the patterning agent is used as part of a photomask, and the relief pattern is formed by etching or removal of a portion of the substrate surface in a pattern. In an embodiment, the patterning agent is an optical medium that absorbs, scatters or reflects signal. The patterning agent may be an agent that has a different index of refraction than the patterning device to generate patterns by phase-shift lithography. The patterning agent may modulate polarization shifts or selectively transmit light of a particular wavelength range. The patterning device and patterning agent are disposed between a signal source and a photosensitive layer such as a solid photoresist that covers at least a portion of the substrate surface. Such an arrangement results in a signal pattern over the surface of the photoresist, wherein the signal, in an embodiment, results in gray-scale patterning, black-and-white patterning, or a combination of gray-scale and black-and-white patterning. Modifications to the photoresist are dependent on signal intensity or quality, and so a pattern is etched into the photoresist after signal exposure, resulting in a patterned photoresist on substrate, wherein the pattern generated is governed by the shape of the device's three-dimensional pattern. The amount and physical properties of the patterning agent located within the recess features of the device and between the polymer and photoresist facing surfaces also influences substrate processing and pattern generation. A commonly used signal for this embodiment is an optical property of electromagnetic radiation. In an aspect, the optical property is UV light intensity and the patterning agent at least partially absorbs UV light.

[0061] Any of the elastomeric patterning device three-dimensional pattern can be in the form of a stamp, mold, or photomask as disclosed in U.S. App. No. 11/115,954 (U.S. Pub. No. 20050238967) filed Apr. 27, 2005, specifically incorporated by reference for the patterning device, polymer composition, mechanical properties and structures disclosed therein. For example, the elastomeric device can comprise a plurality of

polymer or elastomer layers each having selected mechanical properties, such as Young's Modulus and flexural rigidity, selected physical dimensions, such as thickness, surface area and relief pattern dimensions, and selected thermal properties, such as coefficients of thermal expansion, to provide high resolution patterning on a variety of substrate surfaces and surface morphologies. Patterning devices of this aspect of the present invention include multilayer polymer stamps, molds and photomasks useful for a variety of soft lithographic patterning applications including contact printing, molding and optical patterning. In one embodiment, discrete polymer layers having different mechanical properties, physical dimensions, modulating characteristics and/or thermal properties are combined and/or matched to provide patterning devices having cumulative mechanical and thermal properties providing enhanced pattern resolution and fidelity, and improved thermal stability over conventional soft lithography devices. In addition, patterning devices of the present invention comprising a combination of discrete polymer layers, including at least one elastomer layer having a three-dimensional surface, tolerate a wide variety of device configurations, positions and orientations without fracture which make them more easily integrated into existing commercial printing, molding and optical patterning systems than conventional single layer or multiple layer stamps, molds and photomasks.

[0062] The elastomeric or polymeric layers of the patterning device optionally comprise their amplitude, phase or polarization state optical modulating characteristics. The index of refraction of the stamp material can be selected to provide further patterning control. Layers, including thin film layers (e.g. dielectric, metallic and/or semiconductor thin films), can be patterned on a stamp surface, such as patterned on the top face and/or on or in the recessed or relief features of the three-dimensional pattern on the bottom face of the stamp. These layers have optical modulating characteristics, such as phase, wavelength or polarization state modulating characteristic, that provide further patterning control. This control can provide enhanced gray-scale control, binary patterning capability and/or a combination of these functionalities. Particles having optical modulation capability may be embedded within the layer, on an external surface and/or on a surface of a relief or recessed feature to provide additional patterning control and capability.

[0063] In one embodiment, the present invention provides a composite patterning device comprising a first polymer layer having a low Young's modulus and a second polymer layer having a high Young's modulus. The first polymer layer is elastomeric

and comprises a selected three-dimensional relief pattern having at least one contact surface disposed thereon and has an internal surface opposite the contact surface. The second polymer layer has an external surface and an internal surface. First and second polymer layers are arranged such that a force applied to the external surface of the second polymer layer is transmitted to the first polymer layer. For example, first and second polymer layers may be arranged such that a force applied to the external surface of the second layer is transmitted to at least a portion of the contact surface(s) of the first polymer layer. In an embodiment, the internal surface of the first polymer layer is operationally coupled to the internal surface of the second polymer layer. For example, the internal surface of the first polymer layer may be in physical contact with the internal surface of the second polymer layer. Alternatively, the first polymer layer and the second polymer layer may be connected by one or more connecting layers, such as thin metal layers, polymer layers or ceramic layers, positioned between the internal surface of the first polymer layer and the internal surface of the second polymer layer.

[0064] Patterning devices of this aspect of the present invention are capable of establishing conformal contact between at least a portion of the contact surface(s) of the polymer or the first polymer layer and the substrate surface undergoing patterning. Optionally, the polymer or the second polymer layer may be operationally coupled to an actuator, such as a stamping, printing or molding device, capable of providing an external force to the external side of the second polymer layer so as to bring the patterning device into conformal contact with the substrate surface undergoing patterning. Optionally, the substrate may be operationally coupled to an actuator, capable of bringing the substrate into conformal contact with the patterning device. The patterning agent can be applied to the substrate surface, the three-dimensional polymer surface, or to both the substrate and the three-dimensional polymer surface prior to conformal contact. In another embodiment, the patterning agent can be applied after conformal contact is established. Means for establishing conformal contact include an actuator to manipulate one or more of pressure, force or displacement. Any of the disclosed composite patterning devices and related aspects thereof, are optionally incorporated into the ink lithography methods and systems of the present invention to process surfaces and generate patterns.

[0065] In an embodiment, the polymer of the present patterning device can comprise any number of polymer layers including, but not limited, to three polymer layers. The

third polymer layer can be connected to the second polymer layer in the manner described for connection of the first polymer layer connected to a second polymer layer. An exemplary third polymer layer has a thickness which is several times thicker than the roughness and/or radius of curvature of the substrate surface. The use of additional layers provides an ability to further vary mechanical layer attributes thereby further enhancing pattern fidelity on substrate surfaces.

[0066] In another aspect, the present invention provides methods of generating one or more patterns on a substrate surface by using any of the patterning devices of the present invention. In an embodiment, the patterning agent is deposited on at least a portion. In an aspect, the depositing step occurs before conformal contact. In an aspect the depositing step occurs after conformal contact. The patterning agent is exposed to a signal thereby generating a physical or chemical change to the patterning agent to solidify the patterning agent. The signal can comprise adding a polymerization activator to the patterning agent to initiate chemical changes such as polymerization and/or cross linking chemical reactions. After the polymer is separated from the substrate, a pattern remains on the surface of the substrate corresponding to the regions where the patterning agent is solidified.

[0067] In another aspect, the patterning agent absorbs, scatters or reflects electromagnetic radiation to generate a distribution of radiation intensity over the surface of a radiation sensitive material. This intensity distribution generates a pattern of chemically modified material, thereby generating the pattern on the substrate surface. In this aspect, the invention comprises depositing a plurality of patterning agents, each having different signal transmissive properties to generate complex patterns on a substrate surface. The deposition can comprise addressable application, wherein the patterning agent is applied in a pattern. For example, a combination of droplets, lines and pools of patterning agent can be applied to a substrate surface or a three-dimensional polymer surface, corresponding to the three-dimensional polymer pattern or to a desired pattern to-be-generated. Further pattern control is provided by preparing, as known in the art, selected surface regions that are hydrophilic and/or other regions that are hydrophobic, to facilitate patterning. The patterning agent can have selected physical properties including viscosity to ensure at least partial filling of recess features. In an embodiment the patterning agent has a viscosity of about water (e.g., about 1 cP) to facilitate recess filling and patterning agent distribution on a surface.

[0068] In an aspect, any of the devices or methods further comprise means for removing excess patterning agent. The means for removing can comprise channels, orifices, ports, or other similar conduits for conveying excess patterning agent from between the polymer and substrate surfaces to a region outside the region the pattern is to be generated.

[0069] Means for depositing patterning agent onto a surface may be achieved by any means known in the art including, but not limited to, vapor deposition, sputtering deposition, electron beam deposition, physical deposition, chemical deposition dipping and other methods which involve bringing the contact surface into contact with a reservoir of patterning agent. Means for providing droplets of patterning agent to a surface optionally further comprises placement of droplets into regions, where the regions are optionally hydrophilic in combination with any one or more of the means for depositing the patterning agent. The patterning device is contacted to the substrate surface in a manner establishing conformal contact between at least a portion of the contact surface and the substrate surface. Establishing conformal contact exposes at least a portion of the layer of transfer material to the substrate surface. To generate a pattern on the substrate surface, the patterning device is separated from the substrate surface, thus transferring at least a portion of the transfer material to the substrate surface. The present invention also includes fabrication methods wherein these steps are sequentially repeated to construct complex structures comprising patterned multilayer stacks.

[0070] The methods and devices of the present invention optionally comprise a means for aligning the polymer layer relative to the substrate including, for example, an external layer alignment system, such as clamping, fastening and/or bolting systems. The means for aligning can comprise an internal layer alignment system such as a lock-and-key, wherein one of the key is a relief feature extending from one or both of the substrate surface and the polymer surface, with a corresponding lock comprising a corresponding recess feature in one or both of the polymer surface and substrate surface for receiving the key. Alternatively, the means for aligning can be an optical alignment guide.

BRIEF DESCRIPTION OF THE DRAWINGS

[0071] Fig. 1A is a schematic showing a cross sectional view of a composite patterning device of the present invention comprising two polymer layers. Fig. 1B is a schematic

showing a cross sectional view of another composite patterning device of the present invention comprising two polymer layers and exhibiting high thermal stability. Fig. 1C is a schematic showing a cross sectional view of a composite patterning device of the present invention comprising three polymer layers and exhibiting high thermal stability.

5 Fig. 1D is a schematic showing a cross sectional view of a composite patterning device of the present invention comprising four polymer layers and exhibiting good resistance to pattern deformations caused by polymerization and/or curing during fabrication.

[0072] Fig. 2A is a schematic showing an exemplary master relief pattern and an exemplary patterning device fabricated from this master relief pattern. Fig. 2B shows a
10 scanning electron microscopy image of the relief structure of an exemplary patterning device comprising a composite stamp made using the methods of the present invention.

[0073] Fig. 3A is a schematic diagram illustrating a method for making a composite patterning device of the present invention. Fig. 3B is a schematic diagram illustrating an alternative method for making a composite patterning device of the present invention

15 [0074] Fig. 4A shows a schematic illustration of an exemplary patterning device of the present invention comprising a composite stamp. Fig. 4B shows a cross section scanning electron microscopy image of an exemplary composite stamp of the present invention

[0075] Figures 5A and 5B shows distortions that correspond to measurements of
20 positions of features on an exemplary composite stamp compared to those on its master.

[0076] Figs. 6A and 6B show top view optical micrographs that illustrate the reduced tendency for sagging of recessed areas in a composite stamp of the present invention. Figure 6A corresponds to a conventional single layer PDMS stamp and Figure 6B
25 corresponds to a composite stamp of the present invention.

[0077] Fig. 7 shows the extent of shrinkage observed after curing a four layer composite stamp of the present invention comprising a first PDMS layer, a second polyimide layer, a third PDMS layer and a fourth polyimide layer.

[0078] Fig. 8 is a schematic illustration of an exemplary nanotransfer printing
30 processes using a composite stamp of the present invention.

[0079] Figs 9A-D show scanning electron micrographs of patterns of Ti/Au (2 nm / 20 nm) generated using composite stamps of the present invention.

[0080] Fig. 10 shows the extent of distortion during thermal induced polymerization calculated for a four layer composite patterning device of the present invention.

5 **[0081]** Fig. 11A shows the extent of distortion during thermal induced polymerization calculated for a two layer composite patterning device. Fig. 11B is a plot of the radius of curvature after polymerization as a function of the thickness of the PDMS layer for the two layer patterning device. Fig. 11C is a plot of the radius of curvature after polymerization as a function of the curing temperature for the two layer patterning
10 device.

[0082] Fig.12A is a schematic diagram of a composite four layer patterning device comprising two h-PDMS layers and two polyimide (Kapton ®) layers. Figure 12B shows a plot of the predicted vertical displacement of a composite four layer patterning device in units of microns as a function of position along a recessed region about 90 microns in
15 length.

[0083] Figs. 13A-C shows the results of a computational study of horizontal distortion due to thermal/chemical shrinkage during polymerization for a two layer composite stamp of the present invention. Figure 13A is a schematic illustrating a two layer composite stamp comprising a PDMS layer of variable thickness operationally coupled
20 to a 25 micron Kapton layer. Figure 13B is a plot of the predicted horizontal distortion as a function of the thickness of the PDMS first layer. Figure 13C is a plot of the predicted horizontal distortion as a function of the distance along the external surface of the PDMS first layer.

[0084] Figures 14A and 14B provide schematic diagrams illustrating a fiber reinforced
25 composite stamp of the present invention. Figure 14A provides a cross sectional view and Figure 14B provides a perspective view. Figure 14C provides a schematic diagram illustrating first, second, third and fourth selected orientations corresponding to second, third, fourth and fifth layers, respectively, of fiber reinforced composite stamp.

[0085] Figure 15 provides an optical image of a composite polymer layer bonded to a
30 PDMS layer.

[0086] Figure 16 provides a schematic diagram of a composite soft photo mask of the present invention.

[0087] Figure 17A shows an optical image of a composite soft conformal photomask of the present invention and Figure 17B shows an optical image of exposed and developed photo-resist patterns on a silicon substrate.

[0088] Figure 18 provides a process flow diagram illustrating a method of making a composite soft conformal photomask of the present invention.

[0089] Figures 19A and 19B provide schematic diagrams showing alignment systems using a patterning agent for aligning a photomask and substrate.

[0090] Figure 20 provides a schematic diagram illustrating an exemplary patterning method of the present invention using a patterning agent that comprises an optical medium (or ink) of conformable photomask.

[0091] **FIG. 21** is a schematic showing a cross-sectional view of a patterning device (e.g. photomask) of the present invention comprising a radiation sensitive material and shows various steps in a method for generating a pattern. **FIG. 21A** illustrates the initial set-up where a patterning agent is deposited between a photoresist and a polymer. **FIG. 21B** shows a force applied to the device (arrows) to generate conformal contact between the polymer and photoresist with excess patterning agent removed from the device. **FIG. 21C** illustrates electromagnetic irradiation through the polymer toward the photoresist and substrate. **FIG. 21D** indicates after removal of the polymer, regions of the photoresist underneath and protected by the patterning agent remain and regions of the photoresist that are not protected from irradiation are etched. Intensity, exposure time and physical dimensions control the etching depth. This schematic illustrates the embodiment where the entire photoresist depth is etched in the unprotected regions.

[0092] **FIGs. 22-24** illustrate a variety of recess patterns can be employed to generate various patterns within a photoresist. In each of panels **A**, the contact surface of the polymer is contacted to a photoresist such that recesses are filled with patterning agent. After irradiation, the polymer is removed and the photoresist developed, leaving behind a pattern in the photoresist (panels **B**).

[0093] **FIG. 25** illustrates an embodiment comprising a lock and key alignment system. **FIG. 25A** illustrates an embodiment for an unstressed polymer that does not align with

the alignment system in the substrate. By stretching the polymer, the polymer aligns with the substrate (**FIG. 25B**).

[0094] FIG. 26 is a schematic showing a cross-sectional view of a patterning device of the present device useful in generating a molded structure, such as a molded structure comprising a photomask. **FIG. 26A** illustrates a patterning agent deposited onto a substrate surface. The polymer containing a relief pattern is contacted with the substrate surface (**FIG. 26B**) so that the patterning agent is localized to the recess features. After irradiation, the polymer is removed from the substrate surface to reveal a relief pattern on the substrate surface (**FIG. 26C**).

[0095] FIG. 27 is a plot of UV transmission through black wood dye indicating the dye absorbs UV light at the wavelength that induces chemical change to the photoresist.

[0096] FIG. 28 is a photomicrograph of: **(A)** a PDMS stamp floating on ink; **(B)** a PDMS stamp filled with ink; and **(C)** a photoresist patterned by the PDMS stamp as the mask.

[0097] FIG. 29A shows a silicon network deposited on plastic. **B** shows a silicon network patterned into squares. **C** shows electrodes of MOSFETs patterned onto the squares. The scale bar is 200 μm .

[0098] FIG. 30A schematically depicts phase shift lithography without a UV absorber patterning agent. **FIG. 30B** shows the pattern after 3.5 second exposure: develop 7 seconds. **FIG. 30C** shows the pattern after 4 second exposure: develop 7 seconds. The left panels are 12000 times magnification and the right panels 48000 times magnification. Longer exposure decreases the generated relief feature from 144 nm (right panel of **B**) to 137 nm (right panel of **C**)

[0099] FIG. 31A illustrates phase shift lithography with a patterning agent that is a water soluble UV absorber. For comparison purposes, **FIG. 31B** is the pattern generated without a UV absorber, and **FIG. 31C** the pattern generated with a UV absorber (left panel 12000x; right panel 48000x).

[00100] FIG. 32 shows pattern generation of 5 μm feature size over a large area by a device and method of the present invention. The entire pattern is 2x2 cm. The scale bar in **A** is 300 μm and in **B** is 200 μm .

[00101] **FIG. 33** shows results from computational finite element analysis of UV intensity in a photoresist with a UV-absorbent patterning agent filled in a PDMS mask for: **A** no UV absorbent layer; and **B** a 50 nm thick UV absorbent layer.

[00102] **FIG. 34** is a schematic of an actuator comprising a pressurized chamber to apply uniform pressure on the stamp backing to facilitate conformal contact.

[00103] **FIG. 35** illustrates pre-treatment of the substrate surface (using UVO technique) to locally control the quantity of the ink "wetting" the surface. Substrate can then be patterned as-is (blanket UV exposure without an elastomeric patterning device) or finer features can be patterned using a PDMS stamp to refine the final shape of the ink "droplets."

[00104] **FIG. 36** is a process flow diagram summarizing one use of the present invention as a photomask or a mold. The generated molded structure itself can be a photomask useful in subsequent patterning and processing of a photosensitive material.

[00105] **FIG. 37** schematically illustrates coating of selected recess features of the stamp to obtain an amplitude mask that along with the patterning agent provides amplitude modulation. **A** is a side cross-sectional view and **B** is a bottom view.

[00106] **FIG. 38** schematically illustrates patterning of a top surface of a stamp to provide additional amplitude modulation capability. **A** is a side view and **B** is a top view.

[00107] **FIG. 39** illustrates another embodiment for providing a stamp having amplitude-modulation capability by **A** embedding or **B** depositing particles having amplitude modulating capability.

[00108] **FIG. 40** schematically illustrates a process for mask generation useful in subsequent pattern generation by optical lithography. **FIG. 40A** illustrates the initial set-up where a patterning agent is deposited between a photoresist and a polymer. **FIG. 40B** shows an electromagnetic radiation signal (labeled "EMR" and indicated by arrows) through the polymer that polymerizes the patterning agent to generate a molded structure. **FIG. 40C** illustrates removal of the polymer stamp to reveal a molded structure that is a photomask on a photosensitive layer. A second EMR signal is applied in **FIG. 40D** to pattern the photosensitive layer. **FIG. 40E** shows generation of a pattern on a substrate surface that after processing and development.

[00109] **FIG. 41** is a process flow diagram summarizing mask generation wherein the mask is used in subsequent pattern generation by optical lithography.

[00110] **FIG. 42** Fabrication procedures for patterning photoresist (PR) using a water soluble ink as UV absorber: (i) A drop of the UV absorber is placed on a layer of positive PR layer, and a PDMS stamp is then placed on top of the ink: (ii) the ink in channels of the stamp block the UV light during exposure: (iii) developing the exposed photoresist generates a pattern in the geometry of the relief features of the stamp.

[00111] **FIG. 43** (a) optical microscopy ("OM"), (b,c) SEM, and (d) AFM images of 4 μm line-space PDMS phase mask: (e) optical microscopy, (f,g) SEM, and (h) AFM images of photoresist pattern made from PDMS phase mask without use of UV absorber : (i) optical microscopy, (j,k) SEM, and (l) AFM images of photoresist pattern which made from PDMS phase mask with use of UV absorber UVINUL3048.

[00112] **FIG. 44** PDMS phase mask (1mm width and 420nm depth) and photoresist pattern using same phase mask, and pattern with use of UV absorber: OM (a), AFM (b), and SEM (c) image of PDMS phase mask: OM (d), AFM (e), and SEM (f) image from phase shift lithography using same PDMS phase mask: OM (g), AFM (h), and SEM (i) image of pattern with use of UV absorber UVINUL3048 : OM (j) and AFM (k) image of 78nm Ti/Au islands after lift-off the photoresist from same pattern of (g) and (h).

[00113] **FIG. 45** PDMS phase mask (720 nm width and 420 nm depth) and photoresist pattern with and without use of UV absorber UVINUL3048: OM (a), AFM (b), and SEM (c) image of PDMS phase mask: OM (d), AFM (e), and SEM (f) image from phase shift lithography using same PDMS phase mask: OM (g), AFM (h), and SEM (i) image of pattern with use of UV absorber UVINUL3048 : OM (j) and AFM (k) image of 20nm thickness Ti/Au islands from same pattern of (g) and (h) after photoresist lift-off.

[00114] **FIG. 46** FEM (field emission microscope) (left) and NSOM (Near Field Scanning Optical Microscopy) results (right) of 960nm width square dot with and without use of UV absorber Ruthenium(II) Hexahydrate.

[00115] **FIG. 47** AFM (left) and SEM (right) image of 1 μm , 700nm, 440nm, 300nm square dot pattern made using the UV absorber Ruthenium(II) Hexahydrate.

[00116] FIG. 48 is a schematic summary of a grey scale pattern fabrication embodiment of the present invention that generates a molded structure having V-shaped grooves.

[00117] FIG. 49 are OM images (top row) and SEM cross-sections (bottom row) of a Si master showing the grooves having 4 μm depth and groove that is 10 μm wide at the surface, narrowing to 4.3 μm at the bottom.

[00118] FIG. 50 are OM images of a PDMS stamp. The left panel is a top view and the right panel a bottom view. The scale bar is 20 μm.

[00119] FIG. 51 shows a generated pattern without ink for a development time of 10 seconds. The relief features are about 800 nm in height and 10 μm wide.

[00120] FIG. 52 shows a generated grey scale pattern with ink for a development time of 10 seconds. The relief features have a variable height to a maximum of about 600 nm in height and variable in width from about a maximum of 9.8 μm wide.

[00121] FIG. 53 shows a generated pattern without ink for a development time of 45 seconds. The relief features are about 1.2 μm in height and 10 μm wide.

[00122] FIG. 54 shows a generated grey scale pattern with ink for a development time of 45 seconds. The relief features have a variable height to a maximum of about 1 μm in height and variable in width from about a maximum of 9.8 μm wide.

DETAILED DESCRIPTION OF THE INVENTION

[00123] Referring to the drawings, like numerals indicate like elements and the same number appearing in more than one drawing refers to the same element. In addition, hereinafter, the following definitions apply:

[00124] "Coefficient of thermal expansion" refers to a parameter which characterizes the change in size that a material undergoes upon experiencing a change in temperature. Linear thermal expansion coefficient is a parameter which characterizes the change in length a material undergoes upon experiencing a change in temperature and may be expressed by the equation:

$$\Delta L = \alpha L_o \Delta T \quad (I)$$

wherein ΔL is the change in length, α is the linear coefficient of thermal expansion, L_0 is the initial length and ΔT is the change in temperature. The present invention provides composite, multilayer patterning devices wherein thermal properties and physical dimensions of discrete layers are selected to provide a substantially symmetrical distribution of coefficients of thermal expansion about the center of the device along a layer alignment axis extending through the device.

[00125] “Placement accuracy” refers to the ability of a pattern transfer method or device to generate a pattern in a selected region of a substrate. “Good placement” accuracy refers to methods and devices capable of generating patterning in a select region of a substrate with spatial deviations from the absolutely correct orientation less than or equal to 5 microns, particularly for generating patterns on plastic substrates.

[00126] “Fidelity” refers to a measure of the similarity of a pattern transferred to a substrate surface and a relief pattern on a patterning device. Good fidelity refers to similarities between a pattern transferred to a substrate surface and a relief pattern on a patterning device characterized by deviations less than 100 nanometers.

[00127] “Young’s modulus” is a mechanical property of a material, device or layer which refers to the slope of the stress-strain curve for a given substance. Young’s modulus may be provided by the expression;

$$E = \frac{(\text{stress})}{(\text{strain})} = \left(\frac{L_0}{\Delta L} \times \frac{F}{A} \right); \quad (II)$$

wherein E is Young’s modulus, L_0 is the equilibrium length, ΔL is the length change under the applied stress, F is the force applied and A is the area over which the force is applied. Young’s modulus may also be expressed in terms of Lamé constants via the equation:

$$E = \frac{\mu(3\lambda + 2\mu)}{\lambda + \mu}; \quad (III)$$

wherein λ and μ are Lamé constants. Young's modulus may be expressed in units of force per unit area, such as Pascal ($\text{Pa} = \text{N m}^{-2}$).

[00128] High Young's modulus (or "high modulus") and low Young's modulus (or "low modulus") are relative descriptors of the magnitude of Young's modulus in a given material, layer or device. In the present invention, a High Young's modulus is larger than a low Young's modulus, preferably about 10 times larger for some applications, more preferably about 100 times larger for other applications and even more preferably about 1000 times larger for yet other applications. In one embodiment, a material having a high Young's modulus has a Young's modulus selected over the range of about 1 GPa to about 10 GPa and a material having a low Young's modulus has a Young's modulus selected over the range of about 1 MPa to about 10 MPa.

[00129] "Conformal contact" refers to contact established between surfaces and/or coated surfaces, which may be useful for fabricating structures on a substrate surface. In one aspect, conformal contact involves a macroscopic adaptation of one or more contact surfaces of a composite patterning device to the overall shape of a substrate surface. In another aspect, conformal contact involves a microscopic adaptation of one or more contact surfaces of a composite patterning device to a substrate surface leading to an intimate contact without voids. The term conformal contact is intended to be consistent with use of this term in the art of soft lithography. Conformal contact may be established between one or more bare contact surfaces of a polymer or a composite patterning device and a substrate surface. Alternatively, conformal contact may be established between one or more coated contact surfaces, for example contact surfaces having a transfer material and/or patterning agent deposited thereon, of a patterning device (including a composite patterning device) and a substrate surface. Alternatively, conformal contact may be established between one or more bare or coated contact surfaces of a patterning or a composite patterning device and a substrate surface coated with a material such as a transfer material, patterning agent, solid photoresist layer, photosensitive material, prepolymer layer, liquid, thin film or fluid. Conformal contact includes the elastomeric patterning device undergoing conformal contact with the photoresist layer on the substrate. In some embodiments of the present invention, patterning devices of the present invention are capable of establishing conformal contact with flat surfaces. In some embodiments of the present invention, patterning devices of the present invention are capable of establishing conformal contact with contoured surfaces. In some embodiments of the present invention, patterning devices

of the present invention are capable of establishing conformal contact with rough surfaces. In some embodiments of the present invention, patterning devices of the present invention are capable of establishing conformal contact with smooth surfaces. As used herein, contact encompasses the situation where there is a thin layer of, for example, liquid patterning agent between the surfaces.

[00130] “Flexural rigidity” is a mechanical property of a material, device or layer which refers to the ability of a material, device or layer to be deformed. Flexural rigidity may be provided by the expression:

$$D = \frac{Eh^3}{12(1-\nu^2)}; \quad (IV)$$

[00131] wherein D is flexural rigidity, E is Young’s modulus, h is thickness and ν is the Poisson ratio. Flexural rigidity may be expressed in units of force multiplied by unit length, such as Nm.

[00132] “Polymer” refers to a molecule comprising a plurality of repeating chemical groups, typically referred to as monomers. Polymers are often characterized by high molecular masses. Polymers useable in the present invention may be organic polymers or inorganic polymers and may be in amorphous, semi-amorphous, crystalline or partially crystalline states. Polymers may comprise monomers having the same chemical composition or may comprise a plurality of monomers having different chemical compositions, such as a copolymer. Cross linked polymers having linked monomer chains are particularly useful for some applications of the present invention. Polymers useable in the methods, devices and device components of the present invention include, but are not limited to, plastics, elastomers, thermoplastic elastomers, elastoplastics, thermostats, thermoplastics and acrylates. Exemplary polymers include, but are not limited to, acetal polymers, biodegradable polymers, cellulosic polymers, fluoropolymers, nylons, polyacrylonitrile polymers, polyamide-imide polymers, polyimides, polyarylates, polybenzimidazole, polybutylene, polycarbonate, polyesters, polyetherimide, polyethylene, polyethylene copolymers and modified polyethylenes, polyketones, poly(methyl methacrylate, polymethylpentene, polyphenylene oxides and polyphenylene sulfides, polyphthalamide, polypropylene, polyurethanes, styrenic resins, sulphone based resins, vinyl-based resins or any combinations of these.

[00133] “Elastomer” refers to a polymeric material which can be stretched or deformed and return to its original shape without substantial permanent deformation. Elastomers commonly undergo substantially elastic deformations. Exemplary elastomers useful in the present invention may comprise, polymers, copolymers, composite materials or mixtures of polymers and copolymers. Elastomeric layer refers to a layer comprising at least one elastomer. Elastomeric layers may also include dopants and other non-elastomeric materials. Elastomers useful in the present invention may include, but are not limited to, silicon containing polymers such as polysiloxanes including poly(dimethyl siloxane) (i.e PDMS and h-PDMS), poly(methyl siloxane), partially alkylated poly(methyl siloxane), poly(alkyl methyl siloxane) and poly(phenyl methyl siloxane), silicon modified elastomers, thermoplastic elastomers, styrenic materials, olefinic materials, polyolefin, polyurethanes, polyurethane thermoplastic elastomers, polyamides, synthetic rubbers, polyisobutylene, poly(styrene-butadiene-styrene), polybutadiene, polyisobutylene, polyurethanes, polychloroprene and silicones.

[00134] “Polymer layer” refers to a layer (and particularly an elastomer layer) that comprises one or more polymers. Polymer layers useful in the present invention may comprise a substantially pure polymer layer or a layer comprising a mixture of a plurality of different polymers. Polymer layers useful in the present invention also include multiphase polymeric layers and/or composite polymeric layers comprising a combination of one or more polymer and one or more additional material, such as a dopant or structural additive. Incorporation of such additional materials into polymer layers of the present invention is useful for selecting and adjusting the mechanical properties of polymer layers, such as the Young’s modulus and the flexural rigidity. The distribution of additional materials in composite polymer layers may be isotropic, partially isotropic or non isotropic. Useful material for use in a composite polymer layer includes those that impart optical modulation functionality to the polymer layer and thereby to the stamp. Useful composite polymeric layers of the present invention comprise one or more polymer (i) in combination with fibers, such as glass fibers or polymeric fibers, (ii) in combination with particles, such as silicon particles and/or nanosized particles, and/or (iii) in combination with other structural enhancers. In an embodiment of the present invention, a polymer layer having a high Young’s modulus comprises a polymer having a Young’s modulus selected over the range of about 1 GPa to about 10 GPa. Exemplary high Young’s modulus polymer layers may comprise polyimide, polyester, polyetheretherketone, polyethersulphone, polyetherimide, polyethyleneapthalate,

polyketones, poly(phenylene sulfide) any combinations of these materials or other polymeric materials having similar mechanical properties. In an embodiment of the present invention, a polymer layer having a low Young's modulus comprises a polymer having a Young's modulus selected over the range of about 1 MPa to about 10 MPa.

5 Exemplary low Young's modulus polymer layers may comprise elastomers such as, PDMS, h-PDMS polybutadiene, polyisobutylene, poly(styrene-butadiene-styrene), polyurethanes, polychloroprene and silicones. In a specific embodiment, the polymer layer is an elastomer layer. In an aspect, the patterning device comprises a multiple layers, including multiple elastomeric layers, with a layer that is operationally coupled to
10 an actuator having a high Young's modulus.

[00135] "Composite" refers to a material, layer, or device that comprises more than one component, such as more than one material and/or phase. The present invention can utilize composite patterning devices comprising a plurality of polymer or elastomer layers having different chemical compositions and mechanical properties. Composite
15 polymer layers of the present invention include layers comprising a combination of one or more polymer or elastomer and a fiber, such as a glass or elastomeric fiber, particulate, such as nanoparticles or microparticles or any combinations of these, as disclosed in U.S. Pat. App. No. 11/115,954 by Rogers et al. (filed Apr. 27, 2005), specifically incorporated by reference for the composite patterning devices that can be
20 used as a polymer of the present invention.

[00136] The term "electromagnetic radiation" refers to waves of electric and magnetic fields. Electromagnetic radiation useful for the methods of the present invention includes, but is not limited to, gamma rays, X-rays, ultraviolet light, visible light, infrared light, microwaves, radio waves or any combination of these. The patterning
25 agent can be dissolved in water and have a concentration selected to generate appropriate transmission of electromagnetic radiation. In an embodiment, the patterning agent transmittance is selected using Beer's law. In an aspect, the transmittance of the patterning agent is selected to be from between 0.01% and 99%, or less than 0.1%. As used herein, a material is "UV-absorbant" if it transmits less than about 0.1% of UV light
30 at a selected wavelength. The patterning agent composition can be selected so as to match the refractive index of the adjacent polymer. For example, for a PDMS polymer having a refractive index of 1.4, a higher refractive index fluid can be added to a patterning agent that is dissolved in water, including for example glycerol, to better match refractive indices. Refractive index matching decreases phase effects at PDMS-

patterning agent-photosensitive material interface, thereby increasing pattern feature resolution. Alternatively, the patterning agent can be a material that undergoes an alteration when irradiated including but not limited to a liquid prepolymer that cross-links to form a solid upon exposure to UV irradiation. Such a patterning agent is useful in mold applications where a pattern is deposited onto a substrate, rather than patterning by affecting a change in a photosensitive material on or part of a substrate.

[00137] The terms “intensity” and “intensities” refers to the square of the amplitude of an electromagnetic wave or plurality of electromagnetic waves. The term amplitude in this context refers to the magnitude of an oscillation of an electromagnetic wave. Alternatively, the terms “intensity” and “intensities” may refer to the time average energy flux of a beam of electromagnetic radiation or plurality of electromagnetic radiation, for example the number of photons per square centimeter per unit time of a beam of electromagnetic radiation or plurality of beams of electromagnetic radiation.

[00138] “Actuator” refers to a device, device component or element capable of providing a force and/or moving and/or controlling something. Exemplary actuators of the present invention are capable of generating a force, such as a force that is used to bring a patterning device into contact, such as conformal contact, with a substrate surface.

[00139] “Layer” refers to an element of a composite patterning device, polymer, substrate or photosensitive material of the present invention. Exemplary layers have physical dimensions and mechanical properties which provide patterning devices capable of fabricating patterns on substrate surfaces having excellent fidelity and good placement accuracy. The fabricated patterns can be of any size, including nanometer-sized (ranging from between about tens to 1000 nanometers) and micron-sized (ranging from microns to thousands of microns), and larger. Layers of the present invention may be a continuous or unitary body or may be a collection of discontinuous bodies, such as a collection of relief features. Layers of the present invention may have a homogenous composition or an inhomogeneous composition. An embodiment of the present invention provides a patterning device comprising a plurality of layers, such as polymer layers. Layers in the present invention may be characterized in terms of their thickness along a layer alignment axis which extends through a patterning device, such as a layer alignment axis which is positioned orthogonal to a plane containing one or more contact surfaces.

[00140] "Thermally stable" refers to the characteristic of a device or device component to withstand a change in temperature without a loss of characteristic properties, such as the physical dimensions and spatial distribution of relief features of a relief pattern.

5 **[00141]** "Substantially symmetrical distribution of the coefficients of thermal expansion about the center of a patterning device" refers to a device configuration wherein the mechanical and thermal properties of one or more layers comprising a patterning device are selected such that there is a substantially symmetrical distribution about the center of the patterning device along a layer alignment axis, for example a
10 layer alignment axis which is oriented perpendicular to a plane containing one or more contact surfaces. In one embodiment, the coefficients of thermal expansion are characterized by a symmetrical distribution about the center of the patterning device with deviations from an absolutely symmetric distribution less than about 10%. In another embodiment, the coefficients of thermal expansion are characterized by a
15 symmetrical distribution about the center of the patterning device with deviations from an absolutely symmetric distribution less than about 5%.

[00142] "Operationally coupled" refers to a configuration of layers and/or device components of composite patterning devices of the present invention. Operationally coupled layers or device components, such as first, second, third and/or fourth polymer
20 layers, refers to an arrangement wherein a force applied to a layer or device component is transmitted to another layer or device component. Operationally coupled layers or device components may be in contact, such as layers having internal and/or external surfaces in physical contact. Alternatively, operationally coupled layers or device components may be connected by one or more connecting layers, such as thin metal
25 layers, positioned between the internal and/or external surfaces of two layers or device components. In an aspect, the actuator responsible for generating a uniform pressure across the contact surface may comprise a pressure-controllable chamber. Accordingly, there may optionally be no direct physical contact between the actuator and the patterning device, but the actuator and the patterning device remain "operationally
30 coupled."

[00143] Patterning devices comprising one or more polymer layers are used to generate patterns in a one-step process that can have complicated shapes and geometry. "Polymer" refers to a molecule comprising a plurality of repeating chemical

groups, typically referred to as monomers. Polymers are often characterized by high molecular masses. Polymers useable in the present invention may be organic polymers or inorganic polymers and may be in amorphous, semi-amorphous, crystalline or partially crystalline states. Polymers may comprise monomers having the same chemical composition or may comprise a plurality of monomers having different chemical compositions, such as a copolymer. Cross linked polymers having linked monomer chains are particularly useful for some applications of the present invention. Polymers useable in the methods, devices and device components of the present invention include, but are not limited to, plastics, elastomers, thermoplastic elastomers, elastoplastics, thermostats, thermoplastics and acrylates. Exemplary polymers include, but are not limited to, acetal polymers, biodegradable polymers, cellulosic polymers, fluoropolymers, nylons, polyacrylonitrile polymers, polyamide-imide polymers, polyimides, polyarylates, polybenzimidazole, polybutylene, polycarbonate, polyesters, polyetherimide, polyethylene, polyethylene copolymers and modified polyethylenes, polyketones, poly(methyl) methacrylate, polymethylpentene, polyphenylene oxides and polyphenylene sulfides, polyphthalamide, polypropylene, polyurethanes, styrenic resins, sulphone based resins, vinyl-based resins or any combinations of these.

[00144] "Elastomer" refers to a polymeric material which can be stretched or deformed and return to its original shape without substantial permanent deformation.

Elastomers commonly undergo substantially elastic deformations. Exemplary elastomers useful in the present invention may comprise, polymers, copolymers, composite materials or mixtures of polymers and copolymers. Elastomeric layer refers to a layer comprising at least one elastomer. Elastomeric layers may also include dopants and other non-elastomeric materials. Elastomers useful in the present invention may include, but are not limited to, silicon containing polymers such as polysiloxanes including poly(dimethyl siloxane) (i.e PDMS and h-PDMS), poly(methyl siloxane), partially alkylated poly(methyl siloxane), poly(alkyl methyl siloxane) and poly(phenyl methyl siloxane), silicon modified elastomers, thermoplastic elastomers, styrenic materials, olefinic materials, polyolefin, polyurethane thermoplastic elastomers, polyamides, synthetic rubbers, polyisobutylene, poly(styrene-butadiene-styrene), polyurethanes, polychloroprene and silicones.

[00145] The elastomers of the present invention further comprise an elastomer surface having a three-dimensional pattern of recessed features. As used herein, "three-dimensional pattern of recessed features" refers to a surface having recess

features and, therefore, corresponding relief features defined by the geometry, number and location of recess features. In an aspect, the recess features have a variable depth, such that a generated pattern has features of varying height.

[00146] In the context of the present invention, "feature" refers to a structure on, or an integral part of, an elastomeric surface. "Feature" also refers to the pattern generated on a substrate surface, wherein the geometry of the pattern of features is influenced by the features of the elastomeric surface. The term feature encompasses a free-standing structure supported by an underlying surface, such as an entirely undercut free-standing structure and encompasses a feature that is integral connected to the underlying surface (e.g., a monolithic structure, or discrete structures connected by an adhesive layer or by surface forces including van der Waals forces, etc.). Some features useful in the present invention are micro-sized (e.g., ranging from the order of microns to about a millimeter) structures or nano-sized structures (ranging from on the order of nanometers to about a micron). The term feature, as used herein, also refers to a pattern or an array of structures, and encompasses patterns of nanostructures, patterns of microstructures or a pattern of microstructures and nanostructures. In an embodiment, a feature comprises a functional device component or functional device.

[00147] In an aspect, "patterning agent" is used to refer to a material capable of absorbing electromagnetic radiation or that undergoes a phase or chemical change upon exposure to a signal. A patterning agent can be liquid, a colloid suspension, a gel or any other material or phase that is functional in the methods and devices of the present invention. A patterning agent is functional in the present invention, for example, if the presence of the agent can generate or enhance the two-dimensional spatial distribution of an optical signal, including an optical signal corresponding to electromagnetic radiation intensity, wavelength, polarization state, or phase. "Two-dimensional spatial distribution" refers to a pattern of optical properties on a substrate surface effecting a corresponding pattern of chemical or phase changes to the substrate surface, wherein the magnitude or quality of the optical properties can vary as a function of position on the substrate surface. The pattern of changes to a substrate surface encompasses patterned change in one or more physical properties of a substrate, such as a patterned change in thermal properties such as thermal conductivity, photoconducting properties, or electronic properties such as dielectric properties or electrical conductivity.

[00148] "Substrate surface" or "surface of substrate" refers to a material with a surface that is capable of facilitating conformal contact with an opposing surface, such as a contact surface of the present invention. The term is used broadly and can include a substrate surface having a layer of photoresist. A pattern on a substrate surface refers to a pattern of features, wherein the features are recessed or relief, and can comprise different materials, shapes, dimensions and physical properties. Elastomeric patterning devices of the present invention include single-layer or multilayer polymeric and/or elastomeric stamps, molds and photomasks useful for a variety of soft lithographic patterning applications including contact printing, molding and optical patterning.

[00149] A photoresist refers to a material capable of undergoing a wavelength-specific radiation-sensitive chemical reaction. For example, the reaction can cause irradiated regions to be either more (positive photoresist) or less (negative photoresist) acidic. The resist is then developed by, for example, exposing it to an alkaline solution that removes either the exposed (positive photoresist) or the unexposed (negative photoresist) regions. Commonly used photoresists include those that are sensitive to UV radiation. The photosensitive material can itself be a functional material, such as an electronic material, thermal material and/or mechanical material. Useful photosensitive materials include photopolymers, prepolymers, electrically functional material such as a semiconductor material, a dielectric, a thermal conductor, a conducting material. In particular, the patterning can comprise patterning changes in a physical property such as conductivity (e.g., thermal, electrical) or a modulating characteristic (e.g., EMR absorbance, scattering, etc.).

[00150] In an embodiment, the photosensitive material is a polymer that is electrically conducting, such as a semiconducting polymer. In these embodiments, patterning of the photosensitive material generates semiconductor structures, including gray scale structures, useful for electronic device applications, such as a semiconductor channel in a transistor, light generating element in a photodiode or laser device, or a photovoltaic element in a solar cell device. In another embodiment, the photosensitive material is a polymer that is not electrically conducting, such as a dielectric polymer. In these embodiments, patterning of the photosensitive material generates dielectric structures, including gray scale structures, useful as insulators in electronic device applications including transistors. In another embodiment, the photosensitive material is a polymer that is thermally conducting, such as a thermally conductive polymer. In

these embodiments, patterning of the photosensitive material generates structures useful for thermal management strategies in electronic device applications.

[00151] “Placement accuracy” refers to the ability of a pattern transfer method or device to generate a pattern in a selected region of a substrate. “Good placement” accuracy refers to methods and devices capable of generating patterning in a select region of a substrate with spatial deviations from the absolutely correct orientation less than or equal to 5 microns, particularly for generating patterns on plastic substrates.

[00152] “Fidelity” refers to a measure of the similarity of a pattern transferred to a substrate surface and a relief pattern on a patterning device. Good fidelity refers to similarities between a pattern transferred to a substrate surface and a relief pattern on a patterning device characterized by deviations less than 100 nanometers.

[00153] In the following description, numerous specific details of the devices, device components and methods of the present invention are set forth in order to provide a thorough explanation of the precise nature of the invention. It will be apparent, however, to those of skill in the art that the invention can be practiced without these specific details.

[00154] The terms and expressions which have been employed herein are used as terms of description and not of limitation, and there is no intention in the use of such terms and expressions of excluding any equivalents of the features shown and described or portions thereof, but it is recognized that various modifications are possible within the scope of the invention claimed. Thus, it should be understood that although the present invention has been specifically disclosed by preferred embodiments, exemplary embodiments and optional features, modification and variation of the concepts herein disclosed may be resorted to by those skilled in the art, and that such modifications and variations are considered to be within the scope of this invention as defined by the appended claims. The specific embodiments provided herein are examples of useful embodiments of the present invention and it will be apparent to one skilled in the art that the present invention may be carried out using a large number of variations of the devices, device components, methods steps set forth in the present description. Methods and devices useful for the present methods can include a large number of optional device elements and components including, additional polymer layers, glass layers, ceramic layers, metal layers, microfluidic channels and elements, actuators such as rolled printers and flexographic printers, handle elements, fiber optic

elements, birefringent elements such as quarter and half wave plates, optical filters such as FP etalons, high pass cutoff filters and low pass cutoff filters, optical amplifiers, collimation elements, collimating lens, reflectors, diffraction gratings, focusing elements such as focusing lens and reflectors, reflectors, polarizers, fiber optic couplers and transmitters, temperature controllers, temperature sensors, broad band optical sources and narrow band optical sources.

[00155] All references cited in this application are hereby incorporated in their entireties by reference herein to the extent that they are not inconsistent with the disclosure in this application. It will be apparent to one of ordinary skill in the art that methods, devices, device elements, materials, procedures and techniques other than those specifically described herein can be applied to the practice of the invention as broadly disclosed herein without resort to undue experimentation. All art-known functional equivalents of methods, devices, device elements, materials, procedures and techniques specifically described herein are intended to be encompassed by this invention.

[00156] This invention provides methods, devices and device components for fabricating patterns on substrate surfaces, such as patterns comprising micro-sized structures and/or nano-sized structures. The present invention provides composite patterning devices, such as stamps, molds and photomasks, exhibit enhanced thermal stability and resistance to curing induced pattern distortions. The methods, devices and device components of the present invention are capable of generating high resolution patterns exhibiting good fidelity and excellent placement accuracy.

[00157] Figure 1A is a schematic showing a cross sectional view of a composite patterning device of the present invention comprising two polymer layers. The illustrated composite patterning device **100** comprises a first polymer layer **110** having a low Young's modulus and a second polymer layer **120** having a high Young's modulus. First polymer layer **110** comprises a three-dimensional relief pattern **125** having a plurality of relief features **133** separated by a plurality of recessed regions **134**. First polymer layer **110** also has a plurality of contact surfaces **130** positioned opposite to an internal surface **135**. The present invention includes embodiments wherein contact surfaces **130** occupy a common plane and embodiments wherein contact surfaces **130** occupy more than one plane. Second polymer layer **120** has an internal surface **140** and an external surface **150**. In the embodiment shown in Figure 1A, the internal

surface **135** of first polymer layer **110** is positioned in contact with internal surface **140** of second polymer layer **120**. Optionally, second polymer layer **120** is operationally connected to actuator **155** which is capable of directing a force (schematically shown as arrows **156**) onto external surface **150**.

5 **[00158]** First polymer layer **110** and second polymer layer **120** may be coupled in any manner allowing a force exerted on external surface **150** to be transmitted effectively to contact surfaces **130**. In exemplary embodiments, first polymer layer **110** and second polymer layer **120** are coupled via covalent bonding between the polymers comprising each layer. Alternatively, first polymer layer **110** and second polymer layer
10 **120** may be coupled by attractive intermolecular forces between each layer, such as Van der Waals forces, dipole-dipole forces, hydrogen bonding and London forces. Alternatively, first polymer layer **110** and second polymer layer **120** may be coupled by an external layer alignment system, such as clamping, fastening and/or bolting systems. Alternatively, first polymer layer **110** and second polymer layer **120** may be coupled
15 using one or more connecting layers (not shown in Fig. 1A), such as thin metal layers, positioned between internal surface **135** and internal surface **140**. Coupling of first polymer layer **110** and second polymer layer **120** via strong covalent bonding and/or attractive intermolecular forces is preferred for some applications because it provides good mechanical rigidity to relief features **133** and recessed areas **134**, and also
20 provides an effective means of evenly distributing forces applied to external surface **150** to contact surfaces **130**.

[00159] In the exemplary embodiment shown in Figure 1A, the composition, Young's modulus and/or thicknesses along a layer alignment axis **160** positioned orthogonal to a plane including contact surfaces **130** of first polymer layer **110** are
25 selected to provide mechanical properties of patterning device **100** that allow fabrication of high resolution patterns of micro-sized and/or nano-sized structures which exhibit reduced pattern distortions. In addition, the Young's modulus and/or thicknesses of first polymer layer **110** and second polymer layer **120** may also be selected to provide easy integration of the patterning device **100** into commercial printing and molding systems.
30 In an exemplary embodiment, first polymer layer **110** comprises a PDMS layer having a thickness along the layer alignment axis **160** selected from the range of about 5 microns to about 10 microns. The thickness of first polymer layer **110** may alternatively be defined in terms of the shortest distance between contact surfaces **130** and internal surface **140** of second polymer layer **120**. In an exemplary embodiment, second

polymer layer **120** comprises a polyimide layer having a thickness along the layer alignment axis equal to about 25 microns. The thickness of second polymer layer **120** may alternatively be defined in terms of the shortest distance between the internal surface **140** and external surface **150** of second polymer layer **120**.

5 **[00160]** To fabricate patterns comprising one or more structures, the composite patterning device **100** and surface **185** of substrate **180** are brought into contact with each other, preferably contact establishing conformal contact between at least a portion of contact surfaces **130** and substrate surface **185**. Conformal contact between these surfaces may be achieved by application of an external force (schematically represented
10 by arrows **156**) onto external surface **150** in a manner moving patterning device **100** into contact with substrate **180**. Alternatively, an external force (schematically represented by arrows **190**) may be applied to substrate **180** in a manner moving substrate **180** into contact with the patterning device **100**. The present invention also includes embodiments wherein conformal contact is established by a combination of these forces
15 (**156** and **190**) and motions of substrate **180** and patterning device **100**.

[00161] Figure 1B is a schematic showing a cross sectional view of another composite patterning device of the present invention exhibiting high thermal stability comprising two polymer layers. As shown in Fig. 1B, the composite patterning device **200** comprises a discontinuous first polymer layer **210** having a low Young's modulus
20 operationally connected to second polymer layer **120** having a high Young's modulus. In this embodiment, discontinuous first polymer layer **210** comprises a three dimensional relief pattern **225** comprising a plurality of discrete relief features **233** separated by a plurality of recessed regions **234**. As shown in Figure 1B, discrete relief features **233** do not contact each other but are each operationally coupled to the second polymer layer
25 **120**. Incorporation of a first polymer layer comprising a plurality of discrete relief features into composite patterning devices of the present invention is beneficial because it decreases the extent of the mismatch between thermal expansion properties of the first and second polymer layers **210** and **120**, and also decreases the net amount of material in the first polymer layer **210**, which may comprise a material having a high
30 coefficient of thermal expansion, such as PDMS.

[00162] Figure 1C is a schematic showing a cross sectional view of another composite patterning device of the present invention exhibiting high thermal stability comprising three polymer layers. The illustrated composite patterning device **300**

further comprises third polymer layer **310** having an internal surface **315** and an external surface **320**. In the embodiment illustrated in Figure 1C, the internal surface **315** of third polymer layer **310** is in contact with the external surface **150** of second polymer layer **120**. Optionally, third polymer layer **310** is operationally coupled to actuator **155** which is capable of directing a force (schematically shown as arrows **156**) onto external surface **320**.

[00163] In the embodiment shown in Figure 1C, the thickness **330** of third polymer layer **310** along layer alignment axis **160** is approximately equal to the thickness **340** of first polymer layer **110** along layer alignment axis **160**, preferably within 10% for some applications. In this embodiment, selection of third polymer layer **310** and first polymer layer **110** having the same or similar (e.g. within 10%) coefficients of thermal expansion, such as both layers comprising PDMS layers, provides for high thermal stability and resistance to pattern distortions induced by changes in temperature. Particularly, this arrangement provides a substantially symmetrical distribution of the coefficients of thermal expansion about the center (indicated by center line axis **350**) of patterning device **300** along layer alignment axis **160**. A symmetrical distribution of the coefficients of thermal expansion provides for generation of opposing forces upon a change in temperature which minimizes the extent of stretching, bowing, buckling, expansion and compression of relief pattern **125**, relief features **133** and contact surfaces **130**.

[00164] Figure 1D is a schematic showing a cross sectional view of a four layer composite patterning device of the present invention exhibiting good resistance to pattern deformations caused by polymerization and/or curing during fabrication. The illustrated composite patterning device **400** further comprises fourth polymer layer **410** having an internal surface **415** and an external surface **420**. In the embodiment, illustrated in Figure 1D, the internal surface **415** of fourth polymer layer **410** is in contact with the external surface **320** of third polymer layer **310**. Optionally, fourth polymer layer **410** is operationally connected to actuator **155** which is capable of directing a force (schematically shown as arrows **156**) onto external surface **420**.

[00165] In the embodiment shown in Figure 1D, the thickness **330** of third polymer layer **310** along layer alignment axis **160** is approximately equal to the thickness **340** of first polymer layer **110** along layer alignment axis **160**, preferably within 10% for some applications, and the thickness **430** of fourth polymer layer **410** along layer alignment axis **160** is approximately equal to the thickness **440** of second polymer layer **120** along

layer alignment axis **160**, preferably within 10% for some applications. In this embodiment, selection of third polymer layer **310** and first polymer layer **110** having the same coefficients of thermal expansion and Young's modulus, such as both layers comprising PDMS layers, and selection of fourth polymer layer **410** and second polymer layer **120** having the same coefficients of thermal expansion and Young's modulus, such as both layers comprising polyimide layers, provides for good resistance to pattern distortions caused by polymerization and/or curing during fabrication. Particularly, this arrangement minimizes the extent of stretching, bowing, buckling, expansion and compression of relief pattern **125** and contact surfaces **130** during polymerization and/or curing.

[00166] Surfaces of polymer layers including first, second third and fourth layers in the present invention may possess specific relief patterns, such as alignment channels and/or grooves, useful for providing proper alignment between layers. Alternatively, surfaces of polymer layers in the present invention may possess specific relief patterns, such as alignment channels and/or grooves, useful for providing proper alignment between a composite patterning device and an actuator such as a printing device, molding device or contact photolithography apparatus having complimentary (i.e. mating) channels and/or grooves. Alternatively, surfaces of polymer layers in the present invention may possess specific relief patterns, such as alignment channels and/or grooves, useful for providing proper alignment between a composite patterning device and substrate surface having complimentary (i.e. mating) channels and/or grooves. As will be understood by a person of ordinary skill in the art, use of such "lock and key" alignment mechanisms, channels, grooves and systems are well known in the art of microfabrication, and may easily be integrated into the patterning devices of the present invention.

[00167] Selection of the composition, physical dimensions and mechanical properties of polymer layers in composite patterning devices of the present invention depends largely on the material transfer method to be employed (e.g. printing, molding etc.) and the physical dimensions of the structures/patterns to be fabricated. In this sense, the composite patterning device specifications of the present invention may be regarded as selectably adjustable for a particular functional task or pattern/structure dimensions to be accomplished. For example, a two layer patterning device of the present invention useful for printing nanosized structures via soft lithographic methods may comprise an elastomeric first polymer layer having a thickness selected from the

range of about 1 micron to about 5 microns, and a second polymer layer comprising a polyimide layer having a thickness less than or equal to about 25 microns. In contrast, a two layer patterning device of the present invention useful for micro-molding structures having dimensions ranging from about 10 microns to about 50 microns may comprise an elastomeric first polymer layer having a thickness selected from the range of about 20
5 microns to about 60 microns, and a second polymer layer comprising a polyimide layer having a thickness selected over the range of about 25 microns to about 100 microns.

[00168] Composite patterning devices of the present invention, such as stamps, molds and photomasks, may be made by any means known in the art of material
10 science, soft lithography and photolithography. An exemplary patterning device of the present invention is prepared by fabricating a first polymer layer comprising an elastomer by casting and curing polydimethylsiloxane (PDMS) prepolymer (Dow Corning Sylgard 184) against a master relief pattern consisting of patterned features of photoresist (Shipley 1805) prepared by conventional photolithographic means. Master
15 relief patterns useful in the present invention may be fabricated using conventional contact mode photolithography for features larger than about 2 microns or using electron beam lithography for features smaller than about 2 microns. In an exemplary method, PDMS (Sylgard 184 from Dow Corning) or h-PDMS (VDT-731, Gelest Corp) are mixed and degassed, poured over the masters and cured in an oven at about 80
20 degrees Celsius. Alternatively, curing of 184 PDMS may be performed at room temperature using extra amounts of curing agent. First polymer layers comprising PDMS or h-PDMS are preferably cured in the presence of the second high modulus layer, such as a polyimide layer, to reduce shrinkage induced by curing and/or polymerization. In one embodiment, the internal surface of the polyimide layer is
25 roughened prior to being brought into contact with the PDMS prepolymer to enhance the strength of the binding of the PDMS first layer to the polyimide second layer upon curing of the PDMS prepolymer. Surface roughening of the polyimide layer may be achieved by any means known in the art including exposing the internal surface of the polyimide layer to a plasma.

[00169] Fabrication and curing of the additional layers in composite patterning
30 devices, for example high modulus second polymer layers, is preferably done simultaneously with preparation of the elastomeric first layer to minimize the extent of curing and/or polymerization induced shrinkage of the relief pattern and contact surfaces of the elastomeric first layer. Alternatively, a high modulus second polymer layer, for

example polyimide layer, may be attached to the first polymer layer using an adhesive or connecting layer, such as a thin metal layer.

[00170] An exemplary master relief pattern was fabricated using a positive photoresist (S1818, Shipley,) and lift off resist (LOR1A; micron Chem.). In this exemplary method, test grade approximately 450 micron thick silicon wafers (Montco Silicon Technologies) were cleaned with acetone, iso-propanol and deionized water and then dried on a hotplate at 150 degrees Celsius for 10 minutes. LOR 1A resin was spin-coated at 3000 rpm for 30 seconds and then pre-baked on a hot plate at 130 degrees C for five minutes. Next, the S1818 resin was spin coated at 3000 rpm for 30 seconds and backed on a hot plate for 110 degrees Celsius for five minutes. The resulting bilayer (approximately 1.7 microns thick) was exposed ($\lambda = 365 \text{ nm}$, 16.5 mW/cm^2) for 7 seconds with an optical contact aligner (Suss Microtech MJB3) using a chromium ion glass mask, and then developed (MF-319; Shipley) for 75 seconds. The development removed all the S1818 resist that was photoexposed. It also removed, in a roughly isotropic manner, the LOR 1A in both the exposed and unexposed regions. The result of this process is a pattern of S1818 on LOR 1A with regions of bare substrate in the exposed areas and slight undercuts at the edges of the patterns. Composite patterning devices comprising stamps were prepared from this master relief pattern using standard soft lithographic procedures of casting and curing PDMS against the master relief pattern. Figure 2A is a schematic showing an exemplary master relief pattern **461** and an exemplary patterning device **463** fabricated from this master relief pattern. Figure 2B shows a scanning electron microscopy image of the relief structure of an exemplary patterning device comprising a composite stamp made using the methods of the present invention.

[00171] Figure 3A is a schematic diagram illustrating a method for making a composite patterning device of the present invention. As shown in processing step A of Figure 3A, the patterning device may be prepared by spin coating a prepolymer of PDMS on a master relief pattern comprising resin relief features on silicon. Optionally, the master relief pattern may be treated with a self assembled monolayer of material to minimize adhesion of the PDMS first layer to the master. As shown in processing step B of Figure 3A, the PDMS first layer may be fabricated by curing for a few hours using a hot plate and a curing temperature between about 60 and about 80 degrees Celsius. After curing, a thin film of titanium, gold or a combination of both may be deposited on the internal surface of the PDMS first layer via electron beam evaporation methods, as

shown in processing step C of Figure 3A. A thin film of titanium, gold or mixture of both may also be deposited on the internal surface of the high modulus second polymer layer (see step C of Figure 3A). First and second layers are operationally coupled via cold welding the coated internal surfaces of the first and second layers, and the composite
5 patterning device may be separated from the master relief pattern, as shown in processing step D and E of Figure 3A, respectively.

[00172] Figure 3B shows an alternative method of fabricating a composite multilayer patterning device of the present invention. As shown in processing step A of Figure 3B, the internal surface of a high modulus second layer is coated with titanium, silicon oxide or a combination of both. The coated internal side of the high modulus
10 second layer is brought into contact with a master relief spin coated with a PDMS prepolymer and pressure is applied to the external surface of the high modulus second layer, as shown in processing step B of Figure 3B. This configuration allows the thickness of the layer of PDMS prepolymer to be selectably adjusted by spinning the master relief pattern and/or applying pressure to the external surface of the high
15 modulus second layer with a flat or rocker based press. Upon achieving a desired thickness, the PDMS prepolymer is cured for a few hours in an oven using curing temperature ranging from about 60 to 80 degrees Celsius, thereby forming the PDMS first layer, as shown in processing step C of Figure 3B. Finally, the composite
20 patterning device is separated from the master relief pattern. Optionally, this method includes the step of treating the master relief pattern with a self assembled monolayer of material to minimize adhesion of the PDMS first layer to the master.

[00173] The terms and expressions which have been employed herein are used as terms of description and not of limitation, and there is no intention in the use of such
25 terms and expressions of excluding any equivalents of the features shown and described or portions thereof, but it is recognized that various modifications are possible within the scope of the invention claimed. Thus, it should be understood that although the present invention has been specifically disclosed by preferred embodiments, exemplary embodiments and optional features, modification and variation of the
30 concepts herein disclosed may be resorted to by those skilled in the art, and that such modifications and variations are considered to be within the scope of this invention as defined by the appended claims. The specific embodiments provided herein are examples of useful embodiments of the present invention and it will be apparent to one skilled in the art that the present invention may be carried out using a large number of

variations of the devices, device components, methods steps set forth in the present description. Methods and devices useful for the present methods can include a large number of optional device elements and components including, additional polymer layers, glass layers, ceramic layers, metal layers, microfluidic channels and elements, actuators such as rolled printers and flexographic printers, handle elements, fiber optic elements, birefringent elements such as quarter and half wave plates, optical filters such as FP etalons, high pass cutoff filters and low pass cutoff filters, optical amplifiers, collimation elements, collimating lens, reflectors, diffraction gratings, focusing elements such as focusing lens and reflectors, reflectors, polarizers, fiber optic couplers and transmitters, temperature controllers, temperature sensors, broad band optical sources and narrow band optical sources.

[00174] All references cited in this application are hereby incorporated in their entireties by reference herein to the extent that they are not inconsistent with the disclosure in this application. It will be apparent to one of ordinary skill in the art that methods, devices, device elements, materials, procedures and techniques other than those specifically described herein can be applied to the practice of the invention as broadly disclosed herein without resort to undue experimentation. All art-known functional equivalents of methods, devices, device elements, materials, procedures and techniques specifically described herein are intended to be encompassed by this invention.

Example1: Composite Stamps for Nanotransfer Printing

[00175] The ability of the patterning devices of the present invention to provide composite stamps for nanotransfer printing applications was verified by experimental studies. Specifically, it is a goal of the present invention to provide composite stamps capable of patterning large areas of a substrate surface with structures having selected lengths on the order of microns and 10's of nanometers. Further, it is a goal of the present invention to provide composite stamps for contact printing high resolution patterns exhibiting good fidelity and placement accuracy.

[00176] To achieve the aforementioned goals, composite stamps were fabricated using the methods of the present invention and used to generate patterns comprising monolayers of gold on substrates via nanotransfer printing (nTP). Specifically, large area composites stamps were generated and tested, comprising a thin (5 – 10 micron) PDMS layer in contact with a 25 micron thick polyimide (Kapton®, DuPont) backing

layer. In addition, large area composites stamps were generated and tested, comprising additional PDMS and/or polyimide layers. In one embodiment, a second PDMS layer having thickness of about 10 millimeters was attached to the polyimide layer. In another embodiment, a second polyimide layer was provided that was separated from the first polyimide layer by a thin (approximately 4 micron) PDMS layer. Use of additional PDMS and/or polyimide layers facilitated handling of the composite stamps and avoided curling after separation from the master relief pattern due shrinkage of the PDMS layer and/or mismatch of the coefficients of thermal expansion of the PDMS and polyimide layers.

[00177] Figure 4A shows a schematic illustration of an exemplary composite stamp used in this study and Figure 4B shows a corresponding cross section scanning electron microscopy image. As shown in Figure 4B, the relief pattern of the composite stamp is coated with a thin layer of gold. The relief pattern of this composite stamp corresponds to the source/drain level of an active matrix circuit for electronic paper displays consisting of 256 interconnected transistors arranged in a square array of over an area of 16 cm by 16 cm.

[00178] Distortions in composite stamps of the present invention were quantified by measuring with a microscope the misalignment at each transistor location between two successive prints, between one print and the stamp and the stamp used to print and between a stamp and its master relief pattern. Figures 5A and 5B show distortions that correspond to measurements of positions of features on a composite stamp compared to those on its master relief pattern. These results include corrections for overall translation and rotational misalignment and isotropic shrinkage (about 228 ppm for stamps cured at 80 degrees Celsius and about 60 ppm for those cured at room temperature). The residual distortions are close to the estimated accuracy (approximately 1 micron) of the measurement method. These distortions include cumulative effects of (i) fabricating and releasing the stamp from its master relief pattern and (ii) printing (wetting the stamp) on an uneven substrate (the master has some relief features approximately 9 microns thick).

[00179] Another benefit of the composite stamp design of this example is its reduced tendency to sag mechanically in the recessed regions of the relief pattern, which can cause unwanted stamp-substrate contact that distorts a pattern transferred to a substrate surface. As an example, in the case of 60 micron wide lines separated by 60 microns (500 nanometer relief height), recessed areas of a regular single element

PDMS stamp sag completely. In contrast, no sagging is observed for the same relief geometry on a composite stamp comprising four polymer layers: (1) 25 micron PDMS first layer, (2) 25 micron polyimide second layer, (3) 60 micron PDMS third layer, and (4) 25 micron polyimide fourth layer. Figs. 6A and 6B show top view optical micrographs that illustrate the reduced tendency for sagging of recessed areas in a composite stamp of the present invention. Figure 6A corresponds to a conventional single layer PDMS stamp and Figure 6B corresponds to a composite stamp of the present invention. The color uniformity in the recessed areas of the composite stamp (Figure 6B) suggests that the bowing is almost zero. Finite element modeling of the multilayer structure of the composite stamp indicates that the polyimide layer efficiently reduces the tendency of the stamp for sagging when the residual PDMS layer is thin.

[00180] Figure 7 shows the extent of shrinkage observed after curing a two layer stamp of the present invention comprising a thin PDMS layer in contact with a polyimide layer. As shown in Figure 7, composite stamps of the present invention undergo horizontal shrinkage equal to 0.2% or less and vertical shrinkage of 0.3% or less. The resistance to curing induced shrinkage provided by the composite stamp designs of the present invention minimizes distortions of the three-dimensional relief pattern and contact surfaces and provides high resolution patterns exhibiting good fidelity with respect to the master relief pattern.

[00181] Figure 8 is a schematic illustration of a nanotransfer printing processes using a composite stamp of the present invention. As shown in Figure 8, the process begins with deposition of a gold coating on the surface of the composite stamp, thereby forming a discontinuous gold coating on the raised and recessed regions of the elastomeric first layer. Contacting the stamp to a substrate that supports a self assembled monolayer (SAM) designed to bond to the gold (e.g. a thiol terminated SAM) leads to strong adhesion between the gold and the substrate. Removing the stamp, to which gold only weakly adheres, transfers the gold on the raised regions of the stamp to the substrate.

[00182] Metal evaporation was performed with a Temescal electron beam system (BJD 1800) and deposition rates of 1 nm/s were employed. Pressures during evaporation were typically about 1×10^{-6} Torr or less. A deposition rate monitor was installed in position such that the rates could be established and stabilized before exposing the stamps or substrates to the flux of metal. The printing was performed in

open air shortly after deposition. The stamps typically come into intimate contact with the substrates without applied pressure other than the force of gravity. In some cases small pressure applied by hand was used to initiate contact along an edge, which then proceeded naturally across the stamp-substrate interface. After a few seconds, the stamp was removed from contact with substrate to complete the printing.

[00183] Figures 9A-D show scanning electron micrographs of patterns of Ti/Au (2 nm / 20 nm) generated using composite stamps of the present invention. As illustrated in these figures, the methods and devices of the present invention are capable of generating a wide variety of patterns comprising structures having a range of physical dimensions. As shown in Figures 9A- D, the transferred Ti/Au patterns are largely free of cracks and other surface defects. Use of composite stamps of the present invention having a thickness less than 100 μ m are preferred for some applications because the stress developed at the surface of the composite stamp when bent (during handling or initiation of contact) is small relative to conventional PDMS stamps which are often substantially thicker (e.g. approximately 1 cm in thickness).

Example 2: Computer modeling of the Thermal Characteristics and Mechanical Properties of Composite Patterning Devices

[00184] The susceptibility of multilayer patterning devices of the present invention to distortions induced by polymerization during fabrication and mechanical stresses was evaluated by computation simulations. Specifically, the extent of deformation induced by polymerization during fabrication and the weight driven deformation of recessed regions was calculated for a four layer composite patterning device. These studies verified that composite patterning devices of the present invention exhibit enhanced stability with respect to polymerization induced shrinkage and weight driven sagging.

[00185] The extent of polymerization induced distortion was calculated and compared for two different composite pattern designs. First, a four layer composite patterning device **600**, shown schematically in Figure 10, was evaluated comprising a first 5 micron thick PDMS polymer layer **610**, a second 25 micron polyimide (Kapton ®) polymer layer **620**, a third 5 micron thick PDMS polymer layer **630** and a fourth 25 micron polyimide (Kapton ®) polymer layer **640**. Second, a two layer composite patterning device **700** shown schematically in Figure 11A was evaluated comprising a

first 5 micron thick PDMS polymer layer **710**, a second 25 micron polyimide (Kapton ®) polymer layer **720**. A temperature change from 20 degrees Celsius to 80 degrees Celsius was used in both calculations. The Young's modulus and coefficient of thermal expansion of PDMS were assumed to be independent of temperature and equal to 3 MPa and 260 ppm, respectively. The Young's modulus and coefficient of thermal expansion of polyimide were assumed to be independent of temperature and equal to 5.34 GPa and 14.5 ppm, respectively.

[00186] Figure 10 shows the extent of distortion predicted during thermal induced polymerization calculated for the four layer composite patterning device **600**. As shown in Figure 10, no curling of the four layer pattern device is observed upon polymerization. Figure 11A shows the extent of distortion during thermal induced polymerization calculated for the two layer composite patterning device **700**. In contrast to the results for the four layer patterning device, polymerization induced curling is observed for the two layer patterning device. Figures 11B and 11C provide plots of the radius of curvature after polymerization as a function of the thickness of the PDMS layer and the curing temperature, respectively, for the two layer patterning device.

[00187] The extent of vertical displacement of recessed regions of a four layer patterning device of the present invention was also examined via computer simulations. As shown in Figure 12A, the composite patterning device evaluated comprised two h-PDMS layers and two polyimide layers (Kapton ®). The thickness of the first h-PDMS layer was varied over the range of about 6 microns to about 200 microns. The thickness of the polyimide second layer was held constant at 25 microns, the thickness of the h-PDMS third layer was held constant at 5 microns, and the thickness of the polyimide fourth layer was held constant at 25 microns. Figure 12B shows a plot of the predicted vertical displacement in units of microns as a function of position along a recessed region about 90 microns in length. As shown in Figure 12B, distortions due to sagging less than about 0.2 microns is observed are observed for PDMS first layers having thicknesses equal to or less than 50 microns. In addition the extent of sagging observed for all embodiments examined was always less than about 0.1% of each the thickness evaluated. The results of these simulations suggest that four layer composite patterning devices of the present invention are unlikely to exhibit undesirable contact between recessed regions of the first layer and the substrate surface due to sagging of recessed regions of a relief pattern.

[00188] Figs. 13A-C shows the results of a computational study of horizontal distortion due to thermal/chemical shrinkage during polymerization for a two layer composite stamp of the present invention. Figure 13A is a schematic illustrating a two layer composite stamp comprising a PDMS layer of variable thickness operationally coupled to a 25 micron Kapton layer. Figure 13B is a plot of the predicted horizontal distortion as a function of the thickness of the PDMS first layer in microns. Figure 13C is a plot of the predicted horizontal distortion as a function of the distance along the external surface of the PDMS first layer in millimeters. The modeling results suggest that the magnitude of distortions in planes parallel to the contact surfaces on the external surface of the PDMS first layer due to polymerization is directly proportional to the PDMS first layer thickness. In addition, the modeling results show that distortions in planes parallel to the contact surfaces on the external surface of the PDMS first layer due to polymerization are largely confined to the edges of the stamp when the thickness of the PDMS first layer is decreased.

Example 3: Fiber Reinforced Composite Patterning Devices

[00189] The present invention includes composite patterning devices comprising one or more composite polymer layers, including polymer layers having fiber materials providing beneficial mechanical, structural and/or thermal properties. Composite patterning devices of this aspect of the present invention include designs wherein fibers are integrated into and/or between polymer layers in geometries selected to provide a net flexural rigidity that minimizes distortion of the relief features of a relief pattern and which provide patterning devices capable of generating patterns exhibiting good fidelity and placement accuracy on substrate surfaces. Furthermore, composite patterning devices of this aspect of the present invention include designs wherein fibers are integrated into and/or between polymer layers in geometries selected to minimize expansion or contraction of polymer layers due changes in temperature and/or to facilitate physical manipulation of patterning devices of the present invention, for example by adding to the thickness of these devices.

[00190] To evaluate verify the utility of integrated fiber materials in composite patterning devices of the present invention, a patterning device comprising a plurality of glass fiber reinforced polymer layers was designed. Figures 14A and 14B provide schematic diagrams illustrating a fiber reinforced composite stamp of the present invention. Figure 14A provides a cross sectional view and Figure 14B provides a perspective view. As shown in Figures 14A and 14B the fiber reinforced composite

stamp **900** comprises a first layer **905** comprising PDMS and having a relief pattern with relief features of selected physical dimensions, a second layer **910** comprising a composite polymer having an array of fine glass fibers in a first selected orientation, a third layer **915** comprising a composite polymer having a mesh of larger glass fibers in a second selected orientation, a fourth layer **920** comprising a composite polymer having a mesh of large glass fibers in a third selected orientation and a fifth layer **925** comprising a composite polymer having an array of fine glass fibers in a fourth selected orientation. First layer **905** has a low Young's modulus and is capable of establishing conformal contact between its contact surface(s) and a range of surfaces including contoured, curved and rough surfaces. Second layer **910** is a composite polymer layer wherein the addition of an array of fine glass fibers in a selected orientation provides mechanical support to the roof of the relief features of first layer **905**, thereby minimizing distortion of the relief pattern on first layer **905** upon formation of conformal contact with a substrate surface. Third and fourth layers **915** and **920** provide an overall thickness of the fiber reinforced composite stamp **900** such that it can be easily manipulated, cleaned and/or integrated into a stamping device. Incorporation of glass fibers into second, third, fourth and/or fifth layers **910**, **915**, **920** and **925** also provide a means of selecting the net flexural rigidity of the fiber reinforced composite stamp and provides a means of selecting the Young's modulus of individual layers in patterning devices of the present invention. For example, selection of the composition, orientation, size and density of fibers in second, third, fourth and/or fifth layers **910**, **915**, **920** and **925** may provide a net flexural rigidity useful for generating patterns exhibiting good fidelity and placement accuracy on substrate surfaces. Second, third, fourth and fifth layers **910**, **915**, **920** and **925** may comprise fiber reinforced composite layers of a polymer having a low Young's modulus or polymer having a high Young's modulus. Optionally, fiber reinforced composite stamp **900** may further comprise one or more additional high or low Young's modulus polymer layers, include additional composite polymer layers having fiber materials.

[00191] Figure 14C provides a schematic diagram illustrating first **930**, second **935**, third **940** and fourth **945** selected orientations corresponding to second, third, fourth and fifth layers **910**, **915**, **920** and **925**, respectively, of fiber reinforced composite stamp **900**. As shown in Figure 14C, first selected orientation **930** provides an array of longitudinally aligned fine glass fibers in the second layer **910** arranged along axes that are orthogonal to the longitudinally aligned fine glass fibers in the fourth selected orientation **945** of the fifth layer **925**. Second and third selected orientations provide

fiber meshes wherein two sets of fibers are aligned and interwoven along orthogonal axes. Additionally, fiber meshes corresponding to second and third selected orientations **935** and **940** provide fibers orientations that are orthogonal to each other, as shown in Figure 14C. Use of the fiber mesh orientations shown in Figure 14C
5 minimizes anisotropy in the in plane mechanical properties of polymer layers and patterning devices of the present invention.

[00192] Figure 15 provides an optical image of a composite polymer layer bonded to a PDMS layer. As shown in Figure 15, the composite polymer layer **971** comprises a glass fiber mesh and the PDMS layer **972** does not have any integrated fiber materials.

[00193] Referring again to Figure 14A, the stamp design shown provides an arrangement of fiber reinforced layers that is symmetrical about design axis **960**. Use of a second layer **910** and a fifth layer **925** having substantially the same thermal expansion coefficient and a third layer **915** and a fourth layer **920** having substantially the same thermal expansion coefficient provides a fiber reinforced composite stamp **900**
15 having a substantially symmetrical distribution of thermal expansion coefficients about layer alignment axis **980**. This is particularly true if first layer is relatively thin compared to the sum of second, third, fourth and fifth layers, for example preferably less than 10% for some applications and more preferably less than 5% for some applications. As described above, use of device configurations in the present invention providing a
20 substantially symmetrical distribution of thermal expansion coefficients about layer alignment axis **980** orthogonal to a plane containing the contact surface(s) is useful for providing thermally stable patterning devices that exhibit minimal pattern distortions induced by changes in temperature. Further more, this symmetrical arrangement minimizes relief pattern distortions induced during curing, for example pattern distortions
25 caused of curling of polymer layers during curing.

[00194] The use of fiber materials allows for integration of a wide range of materials having useful mechanical and thermal properties, including brittle material, into patterning devices and polymer layers of the present invention in a manner that preserves their ability of to exhibit flexibility allowing for establishment of conformal
30 contact with rough and contoured substrate surfaces, such as surfaces having a large radius of curvature. For example, SiO₂ is a material that is very brittle in the bulk phase. However, use of SiO₂ fibers, fiber arrays and fiber meshes that are relatively thin (e.g. have diameters less than about 20 microns) allow structural reinforcement of polymer

layers and enhances net flexural rigidity while maintaining their ability to be flexed, stretched and deformed. Furthermore, SiO₂ exhibits good adhesion to some polymers, including PDMS. Carbon fibers are another class of material that integration into polymer layers leads to substantially enhancement of flexural rigidity and Young's modulus while allowing for device flexibility useful for establishing good conformal contact with a range of surface morphologies.

[00195] Any composition of fiber material and physical dimensions of fiber materials, may be used in fiber reinforced polymer layers of the present invention that provides patterning device and polymer layers exhibiting beneficial mechanical, structural and thermal properties. Fiber materials useful in the present composite patterning devices include, but are not limited to, fibers comprising glass including oxides such as SiO₂, Al₂O₃, B₂O₃, CaO, MgO, ZnO, BaO, Li₂O, TiO₂, ZrO₂, Fe₂O₃, F₂, and Na₃O / K₂O, carbon, polymers such as aramid fiber and dyneema, metals and ceramics or mixtures of these materials may be incorporated into patterning devices of the present invention. Fiber materials exhibiting good adhesion to the polymer comprising the layer it is integrated into are preferred materials for some applications. Fibers having lengths ranging from about 1 to about 100 microns are useful in fiber reinforced composite patterning devices of present invention, preferably about 5 to about 50 microns for some applications. Fibers having diameters ranging from about 0.5 microns to about 50 microns are useful in fiber reinforced composite patterning devices of present invention, preferably about 5 to about 10 microns for some applications.

[00196] Composite layers in fiber reinforced patterning devices of the present invention may have any selected arrangement of fibers providing patterning devices with useful mechanical and thermal properties. Use of fiber arrangements characterized by a high fiber volume fraction, for example a fiber volume fraction greater than about 0.7, is useful in composite layers (e.g. layer **910** in Figure 14A) providing support to relief features and recessed areas, including roof support, to in relief patterns of low modulus layers having one or more contact surfaces. Use of fiber arrangements characterized by a lower fiber volume fraction, for example a fiber volume fraction less than about 0.5, is useful in composite layers (e.g. layers **915** and **920** in Figure 14A) providing a desirable net stamp thickness in order to maintain the flexibility of the fiber reinforced composite patterning device. As exemplified in the schematic diagrams shown in Figures 14A – 14C, use of a plurality of composite layers having different selected fiber

orientations is useful in for providing fiber reinforced composite patterning devices having isotropic mechanical properties with respect to deformation along axis that are orthogonal to a plane containing the contact surface.

[00197] In addition to their in addition to their structural and mechanical properties, fiber materials for fiber reinforced composite patterning devices of the present invention may also be selected on the basis of their optical and/or thermal properties. Use of fibers having a refractive index equal to or similar to the polymer material in which it is integrated into (i.e. matched to within 10%) is useful for providing optically transparent composite polymer layers. For example, the index of refraction of SiO₂ fiber can be tuned to match the index of refraction of PDMS (typically between 1.4 to 1.6) to make a highly transparent composite polymer layer. Matching refractive index of fiber and polymer materials in a given composite polymer layer is particularly useful for fiber reinforced composite photomasks of the present invention. In addition, selection of a fiber material having a thermal expansion coefficient equal to or similar to the polymer material in which it is integrated into (i.e. matched to within 10%) is useful for providing thermal stable fiber reinforced composite patterning devices.

Example 4: Composite Soft Conformal Photomask

[00198] The present invention includes composite patterning devices comprising photomasks capable of establishing and maintaining conformal contact with the surface of a substrate undergoing processing with electromagnetic radiation. An advantage of composite conformal photomasks of the present invention is that they are able to conform to a wide range of substrate surface morphologies without significantly changing the optical properties, such as two dimensional transmission and absorption properties, of the photomask. This property of the present invention provides photomasks capable of transmitting electromagnetic radiation having well defined two dimensional spatial distributions of intensities, polarization states and/or wavelengths of electromagnetic radiation on selected areas of a substrate surface, thereby allowing fabrication of patterns on substrate exhibiting good fidelity and placement accuracy.

[00199] Figure 16 provides a schematic diagram of a composite soft conformal photomask of the present invention. As shown in Figure 16, the composite soft conformal photomask **1000** comprises a first polymer layer **1005** having a low Young's modulus and having a contact surface **1010**, a patterned layer photomasking layer **1015** comprising a plurality of optically transmissive **1017** and nontransmissive regions **1016**,

and a second polymer layer **1020** having high Young's modulus and an external surface **1025**. In a useful embodiment, the first polymer layer comprises PDMS and the second polymer layer comprises polyimide. Transmissive regions **1017** at least partially transmit electromagnetic radiation exposed to external surface **1025** and nontransmissive regions **1016** at least partially attenuate the intensities of electromagnetic radiation exposed to external surface **1025**, for example by reflecting, absorbing or scattering the electromagnetic radiation. In the embodiment shown in Figure 16, nontransmissive regions **1016** are reflective thin aluminum films in contact with a substantially transparent Ti/SiO₂ layer. In this arrangement, substantially transparent regions between reflective thin aluminum films are transmissive regions.

[00200] To provide patterning on a substrate surface, the composite soft conformal photomask **1000** is brought into contact with a substrate surface such that the contact surface **1010** of first polymer layer **1005** establishes conformal contact with the substrate surface. Electromagnetic radiation having first two dimensional distributions of intensities, polarization states and/or wavelengths is directed onto external surface **1025** of second polymer layer **1020** of composite soft conformal photomask **1000**. Reflection, absorption and/or scattering by nontransmissive regions **1016** generates transmitted electromagnetic radiation characterized by different two dimensional distributions of intensities, polarization states and/or wavelengths. This transmitted electromagnetic radiation interacts with the substrate surface and generates physically and/or chemically modified regions of the substrate surface. Patterns are fabricated either by removing at least a portion of the chemically and/or physically modified regions of the substrate or by removing at least a portion of the substrate that is not chemically and/or physically modified.

[00201] Figure 17A shows an optical image of a composite soft conformal photomask of the present invention and Figure 17B shows an optical image of exposed and developed photo-resist patterns on a silicon substrate. As shown in Figure 17A, the composite soft conformal photomask **1100** has a 5 millimeter thick handle **1105** providing a border which allows easy manipulation, cleaning and integration of the photomask with other processing instrumentation. A comparison of Figures 17A and 17B demonstrate that patterns having high fidelity are generated using the composite soft conformal photomask.

[00202] Figure 18 provides a process flow diagram illustrating a method of making a composite soft conformal photomask of the present invention. As shown in process step A of Figure 18, a thin aluminum layer is deposited onto the internal surface of a high Young's modulus polymer via electron beam evaporation. As shown in process step B of Figure 18, a layer of photoresist is deposited on the aluminum layer, for example by spin coating, and is patterned, for example using conventional photolithography. This patterning step generates a patterned photomasking layer comprising thin aluminum films having selected physical dimensions and positions. As shown in process step C of Figure 18, a thin film of Ti/SiO₂ is deposited on the aluminum patterned photomasking layer and exposed regions of the internal surface of the high Young's modulus polymer layer. Use of a Ti/SiO₂ layer is useful for promoting adhesion to a PDMS layer in subsequent processing steps. As shown in process step D of Figure 18, a substantially flat silicon substrate is treated with a nonstick self assembled monolayer and a thin layer of PDMS is spin coated on top of the self assembled monolayer. Use of the self assembled monolayer in this aspect of the invention is important for preventing irreversible bonding of the PDMS layer to the silicon surface and to avoid damage of the PDMS layer upon separation from the silicon substrate. As shown in process step E of Figure 18, the Ti/SiO₂ layer of the composite structure comprising high Young's modulus layer and the pattern photomasking layer is brought into contact with the PDMS-coated silicon substrate. A force is applied to the external surface of the high Young's modulus layer and the PDMS layer is cured at a temperature between 60 – 80 degrees Celsius for a few hours. Finally, the PDMS layer is separated from the silicon substrate thereby forming the composite soft conformal photomask.

Example 5: Lock and Key Registration System Using Patterning Agent

[00203] The present invention provides methods and patterning devices and/or substrate surfaces having specific relief patterns, such as alignment channels, troughs and/or grooves, useful for providing proper registration and alignment of patterning devices and substrate surfaces. Particularly, use of "lock and key" alignment systems comprising complimentary (i.e. mating) relief features and recessed regions is useful in the present invention because engagement of complementary features constrains the possible relative orientations of the contact surface of a patterning device and a substrate surface. The ability to constrain the relative orientation of these elements is

particularly useful for fabricating devices and device arrays with good placement accuracy over large substrate areas.

[00204] In one aspect, the present invention includes alignment systems using a patterning agent for establishing and maintaining a selected spatial alignment between the contact surface of a patterning device, such as the contact surface of a composite patterning device or the contact surface of a single layer patterning device, and a selected region of the substrate surface. In the context of this description, the term “patterning agent” refers to one or more materials that are provided between at least a portion of the contact surface of a patterning devices and a substrate surface undergoing processing. In this aspect of the present invention, the patterning agent functions to facilitate proper alignment and engagement of complementary relief features and recessed regions in a manner resulting good registration of these elements. Patterning agents of the present invention may provide functionality other than or in addition to facilitating proper alignment of a patterning device and a substrate surface. In one embodiment, patterning agents of the present invention comprise an optical filtering medium for a photomask of the present invention. In another embodiment, patterning agents comprise a transfer material that is molded onto a substrate surface, for example a prepolymer material that is molded into a pattern embossed on the substrate surface upon exposure to electromagnetic radiation or upon increasing temperature. Patterning agents of the present invention may also provide a multifunctional character such as a combination of facilitating alignment of a contact surface of a patterning device and a substrate surface undergoing processing and providing optical filtering and/or a transfer material for patterning a substrate surface.

[00205] In one embodiment, patterning agents of the present invention act as lubricants by reducing friction generated between a mating contact surface and substrate surface pair of an alignment system, such as a lock and key registration system. By reducing friction, the patterning agent allows the patterning device and the substrate to establish conformal contact and move relative to each other, thereby sampling a range of possible relative orientations. In this aspect of the present invention, additional mobility provided by the patterning agent allows the patterning device and substrate surface to realize a stable, selected relative orientation characterized by effective coupling between complementary relief features and recessed regions on the mating surfaces. Effective patterning agents facilitate establishing correct registration without interfering with establishment of conformal

contact. Useful patterning agents include fluids, such as liquids and colloids, thin films and particulate materials. Exemplary patterning agents include Optical Brightener, Benetex OB-EP from Mayzo, Parker ink, Water soluble black wooden dye Powder from Constantines Wood Center.

5 **[00206]** Patterning devices of this aspect of the present invention have a contact surface having a plurality of recessed regions or relief features having shapes and physical dimensions that are complementary to recessed regions or relief features on a substrate surface undergoing processing. Patterning devices of this aspect of the present invention also have a means for introducing the patterning agent into a least a
10 part of the region between the contact surface and the substrate surface. Means for introducing the patterning agent can be a fluidic channel, groove or may involve wetting the contact surface or substrate surface prior to establishing conformal contact, for example using a dipping system. To achieve registration, the patterning device and substrate surface are gradually brought into contact by establishing an appropriate
15 force, for example a force directed orthogonal to a plane containing at least a portion of the contact surface. Optionally, alignment may involve movement of the mating surface of the patterning device and the substrate surface in other directions, for example by lateral movement of the surfaces.

[00207] In another aspect, the patterning agent acts as the optical filtering medium
20 for a conformable photomask. In this aspect of the invention, the composition of the patterning agent is selected such it that it absorbs, scatters, reflects or otherwise modulates some property of electromagnetic radiation directed onto the photomask, thereby selectively adjusting the intensities, wavelengths and polarization states of light transmitted onto a substrate surface undergoing patterning. In one embodiment, for
25 example, the patterning agent is provided between a conformable photomask having a relief pattern and the external surface of a substrate. Conformal contact between the photomask and the external surface of the substrate generates a series of spaces occupied by the patterning agent that are defined by the relief features and recessed regions of the relief pattern. These spaces may comprise a series of channels,
30 chambers, apertures, grooves, slits and/or passages positioned between the photomask and the external surface of the substrate. The shapes and physical dimensions of the relief features and recessed regions of the photomask determine optical thicknesses of the patterning agent present in the spaces between the photomask and the substrate surface. Selection of the relief pattern geometry and composition of the patterning

agent, therefore, provides a means of modulating transmitted electromagnetic radiation to achieve selected two dimensional spatial distributions of the intensities, wavelengths and/or polarization states of light transmitted onto the substrate surface. This aspect of the invention is particularly useful for patterning substrate surfaces having a layer of photosensitive material deposited on their external surfaces.

[00208] Advantages of this patterning approach of the present invention include (i) it is compatible with the types of composite patterning devices described throughout this application, (ii) the patterning agent can have low viscosity, which enables it to flow rapidly and effectively as the patterning device is brought into contact with the patterning agent (which helps to push most of the patterning agent out of the regions that correspond to raised areas on the patterning device), (iii) it lubricates the interface between the contact surface (or coated contact surface) and the substrate surface (or coated substrate surface), (iv) it does not alter the stretchability of the patterning device, which is an important characteristic, especially if the patterning device has to stretch to match the lock and key features (due to slight deformations in the substrate, for example) and (v) it can pattern conventional photoresists whose processing conditions and uses are well established for many important electronic and photonic applications.

[00209] Figures 19A and 19B provide schematic diagrams showing alignment systems using a patterning agent for aligning a photomask and substrate. Referring to Figures 19A and 19B, the alignment system **1300** of the present invention comprises a conformable photomask **1305** having a contact surface **1306**, a substrate **1310** with an external surface **1313** undergoing processing and a patterning agent **1315** disposed between the contact surface **1306** and external surface **1313**. In the embodiment shown in Figures 19A and 19B, external surface **1313** undergoing processing is coated with a photosensitive layer **1314**, such as a photoresist layer. In the design shown in Figure 19A, conformable photomask **1300** comprises a first polymer layer, for example a PDMS layer, having a plurality of recessed regions **1320** having shapes and physical dimensions that are complementary to relief features **1325** present on external surface **1313** undergoing processing. In the design shown in Figure 19B, conformable photomask **1300** comprises a first polymer layer, for example a PDMS layer, having a plurality of relief features **1340** having shapes and physical dimensions that are complementary to recessed regions **1345** present on external surface **1313** undergoing processing. Relief features and recessed regions of this aspect of the present invention may have any pair of complementary shapes including, but not limited to, having shapes

selected from the group consisting of pyramidal, cylindrical, polygonal, rectangular, square, conical, trapezoidal, triangular, spherical and any combination of these shapes.

[00210] Optionally, conformable photomask **1305** may further comprise additional relief features **1308** and recessed regions **1307** having selected shapes and physical dimensions. As shown in Figures 19A and 19B, conformal contact of photomask **1305** and external surface **1313**, generates a plurality of spaces occupied by patterning agent **1315**, because substrate **1310** is not provided with relief features and recessed regions complementary to additional relief features **1308** and recessed regions **1307**. In one embodiment, patterning agent **1315** is a material that absorbs, reflects or scatters electromagnetic radiation directed onto photomask **1305** and, therefore, the shapes and physical dimensions of relief features **1308** and recessed regions **1307** establishes two dimensional spatial distributions of intensities, wavelengths and/or polarization states of electromagnetic radiation transmitted to photosensitive layer **1314** on external surface **1313**. In this manner, selected regions of photosensitive layer **1314** may be illuminated with selected intensities of electromagnetic radiation having selected wavelengths and polarization states, and selected regions of photosensitive layer **1314** may be shielded from exposure to electromagnetic radiation having selected wavelengths and polarization states. This aspect of the present invention is useful for patterning photosensitive layer **1314** by exposure to electromagnetic radiation characterized by a selected two dimensional spatial distribution of intensities capable of generating chemically and/or physically modified regions of photosensitive layer **1314** corresponding to a desired pattern. In one embodiment, the photomask **1305** is a phase only photomask which is substantially transparent. In this embodiment, it only forms an amplitude photomask when the patterning agent is present between contact surface **1306** and external surface **1313**.

[00211] In another embodiment, patterning agent **1315** is a transfer material for molding patterns onto the substrate surface. In this embodiment, therefore, the shapes and physical dimensions of relief features **1308** and recessed regions **1307** establishes features of a pattern that is embossed onto photosensitive layer **1314** on external surface **1313**. Embodiments of this aspect of the present invention, are also useful for patterning a substrate surface via molding patterns on external surface **1313** directly (i.e. without photosensitive layer **1314** present).

[00212] Optionally, conformable photomask **1305** is a composite photomask further comprising additional polymer layers, such as high Young's modulus layers, composite polymer layers and low Young's modulus layers (not shown in Figures 19A and 19B). As discussed throughout the present application, patterning device of the present invention having one or more additional polymer layers provides beneficial mechanical and/or thermal properties. Patterning devices of this Example of the present invention, however, do not have to be composite patterning devices.

[00213] To generate a pattern on the surface of substrate **1310**, patterning agent **1315** is provided between the contact surface **1306** of conformable photomask **1305** and external surface **1313**, and the contact surface **1306** and external surface **1313** are brought into conformal contact. Patterning agent **1315** lubricates the interface between the first polymer layer of conformable photomask **1305** and the photosensitive layer **1314** on external surface **1313**. The decrease in friction caused by the presence of the patterning agent **1315** enables the contact surface **1306** to align with the external surface **1313** such that the relief features (**1325** or **1340**) to optimally engage with recessed regions (**1320** or **1345**). Optimal alignment is achieved by providing a gradual force that brings the mating surface together, such as a force directed along an axis orthogonal to the contact surface (schematically represented by arrows **1380**). Optionally, contact surface **1306** and external surface **1313** may be moved laterally (along an axis parallel to axis **1390**) to enhance establishing of optimal engagement of recessed regions (**1320** or **1345**) and relief features (**1325** or **1340**).

[00214] The conformable photomask **1305** is illuminated with electromagnetic radiation, and transmits electromagnetic radiation having a selected two dimensional spatial distribution of intensities, wavelengths and/or polarization states to photosensitive layer **1314**. For example, patterning agent **1315** present in the region between relief features **1308** and recessed regions **1307** and external surface **1313** may absorb, scatter or reflect incident electromagnetic radiation, thereby providing spatially resolved optical filtering functionality. For example, in one embodiment patterning agent **1315** absorbs UV electromagnetic radiation, thus creating contrast for patterning the photosensitive layer **1314** with ultraviolet light. The transmitted electromagnetic radiation interacts with portions of photosensitive layer **1314** thereby generating patterns of chemically and/or physically modified regions. After exposure to sufficient electromagnetic radiation for a given application, conformable photomask **1305** and substrate **1310** are separated, and photosensitive layer **1314** is developed by either

removing at least a portion of chemically and/or physically modified regions of photosensitive layer **1314** or by removing at least a portion of photosensitive layer **1314** that is not chemically and/or physically modified.

[00215] Figure 20 provides a schematic diagram illustrating an exemplary patterning method of the present invention using a patterning agent that comprises an optical medium (or ink) of conformable photomask. As shown in Figure 20, a substrate having a photoresist layer on its external surface is provided. The photoresist layer is contacted with a patterning agent comprising an ink and a conformable photomask is brought into conformal contact with the substrate. As shown in Figure 20, the pattern agent is present in spaces defined by the relief pattern of the conformable photomask. The conformable photomask is illuminated with electromagnetic radiation, and the pattern agent modulates the intensity of the electromagnetic radiation transmitted to the photoresist layer. As illustrated in Figure 20, the conformable photomask is then removed and the photoresist layer is developed, thereby generating a pattern on the substrate surface defined by the optical thicknesses of pattern agent present between the photomask and substrate.

[00216] The invention further provides methods, devices and device components for fabricating patterns on substrate surfaces, such as three-dimensional patterns comprising microscaled structures and/or nanosized structures. The present invention provides patterning devices, such as stamps, molds and photomasks, with patterning agents for generating three-dimensional patterns. The methods, devices and device components of the present invention are capable of generating high resolution patterns exhibiting good fidelity and excellent placement accuracy.

Example 6: Ink Stamp Photomask for Printing by Soft Photolithography

[00217] In an embodiment, provided is a flexible elastomer mask having relief structures used in combination with UV absorbable ink that is the patterning agent to generate patterns on a substrate by photolithography (see **FIG. 26**). This combination can work as a binary amplitude mask for photolithography. In this process a UV absorbable ink is placed between a layer of photoresist on a substrate and the elastomer mask having patterned relief structures on its surface. The ink can lubricate adjacent surfaces, and is particularly useful for multilevel patterning and UV absorption to generate patterns arising from chemical alteration differences on the underlying UV-sensitive material. The elastomeric mask is pushed against the photoresist such that

the ink is localized to the recessed regions of the three-dimensional relief pattern on the elastomeric stamp. The photoresist is irradiated by, for example, UV light that travels through the elastomeric mask. The intensity of UV light is spatially modulated by the presence of UV-absorbing ink, with lower intensity regions corresponding to regions of photoresist underlying regions where the UV light-path through ink is larger. UV intensity accordingly corresponds to the depth of the ink-filled recess feature in the elastomeric mask. Removing the stamp, rinsing away the ink, and developing the photoresist generates patterns of resist that can then be used, for example, in conventional processing sequences to pattern other materials. Stamps with multiple and/or continuously varying relief depths can be used with inks to achieve "gray scale" modulation of the transmitted light to generate resist features comprising patterns having complex shapes with variable recess and/or relief feature depth.

[00218] In an important embodiment, the molded structure made by the processes of the present invention is a photomask useful for generating patterns in a photosensitive material, such as a photoresist. In these embodiments, the molded structure is generated on an external surface of the photosensitive material. The molded structure is subsequently separated from the patterning device, and illuminated by electromagnetic radiation so as to provide patterning of the underlying photosensitive material. As will be understood by those skilled in the art of optical lithography, the molded structure itself functions as a photomask in these embodiments independent of the patterning device used to fabricate the molded structure.

[00219] **FIG. 21** is a schematic illustration of an exemplary device and method for generating a pattern using an ink-based soft photolithography process. **FIG. 21A** provides an initial configuration of a polymer layer or elastomeric patterning device **2100**, in proximity to a patterning agent **2200** on a photosensitive layer **2300**, such as a photoresist, that at least partially overlies substrate **2400**. The patterning device **2100** has a three-dimensional relief feature **2120** and corresponding recess feature pattern **2130**. The exposed relief and recess features together define the three-dimensional pattern **2105**. A force **2600** is applied to establish conformal contact between at least a portion of patterning device contact surface **2110** and photoresist internal surface **2310** (**FIG. 21B**). Patterning agent **2200** fills and is localized to recess features **2130**. As used herein, "fill" or "localized" refers to a substantial amount of patterning agent being contained within the recesses **2130**. A "substantial amount" refers to sufficient patterning agent in the recess **2130** such that the intensity or quality of signal **2700**,

wherein the signal can be an optical property of electromagnetic radiation, reaching surface **2310** (**FIG. 21C**) is different for regions below the recess **2130** compared to regions below relief pattern **2120** so that there is a differential chemical response in each of the photoresist regions. The spatial distribution of signal (e.g., UV light) **2700** intensities on photoresist surface **2310** results in a photoresist pattern comprising relief features **2320** and recessed features **2330** that correspond to recess **2130** and relief **2120** features on polymer stamp **2100**, respectively (**FIG. 21D**). By varying one or more of three-dimensional pattern **2105** exposure time, and patterning agent absorptive properties, interconnections between relief features are generated to facilitate optional lift-off of patterned photoresist **2300** from substrate **2400**.

[00220] In one embodiment, patterning agent **2200** is a material that absorbs, reflects or scatters electromagnetic radiation directed onto photomask **2100** and, therefore, the shapes and physical dimensions of relief features **2120** and recessed regions **2130** establishes two dimensional spatial distributions of intensities, wavelengths and/or polarization states of electromagnetic radiation transmitted to photosensitive layer **2300** on substrate **2400**. In this manner, selected regions of photosensitive layer **2300** may be illuminated with selected intensities of electromagnetic radiation having selected wavelengths and polarization states, and selected regions of photosensitive layer **2300** may be shielded from exposure to electromagnetic radiation having selected wavelengths and polarization states. This aspect of the present invention is useful for patterning photosensitive layer **2300** by exposure to electromagnetic radiation characterized by a selected two dimensional spatial distribution of intensities capable of generating chemically and/or physically modified regions of photosensitive layer **2300** corresponding to a desired pattern. In one embodiment, the photomask **2100** is a phase only photomask which is substantially transparent. In this embodiment, it only forms an amplitude photomask when the patterning agent is present within recess features **2130** during conformal contact between contact surface **2110** and surface **2310**.

[00221] **FIGs. 22-24** are three different gray-scale generation examples illustrating that the devices and methods of the present invention can be used to generate more complex patterns by modifying the geometry of polymer pattern **2105**. **FIG. 22A** shows patterning agent **2200** filling triangular-shaped recesses in patterning device **2100** when polymer **2200** is contacted with photoresist **2300** overlying substrate **2400**. **FIG. 22B** shows the generated pattern after UV illumination, removal of patterning device **2100**

and patterning agent **2200** and development of photoresist. **FIG. 23** shows a resultant pattern generated by a series of curved recess patterns. **FIG. 24** shows that polymer recess features having different depths results in generation of relief pattern features each having different heights. The generated patterns depicted in **FIGs. 21-24** can be mixed and matched to simultaneously generate a number of geometrical features having distinct shapes, geometries and/or dimensions. The ability to generate even more complex shapes is possible by applying a plurality of patterning agents, each having different absorptive/transmission properties. Using a three-dimensional polymer surface as a conduit for microfluidic flow, multiple patterning agents can occupy an individual recess pattern without significant mixing under laminar flow conditions. As used herein, flow is laminar for Reynolds numbers less than 2000, less than 1000, or less than 100.

[00222] In one aspect, the present invention includes alignment systems using a patterning agent for establishing and maintaining a selected spatial alignment between the contact surface of a patterning device, such as the contact surface of a composite patterning device or the contact surface of a single layer patterning device, and a selected region of the substrate surface. In the context of this description, the term "patterning agent" refers to one or more materials that are provided between at least a portion of the contact surface of a patterning devices and a substrate surface undergoing processing. In this aspect of the present invention, the patterning agent functions to facilitate proper alignment and engagement of complementary relief features and recessed regions in a manner resulting good registration of these elements. Patterning agents of the present invention may provide functionality other than or in addition to facilitating proper alignment of a patterning device and a substrate surface. In one embodiment, patterning agents of the present invention comprise an optical filtering medium for a photomask of the present invention. In another embodiment, patterning agents comprise a transfer material that is molded onto a substrate surface, for example a prepolymer material that is molded into a pattern embossed on the substrate surface upon exposure to electromagnetic radiation or upon increasing temperature. Patterning agents of the present invention may also provide a multifunctional character such as a combination of facilitating alignment of a contact surface of a patterning device and a substrate surface undergoing processing and providing optical filtering and/or a transfer material for patterning a substrate surface.

[00223] FIG. 25 illustrates a lock-and-key registration feature that is useful, for example, to ensure that the elastomer deforms to match substrate distortions. FIG. 25A illustrates a lock feature 2840 that is a recess feature on the patterning device 2100 and a corresponding key feature 2820 that is a relief feature on the photoresist 2300 and substrate 2400. There is an initial mismatch as denoted by the label "misfit." FIG. 25B shows the patterning device 2100 is aligned relative to substrate 2400 by stretching elastomer 2100 and inserting key 2820 into lock 2840. With this alignment system, any subsequent deformations in substrate 2400 causes associated deformations in patterning device 2100, thereby ensuring increased pattern fidelity and accuracy. FIG. 25 illustrates that the patterning agent 2200 can be registrably addressed and deposited on a surface. In other words, the patterning agent 2200 can be positioned or aligned with respect to the patterning device 2100 three-dimensional pattern of recess features, photoresist 2300 and/or substrate 2400. As discussed below, one example of using this addressable droplet patterning is having selected hydrophilic and/or hydrophobic regions of the surface of photoresist 2300. In addition to controllably positioning individual ink droplets or features, the volume within each droplet or feature can also be controllably selected and applied. The term "droplet" is used broadly to encompass application of a pattern of droplets and droplets addressed to specific regions of substrate surface (e.g., positioned relative to hydrophilic and/or hydrophobic regions).

[00224] Advantages of this patterning approach of the present invention include (i) it is compatible with the types of composite patterning devices described throughout this application, (ii) the patterning agent can have low viscosity, which enables it to flow rapidly and effectively as the patterning device is brought into contact with the patterning agent (which helps to push most of the patterning agent out of the regions that correspond to raised areas on the patterning device), (iii) it lubricates the interface between the contact surface (or coated contact surface) and the substrate surface (or coated substrate surface), (iv) it does not alter the stretchability of the patterning device, which is an important characteristic, especially if the patterning device has to stretch to match the lock and key features (due to slight deformations in the substrate, for example) and (v) it can pattern conventional photoresists whose processing conditions and uses are well established for many important electronic and photonic applications.

Example 7: Molded structure Generation by Ink Polymer Stamp Lithography

[00225] In an embodiment, the pattern can be generated by and constrained to the three-dimensional pattern associated with the contact surface of the patterning device **2100** (FIG. 26). FIG. 26A shows the patterning agent **2200** positioned between the patterning device **2100** and substrate **2400**. A force is applied to bring at least a portion of contact surface **2110** of patterning device **2100** into contact with at least a portion of substrate internal surface **2410**, thereby squeezing excess patterning agent **2200** out from the region between contact surface **2110** and substrate **2400**. FIG. 26B illustrates an optional means for removing excess patterning agent comprising a channel **2500** that conveys excess patterning agent **2210** from between contact surface **2110** and internal substrate surface **2410**. FIG. 26C shows that after exposure to a patterning agent chemically-altering signal, the patterning device **2100** is removed to reveal a patterning agent relief pattern **2220**.

[00226] For the photoresist applications, suitable patterning agents including prepolymers in liquid form with low viscosity at processing conditions. Suitable inks include, but are not limited to, Parker ink, water soluble wood dye and optical brighter. All these inks absorb UV light at a spectrum that is sensitive to the photoresist. FIG. 27 shows the UV transmission of black wood dye indicating that the ink absorbs substantially all UV light. Accordingly, the ink that fills the recesses **2130** in the patterning device **2100** function as a photomask in a manner similar to conventional rigid masks. However, due to the low viscosity, flexible nature of the polymer, and the ability to manufacture complex three-dimensional patterns associated with the polymer contact surface, the ink lithography devices and methods disclosed herein are well suited for pattern generation on curved flexible plastic substrates. A patterning agent can be selected by those of ordinary skill in the art, recognizing that the patterning agent should be capable of filling the recess features **2130** when the device **2100** is forced into contact with substrate **2400** and that the patterning agent should absorb at a wavelength that affects (e.g. chemically alters) the photoresist. The absorptive properties of a patterning agent can be controlled by, for example, varying the ink concentration in the solution.

[00227] Alternatively, in the embodiment where the pattern is generated within the recess features **2130**, the patterning agent should remain capable of filling recess features **2130**, as described and capable of undergoing a chemical or physical property

alteration or change in response to exposure to a signal. For example, the recesses could be filled with a prepolymer liquid and cross-linking initiated in response to a UV signal, or crystallization can occur in response to pulsed energy sources.

Example 8: Pattern Generation

5 **[00228]** The polymer stamp interaction with a patterning agent is shown in **FIG. 28**. **FIG. 28A** is a top-view photomicrograph of a PDMS stamp floating on ink. There is no externally applied force to generate intimate contact between the polymer and the substrate. Only portions of each recess feature are filled with ink and there is substantial excess ink present in the non-recess feature regions. **FIG. 28B** shows the
10 PDMS stamp pressed onto the ink and the photoresist substrate layer with the relief features filled with ink. As discussed below, a UV-absorbant ink that absorbs substantially all UV signal results in the process tolerating trapped air pockets in the recess features of the polymer. **FIG. 28B** indicates that most of the excess ink is squeezed out from between the stamp and photoresist. **FIG. 28C** is a photomicrograph
15 of the resultant pattern etched into the photoresist after UV exposure, and processing. The relief features in the photoresist correspond to regions of photoresist below the ink filled recesses outlined in **FIG. 28B**.

[00229] Registration between the polymer stamp and substrate can be done manually by shifting the polymer stamp over the substrate surface because the ink is an
20 effective lubricant. Alternatively, an alignment system can facilitate precise registration. For example, alignment marks at two layers can be aligned and optically verified by microscopic evaluation of a conventional mask aligner. This is a practical method of making a multilayer structure on a plastic substrate. **FIG. 29** shows registration of two layers on a plastic substrate. Initially, a silicon network is deposited on a plastic
25 substrate (**FIG. 29A**). This silicon network is then patterned by the methods and devices of the present invention into regular squares (**FIG. 29B**). Subsequent patterning of a MOSFET is aligned onto the silicon network squares (**FIG. 29C**). As demonstrated by **FIG. 29C**, appropriate alignment means can be important in certain patterning applications.

30 **[00230]** **FIGs. 30-31** illustrate a benefit and advantage of using a patterning agent within recessed features to function as a mask. **FIG. 30A** illustrates use of a conventional phase mask without a patterning agent that is a UV absorber. **FIG. 30B**

and **30C** show the resultant etched pattern after 3.5 second and 4 second UV exposure, respectively. The photoresist is subsequently developed for 7 seconds.

[00231] **FIG. 31A** summarizes the process for when a UV absorbent patterning agent is present. **FIG. 31B** is an image of the etched pattern without a patterning agent and **FIG. 31C** is an image of a pattern obtained when a UV-absorbant patterning agent is used. The difference is that without UV ink only a thin strip (e.g., about 140 nm) is not etched. UV-absorbant ink, in contrast, protects underlying photoresist so that 2.32 μm wide strips of photoresist are not etched (see **FIG. 31C**, right panel). In conventional soft lithography using an elastomer mask as optical element (near field phase shift lithography), the transparent elastomer works only as phase modulating element. Consequently, patterning is limited to the edge boundary of relief feature and forms only thin lines or dot shapes. Stretching elastomer mask results in less definite patterning due to the shape change of phase mask.

[00232] The present invention can pattern features over a large area reliably.

Patterning micron-sized features, for example, is accomplished in an embodiment by: (1) Spin coating photoresist Shipley 1818 onto silicon wafer at 3000 rpm; (2) Prebake the photoresist at 115°C for 10 min to harden photoresist; (3) Spin cast the ink (Mayzo, UV absorber) onto photoresist at 9000 rpm to uniformly reduce ink depth; (4) Provide a relieved PDMS stamp; (5) Press the stamp against the ink-coated photoresist. An appropriate applied force corresponds to removal of the thin ink layer at the interface between the stamp and photoresist. In this example, the ink layer is so thin that the recess features on the polymer PDMS stamp is not completely filled and bubbles in the recess features may be observed; (6) Irradiate with UV light for an appropriate length of time to match the dose contrast arising from the ink-filled PDMS mask; and (7) Develop.

FIG. 32 shows the patterning of 5 μm features over a 2x2cm area. **FIG. 32** is a pattern obtained by four consecutive lithography applications indicating the procedure is reliable and reproducible. Even further resolution is obtained by using the invention in water immersion mode lithography to obtain shorter optical wavelength and higher numerical aperture.

Example 9: Effect of Patterning Agent Coating Thickness

[00233] The effect of photopatterning agent on signal intensity on the photoresist surface can be modeled by finite element analysis to calculate the effect of UV-absorbant ink on the spatial distribution of UV intensity on the photoresist. For example,

FEMLAB software is used to examine the effect of ink coating depth on optical intensity below the ink. **FIG. 33A** shows UV-intensity across a photoresist for an uncoated system (e.g., no patterning agent **2200** covering photoresist interior surface **2310**), where all excess ink is removed from between patterning device **2100** contact surface and photoresist surface **2310**. The patterning agent **2200** that is UV-absorbable ink is restricted to patterning device recess feature **2130**. The results of the simulation indicate that the ink effectively blocks UV transmission underneath the recessed feature, and that the regions of exposed photoresist experience significant UV exposure. **FIG. 33B** shows the computational results for a 50 nm coating of UV absorbent ink on the surface of the photoresist. The results suggest that even thin layers of the ink can affect UV dose to the photoresist. The photoresist underlying the thin coating, however, receives significant UV exposure relative to the photoresist underneath recess feature **2130**, such that patterns are still generated. These studies suggest it is beneficial to remove as much excess ink as possible to increase resolution. Depending on the pattern geometry to be made, resolution may be increased by altering the patterning agent to permit more UV transmission. These results indicate that the ink lithography process disclosed herein can tolerate incomplete ink filling of polymer recess feature as relatively small layers of ink effectively blocks UV exposure.

[00234] Elastomer materials for relief mask are selected for their compatibility with various solvents. Commercial silicone elastomer (PDMS, sylgard 184) and photocurable perfluoropolyethers (PFPEs) are examples of suitable materials. Modeling results also support the absorption response behavior of ink. As discussed herein, by varying the ink concentration and selecting different inks, the amount of UV transmission is controllably varied. The ink material can be water soluble UV-absorber, which is desirable because: i) it avoids dissolving photopolymer; ii) it does not swell the elastomer network of relief and recess features; iii) it minimizes the use of harmful materials; and iv) it is simple to clean after exposure.

[00235] Additional embodiments of the present invention are provided in **FIGs 34** and **35**. An important feature of the present invention is conformal contact between the contact surface of the elastomeric patterning device **2100** and surface of substrate **2400**. **FIG. 34** illustrates that conformal contact is possible by providing a pressure-controllable chamber **2930** defined by soft membrane **2910** and chamber top **2900** and top surface of patterning device **2100**. By increasing the pressure within chamber **2930**

the pressure on the top surface of device **2100** is increased, thereby increasing the force that generates conformal contact of device **2100** with substrate **2400**.

[00236] **FIG. 35** illustrates an optional processing technique, UV/ozone treatment ("UVO") (Childs et al., Masterless Soft Lithography: Patterning UV/Ozone-Induced Adhesion on Poly(dimethylsiloxane) Surfaces. Langmuir, 21 (22), 10096 -10105, 2005), to locally control the quantity of the ink that wets the surface. Corresponding hydrophilic areas **2315** facilitate addressable application of patterning agent droplets **2200** to the photosensitive material surface **2310**. The substrate can then be patterned "as-is", with a pattern generation corresponding to hydrophilic and/or hydrophobic regions. Such a liquid patterning agent device is a "liquid amplitude mask." For finer feature generation, the system can further comprise a patterning device having finer recess pattern in contact with the substrate-coated surface. The patterning agent can be deposited as thin films by any process known in the art such as processes used in ink jet printing, spin coating and dipping. The printer head can be loaded with patterning agent and a pressure used to expel patterning agent in a predetermined pattern and/or depth. Alternatively, for patterning agents that are charged, an electric potential can be used to expel patterning agent in a predetermined pattern and/or depth. Alternatively, the patterning agent is applied with a stamp.

Example 10: Stamps Having Amplitude Modulation Capability

[00237] **FIGs. 37-39** provide examples of patterning devices having another level of amplitude or grey-scale control by conferring modulation control to the stamp. **FIG 37** summarizes surface modification of selected recess regions to provide a stamp that is capable of amplitude modification. In an embodiment, the surface modification is a thin film **2730** in a recess feature **2130**, where the thin film has optical modulating capabilities that can enhance the modulating capability of patterning agent localized within recessed feature **2130**. The thin film can be selectively applied to individual recess features, all the recess features, individual relief features, or all the relief features.

[00238] **FIG. 38** shows a thin film **2740** having optical modulating that is placed on the top surface **2710** of elastomeric patterning device **2100**. The thin layer can be applied in a selected pattern as shown in **FIG. 38**, or can cover substantially all the top surface **2710**. This patterning is optionally combined with the thin film application in

recessed features summarized in **FIG. 37**. The thin film **2730** or **2740** can itself comprise a patterning agent having a selected optical modulating characteristic.

[00239] Another technique useful for imparting amplitude-modulating capability to a patterning device **2100** is embedding particles **2750** that have optical-modulating capability in the device **2100**. **FIG. 39A** shows such particles **2750** that are applied in a pattern. The pattern may correspond to the pattern of recess or relief features on a surface of the elastomeric patterning device **2100**. Particles **2760** may also be applied to the surface of the elastomeric patterning device **2100** (**FIG. 39B**). The particles **2750** or **2760** may be patterned in a layer that spans the length and width of the device **2100** and can further comprise multiple layers. Alternatively, the particles **2750** may be dispersed throughout the height of the device **2100**.

[00240] **FIGs. 40-41** summarize methods of the present invention using mold structure generation by ink lithography to produce a photomask useful in generating patterned structures by photolithography. **FIG. 40A-B** is similar to **FIG. 21A-B** in that a patterning device **2100** is brought into conformal contact with a surface, and patterning agent **2200** is localized to recess features in the device **2100**. The patterning agent **2200** undergoes a physical or chemical change in response to EMR (electromagnetic radiation) (**FIG. 40B**) or other signal, and removing device **2100** generates a molded structure on a surface of a photosensitive material (e.g. layer of photoresist) **2300** (**FIG. 40C**). In this embodiment, the molded structure functions as a photomask **2770** capable of modulating an optical property. The molded structure functioning as photomask **2770** (**FIG. 40D**) is illuminated with EMR so as to generate a two-dimensional distribution of an EMR property over the surface of the photosensitive layer **2300**. Subsequent processing and development generates a pattern on a substrate layer **2400**. **FIG. 40** illustrates a pattern of geometrical features generated via illumination of the molded structure functioning as photomask **2770**. In an embodiment, the pattern comprises a pattern of functional properties, such as electrical or thermal properties, wherein there is no change in the geometry of the photosensitive layer **2300**. Instead, there can be a patterned change in a physical characteristic to generate a functional device, such as an electrical circuit, dielectric or devices having thermally conductive regions.

[00241] Examples of pattern generation are provided in **FIGs 42-54**, and particularly demonstrate the effect of patterning agent on pattern generation. **FIG. 42**

provides a schematic diagram illustrating a method for patterning a photoresist using a patterning agent that is UV absorbent. **FIGs 43-45** are examples of three different patterned PDMS phase masks and resultant pattern generation with and without a patterning agent that is a UV absorber ("UVINUL3048"). **FIGs 46-47** are images of generated square dot patterns in processes that use the UV absorber Ruthenium(II) Hexahydrate.

[00242] **FIGs 48-54** summarize pattern generation of V-shaped grooves with or without a patterning agent and for different developing conditions (10 seconds or 45 seconds). **FIG. 48** provides a schematic diagram illustrating a method for patterning a photoresist to a grooved pattern. The shape of the three-dimensional patterning devices surfaces is provided in **FIGs 49-50** (e.g., grey-scale, having a variable height component and a constant height component). **FIGs 51** and **53** are images of the generated pattern for when no patterning agent is used and for 10 and 45 second development time, respectively. The geometry of the generated relief feature tends to be of uniform height and does not satisfactorily reproduce the three-dimensional feature of the PDMS stamp (e.g., the grey scale groove). In contrast, **FIGs 52** and **54** use patterning agent to generate grey-scale relief features that correspond to the three-dimensional feature of the PDMS stamp. For increasing development time, the depth of etching increases (e.g., 10 seconds results in 600 nm maximum; 45 seconds results in 1 μ m maximum).

REFERENCES

- [00243]** U.S. Pat. App. No. 11/115,954 (U.S. Pub. No. 20050238967)
- [00244]** Chen et al. Gray-scale photolithography using microfluidic photomasks. PNAS 100(4): 1499-1504 (2003).
- [00245]** Chou. Nanoimprint lithography and lithographically induced self-assembly. MRS Bull. 512-517 (2001).
- [00246]** Rogers et al. Using an elastomeric phase mask for sub-100 nm photolithography in the optical near field. Appl. Phys. Lett 70(20):2658-2660 (1997).
- [00247]** Rogers et al. Wave-front engineering by use of transparent elastomeric optical elements. App. Opt. 36(23):5792-5795 (1997).

[00248] Rogers and Nuzzo. Recent progress in soft lithography. *Materials Today* 50-56 (2005).

[00249] Xia et al. Unconventional Methods for fabricating and patterning nanostructures. *Chem. Rev.* 99:1823-1848 (1999).

- 5 **[00250]** Zaumseil et al. Three-dimensional and multilayer nanostructures formed by nanotransfer printing. *Nano Letters* 3(9):1223-1227

CLAIMS

We claim:

1. A method of processing a surface of substrate, said method comprising the steps of:
 - a) providing an elastomeric patterning device having a three-dimensional pattern of recessed features on an external side, wherein said external side has at least one contact surface disposed thereon;
 - b) providing a patterning agent on at least a portion of the surface of the substrate; and
 - c) contacting the elastomeric patterning device with the substrate in a manner establishing conformal contact between at least a portion of the contact surface of the elastomeric patterning device and the surface of the substrate having said patterning agent, wherein said conformal contact results in said patterning agent filling at least a portion of said recessed features of said elastomeric pattern device, thereby processing said surface of said substrate.
2. The method of claim 1, wherein said elastomeric patterning device is at least partially transparent; said method further comprising exposing said elastomeric patterning device in conformal contact with said substrate to electromagnetic radiation; wherein said patterning agent in said recessed features of said elastomeric pattern device modulates an optical property of electromagnetic radiation transmitted by the elastomeric patterning device and the patterning agent in said recessed features.
3. The method of claim 2, wherein said optical property is selected from the group consisting of intensity, phase, wavelength, polarization state, and any combination of these.
4. The method of claim 3 wherein said patterning agent in said recessed features of said elastomeric pattern device absorbs, scatters or reflects electromagnetic radiation exposed to said elastomeric patterning device, thereby generating said electromagnetic radiation transmitted by said elastomeric patterning device and said patterning agent in said recessed features, wherein said transmitted electromagnetic radiation has a selected two-dimensional spatial distribution of said optical properties.

5. The method of claim 3, wherein said substrate comprises a layer of photosensitive material on a supporting material in conformal contact with said contact surface; and wherein said electromagnetic radiation transmitted by said elastomeric patterning device and said patterning agent in said recessed features interacts with said layer of photosensitive material.
6. The method of claim 5, wherein the photosensitive material comprises a photoresist.
7. The method of claim 4, wherein said transmitted electromagnetic radiation selected two-dimensional spatial distribution is generated by shaping said three-dimensional pattern of recessed features, thereby generating said selected two-dimensional spatial distribution.
8. The method of claim 7, wherein said shaping comprises varying one or more of position, length, depth or cross-sectional shape of one or more of said recessed features.
9. The method of claim 8, wherein said recessed feature has a non-uniform depth, a cross-sectional shape that varies with depth, or both.
10. The method of claim 4, wherein said selected two-dimensional spatial distribution of said optical property is generated by providing patterning agent in droplet form, wherein one or more droplets has a different composition from that of at least one other droplet, thereby differentially modulating said optical property of electromagnetic radiation.
11. The method of claim 4, wherein said two-dimensional spatial distribution of said optical property varies in one or two spatial dimensions.
12. The method of claim 11, wherein said two-dimensional spatial distribution of said optical property comprises intensity, wherein said intensity varies continuously in one or two spatial dimensions.

13. The method of claim 5, wherein said interaction of said transmitted electromagnetic radiation with said layer of photosensitive material generates a pattern of chemically modified regions in said photosensitive layer, said method further comprising the step of processing the photosensitive material to generate a three-dimensional pattern in said photosensitive layer.
14. The method of claim 13, wherein the chemically modified regions are removed during the processing step.
15. The method of claim 13, wherein regions that are not chemically modified are removed during the processing step.
16. The method of claim 1, wherein said elastomeric patterning device and said patterning agent in said recessed features comprise an amplitude photomask for generating three-dimensional features on a substrate surface.
17. The method of claim 1, wherein said elastomeric patterning device and said patterning agent in said recessed features comprise a phase-shift photomask for generating three-dimensional features on a substrate surface.
18. The method of claim 1, wherein said recessed features of said elastomeric patterning device comprise a mold, said method further comprising the steps of:
 - a) causing a physical or chemical change in said patterning agent in said recessed features of said elastomeric pattern device; and
 - b) separating said patterning device from said surface of said substrate, thereby generating a pattern of relief features embossed on said surface of said substrate.
19. The method of claim 18, wherein said embossed features comprise a photomask.
20. The method of claim 19 further comprising exposing said photomask in contact with said substrate to electromagnetic radiation; wherein said photomask modulates an optical property of electromagnetic radiation transmitted by said photomask.
21. The method of claim 18, wherein said change in said patterning agent is selected from the group consisting of phase change and polymerization reaction.

22. The method of claim 18, wherein said patterning agent is a prepolymer.
23. The method of claim 18, wherein said change is caused by exposing said patterning agent to a signal, said signal selected from the group consisting of electromagnetic radiation, temperature and polymerizing agent.
24. The method of claim 1, wherein said patterning agent provided to said surface of substrate comprises one or more droplets.
25. The method of claim 24, wherein said droplets are applied in a pattern of droplets.
26. The method of claim 24, wherein said one or more droplets are optionally addressed to selected regions of substrate surface.
27. The method of claim 1, wherein said substrate surface undergoing processing comprises selected hydrophobic regions, selected hydrophilic regions, or both.
28. The method of claim 1, wherein said three-dimensional pattern comprises selected hydrophobic regions, selected hydrophilic regions, or both.
29. The method of claim 1, wherein said patterning agent is provided to said surface of substrate in a pattern.
30. The method of claim 1, wherein said patterning agent is provided to said surface of substrate in a layer or a thin-film that covers at least a portion of said surface of substrate.
31. The method of claim 1 further comprising aligning said elastomeric patterning device with said surface of the substrate.
32. The method of claim 31, wherein the aligning comprises aligning a lock and key registration feature.

33. The method of claim 32 further comprising applying a force to strain said elastomeric patterning device, thereby engaging said lock and key registration feature.
34. The method of claim 1, wherein said surface of substrate is distorted, said method further comprising applying a force to strain said elastomeric patterning device to match said substrate distortion to facilitate said conformal contact.
35. The method of claim 1, wherein at least a portion of said surface of substrate is nonplanar.
36. The method of claim 1, wherein said elastomeric patterning device comprises a single elastomeric layer.
37. The method of claim 1, wherein said elastomeric patterning device is a composite patterning device comprising multiple elastomeric layers.
38. The method of claim 1 further comprising extracting air from the patterning device to facilitate filling of said recessed features with said patterning agent.
39. The method of claim 1 further comprising treating the contact surface, recessed features, surface of substrate, or any combination thereof with HMDS, plasma O₂, UVO, or any combination thereof.
40. A method of generating a pattern on a photosensitive surface of a substrate, said method comprising:
- a) providing a patterning agent on at least a portion of the surface of the substrate, wherein said patterning agent is applied in a pattern to at least partially coat said surface with said patterning agent;
 - b) applying electromagnetic radiation to said coated surface to generate a two-dimensional spatial distribution of electromagnetic radiation on said surface of the substrate; and
 - c) processing said substrate to obtain the pattern.
41. The method of claim 40, wherein said patterning agent comprises a droplet.

42. The method of claim 40, wherein said patterning agent comprises a thin film.
43. The method of claim 40, wherein the surface comprises one or more regions that are hydrophobic or hydrophilic.
44. The method of claim 43 wherein the patterning agent is applied to hydrophilic regions.
45. The method of claim 40 further comprising:
- a) providing an elastomeric patterning device having a three-dimensional pattern of recessed features on an external side, wherein said external side has at least one contact surface disposed thereon; and
 - b) contacting the elastomeric patterning device with the substrate in a manner establishing conformal contact between at least a portion of the contact surface of the elastomeric patterning device and the surface of the substrate having said patterning agent, wherein said conformal contact results in said patterning agent filling at least a portion of said recessed features of said elastomeric pattern device.
46. The method of claim 45 further comprising removing excess patterning agent
47. A patterning device for generating three-dimensional patterns on a substrate surface, said device comprising:
- a) an elastomeric layer comprising an external surface and an internal surface, said external surface having a three-dimensional relief pattern;
 - b) means of providing patterning agent to said substrate surface or said relief pattern; and
 - c) means for establishing conformal contact between said relief pattern and said substrate surface.
48. The device of claim 47, wherein said means for establishing conformal contact comprises an actuator, said actuator operably connected to said elastomeric layer internal surface.

49. The device of claim 48, wherein said actuator applies a uniform pressure, a uniform displacement, or both to said elastomeric layer to establish conformal contact.
50. The device of claim 47, wherein said substrate surface has one or more hydrophilic regions, and wherein means of providing patterning agent comprises droplet application to said one or more hydrophilic regions.
51. The method of claim 1 further comprising applying a thin film to selected regions of said elastomeric patterning device, wherein said thin film modulates an optical property of electromagnetic radiation and said regions are selected from the group consisting of recessed features, relief features, and top surface.
52. The method of claim 1 further comprising embedding particles within said elastomeric patterning device, wherein said particles modulate an optical property of electromagnetic radiation.
53. The method of claim 52, wherein said particles are embedded in a pattern.
54. The method of claim 1 further comprising depositing particles on a top surface of said elastomeric patterning device, wherein said particles modulate an optical property of electromagnetic radiation.