

**ISOTOPICALLY-ENRICHED BORON-CONTAINING COMPOUNDS, AND
METHODS
OF MAKING AND USING SAME**

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims the priority of U.S. Patent Application No. 13/048,367, filed on March 15, 2011 in the names of Robert Kaim, et al. for “ISOTOPICALLY-ENRICHED BORON-CONTAINING COMPOUNDS, AND METHODS OF MAKING AND USING SAME,” which is a continuation in part under 35 USC 120 of U.S. Patent Application No. 12/913,721 filed October 27, 2010 in the names of Robert Kaim, et al. for “ISOTOPICALLY-ENRICHED BORON-CONTAINING COMPOUNDS, AND METHODS OF MAKING AND USING SAME,” which in turn claims the benefit of priority under 35 USC 119(e) of the following U.S. Provisional Patent Applications: U.S. Provisional Patent Application No. 61/378,353 filed August 30, 2010 in the names of Oleg Byl, et al. for “ISOTOPICALLY-ENRICHED BORON-CONTAINING COMPOUNDS, AND METHODS OF MAKING AND USING SAME;” U.S. Provisional Patent Application No. 61/375,031 filed August 18, 2010 in the names of Oleg Byl, et al. for “ISOTOPICALLY-ENRICHED BORON-CONTAINING COMPOUNDS, AND METHODS OF MAKING AND USING SAME;” U.S. Provisional Patent Application No. 61/358,514 filed June 25, 2010 in the names of Edward Jones, et al. for “ACTIVE COOLING FOR ION IMPLANT GAS DELIVERY SYSTEM;” U.S. Provisional Patent Application No. 61/349,202 filed May 27, 2010 in the names of Edward Jones, et al. for “ACTIVE COOLING FOR ION IMPLANT GAS DELIVERY SYSTEM;” and U.S. Provisional Patent Application No. 61/255,097 filed October 27, 2009 in the names of Robert Kaim, et al. for “BORON ION IMPLANTATION APPARATUS AND METHOD.” The priority of aforementioned U.S. Patent Application No. 12/913,721, U.S. Provisional Patent Application No. 61/378,353, and U.S. Provisional Patent Application No. 61/375,031 are additionally claimed in the present application. The disclosures of all of said U.S. Patent Application Nos. U.S. Patent Application No. 13/048,367 and 12/913,721, and U.S. Provisional Patent Application Nos. 61/378,353; 61/375,031; 61/358,514; 61/349,202; and 61/255,097, are hereby incorporated herein by reference, in their respective entireties, for all purposes.

FIELD

[0002] The present disclosure relates to isotopically-enriched boron-containing compounds, compositions, and methods of making and using same.

DESCRIPTION OF THE RELATED ART

[0003] Ion implantation is used in integrated circuit fabrication to accurately introduce controlled amounts of dopant impurities into semiconductor wafers and is a crucial process in microelectronic/semiconductor manufacturing.

[0004] In such implantation systems, an ion source ionizes a desired dopant element of a dopant source gas. The ion source generates ions by introducing electrons into a vacuum chamber filled with the dopant source gas (also commonly referred to as the “feedstock gas”). Feedstock gases used to generate implant species include, but are not limited to, BF_3 , $\text{B}_{10}\text{H}_{14}$, $\text{B}_{12}\text{H}_{22}$, PH_3 , AsH_3 , PF_5 , AsF_5 , H_2Se , N_2 , Ar , GeF_4 , SiF_4 , O_2 , H_2 , and GeH_4 . The compositions containing the dopant element to be implanted are typically referred to as dopant sources or precursors. Collisions of the electrons with dopant atoms and molecules in the gas results in the creation of an ionized plasma consisting of positive and negative dopant ions.

[0005] The resulting ions are extracted from the source in the form of an ion beam of desired energy. Extraction is achieved by applying a high voltage across suitably shaped extraction electrodes, which incorporate apertures for passage of the extracted beam. The extracted beam passes through the aperture and out of the ion source as a collimated ion beam, which is accelerated towards the substrate.

[0006] The ion beam is impinged on the surface of the substrate, such as a semiconductor wafer, in order to implant the substrate with the dopant element. The ions of the beam penetrate the surface of the substrate to form a region of desired conductivity. Implanted ion species variously include B, P, As, Se, N, Ar, Ge, Si, O, and H, with boron being a particularly widely used implant species.

[0007] One of the main steps in manufacturing of integrated circuits is implantation of boron into silicon wafers. Since elemental boron exhibits very low vapor pressure even at high temperatures, utilization of volatile boron-containing compounds is necessary. Currently, boron trifluoride (BF_3) is widely used as a feed gas for boron implantation (for example, it is estimated that the 2007 annual worldwide consumption of BF_3 for ion implantation was ~3000 kg).

[0008] Despite its widespread use, BF_3 does have disadvantages. The BF_3 molecule is very difficult to ionize and only about 15% of all BF_3 flowed into the ion source can be fragmented. The rest is discarded. Further, only about 30% of the ionized BF_3 is converted into B^+ ions that can be used for implantation. This results in low B^+ beam current that severely limits implantation process throughput.

[0009] Some increase of B⁺ beam current can be achieved by varying the process parameters, such as by raising the extraction current, and by increasing the BF₃ flow rate. These measures result in reduced life time of the ion source, high voltage arcing leading to tool instability, and poor vacuum causing beam energy contamination. Even without drastic adjustment of the implantation process parameters, it is well established that implantation of boron requires more frequent preventive maintenance interruptions that present other problems for integrated circuit manufacturers.

[0010] The problem of throughput limitation because of low B⁺ beam current has become more important in recent years due to the semiconductor industry's general trend toward utilization of lower implantation energies. At lower implantation energies, the B⁺ beam experiences a greater blow-out effect due to space charge and the low atomic weight of boron.

[0011] In addition to the foregoing problems, it has been mentioned that elemental boron has a very low vapor pressure. Accordingly, if a boron-containing precursor is susceptible to excessive decomposition resulting in deposition of boron residue, then it may be unsuitable for ion implantation, from an ion implanter tool operation perspective.

[0012] In consequence of the foregoing, the art continues to seek improved boron precursors.

SUMMARY

[0013] The present disclosure relates to isotopically-enriched boron-containing compounds, and methods of making and using same.

[0014] In one aspect, the disclosure relates to an isotopically-enriched, boron-containing compound comprising two or more boron atoms and at least one fluorine atom, wherein at least one of the boron atoms contains a desired isotope of boron in a concentration or ratio greater than a natural abundance concentration or ratio thereof.

[0015] A further aspect of the disclosure relates to a method of implanting boron into a substrate, comprising ionizing the compound of an above-describe type, to generate boron ions; and implanting the boron ions into a substrate.

[0016] Yet another aspect of the disclosure relates to a beam-line ion implantation, plasma immersion ion implantation or plasma doping system, comprising a source of the compound described above.

[0017] Another aspect of the disclosure relates to a gas storage and dispensing vessel comprising a compound of a above-described type.

[0018] The disclosure in another aspect relates to a method of improving beam current for an ion implantation process, comprising: flowing the compound of a type as described above; and generating an ion beam from the compound.

[0019] A further aspect of the disclosure relates to a method of synthesizing the compound of a type as described above, comprising contacting a boron-containing gas with a boron metal.

[0020] The disclosure relates another aspect to a method of preparing a source of the compound of an above described type, comprising filling a storage and dispensing vessel with the compound.

[0021] Another aspect of the disclosure relates to an ion implantation method, comprising flowing a compound of the type described above to an ion implantation tool with at least one co-flowed species selected from the group consisting of inert gas, argon, nitrogen, helium, hydrogen, ammonia, xenon, xenon difluoride, isotopically enriched diborane, and natural abundance diborane.

[0022] A further aspect of the disclosure relates to an ion implantation method, comprising flowing an isotopically-enriched atomic mass 11 boron B_2F_4 compound to an ion implantation tool with an isotopically-enriched atomic mass 11 boron BF_3 compound.

[0023] Yet another aspect of the disclosure relates to an ion implantation method comprising use of a compound of an above-described type in an ion implantation tool, and periodically cleaning said tool or a component thereof by flow therethrough of a cleaning agent that is effective to at least partially remove deposits formed in said tool or a component thereof by ion implantation operation.

[0024] A further aspect of the disclosure relates to a method of carrying out ion implantation, comprising using a compound of a type as described above in an ion implantation tool as the only dopant source compound used in operation of said ion implantation tool.

[0025] Another aspect of the disclosure relates to a method of carrying out ion implantation, comprising conducting said ion implantation in an ion implantation tool processing only isotopically enriched atomic mass 11 boron B_2F_4 as a dopant compound therein.

[0026] In another aspect, the disclosure relates to a method of carrying out ion implantation, comprising conducting said ion implantation in an ion implantation tool using isotopically enriched atomic mass 11 boron B_2F_4 as a dopant compound therein, wherein the ion implantation tool also processes at least one of arsine, phosphine, carbon dioxide, carbon monoxide, silicon tetrafluoride and boron trifluoride.

[0027] A further aspect of the disclosure relates to a storage and dispensing vessel containing a compound of an above-described type in a storage medium selected from the group consisting of physical adsorbents and ionic liquids.

[0028] Yet another aspect of the disclosure relates to a storage and dispensing vessel containing a compound of an above-described type, wherein the vessel contains a restricted flow orifice located either within the vessel or within an output port of the vessel.

[0029] A further aspect the disclosure relates to a storage and dispensing vessel containing a compound of an above-described type, wherein the vessel is pressure-regulated for dispensing of the compound at subatmospheric pressure.

[0030] The disclosure relates in another aspect to an ionized composition useful for AMU separation to generate ionic species for ion implantation, said composition deriving from a boron precursor compound other than BF_3 , wherein said boron precursor compound is isotopically enriched beyond natural abundance in one of ^{10}B and ^{11}B , and wherein said composition comprises one or more species from among B_2F_4^+ , B_2F_3^+ , B_2F_2^+ , BF_3^+ , BF_2^+ , BF^+ , B^+ , F^+ , $\text{B}_2\text{F}_4^{++}$, $\text{B}_2\text{F}_3^{++}$, $\text{B}_2\text{F}_2^{++}$, BF_3^{++} , BF_2^{++} , BF^{++} , B^{++} , F^{++} , $\text{B}_2\text{F}_4^{+++}$, $\text{B}_2\text{F}_3^{+++}$, $\text{B}_2\text{F}_2^{+++}$, BF_3^{+++} , BF_2^{+++} , BF^{+++} , B^{+++} , and F^{+++} , the boron-containing ones of which are isotopically enriched beyond natural abundance in one of ^{10}B and ^{11}B .

[0031] A further aspect of the disclosure relates to a boron ionic species selected from among B_2F_4^+ , B_2F_3^+ , B_2F_2^+ , BF_3^+ , BF_2^+ , BF^+ , B^+ , $\text{B}_2\text{F}_4^{++}$, $\text{B}_2\text{F}_3^{++}$, $\text{B}_2\text{F}_2^{++}$, BF_3^{++} , BF_2^{++} , BF^{++} , B^{++} , $\text{B}_2\text{F}_4^{+++}$, $\text{B}_2\text{F}_3^{+++}$, $\text{B}_2\text{F}_2^{+++}$, BF_3^{+++} , BF_2^{+++} , BF^{+++} and B^{+++} , and isotopically enriched beyond natural abundance in one of ^{10}B and ^{11}B .

[0032] The disclosure in another aspect relates to a method of improving beam current for an ion implantation process, comprising use of an isotopically-enriched, boron-containing compound that is effective to form isotopically enriched ionic species producing such improved beam current, in relation to a corresponding non-isotopically-enriched, boron-containing compound.

[0033] Other aspects, features and embodiments of the invention will be more fully apparent from the ensuing disclosure and appended claims.

BRIEF DESCRIPTION OF THE DRAWINGS

[0034] FIG. 1 is a schematic illustration of a semiconductor manufacturing facility including an ion implantation system arranged to receive an isotopically-enriched boron-containing precursor from a precursor supply vessel, according to one embodiment of the present disclosure.

DETAILED DESCRIPTION

[0035] The present disclosure relates to isotopically-enriched boron-containing compounds, compositions, and to methods of making and using same.

[0036] In one aspect, the disclosure relates to an isotopically-enriched, boron-containing compound comprising two or more boron atoms and at least one fluorine atom, wherein at least one of the boron atoms contains a desired isotope of boron in a concentration or ratio that is greater than a natural abundance concentration or ratio thereof (of the desired isotope).

[0037] The boron-containing compound can be of any suitable type, and can include any number of boron atoms. In one embodiment, the boron-containing compound contains at least two boron atoms and at least one fluorine atom. In another embodiment, the boron-containing compound contains from 2 to 80 boron atoms, including diboron compounds such as B_2F_4 , B_2H_6 , $H_2B_2F_6$, $H_2B_2F_2O_3$, $H_2B_2F_2O_6$, and $H_2B_2F_4O_2$, triboron compounds such as B_3F_6 , tetraboron compounds such as $H_4B_4F_{10}$, $B(BF_2)_3CO$, and $(F_2B)_3BCO$, pentaboron compounds, hexaboron compounds, septaboron compounds, octaboron compounds such as B_8F_{12} , nonaborane compounds, decaboron compounds such as $B_{10}F_{12}$, undecaboron compounds, dodecaboron compounds, etc., up to B_{80} compounds such as B_{80} analogs of fullerenes. In other embodiments, the boron-containing compound can contain 2, 3, 4, 5, 6, 7, 8, 9, 10, or 11 boron atoms. Additional embodiments may comprise cluster boron compounds. In still other embodiments, the boron-containing compound can be a diboron compound. In other embodiments, the boron-containing compound can comprise diboron compounds other than particular boron-containing compound species, e.g., diboron compounds other than diborane. It will therefore be appreciated that the disclosure contemplates a wide variety of classes of boron-containing compounds, within the broad scope thereof.

[0038] In one embodiment of the isotopically-enriched, boron-containing compound, the desired isotope is atomic mass 10 boron and the natural abundance concentration is about 19.9%. In such boron compound, the concentration of atomic mass 10 boron isotope can for example be greater than 19.9%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 80%, 85%, 90%, 95%, 96%, 97%, 98%, 99%, 99.9%, or 99.99%, in specific compositional variants. For example, the concentration of atomic mass 10 boron isotope can be 20-25%, 25-30%, 30-35%, 35-40%, 40-45%, 45-50%, 50-55%, 55-60%, 60-65%, 65-70%, 70-75%, 75-80%, 80-85%, 85-90%, 90-95%, 95-99% or 95-99.9%. In other embodiments, the concentration of atomic mass 10 boron isotope can be 20-30%, 30-40%, 40-50%, 50-60%, 60-70%, 70-80%, 80-90%, or 90-99%. In various ones of these various embodiments, the boron-containing compound contains two boron atoms.

[0039] In another embodiment of the isotopically-enriched, boron-containing compound, the desired isotope is atomic mass 11 boron and the natural abundance concentration is about 80.1%. In such boron compound, the concentration of atomic mass 11 boron isotope can for example be greater than 80.1%, 85%, 90%, 95%, 96%, 97%, 98%, 99%, 99.9% or 99.99%, in specific compositional variants. For example, the concentration of atomic mass 11 boron isotope can be 81-85%, 85-90%, 90-95%, 95-99%, 95-99.9%. In a specific embodiment, the concentration of atomic mass 11 boron isotope can be 81-90% or 90-99%. In various ones of these various embodiments, the boron-containing compound contains two boron atoms and at least one fluorine atom, and in other compounds, the ratio of ^{11}B to ^{10}B is in a range of from 4.1 to 10,000.

[0040] In various embodiments of the isotopically-enriched boron-containing compounds as described above, the boron-containing compound has a chemical formula of B_2F_4 . In various other embodiments of the isotopically-enriched boron-containing compounds as described above, the boron-containing compound has a chemical formula of B_2F_6 .

[0041] More generally, in isotopically-enriched, boron-containing compounds of the present disclosure, the concentration of desired isotopes in the two or more boron atoms can be the same as, or different from, one another. In various embodiments of the isotopically-enriched boron-containing compounds of the present disclosure, the boron-containing compound contains 3, 4, 5, 6, 7, 8, 9, 10, or 11 boron atoms.

[0042] The present disclosure, in one aspect, relates to a method of implanting boron into a substrate, comprising ionizing an isotopically-enriched, boron-containing compound as variously described herein, to generate boron ions, and implanting the boron ions into a substrate. In such method, the isotopically-enriched, boron-containing compound may be of any suitable type described hereinabove. In one embodiment, the compound has a chemical formula of B_2F_4 . In various other embodiments of such method, the isotopically-enriched, boron-containing compound has a chemical formula of B_2F_6 .

[0043] The disclosure in another aspect relates to a beam-line ion implantation, plasma immersion ion implantation or plasma doping system, comprising a source of the isotopically-enriched, boron-containing compound, wherein the compound may be of any type as variously described hereinabove. In one embodiment, the compound has a chemical formula of B_2F_4 . In various other embodiments of such method, the isotopically-enriched, boron-containing compound has a chemical formula of B_2F_6 . In another embodiment, the disclosure relates to ion implantation, in which boron ions are generated and accelerated by an electric field for impingement on a substrate, such as a microelectronic device substrate. Such method of implanting boron-containing ions in one implementation includes ionizing a boron-containing dopant species at a high ionization efficiency of at least 15% using an arc voltage

less than 100 volts, preferably less than 90 volts, more preferably less than 80 volts, and most preferably less than 70 volts, using a conventional hot cathode ion source or comparable voltages using another ion source. In other embodiments, the ion implantation specifically excludes plasma immersion processes.

[0044] The above-described beam-line ion implantation, plasma immersion ion implantation or plasma doping system, in specific implementations thereof, comprise a conduit adapted for delivery of the isotopically-enriched boron-containing compound to an ionization chamber, wherein the conduit is maintained at a temperature effective to minimize or otherwise suppress clogging of the conduit and/or decomposition of the compound in the conduit. For such purpose, the ionization chamber and/or the precursor feed conduit can be equipped with active cooling capability, such as by provision of heat exchange flow circuitry serving to reduce the temperature of the influent dopant gas entering the ionization chamber.

[0045] In the delivery of the isotopically-enriched, boron-containing compound to the ion implanter tool, the isotopically-enriched, boron-containing compound may be delivered, e.g., co-flowed to the ion implanter tool, with other component(s), such as inert gas species, e.g., argon, xenon, nitrogen, helium or the like, hydrogen, ammonia, other boron precursors such as natural abundance boron precursors, other isotopically-enriched boron-containing precursors, other dopant precursors (i.e., non-boron dopant precursors), or one or more of the foregoing components.

[0046] In one embodiment, the isotopically-enriched, boron-containing compound, e.g., enriched atomic mass 11 boron isotope-containing B_2F_4 , is co-flowed to the ion implanter tool with an enriched atomic mass 11 boron isotope-containing BF_3 , whereby the dilution of the isotopically-enriched B_2F_4 with the isotopically-enriched BF_3 serves to enhance the resistance of the precursor stream to clogging of feed lines to the tool. In such case, the beam current can be maintained at levels that provide a significant benefit operationally, while concurrently maximizing the service life of the ion source.

[0047] In various other implementations of the use of isotopically-enriched, boron-containing precursors, operation of the ion implantation system may be carried out with in-situ cleaning of components of the system, such as by flow of a cleaning agent into the system or specific components thereof to be cleaned, at periodic intervals. The cleaning agent utilized in such operation can be of any suitable type, such as for example xenon difluoride, fluorine, nitrogen trifluoride, or other agent that is effective in contact with deposits formed in the ion implantation system or specific components thereof to be cleaned, to at least partially remove such deposits. The location to be cleaned in the ion implantation system by such periodic introduction of cleaning agent can be the gas tube, the arc chamber, forelines, or any other locations or regions in the tool or ancillary equipment in which deposits can be formed by chemical species utilized in the ion implantation operation.

[0048] In another implementation of the use of isotopically-enriched, boron-containing compounds as precursors, an ion implantation tool is operated with isotopically-enriched atomic mass 11 boron B_2F_4 as the only dopant precursor. In yet another implementation, ion implantation is carried out with isotopically-enriched atomic mass 11 boron B_2F_4 as the dopant species on an ion implantation tool that also is used to carry out doping operation involving a dopant precursor selected from the group consisting of arsine, phosphine, carbon dioxide, carbon monoxide, silicon tetrafluoride, and boron trifluoride.

[0049] A further aspect of the disclosure relates to a gas storage and dispensing vessel comprising an isotopically-enriched, boron-containing compound of any type as variously described herein. Such gas storage and dispensing vessel may for example contain an isotopically-enriched, boron-containing compound having the chemical formula of B_2F_4 . The gas storage and dispensing vessel in specific embodiments may comprise one or more of a regulator, check valve, adsorbent, filter, and capillary flow restriction device disposed in an interior volume of the vessel. The vessel in other embodiments may contain a storage medium for the boron-containing compound, such as a solid-phase physical adsorbent, or alternatively an ionic liquid storage medium. In still other embodiments, the vessel can include a restrictive flow orifice located either within an interior volume of the vessel or within a connection port, e.g., outlet port, of the vessel.

[0050] Another aspect of the invention relates to a method of synthesizing an isotopically-enriched, boron-containing compound of any suitable type as described herein above, comprising contacting a boron-containing gas with a boron metal. In such method, one or both of the boron-containing gas and boron metal can be isotopically enriched. Thus, for example, the disclosure contemplates a combination of isotopically enriched boron metal and natural abundance boron trifluoride as being contacted, in one embodiment. In another illustrative embodiment, the disclosure contemplates combination of natural abundance boron metal and isotopically enriched boron trifluoride as being the contacted species, and in yet another illustrative embodiment, the disclosure contemplates contacting of isotopically enriched boron metal and isotopically enriched boron trifluoride.

[0051] As a specific example of the synthesis method described above, the isotopically-enriched, boron-containing compound that is synthesized in the contacting may be B_2F_4 and the boron-containing gas may be boron trifluoride.

[0052] The foregoing synthesis method may be carried out using atomic mass 10 boron isotope in the boron metal at any suitable concentration. In specific embodiments, the concentration of atomic mass 10 boron isotope in the boron metal can be greater than 19.9%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 80%, 85%, 90%, 95%, 99%, 99.9%, or 99.99%.

[0053] In other embodiments, the synthesis method may be carried out using atomic mass 11 boron isotope in the boron metal, and in specific embodiments of such type, the concentration of atomic mass 11 boron isotope in the boron metal can be greater than 80.1%, 85%, 90%, 95%, 99%, 99.9% or 99.99%.

[0054] In still other embodiments of the synthesis method, in which boron trifluoride is employed, isotopically enriched boron trifluoride species can be employed, such as boron trifluoride in which the concentration of atomic mass 10 boron isotope is greater than 19.9%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 80%, 85%, 90%, 95%, 99%, 99.9%, or 99.99%.

[0055] In other embodiments, the synthesis method using boron trifluoride in isotopically enriched form can be carried out, in which the boron trifluoride is enriched in atomic mass 11 boron isotope, wherein the concentration of atomic mass 11 boron isotope in the boron trifluoride is greater than 80.1%, 85%, 90%, 95%, 99%, 99.9% or 99.99%.

[0056] The disclosure in a further aspect relates to a method of improving beam current for an ion implantation process, comprising use of an isotopically-enriched, boron-containing compound that is effective to produce such improved beam current, in relation to a corresponding non-isotopically-enriched, boron-containing compound. In a specific embodiment, the isotopically-enriched, boron-containing compound comprises isotopically-enriched B_2F_4 .

[0057] A further aspect of the disclosure relates to a method of improving beam current in an ion implantation process, comprising flowing an isotopically-enriched, boron-containing compound of any suitable type as described hereinabove, and generating an ion beam from the compound. In such method, the isotopically-rich, boron-containing compound can comprise a compound having a chemical formula of B_2F_4 . Such boron-containing compound upon ionization may form various ionic species and fragments, including one or more species from among $B_2F_4^+$, $B_2F_3^+$, $B_2F_2^+$, BF_3^+ , BF_2^+ , BF^+ , B^+ , F^+ , $B_2F_4^{++}$, $B_2F_3^{++}$, $B_2F_2^{++}$, BF_3^{++} , BF_2^{++} , BF^{++} , B^{++} , F^{++} , $B_2F_4^{+++}$, $B_2F_3^{+++}$, $B_2F_2^{+++}$, BF_3^{+++} , BF_2^{+++} , BF^{+++} , B^{+++} , and F^{+++} .

[0058] Significant improvement can be achieved in beam current as a result of the use of isotopically-enriched boron-containing compounds, and their correspondingly enriched boron-containing ionic species and fragments, as selected for implantation, by a selector comprising an AMU magnet or other selector. In such various embodiments, the concentration of atomic mass 11 boron isotope in the boron-containing compound, and in ionic species and fragments therefrom, can be greater than 80.1%, 85%, 90%, 95%, 99%, 99.9% or 99.99%. Alternatively, boron-containing compounds enriched in atomic mass 10 boron isotope can be utilized, i.e., boron-containing compounds, and corresponding ionic species and fragments therefrom, in which the concentration of atomic mass 10 boron isotope

is greater than 19.9%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 80%, 85%, 90%, 95%, 99%, 99.9% or 99.99%.

[0059] In addition to utilizing isotopically-enriched compounds as feed gas sources for ion implantation, the disclosure contemplates arrangements in which combinations of boron-containing source compounds are utilized, to achieve various improvements, e.g., improvement in beam current and/or other operating parameters of the ion implant operation, reduction in levels of decomposition and deposits therefrom, enhancement of resistance to clogging of flow passages in the ion implantation system, etc.

[0060] The disclosure further contemplates use of compounds that are homogenous in boron isotope as precursors for boron ion implantation, i.e., boron-containing compounds, and ionic species and fragments therefrom, wherein all atomic boron is ^{10}B or ^{11}B , to achieve improvements in beam current or other operational parameters of the ion implantation operation and system.

[0061] Use of isotopically-enriched boron-containing compounds has been demonstrated to afford significant improvement in beam current for selected ionic species, e.g., beam current improvement levels of from 5 to 30% or more, depending on the particular ionic species being selected for ion implantation. The ionic species, isotopically enriched in boron content, can be of any suitable type, and can for example include one or more of B_2F_4^+ , B_2F_3^+ , B_2F_2^+ , BF_3^+ , BF_2^+ , BF^+ , B^+ , F^+ , $\text{B}_2\text{F}_4^{++}$, $\text{B}_2\text{F}_3^{++}$, $\text{B}_2\text{F}_2^{++}$, BF_3^{++} , BF_2^{++} , BF^{++} , B^{++} , F^{++} , $\text{B}_2\text{F}_4^{+++}$, $\text{B}_2\text{F}_3^{+++}$, $\text{B}_2\text{F}_2^{+++}$, BF_3^{+++} , BF_2^{+++} , BF^{+++} , B^{+++} , and F^{+++} . Thus, isotopic enrichment can be utilized to improve AMU magnet selection of ions of a desired type, such as for example BF_2^+ , BF^+ or F^+ . By increasing the beam current in the ion implant tool with such isotopically enriched species, it is possible to avoid the need for increasing the source gas flow and the source arc power, such as may otherwise be required to achieve higher beam current levels, but which are less efficient and result in low utilization of the source gas for ion implantation.

[0062] The use of isotopically-enriched B_2F_4 is particularly preferred, since such boron source compound even at natural abundance isotopic composition affords significant improvement in beam current as compared to beam currents obtained using boron trifluoride under the same conditions and in the same ion implant tool, e.g., for species such as BF_2^+ and B^+ . Isotopic enrichment can further increase the magnitude of such improvements.

[0063] The disclosure in another aspect relates to generation of ion species in ionization of an isotopically-enriched boron-containing compound, as useful for ion implantation, in which the isotopically-enriched boron-containing ion species is selected from among B_2F_4^+ , B_2F_3^+ , B_2F_2^+ , BF_3^+ , BF_2^+ , BF^+ , B^+ , F^+ , $\text{B}_2\text{F}_4^{++}$, $\text{B}_2\text{F}_3^{++}$, $\text{B}_2\text{F}_2^{++}$, BF_3^{++} , BF_2^{++} , BF^{++} , B^{++} , F^{++} , $\text{B}_2\text{F}_4^{+++}$, $\text{B}_2\text{F}_3^{+++}$, $\text{B}_2\text{F}_2^{+++}$, BF_3^{+++} , BF_2^{+++} , BF^{+++} , B^{+++} , and F^{+++} . The disclosure further contemplates AMU magnet selection of one or more of such ion species generated from ionization of an isotopically-enriched boron-containing compound, and implantation of such

isotopically-enriched boron-containing ion species in a substrate, such as a microelectronic device substrate.

[0064] The isotopically-enriched boron-containing species may be isotopically enriched to provide a concentration of atomic mass 11 boron isotope, or a concentration of atomic mass 10 boron isotope varied from natural abundance levels, at any of the concentrations previously described, i.e., concentration of atomic mass 11 boron isotope in the ionic species greater than 80.1%, 85%, 90%, 95%, 99%, 99.9% or 99.99%, or an isotopically-enriched boron containing species in which the concentration of mass 10 boron isotope is greater than 19.9%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 80%, 85%, 90%, 95%, 99%, 99.9% or 99.99%.

[0065] Another aspect of the present disclosure relates to a method of reducing thermal decomposition and deposition of material on surfaces of the ion implantation tool as a result of using isotopically-enriched boron-containing source compounds. Thermal decomposition of boron-containing source compounds used in ion implantation can result in deposition of elemental boron with production of boron trifluoride or other byproduct gas species. Even if the gas feed line is sufficiently cooled, some thermal deposition inevitably occurs on the arc chamber walls. The deposit formed as a result of such decomposition and associated deposition can be a mixture of boron metal deriving from the source gas, and tungsten or molybdenum from the arc chamber walls. Deposits can form in the gas feed lines near the ion source, as well as inside and on surfaces of nozzles, arc chamber base plates, and below base plate liners of the ionizer. Such deposits require periodic maintenance removal, such as by abrasive cleaning and chemical methods, e.g., flow through the tool containing deposits of a suitable cleaning gas, to volatilize the deposits so that they can be removed. The resulting effluent can be processed for remediation or recovery of specific materials from the effluent stream.

[0066] If the ion implanter is not dedicated to operation with only boron dopants, various types of solid materials or ions may be formed by interaction between the ions derived from the boron source compound and materials otherwise present in the vacuum chamber, depending on its materials of construction, such as the tungsten and molybdenum materials previously described. In a tungsten arc chamber with aluminum insulators, ions may be formed of widely varying type, including WF_x^+ wherein $x = 0, 1, 2, 3, 4, 5$ or 6 and AlF_y^+ wherein $y = 0, 1, 2$, or 3 . Such ions can react with the isotopically-enriched boron-containing source compounds to form corresponding isotopically-enriched deposits. The isotopic character of such deposits may afford opportunity to utilize cleaning agents that are selective for same as a result of their isotopic composition.

[0067] A further aspect of the disclosure relates to a method of preparing a source of the isotopically enriched, boron-containing compound of any suitable type as described

hereinabove, in which the method comprises filling a storage and dispensing vessel with the compound. In such method, the isotopically enriched, boron-containing compound in one embodiment has the chemical formula B_2F_4 .

[0068] The isotopically-enriched, boron-containing compound of the present disclosure includes a wide variety of compounds, specific ones of which are in gas, solid or liquid forms at standard conditions (1 atm pressure, 25°C).

[0069] Thus, the disclosure contemplates an ionized composition useful for AMU separation to generate ionic species for ion implantation, said composition deriving from a boron precursor compound other than BF_3 , wherein said boron precursor compound is isotopically enriched beyond natural abundance in one of ^{10}B and ^{11}B , and wherein said composition comprises one or more species from among $B_2F_4^+$, $B_2F_3^+$, $B_2F_2^+$, BF_3^+ , BF_2^+ , BF^+ , B^+ , F^+ , $B_2F_4^{++}$, $B_2F_3^{++}$, $B_2F_2^{++}$, BF_3^{++} , BF_2^{++} , BF^{++} , B^{++} , F^{++} , $B_2F_4^{+++}$, $B_2F_3^{+++}$, $B_2F_2^{+++}$, BF_3^{+++} , BF_2^{+++} , BF^{+++} , B^{+++} , and F^{+++} , the boron-containing ones of which are isotopically enriched beyond natural abundance in one of ^{10}B and ^{11}B .

[0070] In such composition, the boron precursor compound can have the chemical formula of B_2F_4 or any other suitable formula. The composition may be constituted so that concentration of atomic mass 10 boron isotope in the boron-containing ionic species is greater than 19.9%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 80%, 85%, 90%, 95%, 99%, 99.9%, or 99.99%. Alternatively, the composition may be constituted so that concentration of atomic mass 11 boron isotope in said boron-containing ionic species is greater than 80.1%, 85%, 90%, 95%, 99%, 99.9% or 99.99%.

[0071] A further aspect of the disclosure relates to a boron ionic species selected from among $B_2F_4^+$, $B_2F_3^+$, $B_2F_2^+$, BF_3^+ , BF_2^+ , BF^+ , B^+ , $B_2F_4^{++}$, $B_2F_3^{++}$, $B_2F_2^{++}$, BF_3^{++} , BF_2^{++} , BF^{++} , B^{++} , $B_2F_4^{+++}$, $B_2F_3^{+++}$, $B_2F_2^{+++}$, BF_3^{+++} , BF_2^{+++} , BF^{+++} and B^{+++} , and isotopically enriched beyond natural abundance in one of ^{10}B and ^{11}B . In the boron ionic species, the concentration of atomic mass 10 boron isotope in said boron ionic species is greater than 19.9%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 80%, 85%, 90%, 95%, 99%, 99.9%, or 99.99%, or alternatively, the concentration of atomic mass 11 boron isotope in said boron ionic species is greater than 80.1%, 85%, 90%, 95%, 99%, 99.9% or 99.99%.

[0072] A still further aspect of the disclosure relates to a method of improving beam current for an ion implantation process, comprising use of an isotopically-enriched, boron-containing compound that is effective to form isotopically enriched ionic species producing such improved beam current, in relation to a corresponding non-isotopically-enriched, boron-containing compound.

[0073] The isotopically-enriched, boron-containing compound may have the chemical formula of B_2F_4 , or comprise any other suitable isotopically-enriched, boron-containing compound. In one embodiment, the concentration of atomic mass 10 boron isotope in the

isotopically enriched ionic species is greater than 19.9%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 80%, 85%, 90%, 95%, 99%, 99.9%, or 99.99%. In another embodiment, the concentration of atomic mass 11 boron isotope in said isotopically enriched ionic species is greater than 80.1%, 85%, 90%, 95%, 99%, 99.9% or 99.99%.

[0074] A further aspect of the disclosure relates to use of diborane (B_2H_6) in combination with B_2F_4 , as a dopant precursor composition. The B_2F_4 in such dopant precursor composition may be isotopically-enriched as variously described herein, or alternatively in a non-isotopically-enriched form. The diborane in such dopant precursor composition likewise may be isotopically enriched in boron isotopic species, or alternatively in a non-isotopically-enriched form. In the use of such dopant precursor composition of B_2F_4 and diborane, the B_2F_4 and diborane compounds can be premixed with one another and delivered from a same source package, or alternatively, each of such B_2F_4 and diborane compounds can be supplied from separate source packages, and flowed to the process tool from such separate source packages, in any suitable manner. For example, the respective B_2F_4 and diborane compounds can be co-flowed to the process tool from the separate source packages, or alternatively, such compounds may be delivered to the process tool in a sequential or alternating manner.

[0075] In another aspect of the disclosure, boron compounds and compositions of the present disclosure can be utilized for plasma doping of substrates for production of solar cells, using boron ions derived from enriched, or non-enriched, B_2F_4 and B_2F_4 -containing compositions variously described herein.

[0076] Referring now to the drawing, FIG. 1 is a schematic illustration of a semiconductor manufacturing facility including an ion implantation system arranged to receive an isotopically-enriched boron-containing precursor from a precursor supply vessel, according to one embodiment of the present disclosure.

[0077] As shown in FIG. 1, the semiconductor manufacturing facility 180 includes a dopant precursor supply vessel 182, arranged to dispense dopant precursor to the ion source chamber of the ion implantation system. The dopant precursor supply vessel 182 may be of any suitable type, and may for example be constituted by an adsorbent-based fluid storage and dispensing apparatus of the type commercially available from ATMI, Inc. (Danbury, Connecticut, USA) under the trademark "SDS", arranged for supplying dopant precursor gas at sub-atmospheric pressure, e.g., a pressure below 600 torr, such as a pressure in a range of from about 10 to about 500 torr, when the dopant precursor is of gaseous form and physically adsorbable on the sorbent medium contained in the vessel. Alternatively, the dopant precursor may be of liquid form when stored in a pressurized state, e.g., in a pressure-regulated vessel of a type commercially available from ATMI, Inc. (Danbury, Connecticut, USA) under the trademark "VAC", arranged to dispense gas at lower pressure from the liquid-containing vessel. As a still further alternative, the dopant precursor may be of a solid form and may be

provided in a vaporizer vessel of a type commercially available from ATMI, Inc. (Danbury, Connecticut, USA) under the trademark ProE-Vap, in which the dopant precursor solid is heated to generate precursor vapor for the ion implantation operation.

[0078] The dopant precursor in the illustrative FIG. 1 system can for example comprise isotopically-enriched diboron tetrafluoride (B_2F_4), or any other isotopically enriched boron-containing precursor.

[0079] The dopant gas is flowed in feed line 184 to gas delivery unit 186, which is constructed and arranged to suppress ionization of the dopant gas upstream of the high-voltage inlet 188 of ion source 190, in which the dopant gas is subjected to ionization to form dopant ions of the desired character.

[0080] The resulting dopant ions are transmitted in passage 192 from the ion source 190 to the implant chamber 194, in which a wafer (not shown) is disposed in ion impingement position in relation to the ion stream of the dopant species.

[0081] The byproduct effluent from the implant chamber is flowed in effluent treatment line 196 to effluent treatment unit 198, in which the effluent may be subjected to treatment and/or reclamation processing, to produce a final effluent that is discharged from the effluent treatment unit 198.

[0082] While the invention has been described herein in reference to specific aspects, features and illustrative embodiments of the invention, it will be appreciated that the utility of the invention is not thus limited, but rather extends to and encompasses numerous other variations, modifications and alternative embodiments, as will suggest themselves to those of ordinary skill in the field of the present invention, based on the disclosure herein. Correspondingly, the invention as hereinafter claimed is intended to be broadly construed and interpreted, as including all such variations, modifications and alternative embodiments, within its spirit and scope.

THE CLAIMS

What is claimed is:

1. A boron-containing compound comprising two or more boron atoms and at least one fluorine atom, wherein the compound contains a boron isotope in a concentration or ratio greater than a natural abundance concentration or ratio thereof.
2. The compound of claim 1, containing (i) atomic mass 10 boron at concentration higher than 19.9% or (ii) atomic mass 11 boron at concentration higher than 80.1%.
3. The compound of claim 2, wherein the concentration of atomic mass 10 boron isotope is greater than a value selected from the group consisting of 19.9%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 80%, 85%, 90%, 95%, 96%, 97%, 98%, 99%, 99.9%, and 99.99%.
4. The compound of claim 2, wherein the concentration of atomic mass 10 boron isotope is in a range selected from the group consisting of 20-25%, 25-30%, 30-35%, 35-40%, 40-45%, 45-50%, 50-55%, 55-60%, 60-65%, 65-70%, 70-75%, 75-80%, 80-85%, 85-90%, 90-95%, 95-99% and 95-99.9%.
5. The compound of claim 2, wherein the concentration of atomic mass 11 boron isotope is greater than a value selected from the group consisting of 80.1%, 85%, 90%, 95%, 96%, 97%, 98%, 99%, 99.9% and 99.99%.
6. The compound of claim 2, wherein the concentration of atomic mass 11 boron isotope is in a range selected from the group consisting of 81-85%, 85-90%, 90-95%, 95-99%, and 95-99.9%.
7. The compound of claim 1, wherein the compound contains two boron atoms.
8. The compound of claim 1, wherein the compound has a chemical formula of B_2F_4 .
9. The compound of claim 1, having a ratio of ^{11}B to ^{10}B in a range of from 4.1 to 10,000.

10. A method of implanting boron into a substrate, comprising: ionizing a boron-containing compound comprising two or more boron atoms and at least one fluorine atom, wherein the compound contains a boron isotope in a concentration or ratio greater than a natural abundance concentration or ratio thereof, to generate boron ions; and implanting the boron ions into a substrate.

11. The method of claim 10, wherein the boron-containing compound contains (i) atomic mass 10 boron at concentration higher than 19.9% or (ii) atomic mass 11 boron at concentration higher than 80.1%.

12. The method of claim 11, wherein the concentration of atomic mass 10 boron isotope in the boron-containing compound is greater than a value selected from the group consisting of 19.9%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 80%, 85%, 90%, 95%, 96%, 97%, 98%, 99%, 99.9%, and 99.99%.

13. The method of claim 11, wherein the concentration of atomic mass 10 boron isotope in the boron-containing compound is in a range selected from the group consisting of 20-25%, 25-30%, 30-35%, 35-40%, 40-45%, 45-50%, 50-55%, 55-60%, 60-65%, 65-70%, 70-75%, 75-80%, 80-85%, 85-90%, 90-95%, 95-99% and 95-99.9%.

14. The method of claim 11, wherein the concentration of atomic mass 11 boron isotope in the boron-containing compound is greater than a value selected from the group consisting of 80.1%, 85%, 90%, 95%, 96%, 97%, 98%, 99%, 99.9% and 99.99%.

15. The method of claim 11, wherein the concentration of atomic mass 11 boron isotope in the boron-containing compound is in a range selected from the group consisting of 81-85%, 85-90%, 90-95%, 95-99%, and 95-99.9%.

16. The method of claim 10, wherein the boron-containing compound contains two boron atoms.

17. The method of claim 10, wherein the boron-containing compound has a chemical formula of B_2F_4 .

18. The method of claim 10, wherein the boron-containing compound has a ratio of ^{11}B to ^{10}B in a range of from 4.1 to 10,000.

19. The method of claim 10, wherein said ionizing is carried out in an ionization chamber and said boron-containing compound is delivered through a conduit to the ionization chamber for said ionizing, wherein the conduit is maintained at a temperature effective to suppress clogging of the conduit and/or decomposition of the compound in the conduit.

20. The method of claim 19, further comprising actively cooling at least one of the conduit and the ionization chamber.