

ABSTRACT

## MORTAR COMPOSITION BASED ON A SLAG ACTIVATED BY A BY-PRODUCT

One subject of the invention is a dry mortar composition comprising:

- a hydraulic binder comprising at least one calcium aluminosilicate derivative, at least one ground granulated high-alumina slag comprising less than 30% by weight of silica, and at least one source of calcium sulfate,
- aggregates and/or fillers, and
- at least one base in an amount of less than or equal to 0.5% of the total weight of the dry mortar composition.