

DESCRIPTION

HYDROGEN SULFIDE MIXTURE, METHOD FOR PRODUCING SAME, AND FILLING CONTAINER

5

Technical Field

[0001]

The present invention relates to a hydrogen sulfide mixture, a method for producing the same, and a filling
10 container.

Background Art

[0002]

Hydrogen sulfide (H_2S) has been used for producing a
15 phosphor, a compound semiconductor, and a CIGS
(Copper-Indium-Gallium-Selenium) solar cell, and the like
but has been examined to be used also for producing a Si
semiconductor in recent years. In the production of the Si
semiconductor, the hydrogen sulfide has been used for fine
20 processing, and therefore high purity hydrogen sulfide has
been required, and thus a demand for an improvement of the
quality has increased.

However, hydrogen sulfide gas filled into a filling
container has had the following problems. More specifically,
25 the hydrogen sulfide contains a trace amount of moisture
difficult to remove in a production process. Even when high
purity hydrogen sulfide with a sufficiently low moisture
concentration is filled into a filling container, the

moisture is concentrated within the filling container in some cases. Therefore, there has been a possibility that hydrogen sulfide gas with an insufficiently low moisture concentration is emitted from the filling container. This problem is
5 described in detail below.

[0003]

When the hydrogen sulfide gas is emitted from the filling container, liquefied hydrogen sulfide of a liquid phase evaporates to maintain the vapor-liquid equilibrium within
10 the filling container. In that case, moisture having a vapor-liquid equilibrium constant of about 0.2 has a small evaporation amount as compared with that of the hydrogen sulfide, and therefore is likely to remain on the liquid phase side, and then the moisture is concentrated within the filling
15 container with the emission of the hydrogen sulfide gas. Therefore, the amount of the moisture entrained in the hydrogen sulfide gas is very small in the early stage of the start of the emission and the moisture concentration of the hydrogen sulfide gas is sufficiently low. However, with the
20 progress of a reduction in the liquid phase by the evaporation, the amount of the moisture entrained in the hydrogen sulfide gas gradually increases, and thus the moisture concentration of the hydrogen sulfide gas increases.

[0004]

25 For example, the moisture concentration of the liquid phase in the completion of the filling into the filling container in the hydrogen sulfide generally referred to as a high purity article is about 300 mol ppm. However, in a

state where the moisture is concentrated on the liquid phase side with the emission of the hydrogen sulfide gas from the filling container and the entire amount of the liquefied hydrogen sulfide is finally gasified, the moisture
5 concentration of a gaseous phase increases to about 1500 mol ppm. Although products with lower moisture concentrations are also circulating in the market, the moisture concentration of the liquid phase in the completion of the filling into the filling container is about 20 mol ppm and
10 the moisture concentration of the gaseous phase in the state where the entire amount of the liquefied hydrogen sulfide is finally gasified is about 100 mol ppm.

[0005]

When the moisture concentration of the hydrogen sulfide
15 gas is high, the moisture is likely to adhere to the inner wall surface of piping through which the hydrogen sulfide gas flows. The hydrogen sulfide is absorbed into the moisture to be hydrosulfuric acid, and therefore there is a possibility that the piping corrodes and deteriorates, and thus the repair
20 cost increases. Moreover, when the degradation of the piping proceeds to cause the leakage of hydrogen sulfide gas harmful to a human body, there is a possibility that a disaster or an accident occurs. Furthermore, the piping is formed of stainless steel in many cases. When heavy metals, such as
25 nickel, chromium, and iron, eluted from the piping due to the corrosion are entrained in the hydrogen sulfide gas, there is a possibility that, when hydrogen sulfide gas is used as an additive of an etching gas of a semiconductor wafer, for

example, the heavy metals adhere to the wafer surface to pollute the wafer.

[0006]

To solve the problems, PTL 1 discloses a removal method
5 by dehumidification agents, such as synthetic zeolite, for
example, as a method for removing the moisture in the hydrogen
sulfide. However, the moisture concentration required for
corrosion control is unknown, and therefore the method
described in Patent Document 1 has been difficult to provide
10 hydrogen sulfide capable of controlling corrosion.

Citation List

Patent Literature

PTL 1: JPH2-141406 A1

15

Summary of Invention

Technical Problem

[0008]

Then, it is an object of the present invention to solve
20 the problems of conventional technologies described above and
provide a hydrogen sulfide mixture hardly corroding metals
and a method for producing the same. It is another object
of the present invention to provide a filling container filled
with the hydrogen sulfide mixture hardly corroding metals.

25

Solution to Problem

[0009]

To solve the above-described problems, one aspect of the present invention is as described in [1] to [11] below.

[1] A hydrogen sulfide mixture contains hydrogen sulfide and water, in which the hydrogen sulfide mixture is filled
5 into a filling container so that at least one part of the hydrogen sulfide mixture is liquid and the moisture concentration of a gaseous phase is 0.001 mol ppm or more and less than 75 mol ppm.

[2] A hydrogen sulfide mixture contains hydrogen sulfide
10 and water, in which the hydrogen sulfide mixture is filled into a filling container so that at least one part of the hydrogen sulfide mixture is liquid and the moisture concentration of a liquid phase is 0.01 mol ppm or more and less than 15 mol ppm.

15 [3] The hydrogen sulfide mixture according to [1] or [2], in which a ratio V/G_0 of the internal volume V (unit: L) of the filling container to the initial filling amount G_0 (unit: kg) into the filling container is 1.47 or more and 2.10 or less.

20 [0010]

[4] A method for producing a hydrogen sulfide mixture containing hydrogen sulfide and water includes a dehydration process of bringing a hydrogen sulfide mixture having a moisture concentration of 15 mol ppm or more into contact with
25 a moisture adsorbent to reduce the moisture concentration to less than 10 mol ppm and a filling process of filling the hydrogen sulfide mixture obtained in the dehydration process into a filling container so that at least one part of the

hydrogen sulfide mixture is liquid and the moisture concentration of a liquid phase in the completion of the filling is 0.01 mol ppm or more and less than 15 mol ppm.
[0011]

5 [5] The method for producing a hydrogen sulfide mixture according to [4], in which at least one part of the filling container is formed of stainless steel.

 [6] The method for producing a hydrogen sulfide mixture according to [4] or [5], in which a ratio V/G_1 of the internal
10 volume V (unit: L) of the filling container to the filling amount G_1 (unit: kg) of the hydrogen sulfide mixture into the filling container in the filling process is 1.47 or more and 37.0 or less.

[0012]

15 [7] A filling container filled with a hydrogen sulfide mixture containing hydrogen sulfide and water, in which the hydrogen sulfide mixture is filled so that at least one part of the hydrogen sulfide mixture is liquid and the moisture concentration of a gaseous phase is 0.001 mol ppm or more and
20 less than 75 mol ppm.

 [8] A filling container filled with a hydrogen sulfide mixture containing hydrogen sulfide and water, in which the hydrogen sulfide mixture is filled so that at least one part of the hydrogen sulfide mixture is liquid and the moisture
25 concentration of a liquid phase is 0.01 mol ppm or more and less than 15 mol ppm.

[0013]

[9] The filling container according to [7] or [8], in which the ratio V/G_0 of the internal volume V (unit: L) to the initial filling amount G_0 (unit: kg) of the hydrogen sulfide mixture is 1.47 or more and 2.10 or less.

5 [10] The filling container according to any one of [7] to [9], in which the capacity is 1 L or more and 2000 L or less.

[11] The filling container according to any one of [7] to [10], in which at least one part is formed of stainless
10 steel.

Advantageous Effects of Invention

[0014]

The present invention can provide a hydrogen sulfide
15 mixture hardly corroding metals.

Description of Embodiments

[0015]

The present invention specifies the moisture
20 concentration in hydrogen sulfide to control the corrosion of metals by the hydrogen sulfide. It is generally known that the corrosion of metals by the hydrogen sulfide is strongly influenced by the moisture concentration but the influence of the moisture concentration of a ppm level has not been
25 clarified.

Then, as a result of extensively examining the corrosion of metals by a trace amount of moisture in the hydrogen sulfide, the present inventors have surprisingly found that the

corrosion of metals is remarkably controlled when the moisture concentration is sufficiently low at a ppm level, and thus have accomplished the present invention.

Hereinafter, one embodiment of the present invention is
5 described in detail.

[0016]

A hydrogen sulfide mixture of this embodiment contains hydrogen sulfide and water. The hydrogen sulfide mixture is filled into a filling container so that at least one part of
10 the hydrogen sulfide mixture is liquid and the moisture concentration of a gaseous phase is 0.001 mol ppm or more and less than 75 mol ppm. The moisture concentration of a liquid phase is 0.01 mol ppm or more and less than 15 mol ppm.

A filling container of this embodiment is a filling
15 container filled with the hydrogen sulfide mixture containing hydrogen sulfide and water. The hydrogen sulfide mixture is filled into the filling container so that at least one part of the hydrogen sulfide mixture is liquid and the moisture concentration of the gaseous phase is 0.001 mol ppm or more
20 and less than 75 mol ppm. The moisture concentration of the liquid phase is 0.01 mol ppm or more and less than 15 mol ppm.

[0017]

The moisture concentrations of the gaseous phase and the liquid phase described above are the moisture concentrations
25 of the gaseous phase and the liquid phase from the point of time when the filling of the hydrogen sulfide mixture into the filling container is completed to the point of time when

the substantially entire amount of the hydrogen sulfide mixture in the filling container is discharged.

When the moisture concentration of the gaseous phase of the hydrogen sulfide mixture in which the gaseous phase and the liquid phase coexist is less than 0.01 mol ppm, it is difficult to directly measure the moisture concentration. Therefore, one fifth of the moisture concentration of the liquid phase is regarded as the moisture concentration of the gaseous phase. This is based on the fact that it is experientially known that the moisture concentrations in the hydrogen sulfide in which the gaseous phase and the liquid phase coexist satisfy Moisture concentration of gaseous phase:Moisture concentration of liquid phase = 1:5.

[0018]

In such a hydrogen sulfide mixture, the moisture concentration of the liquid phase in the completion of the filling into the filling container is very low. Therefore, even when the moisture is concentrated on the liquid phase side with the emission of hydrogen sulfide mixture gas from the filling container, a state where the moisture concentration of the liquid phase is sufficiently low is maintained until the entire amount of the liquefied hydrogen sulfide mixture in the filling container is gasified. Accordingly, the moisture concentration of the hydrogen sulfide mixture gas emitted from the filling container is sufficiently low from the early stage of the emission to the end of the emission (time when the entire amount of the liquefied hydrogen sulfide mixture in the filling container

is gasified). Therefore, the corrosion of metals by the hydrogen sulfide mixture gas emitted from the filling container can be remarkably controlled to the end of the emission.

5 [0019]

The moisture concentration of the liquid phase is 0.01 mol ppm or more and less than 15 mol ppm and is preferably 0.01 mol ppm or more and 14 mol ppm or less, more preferably 0.01 mol ppm or more and 7.0 mol ppm or less, and still more
10 preferably 0.01 mol ppm or more and 0.75 mol ppm or less.

When the moisture concentration of the liquid phase is less than 15 mol ppm, the moisture concentration of the hydrogen sulfide mixture gas emitted from a filling container is maintained at a level (for example, less than 75 mol ppm)
15 where the corrosion of metals is controlled to the end of the emission, even when the moisture is concentrated on the liquid phase side with the emission of the hydrogen sulfide mixture gas from the filling container. The moisture concentration lower than 0.01 mol ppm is difficult to confirm.

20 [0020]

The hydrogen sulfide mixture in the filling container and the hydrogen sulfide mixture gas emitted from the filling container have low moisture concentrations and are hard to corrode metals as described above. Therefore, for a portion
25 which the hydrogen sulfide mixture in the filling container and the hydrogen sulfide mixture gas emitted from the filling container contact, metals, such as stainless steel, can be used, without the use of expensive corrosion-resistant alloys,

such as HASTELLOY (Trademark). For example, portions in contact with the hydrogen sulfide mixture in a filling container, piping, a production device, a supply device, a conveying device, a reaction device, and the like of the hydrogen sulfide mixture can be formed of metals, such as stainless steel. The type of usable stainless steel is not particularly limited and SUS316, SUS316L, SUS304, SUS304L, and the like are mentioned.

[0021]

10 The initial filling amount G_0 (unit: kg) of the hydrogen sulfide mixture into the filling container is the filling amount in the completion of a filling process and may also be set to 70% or more and 100% or less of the upper limit of the mass calculated according to the internal volume V of the filling container prescribed by Paragraph 4 of Article 48 of High Pressure Gas Safety Act, although not particularly limited. In other words, the ratio V/G_0 of the internal volume V (unit: L) of the filling container to the initial filling amount G_0 (unit: kg) of the hydrogen sulfide mixture into the filling container is not particularly limited and may be set to 1.47 or more and 2.10 or less.

[0022]

25 When the ratio V/G_0 is 1.47 or more (i.e., when the initial filling amount G_0 of the hydrogen sulfide mixture into the filling container is 100% or less of the upper limit of the mass calculated according to the internal volume V of the filling container), the filling of the hydrogen sulfide mixture into the filling container is not overfilling, and

thus is safe. On the other hand, when the ratio V/G_0 is 2.10 or less (i.e., when the initial filling amount G_0 of the hydrogen sulfide mixture into the filling container is 70% or more of the upper limit of the mass calculated according to the internal volume V of the filling container), the initial filling amount G_0 of the hydrogen sulfide mixture to the internal volume V of the filling container is a sufficient amount, and therefore the transportation efficiency of the hydrogen sulfide mixture by the filling container is high.

10 [0023]

The ratio V/G_0 of the internal volume V (unit: L) of the filling container to the initial filling amount G_0 (unit: kg) of the hydrogen sulfide mixture into the filling container is more preferably 1.50 or more and 2.00 or less and still more preferably 1.53 or more and 1.90 or less.

Next, one embodiment of a method for producing the above-described hydrogen sulfide mixture is described. First, the moisture is removed from hydrogen sulfide mixture gas having a moisture concentration of 15 mol ppm or more in a dehydration process to obtain a hydrogen sulfide mixture gas having a moisture concentration of less than 10 mol ppm. In the dehydration process, the hydrogen sulfide mixture gas having a moisture concentration of 15 mol ppm or more is brought into contact with a moisture adsorbent to be dehydrated to set the moisture concentration to less than 10 mol ppm. The type of the moisture adsorbent is not particularly limited insofar as the moisture concentration of the hydrogen sulfide mixture gas can be set to less than

10 mol ppm. For example, zeolite, activated carbon, silica gel, and diphosphorus pentoxide are mentioned. The type of the zeolite is not particularly limited and a ratio of silica and alumina contained in the zeolite and the pore size of fine
5 pores are also not particularly limited. Those having hydrogen sulfide resistance are preferable and, for example, Molecular Sieve 3A and high silica zeolite are mentioned.
[0024]

The hydrogen sulfide mixture gas having a moisture
10 concentration set to less than 10 mol ppm by the dehydration process is compressed, and then filled into a filling container having a capacity of 1 L or more and 2000 L or less, for example, in the filling process. In that case, the hydrogen sulfide mixture gas is compressed and filled so that
15 at least one part of the hydrogen sulfide mixture gas is liquid and the moisture concentration of a liquid phase in the completion of the filling is 0.01 mol ppm or more and less than 15 mol ppm.

[0025]

20 A method for compressing the hydrogen sulfide mixture gas and filling the compressed hydrogen sulfide mixture gas into a filling container is not limited. For example, a method is mentioned which includes increasing the pressure of the hydrogen sulfide mixture gas with a compressor to
25 liquefy the hydrogen sulfide mixture gas, removing a low boiling point component and a high boiling point component using a distillation column, storing the resultant hydrogen sulfide mixture gas in a product tank, and then moving the

resultant hydrogen sulfide mixture gas to a filling container from the product tank to fill the resultant hydrogen sulfide mixture gas into the filling container.

The capacity of the filling container can be set to 1
5 L or more and 2000 L or less and preferably 2 L or more and 1800 L or less and more preferably 3 L or more and 1500 L or less. When the capacity of the filling container is 1 L or more, the amount of the usable hydrogen sulfide mixture is large, and therefore the efficiency is excellent. On the
10 other hand, when the capacity of the filling container is 2000 L or less, the filling container is easily produced and transported.

[0026]

The temperature of the filling container is not
15 particularly limited in filling the hydrogen sulfide mixture into the filling container. The filling container may be cooled beforehand to -90°C or more and 0°C or less. Furthermore, when the moisture remains in the filling container, the moisture concentration of the filled hydrogen
20 sulfide mixture increases. Therefore, heating decompression treatment may be performed beforehand so that the amount of the remaining moisture in the filling container is 0.1 mol ppm or less.

[0027]

25 Furthermore, the ratio V/G_1 of the internal volume V (unit: L) of the filling container to the filling amount G_1 (unit: kg) of the hydrogen sulfide mixture into the filling container in the filling process is not particularly limited

and may also be set to 1.47 or more and 37.0 or less. When the ratio V/G_1 is 1.47 or more, the filling of the hydrogen sulfide mixture into the filling container is not overfilling, and thus is safe. On the other hand, when the ratio V/G_1 is 5 37.0 or less, the hydrogen sulfide mixture is liquefied.
[0028]

The ratio V/G_1 of the internal volume V (unit: L) of the filling container to the filling amount G_1 (unit: kg) of the hydrogen sulfide mixture into the filling container in the 10 filling process is more preferably 1.47 or more and 2.70 or less and still more preferably 1.47 or more and 2.10 or less.

A method for measuring the moisture concentration of the hydrogen sulfide mixture in each process (dehydration process, filling process) of the method for producing the hydrogen 15 sulfide mixture of this embodiment is not particularly limited insofar as the measurement up to about 0.01 mol ppm can be correctly performed. For example, a mirror surface cooling type dew point meter, a Fourier transform infrared spectrometer (FT-IR), a method using a phosphorus pentaoxide 20 type moisture meter or the like, and a cavity ring-down spectroscopy (CRDS) are mentioned.
[0029]

In the case of a gaseous phase, the moisture concentration in the present invention is one measured by 25 taking out a sample from a gaseous phase portion of the filling container, and then measuring the moisture concentration by the cavity ring-down spectroscopy. On the other hand, in the case of a liquid phase, the moisture concentration in the

present invention is one measured by taking out a sample from a liquid phase portion of the filling container, gasifying the same, and then measuring the moisture concentration by the cavity ring-down spectroscopy as in the case of the
5 gaseous phase.

According to such a method for producing the hydrogen sulfide mixture of this embodiment, a hydrogen sulfide mixture having a very low moisture concentration and hardly causing the corrosion of metals, such as stainless steel, can
10 be produced with a simple facility. The hydrogen sulfide mixture produced by the method for producing the hydrogen sulfide mixture of this embodiment is usable as an addition gas or an interface treatment gas in etching in the production of a semiconductor or a thin film transistor.

15 [0030]

Furthermore, the hydrogen sulfide mixture obtained by the method for producing the hydrogen sulfide mixture of this embodiment is also usable for the production of various chemicals, such as pharmaceutical agents and dye
20 intermediates.

Although this embodiment describes an example of the present invention, the present invention is not limited to this embodiment. Moreover, this embodiment can be variously altered or modified and embodiments subjected to the
25 alternations or the modifications can also be encompassed in the present invention.

EXAMPLES

[0031]

Hereinafter, the present invention is described in more detail with reference to Examples and Comparative Examples.

[Example 1]

5 Into a filling container having a capacity of 47 L, 30 kg of a hydrogen sulfide mixture containing hydrogen sulfide and water was filled so that one part of the hydrogen sulfide mixture was a liquid. The ratio V/G_0 of the internal volume V of the filling container to the initial filling amount G_0
10 at this time is 1.57. The hydrogen sulfide mixture in the filling container was separated into a gaseous phase and a liquid phase. The moisture concentration of the liquid phase in the completion of the filling was 12 mol ppm.

[0032]

15 The gaseous phase was extracted from the filling container at a discharge rate of 2 L/min until the remaining amount of the hydrogen sulfide mixture in the filling container was 1 kg. In this state, the liquid phase in the filling container disappeared, the entire amount of the
20 hydrogen sulfide mixture was gasified, and the moisture concentration of the gas was 60 mol ppm.

 A rectangular-shaped (10 mm in width, 50 mm in length, and 1 mm in thickness) SUS316L test piece was prepared, the mass was measured, and then the test piece was hung in a
25 pressure resistant container using a string containing Teflon (Registered Trademark). The hydrogen sulfide mixture gas having a moisture concentration of 60 mol ppm was introduced

into the pressure resistant container, and then the internal pressure was set to 0.5 MPaG.

[0033]

The pressure resistant container was allowed to stand
5 for 5 days in a state of being heated at 100°C, and then
sufficiently purged with N₂. Then, after confirming that the
hydrogen sulfide concentration was less than 0.1 mol ppm, the
pressure resistant container was opened, and then the test
piece was taken out. The taken-out test piece was
10 ultrasonically cleaned with ultrapure water and a 10% by mass
nitric acid aqueous solution for 10 minutes, respectively,
and then dried. Thereafter, the mass was measured, and then
the corrosion rate was calculated from mass changes. As a
result, the corrosion rate was 0.83 μm/y. Thus, the progress
15 of the corrosion by the remaining gas was very slow even in
a state where 97% of the initial filling amount was
discharged.

[0034]

[Example 2]

20 A hydrogen sulfide mixture gas having a moisture
concentration of 30 mol ppm was obtained by performing the
same operation as that of Example 1, except that the moisture
concentration of the liquid phase in the completion of the
filling into the filling container was 6.0 mol ppm. The
25 corrosion rate of a test piece was 0.64 μm/y as measured by
performing the same operation as that of Example 1, except
using the hydrogen sulfide mixture gas.

[0035]

[Example 3]

A hydrogen sulfide mixture gas having a moisture concentration of 3.8 mol ppm was obtained by performing the same operation as that of Example 1, except that the moisture concentration of the liquid phase in the completion of the filling into the filling container was 0.75 mol ppm. The corrosion rate of a test piece was 0.41 $\mu\text{m}/\text{y}$ as measured by performing the same operation as that of Example 1, except using the hydrogen sulfide mixture gas.

10 [0036]

[Example 4]

A hydrogen sulfide mixture gas having a moisture concentration of 0.75 mol ppm was obtained by performing the same operation as that of Example 1, except that the moisture concentration of the liquid phase in the completion of the filling into the filling container was 0.15 mol ppm. The corrosion rate of a test piece was 0.38 $\mu\text{m}/\text{y}$ as measured by performing the same operation as that of Example 1, except using the hydrogen sulfide mixture gas.

20 [0037]

[Comparative Example 1]

A hydrogen sulfide mixture gas having a moisture concentration of 75 mol ppm was obtained by performing the same operation as that of Example 1, except that the moisture concentration of the liquid phase in the completion of the filling into the filling container was 15 mol ppm. The corrosion rate of a test piece was 7.1 $\mu\text{m}/\text{y}$ as measured by

performing the same operation as that of Example 1, except using the hydrogen sulfide mixture gas.

[0038]

[Comparative Example 2]

5 A hydrogen sulfide mixture gas having a moisture concentration of 150 mol ppm was obtained by performing the same operation as that of Example 1, except that the moisture concentration of the liquid phase in the completion of the filling into the filling container was 30 mol ppm. The
10 corrosion rate of a test piece was 47 $\mu\text{m}/\text{y}$ as measured by performing the same operation as that of Example 1, except using the hydrogen sulfide mixture gas.

[0039]

 These results (see Table 1) indicate that, when the
15 moisture concentration of the liquid phase in the completion of the filling into the filling container is less than 15 mol ppm, the moisture concentration of the hydrogen sulfide mixture gas emitted from the filling container is sufficiently low to the end of the emission (time when the
20 entire amount of the liquefied hydrogen sulfide mixture in the filling container is gasified), and therefore the corrosion of metals is remarkably controlled.

[0040]

[Table 1]

	Ex. 1	Ex. 2	Ex. 3	Ex. 4	Comp. Ex. 1	Comp. Ex. 2
Moisture concentration of liquid phase in completion of filling (mol ppm)	12	6.0	0.75	0.15	15	30
Moisture concentration of gaseous phase after extracting gaseous phase until remaining amount is 1 kg (mol ppm)	60	30	3.8	0.75	75	150
Corrosion rate ($\mu\text{m}/\text{y}$)	0.83	0.64	0.41	0.38	7.1	47

[0041]

[Example 5]

Next, an example of a method for producing a hydrogen sulfide mixture having a moisture concentration of less than 5 15 mol ppm is described. A crude hydrogen sulfide mixture gas having a moisture concentration of 1000 mol ppm was sent to a moisture adsorption column at a flow of 320 m³/h to be brought into contact with a moisture adsorbent (Molecular 10 Sieve 3A manufactured by UNION SHOWA K.K.) filled into the moisture adsorption column to be dehydrated. With respect to the circulation velocity of the crude hydrogen sulfide mixture gas, the linear velocity LV is 10 m/min and the space velocity SV is 1000/h. The moisture concentration of the 15 hydrogen sulfide mixture gas at an outlet of the moisture adsorption column was 5.1 mol ppm.

30 kg of the hydrogen sulfide mixture gas having a moisture concentration of 5.1 mol ppm was filled into a filling container having a capacity of 47 L while increasing 20 the pressure with a pump. The moisture concentration of a liquefied hydrogen sulfide mixture (liquid phase) in the filling container was 6.2 mol ppm.

CLAIMS

1. A hydrogen sulfide mixture comprising:
hydrogen sulfide; and
5 water,

wherein the hydrogen sulfide mixture is filled into a filling container so that at least one part of the hydrogen sulfide mixture is liquid and a moisture concentration of a gaseous phase is 0.001 mol ppm or more and less than 75 mol
10 ppm.

2. A hydrogen sulfide mixture comprising:
hydrogen sulfide; and
water,

15 wherein the hydrogen sulfide mixture is filled into a filling container so that at least one part of the hydrogen sulfide mixture is liquid and a moisture concentration of a liquid phase is 0.01 mol ppm or more and less than 15 mol ppm.

20 3. The hydrogen sulfide mixture according to Claim 1 or 2,

wherein a ratio V/G_0 of an internal volume V (unit: L) of the filling container to an initial filling amount G_0 (unit: kg) into the filling container is 1.47 or more and 2.10 or
25 less.

4. A method for producing a hydrogen sulfide mixture containing hydrogen sulfide and water, the method comprising:

a dehydration step of bringing a hydrogen sulfide mixture having a moisture concentration of 15 mol ppm or more into contact with a moisture adsorbent to reduce the moisture concentration to less than 10 mol ppm; and

5 a filling step of filling the hydrogen sulfide mixture obtained in the dehydration step into a filling container so that at least one part of the hydrogen sulfide mixture is liquid and the moisture concentration of a liquid phase in completion of the filling is 0.01 mol ppm or more and less
10 than 15 mol ppm.

5. The method for producing a hydrogen sulfide mixture according to Claim 4,

 wherein at least one part of the filling container is
15 formed of stainless steel.

6. The method for producing a hydrogen sulfide mixture according to Claim 4 or 5,

 wherein a ratio V/G_1 of an internal volume V (unit: L)
20 of the filling container to a filling amount G_1 (unit: kg) of the hydrogen sulfide mixture into the filling container in the filling step is 1.47 or more and 37.0 or less.

7. A filling container filled with a hydrogen
25 sulfide mixture containing hydrogen sulfide and water,

 wherein the hydrogen sulfide mixture is filled so that at least one part of the hydrogen sulfide mixture is liquid

and a moisture concentration of a gaseous phase is 0.001 mol ppm or more and less than 75 mol ppm.

8. A filling container filled with a hydrogen sulfide mixture containing hydrogen sulfide and water,
5 wherein the hydrogen sulfide mixture is filled so that at least one part of the hydrogen sulfide mixture is liquid and a moisture concentration of a liquid phase is 0.01 mol ppm or more and less than 15 mol ppm.

10

9. The filling container according to Claim 7 or 8,
wherein a ratio V/G_0 of an internal volume V (unit: L) to an initial filling amount G_0 (unit: kg) of the hydrogen sulfide mixture is 1.47 or more and 2.10 or less.

15

10. The filling container according to any one of Claims 7 to 9,
wherein a capacity is 1 L or more and 2000 L or less.

20 11. The filling container according to any one of Claims 7 to 10,
wherein at least one part is formed of stainless steel.