



ABSTRACT

A thermoplastic resin composition comprising from 3 to 50 parts by weight of component (A) which is a maleimide copolymer comprising from 40 to 80 wt% of residues of an aromatic vinyl monomer, at most 20 wt% (excluding 0 wt%) of residues of an unsaturated dicarboxylic acid anhydride monomer, at least 10 wt% and less than 60 wt% of residues of an unsaturated dicarboxylic acid imide derivative and from 0 to 20 wt% of residues of a vinyl monomer copolymerizable therewith; from 0 to 50 parts by weight of component (B) which is a vinyl copolymer comprising from 60 to 80 wt% of residues of an aromatic vinyl monomer, from 20 to 40 wt% of residues of a vinyl cyanide monomer and from 0 to 20 wt% of residues of a vinyl monomer copolymerizable therewith; from 3 to 50 parts by weight of component (C) which is a graft copolymer obtained by graft polymerizing from 35 to 65 parts by weight of a monomer mixture comprising from 50 to 80 wt% of an aromatic vinyl monomer, from 20 to 40 wt% of a vinyl cyanide monomer and from 0 to 30 wt% of a vinyl monomer copolymerizable therewith, to from 35 to 65 parts by weight of a rubbery polymer; more than 20 parts by weight and not more than 56 parts by weight of component (D) which is a polyamide resin; and more than 12 parts by weight and not more than 40 parts by weight of component (E) which is an elastomer copolymer of ethylene- α -olefin containing at most 5 wt% (excluding 0





wt%) of residues of an unsaturated dicarboxylic acid
monomer and/or residues of an unsaturated dicarboxylic
acid anhydride monomer; provided that the total of
components (A) to (E) is 100 parts by weight; said
5 thermoplastic resin composition having a melt flow rate
(MFR) of from 3 to 40 g/10 minutes at 265°C under a load
of 10 kg.

