

ANTI-REFLECTION MEMBER, MANUFACTURING METHOD THEREOF, AND CATHODE-RAY TUBE

BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates to an anti-reflection member and manufacturing method thereof, and relates to a cathode ray tube having a front panel applied with such anti-reflection member.

Description of Related Art

For example for conventional cathode ray tubes (CRT), a picture displayed on the cathode ray tube is viewed not clearly because external light is reflected on the panel surface, that is a problem of conventional cathode ray tubes. On the other hand, the potential of the panel surface changes because of high voltage applied on the fluorescent screen formed on the inside surface of the panel of the cathode ray tube. As the result, dusts adheres on the panel surface, and the panel causes electric discharge to a human body when approaching. To prevent such phenomena, it is required to provide antistatic function on the panel surface. In addition, it is also important to provide electromagnetic radiation shielding function so as not

REPLACED SHEETS		SG
☒	Description : paged 27, 4, 10, 11, 15-17, 19	to paged 5
☒	Claim(s) : paged 41	to paged 41
☐	Drawing(s) : paged	to paged
☒	Abstract : paged 50	to paged 1
DATE OF RECEIPT		

2-4-2010

to release electromagnetic wave from the cathode ray tube. As a method for solving all the technical problems as described herein above, a technique in which an anti-reflection member having conductivity is applied on the panel surface has been known.

Such an anti-reflection member comprises a laminate composed of a substrate, hard coat layer, and multilayered reflection preventing optical thin film. The substrate consists of, for example, polyethylene-terephthalate (PET) or polycarbonate (PC), and a hard coat layer consisting of, for example, polymethylmethacrylate (PMMA), is formed on the surface of the substrate because the surface is susceptible to touching. In the case that it is not necessary to provide antistatic function and electromagnetic radiation shielding function to an anti-reflection member, at least two layers of dielectric thin film consisting of SiO , SiO_2 , TiO_2 , ZrO_2 , Ta_2O_5 , and Y_2O_5 (for example, lamination structure such as a high refractive index film/low refractive index film/high refractive index/low refractive index film ...) are formed on the hard coat layer. Materials having high refractive index (having a refractive index of 1.8 to 2.7 at around the wave length of 550 nm) such as TiO_2 , ZrO_2 , Ta_2O_5 , and

Y_2O_5 are excellent in adhesion with hard coat layer consisting of polymethyl-methacrylate.

On the other hand, in the case that it is necessary to provide antistatic function and electromagnetic radiation shielding function to an anti-reflection member, it is preferable to structure a reflection preventing optical thin film by laminating a transparent conductive oxide film and a thin film (referred as to low refractive index film hereinafter) consisting of a material having lower refractive index than that of the material used for the transparent conductive oxide film. By structuring the reflection preventing optical thin film as described herein, not only antistatic function and electromagnetic radiation shielding function due to transparent conductive oxide film is provided to the anti-reflection member but also anti-reflection function due to the high refractive index film/low refractive index film structure is provided simultaneously, thereby the structure of a reflection preventing optical thin film is simplified. As an example of the transparent conductive oxide film includes ITO (I_2O_3 doped with Sn) film (refractive index is 1.9 to 2.0). On the other hand, as examples of the low refractive index film include SiO_2 film (refractive

index = 1.46 at 550 nm) and MgF_2 film (refractive index = 1.38 at 550 nm).

Usually, by repeating the film forming process, namely, ITO film/low refractive index film/ITO film/low refractive index film ... on a hard coat layer formed on a substrate, an anti-reflection member is provided with excellent anti-reflection function in the wide wave length range from 450 to 650 nm. A schematic partial cross-sectional view of the anti-reflection member having such structure is shown in Fig. 4A. In Fig. 4A, a reflection preventing optical thin film having four layer structure is shown, the first layer and third layer consist of ITO film, and the second and fourth layer consist of low refractive index film. Usually, ITO film is formed by sputtering using a target of oxide ITO. An ITO film is formed under the sputtering condition that the composition of such ITO target is, for example, $\text{In}_2\text{O}_3/\text{SnO}_2 = 90$ parts by weight/10 parts by weight, target current density is 2 W/cm^2 , and others are $\text{Ar}/\text{O}_2 = 50$ volume %/50 volume %, and 0.2 Pa.

It is reported that the crystallization temperature of ITO ranges from 150 to 200°C. Therefore, to improve the adhesion (adhesion strength) to a hard

coat layer, it is desirable to heat the substrate to a temperature of 120°C or higher. However, such heating of a substrate can cause thermal damage such as deformation of the substrate consisting of plastic material. Heating of a hard coat layer consisting of polymethyl-methacrylate to a temperature of 100°C or higher can cause the reduction of the hardness.

Recently, ITO film formed on a color filter is used as transparent electrode for a flat panel display of liquid crystal display devices. Such ITO film is formed by DC magnetron sputtering using ITO target. ITO film formed by such method is excellent in resistivity, wet etching performance, and reproducibility of characteristics. However, ITO film formed on a hard coat layer by DC magnetron sputtering using an ITO target is insufficient in adhesion strength to the hard coat layer.

The inventors of the present invention proposed a new anti-reflection member comprising a laminate of a substrate, hard coat layer, and multilayered reflection preventing optical thin films in Japanese Patent Application Hei 7-170925 (application date: July 6, 1995). A schematic partial cross-sectional view of the anti-reflection member having such

structure is shown in Fig. 4B. The substrate of the anti-reflection member consists of, for example, polyethylene-terephthalate (PET) and polycarbonate (PC), a hard coat layer consisting of, for example, polymethyl-methacrylate (PMMA) is formed thereon. To provide antistatic function and electromagnetic radiation shielding function to the anti-reflection member, the anti-reflection member has the first layer of the reflection preventing optical thin film comprising a conductive light absorbing film, and the second layer of the reflection preventing optical thin film consisting of a material having lower refractive index than that of the material used to structure the first layer.

The conductive light absorbing film consists of a material selected from the group composed of Ag, Au, TiN_x ($x = 0.3$ to 1), TiO_xN_y (wherein $x = 0.3$ to 1 , $y < 1$, and $y \leq x$), TaN_x (wherein $x = 0.2$ to 1), Pt, Al, Cu, Ta, Ni-Cr, Cu-Al, Cu-Zn-Al, Cu-Ni-Al and Cu-Sn-Al, and the thickness ranges from 4 to 40 nm. On the other hand, the second layer of the reflection preventing optical thin film consists of SiO_2 or MgF_2 . The above-mentioned material to be used for the conductive light absorbing film has a characteristics that light

absorption coefficient changes dependently on wave length. Reflection is prevented for the wide range of wave length, prevention of light with the wide range of wave length (430 to 650 nm) is possible even if the reflection preventing optical thin film has a two layer structure. The light transmittance of these materials ranges from 70 to 90 %, however, because the two layer structure can be used for the reflection preventing optical thin film, therefore the low light transmittance of the conductive light absorbing film does not cause any problem.

However, it was found that the adhesion (adhesion strength) of such conductive light absorbing film to a hard coat consisting of polymethylmethacrylate was insufficient.

Therefore, it is the object of the present invention to provide an anti-reflection member provided with antistatic function and electromagnetic radiation shielding function and having a reflection preventing optical thin film excellent in adhesion to a hard coat layer, and a manufacturing method thereof, in addition, a cathode ray tube having a front panel applied with such anti-reflection member.

This Sheet Has Been Replaced



SUMMARY OF THE INVENTION

A anti-reflection member in accordance with the first embodiment of the present invention for achieving the above mentioned object is the anti-reflection member comprising a laminate of substrate, hard coat layer, and reflection preventing optical thin film having at least two layers, wherein

the first layer of the reflection preventing optical thin film in contact with the hard coat layer consists of transparent conductive oxide film formed by reactive physical vapor phase deposition, and

the second layer of the reflection preventing optical thin film consists of a material having a lower refractive index than that of the first layer.

A manufacturing method of an anti-reflection member in accordance with the first embodiment of the present invention for achieving the above-mentioned object is the manufacturing method of an anti-reflection member comprising a laminate of substrate, hard coat layer, and reflection preventing optical thin film having at least two layers, wherein

the first layer of the reflection preventing optical thin film in contact with the hard coat layer consists of transparent conductive oxide film, and

This Sheet Has Been Replaced



the second layer of the reflection preventing optical thin film consists of a material having a lower refractive index than that of the first layer, and

the transparent conductive oxide film is formed by reactive physical vapor phase deposition.

Wherein, the "transparent" of the transparent conductive oxide film means the absorption coefficient α based on Lambert's law of 0 to 0.3, preferably, 0 to 0.2 when a light with a wave length of 550 nm is transmitted. The "conductive" of the transparent conductive oxide film means the value of resistance measured by eddy current method of 1×10 to 1×10^4 $\Omega/\square$, preferably, 1×10 to 5×10^3 $\Omega/\square$.

In the anti-reflection member or the manufacturing method thereof in the first embodiment of the present invention, examples of the reactive physical vapor phase deposition, namely, physical vapor phase deposition (PVD, Physical Vapor Deposition) accompanying chemical reaction between at least partial material to be deposited on the hard coat layer and the material used for the hard coat layer, include;

(A) various vacuum deposition such as electron beam heating, resistance heating, and flush deposition,

(B) plasma deposition,

This Sheet Has Been Replaced



(C) various sputtering such as bipolar sputtering, DC sputtering, DC magnetron sputtering, high frequency sputtering, magnetron sputtering, ion-beam sputtering, and bias-sputtering, and

(D) various ion-plating such as DC method, RF method, multi-cathode method, activation reaction method, HCD method, electric field deposition, high frequency ion-plating, and reactive ion-plating,

wherein among these methods, reactive sputtering using a metal or alloy target, in detail, DC magnetron sputtering is preferably used. In this case, a target consisting of Sn, Zn, In, or In-Sn alloy is preferably used. When Sn is used as a target, a transparent conductive oxide film obtained by reactive physical vapor phase deposition consists of SnO_2 . When Zn is used as a target, a transparent conductive oxide film obtained by reactive physical vapor phase deposition consists of ZnO . When In is used as a target, a transparent conductive oxide film obtained by reactive physical vapor phase deposition consists of In_2O_3 . Further, when In-Sn is used as a target, a transparent conductive oxide film obtained by reactive physical deposition consists of ITO. Sputtering is carried out in an O_2 atmosphere for the reactive

This Sheet Has Been Replaced



spattering. On the other hand, spattering is carried out in an Ar+O₂ (content of O₂ is 0 to 30 volume %) atmosphere for conventional spattering using an oxide target.

To improve the adhesion to a hard coat layer, it is preferable that an element (referred to as element B) having the same or higher affinity with oxygen as an element (referred to as element A hereinafter) which constitutes the transparent conductive oxide film is contained in the transparent conductive oxide film. In general, the affinity of an element to oxygen can be estimated from the standard free energy of formation of the oxide. In other words, an oxide having smaller standard free energy of formation forms oxide easier. Though it depends on the element A, an example of the element B includes an element selected from the group composed of Ti, Zr, Al, Mg, Si, Cr, W, Fe, and Mn. Examples of combination of the element A and element B are listed in Table 1. The ratio element B/(element A + element B) (in atomic ratio) is 0.001 to 0.1, preferably 0.005 to 0.05.

This Sheet Has Been Replaced



Table 1

Element A	Element B
-----------	-----------

Sn	Cr, Ti, Al, Zr
Zn	Cr, Ti, Al, Zr
In	Cr, Ti, Al, Zr
In and Sn	Cr, Ti, Al, Zr

In the manufacturing method of the anti-reflection member in accordance with the first embodiment of the present invention, a material consisting of the second layer of the reflection prevention optical thin film may be a material having a refractive index of about 1.7 or smaller, examples include SiO_2 , SiO , MgF_2 , CaF_2 , LaF_3 , Na_3AlF_6 , $\text{Na}_5\text{Al}_3\text{F}_{14}$, NdF_3 , LaF_3 , CeF_3 , BaF_2 , NaF , SrF_2 , and Al_2O_3 , among these materials, SiO_2 or MgF_2 is preferably used.

It is preferable that the hard coat layer consists of a material which contains oxygen as a constituent element. In detail, the hard coat layer may be an organic film consisting of a resin-based material selected from the group composed of silicon-based material, polyfunctional acrylate-based material or urethane resin-based material, melamine resin-based material, and epoxy resin-based material, and may be an organic-inorganic film. Examples of silicon-based material include co-hydrolysates of tetra-alkoxysilane

or alkyl-trialcoxysilane and silane coupling agent having functional group such as epoxy group or methacryl group. Examples of polyfunctional acrylate-based material include, for example, polyol-acrylate, polyester-acrylate, urethane-acrylate, and epoxy-acrylate. Furthermore, an example of urethane resin-based material includes, for example, melamine-polyurethane. The hard coat layer consists preferably of acryl-based material, more preferably in detail for example, polymethyl-methacrylate (PMMA). An example of organic-inorganic film includes acryl-silicon. Otherwise, the hard coat layer of organic-inorganic film may be formed from colloidal silica in a form of hydrophylic sol or lipophilic sol. The hard coat layer may be formed by various methods for coating a material such as dipping coating, spin coating, spray coating, and flow coating followed by drying and thermosetting or ultraviolet ray curing.

In the manufacturing method of the light reflection prevention member in accordance with the first embodiment of the present invention, the anti-reflection member may be manufactured continuously by a process in which substrate comprises a roll film, the film on which a hard coat layer had been formed

previously is unwound, the first layer comprising a transparent conductive oxide film is formed on the hard coat layer by reactive sputtering using a metal or alloy target, subsequently the second layer of reflection preventing optical thin film is formed on the first layer by sputtering, then the film comprising the reflection preventing optical thin film formed on the hard coat layer is wound.

In the manufacturing process of the anti-reflection member in accordance with the first embodiment of the present invention, a SnO_2 layer, ZnO layer, I_2O_3 layer, or ITO layer is formed on the second layer of the reflection preventing optical thin film, thereon a SiO_2 layer or MgF_2 layer is formed, further, these two layers may be laminated one above another alternately. In detail, for example, the reflection preventing optical thin film may have a structure such as ITO layer/ SiO_2 layer/ITO layer/ SiO_2 layer/.../ITO layer/ SiO_2 layer, SnO_2 layer/ SiO_2 layer/ SnO_2 layer/ SiO_2 layer/.../ SnO_2 layer/ SiO_2 layer, or ZnO layer/ SiO_2 layer/ ZnO layer/ SiO_2 layer/.../ ZnO layer/ SiO_2 layer. Otherwise, the structure may comprise m -th layers (m is odd numbers) consisting of the same or different materials selected from the group composed of SnO_2 , ZnO ,

I_2O_3 , and ITO, and n-th layers (n is even numbers) consisting of the same or different materials selected from the group composed of SiO_2 and MgF_2 (for example, SnO_2 layer/ SiO_2 layer/ITO layer/ SiO_2 layer). In this case, a SnO_2 , ZnO layer, I_2O_3 layer, or ITO layer of (2N-1)th layer (wherein $1 < N$) may be formed by, for example, either reactive sputtering or conventional sputtering using an oxide target.

The anti-reflection member in accordance with the second embodiment of the invention for achieving the above-mentioned object comprises a laminate of substrate, hard coat layer, and reflection preventing optical thin film having at least three layers, wherein

the first layer of the reflection preventing optical thin film in contact with the hard coat layer consists of transparent oxide film formed by reactive physical vapor phase deposition, and

the second layer of the reflection preventing optical thin film consisting of conductive light absorbing film, and

the third layer of the reflection preventing optical thin film consists of a material having a lower refractive index than that of the second layer.

This Sheet Has Been Replaced



The manufacturing method of the anti-reflection member in accordance with the second embodiment of the present invention for achieving the above-mentioned object is the manufacturing method of an anti-reflection member comprising a laminate of a substrate, hard coat layer, and reflection preventing optical thin film having at least three layers, wherein

the first layer of the reflection preventing optical thin film in contact with said hard coat layer consists of transparent oxide film, and

the second layer of the reflection preventing optical thin film consisting of conductive light absorbing film, and

the third layer of the reflection preventing optical thin film consists of a material having a lower refractive index than that of the second layer, and

the transparent oxide film is formed by reactive physical vapor phase deposition.

Wherein, the "transparent" of the transparent conductive oxide film means the absorption coefficient α based on Lambert's law of 0 to 0.3, preferably, 0 to 0.2 when a light with a wave length of 550 nm is transmitted. The "conductive" of the transparent conductive oxide film means the value of resistance

This Sheet Has Been Replaced



measured by eddy current method of 1×10 to 1×10^4 $\Omega/\square$, preferably, 1×10 to 5×10^3 $\Omega/\square$. Further, the "light absorptive" of the conductive light absorbing film means the absorption coefficient of 0 to 0.5 when a light of 550 nm is transmitted, preferably 0.1 to 0.3.

In the anti-reflection member or the manufacturing method thereof in accordance with the second embodiment of the present invention, the same reactive physical vapor phase deposition as described in the anti-reflection member or the manufacturing method thereof in accordance with the first embodiment of the present invention may be used, among these methods, reactive sputtering using a metal or alloy target, in detail, DC magnetron sputtering is preferably used.

The thickness of the transparent oxide film may be arbitrary as far as the thickness does not influence adversely on the anti-reflection effect, but generally, the thickness is 1 to 20 nm in average provided on a hard coat layer. The transparent oxide film is formed only to improve the adhesion between the second layer of the reflection preventing optical thin film and the hard coat layer.

In the anti-reflection member or the manufacturing method thereof in accordance with the

This Sheet Has Been Replaced



second embodiment of the present invention, the transparent oxide film consists preferably of at least one material selected from the group composed of ZrO_2 , TiO_2 , SiO_x (wherein $x = 1$ to 2), SiO_xN_y (wherein $x = 1$ to 2 , $y = 0.2$ to 0.6), and CrO_x (wherein $x = 0.2$ to 1.5). When reactive sputtering is used as the reactive physical vapor phase deposition, a target consisting of Zr is used for forming ZrO_2 film, a target consisting of Ti is used for forming TiO_2 film, a target consisting of Si is used for forming SiO_x (wherein $x = 1$ to 2) film or SiO_xN_y (wherein $x = 1$ to 2 , and $y = 0.2$ to 0.6), and a target consisting of Cr is used for forming CrO_x film. The transparent oxide film may be provided with conductivity. For providing conductivity, the transparent oxide film may consist of SnO_2 , ZnO , In_2O_3 , or ITO, and the film is formed by reactive physical vapor deposition in the same manner as described in the description of the anti-reflection member or the manufacturing method thereof in accordance with the first embodiment of the present invention.

To improve the adhesion to a hard coat layer, it is preferable that an element (referred to as element D hereinafter) having the same or higher affinity with oxygen as an element (referred to as element D

This Sheet Has Been Replaced



hereinafter) which constitutes the transparent oxide film is contained in the transparent oxide film. Though it depends on the element C, an examples of the element D includes an element selected from the group composed of Ti, Zr, Al, Mg, Be, Si, Cr, W, Fe, Mn, and Sn. Examples of combination of the element C and element D are listed in Table 2. The ratio element D/(element C + element D) (in atomic ratio) is 0.001 to 0.1, preferably 0.005 to 0.05.

Table 2

Element C	Element D
Zr	Mg, Be
Ti	Al, Zr, Be
Si	Ti, Al, Zr, Be
Cr	Si, Ti, Al, Zr, Be

In the anti-reflection member or the manufacturing method thereof in accordance with the second embodiment of the present invention, the conductive light absorbing film consists preferably of metal, alloy, metal nitride or metal oxide-nitride. Wherein, nitrides of alloy and nitride-oxides of alloy are included in the term "metal nitride" and "metal oxide-nitride". In detail, examples of material to be used for the conductive light absorbing film include materials selected from the group composed of Ag, Au, $TiNX$ ($X = 0.3$ to 1), TiO_xN_y (wherein $X = 0.3$ to 1 , $Y < 1$, and $Y \leq X$), TaN_x (wherein $X = 0.2$ to 1), Pt, Al, Cu, Ta, Ni-Cr, Cu-Al, Cu-Zn-Al, Cu-Ni-Al and Cu-Sn-Al. Oxygen and Nitrogen happen to be trapped occasionally during forming of the conductive light absorbing film consisting of metal or alloy, however herein, this conductive light absorbing film is defined as the

conductive light absorbing film consisting of metal or alloy.

In the anti-reflection member or the manufacturing method thereof in accordance with the second embodiment of the present invention, examples to be used for the third layer of the reflection preventing optical thin film include SiO_2 , MgF_2 , CaF_2 , LaF_3 , Na_3AlF_6 , NdF_3 , LaF_3 , and Al_2O_3 , among these materials, SiO_2 or MgF_2 is preferably used. The hard coat layer may consist of the same material as described in the description of the reflection preventing member or the manufacturing method thereof in accordance with the first embodiment of the present invention, among these materials, in detail, the hard coat layer consists preferably of polymethyl-methacrylate (PMMA).

In the manufacturing method of the light reflection prevention member in accordance with the second embodiment of the present invention, the anti-reflection member may be manufactured continuously by a process in which substrate comprises a roll film, the film on which a hard coat layer had been formed previously is unwound, the first layer comprising the transparent oxide film is formed on the hard coat layer by reactive sputtering using a metal or alloy target,

subsequently the second layer of reflection preventing optical thin film comprising the conductive light absorbing film is formed on the first layer by sputtering, then the third layer of the reflection preventing optical thin film is formed on the second layer by sputtering, finally the film comprising the reflection preventing optical thin film formed on the hard coat layer is wound.

In the present invention, the substrate may consist of any material as far as the material transmits light. A material to be used for the substrate may be selected dependently on required specification and application field of the anti-reflection member, and may be selected from plastic materials or glass materials. When plastic material is selected to form the substrate, examples include, for example, polyethylene-terephthalate (PET), polycarbonate (PC), polypropylene (PP), polymethyl-methacrylate and copolymer thereof, unsaturated polyester, acrylonitrile-styrene copolymer, vinylchloride, polyurethane, epoxy resin, and cellulose-based resin such as triacetyl-cellulose and diacetyl-cellulose, among these materials, polyethylene-terephthalate (PET) or polycarbonate (PC) is preferably used. The form of the substrate may be film, sheet, or

plate dependently on required specification and application. The thickness of the substrate is not limited, and may be selected dependently on required specification and application. A hard coat layer may be formed on the back side (the side on which the reflection preventing optical thin film is not formed) of the anti-reflection member dependently on application of the anti-reflection member.

Examples of application of the anti-reflection member in accordance with the first embodiment and the second embodiment of the present invention include, for example, application on the panel surface of cathode ray tubes, and the surface of picture display portion of liquid crystal displays, plasma displays, and EL displays, and for example, application as filter to be provided in front of a cathode ray tube and application on the surface of various optical lenses. For example, on the back side (the side on which the hard coat layer is not formed) of the anti-reflection member in accordance with the first embodiment and the second embodiment of the present invention, an adhesive layer or pressure sensitive adhesive layer is formed, and the anti-reflection member may be applied on the panel surface of a cathode ray tube with interposition of such

adhesive layer or pressure sensitive adhesive layer. When, by applying the anti-reflection member with pressing thereon in vacuum, trapping of air between the anti-reflection member and the panel surface of the cathode ray tube is prevented. Further, ultraviolet-curing resin adhesives are also used effectively.

On the uppermost layer of the reflection preventing optical thin film, a layer consisting of fluorine-based material such as polytetrafluoroethylene, tetrafluoroethylene-perfluoro-alkyl-vinyl-ether copolymer, polychloro-trifluoroethylene, tetrafluoroethylene-ethylene copolymer, chloro-trifluoroethylene-ethylene copolymer, polyvinylidene-fluoride, and polyvinyl-fluoride may be formed to prevent staining with fingerprints. In this case, the thickness of the layer may be 3 to 100 nm so as not to influence adversely on the reflection preventing effect.

Film thickness of the first layer and the second layer of the reflection preventing optical thin film of the anti-reflection member in accordance with the first embodiment of the present invention, or film thickness of the second layer and the third layer of the reflection preventing optical thin film of the anti-reflection member in accordance with the second

embodiment of the present invention may be determined according to the film thickness determining method based on two layered structure with V-shape structure and W-shaped structure comprising what is called $(\lambda/4-\lambda/2)$ film or the film thickness determining method based on three layered structure comprising what is called $(\lambda/4-\lambda/2-\lambda/4)$ film.

In conventional art, an ITO layer is formed by sputtering using a target of oxide ITO. On the other hand, in the anti-reflection member or the manufacturing method thereof in accordance with the first embodiment of the present invention, the transparent conductive oxide film which is the first layer of the reflection preventing optical thin film in contact with the hard coat layer is formed by reactive physical vapor phase deposition. When reactive sputtering using a metal or alloy target is used as reactive physical vapor phase deposition, the sputtering is carried out under a sputtering condition of insufficient oxygen unlike conventional sputtering technique in which a oxide target is used. In this case, when sputtered particles are deposited on a hard coat layer, completely oxidized particles are not deposited on a hard coat layer, but partially active metal or alloy sputtered particles are

deposited on a hard coat layer and react with oxygen atoms in molecules which forms the hard coat layer, thus the reaction results in chemical strong adhesion. As the result, the adhesion (adhesion strength) between the transparent conductive oxide film and hard coat layer is improved. In the anti-reflection member in accordance with the first embodiment of the present invention, the combination of the transparent conductive oxide film with the second layer leads to the effective prevention of light reflection, on the other hand, transparent conductive oxide film provides antistatic function and electromagnetic radiation shielding function to the anti-reflection member.

In the case that elements which form the conductive light absorbing film have no or little affinity with oxygen in molecules which form the hard coat layer, adhesion between the conductive light absorbing film and hard coat layer is considered to be insufficient. On the other hand, in the anti-reflection member or the manufacturing method thereof in accordance with the second embodiment of the present invention, the transparent oxide film which is the first layer of the reflection preventing optical thin film in contact with the hard coat layer is formed by reaction physical vapor

phase deposition. When reactive sputtering using a metal or alloy target is used as reactive physical vapor phase deposition, the sputtering is carried out under a sputtering condition of insufficient oxygen unlike conventional sputtering technique in which an oxide target is used. In this case, when sputtered particles are deposited on a hard coat layer, completely oxidized particles are not deposited on a hard coat layer, but partially active metal or alloy sputtered particles are deposited on a hard coat layer and react with oxygen atoms in molecules which forms the hard coat layer, thus the reaction results in chemical strong adhesion. As the result, the adhesion (adhesion strength) between the transparent oxide film and hard coat layer is improved. In the anti-reflection member in accordance with the second embodiment of the present invention, the combination of the conductive light absorbing film with the third layer leads to the effective prevention of light reflection, on the other hand, conductive light absorbing film provides antistatic function and electromagnetic radiation shielding function to the anti-reflection member. The transparent oxide film is provided with anti-reflection function by adjusting the film thickness of the transparent oxide film. The

transparent oxide film is provided with antistatic function and electromagnetic radiation shielding function by using a conductive transparent oxide film.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a schematic partial cross-sectional view of the anti-reflection member of Example 1.

Fig. 2 is a schematic partial cross-sectional view of the anti-reflection member of Example 2.

Fig. 3 is a schematic diagram of a spattering equipment suitable for continuous manufacturing of the anti-reflection member of the present invention.

Figs. 4A and 4B are a schematic partial cross-sectional view of a conventional anti-reflection member, and a schematic partial cross-sectional view of the anti-reflection member proposed by the applicant of the present invention in Japanese Patent Application Hei 7-170925 (1995).

DETAIL DESCRIPTION OF PREFERRED EXAMPLE

The present invention will be described in detail hereinafter based on examples referring to the drawings.

Example 1

Example 1 relates to the anti-reflection member and the manufacturing method thereof in accordance with the first embodiment of the present invention. In Table 3, target materials and film forming conditions for reactive sputtering (in detail, DC magnetron sputtering) are shown. A schematic partial cross-sectional view of the obtained anti-reflection member is shown in Fig. 1. In Fig. 1, the first layer of the reflection preventing optical thin film is a transparent conductive oxide film (thickness is 15 nm) formed by reactive DC magnetron sputtering. The second layer of the reflection preventing optical thin film is a SiO_2 film with a thickness of 20 nm formed by conventional sputtering using a target of oxide. The third layer of the reflection preventing optical thin film is a transparent conductive oxide film (thickness is 100 nm) formed by reactive DC magnetron sputtering under the same conditions for forming the first layer. The fourth layer of the reflection preventing optical thin film is a SiO_2 film with a thickness of 85 nm formed by conventional sputtering. The hard coat layer consists of PMMA. The substrate consists of PET. Film

forming sputtering conditions for forming the second layer and the fourth layer are shown herein under.

Target : SiO_2
Power density : 5 W/cm^2
Atmosphere gas : Ar
Atmospheric pressure: 0.2 Pa

A anti-reflection member having the same structure was prepared by conventional method. In detail, as to the conventional method shown in Table 3, the first layer of the reflection preventing optical thin film is a transparent conductive oxide film (thickness is 15 nm) formed by DC magnetron sputtering using a target of oxide. The second layer of the reflection preventing optical thin film is a SiO_2 film with a thickness of 20 nm formed by conventional sputtering using a target of oxide. The third layer of the reflection preventing optical thin layer is a transparent conductive oxide film (thickness is 100 nm) formed by DC magnetron sputtering using a target of oxide. The fourth layer of the reflection preventing optical thin film is a SiO_2 film with a thickness of 85 nm formed by conventional sputtering using a target of oxide. The substrate consists of PET. The same film forming conditions as used in Example 1 were used for

forming the second layer and fourth layer. Film forming conditions for forming the third layer by sputtering are shown herein under.

Target	: ITO
Power density	: 5 W/cm ²
Atmosphere gas	: Ar
Atmospheric pressure:	0.2 Pa

Table 3

Example	Target material	Transparent conductive oxide film	Target power density (W/cm ²)	Atmospheric gas concentration (volume %)		Atmos- pheric pressure (Pa)	Rating of adhesion strength
				Ar	O ₂		
1	In-Sn alloy	ITO	4	0	100	0.2	4
	In-Sn alloy	ITO	4	30	70	0.2	4
	In-Sn alloy	ITO	2	0	100	0.2	4
	In-Sn alloy	ITO	2	30	70	0.2	5
	Sn metal	SnO ₂	4	0	100	0.2	5
	Sn metal	SnO ₂	4	30	70	0.2	5
	Sn metal	SnO ₂	2	0	100	0.2	5
	Sn metal	SnO ₂	2	30	70	0.2	5
	Zn metal	ZnO	4	0	100	0.2	3
	Zn metal	ZnO	4	30	70	0.2	3
	Zn metal	ZnO	2	0	100	0.2	3
	Zn metal	ZnO	2	30	70	0.2	3
Conven- tional method	ITO oxide	ITO	4	0	100	0.2	0
	ITO oxide	ITO	4	50	50	0.2	0
	ITO oxide	ITO	2	0	100	0.2	0
	ITO oxide	ITO	2	50	50	0.2	0

Sliding test was carried out for evaluation of adhesion (adhesion strength). The sliding test includes following procedures. Four pieces of cotton cloth impregnated with ethyl alcohol are wound on a steel ball with a diameter of 20 mm, 3 kgf of load is loaded on the steel ball and the loaded steel ball is brought into a contact with the uppermost layer of a reflecting preventing optical thin film placed flat, and the steel ball is reciprocated horizontally between 10 cm distance. The number of reciprocation until the steel ball causes delamination of the reflection preventing optical thin film is measured for rating of adhesion (adhesion strength).

The rating result of adhesion (adhesion strength) is shown in Table 3. The adhesion strength rating of "0" represents the delaminating within 5 cycles of reciprocation. The adhesion strength rating of "1" represents the delamination in the reciprocation cycle range from 5 to 10. The adhesion strength rating of "2" represents the delamination in the reciprocation cycle range from 10 to 20. The adhesion strength rating of "3" represents the delamination in the reciprocation cycle range from 20 to 30. The adhesion strength rating of "4" represents the delamination in the reciprocation

cycle range from 30 to 40. The adhesion strength rating of "5" represents no delamination until 50 reciprocation cycles. All delamination of the reflection preventing optical thin films was caused between the first layer and hard coat layer.

From the Table 3, it is obvious that the adhesion (adhesion strength) between the first layer and hard coat layer is greatly improved for the anti-reflection member manufactured by the manufacturing method of the anti-reflection member in accordance with the first embodiment of the present invention in comparison with the anti-reflection member manufactured by the conventional method. The case in which DC magnetron sputtering using Si target in oxygen gas atmosphere is applied instead of RF sputtering for forming of second layer and fourth layer gives the same result.

Example 2

Example 2 relates to the anti-reflection member and the manufacturing method thereof in accordance with the second embodiment of the present invention. In Table 4, target materials and film forming conditions for reactive sputtering (in detail,

DC magnetron sputtering) are shown. A schematic partial cross-sectional view of the obtained anti-reflection member is shown in Fig. 2. In Fig. 2, the first layer of the reflection preventing optical thin film is a transparent oxide film (thickness is 4 nm) formed by reactive DC magnetron sputtering. The second layer of the reflection preventing optical thin film is a TiNX (X=about 0.9) film with a thickness of 10 nm formed by reaction DC magnetron sputtering in a nitrogen gas atmosphere using a target of Ti. The third layer of the reflection preventing optical thin film is a SiO₂ with a thickness of 100 nm formed by conventional sputtering using a target of oxide. The film forming conditions for forming the third layer is the same as those used in Example 1. The hard coat layer consists of PMMA. The substrate consists of PET. Film forming sputtering conditions for forming the second layer are shown herein under.

Target	: Ti
Power density	: 4 W/cm ²
Atmosphere gas	: Ar + N ₂ (N ₂ : 50 % by volume)
Atmospheric pressure:	0.2 Pa

A anti-reflection member having the same structure was prepared by conventional method. In

detail, as to the conventional method shown in Table 4, the first layer of the reflection preventing optical thin film is a transparent oxide film (thickness is 4 nm) formed by RF sputtering using a target of oxide. the second layer and the third layer of the reflection preventing optical thin film, and hard coat layer and substrate have the same structures as those films in Example 2. The structure of the anti-reflection member when the transparent oxide film (the first layer) is not provided is the same. Film forming conditions for forming the first layer by sputtering are shown herein under. Film forming conditions for forming the second layer and the third layer by sputtering are the same as those in Example 2.

Target	: SiO_2 , ZrO_2 ,
Power density	: 4 W/cm^2
Atmosphere gas	: $\text{Ar} + \text{O}_2$ (O_2 : 50 % by volume)
Atmospheric pressure	: 0.2 Pa

Table 4

Example	Target material	Transparent conductive oxide film	Target power density (W/cm ²)	Atmospheric gas concentration (volume %)		Atmospheric pressure (Pa)	Rating of adhesion strength
				Ar	O ₂		
2	Zr	ZrO ₂	4	20	80	0.2	5
	Ti	TiO ₂	4	20	80	0.2	4
	Si	SiO ₂	4	20	80	0.2	4
	Si	SiO _{1.5} N _{0.3}	4	20	60	0.2	4
	Sn	SnO ₂	4	20	80	0.2	5
	Cr	Cr ₂ O ₃	4	20	80	0.2	5
Conventional method	SiO ₂	SiO ₂	4	50	50	0.2	0
	ZrO ₂	ZrO ₂	4	50	50	0.2	0
	TiO ₂	TiO ₂	4	50	50	0.2	0
	SnO ₂	SnO ₂	4	50	50	0.2	0
	Cr ₂ O ₃	Cr ₂ O ₃	4	50	50	0.2	0
	ZnO	ZnO	4	50	50	0.2	0
							1

Note: Atmosphere for film forming of SiO_{1.5}N_{0.3}

Ar/O₂/N₂ = 20/60/20 (volume %)

For evaluation of adhesion (adhesion strength), sliding test was carried out in the same manner as described in Example 1. From the result shown in Table 4, it is obvious that the adhesion (adhesion strength) between the first layer and hard coat layer is greatly improved for the anti-reflection member manufactured by the manufacturing method of the anti-reflection member in accordance with the second embodiment of the present invention in comparison with the anti-reflection member manufactured by the conventional method.

For manufacturing of the anti-reflection member in accordance with the first or second embodiment of the present invention, reflection prevention optical thin films can be formed continuously using a sputtering equipment shown schematically in Fig. 3. The sputtering equipment comprises a roll film feeding chamber 20 for unwinding a roll film 10 on which a hard coat layer is formed previously, a sputtering chamber 30 which can be brought to a reduced pressure atmosphere, and a roll film winding chamber 22 for winding the film 10. A plurality of cathodes 32 is provided in the sputtering chamber 30. A target (not shown in the figure) is placed on each cathode 32, oxygen gas atmosphere is

formed on each cathode surface, thus various thin films are formed successively on a hard coat layer by reactive sputtering or conventional sputtering.

For manufacturing the anti-reflection member in accordance with the first embodiment of the present invention using a sputtering equipment having such structure, film 10 on which a hard coat layer had been formed previously is fed from the roll film feeding chamber 20, the film 10 is wound around the roller 34 in the sputtering chamber 30, while, the first layer comprising transparent conductive oxide film is formed on the hard coat layer by reactive sputtering using a target of metal or alloy, subsequently the second layer of the reflection preventing optical thin film is formed on the first layer by sputtering, then the film 10 comprising the reflection preventing optical thin film formed on the hard coat layer is wound in the roll film winding chamber 22.

For manufacturing the anti-reflection member in accordance with the second embodiment of the present invention, film 10 on which a hard coat layer had been formed previously is fed from the roll film feeding chamber 20, the film 10 is wound around the roller 34 in the sputtering chamber 30, while, the first layer

comprising transparent oxide film is formed on the hard coat layer by reactive sputtering using a target of metal or alloy, subsequently the second layer of the reflection preventing optical thin film comprising a conductive light absorbing film is formed on the first layer by sputtering, subsequently the third layer of the reflection preventing optical thin film is formed on the second layer by sputtering, and then the film 10 comprising the reflection preventing optical thin film formed on the hard coat layer is wound in the roll film winding chamber 22.

For example, Japanese Patent Laid-Open Hei 2-4967 (1990) discloses a method for forming an oxide film using a metal target. In the case of the sputtering equipment disclosed in the Japanese Patent Laid-Open, a station for forming metal layer and a station for forming oxide film by oxidizing the formed metal layer are provided separately. A substrate is passed by these stations repeatedly to form desired metal oxide layers. According to the technique disclosed in this Japanese Patent Laid-Open, the sputtering equipment is very complex, the productivity of metal oxide film is low.

On the other hand, the structure of the sputtering equipment shown in Fig. 3 is simple, and the

high productivity production of the multilayered reflection preventing optical thin film is possible, thus the production cost of the anti-reflection member can be suppressed to a low level.

On the back side (the side on which a hard coat layer is not formed) of the substrate of the anti-reflection member in accordance with the first and second embodiment of the present invention, an adhesive layer or pressure sensitive adhesive layer, for example, consisting of ultraviolet ray curing acryl-based adhesive is formed, the anti-reflection member is applied on the panel surface of a cathode ray tube with interposition of such adhesive layer or pressure sensitive adhesive layer, then the cathode ray tube applied with the anti-reflection member on its panel surface is obtained. When, by applying the anti-reflection member with pressing thereon in vacuum, trapping of air between the anti-reflection member and the panel surface of the cathode ray tube is prevented. Further, ultraviolet-curing resin adhesives are also used effectively.

The present invention has been described based on preferred examples hereinbefore, however, the present invention is by no means limited to these examples. The

materials, thickness, and structure of the reflection preventing optical thin films, sputtering conditions, and further, materials of the substrate and hard coat layer, and the structure of the sputtering equipment for continuous film forming of the reflection preventing optical thin film are described only for example, and may be changed desirably.

According to the anti-reflection member and the manufacturing method thereof in accordance with the first embodiment of the present invention, the adhesion between the reflection preventing optical thin film and hard coat layer is greatly improved, and the anti-reflection member having high reliability for cleaning and use is provided. The transparent conductive oxide film functions as a high refractive index layer, therefore it is not necessary to form a high refractive index layer and conductive layer separately, thus the structure of the reflection preventing optical thin film is simplified, and anti-reflection members are manufactured at a low cost level. Moreover, it is not necessary to use TiO_2 , ZrO_2 , and Ta_2O_5 , which have slow deposition speed in sputtering, and Y_2O_3 , which is expensive, and instead, for example, ITO , SnO_2 , ZnO , and I_2O_3 can be used economically, thus the film forming

cost is suppressed, and the manufacturing cost of anti-reflection members is reduced.

Also according to the anti-reflection member and the manufacturing method thereof in accordance with the second embodiment of the present invention, the adhesion between the reflection preventing optical thin film and hard coat layer is greatly improved, and the anti-reflection member having high reliability for cleaning and use is provided. Further, the structure of the reflection preventing optical thin film is simple, and thin films which constitute the reflection preventing optical thin film may be thin, therefore it is possible to manufacture anti-reflection members at a reduced cost. Moreover, for example, by using reactive DC magnetron sputtering, the film forming cost is reduced, thus the manufacturing cost of anti-reflection members is reduced.



WHAT IS CLAIMED IS:

1. An anti-reflection optical element comprising;
a substrate,
a hard coat layer,
an anti-reflection film having two layers,
the first layer of the anti-reflection film being formed on the substrate by PVD method, wherein the first layer is transparent oxide layer, and the second layer of the anti-reflection film having a refractive index which is lower than that of the first layer.
2. The anti-reflection optical element as claimed in claim 1, wherein said PVD method is a reactive sputtering method using a target of metal or alloy.
3. The anti-reflection optical element as claimed in claim 2, wherein
said target is Sn, Zn, In, and alloy consisting of In and Sn.
4. The anti-reflection optical element as claimed in claim 1, wherein an element having higher oxygen affinity than that of the element mainly contained in said transparent oxide layer.

This Sheet Has Been Replaced





5. The anti-reflection optical element as claimed in claim 1, wherein said second layer contains SiO_2 or MgF_2 .

6. The anti-reflection optical element as claimed in claim 1, wherein said hard coat layer consists of polymethyl-methacrylate.

7. The anti-reflection optical element as claimed in claim 1, wherein a conductive light absorbing layer is provided between said first layer and said second layer, and said second layer has a lower refractive index than that of said conductive light absorbing layer.

8. The anti-reflection optical element as claimed in claim 1, wherein the thickness of said transparent oxide layer ranges from 1 to 20 nm.

9. The anti-reflection optical element as claimed in claim 1, wherein said transparent oxide layer consists of at least one material selected from a group composed of ZrO_2 , TiO_x ($x = 1$ to 2), SiO_xN_y ($x = 1$ to 2 , $y = 0.2$ to 0.6), and CrO_x ($x = 0.2$ to 1.5).

10. The anti-reflection optical element as claimed in claim 7, wherein said conductive light absorbing layer contains any one of metal, alloy, metal nitride, and metal-oxide-nitride.

This Sheet Has Been Replaced





11. The anti-reflection optical element as claimed in claim 10, wherein said conductive light absorbing layer contains a material selected from a group composed of Ag, Au, TiN_x ($x = 0.3$ to 1), Pt, TiO_xN_y ($x = 0.3$ to 1 , $y < 1$, $y \leq x$), TaN_x ($x = 0.2$ to 1), Pt, Al, Cu, Ta, Ni-Cr, Cu-Al, Cu-Zn-Al, Cu-Ni-Al, and Cu-Sn-Al.

12. A method for manufacturing the anti-reflection optical element having a hard coat layer and multilayered anti-reflecting film comprising the steps of;

forming the hard coat layer on a substrate,

forming a first layer of the anti-reflecting film by PVD method, the first layer being composed of a transparent oxide layer, and

forming a second layer of the anti-reflecting film having a refractive index which is lower than that of the first layer on the first layer.

13. A method for manufacturing the anti-reflection optical element as claimed in claim 12, wherein said PVD method is a reactive sputtering method using a target of metal or alloy.

14. A method for manufacturing the anti-reflection optical element as claimed in claim 13,

This Sheet Has Been Replaced





wherein said target is Sn, Zn, In, and alloy consisting of In and Sn.

15. A method for manufacturing the anti-reflection optical element as claimed in claim 13, wherein an element having higher oxygen affinity than that of the element mainly contained in said transparent oxide layer.

16. A method for manufacturing the anti-reflection optical element as claimed in claim 12, wherein said second layer contains SiO_2 or MgF_2 .

17. A method for manufacturing the anti-reflection optical element as claimed in claim 13, wherein said hard coat layer consists of polymethylmethacrylate.

18. A method for manufacturing the anti-reflection optical element as claimed in claim 12, wherein a conductive light absorbing layer is provided between said first layer and said second layer, and said second layer has a lower refractive index than that of said conductive light absorbing layer.

19. A method for manufacturing the anti-reflection optical element as claimed in claim 12, wherein the thickness of said transparent oxide layer ranges from 1 to 20 nm.

This Sheet Has Been Replaced





20. A method for manufacturing the anti-reflection optical element as claimed in claim 12, wherein said transparent oxide layer consists of at least one material selected from a group composed of ZrO_2 , TiO_x ($x = 1$ to 2), SiO_xN_y ($x = 1$ to 2 , $y = 0.2$ to 0.6), and CrO_x ($x = 0.2$ to 1.5).

21. A method for manufacturing the anti-reflection optical element as claimed in claim 18, wherein said conductive light absorbing layer contains any one of metal, alloy, metal nitride, and metal-oxide-nitride.

22. A method for manufacturing the anti-reflection optical element as claimed in claim 21, wherein said conductive light absorbing layer contains a material selected from a group composed of Ag, Au, $TiNx$ ($x = 0.3$ to 1), Pt, TiO_xN_y ($x = 0.3$ to 1 , $y < 1$, $y \leq x$), TaN_x ($x = 0.2$ to 1), Pt, Al, Cu, Ta, Ni-Cr, Cu-Al, Cu-Zn-Al, Cu-Ni-Al, and Cu-Sn-Al.

23. A cathode ray tube comprising;
a glass bulb having a neck portion, a funnel portion, and a panel portion;

outer surface of the panel is provided with an anti-reflection optical element having the structure described in claim 1.

This Sheet Has Been Replaced





24. A cathode ray tube as claimed in claim 23, wherein a conductive light absorbing layer is provided between said first layer and said second layer, and said second layer has a lower refractive index than that of said conductive light absorbing layer.

This Sheet Has Been Replaced

