

DESCRIPTION

Title of Invention: METHOD FOR STORING FLUOROBUTENE

5 Technical Field

[0001]

The present invention relates to a method for storing a fluorobutene.

10 Background Art

[0002]

Unsaturated fluorocarbons disclosed, for example, in PTLs 1 and 2 may be used as an etching gas for dry etching.

15

Citation List

Patent Literature

[0003]

PTL 1: JP 6451810 B

20

PTL 2: JP 2019-034972 A

Summary of Invention

Technical Problem

[0004]

25

Unsaturated fluorocarbons may, however, decompose during storage for a long time, and the purity may decrease.

The present invention is intended to provide a

method for storing a fluorobutene by which decomposition is unlikely to proceed during storage.

Solution to Problem

5 [0005]

To solve the problems, aspects of the present invention are the following [1] to [4].

[1] A method for storing a fluorobutene represented by general formula $C_4H_xF_y$ where x is 0 or more and 7 or less, y is 1 or more and 8 or less, and x + y is 8, in
10 which

the fluorobutene contains or does not contain at least one of manganese, cobalt, nickel, and silicon as a metal impurity, and the fluorobutene is stored in a
15 container in which the total concentration of manganese, cobalt, nickel, and silicon is 1,000 ppb by mass or less when the fluorobutene contains at least one of manganese, cobalt, nickel, and silicon.

[0006]

20 [2] The method for storing a fluorobutene according to the aspect [1], in which the fluorobutene further contains or does not contain at least one of sodium, potassium, magnesium, and calcium as the metal impurity, and the fluorobutene is stored in a container in which
25 the sum total concentration of manganese, cobalt, nickel, silicon, sodium, potassium, magnesium, and calcium is 2,000 ppb by mass or less when the fluorobutene further contains at least one of sodium, potassium, magnesium,

and calcium.

[0007]

[3] The method for storing a fluorobutene according to the aspect [1] or [2], in which the fluorobutene is at least one selected from 1,1,1,4,4,4-hexafluoro-2-butene, 1,1,1,2,4,4,4-heptafluoro-2-butene, 3,3,4,4,4-pentafluoro-1-butene, and 2,3,3,4,4,4-hexafluoro-1-butene.

[4] The method for storing a fluorobutene according to any one of the aspects [1] to [3], in which the fluorobutene is stored at a temperature of -20°C or more and 50°C or less.

Advantageous Effects of Invention

[0008]

According to the present invention, a fluorobutene is unlikely to decompose during storage.

Description of Embodiments

[0009]

Embodiments of the present invention will now be described. The embodiments are merely examples of the present invention, and the present invention is not limited to the embodiments. Various modifications or improvements can be made in the embodiments, and such modifications and improvements can be encompassed by the present invention.

[0010]

The method for storing a fluorobutene pertaining to the present embodiment is a method for storing a fluorobutene represented by general formula $C_4H_xF_y$ where x is 0 or more and 7 or less, y is 1 or more and 8 or less, and $x + y$ is 8. In the method, the fluorobutene contains or does not contain at least one of manganese (Mn), cobalt (Co), nickel (Ni), and silicon (Si) as a metal impurity, and the fluorobutene is stored in a container in which the total concentration of manganese, cobalt, nickel, and silicon is 1,000 ppb by mass or less when the fluorobutene contains at least one of manganese, cobalt, nickel, and silicon.

[0011]

When a fluorobutene contains at least one of manganese, cobalt, nickel, and silicon as a metal impurity, the catalytic action of the metal impurity accelerates decomposition reaction of the fluorobutene. Hence, a fluorobutene containing a metal impurity may decompose during storage, and the purity may decrease.

[0012]

A fluorobutene stored by the method for storing a fluorobutene pertaining to the present embodiment contains no metal impurity or contains a metal impurity at a small content and thus is unlikely to decompose even when stored for a long time, and the purity is unlikely to decrease. Accordingly, the fluorobutene can be stably stored over a long time.

[0013]

The technology disclosed in PTLs 1 and 2 does not consider the concentration of a metal impurity in an unsaturated fluorocarbon. Hence, when an unsaturated fluorocarbon is stored by the technology disclosed in PTLs 1 and 2, a metal impurity may accelerate decomposition reaction of the unsaturated fluorocarbon. As a result, the unsaturated fluorocarbon may decompose during storage, and the purity may decrease.

[0014]

Hereinafter, the method for storing a fluorobutene pertaining to the present embodiment will be described in further detail.

[Fluorobutene]

The fluorobutene pertaining to the present embodiment is represented by general formula $C_4H_xF_y$ and satisfies three requirements in the general formula: x is 0 or more and 7 or less; y is 1 or more and 8 or less; and $x + y$ is 8. The fluorobutene may be any type that satisfies the above requirements and may be either a linear fluorobutene or a branched fluorobutene (isobutene) but is preferably a fluoro-1-butene or a fluoro-2-butene.

[0015]

Specific examples of the fluoro-1-butene include $CHF_2-CF_2-CF=CF_2$, $CF_3-CF_2-CF=CHF$, $CF_3-CHF-CF=CF_2$, $CF_3-CF_2-CH=CF_2$, $CHF_2-CHF-CF=CF_2$, $CHF_2-CF_2-CF=CHF$, $CF_3-CHF-CF=CHF$, $CF_3-CF_2-CH=CHF$, $CF_3-CHF-CH=CF_2$, $CHF_2-CF_2-CH=CF_2$, $CH_3-CF_2-CF=CF_2$, $CH_2F-CHF-CF=CF_2$, $CH_2F-CF_2-CH=CF_2$, $CH_2F-CF_2-CF=CHF$,

$\text{CHF}_2\text{-CH}_2\text{-CF=CF}_2$, $\text{CHF}_2\text{-CHF-CH=CF}_2$, $\text{CHF}_2\text{-CHF-CF=CHF}$, $\text{CHF}_2\text{-CF}_2\text{-CH=CHF}$, $\text{CHF}_2\text{-CF}_2\text{-CF=CH}_2$, $\text{CF}_3\text{-CH}_2\text{-CH=CF}_2$, $\text{CF}_3\text{-CH}_2\text{-CF=CHF}$, $\text{CF}_3\text{-CHF-CH=CHF}$, $\text{CF}_3\text{-CHF-CF=CH}_2$, $\text{CF}_3\text{-CF}_2\text{-CH=CH}_2$, $\text{CH}_3\text{-CHF-CF=CF}_2$, $\text{CH}_3\text{-CF}_2\text{-CH=CF}_2$, $\text{CH}_3\text{-CF}_2\text{-CF=CHF}$, $\text{CH}_2\text{F-CH}_2\text{-CF=CF}_2$,
5 $\text{CH}_2\text{F-CHF-CH=CF}_2$, $\text{CH}_2\text{F-CHF-CF=CHF}$, $\text{CH}_2\text{F-CF}_2\text{-CH=CHF}$, $\text{CH}_2\text{F-CF}_2\text{-CF=CH}_2$, $\text{CHF}_2\text{-CH}_2\text{-CH=CF}_2$, $\text{CHF}_2\text{-CH}_2\text{-CF=CHF}$, $\text{CHF}_2\text{-CHF-CH=CHF}$, $\text{CHF}_2\text{-CHF-CF=CH}_2$, $\text{CHF}_2\text{-CF}_2\text{-CH=CH}_2$, $\text{CF}_3\text{-CH}_2\text{-CH=CHF}$, $\text{CF}_3\text{-CH}_2\text{-CF=CH}_2$, $\text{CF}_3\text{-CHF-CH=CH}_2$, $\text{CH}_3\text{-CH}_2\text{-CF=CF}_2$, $\text{CH}_3\text{-CHF-CH=CF}_2$, $\text{CH}_3\text{-CHF-CF=CHF}$, $\text{CH}_3\text{-CF}_2\text{-CH=CHF}$, $\text{CH}_3\text{-CF}_2\text{-CF=CH}_2$,
10 $\text{CH}_2\text{F-CH}_2\text{-CH=CF}_2$, $\text{CH}_2\text{F-CH}_2\text{-CF=CHF}$, $\text{CH}_2\text{F-CHF-CH=CHF}$, $\text{CH}_2\text{F-CHF-CF=CH}_2$, $\text{CH}_2\text{F-CF}_2\text{-CH=CH}_2$, $\text{CHF}_2\text{-CH}_2\text{-CH=CHF}$, $\text{CHF}_2\text{-CH}_2\text{-CF=CH}_2$, $\text{CHF}_2\text{-CHF-CH=CH}_2$, $\text{CF}_3\text{-CH}_2\text{-CH=CH}_2$, $\text{CH}_3\text{-CH}_2\text{-CH=CF}_2$, $\text{CH}_3\text{-CH}_2\text{-CF=CHF}$, $\text{CH}_3\text{-CHF-CH=CHF}$, $\text{CH}_3\text{-CHF-CF=CH}_2$, $\text{CH}_3\text{-CF}_2\text{-CH=CH}_2$, $\text{CH}_2\text{F-CH}_2\text{-CH=CHF}$, $\text{CH}_2\text{F-CH}_2\text{-CF=CH}_2$, $\text{CH}_2\text{F-CHF-CH=CH}_2$,
15 $\text{CHF}_2\text{-CH}_2\text{-CH=CH}_2$, $\text{CH}_3\text{-CH}_2\text{-CH=CHF}$, $\text{CH}_3\text{-CH}_2\text{-CF=CH}_2$, $\text{CH}_3\text{-CHF-CH=CH}_2$, and $\text{CH}_2\text{F-CH}_2\text{-CH=CH}_2$.

[0016]

Specific examples of the fluoro-2-butene include
 $\text{CHF}_2\text{-CF=CF-CF}_3$, $\text{CF}_3\text{-CH=CF-CF}_3$, $\text{CH}_2\text{F-CF=CF-CF}_3$, $\text{CHF}_2\text{-CH=CF-CF}_3$, $\text{CHF}_2\text{-CF=CF-CHF}_2$, $\text{CF}_3\text{-CH=CH-CF}_3$, $\text{CH}_3\text{-CF=CF-CF}_3$, $\text{CH}_2\text{F-CH=CF-CF}_3$, $\text{CH}_2\text{F-CF=CH-CF}_3$, $\text{CH}_2\text{F-CF=CF-CHF}_2$, $\text{CHF}_2\text{-CH=CH-CF}_3$, $\text{CHF}_2\text{-CF=CH-CHF}_2$, $\text{CH}_3\text{-CH=CF-CF}_3$, $\text{CH}_3\text{-CF=CH-CF}_3$, $\text{CH}_3\text{-CF=CF-CHF}_2$, $\text{CH}_2\text{F-CH=CH-CF}_3$, $\text{CH}_2\text{F-CH=CF-CHF}_2$, $\text{CH}_2\text{F-CF=CH-CHF}_2$, $\text{CH}_2\text{F-CF=CF-CH}_2\text{F}$, $\text{CHF}_2\text{-CH=CH-CHF}_2$, $\text{CH}_3\text{-CH=CH-CF}_3$, $\text{CH}_3\text{-CH=CF-CHF}_2$, $\text{CH}_3\text{-CF=CH-CHF}_2$, $\text{CH}_3\text{-CF=CF-CH}_2\text{F}$, $\text{CH}_2\text{F-CF=CH-CH}_2\text{F}$, $\text{CH}_2\text{F-CH=CH-CHF}_2$, $\text{CH}_3\text{-CH=CH-CHF}_2$, $\text{CH}_3\text{-CH=CF-CH}_2\text{F}$, $\text{CH}_3\text{-CF=CH-CH}_2\text{F}$, $\text{CH}_3\text{-CF=CF-CH}_3$, $\text{CH}_2\text{F-CH=CH-CH}_2\text{F}$, $\text{CH}_3\text{-CH=CH-CH}_2\text{F}$, and $\text{CH}_3\text{-CH=CF-CH}_3$.

[0017]

These fluorobutenes may be used singly or in combination of two or more of them. Some of the fluorobutenes have cis-trans isomers, and both cis- and
5 trans-fluorobutenes can be used in the method for storing a fluorobutene pertaining to the present embodiment.

[0018]

When a fluorobutene is stored in a container, a gas consisting only of the fluorobutene may be stored in a
10 container, or a mixed gas containing the fluorobutene and a dilution gas may be stored in a container. As the dilution gas, at least one gas selected from nitrogen gas (N₂), helium (He), neon (Ne), argon (Ar), krypton (Kr), and xenon (Xe) can be used. The content of the dilution
15 gas is preferably 90% by volume or less and more preferably 50% by volume or less relative to the total volume of the gases stored in a container.

[0019]

[Container]

20 The container in which a fluorobutene is stored may be any container that can store a fluorobutene and be sealed, and the shape, the size, the material, and the like are not specifically limited. The material of the container may be, for example, a metal, ceramics, or a
25 resin. Examples of the metal include manganese steel, stainless steel, Hastelloy (registered trademark), and Inconel (registered trademark).

[0020]

[Metal impurity]

The fluorobutene pertaining to the present embodiment contains or does not contain at least one of manganese, cobalt, nickel, and silicon as a metal
5 impurity. The fluorobutene is stored in a container in which the total concentration of manganese, cobalt, nickel, and silicon is 1,000 ppb by mass or less when containing at least one of manganese, cobalt, nickel, and silicon. As described above, this condition suppresses
10 the decomposition reaction of the fluorobutene, and consequently, the fluorobutene is unlikely to decompose during storage. In the description, the not containing something means that it cannot be quantified by using an inductively coupled plasma mass spectrometer (ICP-MS).

15 [0021]

To suppress decomposition of a fluorobutene during storage, the total concentration of manganese, cobalt, nickel, and silicon in the fluorobutene is required to be 1,000 ppb by mass or less, but is preferably 500 ppb by
20 mass or less and more preferably 100 ppb by mass or less.

[0022]

To better suppress decomposition of a fluorobutene during storage, each concentration of manganese, cobalt, nickel, and silicon in the fluorobutene is preferably 300
25 ppb by mass or less and more preferably 100 ppb by mass or less.

[0023]

The total concentration of manganese, cobalt,

nickel, and silicon may be 1 ppb by mass or more.

The concentration of a metal impurity such as manganese, cobalt, nickel, and silicon in a fluorobutene may be quantified by using an inductively coupled plasma
5 mass spectrometer (ICP-MS).

[0024]

To better suppress decomposition of a fluorobutene during storage, the concentrations of sodium (Na), potassium (K), magnesium (Mg), and calcium (Ca) are also
10 preferably low, as well as the concentrations of manganese, cobalt, nickel, and silicon, in the fluorobutene.

[0025]

In other words, a fluorobutene contains or does not
15 contain at least one of manganese, cobalt, nickel, and silicon as a metal impurity, and the total concentration of manganese, cobalt, nickel, and silicon is 1,000 ppb by mass or less when the fluorobutene contains at least one of manganese, cobalt, nickel, and silicon. In addition
20 to this requirement, the fluorobutene further contains or does not contain at least one of sodium, potassium, magnesium, and calcium as the metal impurity, and the fluorobutene is preferably stored with a sum total concentration of manganese, cobalt, nickel, silicon,
25 sodium, potassium, magnesium, and calcium of 2,000 ppb by mass or less when further containing at least one of sodium, potassium, magnesium, and calcium. The fluorobutene is more preferably stored with a sum total

concentration of 1,000 ppb by mass or less, and the fluorobutene is even more preferably stored with a sum total concentration of 500 ppb by mass or less.

The sum total concentration of manganese, cobalt,
5 nickel, silicon, sodium, potassium, magnesium, and calcium may be 2 ppb by mass or more.

[0026]

To further suppress decomposition of a fluorobutene during storage, the concentrations of copper (Cu), zinc
10 (Zn), and aluminum (Al) are also preferably low, as well as the concentrations of manganese, cobalt, nickel, and silicon and the concentrations of sodium, potassium, magnesium, and calcium, in the fluorobutene.

[0027]

15 In other words, when a fluorobutene contains at least one of manganese, cobalt, nickel, and silicon and at least one of sodium, potassium, magnesium, and calcium as metal impurities and further contains at least one of copper, zinc, and aluminum as a metal impurity, the
20 fluorobutene is preferably stored with a total concentration of all these metal impurities contained of 3,000 ppb by mass or less, the fluorobutene is more preferably stored with a total concentration of 1,500 ppb by mass or less, and the fluorobutene is even more
25 preferably stored with a total concentration of 1,000 ppb by mass or less.

[0028]

The above metal impurities may be contained as an

elemental metal, a metallic compound, a metal halide, or a metal complex in a fluorobutene. Examples of the form of the metal impurity in a fluorobutene include microparticles, droplets, and gas. Manganese, cobalt,
5 nickel, and silicon are mixed in a fluorobutene supposedly from a material, a reaction catalyst, a reaction vessel, a refiner, or the like used to synthesize the fluorobutene.

[0029]

10 [Method for producing fluorobutene containing metal impurity at low concentration]

A fluorobutene containing metal impurities at low concentrations may be produced by any method, and examples of the method include a method of removing metal
15 impurities from a fluorobutene containing metal impurities at high concentrations. Metal impurities may be removed from a fluorobutene by any method, and a known method may be used. Examples of the method include a method using a filter, a method using an adsorbent, and
20 distillation.

[0030]

The material of the filter through which a fluorobutene gas selectively passes is preferably a resin and specifically preferably polytetrafluoroethylene to
25 prevent a metal component from mixing with a fluorobutene. The average pore size of the filter is preferably 0.01 μm or more and 30 μm or less and more preferably 0.1 μm or more and 10 μm or less. A filter

having an average pore size within the above range can be used to thoroughly remove metal impurities and can allow a fluorobutene gas to pass through at a sufficient flow rate, achieving high productivity.

5 [0031]

The flow rate of a fluorobutene gas passing through the filter is preferably 100 mL/min or more and 5,000 mL/min or less and more preferably 300 mL/min or more and 1,000 mL/min or less. When the flow rate of a
10 fluorobutene gas is within the above range, the fluorobutene gas is prevented from reaching a high pressure, and this can reduce the risk of fluorobutene gas leakage. In addition, high productivity can be achieved.

15 [0032]

[Pressure conditions during storage]

Pressure conditions during storage in the method for storing a fluorobutene pertaining to the present embodiment are not specifically limited as long as a
20 fluorobutene can be sealed and stored in a container, but the pressure is preferably 0.05 MPa or more and 5 MPa or less and more preferably 0.1 MPa or more and 3 MPa or less. When the pressure conditions are within the above range, a fluorobutene can be allowed to pass without
25 warming through a container that is connected to a dry etching system.

[0033]

[Temperature conditions during storage]

Temperature conditions during storage in the method for storing a fluorobutene pertaining to the present embodiment are not specifically limited, but the temperature is preferably -20°C or more and 50°C or less and more preferably 0°C or more and 40°C or less. At a temperature of -20°C or more during storage, a container is unlikely to deform and thus is unlikely to lose the airtightness. This reduces the possibility of oxygen, water, or the like entering the container. If oxygen, water, or the like entered a container, polymerization reaction or decomposition reaction of a fluorobutene could be accelerated. At a temperature of 50°C or less during storage, polymerization reaction or decomposition reaction of a fluorobutene is suppressed.

[0034]

[Etching]

The fluorobutene pertaining to the present embodiment can be used as an etching gas. An etching gas containing the fluorobutene pertaining to the present embodiment can be used in both plasma etching with plasma and plasmaless etching without plasma.

[0035]

Examples of the plasma etching include reactive ion etching (RIE), inductively coupled plasma (ICP) etching, capacitively coupled plasma (CCP) etching, electron cyclotron resonance (ECR) plasma etching, and microwave plasma etching.

In plasma etching, plasma may be generated in a

chamber in which a member to be etched is placed, or a plasma generation chamber may be installed separately from a chamber in which a member to be etched is placed (i.e., remote plasma may be used).

5

[Examples]

[0036]

The present invention will next be described more specifically with reference to examples and comparative
10 examples. Fluorobutenes containing metal impurities at various concentrations were prepared. Fluorobutene preparation examples will be described below.

(Preparation Example 1)

A manganese steel tank having a volume of 10 L and
15 four manganese steel cylinders each having a volume of 1 L were prepared. These cylinders are called cylinder A, cylinder B, cylinder C, and cylinder D. The tank was filled with 5,000 g of 1,1,1,4,4,4-hexafluoro-2-butene (boiling point: 9°C) and was cooled at 0°C for
20 liquefaction, and a liquid phase portion and a gas phase portion were formed at about 100 kPa. The cylinders A, B, C, and D were depressurized to 1 kPa or less by using a vacuum pump and then were cooled to -78°C.

[0037]

25 From the upper outlet where the gas phase portion was present in the tank, 500 g of 1,1,1,4,4,4-hexafluoro-2-butene gas was extracted, allowed to pass through a filter, and collected in the cylinder A at a reduced

pressure. The filter was a PTFE filter manufactured by Flon Industry and having an outer diameter of 50 mm, a thickness of 80 μm , and an average pore size of 0.3 μm . The flow rate of the gas passing through the filter was adjusted to 500 mL/min by using a mass flow controller. The amount of 1,1,1,4,4,4-hexafluoro-2-butene gas collected in the cylinder A was 492 g.

[0038]

The 1,1,1,4,4,4-hexafluoro-2-butene collected in the cylinder A is regarded as sample 1-1. The 1,1,1,4,4,4-hexafluoro-2-butene gas collected in the cylinder A was extracted from the upper outlet, and the concentrations of various metal impurities were determined by using an inductively coupled plasma mass spectrometer. The results are shown in Table 1.

[0039]

[Table 1]

	Na	K	Mg	Ca	Total	Mn	Co	Ni	Si	Total
Sample 1-1	-	-	-	-	-	2	4	3	5	14
Sample 1-2	-	-	-	-	-	21	17	18	24	80
Sample 1-3	214	208	171	178	771	184	163	199	232	778
Sample 1-4	-	-	-	-	-	385	349	401	487	1622

*) The unit of numerical values is ppb by mass. “-” means no measurement data.

[0040]

Next, the temperature of the cylinder A was raised to about 0°C, and a liquid phase portion and a gas phase portion were formed. From the upper outlet where the gas phase portion was present in the cylinder A, 100 g of 1,1,1,4,4,4-hexafluoro-2-butene gas was extracted and transferred to the cylinder B at a reduced pressure.

From the tank, 10 g of 1,1,1,4,4,4-hexafluoro-2-butene gas was extracted and transferred to the cylinder B at a reduced pressure. The temperature of the cylinder B was then raised to room temperature and was allowed to stand
5 for 24 hours. The 1,1,1,4,4,4-hexafluoro-2-butene after standing is regarded as sample 1-2. From the upper outlet where the gas phase portion was present in the cylinder B after standing, the 1,1,1,4,4,4-hexafluoro-2-butene gas was extracted, and the concentrations of
10 various metal impurities were determined by using an inductively coupled plasma mass spectrometer. The results are shown in Table 1.

[0041]

In a similar manner, from the upper outlet where the
15 gas phase portion was present in the cylinder A, 100 g of 1,1,1,4,4,4-hexafluoro-2-butene gas was extracted and transferred to the cylinder C at a reduced pressure. From the tank, 100 g of 1,1,1,4,4,4-hexafluoro-2-butene gas was extracted and transferred to the cylinder C at a
20 reduced pressure. The temperature of the cylinder C was then raised to room temperature and was allowed to stand for 24 hours. The 1,1,1,4,4,4-hexafluoro-2-butene after standing was regarded as sample 1-3. From the upper outlet where the gas phase portion was present in the
25 cylinder C after standing, the 1,1,1,4,4,4-hexafluoro-2-butene gas was extracted, and the concentrations of various metal impurities were determined by using an inductively coupled plasma mass spectrometer. The

results are shown in Table 1.

[0042]

In a similar manner, from the upper outlet where the gas phase portion was present in the cylinder A, 100 g of
5 1,1,1,4,4,4-hexafluoro-2-butene gas was extracted and transferred to the cylinder D at a reduced pressure. From the tank, 200 g of 1,1,1,4,4,4-hexafluoro-2-butene gas was extracted and transferred to the cylinder D at a reduced pressure. The temperature of the cylinder D was
10 then raised to room temperature and was allowed to stand for 24 hours. The 1,1,1,4,4,4-hexafluoro-2-butene after standing was regarded as sample 1-4. From the upper outlet where the gas phase portion was present in the cylinder D after standing, the 1,1,1,4,4,4-hexafluoro-2-
15 butene gas was extracted, and the concentrations of various metal impurities were determined by using an inductively coupled plasma mass spectrometer. The results are shown in Table 1.

[0043]

20 (Preparation Example 2)

The same procedure as in Preparation Example 1 was performed except that 1,1,1,2,4,4,4-heptafluoro-2-butene was used as a fluorobutene, and samples 2-1 to 2-4 were prepared. The concentrations of various metal impurities
25 in each sample were determined by using an inductively coupled plasma mass spectrometer. The results are shown in Table 2.

[0044]

[Table 2]

	Na	K	Mg	Ca	Total	Mn	Co	Ni	Si	Total
Sample 2-1	-	-	-	-	-	1	4	2	6	13
Sample 2-2	-	-	-	-	-	18	17	19	25	79
Sample 2-3	218	210	168	171	767	191	167	189	222	769
Sample 2-4	-	-	-	-	-	398	324	388	452	1562

*) The unit of numerical values is ppb by mass. "-" means no measurement data.

[0045]

(Preparation Example 3)

The same procedure as in Preparation Example 1 was
 5 performed except that 3,3,4,4,4-pentafluoro-1-butene was
 used as a fluorobutene, and samples 3-1 to 3-4 were
 prepared. The concentrations of various metal impurities
 in each sample were determined by using an inductively
 coupled plasma mass spectrometer. The results are shown
 10 in Table 3.

[0046]

[Table 3]

	Na	K	Mg	Ca	Total	Mn	Co	Ni	Si	Total
Sample 3-1	-	-	-	-	-	2	3	1	4	10
Sample 3-2	-	-	-	-	-	23	19	21	26	89
Sample 3-3	219	206	173	178	776	210	191	200	241	842
Sample 3-4	-	-	-	-	-	410	384	404	462	1660

*) The unit of numerical values is ppb by mass. "-" means no measurement data.

[0047]

(Preparation Example 4)

15 The same procedure as in Preparation Example 1 was
 performed except that 2,3,3,4,4,4-hexafluoro-1-butene was
 used as a fluorobutene, and samples 4-1 to 4-4 were
 prepared. The concentrations of various metal impurities
 in each sample were determined by using an inductively

coupled plasma mass spectrometer. The results are shown in Table 4.

[0048]

[Table 4]

	Na	K	Mg	Ca	Total	Mn	Co	Ni	Si	Total
Sample 4-1	-	-	-	-	-	3	2	3	5	13
Sample 4-2	-	-	-	-	-	21	19	19	25	84
Sample 4-3	233	218	193	202	846	197	184	204	237	822
Sample 4-4	-	-	-	-	-	402	392	407	442	1643

*) The unit of numerical values is ppb by mass. "-" means no measurement data.

5 [0049]

(Example 1)

The cylinder A was allowed to stand at 20°C for 30 days, and then from the gas phase portion of the cylinder A, 1,1,1,4,4,4-hexafluoro-2-butene gas was extracted and
10 analyzed by gas chromatography to quantify the concentration of a decomposition product of 1,1,1,4,4,4-hexafluoro-2-butene in sample 1-1. As a result, no decomposition product was detected.

Measurement conditions of the gas chromatography
15 were as follows:

Gas chromatograph: GC-2014 manufactured by Shimadzu Corporation

Column: carbopackB_1% sp-1000

Injection temperature: 200°C

20 Column temperature: 100°C

Detector: FID

Detector temperature: 200°C

Carrier gas: helium

Detection limit: 1 ppm by mass

[0050]

(Examples 2 to 12 and Comparative Examples 1 to 4)

Analysis objects and analysis results in Examples 2 to 12 and Comparative Examples 1 to 4 are shown in Table 5 in comparison with those in Example 1. In other words, substantially the same analysis as in Example 1 was performed except the items shown in Table 5.

[0051]

[Table 5]

	Sample/cylinder	Fluorobutene	Decomposition product/concentration (ppm by mass)	Result
Ex. 1	1-1/A	1,1,1,4,4,4-Hexafluoro-2-butene	Not detected	(-)
Ex. 2	1-2/B	Ditto	Not detected	(-)
Ex. 3	1-3/C	Ditto	Not detected	(-)
Comp. Ex. 1	1-4/D	Ditto	1,3,3,3-tetrafluoro-1-propene/138	(+)
Ex. 4	2-1/A	1,1,1,2,4,4,4-Heptafluoro-2-butene	Not detected	(-)
Ex. 5	2-2/B	Ditto	Not detected	(-)
Ex. 6	2-3/C	Ditto	Not detected	(-)
Comp. Ex. 2	2-4/D	Ditto	1,2,3,3,3-pentafluoro-1-propene/78	(+)
Ex. 7	3-1/A	3,3,4,4,4-Pentafluoro-1-butene	Not detected	(-)
Ex. 8	3-2/B	Ditto	Not detected	(-)
Ex. 9	3-3/C	Ditto	Not detected	(-)
Comp. Ex. 3	3-4/D	Ditto	1,2,3,3,3-pentafluoro-1-propene/48	(+)
Ex. 10	4-1/A	2,3,3,4,4,4-Hexafluoro-1-butene	Not detected	(-)
Ex. 11	4-2/B	Ditto	Not detected	(-)
Ex. 12	4-3/C	Ditto	Not detected	(-)
Comp. Ex. 4	4-4/D	Ditto	Hexafluoropropene/37	(+)

(-): No decomposition product was detected.

(+): A decomposition product was detected.

CLAIMS

1. A method for storing a fluorobutene represented
by general formula $C_4H_xF_y$ where x is 0 or more and 7 or
5 less, y is 1 or more and 8 or less, and $x + y$ is 8,
wherein

the fluorobutene contains or does not contain at
least one of manganese, cobalt, nickel, and silicon as a
metal impurity, and the fluorobutene is stored in a
10 container in which a total concentration of manganese,
cobalt, nickel, and silicon is 1,000 ppb by mass or less
when the fluorobutene contains at least one of manganese,
cobalt, nickel, and silicon.

15 2. The method for storing a fluorobutene according
to claim 1, wherein the fluorobutene further contains or
does not contain at least one of sodium, potassium,
magnesium, and calcium as the metal impurity, and the
fluorobutene is stored in a container in which a sum
20 total concentration of manganese, cobalt, nickel,
silicon, sodium, potassium, magnesium, and calcium is
2,000 ppb by mass or less when the fluorobutene further
contains at least one of sodium, potassium, magnesium,
and calcium.

25

3. The method for storing a fluorobutene according
to claim 1 or claim 2, wherein the fluorobutene is at
least one selected from 1,1,1,4,4,4-hexafluoro-2-butene,

1,1,1,2,4,4,4-heptafluoro-2-butene, 3,3,4,4,4-pentafluoro-1-butene, and 2,3,3,4,4,4-hexafluoro-1-butene.

- 5 4. The method for storing a fluorobutene according to any one of claims 1 to 3, wherein the fluorobutene is stored at a temperature of -20°C or more and 50°C or less.