



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C08G 18/62, 18/40, C08F 216/00, C09D 133/00, C08K 5/103	A1	(11) International Publication Number: WO 99/21906 (43) International Publication Date: 6 May 1999 (06.05.99)
(21) International Application Number: PCT/EP98/07017 (22) International Filing Date: 28 October 1998 (28.10.98) (30) Priority Data: 97203351.8 29 October 1997 (29.10.97) EP 97204126.3 29 December 1997 (29.12.97) EP (71) Applicant: SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V. [NL/NL]; Carel van Bylandtlaan 30, NL-2596 HR The Hague (NL). (72) Inventors: HENRY, Nathalie; Avenue Jean Monnet 1, B-1348 Ottignies, Louvain-la-Neuve (BE). KREBS, Achim; Avenue Jean Monnet 1, B-1348 Ottignies, Louvain-la-Neuve (BE). MOERMAN, Marc, Carlo; Avenue Jean Monnet 1, B-1348 Ottignies, Louvain-la-Neuve (BE). UYTTERHOEVEN, Griet; Avenue Jean Monnet 1, B-1348 Ottignies, Louvain-la-Neuve (BE).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: HIGH SOLIDS COATING COMPOSITIONS (57) Abstract Coating composition comprising 60 to 90 percent by weight of binder components and from 40 to 10 percent by weight of an organic liquid carrier, wherein the binder comprises the following separate components: (a) 5 to 50 percent by weight, relative to the weight of the binder of one or more hydroxy-functional oligoether derived from at least one polyol free of carboxyl groups and having three or four hydroxyl groups, and a mono-glycidyl ester of a branched carboxylic acid, containing from 5 to 13 carbon atoms, the oligoether having a number average molecular weight (Mn) of from 150 to 1000, a molecular weight distribution (MWD) <1.10 and a hydroxy value of between 180 and 700, (b) 40 to 60 percent by weight, relative to the weight the binder of one or more hydroxy-functional acrylic or methacrylic copolymer with an Mn between 500 and 2500, having a hydroxy-functional comonomer content between 10 and 50 weight percent of the copolymer, derived from the reaction products of mono-glycidyl esters of a branched carboxylic acid containing from 5 to 13 carbon atoms and acrylic acid or methacrylic acid, and combinations thereof, and optionally mixed with an amount of at most 10 wt.% of comonomers, which have been selected from the group consisting of cycloaliphatic (meth)acrylic comonomers and/or alkyl substituted aromatic vinyl comonomers, (c) 5 to 40 percent, relative to the weight of the binder, of polyisocyanate cross-linkers, and (d) an effective amount of curing catalyst.		