

INTEGRALLY WATERPROOFED CONCRETE

Inventors:

5 ***Antonio J. Aldykiewicz, Jr., Arnon Bentur, Neal S. Berke, and Chia-Chih Ou***

Field of the Invention

The present invention pertains to additives and admixtures for hydratable cementitious compositions, and more particularly to additives and admixtures for
10 imparting water repellant properties to cementitious compositions.

Background of the Invention

It is known to incorporate water repellant materials into hydratable cementitious materials such as cement pastes, masonry cements, mortars, and concrete to achieve a degree of moisture impermeability. A cementitious composition which is impermeable to
15 water and dampness, ideally, may not require the application of externally applied moisture barriers such as bituminous coatings or waterproofing membrane laminates.

In US Patent 6,761,765 B2 (issued July 13, 2004), Lu disclosed an emulsion admixture for imparting water repellant properties to cements. The admixture comprised a polymer, a surfactant, and hydrophobic material in the form of organic esters of
20 aliphatic carboxylic acid. The polymer was preferably a latex polymer (e.g., styrene butadiene copolymer latex). The surfactant could include any surfactant capable of emulsifying the hydrophobic material, and most preferably was an ethoxylated nonylphenol. Lu theorized that mixing the emulsified hydrophobic material into the cementitious composition would evenly distribute it throughout the cementitious matrix
25 as well as over its surface. This purportedly prevented water from entering and exiting porous cementitious structures such as blocks, pavers, and retaining wall units (*See* Col. 4, ll. 17-24).

Emulsified hydrophobic materials, however, were long known and used previously. For example, US Patents 3,865,601 and 3,885,985 disclosed additives
30 comprising oil-in-water emulsions that contained a water-insoluble, water-repelling acid component (e.g., tall oil, an emulsifier (e.g., a salt of such an acid)) and a setting time retarding agent (e.g., sucrose). As explained in the background of US Patent 5,108,511,

this additive was dispersible in water form so that the risk of overdosing could be minimized. Further, the additive was provided in a form that allowed additional optional components, such as air-entraining agents, to be included. An improved emulsion additive, as described in US Patent 4,375,987, further included an emulsion stabilizer
5 (e.g., a glycol). The stabilizer, as is now well known, prevents oil-in-water emulsions from breaking down when exposed to freezing temperatures during shipping or storage. (See e.g., US 5,108,511 at column 2, lines 11-23).

In US Patent 5,108,511, Wiegand observed that oil-in-water emulsions were unusable when they broke down. Even when stabilizers (such as glycol) were used in
10 such aqueous systems, the emulsion could break down due to extreme temperature fluctuation and long term thermal cycling. Thus, for the express purpose of increasing workability, plasticity, and board life in mortar cement, Wiegand proposed an additive that comprised a salt of stearic acid (e.g., calcium stearate, aluminum stearate), a set retarding carbohydrate, an ethylenic glycol selected from mono-, di-, tri-, and
15 tetraethylene glycols, and cellulose ether. The stearic salt was saponified by heating the stearic acid and lime powder.

The use of oil-in-water emulsions and saponified metal salts (e.g., calcium stearate) has been commercialized in the industry for some time. An emulsion-based, water-repellancy enhancer, added during the intergrinding process for making cement
20 from clinker, is commercially available from Grace Construction Products, Cambridge USA, under the tradename HYDROPHOBE®. A calcium stearate suspension, provided in the form of finely ground calcium stearate powder, dispersed in an aqueous carrier, is commercially available from Grace under the tradename DARAPEL®.

To improve upon the prior art water repellency technology, the present inventors
25 propose to avoid the use of aqueous emulsions or aqueous solvents.

Summary of the Invention

The present invention provides a novel composition for enhancing water repellency in cement, masonry cement, concrete, and other cementitious materials. In many cases, it is hoped that the moisture permeability in such cementitious materials can be lowered to the point at which an externally-applied waterproofing coating or membrane is eliminated, thereby achieving a reduction of materials and labor expense.

Novel compositions of the invention may be combined with a cement or cementitious material such as concrete, either as an additive (e.g., during intergrinding of clinker to produce cement) or admixture (e.g., to finished cement, mortar, or concrete) in a liquid-dispensible form. This favors accurate, controllable, verifiable dosage amounts.

Exemplary compositions of the invention comprise: a solute portion having at least one hydrophobic material operative to enhance water repellency in a cementitious material; and a non-aqueous solvent portion having at least one glycol ether, which is preferably operative to inhibit drying shrinkage in a cementitious material; said solute and solvent being present in said composition in a ratio of 95:5 to 5:95; said solute and solvent portions being mixed uniformly together in the form of a nonaqueous solution or in the form of an emulsion wherein water is present as a non-continuous phase. It is preferred that the hydrophobic material be non-air-entraining and non-saponified.

Because compositions of the invention are not intended to achieve oil-in-water emulsions, but rather are intended to be used in the form of nonaqueous solutions or emulsions wherein water is present only as a non-continuous phase, the use of surfactants can be avoided. Surfactants often entrain too much air when used in mortars and concretes. Although a certain amount of air, when distributed as fine micro-bubbles, can bestow freeze-thaw durability to mortars and concretes, air levels which are too high may lead to passageways by which moisture can penetrate. It is believed that the present invention provides better air level management in cementitious materials without requiring that defoamers be added.

The present invention allows certain conventional hydrophobic materials to be employed for use in modifying cementitious compositions, and these would include materials that are preferably non-air-entraining in nature. This may be accomplished by dissolving the hydrophobic materials directly in a non-aqueous liquid carrier, one that
5 preferably comprises one or more shrinkage reducing admixtures, such as certain glycol ethers, as will be further discussed hereinafter.

This combination of solute and non-aqueous solvent results in a larger temperature stability range, and eliminates the need for heated storage in colder environments. This is a tremendous advantage when compared with prior art water
10 repellant systems that were based on conventional emulsions or aqueous suspensions.

For example, exemplary hydrophobic materials believed to be suitable for use in the present invention include an aliphatic carboxylic acid or salt or ester thereof, a fatty acid or salt or the ester thereof, a natural or synthetic wax, a natural or synthetic oil, a silicone compound, a silane compound, a siloxane compound, a naphthalene compound,
15 a melamine compound, a dicarboxylic acid or the salt thereof, or a mixture of any of the foregoing.

Especially preferred hydrophobic materials (solute) contemplated for use in the invention include fatty acids such as butyl stearate, butyl oleate, or a mixture thereof; while preferred glycol ethers (solvent) include di(oxypropylene)glycol-t-butyl ether
20 (DPTB), di(oxypropylene)glycol-n-butyl ether (DPNB), or a mixture thereof. The solvent may additionally include a low molecular glycol such as di(oxypropylene)glycol (DPG), di(oxyethylene)glycol (DIEG), or mixture thereof.

A further detailed description of exemplary solutes (hydrophobic materials) and solvents (such as glycol ethers) is provided hereinafter.

25 By avoiding the use of a large water portion, the compositions of the invention will realize several advantages. First, manufacturers can avoid the additional step required for making the aqueous emulsion or dispersion as well as the costs of surfactants and stabilizers. Further, the cost of shipping water that constitutes the bulk of the aqueous emulsion or suspension will be decreased. Furthermore, with little or no water content,

the compositions of the invention will be less hospitable to bacteria and other microorganisms.

In further exemplary compositions of the invention, one or more comb polymer superplasticizers, such as poly(oxyalkylene) types as known in the art, may be additionally incorporated to lower the water-to-cement ratio and improve workability or fluidity of the cementitious composition. While such superplasticizers may involve a small amount of water, it is nevertheless preferred that compositions of the invention be substantially devoid of water, e.g., less than 35% and more preferably less than 15% by total volume.

10 The present invention also concerns methods for enhancing water repellency in cementitious materials, and also concerns cementitious materials containing the above-described water repellency enhancing compositions. Other advantages and features of the invention are described hereinafter.

Detailed Description of Exemplary Embodiments

The inventive compositions of the invention, as previously described, are useful as additives or admixtures for modifying cements and cementitious compositions and materials. The present invention thus also pertains to cementitious materials and methods for enhancing water repellency in them.

The terms "cementitious composition" or "cementitious material" as may be used herein, sometimes interchangeably, include and refer to not only to "cements" but also to pastes (or slurries), mortars, and grouts, such as oil well cementing grouts, shotcrete, and concrete compositions comprising a hydraulic cement binder. The terms "paste", "mortar" and "concrete" are terms of art: pastes are mixtures composed of a hydratable (or hydraulic) cement binder (usually, but not exclusively, Portland cement, Masonry cement, Mortar cement, and/or gypsum, and may also include limestone, hydrated lime, pozzolans such as fly ash and/or granulated blast furnace slag, metakaolin, rice hull ash, and silica fume or other materials commonly included in such cements) and water; "mortars" are pastes additionally including fine aggregate (e.g., sand), and "concretes" are mortars additionally including coarse aggregate (e.g., crushed rock or gravel). The cementitious materials described in this invention are formed by mixing required amounts of certain materials, e.g., a hydraulic cement, water, and fine and/or coarse aggregate, as may be required for making a particular cementitious composition.

In addition, the term "cement" may also include and refer to calcium aluminate cement, hydratable alumina, hydratable aluminum oxide, colloidal silica, silicon oxide, magnesia, in addition to Portland cement and pozzolans as just mentioned above.

The water-to-cement (W/C) ratio used in making cast or spray-applied cementitious mixtures is not believed to be critical to achieving optimal water repellency properties, although a suitable W/C ratio could be from about 0.25 to about 0.60. It is desirable to minimize the amount of water needed so as to consolidate, and to avoid deformities in, the structure formed by the cementitious mixture.

When used as admixtures for modifying cement, concrete, or other cementitious material, the compositions of the invention may be combined with hydratable cement binder material before, during, or after addition of water. Alternatively, the inventive compositions can be added as an interground additive during the manufacturing process
5 wherein clinker is transformed into hydratable cement.

Exemplary compositions of the invention may be generally described as non-aqueous solutions having at least one solute and a non-aqueous solvent present in a ratio of 95:5 to 5:95, and, more preferably, 70:30 to 30:70. Preferably, the solute and solvent portions are mixed uniformly together to form a non-emulsion liquid solution. More
10 preferably, the solute may be present in the composition in an amount of 70 to 30 percent based on total dry weight solids in the composition; while the solvent may be present in an amount of 30 to 70 percent based on total weight of the composition.

Exemplary hydrophobic materials contemplated for use in the invention include but are not limited to aliphatic carboxylic acid or salt or ester thereof, a fatty acid or salt
15 or the ester thereof, a natural or synthetic wax, a natural or synthetic oil, a silicone compound (silane, siloxane), a naphthalene compound, a melamine compound, a dicarboxylic acid or the salt thereof, or a mixture thereof. The most preferred hydrophobic materials which are by themselves non-air-entraining when incorporated into hydratable cementitious compositions. Where the hydrophobic material is
20 incorporated into the solvent in solid form, it is preferable to ground the material as finely as possible to facilitate dissolving of the solute into the solution.

Among the preferred hydrophobic materials, therefore, are aliphatic carboxylic acids, salts, or esters thereof, and in particular the organic (e.g., aliphatic) esters of these carboxylic acids or salts. Preferably, the organic ester of an aliphatic carboxylic acid is
25 represented by the general formula R_1-R_2 , wherein R_1 is $C_{12}-C_{18}$ aliphatic carboxylic acid ester, and R_2 is a linear or branched C_1-C_{10} alkyl. Preferred aliphatic carboxylic acid esters include, but are not limited to, stearate, oleate, naturally occurring oils (e.g., coconut oil, castor oil, tall oil fatty acid), laurate, palmitate, myristic ester, linoleic ester, and salts and/or mixtures thereof.

Preferred hydrophobic materials include, but are not limited to, alkyl stearate esters, alkyl oleate esters, and mixtures thereof. Preferably, the organic ester of a stearate has the general formula $C_{17}H_{35}COOR_3$ and the organic ester of an oleate has the general formula $CH_3(CH_2)_7=(CH_2)_7COOR_4$, wherein R_3 and R_4 are each independently a linear or
5 branched C_1 to C_{10} alkyl. A preferred stearate is butyl stearate, and a preferred oleate is butyl oleate. In particularly preferred non-air-entraining hydrophobic materials, both butyl oleate and butyl stearate are used together.

More generally speaking, exemplary compositions of the invention comprise at least one hydrophobic material such as a stearate, an oleate, a laurate, a palmitate, a
10 myristic ester, a linoleic ester, a coconut oil, a castor oil, tall oil fatty acid, or a salt thereof, or a mixture thereof. Preferably such hydrophobic material is non-air-entraining when incorporated into cementitious materials (e.g., cement mortars and concretes). Preferably, hydrophobic material is an alkyl stearate ester, an alkyl oleate ester, or mixture thereof. More preferably, the hydrophobic material is butyl oleate (BO), butyl
15 stearate (BS), or a mixture of these two, which may be used in a ratio (BO:BS) of 5:1 to 1:5; more preferably, in a ratio of 4:1 to 1:2; and, most preferably, in a ratio of 3:1 to 1:1.

Exemplary hydrophobic materials may also include fatty acids as well as their salts. For example, calcium stearate and zinc stearate may be used, and these are commercially available (both in powder form) from NORAC, Inc. Another example is
20 tall oil fatty acid (TOFA) which is available from Grace Construction Chemicals, Cambridge, USA, under the tradename RX-901.

Exemplary hydrophobic materials may also include natural waxes, such as paraffinic wax, ceresin wax, and beeswax. Exemplary synthetic waxes may also be used. For example, such waxes are commercially available from Dow Chemicals under the
25 tradename Carbowax®.


Exemplary hydrophobic materials may also include naturally occurring oils (e.g., coconut oil, castor oil), some of these being already noted above, as well as synthetic oils.

Other exemplary hydrophobic materials are silicones, silanes, and siloxanes. For example, butyltrimethoxysilane and other silanes are commercially available from Dow


Corning. A wide range of organosilicon compounds are available as well from Dow Corning.

Still further exemplary hydrophobic materials believed to be suitable for purposes of the invention include naphthalene compounds (e.g., bis isopropenyl naphthalene, calcium di(naphthalene) sulfonate), and also melamine compounds.

Another exemplary hydrophobic material is a dicarboxylic acid or the salt thereof. Such materials will have the chemical formula



wherein R^1 is a C_{12} to C_{18} alkyl or alkylene group; R^2 and R^3 are hydrogen or a cation (e.g., sodium, potassium, lithium, zinc, butyl), and "n" is an integer from 1 to 6. A preferred dicarboxylic salt is di-sodium salt of tetrapropenyl butanediodic acid, having the formula



For example, a 20% solution of this dicarboxylic salt ("DSS") can be mixed into a glycol ether solvent as follows: 45% DPTB, 45% DPG, 2% DSS, and 8% water (wherein "DPTB" represents di(oxypropylene)glycol-t-butyl ether and "DPG" represents di(oxypropylene)glycol).

Exemplary glycol ether solvents believed to be suitable for use in the invention comprise (i) an oxyalkylene glycol; (ii) an oxyalkylene ether adduct of an alcohol, glycol, or glycerol; or (iii) a mixture thereof. Exemplary oxyalkylene glycols which are believed to be suitable for use in the present invention can be represented by the formula $HO(AO)_nH$ wherein: A represents a C_2 - C_4 alkylene group (such as ethylene, propylene, butylenes, and the like, along with mixtures thereof, with ethylene and propylene being most preferred); O represents an oxygen atom, and n represents an integer of from 1 to about 30, and more preferably 1-3. The AO groups in a particular glycol molecule may be the same or may be different. Examples of such glycols include diethylene glycol, dipropylene glycol, tripropylene glycol, di(ethoxy)(di(propoxy)glycol and the like. Further glycols may include polyalkylene glycols (poly(oxyalkylene)glycols) having molecular weights up to about 1200. The AO groups forming the chain of such glycols

may contain a single type of alkylene ether group or a mixture of alkylene ether groups which may be in block or random arrangement. Examples of the oxyalkylene glycols are polypropylene glycol, polyethylene glycol, poly(oxyethylene)(oxypropylene)glycol and the like.

5 Exemplary oxyalkylene adducts of monoalcohols which are believed to be suitable for use in the invention can be represented by the formula $RO(AO)_mH$ wherein R is a hydrocarbon group, such as a C_1 - C_7 alkyl or a C_5 - C_6 cycloalkyl group; A represents a C_2 - C_4 alkylene group, O represents an oxygen atom and m represents an integer of from 1 to about 10. Examples of such R groups are methyl, ethyl, propyl, isopropyl, n-butyl,
10 isobutyl, t-butyl, n-pentyl, isopentyl, cyclopentyl, cyclohexyl and the like. The preferred R groups are C_3 - C_5 alkyl such as n-propyl, isopropyl, n-butyl, t-butyl and the like. In various embodiments of the invention, is preferred that the R groups be the same. A is a C_2 - C_4 (preferably C_2 - C_3) alkylene group, such as ethylene, propylene and the like and mixtures thereof in the same chain, and m is an integer of from 1 to about 10, preferably
15 2 or 3.

In preferred embodiments, the solvent is di(oxypropylene)glycol-tertiary-butyl ether ("DPTB"), di(oxypropylene)glycol-n-butyl ether ("DPNB"), or a mixture thereof, optionally with di(oxypropylene)glycol ("DPG"), di(oxyethylene)glycol (DEIG), or mixture thereof.

20 Exemplary compositions of the invention therefore comprise at least one hydrophobic material which could include a stearate, an oleate, a naturally occurring oil, a laurate, a palmitate, a myristic ester, a linoleic ester, or a salt thereof, or a mixture thereof; and a glycol ether solvent which could include (i) an oxyalkylene glycol; (ii) an oxyalkylene ether adduct of an alcohol, glycol, or glycerol; or (iii) a mixture thereof. In
25 most preferred compositions, the at least one hydrophobic material comprises butyl oleate and butyl stearate, and the glycol ether solvent is DPTB, DPNB, or a mixture thereof, optionally with low molecular weight DPG or DIEG. These solvents are especially preferred because they have excellent shrinkage and air detraining capabilities when incorporated into hydratable cementitious mixtures. Hence, preferred solvents are
30 operative to detrain air in cementitious materials.

Further exemplary compositions of the invention may comprise at least one comb polymer superplasticizer, as conventionally used in the industry, for improving plasticity, workability, and/or slump as may be desired. Most preferred are comb polymer superplasticizers having pendant poly(oxyalkylene) groups. Such plasticizers are generally known. A suitable superplasticizer is commercially available from Grace under the tradename ADVA®. Superplasticizers can be incorporated into compositions of the invention, preferably after the solute(s) and solvent are mixed thoroughly together, in an amount of 5 to 30 percent based on total weight of the composition. Poly(oxyalkylene) superplasticizers may contain a small amount of water as a result of formulation or manufacture. However, it is preferable that the total amount of water not exceed 30% by total volume of composition, and more preferably not exceed 5% by total volume of composition.

Preferably, the compositions of the invention are substantially devoid of surfactants, or other surface active agents, as would normally be otherwise required to form emulsion systems. Thus, the use of a metal salt (e.g., sodium, potassium, lithium) of a fatty acid or tall oil fatty acid is less preferred due to the tendency of such metal salts to entrain air when incorporated into cementitious materials; and thus, if certain metal salts are used as hydrophobic materials, it may be advisable to employ an air-detraining agent.

Exemplary methods of the invention therefore include modifying a cementitious material by introducing to a hydratable cementitious material the above-described water repellency enhancing compositions. As previously mentioned, these can be incorporated as additives during the manufacture of cement from clinker, or as admixtures incorporated into the finished cement, mortar, concrete, or other cementitious mixture.

The following examples are provided for illustrative purposes.

Example 1

Several solutions of the invention were produced by dissolving an organic ester of an aliphatic acid, or an aliphatic carboxylic acid, into glycol ether. These resulted in transparent solutions as confirmed by shining a laser through the liquid. (According to Tyndall, a solution will not scatter the laser beam, whereas an emulsion or dispersion

will). Unlike emulsions, these solutions are stable at a high temperature of 46 degrees C and will revert to a solution if taken below solidification temperature and melted. In addition, viscosities at low temperatures are well below the 250 cP criterion needed for pumping with standard admixture pumps. The data is presented in Table 1 below.

- 5 Sample 1 shows the benefit of using DPNB and DPG to reduce the freezing point of butyl oleate ("BO") and butyl stearate ("BS") blends.

Table 1

% Components					At 2 °C		5°C	46°C	
Sample	DPNB	DP G	BO	BS	Form	Viscos ity (cP)	Form	Viscosity (cP)	Form
1	38	21	20.5	20.5	HS*	-	HL**	21	HL
2	38	21	27.3	13.7	HL	23.8	HL	20.1	HL
3	38	21	30.75	10.25	HL	23.7	HL	20.5	HL
4	0	0	67	33	HS				HL
5	29.5	29.5	20.5	20.5	HS		HL		HL
6	29.5	29.5	27.3	27.7	HL		HL		HL
7	33	33	17	17	HL		HL		HL
8	33	33	22,7	11,3	HL		HL		HL

- 10 *HS=Homogeneous solid/gel; **HL=Homogeneous liquid solution;
DPNB=dipropylene glycol n butyl ether; DPG=dipropylene glycol
BO=butyl oleate; BS=butyl stearate

Example 2

- 15 An exemplary additive of the invention, wherein a hydrophobic material was dissolved in a glycol ether shrinkage reducing solvent to obtain the additive, was shown to enhance moisture impermeability of concrete samples. This enhanced impermeability was confirmed in terms of reducing water absorption, shrinkage, and electrical conductivity, in comparison to concrete samples not containing the additive.

- 20 The improvements are seen in concretes having high water-to-cement ratios (w/c) as well as lower w/c ratios which are typical of less permeable concretes. Table 2 shows typical improvements in the British Absorption Test (BS 1881 Part 122) for composition 1, 2 and 3 from Table 1 denoted as "TWC1," "TWC2," and "TWC3." This is a key test for evaluating admixtures for achieving integral waterproofing of cementitious compositions,
25 and numbers of about 1% or less are considered excellent.

The data suggests that IWC mixes had better workability with lower superplasticizer levels than shrinkage reducing admixture (SRA) used alone (Mixture

10), and had reduced absorption levels when compared to SRA used alone, and showed a 25% improvement at two-thirds dosage.

Table 2

Mixture	Polycarboxylate Superplasticizer (oz/cwt)*	Air (%)	Final Slump (in)**	UW (pcf)	British Absorption%
1. Control 0.5w/c	2.5	4	8.00	151.7	2.8515
2. Control 0.4w/c	6	2.4	7.00	151.7	1.8487
3. WC1/ @.5gpy	6	1.7	7.50	158.9	0.9925
4. IWC1/ @.075gpy	6	1.7	7.25	158.5	0.9819
5. IWC1/ @1gpy	5.5	1.8	4.00	157.8	0.9266
6. IWC2/ @0.5gpy	6	1.4	7.25	159.0	1.0174
7. IWC3/ @0.5gpy	6	1.5	7.25	158.5	0.9439
8. IWC2/ @0.75gpy	8	1.7	7.50	158.1	0.9338
9. IWC3/0@0.75gpy	6.5	1.7	6.50	158.2	0.9715
10. 50%DPNB/ 50%DPG@0.75gpy	12	2.4	4.00	156.4	1.2618

*The polycarboxylate Superplasticizer was Grace Construction Products brand available under the tradename Adva®.

**Slump is an indication of workability and is measured using the standard slump cone technique, and values shown were found to be between 4 and 8 inches which is desirable for normal concretes used in flooring and wall applications.

Example 3

Properties for various mixes produced using IWC1, SRA, and damp-proofing materials such as calcium stearate emulsion (Grace Darapel® brand), butyl oleate, and butyl stearate. The damp-proofing materials have a minor effect on drying shrinkage. As shown in Example 2 above, the SRA does not reduce water absorption as well as the IWC samples.

Synergy was surprisingly discovered by dissolving the hydrophobic material or materials in a shrinkage reducing admixture (SRA) solvent before addition to cement or concrete, because the combined additive allowed for lower overall component dosages in comparison to separate use of hydrophobic material and separate use of the SRA.

Furthermore, less air was created in the concrete than was the case with separately added damp-proofing components. This is beneficial for interior flooring applications.

Permeability of concrete samples was measured using methodology similar to that described in ASTM C 1202. Current across the ends of a cylindrically shaped concrete sample having a 4-inch diameter by 12-inch length was measured at 60 Volts DC after one minute. Higher currents correspond to concretes having higher permability to water and moisture. It is noted that reducing the water/cement ratio of the concrete from 0.5 to 0.4 had a major effect, and the addition of calcium stearate by itself showed little improvement. However, the concrete mixtures having the IWC additives of the invention showed a significant drop. It was found that although the hydrophobic material or the shrinkage reducing admixtures (SRA), when used separately, could match or exceed some of the qualities of the IWC samples of the invention, the IWC samples used less overall material and achieved favorable reductions in absorption, permeability, and shrinkage all across the board.

TABLE 3

Mix #	Mixture	BSI Abs.	ASTM C157 Drying Shrinkage 28 days drying 1- day cure in mold	Air (%)	Current (mA) (Modified ASTM C1202) at 12 days wet curing
04353-1	Control 0.5w/c	2.83	0.0675	2.5	69.2
04353-2	Control 0.4w/c	1.84		2.4	45.3
04353-3	Control 0.4w/c 1.0galDarapel	0.96	0.0465	2.7	43.6
04353-4	Control 0.4w/c 1.5galDarapel	0.73	0.0535	2.9	44.1
04353-5	IWC1@.5gpy	1.08	0.042	1.9	37.245
04353-6	IWC1@.75gpy	0.98	0.040	1.5	37.455
04353-7	IWC1@1gpy	0.90	0.036	1.5	34.68
04353-8	DPNB(DPG50/50)@1gpy	1.20	0.0315	1.9	38.94
04353-9	50/50BO/BS@0.5gpy	0.82	0.0515	1.7	37.535

Example 4

Other hydrophobic solute materials that can provide excellent properties are naphthalenes, e.g., Ruetasolv DI, which is $C_{16}H_{20}$, Naphthalene, bis(1-methylethyl)-(9Cl). When added at 1:2 to 2:1 to 50% dipropylene glycol t-butyl ether/50% dipropylene glycol, the naphthalene formed a clear solution as confirmed by laser light test, and was also found to be soluble in IWC2 (See Formula 2 in Table 1). Properties of concrete

samples made using these materials, compared to control samples, are shown in Table 4. Reducing the water-to-cement (w/c) ratio slightly improved initial capillary absorption (Si) as measured using ASTM C 1585. However, there was a significant reduction in Si when additives of the invention were employed, as well as a significant decrease in shrinkage (in comparison to samples wherein w/c ratio was merely lowered).

Table 4

Formulation	w/c	Si (mm-s ^{1/2})	28-day shrinkage after 7 days moist curing (%)	Current (mA) (Modified ASTM C1202) at 28 days wet curing
1. Control 1	0.5	30.5	0.0335	55.6
2. Control 2	0.4	26.5	0.0245	33.9
3. 25%DPTB/ 25% DPG/ 50%Ruetasolv	0.4	10.5	0.0075	34.3
4. 66.7%DPNB/ 33.3%RUETASOLV	0.4	10.0	0.0145	31.6

Example 5

Stable non-oil-in-water emulsions were made using glycol ether to provide a continuous liquid phase and a naphthalenesulfonic acid as the hydrophobic material. An exemplary hydrophobic material was NaCorr® which is a tradename for naphthalenesulfonic acid, dinonyl-calcium salt (C₂₈H₄₄O₃S.1/2Ca)). This additive, when employed in a concrete sample, provided benefits in terms of reducing shrinkage and absorption. Laser light tests confirmed that these formulations are emulsions in at least a range of 1:2 to 2:1 mass ratio to the glycol ether. They did not freeze or separate at temperatures from -5 to +46 degrees Celcius. Shrinkage and absorption data of samples containing the hydrophobic agent in a glycol ether shrinkage reduction agent (SRA), using an SRA available from Grace Construction Products under the tradename ECLIPSE® are summarized in the table below.

Table 5

Formulation	Shrinkage at 28 days (7-day wet cure) %	Capillary Absorption* C _{ab} (g/m ² -s ^{1/2})
1. Control	0.029	13.3
2. Eclipse (1.5 gpy)	0.014	10.8
3. 25%DPTB/25%DPG/50%NaCorr	0.0165	8.93

Note all concrete at 0.45 w/c.

*3-inch x 3-inch cylinders dried at 70°C, cooled to 21°C, and placed in water at 21°C.

5

Example 6

A wide range of formulations of the invention was tested to demonstrate that formed stable solutions or non-oil-in-water emulsions could be provided. The combinations, which are provided for illustrative purposes only and are not inclusive of all potential combinations realizable from the present disclosure, are identified in Table 6 below.

15

Table 6

Formula	Components (%)							Stearic Acid	Stable Solution (S) or Emulsion (E)
	DPNB	DPG	BO	BS	DPTB	Ruetasolv	NaCorr		
1		33.3			33.3		33.4		E
2		16.7			16.7		66.6		E
3		25			25		50		E
4		16.7			16.7		66.6		S
5		25			25		50		S
6		33.3			33.3		33.4		S
7	66.6		16.7	16.7					S
8	66.7		30	3.3					S
9	38	21	20.5	20.5					S
10	38	21	27.3	13.7					S
11	38	21	30.75	10.25					S
12	38	21	41	0					S
13	34.2	18.9	24.6	12.3		10			S
14	34.2	18.9	24.6	12.3			10		S
15	34.2	18.9	18.45	18.45			10		S
16		46.75			46.75			6.5	S
17	47.5		23.75	23.75				5	S

Example 7

Further exemplary hydrophobic materials were into DPTB and DPG. These hydrophobic materials included tall oil fatty acid (TOFA), a metal salt of a fatty acid (e.g., zinc stearate), and a wax (e.g., polyethylene glycol, about 200 molecular weight, available from Dow Chemical as CARBOWAX). TOFA (50%) was blended with DPTB

(25%) and DPG (25%) formed a stable mixture at room temperature, percentages based on weight). Zinc stearate (5.6%) was blended with DPTB (47.2%) and DPG (47.2%) and also provided a stable mixture at room temperature. The wax (33.4%) was blended with DPTB and DPG each at 33.3%, and provided a stable mixture at room temperature.

5

Example 8

A further exemplary stable solution of the invention was made by combining a hydrophobic material, polyethylene glycol (PEG) having approximately 1000 molecular weight, in di(oxypropylene)glycol-t-butyl ether (DPTB) and di(oxypropylene)glycol (DPG), in the following ratio: 47.15% DPTB, 47.15% DPG, and 5.7% PEG. The PEG
10 was commercially available from DOW under the tradename CARBOWAX 1000.

Example 9

A still further exemplary stable solution of the invention was made by dissolving a 20% solution of di-sodium salt of tetrapropenyl butanedioic acid, having the formula $\text{Na}^+ \text{ } ^-\text{OOC}-\text{C}(\text{C}_{12}\text{H}_{23})(\text{H})-\text{CH}_2-\text{COO}^- \text{Na}^+$ into DPTB and DPG, such that the final
15 solution had the following components: 45% DPTB, 45% DPG, 2% DSS, and 8% H₂O. Another solution was made and also found to be stable, and this had the following components: 35% DPTB, 35% DPG, 6% DSS, and 24% H₂O. It is believed that increasing the amount of the hydrophobic material, without using the aqueous solution (so that no water would be introduced into the solution), would also work.

20

Example 10

A still further exemplary stable solution of the invention was made by incorporating a silane (e.g., i-butyltrimethoxysilane from Dow Corning under the tradename Z-2306) in solvent, as follows: 29.4% DPTB, 29.4% DPG, and 41.2% Z-2306. This rendered a clear solution at room temperature

25

The foregoing examples and exemplary embodiments are provided for illustrative purposes and are not intended to limit the scope of the invention.

It is claimed:

1. A composition, comprising: a solute portion having at least one hydrophobic material operative to enhance water repellency in a cementitious material; and a non-aqueous solvent portion having at least one glycol ether operative to inhibit drying shrinkage in a cementitious material; said solute and solvent being present in said composition in a ratio of 95:5 to 5:95; said solute and solvent portions being mixed uniformly together in the form of a nonaqueous solution.
2. The composition of claim 1 wherein said hydrophobic material is non-air-entraining when incorporated into a hydratable cementitious composition.
3. The composition of claim 1 wherein said hydrophobic material is non-saponified.
4. The composition of claim 1 comprising water in an amount of 0-30% based on total volume of said composition.
5. The composition of claim 1 wherein said composition is devoid of water.
6. The composition of claim 1 wherein said solute and solvent is present in said composition in a ratio of 70:30 to 30:70.
7. The composition of claim 1 wherein said at least one hydrophobic material solute comprises an aliphatic carboxylic acid or salt thereof.
8. The composition of claim 7 wherein said at least one hydrophobic material solute comprises an aliphatic ester of an aliphatic carboxylic acid or salt thereof.
9. The composition of claim 1 wherein said at least one hydrophobic material is an organic ester of an aliphatic carboxylic acid represented by the general formula R_1-R_2 , wherein R_1 is $C_{12}-C_{18}$ aliphatic carboxylic acid ester, and R_2 is a linear or branched C_1 to C_{10} alkyl.
10. The composition of claim 9 wherein said at least one hydrophobic material solute comprises a stearate, an oleate, a naturally occurring oil, a laurate, a

palmitate, a myristic ester, a linoleic ester, coconut oil, castor oil, or a salt or a mixture thereof.

11. The composition of claim 9 wherein said at least one hydrophobic material solute comprises an alkyl oleate ester, an alkyl stearate ester, or mixture thereof.

12. The composition of claim 9 wherein said at least one hydrophobic material solute comprises butyl oleate, butyl stearate, or a mixture thereof.

13. The composition of claim 12 wherein said solute comprises a butyl oleate and a butyl stearate.

14. The composition of claim 13 wherein said butyl oleate and butyl stearate are present in said composition in an amount no less than 30 percent and in an amount no greater than 50 percent based on dry weight total solids in said composition.

15. The composition of claim 1 wherein said at least one hydrophobic material comprises: an aliphatic carboxylic acid or salt or ester thereof, a fatty acid or salt or the ester thereof, a natural or synthetic wax, a natural or synthetic oil, a silicone compound, a silane compound, a siloxane compound, a naphthalene compound, a melamine compound, a dicarboxylic acid or the salt thereof, or a mixture thereof.

16. The composition of claim 1 wherein said glycol ether solvent comprises (i) an oxyalkylene glycol; (ii) an oxyalkylene ether adduct of an alcohol, glycol, or glycerol; or (iii) a mixture thereof.

17. The composition of claim 16 wherein said glycol ether solvent comprises (i) di(propylene)glycol-tertiary-butyl ether, di(propylene)glycol-n-butyl ether, or a mixture thereof; and (ii) optionally di(oxypropylene)glycol, di(oxyethylene)glycol, or mixture thereof.

18. The composition of claim 1 wherein said at least one hydrophobic material solute comprises a stearate, an oleate, a naturally occurring oil, a laurate, a palmitate, a myristic ester, a linoleic ester, or a salt or a mixture thereof; and said glycol ether solvent comprises (i) an oxyalkylene glycol; (ii) an oxyalkylene ether adduct of an alcohol, glycol, or glycerol; or (iii) mixture thereof.

19. The composition of claim 1 wherein said at least one hydrophobic material comprises butyl stearate and butyl oleate, and said at least one glycol ether solvent comprises (i) di(oxypropylene)glycol-t-butyl ether, di(oxypropylene)glycol-n-butyl ether, or a mixture thereof; and optionally (ii) optionally di(oxypropylene)glycol, di(oxyethylene)glycol, or mixture thereof.

20. The composition of claim 15 wherein said at least one hydrophobic material is a dicarboxylic acid or salt having the formula $R^2OOC-C(R^1)(H)-(CH_2)_n-COOR^3$ wherein R^1 is a C_{12} to C_{18} alkyl or alkylene group; R^2 and R^3 are hydrogen or a cation, and "n" is an integer from 1 to 6.

21. The composition of claim 1 wherein said at least one solvent is operative to detrain air in hydratable cementitious compositions.

22. The composition of claim 1 further comprising at least one comb polymer superplasticizer.

23. The composition of claim 22 wherein said at least one comb polymer superplasticizer comprises poly(oxyalkylene) groups, and said comb polymer superplasticizer comprises water in an amount of 0-30% by total volume of said composition.

24. The composition of claim 1 further comprising water in an amount not exceeding 5% by total volume of said composition.

25. The composition of claim 1 which is devoid of a surfactant.

26. The composition of claim 1 which is devoid of an air entraining metal fatty acid.

27. Method for modifying a cementitious material comprising combining with a hydratable cementitious binder the composition of claim 1.

28. A cementitious material containing the composition of claim 1.

29. The composition of claim 1 wherein said at least one hydrophobic material is tetrapropenyl butandiodic acid.