

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
13 September 2001 (13.09.2001)

PCT

(10) International Publication Number
WO 01/66620 A2

(51) International Patent Classification⁷: **C08G 75/00**

(21) International Application Number: PCT/US01/06314

(22) International Filing Date: 28 February 2001 (28.02.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/186,864 3 March 2000 (03.03.2000) US
09/794,523 27 February 2001 (27.02.2001) US

(71) Applicant: **BP CORPORATION NORTH AMERICA INC.** [US/US]; 200 East Randolph Drive, MC 2207A, Chicago, IL 60601 (US).

(72) Inventor: **SCHWAB, Thomas, H.**; 6325 Buckingham Place, Cumming, GA 30040 (US).

(74) Agent: **NEMO, Thomas, E.**; BP Amoco Corporation, Law Department, 200 East Randolph Drive, MC 2207A, Chicago, IL 60601 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **LOW COLOR POLY(BIPHENYL ETHER SULFONE) AND IMPROVED PROCESS FOR THE PREPARATION THEREOF**

(57) Abstract: Improved carbonate method for producing poly(biphenyl ether sulfones) having a low color, the improvement being the use of small particle size anhydrous potassium carbonate. The resulting poly(biphenyl ether sulfones) are significantly improved in color.

WO 01/66620 A2