10 Mar 03

20030011400

162162

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau

(43) International Publication Date
21 March 2002 (21.03.2002)

PCT

(10) International Publication Number
WO 02/23602 A1

(51) International Patent Classification[7]: H01L 21/027, 21/3213

(21) International Application Number: PCT/US01/28568

(22) International Filing Date:
12 September 2001 (12.09.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/660,354 12 September 2000 (12.09.2000) US

(71) Applicant: ECO-SNOW SYSTEMS, INC. [US/US]; 4935 A Southfront Road, Livermore, CA 94550 (US).

(72) Inventor: BOWERS, Charles, W.; 1632 Scenic Avenue, Livermore, CA 94550 (US).

(74) Agents: PEDERSEN, Ken, J. et al.; Pedersen and Company, PLLC, 1410 North 28th Street, Boise, ID 83703 (US).


(81) Designated States *(national)*: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States *(regional)*: ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:
— *with international search report*
— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD FOR SELECTIVE METAL FILM LAYER REMOVAL USING CARBON DIOXIDE JET SPRAY



(57) Abstract: A method for the selective removal of the metal film layer (14) accumulated upon a photoresist layer (10) during processing of substrates using a stream of carbon dioxide spray (20) without disturbing conductor portions is provided. A constant stream (20) of high pressure CO_2 snow is applied to the metal film layer thereby rapidly cooling the metal layer on top of said resist layer causing it to shrink rapidly, and to debond, and peel from the photoresist layer underneath. The temperature of the substrate is raised and maintained at significantly higher than room temperature. Continuing the application of the CO_2 spray causes thermal shock to the photoresist under the metalized layer causing large cracks in the remaining metal layer portions, said cracks typically including at least one loose metal edge. The CO_2 spray is continually applied to the cracks thereby peeling away the remaining metal portions, leaving the exposed photoresist and underlying surface features. Preferably, continued treatment of the surface with CO_2 snow particals erodes a surface layer of the photoresist and heavily cross-linked layers created during the metalization process. After the metal layer and the surface layer of the photoresist are removed, a simple chemical strip, such as acetone, completely removes all the remaining resist, leaving the wafer with undamaged conductor portions.

WO 02/23602 A1

ACTION