

**PLASTIC PALLET WITH SLEEVED REINFORCING RODS AND
ASSOCIATED METHOD FOR MAKING THE SAME**

Field of the Invention

[0001] The present invention relates to the field of pallets useful in material handling, and more particularly, to a multi-piece plastic pallet designed for use with forklift equipment.

Background of the Invention

[0002] Pallets are customarily used to transport and store goods. A pallet typically includes an upper deck and a lower deck separated by support blocks. Pallets have traditionally been formed of wood. While advantageous in terms of cost, wood pallets have many disadvantages. For example, they are subject to breakage and are therefore reusable only over a short period of time. Wooden pallets are also difficult to maintain in a sanitary condition, thereby limiting their usability in applications where sanitation is important, such as in food handling applications.

[0003] With the growth of the plastics industry a wide variety of plastics have been investigated to determine their suitability for use in producing pallets. Plastic pallets can easily be molded and are stronger and lighter weight than wooden pallets. They can also be made with recyclable materials. Furthermore, plastic pallets are more durable than wooden pallets.

[0004] To increase the durability of plastic pallets, reinforcing elements or rods have been used. For example, U.S. Patent No. 6,199,488 discloses a reinforced plastic pallet comprising an upper deck formed of a plastic material having a first coefficient of thermal expansion, and a lower deck formed of a plastic material having substantially the first

coefficient of thermal expansion. The lower deck includes a plurality of channels formed in its upper surface, and a plurality of reinforcing elements having a second coefficient of thermal expansion different from the first degree of expansion are in the plurality of channels. The channels are provided with retainers to retain the reinforcing elements therein.

[0005] U.S Patent No. 5,868,080 discloses a reinforced plastic pallet with reinforcing rods. At least some of the reinforcing rods have an exposed surface at a top surface of the pallet. In addition to functioning as a reinforcing member, the exposed surfaces of the reinforcing rods comprise an anti-skid surface for maintaining positioning of a payload on the pallet.

[0006] Yet another approach to increase the durability of plastic pallets is disclosed in U.S. Patent No. 4,735,154. The '154 patent provides a reinforced loading pallet comprising two essentially rectangular matching panels one superposed over the other, with each panel having a rigid frame including ties equipped with hollow, polygonal feet arranged at four outer corners of the frame. At least some of the ties in at least one of the frames are provided with channels, with at least some of the channels intersecting in a single plane. Rods are inserted into the channels for reinforcing the pallet.

[0007] While plastic pallets offer several advantages over wood pallets, there is still a demand to increase durability and strength of plastic pallets.

Summary of the Invention

[0008] In view of the foregoing background, an object of the present invention is to increase the durability of plastic pallets.

[0009] This and other objects, advantages and features in accordance with the present invention are to provide a plastic pallet comprising an upper and lower deck. A plurality of first joining members may project downwardly from the upper deck, with each first joining member including an outer sleeve. A plurality of second joining members may project upwardly from the lower deck, with each second joining

member including an inner sleeve. At least one of the upper and lower decks may include a plurality of channels between top and bottom surfaces thereof, with each channel extending from a side edge to an opposing side edge of the corresponding deck.

[0010] A plurality of sleeved reinforcing rods may be in the plurality of channels. Each sleeved reinforcing rod may comprise a reinforcing rod having opposing ends and side surfaces therebetween, and a sleeve enclosing the side surfaces of the reinforcing rod. There is preferably relative movement between the sleeve and the reinforcing rod. The inner sleeves of the second joining may members receive the outer sleeves of the first joining members to define support blocks joining the upper and lower decks.

[0011] The channels may be in the lower deck only, in the upper deck only, or in both the upper and lower decks. When the sleeved reinforcing rods are in both decks, the sleeved reinforcing rods in the upper deck may be orthogonal to the sleeved reinforcing rods in the lower deck. All of the sleeved reinforcing rods in a same deck may be co-planar and parallel to one another.

[0012] The sleeved reinforcing rods are inserted into upper and/or lower deck molds before the upper and lower decks are formed. The sleeved reinforcing rods are thus insert molded. Plastic pallet manufacturers typically add reinforcing rods to a pallet after the pallet is formed. This requires the pallet to be molded first, and then add the reinforcing rods. In accordance with the present invention, the sleeved reinforcing rods are inserted into the pallet mold.

[0013] The plastic of the sleeve may have a melting point that is slightly higher than the melting point of the plastic used to form the upper and lower decks. As a result, the outside surface of the sleeves will partially melt or bond to the plastic of the upper and lower decks while still allowing movement of the reinforcing rods therein. Alternatively, the melting point of the sleeve may be the same as the melting point of the upper and lower decks, but cooling characteristics of the molten plastic during manufacturing may still result in the outside surface of the sleeves

partially melting or bonding to the plastic of the upper and lower decks layers without melting down to the reinforcing rods.

[0014] Each reinforcing rod may be hollow so that an opening extends between the opposing open ends thereof. The plastic pallet may further comprise a plurality of end caps inserted into the open ends of the reinforcing rods. Each reinforcing rod may comprise fluorine-containing polymers to assist with the relative movement with its sleeve.

[0015] The upper deck may further include a plurality of snap-pin openings, with each outer sleeve projecting downwardly from the upper deck surrounding a respective snap-pin opening. Each second joining member projecting upwardly from the lower deck may include a snap-pin receiving cavity positioned therein. Snap-pins may be inserted may be into the snap-pin openings in the upper deck, with each snap-pin extending through the snap-pin receiving cavity for engaging a backside of the inner sleeve associated therewith.

[0016] Another aspect is directed to a method for making a pallet as described above. The method may comprise forming a plurality of sleeved reinforcing rods, with each sleeved reinforcing rod comprising a reinforcing rod having opposing ends and side surfaces therebetween, and a sleeve enclosing the side surfaces of the reinforcing rod. There is relative movement between the sleeve and the reinforcing rod. The method may further comprise providing respective molds for the upper and lower decks, and positioning the sleeved reinforcing rods in the respective decks. The upper and lower decks including their respective first and second joining members are formed. The inner sleeves of the second joining members may be positioned for receiving the outer sleeves of the first joining members to define the support blocks joining the upper and lower decks.

Brief Description of the Drawings

[0017] FIG. 1 is a top perspective view of an assembled pallet in accordance with the present invention.

[0018] FIG. 2 is a bottom perspective view of the pallet shown in FIG. 1.

[0019] FIG. 3 is a bottom perspective view of the upper deck of the pallet shown in FIG. 1.

[0020] FIG. 4 is a top perspective view of the lower deck of the pallet shown in FIG. 1.

[0021] FIG. 5 is a perspective view of a snap-pin used within each support block in accordance with the present invention.

[0022] FIG. 6 is a top view of the snap-pin shown in FIG. 5.

[0023] FIG. 7 is a partial cross-sectional side view of a pallet illustrating a snap-pin within a support block in accordance with the present invention.

[0024] FIG. 8 is a perspective view of the pallet unassembled in accordance with the present invention.

[0025] FIG. 9 is a perspective view of the pallet shown in FIG. 8 assembled.

[0026] FIG. 10 is a side view of the pallet illustrating positioning of the channels in the upper deck in accordance with the present invention.

[0027] FIG. 11 is a side view of the pallet illustrating positioning of the channels in the lower upper deck in accordance with the present invention.

[0028] FIG. 12 is a cross-sectional view of a sleeved reinforcing rod in accordance with the present invention.

[0029] FIG. 13 is a flow chart illustrating a method for making a pallet in accordance with the present invention.

Detailed Description of the Preferred Embodiments

[0030] The present invention will now be described more fully hereinafter with reference to the accompanying drawings, in which preferred embodiments of the invention are shown. This invention may, however, be embodied in many different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in

the art. Like numbers refer to like elements throughout, and prime notation is used to indicate similar elements in alternative embodiments.

[0031] FIGS. 1-4 illustrate top and bottom perspective views of a pallet 10 having upper and lower decks 12, 14 that are held together using snap-pins 16. The upper deck 12 is also known as the cargo layer, and the lower deck 14 is also known as the base layer.

[0032] The upper deck 12 includes a plurality of first joining members that project downwardly from the upper deck, with each first joining member including an outer sleeve 40. The lower deck 14 includes a plurality of second joining members that project upwardly from the lower deck, with each second joining member including an inner sleeve 42. The inner sleeves 42 of the second joining members receive the outer sleeves 40 of the first joining members to define support blocks 18, 18a joining the upper and lower decks 12, 14.

[0033] The support blocks 18, 18a define a space 20 between the upper and lower decks 12, 14 for receiving at least one lifting member, such as a tine of a pallet jack. An advantage of the snap-pins 16 is that they act as fusible links in the event a separation force is applied between the upper and lower decks 12, 14 of the pallet 10. This separation force may result when the wheels of the pallet jack are resting on the lower layer 14, and the tines extending from the pallet jack are lifted upwards. This causes the upper deck 12 to become separated from the support blocks 18, 18a. The tabs 50 on the fusible links 16 will snap or break when the separation force becomes too excessive. Consequently, instead of replacing the entire upper deck 12, the snap-pins 16 with the broken tabs 50 are replaced.

[0034] As will be discussed in greater detail below, the support blocks 18, 18a are formed by the outer and inner sleeves 40, 42 extending from the respective upper and lower decks 12, 14. The outer and inner sleeves 40, 42 are molded as part of their respective upper and lower decks 12, 14. However, the upper and lower decks 12, 14 are separately molded.

[0035] The upper deck 12 includes a generally flat, planar surface

having a plurality of holes **22** extending therethrough. Likewise, the lower deck **14** includes a generally flat, planar surface having a plurality of holes **23** extending therethrough. The holes **22**, **23** provide several benefits including a reduced surface area of the upper and lower decks **12**, **14**, increased air circulation for items placed on the upper deck, and a reduced weight of the pallet, for example. An example plastic pallet with upper and lower decks is disclosed in U.S. published patent application number 2007/0256609. This patent is assigned to the current assignee of the present invention, and is incorporated herein by reference in its entirety.

[0036] The upper deck **12** may include an outer perimeter **24** of the planar surface that does not include any holes **12**. This area may be about 3 to 5 inches wide, for example. The lower deck **14** has a perimeter shape that substantially matches the perimeter shape of the upper deck **12**. The lower deck **14** may include a rectangular perimeter shape having cross members **26**, **28** that intersect a center portion of each side of the rectangular perimeter, midway between the corners of the pallet **10**.

[0037] The upper and lower decks **12**, **14** may be molded from thermoplastic or other polymer materials, including high density polyethylene (HDPE), polypropylene (PP), among other polymer materials. As may be appreciated by those skilled in the art, the polymer materials may be filled or unfilled and/or may include particulate or fibrous, natural or synthetic materials, among other features. For example, unfilled HDPE may provide improved impact strength, PP having strengtheners (i.e., long glass fibers) may provide improved structural properties, and unfilled PP with random copolymers may provide improved reinforcement qualities.

[0038] The upper and lower decks **12**, **14** may be molded from different thermoplastics or polymer materials. For example, the upper deck **12** may be molded from a first type of thermoplastic or polymer material, while the lower deck **12** may be molded from a second type of thermoplastic or polymer material. According to alternative embodiments, all or a portion of the upper and lower decks **12**, **14** may be constructed from materials other than plastic, such as wood and/or metal, for example.

[0039] The illustrated pallet **10** is substantially square-shaped. An

example size of the pallet **10** is 48 inches by 48 inches, for example. As readily appreciated by those skilled in the art, the pallet **10** may also be formed with other rectangular shapes, such as 40 inches by 48 inches, for example. The pallet **10** may include rounded corners/edges **30** along the perimeter thereof. Rounded corners/edges **30** help to reduce and/or deflect damage during impact with the tines of a forklift, as well as providing an improved aesthetic appearance.

[0040] The illustrated pallet **10** includes a plurality of support blocks **18, 18a** that are provided to join the upper and lower decks **12, 14** together as well as providing separation so that the tines of a pallet jack can be inserted therebetween. For example, the illustrated pallet **10** includes nine support blocks **18, 18a** that are located at the corners of the pallet, as well as between the corners of the pallet along the outer edges of the pallet. A support block **18a** is also provided in a center of the pallet **10** at the intersection of cross members **26, 28** in the lower deck **14**.

[0041] Each support block **18, 18a** is defined by an outer sleeve **40** projecting downwardly from the upper deck **12** and an inner sleeve **42** projecting upwardly from the lower deck **14**. The outer and inner sleeves **40, 42** are molded with their respective upper and lower decks **12, 14**. The outer and inner sleeves **40, 42** are sized so that they overlap one another when joined together. The shapes of the outer and inner sleeves **40, 42** are not limited to any particular shape. The outer and inner sleeves **40, 42** may be square-shaped, triangular-shaped, oval-shaped or cross-shaped, for example. The edges of the outer sleeves **40** may be rounded.

[0042] The upper deck **12** includes a plurality of snap-pin openings for receiving the snap-pins **16**. Each outer sleeve **40** surrounds a respective snap-pin opening. The lower deck **14** includes a snap-pin receiving cavity **44** positioned within each inner sleeve **42**. A plurality of radial ribs **43** extending between the snap-pin receiving cavity **44** and the inner sleeve **42**.

[0043] An advantage of the support blocks **18, 18a** is that the impact energy from contact with the tines of the forklift can be dissipated among the following elements: the outer sleeve **40**, the inner sleeve **42**, the radial

ribs **43** and the cylindrical core defined by the snap-pin receiving cavity **44** in the inner sleeve. The fork tines strike the outer sleeve **40** first, which absorbs most of the impact energy. The impact energy may then be transmitted to the inner sleeve **42**, which also absorbs some of the impact energy. More absorption of the impact energy takes place at the radial ribs **43**. The remaining impact energy reaches the snap-pin receiving cavity **44** for dissipation.

[0044] Each snap-pin **16** includes a head **46**, a body **48** and spaced apart tips **50**, as best illustrated in FIG. 5. The head **46** is for engaging a snap-pin opening in the upper deck **12**. The head **46** of each snap-pin **16** may be shaped to include spaced apart straight edges **49**, as illustrated in FIG. 6. Each snap-pin opening in the upper deck **12** is correspondingly shaped the same. This helps to hold the snap-pins **16** in place. The snap-pins **16** are typically inserted into the pallet **10** after the upper and lower decks **12**, **14** have been joined together to form the support blocks **18**, **18a**.

[0045] The spaced apart tips **50** extend through the snap-pin receiving cavity **44** for engaging a backside **50** of the inner sleeve, as best illustrated in FIG. 7. The snap-pin receiving cavity **44** does not extend all the way from the top of the inner sleeve **42** to the bottom of the lower deck **14**. This is to allow room for the tabs **50** on the snap-pin **16** to clear and engage the backside **60** of the inner sleeve **42**.

[0046] Even though the upper and lower decks **12**, **14** are separated in FIGS. 3 and 4, the snap-pins **16** are positioned accordingly for illustration purposes. As illustrated in FIG. 3, the snap-pins **16** extend within and past the outer sleeves **40**. As illustrated in FIG. 4, the heads **46** of the snap-pins **16** are raised above the inner sleeve **42** and the snap-pin receiving cavities **44** without the lower deck **14** in place. This allows clearance for the head **46** of each snap-pin **16** to engage a snap-pin opening in the upper deck **12**, while the spaced apart tips **50** extend through the snap-pin receiving cavity **44** for engaging a backside **60** of the inner sleeve **42** associated therewith.

[0047] The spaced apart tips **50** of each snap-pin **16** resiliently extend outwards from the body **48** after having passed through the snap-pin receiving cavity **44** for engaging the backside **50** of the inner sleeve **42**

associated therewith. The spaced apart tips 50 of each snap-pin 16 may be angled to facilitate insertion thereof through the snap-pin receiving cavity 44. The spaced apart tips 50 of each snap-pin comprise a respective lip 51 for engaging the backside of the inner sleeve. The respective lips 51 are configured to break off based on an excessive separation force applied between the upper and lower decks 12, 14. The snap-pins 16 are also formed out of plastic. Alternatively, the snap-pins 16 may be formed out any of the materials used to form the upper and lower decks 12, 14 as discussed in detail above.

[0048] Another aspect is directed to improving the durability of the pallet. This is accomplished by inserting sleeved reinforcing rods 80' into the upper and/or lower molds of the pallet 10' for the respective upper and/or lower decks 12', 14'. As readily appreciated by those skilled in the art, the sleeved reinforcing rods 80' are insert molded.

[0049] As best illustrated by the exploded view of the pallet 10' in FIG. 8, four sleeved reinforcing rods 80' are used in the lower deck 14', and four sleeved reinforcing rods 80' are used in the upper deck 12'. The actual number of sleeved reinforcing rods 80' will vary depending on the size of the pallet 10' and its intended use, as well as on the actual number of support blocks 18', 18a'. As noted above, the sleeved reinforcing rods 80' may be in the lower deck 14' only, in the upper deck 12' only, or in both the upper and lower decks. For illustration purposes, both the upper and lower decks 12', 14' include sleeved reinforcing rods 80'. The assembled pallet 10' is illustrated in FIG. 9.

[0050] The upper deck 12' includes channels 92 between its top and bottom surfaces 94', 96', as illustrated in FIG. 10. The upper surface of the sleeved reinforcing rod 80' is below the top surface 94' of the upper deck 12', and is above the bottom surface 96' of the upper deck 12'. Each channel 92' extends from a side edge to an opposing side edge of the upper deck 12'.

[0051] Similarly, the lower deck 14' includes channels 102' between its top and bottom surfaces 104', 106', as illustrated in FIG. 11. The upper surface of the sleeved reinforcing rod 80' is below the top surface 104' of

the lower deck 14', and is above the bottom surface 106' of the lower deck 14'. Each channel 102' extends from a side edge to an opposing side edge of the lower deck 12'.

[0052] The illustrated channels 92', 102' are positioned so that they are on top or bottom of the support blocks 18', 18a'. The center support blocks 18a' may be wider than the other support blocks 18' so that the two sleeved reinforcing rods 80' in the channels 92' in the center portion of the upper deck 12' and the two sleeved reinforcing rods 80' in the channels 102' in the center portion of the lower deck 14' can each be supported by a support block yet still provide strength to the upper and lower decks. Alternatively, all of the support blocks 18', 18a' are the same size.

[0053] Referring now to FIG. 12, a sleeved reinforcing rod 80' comprises a reinforcing rod 82' having opposing ends and side surfaces therebetween, and a sleeve 84' enclosing the side surfaces of the reinforcing rod. The ends of the reinforcing rod 82' are exposed. The sleeved reinforcing rod 80' allows relative movement between the sleeve 84' and the reinforcing rod 82'.

[0054] The reinforcing rod 82' is made of metal, for example, and the sleeve 84' is made of plastic, for example. The metal may comprise steel. However, other types of metals may be used. Alternatively, the reinforcing rod 82' may comprise non-metal materials, such as reinforced fiberglass, for example.

[0055] As the pallet 10' is flexed or as the metal contracts, relative movement is needed between the reinforcing rod 82' and the plastic sleeve 84'. Consequently, the reinforcing rod 82' is simply not coated in plastic. Otherwise, the local plastic around the reinforcing rod 82' can be over stressed, resulting in cracks.

[0056] The illustrated reinforcing rod 82' has a rectangular shape, and is hollow so that an opening extends between the opposing ends thereof. In one embodiment, the sleeve 84' is extruded over the reinforcing rod 82' to form the sleeved reinforcing rod 80'. The shape of the reinforcing rod 82' may vary, and may even be filled in other embodiments. To assist with the relative movement between the reinforcing rod 82' and

the sleeve 84', the reinforcing rod may comprise fluorine-containing polymers. Fluorine-containing polymers are also known as Teflon®, and includes the following: polytetrafluoroethylene (PTFE), perfluoroalkoxy (PFA) and fluorinated ethylene propylene (FEP).

[0057] Plastic pallet manufacturers typically add reinforcing rods to a pallet after the pallet is formed, as is the case for the prior art patents discussed in the background section. This requires the pallet to be molded first, and then add the reinforcing rods. In sharp contrast, the sleeved reinforcing rods 80' are inserted into the pallet mold before the upper and lower decks 12', 14' are formed therein.

[0058] The plastic of the sleeve 84' has a melting point that is slightly higher than the melting point of the plastic used to form the upper and lower decks 12', 14'. As a result, the outside surface of the sleeves 84' will partially melt or bond to the plastic of the upper and lower decks 12', 14' while still allowing movement of the reinforcing rods 82' therein.

Alternatively, the melting point of the sleeve 64' is the same as the melting point of the upper and lower decks 12', 14', but cooling characteristics of the molten plastic during manufacturing still results in the outside surface of the sleeves 84' partially melting or bonding to the plastic of the upper and lower decks 12', 14' without melting down to the reinforcing rods 82'.

[0059] After the upper and lower decks 12', 14' have been formed with the sleeved reinforcing rods 80' therein, end caps 90' are used to enclose the ends of the reinforcing rods 82'. Alternatively, the ends of the sleeved reinforcing rods 80' may be closed as a result of being formed. If a plastic pallet 10' is to be recycled, , the ends of the sleeve 84' are punctured or the end caps 90' are removed so that the reinforcing rod 82' can be removed therefrom for use in another pallet.

[0060] The upper and lower decks 12', 14' include additional holes 71', 73' for exposing the sleeved reinforcing rods 80'. This also allows the sleeves 84' to be punctured from the side to help in removing the reinforcing rods 82' therefrom.

[0061] The illustrated pallet 10' further includes friction plugs 110' to prevent a load from sliding over the top surface 94' of the upper deck 12'.

The friction plugs **110'** are inserted through corresponding openings in the upper deck **12'** after the pallet **10'** has been formed.

[0062] Another aspect is directed to a method for making a pallet **10'** as described above. Referring now to the flow chart illustrated in FIG. 13, the method comprises from the start (Block **120**), forming at Block **122** a plurality of sleeved reinforcing rods **80'**, with each sleeved reinforcing rod comprising a reinforcing rod **82'** having opposing ends and side surfaces therebetween, and a sleeve **84'** enclosing the side surfaces of the reinforcing rod. There is relative movement between the sleeve **84'** and the reinforcing rod **82'**.

[0063] The method further comprises providing respective molds for the upper and lower decks **12'**, **14'** at Block **124**, and positioning the sleeved reinforcing rods **80'** in the respective decks at Block **126**. The upper and lower decks **12'**, **14'** including their respective first and second joining members **40'**, **42'** are formed at Block **128**. The inner sleeves of the second joining members **42'** are positioned at Block **130** for receiving the outer sleeves of the first joining members **40'** to define the support blocks **18'**, **18a'** joining the upper and lower decks **12'**, **14'**. The method ends at Block **132**.

[0064] Many modifications and other embodiments of the invention will come to the mind of one skilled in the art having the benefit of the teachings presented in the foregoing descriptions and the associated drawings. Therefore, it is understood that the invention is not to be limited to the specific embodiments disclosed, and that modifications and embodiments are intended to be included as readily appreciated by those skilled in the art.

THAT WHICH IS CLAIMED:

1. A pallet comprising:
an upper deck;
a plurality of first joining members that project downwardly from said upper deck, each first joining member including an outer sleeve;
a lower deck;
a plurality of second joining members that project upwardly from said lower deck, each second joining member including an inner sleeve;

at least one of said upper and lower decks including a plurality of channels between top and bottom surfaces thereof, each channel extending from a side edge to an opposing side edge of said corresponding deck;

a plurality of sleeved reinforcing rods in the plurality of channels, each sleeved reinforcing rod comprising
a reinforcing rod having opposing ends and side surfaces therebetween and
a sleeve enclosing the side surfaces of said reinforcing rod, with there being relative movement between said sleeve and said reinforcing rod; and
the inner sleeves of said plurality of second joining members receiving the outer sleeves of said plurality of first joining members to define a plurality of support blocks joining said upper and lower decks.

2. The pallet according to claim 1, wherein the plurality of channels is in both of said upper and lower decks.

3. The pallet according to claim 2, wherein said sleeved reinforcing rods in said upper deck are orthogonal to said sleeved reinforcing rods in said lower deck.

4. The pallet according to claim 1, wherein all of said sleeved reinforcing rods in said corresponding deck are co-planar and parallel to one another.

5. The pallet according to claim 1, wherein each reinforcing rod is hollow so that an opening extends between the opposing open ends thereof.

6. The pallet according to claim 5, further comprising a plurality of end caps inserted into the open ends of said plurality of sleeved reinforcing rods.

7. The pallet according to claim 1, wherein each reinforcing rod has a rectangular shape.

8. The pallet according to claim 1, wherein the at least one of said upper and lower decks including the plurality of channels comprises a material having a first melting point; and wherein each sleeve comprises a material having a second melting point higher than the first melting point.

9. The pallet according to claim 1, wherein each reinforcing rod comprises fluorine-containing polymers.

10. The pallet according to claim 1, wherein said upper deck includes a plurality of snap-pin openings, with each outer sleeve projecting downwardly from said upper deck surrounding a respective snap-pin opening; wherein each second joining member projecting upwardly from said lower deck including a snap-pin receiving cavity positioned therein; and further comprising a plurality of snap-pins inserted into the plurality of snap-in openings in said upper deck, with each snap-pin extending through the snap-pin receiving cavity for engaging a backside of the inner sleeve associated therewith.

11. The pallet according to claim 10, wherein each snap-pin comprises a head at one end thereof for engaging a snap-pin opening, and spaced apart tips at an opposite end thereof for extending through the snap-pin receiving cavity for engaging a backside of the inner sleeve associated therewith.

12. The pallet according to claim 11, wherein the spaced apart tips resiliently extend outwards from the snap-pin receiving cavity after having passed therethrough.

13. The pallet according to claim 12, wherein the spaced apart tips of each snap-pin are angled to facilitate insertion thereof through the snap-pin receiving cavity.

14. The pallet according to claim 11, wherein the spaced apart tips of each snap-pin comprise a respective lip for engaging the backside of the inner sleeve; and wherein the respective lips of each snap-pin are configured to break off based on a separation force applied between said upper and lower decks.

15. The pallet according to claim 1, wherein said upper and lower decks, said plurality of first and second joining members, and said sleeves comprise plastic.

16. A plastic pallet comprising:
an upper deck comprising plastic having a first melting point;
a plurality of first joining members that project downwardly from said upper deck, each first joining member including an outer sleeve;
a lower deck comprising plastic having the first melting point;
a plurality of second joining members that project upwardly from said lower deck, each second joining member including an inner sleeve;

at least one of said upper and lower decks including a plurality of channels between top and bottom surfaces thereof;
a plurality of sleeved reinforcing rods in the plurality of channels, each sleeved reinforcing rod comprising
a reinforcing rod having opposing ends and side surfaces therebetween, and
a sleeve enclosing the side surfaces of said reinforcing rod, with there being relative movement between said sleeve and said reinforcing rod, said sleeve comprising plastic having a second melting point higher than the first melting point; and
the inner sleeves of said plurality of second joining members receiving the outer sleeves of said plurality of first joining members to define a plurality of support blocks joining said upper and lower decks.

17. The plastic pallet according to claim 16, wherein the plurality of channels is in both of said upper and lower decks.

18. The plastic pallet according to claim 17, wherein said sleeved reinforcing rods in said upper deck are orthogonal to said sleeved reinforcing rods in said lower deck.

19. The pallet according to claim 16, wherein each reinforcing rod is hollow so that an opening extends between the opposing open ends thereof.

20. The plastic pallet according to claim 19, further comprising a plurality of end caps inserted into the open ends of said plurality of sleeved reinforcing rods.

21. The plastic pallet according to claim 16, wherein each reinforcing rod has a rectangular shape.

22. The plastic pallet according to claim 16, wherein each reinforcing rod comprises fluorine-containing polymers.

23. The plastic pallet according to claim 16, wherein said upper deck includes a plurality of snap-pin openings, with each outer sleeve projecting downwardly from said upper deck surrounding a respective snap-pin opening; wherein each second joining member projecting upwardly from said lower deck including a snap-pin receiving cavity positioned therein; and further comprising a plurality of snap-pins inserted into the plurality of snap-in openings in said upper deck, with each snap-pin extending through the snap-pin receiving cavity for engaging a backside of the inner sleeve associated therewith.

24. The plastic pallet according to claim 23, wherein each snap-pin comprises a head at one end thereof for engaging a snap-pin opening, and spaced apart tips at an opposite end thereof for extending through the snap-pin receiving cavity for engaging a backside of the inner sleeve associated therewith.

25. A method for making a pallet comprising an upper deck; a plurality of first joining members that project downwardly from the upper deck, each first joining member including an outer sleeve; a lower deck; a plurality of second joining members that project upwardly from the lower deck, each second joining member including an inner sleeve; at least one of the upper and lower decks including a plurality of channels between top and bottom surfaces thereof, the method comprising:

forming a plurality of sleeved reinforcing rods, each sleeved reinforcing rod comprising a reinforcing rod having opposing ends and side surfaces therebetween, and a sleeve enclosing the side surfaces of the reinforcing rod, with there being relative movement between the sleeve and the reinforcing rod;

providing respective molds for the upper and lower decks;

positioning the plurality of sleeved reinforcing rods in at least one of the deck molds corresponding to the at least one upper and lower deck including the plurality of channels;

forming the upper and lower decks including their respective first and second joining members; and

positioning the inner sleeves of the plurality of second joining members for receiving the outer sleeves of the plurality of first joining members to define a plurality of support blocks joining the upper and lower decks.

26. The method according to claim 25, wherein the plurality of channels is in both of the upper and lower decks so that the plurality of sleeved reinforcing rods are positioned in both of the upper and lower deck molds.

27. The method according to claim 26, wherein the sleeved reinforcing rods in the upper deck are orthogonal to the sleeved reinforcing rods in the lower deck.

28. The method according to claim 25, wherein each reinforcing rod is hollow so that an opening extends between the opposing open ends thereof; and further comprising inserting a plurality of end caps into the open ends of the plurality of sleeved reinforcing rods.

29. The method according to claim 25, wherein forming each sleeved reinforcing rod comprises extruding the sleeve over the reinforcing rod.

30. The method according to claim 25, wherein the at least one of the upper and lower decks including the plurality of channels comprises a material having a first melting point; and wherein each sleeve comprises a material having a second melting point higher than the first melting point.

31. The method according to claim 25, wherein each reinforcing rod comprises fluorine-containing polymers.

32. The method according to claim 25, wherein the upper deck includes a plurality of snap-pin openings, with each outer sleeve projecting downwardly from the upper deck surrounding a respective snap-pin opening; wherein each second joining member projecting upwardly from the lower deck including a snap-pin receiving cavity positioned therein; and further comprising inserting a plurality of snap-pins into the plurality of snap-in openings in the upper deck, with each snap-pin extending through the snap-pin receiving cavity for engaging a backside of the inner sleeve associated therewith.

33. The method according to claim 25, wherein the upper and lower decks, the plurality of first and second joining members, and the sleeves comprise plastic.