
CLAIMS

1. An elastomeric composition comprising, per 100 parts by weight of rubber (phr): 100 phr of a diene elastomer; 0 to 80 phr of processing oil; 0 to 80 phr of a hydrocarbon resin; 60 to 140 phr of filler; a curative agent; and 5 to 30 phr of a silane functionalized propylene-ethylene-diene terpolymer comprising from 2 to 40 wt % of ethylene and C_4-C_{20} α-olefins derived units, and from 0.5 to 10 wt % of diene derived units,


wherein the silane functionalized propylene-ethylene-diene terpolymer is functionalized by a silane coupling agent selected from the group consisting of

[Chemical formula 2]




,

[Chemical formula 4]



, and

[Chemical formula 5]



.

2. The elastomeric composition of any preceding claim, wherein the propylene-ethylene-diene terpolymer contains from 0.5 wt % to 10 wt % ethylidene norbornene based on the terpolymer.

3. The elastomeric composition of any preceding claim, wherein the propylene-ethylene-diene terpolymer contains from 2 wt % to 20 wt % ethylene based on the terpolymer.

4. The elastomeric composition of any preceding claim, wherein the propylene-ethylene-diene terpolymer contains 60 wt % to 95 wt % propylene based on the terpolymer.

5. The elastomeric composition of any preceding claim, wherein the melt flow rate (MFR) at 2.16 kg weight at 230°C of the propylene-ethylene-diene terpolymer is from 0.2 to 10 g/10 min.

6. The elastomeric composition of any preceding claim, wherein the diene elastomer is a styrene-butadiene rubber, a functionalized diene rubber, a styrenic copolymer, a polybutadiene, natural rubber, a polyisoprene, a butadiene copolymer, an isoprene copolymer or blends thereof.

7. A tire tread composition comprising the elastomeric composition of any preceding claim, wherein the tire tread composition further comprises a second silane coupling agent.

8. A method of making the elastomeric composition of claims 1-6, comprising the steps of:

(a) blending polybutadiene, styrene/butadiene copolymer, natural rubber or polyisoprene, the filler, the processing oil, and the silane functionalized propylene-ethylene diene terpolymer to form a first component at a temperature in the range from 110^{o}C to 200^{o}C;

(b) blending the curative agent with the first component at a temperature in the range of less than 110^{o}C; and

(c) recovering the elastomeric composition.

9. A method of balancing the wet traction performance and rolling resistance in a tire tread comprising the elastomeric composition of claims 1-6:

(a) combining at least the filler, polybutadiene, styrene/butadiene copolymer, natural rubber or polyisoprene and the curative agent with one or more of the silane functionalized propylene-ethylene-diene terpolymers to form the tire tread;

(b) effecting a cure of the components to form a tire tread; and

wherein the level of the silane functionalized propylene-ethylene-diene terpolymer(s) relative to the other components, and its comonomer content, can be varied to improve the balance of wet traction and rolling resistance of a tire tread.