

DESCRIPTION

PROCESS FOR PRODUCING A PARTICULATE COMPOSITION COMPRISING CRYSTALLINE ALPHA, ALPHA-TREHALOSE DI-HYDRATE

5

Technical Field

[0001]

The present invention relates to a process for producing a particulate composition containing crystalline α,α -trehalose dihydrate, particularly, to a process for producing a high-purity particulate composition containing crystalline α,α -trehalose dihydrate, which produces a particulate composition containing crystalline α,α -trehalose dihydrate from starch on an industrial scale and in a satisfactory yield through consistent steps, and to a particulate composition containing crystalline α,α -trehalose dihydrate obtained thereby.

15

Background Art

[0002]

20

25

Various methods have been conventionally known as processes for producing particulate compositions containing crystalline α,α -trehalose dihydrate (" α,α -trehalose" is abbreviated as "trehalose" throughout the specification, hereinafter). For example, Patent Literature 1 discloses a process for producing a particulate composition containing crystalline trehalose dihydrate by allowing β -amylase with or without a starch debranching enzyme to act on liquefied starch, allowing a maltose/trehalose converting enzyme to act on the resulting mixture to obtain a trehalose-containing saccharide

solution, appropriately purifying the saccharide solution, and crystallizing trehalose; and Patent Literature 2 discloses a process for producing a particulate composition containing crystalline trehalose dihydrate by allowing an
5 α -glycosyltrehalose-forming enzyme (another name "a non-reducing saccharide-forming enzyme") and a trehalose-releasing enzyme along with a starch debranching enzyme to act on liquefied starch, allowing glucoamylase to act on the resulting mixture to obtain a trehalose-containing
10 saccharide solution, appropriately purifying the saccharide solution, and crystallizing trehalose.

[0003]

Patent Literatures 3 and 4 disclose processes for producing particulate compositions containing crystalline
15 trehalose dihydrate, which increase the trehalose content in the above-identified trehalose-containing saccharide solution by modifying the process disclosed in Patent Literature 2, wherein a starch debranching enzyme and a cyclodextrin glucanotransferase (abbreviated as "CGTase",
20 hereinafter) are allowed to act on their substrates, with a combination use of an α -glycosyltrehalose-forming enzyme and a trehalose-releasing enzyme. Patent Literatures 5 and 6 disclose processes for producing particulate compositions containing crystalline trehalose dihydrate by allowing a
25 thermostable α -glycosyltrehalose-forming enzyme derived from a microorganism of the genus *Sulfolobus* or a thermostable α -glycosyltrehalose-forming enzyme and a thermostable trehalose-releasing enzyme to act on liquefied starch to obtain a trehalose-containing saccharide solution, appropriately

purifying the solution, and crystallizing trehalose.

[0004]

Among these conventional production processes, in the case of combinationally using the enzymes disclosed in Patent Literatures 3 and 4, a trehalose-containing saccharide solution with a trehalose content of over 80% by weight, on a dry solid basis (d.s.b.), can be easily prepared from liquefied starch as a material with only enzymatic reactions without passing through a fractionation step by column chromatography, and has the merit that the trehalose-containing saccharide solution thus prepared has a satisfactory crystallizability of trehalose because the saccharide composition thereof is composed of almost glucose except for trehalose. Therefore, according to the above production processes disclosed in Patent Literatures 3 and 4, a relatively high-purity particulate composition containing crystalline trehalose dihydrate can be produced by precipitating crystalline trehalose dihydrate from the above trehalose-containing saccharide solution and subjecting the resulting mixture to a solid-liquid separation method by centrifugation to collect the crystals.

[0005]

Particularly, in the above production processes disclosed in Patent Literatures 3 and 4, when the enzymes derived from microorganisms of the genus *Arthrobacter* are used as the α -glycosyltrehalose-forming enzyme and the trehalose-releasing enzyme, such enzymes can be distinctly advantageously used in producing a particulate composition containing crystalline trehalose dihydrate on an industrial

scale because the above microorganisms can grow relatively fast and also have a high productivity of the above enzymes. Thus, the applicant of the present invention has now been producing "TREHA", a product name of a high-purity particulate composition containing crystalline trehalose dihydrate with a purity of at least 98.0% by weight as a product standard, commercialized by Hayashibara Co., Ltd., Okayama, Japan (called "a food-grade powder containing crystalline trehalose dihydrate", hereinafter), by using the enzymes derived from a microorganism of the genus *Arthrobacter* as the α -glycosyltrehalose-forming enzyme and the trehalose-releasing enzyme, and by the processes disclosed in Patent Literatures 3 and 4; and commercializing "TREHA" mainly as a material for food products, cosmetics, etc. At present, according to the above production process, however, the trehalose content in the trehalose-containing saccharide solution obtained by the enzymatic reactions remains at around about 85% by weight, d.s.b., and the trehalose yield against starch does not reach 40% by weight even when the enzymatic reaction conditions are variously optimized.

[0006]

While, Non-Patent Literatures 1 and 2 disclose that a trehalose-containing saccharide solution with a trehalose content of about 87% by weight, d.s.b., is obtained by either allowing recombinant enzymes, which have been prepared by allowing respective genes for a thermostable α -glycosyltrehalose-forming enzyme, thermostable trehalose-releasing enzyme, and thermostable isoamylase derived from a microorganism of the species *Sulfolobus*

solfataricus to express in *Escherichia coli* (*E. coli*), or allowing mutant enzymes, which have been constructed by additionally introducing site specific mutations into the above genes, to act on soluble starch.

5 [0007]

However, since the soluble starch used as a material in Non-Patent Literatures 1 and 2, which is prepared by treating starch with an acid to remove amorphous parts in starch granules, is a quite specific and expensive material, the use of such soluble starch as a material for industrial scale production of a particulate composition containing crystalline trehalose dihydrate is costly, unlikely acceptable, even if an enzymatic reaction solution with an increased trehalose content is obtained. When the recombinant enzymes or mutant enzymes disclosed in Non-Patent Literatures 1 and 2 are allowed to act on not soluble starch but liquefied starch used in an industrial scale production, the trehalose content in the trehalose-containing saccharide solution obtained by the enzymatic reactions is understandably as below as about 87% by weight and is still remained at the level of about 85% by weight, and it cannot be expected to improve the yield of a particulate composition containing crystalline trehalose dihydrate against starch more than those of the current production processes.

25 [0008]

Incidentally, if only the trehalose content in a trehalose-containing saccharide solution is merely increased to 86.0% by weight or more, a column fractionation using column chromatography can possibly be applied to the

trehalose-containing saccharide solution to obtain a trehalose-rich fraction. When such a column fractionation is employed, the more the steps, the higher the production cost becomes, and moreover, an inevitable loss of trehalose contained in fractions other than collected fractions rich in trehalose may be induced and it cannot be avoided the reduction of the yeild of a particulate composition containing crystalline trehalose dihydrate against starch by a large margin even if a trehalose-containing saccharide solution with a trehalose content of over 86.0% by weight, d.s.b., is obtained by the above column fractionation in such a manner of preparing a particulate composition containing crystalline trehalose dihydrate by collecting crystalline trehalose dihydrate precipitated from such a saccharide solution.

[0009]

If only to simply increase the production yield against starch, the following so called total sugar method can be employed in place of employing the solid-liquid separation method for collecting precipitated crystals by centrifugation; a massecuite containing precipitated crystals is placed in a container and allowed to crystallize/solidify the total contents and pulverize the resultant to obtain a powder, or a massecuite is spray-dried to obtain a powder. However, in the case of such total sugar method, since even concomitants, which are characteristic to the method used, such as glucose contained in a massecuite are pulverized together with crystallized trehalose, the trehalose content in the resulting particulate composition containing crystalline trehalose dihydrate is not increased to a level more than the

trehalose content in the massecuite, and a high-purity particulate composition containing crystalline trehalose dihydrate could not be obtained as a disadvantage.

[0010]

5 Starch is a material that is now relatively abundant and easily available at a low price, however, it is not an inexhaustible substance and is limited in its total amount produced annually by humans on the earth. On the other hand, starch is extensively used and it has recently been used
10 as a new fuel material for bioethanol, etc., as a recent increased demand for clean energy in addition to conventional uses for industries, food products, feeds, and food materials. Under these circumstances, the improvement of the production yield against starch for a product or a particulate composition
15 containing crystalline trehalose dihydrate is quite important in terms of effective utilization of limited resources.

Prior Art Literature

Patent Literature

[0011]

20 [Patent Literature 1] Japanese Patent Kokai No.
170977/95

 [Patent Literature 2] Japanese Patent Kokai No.
213283/95

25 [Patent Literature 3] Japanese Patent Kokai No.
73504/96

 [Patent Literature 4] Japanese Patent Kokai No.
2000-228980

 [Patent Literature 5] Japanese Patent Kokai No.
66188/96

[Patent Literature 6] Japanese Patent Kokai No.
66187/96

Non-Patent Literature

[0012]

5 [Non-Patent Literature 1] *Journal of Agricultural
and Food Chemistry*, Fang et al., Vol. 55, pp. 5588-5594, 2007

[Non-Patent Literature 2] *Journal of Agricultural
and Food Chemistry*, Fang et al., Vol. 56, pp. 5628-5633, 2008

10 Disclosure of Invention

Object of the Invention

[0013]

The present invention, which was made to solve the
15 inconvenience in the above-identified conventional processes
for producing particulate compositions containing crystalline
trehalose dihydrate and to increase the yield of such a
particulate compositions against starch while keeping the
trehalose purity, has objects to provide a process for
20 producing a particulate composition containing crystalline
trehalose dihydrate that enables the production of a
high-purity particulate composition containing crystalline
trehalose dihydrate in a satisfactory yield through consistent
steps using starch as a material, and to provide a novel
25 particulate composition containing crystalline trehalose
dihydrate produced by the process.

Means to Attain the Object

[0014]

To overcome the above objects, the present

inventors continued studying by considerations and repeated trial and error about the combination of the enzymes used in the above production methods disclosed in Patent Literatures 3 and 4, revealing that, when the enzymes derived from microorganisms of the genus *Arthrobacter*, which are easy to culture and high in enzyme productivity, are used as an α -glycosyltrehalose-forming enzyme and a trehalose-releasing enzyme, the use of a natural or recombinant CGTase derived from a microorganism of the genus *Paenibacillus* or a mutant enzyme thereof, in place of the CGTase derived from *Geobacillus stearothermophilus* Tc-91 strain (FERM BP-11273) that has been used so far, more efficiently proceeds a trehalose-forming reaction and improves the trehalose content in a trehalose-containing saccharide solution after glucoamylase treatment up to a level of, on a dry solid basis, over 86.0% by weight, preferably, 87.0% by weight or more without passing through a fractionation step by column chromatography. The trehalose-containing saccharide solution thus obtained is in conventional manner decolored, desalted, and concentrated before precipitating crystalline trehalose dihydrate, followed by collecting the resulting crystals by a centrifuge and ageing and drying the crystals to obtain a high-purity particulate composition containing crystalline trehalose dihydrate with a trehalose content of 98.0% by weight or more, d.s.b., in a higher production yield against starch than ever before. Thus, they accomplished the present invention.

[0015]

The present invention solves the above objects by providing a process for producing a particulate composition

containing crystalline trehalose dihydrate with a trehalose content of 98.0% by weight or more, d.s.b., characterized in that the process contains the steps of allowing, together with a starch debranching enzyme and CGTase, an
5 α -glycosyltrehalose-forming enzyme and a trehalose-releasing enzyme which are derived from a microorganism of the genus *Arthrobacter* to act on liquefied starch, allowing glucoamylase to act on the resulting mixture to obtain a trehalose-containing saccharide solution, precipitating
10 crystalline trehalose dihydrate from the saccharide solution, collecting the precipitated crystalline trehalose dihydrate by a centrifuge, and ageing and drying the crystals, wherein a natural or recombinant CGTase derived from a microorganism of the genus *Paenibacillus* or a mutant thereof is used as the
15 above CGTase to increase the trehalose content in the above saccharide solution to over 86.0% by weight, d.s.b., without passing through a fractionation step by column chromatography.
[0016]

According to the present inventors' confirmation,
20 the particulate composition containing crystalline trehalose dihydrate produced by the above process of the present invention is in no way inferior to a conventional food-grade powder containing crystalline trehalose dihydrate in view of its satisfactory trehalose purity and free-flowing ability,
25 and it can be used as a material for food products and cosmetics similar to a conventional food-grade powder containing crystalline trehalose dihydrate.
[0017]

Examples of the above microorganism of the genus

Paenibacillus as a source for CGTase include those of the species *Paenibacillus illinoisensis*, *Paenibacillus pabuli*, and *Paenibacillus amylolyticus*, among which those of the species *Paenibacillus illinoisensis* and *Paenibacillus pabuli* are preferable in that they produce CGTases having an effect of highly improving the trehalose content in an enzymatic reaction solution in the formation reaction of trehalose, particularly, those of the species *Paenibacillus illinoisensis* are preferable.

10 [0018]

As the above CGTases, those which have the following partial amino acid sequences of (a) to (d) are preferably used:

(a) Gly-Ser-X₁-Ala-Ser-Asp;

15 (b) Lys-Thr-Ser-Ala-Val-Asn-Asn;

(c) Lys-Met-Pro-Ser-Phe-Ser-Lys; and

(d) Val-Asn-Ser-Asn-X₂-Tyr.

(Wherein X₁ means Ala or Ser and X₂ means Ala or Thr, respectively.)

20 [0019]

Examples of more preferable CGTases usable in the present invention are those which have any one of the amino acid sequences represented by SEQ ID NOs: 1, 2, 3, 12 and 13.

[0020]

25 The present inventors further repeated trial and error and revealed that, when crystalline trehalose dihydrate is precipitated from the above trehalose-containing saccharide solution with a trehalose content of, on a dry solid basis, over 86.0% by weight, preferably, 87.0% by weight or

more, the production yield of the resulting particulate composition containing crystalline trehalose dihydrate against starch can be more increased by applying thereunto the later described controlled cooling method or semi-controlled cooling method, compared to the case of precipitating crystalline trehalose dihydrate by an unforced cooling method for cooling the temperature of a trehalose-containing saccharide solution by leaving it to nature. In detail, the present invention also solves the above objects by providing a process for producing a particulate composition containing crystalline trehalose dihydrate, wherein the above step for precipitating crystalline trehalose dihydrate is effected by a controlled cooling method or semi-controlled cooling method. [0021]

The reason why the production yield against starch is increased by the application of such a controlled cooling method or semi-controlled cooling method is uncertain, however, it can be speculated that any of these methods can inhibit both a rapid increment of saturation degree and a formation of secondary crystal nuclei by cooling to form a plurality of substantially homogeneous-sized minute crystal nuclei in the early phase of crystallization, and can grow a plurality of homogeneous-sized crystal nuclei all together by promptly cooling a plurality of roughly homogeneous-sized crystal nuclei in the late phase of crystallization, and therefore a massequite containing crystals with a lesser amount of microcrystals and a uniform granule size is obtained to facilitate the recovery of crystals by centrifugation, and the recovered crystals can be washed with a relatively small amount

of water to reduce the loss of trehalose when in washing.

[0022]

5 In addition, the present inventors found that the particulate composition containing crystalline trehalose dihydrate prepared by applying a controlled cooling method or semi-controlled cooling method to the precipitation of crystalline trehalose dihydrate similarly as in the above is surprisingly superior in that it is hardly cakeable compared to a particulate composition containing crystalline trehalose dihydrate and a conventional food-grade powder containing crystalline trehalose dihydrate, which are prepared by an unforced cooling method. They confirmed that these superior properties are due to the differences in the purity of trehalose and the degree of crystallinity for crystalline trehalose dihydrate of a particulate composition containing crystalline trehalose dihydrate, and thus they accomplished the present invention for a particulate composition containing crystalline trehalose dihydrate *per se*.

[0023]

20 More specifically, the present invention solves the above objects by providing a particulate composition containing crystalline trehalose dihydrate, obtained by the process of employing a controlled cooling method or semi-controlled cooling method in precipitating crystalline trehalose dihydrate, which contains, on a dry solid basis, 25 99.0% by weight or more but not more than 99.6% by weight of trehalose and has a degree of crystallinity for crystalline trehalose dihydrate of 90.0% or higher but not higher than 96.0% when determined on its powder X-ray diffraction profile.

[0024]

For reference, a particulate composition containing crystalline trehalose dihydrate, which contains, on a dry solid basis, 99.0% by weight or more but not more than 5 99.6% by weight of trehalose and has a degree of crystallinity for crystalline trehalose dihydrate of 90.0% or higher but not higher than 96.0% when determined on its powder X-ray diffraction profile, is a novel particulate composition distinguishable from a conventional food-grade powder 10 containing crystalline trehalose dihydrate in that it has a significantly higher degree of crystallinity for crystalline trehalose dihydrate than that of a conventional food-grade powder containing crystalline trehalose dihydrate even though the trehalose content is substantially the same or a slightly 15 higher level than that of a conventional food-grade powder containing crystalline trehalose dihydrate.

[0025]

The reason why a hardly cakeable particulate composition containing crystalline trehalose dihydrate is 20 obtained by applying a controlled cooling method or semi-controlled cooling method is uncertain, however, it can be speculated that the increment of both the purity of trehalose and the degree of crystallinity for crystalline trehalose dihydrate may Effect on the above because, as described above, 25 a massecuite that contains crystals with a lesser amount of microcrystals and a homogeneous granule size is obtained by such a controlled cooling method or semi-controlled cooling method. This speculation can also be evidenced even by the fact that the degree of crystallinity for crystalline trehalose

dihydrate of the particulate composition containing crystalline trehalose dihydrate of the present invention, obtained by applying a controlled cooling method or semi-controlled cooling method, is significantly higher than that of a particulate composition obtained by an unforced cooling method and a conventional food-grade powder containing crystalline trehalose dihydrate.

Effect of the Invention

[0026]

According to the process of the present invention, a high-purity particulate composition containing crystalline trehalose dihydrate can be obtained in a satisfactory production yield against starch and on an industrial scale by consistent steps of using starch as a material and an α -glycosyltrehalose-forming enzyme and a trehalose-releasing enzyme derived from a microorganism of the genus *Arthrobacter* that is easily cultured and high in enzyme productivities. Accordingly, the process imparts an advantageous contribution to the effective use of starch resources as a material. In particular, when a controlled cooling method or semi-controlled cooling method is applied in precipitating crystalline trehalose dihydrate from a trehalose-containing saccharide solution, the production yield of a produced particulate composition, containing crystalline trehalose dihydrate, against starch is more improved as a merit. The particulate composition containing crystalline trehalose dihydrate produced by the process of the present invention, which applies a controlled cooling method or semi-controlled cooling method, is a superior particulate composition in that

it is hardly cakeable and high in both trehalose purity and degree of crystallinity for crystalline trehalose dihydrate, compared to a conventional food-grade powder containing crystalline trehalose dihydrate.

5

Brief Description of Drawings

[0027]

FIG. 1 is an example of a powder X-ray diffraction pattern with a characteristic X-ray for a particulate composition containing crystalline trehalose dihydrate, which substantially consists of crystalline trehalose dihydrate.

FIG. 2 is an example of a powder X-ray diffraction pattern with a characteristic X-ray for a particulate composition containing trehalose, which substantially consists of an amorphous form of trehalose.

FIG. 3 is an example of a powder X-ray diffraction pattern with a synchrotron radiation for a particulate composition containing crystalline trehalose dihydrate, which substantially consists of crystalline trehalose dihydrate.

FIG. 4 is an example of a powder X-ray diffraction pattern with a synchrotron radiation for a particulate composition containing trehalose, which substantially consists of an amorphous form of trehalose.

FIG. 5 is a figure of cooling patterns.

FIG. 6 is a figure of the structure and the restriction enzyme recognition sites of a recombinant DNA "pRSET-iPI", which contains a CGTase gene derived from *Paenibacillus illinoisensis* NBRC15379 strain.

Best Mode For Carrying Out the Invention

[0028]

5 1. Definition of terms

Throughout the specification, the following terms mean as follows:

[0029]

<Production yield against starch>

10 The term "production yield against starch" as referred to in the specification is expressed by a percentage (%) for the rate of the weight, d.s.b., of a particulate composition containing crystalline trehalose dihydrate per unit mass, d.s.b, of a material starch. The specification
15 assumes that a particulate composition containing crystalline trehalose dihydrate is produced by consistent steps of allowing enzymes to act on starch as a material to form trehalose, crystallizing the formed trehalose, and then collecting, ageing, and drying the crystallized trehalose; and the meaning
20 of "production yield against starch" as referred to in the specification means the production yield of a particulate composition containing crystalline trehalose dihydrate, which is produced from the firstly precipitated crystals, i.e., the first-stage crystals precipitated from a trehalose-containing
25 saccharide solution obtained by allowing enzymes to act on starch, against the starch; and it does not include any particulate composition containing crystalline trehalose dihydrate produced by recrystallization from a saccharide solution remained after collecting the precipitated crystals

or from the one returned with a syrup separated from a massecuite, i.e., it does not include any particulate composition containing crystalline trehalose dihydrate prepared from the second and more stage crystals. For
5 comparison, when crystallized by adding a seed crystal, the amount of the seed crystal is included in the amount of the obtained particulate composition containing crystalline trehalose dihydrate, when calculating the production yield against starch, throughout the specification.

10 [0030]

<CGTase activity>

The term "CGTase activity" as referred to in the specification is defined as follows: To five milliliters of an aqueous substrate solution containing 0.3% (w/v) of a
15 soluble starch, 20 mM acetate buffer (pH 5.5), and 1 mM calcium chloride is added 0.2 ml of an enzyme solution diluted appropriately, and the resulting substrate solution is kept at 40°C and sampled at 0 min and 10 min after initiating the enzymatic reaction in respective amounts of 0.5 ml, followed
20 by immediately adding 15 ml of 0.02 N sulfuric acid solution to each sample to stop the enzymatic reaction. Each of the resulting sulfuric acid solutions is admixed with 0.2 ml of 0.1 N iodine solution to develop colors, and, after 10 min, the colored solutions are respectively measured for absorbance
25 at a wavelength of 660 nm by a spectrophotometer, followed by calculating for starch decomposing activity with the following Formula [1]. One unit activity of CGTase is defined as the enzyme amount that completely diminishes the iodine color of a solution containing 15 mg of starch.

[0031]

Formula [1]:

[Equation 1]

$$5 \quad \text{Activity (unit/ml)} = \frac{A_a - A_b}{A_a} \times \frac{1}{0.2} \times (\text{dilution rate})$$

Note: "Aa" means the absorbance at a wavelength of 660 nm
of a reaction solution at 0 min after initiating
10 the enzymatic reaction.

"Ab" means the absorbance at a wavelength of 660 nm
of a reaction solution at 10 min after initiating
the enzymatic reaction.

15 [0032]

<Controlled cooling method>

The term "controlled cooling method" as referred
to in the specification means a method for precipitating
crystals by "controlled cooling" and means a cooling method
20 where the liquid temperature "T" at the time "t" is basically
expressed by Formula [7], wherein "τ" is the operation time
established for a crystallization step, "T₀" is the liquid
temperature at the initiation of crystallization, and "T_f" is
the targeted liquid temperature at the termination of
25 crystallization.

[0033]

Formula [2]:

[Equation 2]

$$T = T_0 - (T_0 - T_f) (t/\tau)^3$$

30 [0034]

A controlled cooling method is expressed with "a" in FIG. 5, when expressed with a graph that describes concretely (schematically) the controlled cooling method, wherein the abscissa axis corresponds to the operation time settled for a crystallization step and the longitudinal axis corresponds to the liquid temperature when in crystallization. As shown in the symbol "a" in FIG. 5, according to a controlled cooling method, the liquid temperature gradually decreases in the early phase of crystallization at which the liquid temperature is relatively high but the liquid temperature promptly decreases in the later phase at which the liquid temperature has decreased to some extent. Accordingly, at the time of $t=\tau/2$, i.e., the liquid temperature " T_m " at the middle point of crystallization step is maintained at least on the connection of $T_m > [(T_0 - T_f) / 2 + T_f]$ (or the temperature change at the middle point of crystallization step becomes less than 50% of the total temperature change). In the changing pattern of the liquid temperature against time, the controlled cooling method is clearly distinguished from both a linear cooling method (the symbol "b" in FIG. 5) where the liquid temperature linearly decreases with the time " τ " from the liquid temperature T_0 to T_f , and a usual unforced-cooling method (the symbol "c" in FIG. 5) where the liquid temperature decreases exponentially and promptly at the early phase of crystallization but gradually decreases at the more later phase of crystallization with a decreased liquid temperature. To alter the liquid temperature " T " as a function of the time " t " represented in the above Formula [2], for example, a commercialized general-purpose programmed constant circulator for crystallization system,

etc., can be used.

[0035]

When such a controlled cooling method is applied in crystallization step, the cooling of the liquid temperature is gradually carried out at the early phase of crystallization after the addition of seed crystals of trehalose, and this inhibits both a prompt increment of the saturation degree of trehalose and a secondary crystal nucleation by cooling and results in a predominant growth of crystals from the added seed crystals as crystal nuclei. Meanwhile, in the later phase of crystallization at which crystals from the added seed crystals as crystal nuclei have been homogeneously generated, the homogeneously formed crystals are allowed to grow all together when the liquid temperature is promptly cooled, and therefore it gives the merit that a controlled cooling method affords a masseccuite containing crystals with a homogeneous particle size and a lesser amount of microcrystals. For reference, "controlled cooling method" is described in detail in "Wakariyasui-Batch-Shoseki" (Accessible batch crystallization), edited by Noriaki KUBOTA, published by The Society of Separation Process Engineers, Japan, published on April 30, 2010, pp. 32-47.

[0036]

<Semi-controlled cooling method>

The term "semi-controlled cooling method" as referred to in the specification means literally a semi-cooling-method of the above-identified controlled cooling method, wherein the liquid temperature "T" is not strictly altered against the time "t" according to the above

Formula [2], and more specifically it means a cooling method, wherein the liquid temperature "T" is allowed to linearly or stepwisely decrease against the time "t" in order to keep the variation ($T_0 - T_m$) of the liquid temperature "T" at the point of " $t = \tau/2$ " to be at least 5% but less than 50% of the total temperature change ($T_0 - T_f$), preferably, at least 10% but less than 30%, because, varying depending on the purity, concentration, saturation degree, and seed-crystal content of trehalose in a solution containing trehalose used in crystallization, it is preferable that crystal nuclei are almost completely generated at the operation time " $t = \tau/2$ " (at the middle point in crystallization step). In the case of allowing the liquid temperature "T" to linearly or stepwisely decrease against the time "t" so as to adjust the variation ($T_0 - T_m$) of the liquid temperature "T" at the point of " $t = \tau/2$ " to be at least 5% but less than 50% of the total temperature change ($T_0 - T_f$), the liquid temperature "T" gradually decreases against the time "t" at early phase of crystallization, where the liquid temperature is relatively high, while the liquid temperature "T" promptly decreases against the time "t" at a later phase of crystallization, where the liquid temperature has decreased to some extent. As a result, it may be somewhat inferior to a controlled cooling method, however, a semi-controlled cooling method exerts substantially the same merits as the controlled cooling method, wherein the semi-controlled cooling method enables to provide a massecuite containing crystals with a lesser amount of microcrystals and a homogeneous particle size.

[0037]

Concretely speaking, for example, the liquid temperature "T" is allowed to linearly or stepwisely decrease against the time "t" in such a manner of dividing the operation time " τ " into at least two, preferably, at least three zones and then, in a zone of early phase of crystallization step, allowing the thermal gradient in cooling to change gradually (to slow the cooling rate); and as it changes from the early phase or from the middle phase to the later phase, allowing the thermal gradient to increase (to fasten the cooling rate) to make the variation $(T_0 - T_m)$ of the liquid temperature "T" at the point of " $t = \tau/2$ " to be at least 5% but less than 50% of the total temperature change $(T_0 - T_f)$, preferably, at least 10% but less than 30%. In the case that the variation $(T_0 - T_m)$ of the liquid temperature "T" at the point of " $t = \tau/2$ " is at least 50% of the total temperature change $(T_0 - T_f)$, the cooling rate in the early phase of crystallization step is so fast as to possibly promptly increase the saturation degree by cooling to form the secondary crystal nuclei, while in the case of less than 5%, the cooling rate in the early phase of crystallization step is so slow as to get into the later phase of crystallization step, where a prompt cooling will start before the completion of forming crystals from crystal nuclei that have not been sufficiently formed from the added seed crystals. In any event, it becomes impossible to obtain a massecuite containing crystals with a lesser amount of microcrystals and a homogeneous particle size.

[0038]

To conduct the controlled cooling method as described above, the liquid temperature "T" should be changed

as a function of the time "t" represented in Formula [2], and an apparatus or a crystallizer, which can control the liquid temperature by a predetermined program, is essential; however, according to a semi-controlled cooling method, the liquid temperature "T" can be linearly or stepwisely decreased against the time "t" so as to adjust the variation ($T_0 - T_m$) of the liquid temperature "T" at the point of " $t = \tau/2$ " to a level of at least 5% but less than 50% of the total temperature change ($T_0 - T_f$), preferably, at least 10% but less than 30% so that such a semi-controlled cooling method has the merit that it can be relatively easily conducted even in the case that there is no facility that controls the liquid temperature accurately.

[0039]

<Degree of crystallinity>

The term "a degree of crystallinity for crystalline trehalose dihydrate" as referred to in the specification means a value defined by the following Formula [3].

[0040]

Formula [3]:

[Equation 3]

$$\text{Degree of crystallinity (\%)} = \frac{H_s - H_0}{H_{100} - H_0} \times 100$$

H_{100} : An analytical value for a degree of crystallinity, determined based on the powder X-ray diffraction profile for a powdered standard sample containing crystalline trehalose dihydrate, where the powdered standard sample consists substantially of

crystalline trehalose dihydrate.

H_0 : An analytical value for a degree of crystallinity, determined based on the powder X-ray diffraction profile for a powdered standard sample containing trehalose, where the powdered standard sample consists substantially of an amorphous form of trehalose.

H_s : An analytical value for a degree of crystallinity, determined based on the powder X-ray diffraction profile for, as a test sample, a powder containing trehalose.

[0041]

In Formula [3], the powder X-ray diffraction profiles for the basis of determining analytical values H_{100} , H_0 , and H_s can be usually determined by a powder X-ray diffractometer equipped with a reflective or transmissive optical system. The powder X-ray diffraction profiles contain data for diffraction angles and diffraction strengths of crystalline trehalose dihydrate contained in a test or standard sample. Examples of methods for determining the analytical data for the degrees of crystallinity of such samples include the Hermans' method, Vonk's method, etc. Among which the Hermans' method is preferable because of its easiness and accuracy. Since these analytical methods have now been provided as computer softwares, any powder X-ray diffractometers, equipped with an analytical apparatus installed with any of the above computer softwares, can be

suitably used.

[0042]

As "a powdered standard sample containing crystalline trehalose dihydrate, where the powdered standard sample consists substantially of crystalline trehalose dihydrate", for determining the analytical value H_{100} , there must be used a crystalline trehalose dihydrate in the form of a powder or a single crystal, which has a trehalose purity of 99.9% by weight or higher (throughout the specification, "% by weight" is abbreviated as "%", unless specified otherwise but the "%" affixed to the degree of crystallinity should not be limited thereunto), exhibits characteristic diffraction peaks inherent to crystalline trehalose dihydrate on its powder X-ray diffraction pattern, and consists substantially of crystalline trehalose dihydrate. Examples of those in the form of a particulate composition or a single crystal include "TREHALOSE 999" (Code No: TH224, a trehalose purity of at least 99.9%), a product name of a particulate composition containing crystalline trehalose dihydrate, commercialized by Hayashibara Co., Ltd., Okayama, Japan, or sold by the present applicant as an analytical reagent; and those in the form of a particulate composition containing crystalline trehalose dihydrate or in the form of a single crystal, obtained by recrystallizing the above product. For reference, when analyzed with a computer software for the Hermans' method, the powder X-ray diffraction profile of a particulate composition containing crystalline trehalose dihydrate, as the above-identified powdered standard sample, which consists substantially of crystalline trehalose dihydrate, gives an

analytical value H_{100} , usually, ranging from about 50.6% to about 50.9%.

[0043]

As "a powdered standard sample containing
5 trehalose, where the powdered standard sample consists
substantially of an amorphous form of trehalose" for
determining the analytical value H_0 , the one, which has a
trehalose purity of 99.9% or higher and consists substantially
of amorphous trehalose, is used. Examples of such a powdered
10 standard sample include those which are obtained by dissolving
the above-identified powdered standard sample for determining
the aforesaid analytical value H_{100} in an appropriate amount
of refined water, concentrating the solution, freeze-drying
the concentrate, and drying the resultant *in vacuo* up to give
15 a moisture content of 2.0% or lower, when determined on the
Karl Fischer method. With these treatments, it is known by
experience that a particulate composition consisting
substantially of an amorphous form of trehalose is obtained.
In general, even a particulate composition consisting
20 substantially of an amorphous form of trehalose, the analytical
value should not necessarily be 0% because, when the
particulate composition is subjected to a powder X-ray
diffractometer and the resulting powder X-ray diffraction
profile is analyzed on the Hermans' method, Vonk's method, etc.,
25 a part of the scattering light, derived from the amorphous form
inherent to the algorithm of a computer software for operating
the analytical methods, is calculated. For reference, when
analyzed with a computer software for the Hermans' method, the
powder X-ray diffraction profile of the particulate

composition containing trehalose, as the above-identified powdered standard sample, which consists substantially of an amorphous form of trehalose, gives an analytical value H_0 , usually, ranging from about 8.5% to about 8.7%.

5 [0044]

<Average crystallite diameter>

In general, a powder particle is recognized as being constituted by a plurality of single crystals, i.e., crystallites. The size of crystallite (crystallite diameter)
10 in a powder containing crystals is speculated to be reflected in its property. The term "an average crystallite diameter for crystalline trehalose dihydrate" (called simply "crystallite diameter", hereinafter) as referred to in the present invention means an average of crystallite diameters
15 calculated in such a manner of subjecting a particulate composition containing crystalline trehalose dihydrate to the powder X-ray diffraction analysis; selecting five diffraction peaks from among diffraction peaks detected on the obtained powder X-ray diffraction patterns, i.e., diffraction peaks
20 (the symbols "a" to "e" in FIG. 1) at diffraction angles (2θ) of 13.7° (Miller's index (hkl):101), 17.5° (Miller's index (hkl):220), 21.1° (Miller's index (hkl):221), 23.9° (Miller's index (hkl):231), and 25.9° (Miller's index (hkl):150), which located in a relatively low-angle region that is to be least
25 disruptive to diffraction peak width due to heterogeneous strain of crystallite, and which were well separated from other diffraction peaks; calibrating the respective half widths (full widths at half maxima) and the diffraction angles based on the measured values determined when silicon ("Si640d",

provided by NIST: National Institute of Standards and Technology, as a standard sample for X-ray diffraction) is used as a standard sample; and calculating respective averages of crystallite diameters with the Scherrer's equation shown in the following Formula [4]:

[0045]

Formula [4]:

[Equation 4]

$$D = \frac{K\lambda}{B\cos\theta}$$

D : Size of crystallite ($\text{\AA}$)

λ : Wavelength of X-ray ($\text{\AA}$)

15 β : Diffraction linewidth (rad)

θ : Diffraction angle ($^\circ$)

K : Constant (0.9 when a half-width (a full-width at half maximum) is used for β)

20 [0046]

Since a common powder X-ray diffractometer is installed with a computer software for calculating such crystallite diameters, an average crystallite diameter of crystalline trehalose dihydrate is relatively easily determined as long as a particulate composition containing crystalline trehalose dihydrate is available. Prior to powder X-ray diffraction analysis, each test sample is brayed in a mortar and sieved with a 53 μm sieve to obtain a powder passed through the sieve for use.

30 [0047]

<Reducing power>

The term "a reducing power of the whole particulate composition" as referred to in the specification can be obtained by using D-glucose as a standard substance; determining the reducing sugar content and the total sugar content, respectively, based on the D-glucose conversion, by the Somogyi-Nelson method and the anthrone-sulfuric acid method widely used in the art; and calculating the percentage (%) of the reducing saccharide content to the total sugar content in a particulate composition by using the following Formula [5].

[0048]

Formula [5]:

[Equation 5]

$$\text{Reducing power (\%)} = \frac{\text{Reducing sugar content}}{\text{Total sugar content}} \times 100$$

[0049]

<Particle size distribution>

The particle size distribution of a particulate composition is determined as follows in the specification: Metal sieves with opening sizes of 425, 300, 212, 150, 106, 75 and 53 μm , produced by Kabushiki Gaisha Iida Seisaku-sho, Tokyo, Japan, which are compliant with Japanese Industrial Standards (JIS Z 8801-1), are accurately weighed, stacked in the above-identified order, and mounted on "R-1", a product name of a ro-tap sieving shaker, produced by Kabushiki Gaisha Tanaka Kagaku Kikai Seisaku-sho, Osaka, Japan. A prescribed amount of weighed sample is placed on the uppermost sieve

(having an opening size of 425 μm) in the stacked sieves, followed by shaking the sieves for 15 min while keeping the stacked state. Thereafter, each of the stacked sieves was accurately weighed again, and the weight of the sample collected on each of the sieves was determined by subtracting the weight of each of the sieves before loading on it the sample from the weight of the corresponding each of the sieves after shaking. Particle size distribution is expressed by calculating the weight percentage (%) of each of the weights of the particulate compositions with respective particle sizes collected on each of the sieves to the weight of the sample loaded on the uppermost sieve.

2. Process for producing crystalline trehalose dihydrate of the present invention
[0050]

The process of the present invention basically includes the following steps (1) to (6):

- (1) a step of forming trehalose by allowing an α -glycosyltrehalose-forming enzyme and a trehalose-releasing enzyme, which are derived from a microorganism of the genus *Arthrobacter*, along with a starch debranching enzyme and a natural or recombinant CGTase or a mutant thereof to act on a liquefied starch solution to form trehalose;
- (2) a step of treating with glucoamylase by allowing glucoamylase to act on the resulting reaction solution containing trehalose obtained in the step of forming trehalose;

- (3) a step of purifying and concentrating the reaction solution containing trehalose by filtering, decoloring, desalting, and concentrating the reaction solution;
- (4) a step of precipitating crystalline trehalose dihydrate by incorporating a seed crystal of crystalline trehalose dihydrate into the concentrate containing trehalose;
- (5) a step of collecting a resulting crystalline trehalose dihydrate from the massecuite obtained in the precipitation step ; and
- (6) a step of ageing, drying, and optionally pulverizing the collected crystalline trehalose dihydrate.

The above steps (1) to (6) are subsequently explained below:

[0051]

<Step (1) (Step of forming trehalose)>

[0052]

This step is the one of allowing an α -glycosyltrehalose-forming enzyme and a trehalose-releasing enzyme, both of which are derived from a microorganism of the genus *Arthrobacter*, along with a starch debranching enzyme and a natural or recombinant CGTase or a mutant thereof to act on liquefied starch as a material to form trehalose.

[0053]

The α -glycosyltrehalose-forming enzyme is an enzyme that forms α -glycosyltrehalose having a trehalose structure at the molecular terminus by acting on liquefied starch, while the trehalose-releasing enzyme is an enzyme that releases trehalose by acting on α -glycosyltrehalose. Accordingly, trehalose can be efficiently produced by allowing

the α -glycosyltrehalose-forming enzyme and the trehalose-releasing enzyme along with a starch debranching enzyme to act on liquefied starch obtained by gelatinizing and liquefying starch.

5 [0054]

Examples of the material starch used in producing trehalose include any of aboveground starches such as corn starch, rice starch, and wheat starch; subterranean starches such as potato starch, ocarina starch, and tapioca starch; and
10 partial starch hydrolyzates obtained by partially hydrolyzing these starches with acids or amylases. The material starch is usually suspended in water into an about 10 to about 50% starch suspension and gelatinized/liquefied by heating in the presence of a thermostable α -amylase. The liquefaction degree
15 of liquefied starch is usually controlled to a dextrose equivalent (DE) of less than 10, more particularly, less than 5.

[0055]

Examples of the α -glycosyltrehalose-forming
20 enzyme and the trehalose-releasing enzyme, which are derived from microorganisms of the genus *Arthrobacter*, include those disclosed in Japanese Patent Kokai No. 143876/95, Patent Literatures 2 to 4, etc. Recombinant α -glycosyltrehalose-forming enzymes and trehalose-releasing
25 enzymes, which are disclosed in Japanese Patent Kokai Nos. 322880/95, 322883/95, 298887/95, and 298880/95, and Patent Literature 4, etc., can be used and positively modified mutant enzymes prepared by introducing site specific mutations into these enzymes can be also used. Particularly, an

α -glycosyltrehalose-forming enzyme and trehalose-releasing enzyme, which are derived from *Arthrobacter* sp. S34 strain (FERM BP-6450) disclosed in Patent Literature 4 or derived from mutants thereof with high enzyme productivity, can be suitably used.

[0056]

In the process of the present invention, isoamylase and pullulanase, which are widely used in the art, can be used as starch debranching enzymes. Any of commercialized enzyme preparations and those isolated from microorganisms can be used. Examples of such isoamylase include those which are derived from microorganisms of the species *Pseudomonas amyloclavata* and *Myroides odoratus* are well known, particularly, an isoamylase specimen derived from a microorganism of the species *Pseudomonas amyloclavata*, produced by Hayashibara Co., Ltd., Okayama, Japan, is preferable. Examples of pullulanase preparations include a pullulanase derived from a microorganism of the species *Klebsiella pneumoniae* commercialized by Hayashibara Co., Ltd., Okayama, Japan; and "PROMOZYME", a product name of a pullulanase derived from a microorganism of the species *Bacillus amyloliquefaciens*, commercialized by Novozymes Japan Ltd., Tokyo, Japan.

[0057]

The role of CGTase in the above steps of forming trehalose is to more proceed the above reaction of forming trehalose to more increase the trehalose content in the reaction solution by mainly converting maltooligosaccharides, having a glucose polymerization degree of four or lower, which

are inevitably formed in the above trehalose-forming reaction process by an α -glycosyltrehalose-forming enzyme and a trehalose-releasing enzyme, into maltooligosaccharides, having a glucose polymerization degree of five or more, by a disproportionation reaction (an intermolecular rearrangement reaction of linear saccharides) catalyzed by CGTase.

[0058]

CGTases have been isolated from different microorganisms and their functions and physicochemical properties have been revealed (see, for example, "Kogyo-yo-Toshitsu-Handbook" (Handbook of Industrial Enzyme for Saccharides), edited by Kodansha Scientific Ltd., Tokyo, Japan, published by Kodansha Ltd., Tokyo, Japan, pp. 28-32, 1999, etc). The genes for some of the above-identified CGTases have been cloned and the amino acid sequences have been determined based on the base sequences of the cloned genes. It has been also known that there exist four conserved regions that are recognized to commonly exist in the group of enzymes classified as α -amylase family on the amino acid sequences of the above CGTases. The CGTase protein derived from a microorganism of the species *Geobacillus stearothermophilus* has been already revealed its stereostructure by an X-ray crystal structural analysis, and the three catalytic residues of the CGTase, i.e., the 225th aspartic acid residue (D225), the 253rd glutamic acid residue (E253), and the 324th aspartic acid residue (D324) in the amino acid sequence of SEQ ID NO:4 have been also revealed (see, for example, "Kogyo-yo-Toshitsu-Koso-Handbook" (Handbook of Industrial Enzyme for Saccharides), edited by Kodansha Scientific Ltd.,

Tokyo, Japan, published by Kodansha Ltd., Tokyo, Japan, pp. 56-63, 1999).

[0059]

A natural or recombinant CGTase, derived from a
5 microorganism of the genus *Paenibacillus*, or mutant enzymes
thereof can be suitably used as CGTase in the process of the
present invention. For example, CGTases derived from
heretofore known strains of microorganisms of the species
Paenibacillus illinoisensis, *Paenibacillus pabuli*, and
10 *Paenibacillus amylolyticus*, and those derived from a
microorganism of the genus *Paenibacillus*, isolated from the
natural world, can be used as "a natural CGTase derived from
a microorganism of the genus *Paenibacillus*" as referred to in
the present invention. More concretely, CGTases derived from
15 *Paenibacillus illinoisensis* NBRC15959 strain, *Paenibacillus*
illinoisensis NBRC15379 strain, *Paenibacillus pabuli*
NBRC13638 strain, and *Paenibacillus amylolyticus* NBRC15957
strain, and those derived from mutant strains thereof with high
enzyme productivity, which are obtained by introducing
20 mutations into the above microorganisms of the genus
Paenibacillus, for example, by such as mutation treatments with
ultraviolet irradiation and chemical substances,
conventionally used in the art, are most suitably used.
Further, "ALKALI CD AMYLASE", a product name of a CGTase derived
25 from a microorganism of the species *Paenibacillus* sp., produced
by Nagase Chemtex Corp., Osaka, Japan, can also be used as a
CGTase derived from a microorganism of the genus *Paenibacillus*.
Incidentally, CGTase, which has been conventionally used in
producing a food-grade powder containing crystalline

trehalose dihydrate, is the one derived from a microorganism of the species *Geobacillus stearothermophilus*.

[0060]

In the process of the present invention, CGTases, having the following partial amino acid sequences of (a) to (d), are suitably used:

- (a) Gly-Ser-X₁-Ala-Ser-Asp;
- (b) Lys-Thr-Ser-Ala-Val-Asn-Asn;
- (c) Lys-Met-Pro-Ser-Phe-Ser-Lys; and
- (d) Val-Asn-Ser-Asn-X₂-Tyr.

(Wherein X₁ means Ala or Ser and X₂ means Ala or Thr, respectively.)

The above partial amino acid sequences are characteristic of CGTases derived from microorganisms of the genus *Paenibacillus*.

[0061]

As examples of "a recombinant CGTase derived from a microorganism of the genus *Paenibacillus*" as referred to in the present invention, those, which are obtained by cloning a CGTase gene derived from the above microorganism of the genus *Paenibacillus* and allowing to express the cloned CGTase gene in an appropriate host microorganism such as *E. coli* and *Bacillus subtilis*, can be suitably used. For comparison, CGTases derived from *Paenibacillus illinoisensis* NBRC15379 strain, *Paenibacillus pabuli* NBRC13638 strain, and *Paenibacillus amylolyticus* NBRC15957 strain are respectively cloned CGTase genes from these microorganisms by the present applicant independently and determined base sequences of the cloned genes, revealing that they have the amino acid sequences

of SEQ ID NOs: 1, 2 and 3, respectively. The recombinant CGTases having any one of the amino acid sequences of SEQ ID NOs: 1 to 3 can be used similarly as a natural CGTase derived from a microorganism of the genus *Paenibacillus* in the process of the present invention.

[0062]

As examples of "a mutant enzyme of a CGTase derived from a microorganism of the genus *Paenibacillus*" (abbreviated as "a mutant CGTase", hereinafter) as referred to in the present invention, mutant CGTases, into which deletion, replacement or addition of one or more amino acids are introduced into the amino acid sequence of the above microorganism within a range of not substantially altering substrate specificity and enzyme activity as CGTase, can be suitably used. The number of amino acid residues which can be deleted, replaced, or added in the amino acid sequence of such a mutant CGTase should not specifically be restricted as long as the substrate specificity and enzyme activity as CGTase can be retained, however, preferable are less than 5% of the amino acid sequence consisting of about 680 amino acid residues, i.e., amino acid residues of up to about 30, preferably, at least one but less than 20, more preferably, at least one but less than 10. Also referring to the mutation-introduced site on the amino acid sequence, it should not specifically be restricted as long as substrate specificity and enzyme activity as CGTase are substantially retained, however, there should desirably be avoided any mutation introduction to four conservative regions that are common in a group of enzymes classified as the alpha-amylase family and present on the amino acid sequence

of CGTase, and to the above-identified partial amino acid sequences of (a) to (d) that are characteristic to CGTases derived from microorganisms of the genus *Paenibacillus*.

[0063]

5 More concrete examples of "a natural or recombinant CGTase derived from a microorganism of the genus *Paenibacillus* or a mutant enzyme thereof" include the above-identified CGTases having any of the above-mentioned respective amino acid sequences of SEQ ID NOs: 1 to 3, and mutant
10 CGTases having the amino acid sequence of SEQ ID NO: 12 or 13, prepared by introducing a site specific mutation into the CGTase gene of *Paenibacillus illinoisensis* NBRC15379 strain disclosed in the later described Example.

[0064]

15 In the process of the present invention, the above-identified α -glycosyltrehalose-forming enzyme derived from a microorganism of the genus *Arthrobacter*, the above-identified trehalose-releasing enzyme derived from a microorganism of the genus *Arthrobacter*, a starch debranching
20 enzyme, and a CGTase derived from a microorganism of the genus *Paenibacillus* are suitably added to liquefied starch (pH of about 4 to about 10) as a substrate in respective amounts of 0.5 to 10 units, 2.5 to 25 units, 50 to 1,000 units, and 0.5 to 50 units per gram starch at a temperature in the range of
25 30 to 60°C for 10 to 100 hours. The trehalose content in the resulting reaction solution at the time upon termination of enzymatic reactions is usually about 86%, d.s.b.

[0065]

<Step (2) (step of glucoamylase treatment)>

This step is the one of further allowing a glucoamylase specimen to act on the reaction solution, obtained in the step (1) of forming trehalose, to increase the trehalose content, d.s.b. Incidentally, the reaction solution obtained
5 in the step of forming trehalose contains, along with trehalose, saccharides such as D-glucose, maltose, maltooligosaccharides having a glucose polymerization degree of at least three, α -glucosyltrehalose, and α -maltosyltrehalose, and, when glucoamylase is allowed to act on the solution, maltose and
10 maltooligosaccharides having a glucose polymerization degree of at least three can be hydrolyzed up to D-glucose, while α -glycosyltrehalose such as α -glucosyltrehalose and α -maltosyltrehalose can be hydrolyzed up to D-glucose and trehalose to increase the trehalose purity, i.e., the trehalose
15 content, d.s.b., in the reaction solution.
[0066]

Glucoamylases usable in the process of the present invention should not specifically be restricted depending on their sources and origins as long as they can hydrolyze maltose
20 and maltooligosaccharides having a glucose polymerization degree of at least three up to D-glucose and also hydrolyze α -glycosyltrehalose such as α -glucosyltrehalose and α -maltosyltrehalose up to D-glucose and trehalose. Commercialized glucoamylase specimens, for example, such as
25 "GLUCZYME AF6", a product name thereof commercialized by Amano Enzyme Inc., Aichi, Japan, and "GLUCOZYME", a product name thereof commercialized Nagase Chemtex Corp., Osaka, Japan, can be suitably used.
[0067]

The trehalose content in the reaction solution after glucoamylase treatment or in the trehalose-containing saccharide solution is usually over 86.0%, d.s.b., preferably, 87.0% or higher. For comparison, when CGTase derived from a microorganism of the species *Geobacillus stearothermophilus* is used instead of using CGTase derived from a microorganism of the genus *Paenibacillus*, the trehalose content in the trehalose-containing saccharide solution after glucoamylase treatment is less than 86.0%, d.s.b., and never be 86.0% or higher.

[0068]

<Step (3) (step of purification and concentration)>

This step is the one of removing impurities by treating a trehalose-containing saccharide solution having an increased trehalose content, d.s.b., after glucoamylase treatment, with filtration, centrifugation, etc., in usual manner; decoloring the resulting saccharide solution with an activated charcoal; desalting the solution with a cation-exchange resin (H^+ -form) and an anion-exchange resin (OH^- -form); and concentrating the resulting solution up to give a concentration suitable for crystallization. Since the trehalose content, d.s.b., in the reaction solution has been increased up to a level of 86.0% or higher through the step (2) of glucoamylase treatment, in the step (3) of purification and concentration, there requires no need of a step of further increasing the trehalose content, such as a fractionation step by column chromatography.

[0069]

<Step (4) (step of crystallization)>

This step is the one of precipitating crystalline trehalose dihydrate from the trehalose-containing saccharide solution obtained through the steps (1) to (3) in the presence of a seed crystal of crystalline trehalose dihydrate. After the saccharide solution with a trehalose content, d.s.b., which had been increased up to a prescribed level, is usually controlled to give a saturation degree of trehalose in the range of 1.05 to 1.50, or controlled to give a trehalose concentration of about 60 to about 85% and to give a liquid temperature of about 40 to about 80°C, the resulting saccharide solution is transferred to a crystallizer, incorporated with a seed crystal of crystalline trehalose dihydrate in an amount usually equal to 0.1 to 5% (w/v), and particularly, 0.5 to 2% (w/v) of the volume of the resulting concentrated saccharide solution in the crystallizer, and the concentrated saccharide solution is unforcedly cooled to 5 to 60°C over 3 to 48 hours under gentle stirring conditions to induce the precipitation of crystalline trehalose dihydrate. For comparison, when a seed crystal of crystalline trehalose dihydrate is already present in the crystallizer, etc., no additional seed crystal of crystalline trehalose dihydrate should specifically be required. The precipitation of crystalline trehalose dihydrate from the concentrated solution is, in view of work efficiency, usually effected in the presence of a seed crystal.

[0070]

A controlled cooling method or semi-controlled cooling method can be advantageously used in the crystallization step, in place of the above unforced cooling

method. In the case of conducting crystallization by such a controlled cooling method or semi-controlled cooling method, the trehalose-containing saccharide solution, which had been adjusted to a prescribed temperature through the above step (3), is transferred to a crystallizer, incorporated with a seed crystal of crystalline trehalose dihydrate in an amount equal to 0.1 to 5% (w/v), particularly, 0.5 to 2% (w/v) of the volume of the concentrated saccharide solution in the crystallizer, and allowed to effect crystallization by allowing the liquid temperature to gradually decrease in the early stage of the crystallization step and to promptly decrease in the later stage of the cooling step by controlling the cooling under gentle stirring conditions. The time required for crystallization varies depending on the amount of a seed crystal of crystalline trehalose dihydrate to be added; for example, in the case of a semi-controlled cooling method, the total cooling time is sectioned by at least two zones, preferably, at least three zones, and then, in each zone the temperature is roughly linearly decreased against time; the liquid temperature "T" is allowed to linearly or stepwisely decrease against the time "t" in such a manner of allowing the variation ($T_0 - T_m$) of the liquid temperature "T" at the point of " $t = \tau/2$ " to be at least 5% but less than 50% of the total temperature change ($T_0 - T_f$), preferably, at least 10% but less than 30%. For example, when crystals are precipitated by cooling the trehalose-containing saccharide solution from 60°C to 20°C over 10 hours, the cooling time is divided into two zones of 6 hours and 4 hours, where the solution is preferably cooled from 60°C to 50°C over 6 hours and then the

solution is cooled from 50°C to 20°C over 4 hours, or the cooling time is divided into two zones of 7 hours and 3 hours, where the solution is also preferably cooled from 60°C to 45°C over 7 hours and then the solution is cooled from 45°C to 20°C over 3 hours. More preferably, the cooling time is divided into three zones of 4, 3 and 3 hours, and the solution is successively cooled from 60°C to 55°C over 4 hours in the first zone, cooled from 55°C to 50°C over 3 hours in the next zone, and cooled from 50°C to 20°C over 3 hours in the last zone.

10 [0071]

In this way, according to a controlled cooling method or semi-controlled cooling method, a massecuite, which hardly generates microcrystals of crystalline trehalose dihydrate and contains crystals with a substantially homogeneous particle diameter, can be obtained, compared to a crystallization method that unforcedly cools the liquid solution without controlling the temperature. As a result, the production yield of the obtained crystalline trehalose dihydrate against starch can be more increased than that attained by an unforced cooling method. As described later, the obtained particulate composition containing crystalline trehalose dihydrate has characteristic features of having both a higher purity of trehalose and a higher degree of crystallinity for crystalline trehalose dihydrate that becomes to be an important index for cakeability than those of a powder obtained by an unforced cooling method. In the case of a controlled cooling method or semi-controlled cooling method, a particulate composition with more homogeneous particle size distribution is obtained as a merit, compared

to a powder obtained by a crystallization method of unforced cooling.

[0072]

<Step (5) (step of collection)>

5 This step is the one of collecting crystalline trehalose dihydrate by centrifugation according to a conventional solid-liquid separation method from the massecuite obtained in the crystallization step (4). The collected crystalline trehalose dihydrate is washed by
10 spraying (showering) with a small amount of refined water to remove a syrup with amorphous saccharides, adhered to the surface of the crystalline trehalose dihydrate. The amount of refined water used for washing the crystals is preferably usually at least 3% but not more than 10% to the weight of a
15 massecuite before centrifugation. When the amount of the above refined water is less than 3%, a sufficient washing could not be attained, resulting in remaining a syrup with amorphous saccharides and a fear of not obtaining a desired trehalose purity. On the contrary, when the amount of refined water used
20 for washing is over 10%, the amount of crystalline trehalose dihydrate to be dissolved and removed by washing increases and results in a fear of decreasing the production yield against starch.

[0073]

25 <Step (6) (step of ageing and drying)>

 This step is the one of obtaining a particulate composition containing crystalline trehalose dihydrate by allowing the collected crystalline trehalose dihydrate to stand in an atmosphere with a prescribed temperature and

humidity for a prescribed period of time to age the crystals while drying with hot air. The product temperature of crystals, the relative humidity of atmosphere, and the retention time in the ageing and drying step are not specifically restricted as long as a desired particulate composition is obtained, however, the crystals should preferably be kept at a temperature of 20 to 55°C as a product temperature and at an ambient relative humidity of 60 to 90%, and the ageing and drying time should preferably be about 5 to about 24 hours. The particulate composition obtained through the ageing and drying step is then unforcedly cooled down to an ambient temperature. The particulate composition can be advantageously forcedly cooled down to make the product temperature to give about ambient temperature by blowing to the contents a clean air with about ambient temperature. The particulate composition thus obtained can be used intact or optionally pulverized into a final product.

[0074]

According to the process of producing the particulate composition containing crystalline trehalose dihydrate of the present invention, a trehalose-containing saccharide solution with a trehalose content of as high as over 86.0%, d.s.b., and it requires no fractionation step by column chromatography and there is no loss by fractionation. Thus, a particulate composition containing crystalline trehalose dihydrate can be obtained in a high production yield against starch. Since the process employs a separation method of centrifugally separating the precipitated crystals to remove a syrup containing impurities without employing a total sugar

method of crystallizing a whole massecuite containing precipitated crystals and solidifying or spray-drying the resultant, the trehalose content in the resulting particulate composition containing crystalline trehalose dihydrate can be easily increased to a level of 98.0% or more to produce a high-purity particulate composition containing crystalline trehalose dihydrate.

[0075]

When crystallization is effected by an unforced cooling method, the particulate composition containing crystalline trehalose dihydrate thus produced is substantially the same powder as a conventional food-grade powder containing trehalose in terms of the property of cakeability, etc., when stored, and it usually contains particles with a particle size of 53 μm or larger but smaller than 425 μm in an amount of 70% or more of the whole particulate composition and those with a particle size of 53 μm or larger but smaller than 300 μm in an amount of 50% or more of the whole particulate composition. When crystallization is effected by a controlled cooling method or semi-controlled cooling method, the particulate composition containing crystalline trehalose dihydrate produced by the process of the present invention is a significantly, hardly cakeable powder compared to the conventional food-grade powder containing trehalose, and it usually contains particles with a particle size of 53 μm or larger but smaller than 425 μm in an amount of 80% or more of the whole particulate composition and those with a particle size of 53 μm or larger but smaller than 300 μm in an amount of 60% or more of the whole particulate composition. The particulate

composition containing crystalline trehalose dihydrate produced by the process of the present invention usually has a reducing power of 0.5% or lower when calculated by the above-mentioned Formula [5], and it is a superior particulate composition free of causing color change induced by browning even when incorporated into food products, pharmaceuticals, etc.

[0076]

Accordingly, the particulate composition produced by the process of the present invention can be used intact or used after appropriately controlling the particle size as a powdered material for food products, cosmetics, quasi-drugs, pharmaceuticals, etc. In particular, as described above, the particulate composition containing crystalline trehalose dihydrate produced by the process of the present invention that employs a controlled cooling method when in crystallization is a significantly, hardly cakeable particulate composition compared to a conventional food-grade powder containing trehalose and it can be said to be a conventionally unknown, completely novel particulate composition containing crystalline trehalose dihydrate. The particulate composition has a superior merit that it can be incorporated into a single or plurality of other powdered materials for food products, cosmetics, quasi-drugs, pharmaceuticals, etc., in the fields of producing food products, cosmetics, quasi-drugs, and pharmaceuticals, which are produced by using production plants that are designed where powdered materials will be used on the premise.

[0077]

The following experiments concretely explain the process for producing the particulate composition containing crystalline trehalose dihydrate of the present invention:
[0078]

5 <Experiment 1: Effect of the origin of CGTase on the trehalose content in enzymatic reaction solution>

The following experiments were conducted to examine how does the origin of CGTase used effect on the trehalose content in a saccharide solution, formed by an enzymatic reaction, in an enzymatic reaction system, where an
10 α -glycosyltrehalose-forming enzyme derived from a microorganism of the genus *Arthrobacter* and a trehalose-releasing enzyme derived from also a microorganism of the genus *Arthrobacter* are allowed to act on liquefied starch
15 along with a starch-debranching enzyme and CGTase, and then glucoamylase is allowed to act on the resulting mixture to form trehalose.

[0079]

<Experiment 1-1: Preparation of enzyme solution containing
20 α -glycosyltrehalose-forming enzyme and trehalose-releasing enzyme derived from microorganism of the genus *Arthrobacter*>

By the method disclosed in Example 2-1 of Patent Literature 4 (Japanese Patent Kokai No. 2000-228980), *Arthrobacter* sp. S34 strain (FERM BP-6450) was cultured to
25 obtain an about 20 L culture. To the 20 L culture was added two grams of "EGG WHITE LYSOZYME", a product name of a lysozyme specimen produced by Nagase Chemtex Corp., Osaka, Japan, to effect cell lysis in the culture by stirring at 260 rpm at 37°C for 24 hours. The resulting cell-lysed solution was

centrifuged to collect a supernatant to obtain a cell extract, which was then in usual manner salted out with ammonium sulfate. The formed precipitation was dialyzed against 10 mM sodium phosphate buffer (pH 7.0), and the dialysate was subjected to an anion-exchange chromatography using "SEPABEADS FP DA13", a gel produced by Mitsubishi Chemical Industries, Co., Tokyo, Japan, to collect an enzyme fraction. The collected fraction was a partially purified enzyme preparation containing about 15,600 units of a trehalose-releasing enzyme and about 3,100 units of an α -glycosyltrehalose-forming enzyme. The activities of the α -glycosyltrehalose-forming enzyme and the trehalose-releasing enzyme were determined in accordance with the methods disclosed in the above Patent Literature 4 (Japanese Patent Kokai No. 2000-228980).

[0080]

<Experiment 1-2: CGTases derived from various microorganisms>

The following CGTases were used as those derived from various microorganisms. A CGTase derived from *Geobacillus stearothermophilus* Tc-91 strain (FERM BP-11273), produced by Hayashibara Co., Ltd., Okayama, Japan, was used as a CGTase derived from a microorganism of the species *Geobacillus stearothermophilus*; "CONTIZYME", a product name of a commercialized CGTase sold by Amano Enzyme Inc., Aichi, Japan, was used as a CGTase derived from a microorganism of the species *Bacillus macerans*; and "TORUZYME", a product name of a commercialized CGTase sold by Novozymes Japan Ltd., Tokyo, Japan, was used as a CGTase derived from a microorganism of the species *Thermoanaerobacterium thermosulfurigenes*.

[0081]

The following CGTases were prepared as CGTases derived from microorganisms of the genus *Paenibacillus*: *Paenibacillus illinoisensis* NBRC15959 strain, *Paenibacillus* 5 *illinoisensis* NBRC15379 strain, *Paenibacillus pabuli* NBRC13638 strain, and *Paenibacillus amylolyticus* NBRC15957 strain were respectively cultured in a liquid culture medium containing 2% dextrin, 0.5% ammonium chloride, 0.05% potassium hydrogen phosphate, 0.025% magnesium sulfate, and 0.5% calcium 10 carbonate at 27°C for three days. The resulting cultures were centrifuged, and the respective supernatants were in usual manner salted out with ammonium sulfate and dialyzed to obtain crude enzyme solutions of CGTases derived from different microorganisms. The crude enzyme solutions of CGTases thus 15 obtained were respectively subjected to an anion-exchange column chromatography using DEAE-TOYOPEARL 650S GEL commercialized by Tosoh Corp., Tokyo, Japan, and a hydrophobic column chromatography using BUTYL-TOYOPEARL 650M GEL commercialized by Tosoh Corp., Tokyo, Japan, to obtain 20 partially purified CGTases. The activity of each of the CGTases derived from different microorganisms was determined according to the above-identified method and calculated with Formula [1].

[0082]

25 <Experiment 1-3: Trehalose-forming reaction>

Corn starch was suspended in water to give a concentration of 30% and admixed with 0.1% calcium carbonate. The resulting suspension was adjusted to pH 6.0 and admixed with "TERMAMEAL 60L", a product name of a thermostable

α -amylase specimen commercialized by Novozymes Japan Ltd., Tokyo, Japan, in an amount equal to 0.2% of the starch, d.s.b., to gelatinize and liquefy the starch by enzymatically reacting at 95°C for 15 min. The resulting liquefied starch solution was autoclaved at 120°C for 30 min, cooled to 51°C, adjusted to pH 5.7, admixed with two units/g starch, d.s.b., of an α -glycosyltrehalose-forming enzyme, 10 units/g starch, d.s.b., of a trehalose-releasing enzyme, 300 units/g starch, d.s.b., of an isoamylase specimen commercialized by Hayashibara Co., Ltd., Okayama, Japan, and 2 units/g starch, d.s.b., of any of the CGTases disclosed in Experiment 1-2 or prepared in Experiment 1-2, and enzymatically reacted for 64 hours. The resulting reaction solution was heated at 97°C for 30 min to inactivate the remaining respective enzymes, adjusted to pH 4.5, admixed with 10 units/g starch, d.s.b., of "GLUCOZYME #20000", a product name of a glucoamylase specimen commercialized by Nagase Chemtex Corp., Osaka, Japan, and enzymatically reacted for 24 hours. The reaction solution thus obtained was heated at 95°C for 10 min to inactivate the remaining enzyme, and subjected to the assay for trehalose content in the reaction solution disclosed in the below. Incidentally, a reaction solution, obtained by conducting an enzymatic reaction under the same condition as above except for not adding CGTase, was made as a control.

[0083]

<Experiment 1-4: Assay for trehalose content in reaction solution>

The reaction solutions obtained in Experiment 1-3 were respectively made into reaction solutions 1 to 8 shown

in Table 1, and the trehalose content in each reaction solution was determined as follows: The reaction solutions 1 to 8 were respectively prepared into 1% solutions with refined water, filtered with a 0.45 μ m membrane filter, and subjected to HPLC analysis under the following conditions, followed by calculating the trehalose content in each reaction solution based on the peak areas appeared on chromatograms by a differential refractometer and converting the values based on a dry solid basis. The results are in Table 1. The trehalose contents in the reaction solutions shown in Table 1 are the values that can be obtained in a relatively high reproducibility within a considerable variability even when the respective CGTases are repeatedly subjected to trehalose-forming reaction and glucoamylase treatment five times under the same conditions.

Analytical conditions:

HPLC system: "LC-10AD", commercialized by Shimadzu Corp., Kyoto, Japan;

Degasser: "DGU-12AM", commercialized by Shimadzu Corp., Kyoto, Japan;

Column: "MCL GEL CK04SS", commercialized by Mitsubishi Chemical Corp., Tokyo, Japan;

Sample injection volume: 20 μ l;

Eluent: Refined water;

Flow rate: 0.4 ml/min;

Temperature: 85°C;

Differential refractometer: "RID-10A", commercialized by

Shimadzu Corp., Kyoto,
Japan;

Data processing apparatus: "CHROMATOPAC C-R7A",

commercialized by

Shimadzu Corp., Kyoto,
Japan;

[0084]

Table 1

Reaction solution	Origin of CGTase	Trehalose content in reaction solution after glucoamylase treatment (% by weight, d.s.b.)
1	Control (with no addition of CGTase)	82.8
2	<i>Geobacillus stearothermophilus</i> Tc-91	84.7
3	<i>Bacillus macerans</i>	85.1
4	<i>Thermoanaerobacterium thermosulfurigenes</i>	83.4
5	<i>Paenibacillus illinoisensis</i> NBRC15959	87.6
6	<i>Paenibacillus illinoisensis</i> NBRC15379	87.4
7	<i>Paenibacillus pabuli</i> NBRC13638	87.1
8	<i>Paenibacillus amylolyticus</i> NBRC15957	86.5

[0085]

As evident from Table 1, when the CGTase derived from *Geobacillus stearothermophilus* Tc-91 strain which had been conventionally used to form trehalose (reaction solution 2), the trehalose content after glucoamylase treatment was up to 84.7%, while the trehalose content was increased to 85.1%,

when the CGTase derived from a microorganism of the species *Bacillus macerans* was used (reaction solution 3), even though the increased amount was negligible. When the CGTase derived from a microorganism of the species *Thermoanaerobacter*
5 *thermosulfurigenes* (reaction solution 4), the trehalose content was 83.4% that was lower than the case of using a conventionally used CGTase, derived from *Geobacillus stearothermophilus* Tc-91 strain (reaction solution 2), in forming trehalose.

10 [0086]

On the contrary, when the CGTases derived from microorganisms of the genus *Paenibacillus* were used (reaction solutions 5 to 8), the trehalose content of any of the solutions after glucoamylase treatment was over 86.0%, d.s.b., which was
15 significantly increased compared to that of using the CGTase derived from *Geobacillus stearothermophilus* Tc-91 strain that had been conventionally used in forming trehalose (reaction solution 2). Particularly, when the CGTases derived from *Paenibacillus illinoisensis* NBRC15959 strain (reaction
20 solution 5), *Paenibacillus illinoisensis* NBRC15379 strain (reaction solution 6), and *Paenibacillus pabuli* NBRC13638 strain (reaction solution 7) were used as CGTases, the trehalose contents were over 87.0%, revealing that trehalose-containing saccharide solutions with a high
25 trehalose content are obtained by such enzymatic reactions. Among the results of this experiment, when a CGTase derived from a microorganism of the species *Paenibacillus illinoisensis* was used, the highest trehalose content was obtained, revealing that the CGTases derived from

microorganisms of the species *Paenibacillus illinoisensis* are most preferable.

[0087]

<Experiment 2: Trehalose purity, production yield against starch, and properties of particulate compositions containing crystalline trehalose dihydrate, prepared from saccharide solutions with different trehalose contents>

[0088]

<Experiment 2-1: Preparation of test samples>

<Test samples 1 to 8>

The reaction solutions 1 to 8 with different trehalose contents, obtained in Experiment 1, were respectively purified by decoloration treatment using an activated charcoal and desalting treatment using an ion-exchange resin, and concentrated up to give a solid concentration of about 60%, d.s.b., to obtain trehalose-containing saccharide solutions 1 to 8 (containing 82.8 to 87.6% trehalose, d.s.b.) which corresponded to the reaction solutions 1 to 8, respectively.

[0089]

The above trehalose-containing saccharide solutions 1 to 8 were respectively concentrated *in vacuo* to give a solid concentration of about 85%, d.s.b., placed in a crystallizer, admixed with about 1% w/v crystalline trehalose dihydrate as a seed crystal to the volume of each saccharide solution, and crystallized under stirring conditions by unforcedly cooling the mixture from 60°C to 20°C over about 10 hours to obtain masseccutes with precipitated crystalline trehalose dihydrate. From each of the above masseccutes, a

crystalline trehalose dihydrate was collected in usual manner by a basket-type centrifuge, washed with 8% deionized water to the weight of each masseccuite, aged and dried at 40°C for eight hours, forcedly cooled by blowing to the resultants 25°C clean air for 30 min, and pulverized to obtain particulate compositions containing crystalline trehalose dihydrate. The particulate compositions containing crystalline trehalose dihydrate, which had been respectively prepared from the trehalose-containing saccharide solutions 1 to 8, were respectively made into test samples 1 to 8.

[0090]

<Test sample 9>

"TREHA" (Lot No.: 91131), a product name of a food-grade powder containing crystalline trehalose dihydrate, commercialized by Hayashibara Co., Ltd., Okayama, Japan, was used as test sample 9.

[0091]

<Experiment 2-2: Trehalose purity, production yield against starch, and cakeability of test samples 1 to 9>

<Trehalose purity>

The trehalose purity of test samples 1 to 9 were determined by the same HPLC method as in Experiment 1-3. The results are in Table 2.

[0092]

<Production yield against starch>

The production yields against starch of test samples 1 to 8 prepared in the above were obtained by calculating the weight, d.s.b., of a material starch based on the weight of each of the enzymatic reaction solutions used

in preparing the test samples and the concentration (30%) of a material starch at the initial production, dividing the weight, d.s.b., of each of the test samples 1 to 8 by the weight calculated in the above, and multiplying the resulting values by 100. The results are in Table 2.

[0093]

<Caking test>

For each test samples 1 to 9, the following experiments were conducted for the purpose of examining the cakeability of each powder. Test samples 1 to 9 were respectively weighed by one gram, separately placed in "FALCON TUBE 2059", a product name of a 14-ml polypropylene cylindrical tube, 1.7 cm in diameter and 10 cm in height, having a hemispherical bottom shape and a cap, commercialized by Becton, Dickinson and Company, New Jersey, USA. The tubes were set to a tube rack uprightly and housed in "IC-410", a product name of an incubator commercialized by Advantec Toyo Kaisha, Ltd., Tokyo, Japan, controlled at 50°C. After allowing to stand for 24 hours, the tubes were taken out from the incubator, followed by removing the cap from each tube, taking out each test sample from the tubes to place them on a black-plastic-plane plate by turning the tubes upside down slowly, and macroscopically observing the conditions of the taken-out test samples.

[0094]

The degree of caking of each test sample was judged based on the following criteria: "Caked", (+): Test sample clearly kept the hemispherical shape of the bottom of the tube even when placed on the plane plate; "Slightly caked", (±): Test sample slightly, recognizably showed the hemispherical

shape of the bottom of the tube; and "Not caked", (-): Test sample deformed and kept no hemispherical shape of the bottom of the tube. The results are shown in the column of "Caking" in Table 2.

5 [0095]

Table 2

Test sample	Trehalose purity (% by weight)	Production yield against starch (% by weight)	Caking
1	98.4	31	+
2	98.8	38	±
3	99.2	39	±
4	98.7	37	+
5	99.3	42	±
6	99.2	42	±
7	99.2	42	±
8	99.1	41	±
9	99.0	-	±

[0096]

10 As shown in Table 2, the trehalose contents, d.s.b.,
of the particulate compositions containing crystalline
trehalose dihydrate of test samples 1 to 8, i.e., the trehalose
purities were all over 98.0%, and they were high-purity
particulate compositions containing crystalline trehalose
15 dihydrate similarly as test sample 9 as a conventional
food-grade powder containing crystalline trehalose dihydrate.
Nevertheless, as for the production yield against starch, those
in test samples 2 to 4, where CGTases other than those derived

from microorganisms of the genus *Paenibacillus*, remained in a production yield against starch of as high as 39%, while test samples 5 to 8, prepared with CGTases derived from microorganisms of the genus *Paenibacillus*, showed a production yield against starch of 41 to 42% as higher than 40%, revealing that there was found a difference among the origins of CGTases used. Comparing the results in Table 1 with those in Table 2, the particulate compositions containing crystalline trehalose dihydrate prepared from enzymatic reaction solutions with higher trehalose contents after glucoamylase treatment were tended to have a higher production yield against starch, and there was found a relationship between the trehalose contents in enzymatic reaction solutions and the production yields against starch.

[0097]

Based on these results, when CGTases derived from microorganisms of the genus *Paenibacillus* (test samples 5 to 8) are used as CGTases, the trehalose contents in enzymatic reaction solutions after glucoamylase treatment are over 86.0%, and as a result it was revealed that the production yields against starch for particulate compositions containing crystalline trehalose dihydrate also increase to 41% or higher. In particular, when CGTases derived from microorganisms of the species *Paenibacillus illinoisensis* or *Paenibacillus pabuli* (test samples 5 to 7), the trehalose contents in enzymatic reaction solutions after glucoamylase treatment are over 87.0% and the production yields against starch further increase to 42%. When CGTases derived from microorganisms of the genus *Paenibacillus* are used, the levels of improvement in the

production yields against starch (the production yields against starch for test samples 5 to 8) are 3 to 4% compared to that with a conventionally used CGTase derived from *Geobacillus stearothermophilus* Tc-91 strain (test sample 2), however, it must be distinctly extraordinary the fact that the production yields against starch are improved even by 3 to 4% on an industrial scale production of particulate compositions containing crystalline trehalose dihydrate.

[0098]

As for cakeability as an important property in handling as a powder, test sample 1 prepared from a trehalose-containing saccharide solution without using any CGTase and test sample 4 prepared with a CGTase derived from a microorganism of the species *Thermoanaerobacter thermosulfurigenes* were judged as "Caked" (+) in the above caking test, while test samples 2, 3 and 5 to 8 prepared with other CGTases were judged as only "Slightly caked" ($\pm$) in the above caking test similarly as a conventional food-grade powder containing crystalline trehalose dihydrate (test sample 9). The results indicate that the particulate compositions containing crystalline trehalose dihydrate prepared by using CGTases derived from microorganisms of the genus *Paenibacillus* (test samples 5 to 8) are in no way inferior to a commercialized conventional food-grade powder containing crystalline trehalose dihydrate (test sample 9) and they are particulate compositions that can be used as powdered materials for food products, cosmetics, quasi-drugs, or pharmaceuticals similarly as a conventionally commercialized food-grade powder containing crystalline trehalose dihydrate.

[0099]

<Experiment 3: Effect of semi-controlled cooling when in crystallization on trehalose purity, production yield against starch, and cakeability>

5 In this experiment, it was examined the Effect of the application of a semi-controlled cooling method to the preparation of a particulate composition containing crystalline trehalose dihydrate on the trehalose purity, production yield against starch, and cakeability of the
10 particulate composition, when crystalline trehalose dihydrate is precipitated from the trehalose-containing saccharide solutions 1 to 8 prepared in Experiment 2-1.

[0100]

<Experiment 3-1: Preparation of test samples>

15 The trehalose-containing saccharide solutions 1 to 8 with different trehalose contents, d.s.b, prepared in Experiment 2-1, were respectively concentrated *in vacuo* up to give a solid concentration of about 85%, d.s.b., placed in a crystallizer, admixed with about one percent of crystalline
20 trehalose dihydrate as a seed crystal to the volume of each saccharide solution, followed by preparing massecuites having precipitated crystalline trehalose dihydrate similarly as in Experiment 2 except for crystallizing by a semi-controlled cooling method of cooling the solutions from 60°C to 20°C over
25 about 10 hours. The semi-controlled cooling method was carried out in such a manner of dividing the total 10 hours of cooling time into three zones with four, three, and three hours, roughly linearly cooling the liquid temperature against time in such a manner of decreasing from 60°C to 55°C over four

hours in the first zone, from 55°C to 50°C over three hours in the next zone, and from 50°C to 20°C over three hours in the last zone. Crystalline trehalose dihydrate was collected from each of the obtained massecuites in usual manner by a
5 basket-type centrifuge, washed with eight percent of deionized water to the weight of each massecuite, aged and dried at 40°C for eight hours, forcedly cooled by blowing 25°C clean air for 30 min, and pulverized into particulate compositions containing crystalline trehalose dihydrate. The particulate
10 compositions containing crystalline trehalose dihydrate, obtained from respective trehalose-containing saccharide solutions 1 to 8 by the semi-controlled cooling method, were made into test samples 1c to 8c.

[0101]

15 <Experiment 3-2: Trehalose purity, production yield against starch, and cakeability of test samples 1c to 8c>

<Trehalose purity>

The trehalose purities of test samples 1c to 8c were determined by the same HPLC method as in Experiment 1-3.

20 The results are in Table 3.

[0102]

<Production yield against starch>

The production yields against starch of test samples 1c to 8c were calculated by the same method as in
25 Experiment 2-2. The results are in Table 3 in parallel.

[0103]

<Caking test>

[0104]

The cakeability of test samples 1c to 8c were

evaluated by the same caking test as in Experiment 2-2. The results are in Table 3 in parallel.

[0105]

Table 3

5

Test sample	Trehalose purity (% by weight)	Production yield against starch (% by weight)	Caking
1c	99.0	35	±
2c	99.2	40	±
3c	99.4	41	±
4c	99.1	39	±
5c	99.6	45	-
6c	99.6	45	-
7c	99.5	44	-
8c	99.4	43	-

[0106]

As evident from Table 3, the trehalose purities of test samples 1c to 8c, prepared by applying a semi-controlled cooling method in their crystallization steps, were in the range of 99.0 to 99.6%. Comparing the result with the trehalose purities of test samples 1 to 8 obtained through crystallization by an unforced cooling method in Experiment 2 (the column of "trehalose purity" in Table 2), the trehalose purity of any of test samples 1c to 8c were increased by 0.2 to 0.6%. The result indicates that the trehalose purity of a particulate composition can be increased by applying a semi-controlled cooling method in its crystallization step.

10

15

[0107]

The production yields against starch of test samples 1c to 8c were 35 to 45%. Comparing the result with the production yields against starch of test samples 1 to 8 obtained through precipitation by an unforced cooling method in Experiment 2, the production yields against starch of test samples 1c to 8c were increased by about 2 to 4%. The result means that the application of a semi-controlled cooling method to crystallization will increase the production yield against starch, compared to the case of crystallization by an unforced cooling method. The reason why the production yield against starch of a resulting particulate composition containing crystalline trehalose dihydrate is increased by applying a semi-controlled cooling method, even though there is found no change in trehalose content in a trehalose-containing saccharide solution used in crystallization, is not sure; however, it can be speculated that a loss of trehalose is reduced when in collecting crystals from a massecuite by centrifugation and washing the collected crystals with water because crystals that have a lesser amount of microcrystals and a uniform particle size are obtained by a semi-controlled cooling method as mentioned above.

[0108]

When test samples 1c to 8c were subjected to caking test similarly as in Experiment 2-2 to examine their cakability, test samples 1c to 4c as shown in Table 3 were all judged as "Slightly caked" ($\pm$), while any of test samples 5c to 8c deformed when taken out on a plane plate and did not keep their shapes with the bottom of the tube, and thus they were judged as "Not caked" (-). These results indicate that, when a

semi-controlled cooling method is applied in crystallization, the cakeability of a resulting particulate composition is tended to be surprisingly improved compared to the case of crystallization by an unforced cooling method. Among which, 5 the conventional food-grade powder containing crystalline trehalose dihydrate (test sample 9) was judged as "Slightly caked" ($\pm$) (see, for example, Table 2) in caking test, while the particulate compositions containing crystalline trehalose dihydrate obtained from trehalose-containing saccharide 10 solutions 5 to 8 with a relatively-high trehalose content of as over as 86% (test samples 5c to 8c) by applying a semi-controlled cooling method were judged as "Not caked" (-). The fact indicates that a particulate composition containing crystalline trehalose dihydrate, which is significantly 15 hardly cakeable compared to a conventional food-grade powder containing crystalline trehalose dihydrate and is superior in property as a particulate composition, can be produced by being precipitated from a trehalose-containing saccharide solution with a relatively-high trehalose content of as over as 86% by 20 applying a semi-controlled cooling method.

[0109]

Based on the above results, it was revealed that a particulate composition containing crystalline trehalose dihydrate with a higher trehalose purity can be obtained in 25 a higher production yield against starch by applying a semi-controlled cooling method in crystallization step, compared to the case of being precipitated by an unforced cooling method. It was revealed that a particulate composition containing crystalline trehalose dihydrate,

produced from a saccharide solution with a relatively high trehalose content of as over as 86% through crystallization by a semi-controlled cooling method, is an advantageous particulate composition in that it is not caked even under the conditions where a conventional food-grade powder containing crystalline trehalose dihydrate produced by an unforced cooling method is judged as "Slightly caked" ($\pm$), and it retains a free-flowing ability as a particulate composition.

[0110]

10 <Experiment 4: Effect of the degree of crystallinity and the average crystallite diameter on the difference of cakeability of particulate composition>

Test samples 5c to 8c as particulate compositions containing crystalline trehalose dihydrate, which had been prepared from a saccharide solution with a relatively high trehalose content of over 86% by applying a semi-controlled cooling method in Experiment 3, had a superior powder property of hardly caking even though they were not so different from other test samples in terms of trehalose purity. For the purpose of revealing the reason, the degrees of crystallinity and the average crystallite diameters of the particulate compositions containing crystalline trehalose dihydrate of test samples 1 to 8 obtained in Experiment 2 and test samples 1c to 8c obtained in Experiment 3 were measured in this experiment. As a control, test sample 9 was also examined similarly.

[0111]

<Experiment 4-1: Preparation of standard samples used for measuring the degree of crystallinity>

<Standard sample A>

As test sample A, a standard specimen consisting substantially of crystalline trehalose dihydrate was prepared by recrystallizing "TREHALOSE 999" (Code No.: TH224, purity of 99.9% or higher), a product name of a reagent-grade powder containing crystalline trehalose dihydrate: In 1,000 g of refined water was dissolved by heating 1,840 g of the above reagent-grade powder containing crystalline trehalose dihydrate, and the solution was placed in a constant-temperature chamber controlled at 20°C and allowed to stand overnight to effect recrystallization. The crystalline trehalose dihydrate precipitated by the recrystallization was collected in usual manner by using a basket-type centrifuge, dried at 40°C for eight hours to obtain an about 950 g crystalline trehalose dihydrate for use as test sample A. The trehalose purity of test sample A was revealed to be 100% when determined on the HPLC method disclosed in Experiment 1.

[0112]

<Standard sample B>

A standard specimen consisting substantially of amorphous trehalose as test sample B was prepared by the following procedure: Test sample A was dissolved in an adequate amount of refined water, freeze-dried over three days, and dried *in vacuo* at 40°C or lower overnight to obtain a powder consisting substantially of amorphous trehalose for use as test sample B. The trehalose purity of test sample B was revealed to be 100% when determined on the HPLC method disclosed in Experiment 1. The moisture content of test sample B was 2.0%

when determined on the Karl Fischer method.

[0113]

<Experiment 4-2: Degree of crystallinity of test samples A and B, test samples 1 to 9, and test samples 1c to 8c>

5 <Degree of crystallinity>

The degrees of crystallinity for crystalline trehalose dihydrate of test samples A and B, test samples 1 to 9, and test samples 1c to 8c were determined as follows: Analytical values for the degrees of crystallinity of test
10 samples A and B, test samples 1 to 9, and test samples 1c to 8c were respectively determined by the Hermans' method based on the powder X-ray diffraction profiles obtained by using "X' Pert PRO MPD", a product name of a commercially available reflected-light powder X-ray diffractometer commercialized by
15 Spectris Co., Ltd., Tokyo, Japan, which irradiates a CuK α -ray (X-ray electric current: 40 mA, X-ray tube voltage: 45 kV, wavelength: 1.5405 Å), as a characteristic X-ray irradiated from a Cu target; and using a computer analysis software exclusively installed in the diffractometer. Prior to the
20 analysis of the degree of crystallinity by the Hermans' method, the particle degree and the bending factor pre-set in the software were respectively adjusted to appropriate levels for obtaining a base-line judged to be most preferable, while considering mutually overlapping peaks, diffraction intensity,
25 and scattering intensity in respective powder X-ray diffraction patterns. The Hermans' method is described in detail in P. H. Hermans and A. Weidinger, "Journal of Applied Physics, Vol. 19, pp. 491-506 (1948) and P. H. Hermans and A. Weidinger, "Journal of Polymer Science", Vol. 4, pp. 135-144

(1949).

[0114]

The degrees of crystallinity were determined by substituting into the aforesaid Formula [3] the analytical values for the degrees of crystallinity of test sample A, test sample B, and each test sample as respective analytical values H_{100} , H_0 , and H_s . Incidentally, when analyzed by the Hermans' method, the analytical value of the degree of crystallinity for test sample A (H_{100}) and that for test sample B (H_0) were respectively 50.69% and 8.59%. The results are in Table 4. For test samples A and B, their powder X-ray diffraction patterns are respectively shown in FIGs. 1 and 2.

[0115]

As found in FIG. 1, clear and sharp diffraction peaks specific to crystalline trehalose dihydrate were found in the range of diffraction angles (2θ) of 5 to 50° in the powder X-ray diffraction pattern of test sample A, but no halo specific to an amorphous form of trehalose was found. While, as found in FIG. 2, unlike the powder X-ray diffraction pattern of FIG. 1, a halo specific to an amorphous form of trehalose was clearly found as a bunch of baseline in the powder X-ray diffraction pattern of test sample B, but no diffraction peak specific to crystalline trehalose dihydrate or anhydrous crystalline trehalose was found.

[0116]

<Experiment 4-3: Powder X-ray diffractions of test samples A and B using synchrotron radiation>

This experiment was carried out to further confirm that test samples A and B were proper samples for determining

the analytical values H_{100} and H_0 , respectively: These samples were subjected to a transmitted-light powder X-ray diffraction, which detects a weak diffraction and scattering signal, using a synchrotron radiation (called "radiation", hereinafter), as an X-ray source. The analytical conditions were as follows.

[0117]
<Analytical conditions>

Powder X-ray diffractometer: Model "PDS-16", a high-speed powder X-ray diffractometer (debye Scherrer mode, camera length: 497.2 mm) commercialized by Kohzu Precision Co., Ltd., Kanagawa, Japan;

X-Ray source : "Beam line of Hyogo Prefecture (BL08B2)", a radiation light from bending electromagnet;

Wavelength : 1.2394Å (10.00 keV);

Strength : 10^9 photons/sec;

Measuring angle : 3 to 38°;

Exposure time : 600 sec;

Image recording : "IMAGING PLATE BAS-2040", an imaging plate commercialized by Fujifilm Corp., Tokyo, Japan; and

Image reading system : "BIO-IMAGE ANALYZER BAS-2500", an image analyzer commercialized by Fujifilm Corp., Tokyo, Japan.

[0118]

The measurement was conducted by using "Beam line of Hyogo Prefecture (BL08B2)" placed in "SPring-8", a

synchrotron radiation facility, 1-1-1, Kouto, Sayo-cho, Sayo-gun, Hyogo, Japan.

[0119]

Prior to powder X-ray diffraction measurement, test samples A and B were respectively ground in a mortar and sieved with a 53 μm mesh-sieve. Then, each of the resulting particulate compositions passed through the sieve was homogeneously injected into "MARKTUBE No. 14", a product name of a capillary for powder X-ray diffraction (diameter: 0.6 mm, Lindeman glass), commercialized by Toho KK, Tokyo, Japan, to give an injected sample length of about 30 mm. Successively, the capillary was cut at the end terminal of the injected sample and the open end was sealed with an adhesive. Then, the capillary was fixed on a sample mount with a clay, and the sample mount was set to the powder X-ray diffractometer to give the longitudinal direction of the capillary perpendicularly against the optic axis of the powder X-ray diffractometer. To remove adverse effect of the orientation of crystalline trehalose dihydrate on its powder X-ray diffraction profile, the measurement of the powder X-ray diffraction was carried out by allowing the sample mount to rotate at a uniform velocity and at a cycle of twice/sec.

[0120]

In the processes of analyzing the powder X-ray diffraction profiles and preparing the powder X-ray diffraction patterns of test samples A and B, background signals inherent to the powder X-ray diffractometer were eliminated from each powder X-ray diffraction profile according to conventional manner for improving the measurement

accuracy. The resulting powder X-ray diffraction patterns of test samples A and B are respectively shown in FIGs. 3 and 4. [0121]

As found in FIG. 3, the diffraction peaks specific to crystalline trehalose dihydrate appeared clearly and sharply in the range of diffraction angles (2θ) of 3 to 38° for the powder X-ray diffraction pattern of test sample A, measured on the powder X-ray diffraction using the synchrotron radiation. Since the wavelength of the synchrotron radiation (1.2394 Å) was different from that of the characteristic X-ray (1.5405 Å) compared to FIGs. 3 and 1, each diffraction peak in FIG. 3 appeared by about four fifth of the diffraction angle (2θ) of each of the corresponding peaks in FIG. 1. However, the powder X-ray diffraction patterns in FIGs. 1 and 3 were extremely well coincided with each other. The half width of each diffraction peak in FIG. 3 was evidently narrower than that in FIG. 1 and each diffraction peak in FIG. 3 showed a higher resolution than that in FIG. 1, although the strength of each diffraction peak in FIG. 3 was higher than that in FIG. 1 by nearly 50-folds. The powder X-ray diffraction pattern in FIG. 3 showed no halo specific to an amorphous form of trehalose, as shown in the later described FIG. 4. The result indicates that test sample A has a distinctly high crystallinity for crystalline trehalose dihydrate and it consists substantially of crystalline trehalose dihydrate. [0122]

As shown in FIG. 4, the powder X-ray diffraction pattern of test sample B, obtained by the powder X-ray diffraction using the synchrotron radiation, showed a

remarkable halo specific to an amorphous form of trehalose as a bunch of baseline but no diffraction peak specific to crystalline trehalose dihydrate was observed. The fact indicates that test sample B consists substantially of an

5 [0123]

The above results, obtained by using the synchrotron radiation as an X-ray source, support that test samples A and B are proper samples for defining the analytical values H_{100} and H_0 , respectively, for use in Formula [3].

10 [0124]

<Experiment 4-4: Average crystallite diameters of test sample A, test samples 1 to 9, and test samples 1c to 8c>

Based on the half widths and the diffraction angles (2 θ) of each diffraction peak in a powder X-ray diffraction pattern, crystallite diameters can be calculated. The present inventors considered that an average value of crystallite diameters (average crystallite diameter) calculated from diffraction peaks would be a parameter that defines the physical property of a particulate composition containing crystals, and they determined average crystallite diameters for test samples as particulate compositions containing crystalline trehalose dihydrate.

20 [0125]

25 Test sample A, test samples 1 to 9, and test samples 1c to 8c, excluding test sample B which is an amorphous powder and which exhibits no diffraction peak in its powder X-ray diffraction pattern, were further determined their respective average crystallite diameters by using each of their powder

X-ray diffraction patterns that had been used in determining their degrees of crystallinity. Each average crystallite diameter was determined by selecting five diffraction peaks in the powder X-ray diffraction patterns for each particulate composition containing crystalline trehalose dihydrate, i.e., diffraction peaks (the symbols "a" to "e" in FIG. 1) at diffraction angles (2θ) of 13.7° (Miller's index (hkl):101), 17.5° (Miller's index (hkl):220), 21.1° (Miller's index (hkl):221), 23.9° (Miller's index (hkl):231), and 25.9° (Miller's index (hkl):150), which located in a relatively low-angle region that was considered to be least disruptive to diffraction peak width due to heterogeneous strain of crystallite, and which were well separated from other diffraction peaks; calibrating the half widths and diffraction angles (2θ) of the diffraction peaks based on a measured value determined by using "X' pert Highscore Plus" as an analytical processing computer software exclusively installed in the powder X-ray diffractometer, and a silicon ("Si640d", provided by NIST: National Institute of Standards and Technology, as a standard sample for X-ray diffraction) as a standard sample; calculating crystallite diameters based on the above Formula [4]; and averaging the above five data. The results are in Table 4 in parallel.

[0126]

The results on the trehalose purity and the caking test on particulate compositions for test samples 1 to 9 and test samples 1c to 8c are respectively transcribed from Tables 2 and 3 and shown in parallel in Table 4. Test samples A and B, used as standard specimens for determining degree of

crystallinity, were respectively subjected to the same caking test as in Experiments 2-2 and 3-2 and evaluated their cakeability. The results are in Table 4 in parallel.

[0127]

5

Table 4

Test sample	Trehalose purity (% by weight)	Degree of crystallinity (%)	Average crystallite diameter (Å)	Caking
A	100	100	3,910	-
B	100	0	-	+
1	98.4	78.7	2,150	+
2	98.8	85.1	2,540	±
3	99.2	85.3	2,660	±
4	98.7	80.8	2,200	+
5	99.3	88.1	2,830	±
6	99.2	87.7	2,750	±
7	99.2	87.4	2,670	±
8	99.1	86.6	2,610	±
9	99.0	85.4	2,590	±
1c	99.0	85.7	2,540	±
2c	99.2	87.3	2,780	±
3c	99.4	88.6	2,850	±
4c	99.1	88.3	2,630	±
5c	99.6	96.0	3,580	-
6c	99.6	94.2	3,490	-
7c	99.5	93.3	3,300	-
8c	99.4	91.0	3,210	-

[0128]

The average crystallite diameter of test sample A (trehalose purity: 100.0%, degree of crystallinity: 100.0%), used as a standard sample for determining analytical value H_{100} in measuring the degree of crystallinity, was 3,910 Å. As shown in Table 4, test sample A was judged as "Not caked" (-) in the caking test. In contrast, test sample B used as a standard sample for determining the analytical value H_0 (trehalose purity: 100.0%, degree of crystallinity: 0.0%) was judged as "Caked" (+) because it still kept its hemispherical shape of the bottom of a tube even when taken out from the tube and placed on a plane plate. The hemispherical shape of test sample B was not collapsed when a slight vibration was merely given to the plate. While, the trehalose purity and the degree of crystallinity of test sample 9 as a conventionally commercialized food-grade crystalline trehalose dihydrate were respectively 99.0% and 85.4%.

[0129]

As shown in the column of "Degree of crystallinity" in Table 4, the degrees of crystallinity of test samples 1 to 8, which had been obtained by precipitation by an unforced cooling method in the crystallization step, were in the range of 78.7 to 88.1%, while those of test samples 1c to 8c, which had been obtained by applying a semi-controlled cooling method in the crystallization step, were in the range of 85.7 to 96.0%. Comparing the degrees of crystallinity of test samples 1 to 8 with those of test samples 1c to 8c in terms of the difference of crystallization methods, it was revealed that the degrees of crystallinity of test samples 1c to 8c obtained by a

semi-controlled cooling method were increased by 3.1 to 7.9% compared to those of test samples 1 to 8 obtained by an unforced cooling method, though the degrees of crystallinity of test samples 1c to 8c varied one another.

5 [0130]

The results in Table 4 indicate that the degree of crystallinity of a particulate composition correlates with its cakeability. More specifically, as shown in Table 4, every test sample A and test samples 5c to 8c with a degree of crystallinity of 90% or higher were judged as "Not caked" (-), while every test samples 2, 3, and 5 to 9 and test samples 1c to 4c with a degree of crystallinity of 85% or higher but less than 90% were judged as "Slightly caked" ($\pm$), and every test sample B and test samples 1 and 4 with a degree of crystallinity of less than 85% were judged as "Caked" (+). The fact indicates that the degree of crystallinity can be a potent index for defining a hardly cakeable particulate composition containing crystalline trehalose dihydrate.

[0131]

20 Further the above result indicates that, in the process for producing a particulate composition containing crystalline trehalose dihydrate, the degree of crystallinity for crystalline trehalose dihydrate becomes 90% or higher by increasing the trehalose content in a reaction solution up to over 86.0% and then applying a semi-controlled cooling method in the following crystallization step, resulting in obtaining a significantly, hardly cakeable particulate composition containing crystalline trehalose dihydrate compared to a conventional food-grade powder containing crystalline

trehalose dihydrate.

[0132]

As shown in the column of "Average crystallite diameter" in Table 4, the average crystallite diameters of test samples 1 to 8 obtained by crystallization by an unforced cooling method in the crystallization step were in the range of 2,150 to 2,830 Å, while those of test samples 1c to 8c prepared by a semi-controlled cooling method in the crystallization step were in the range of 2,540 to 3,580 Å. Comparing test samples 1c to 8c with test samples 1 to 8 in terms of their average crystallite diameters, it was revealed that the average crystallite diameters of test samples 1c to 8c obtained by a semi-controlled cooling method were increased by 190 to 750 Å compared to those of test samples 1 to 8 obtained by an unforced cooling method, though the average crystallite diameters of test samples 1c to 8c varied one another. The result shows that the application of a semi-controlled cooling method in the crystallization step for crystalline trehalose dihydrate is a superior method for obtaining a particulate composition containing crystalline trehalose dihydrate with a relatively large average-crystallite-diameter.

[0133]

In test samples 1 to 8 and test sample 1c to 8c, there was found a tendency that the higher the trehalose purity and the degree of crystallinity for crystalline trehalose dihydrate in particulate compositions, the larger the average crystallite diameter. This tendency indicates that the average crystallite diameter of a particulate composition containing crystalline trehalose dihydrate has a certain

correlation with both the trehalose purity and the degree of crystallinity of a particulate composition containing crystalline trehalose dihydrate, considering both the fact that the average crystallite diameter of test sample 1, which
5 had a trehalose purity of 100.0% and a degree of crystallinity of 100.0%, was 3,910 Å and that test sample 9 as a food-grade powder containing crystalline trehalose dihydrate was 2,590 Å.

[0134]

10 Further, the results in Table 4 indicate that the average crystallite diameter also correlates with the cakeability of a particulate composition. In detail, as shown in Table 4, test sample A and test samples 5c to 8c, which had an average crystallite diameter of 3,210 Å or larger, were all
15 judged as "Not caked" (-); test samples 2, 3, and 5 to 9 and test samples 1c to 4c, which had an average crystallite diameter in the range of 2,500 Å or larger but less than 3,200 Å, were all judged as "Slightly caked" (±); and test sample B and test
20 samples 1 to 4, which had an average crystallite diameter of less than 2,500 Å, were all judged as "Caked" (+). The fact indicates that, in addition to the degree of crystallinity, the average crystallite diameter can also be a potent index for defining a hardly cakeable crystalline trehalose dihydrate.

25 [0135]

<Experiment 5: Powder characteristics of test samples (storage stability, solubility in water)>

Tests for storage stability and solubility in water were conducted for the purpose of further revealing the

property of test samples 1 to 9 and test samples 1c to 8c.
[0136]

<Experiment 5-1: Storage stability test>

To confirm whether the caking test conducted in
5 Experiments 2-2, 3-2, etc., are acceptable as a test for
evaluating the cakeability of a particulate composition
containing crystalline trehalose dihydrate when in actual
storage, test samples A and B obtained by the method in
Experiment 4-1, test samples 1 to 9 obtained in Experiment 2,
10 and test samples 1c to 8c obtained in Experiment 3 were
subjected to a storage stability test designed by considering
conditions, circumstances, and period for actually storing
particulate compositions containing crystalline trehalose
dihydrate as commercially distributed products.

15 [0137]

One hundred and fifty grams of any one of test
samples A and B, test samples 1 to 9, and test samples 1c to
8c was weighed, placed in "UNI-PACK F-4", a product name of
a polyethylene bag, 17 cm x 12 cm, commercialized by
20 Seisannipponsha Ltd., Tokyo, Japan, and sealed therein in a
deaerated condition to obtain three polyethylene bags for each
test sample. A 13.2-kg-weight was placed on each polyethylene
bag to homogeneously put a load over the upper surface of each
bag so as to give a load of 648 kg/m^2 for one surface of each
25 bag and stored at the conditions for 60 days under circumstances
free of a relatively high temperature and humidity. By
comparison, a product of a food-grade powder containing
crystalline trehalose dihydrate usually has a 20-kg packing
style, and about 10 bags of which are piled up when stored in

a storehouse, etc. The load of 648 kg/m² for one surface of a polyethylene bag corresponds to the load received by the lowest bag among the piled-up 10 bags. After 60 days storage, each test sample was taken out from each polyethylene bag, sieved with a sieve having a pore size of 425 µm, and the weights of powders passed through or not passed through the sieve were respectively weighed, followed by determining the weight percentage (%) of particles with a particle size of 425 µm or larger to the whole powder and averaging the data from three bags for each of the test samples tested to evaluate the caking of each particulate composition after 60 days storage. The caking of particulate compositions were evaluated as follows: "Not caked" (-), where particles with a particle size of 425 µm or larger are less than 30% of the whole particulate composition; and "Caked" (+), where particles with a particle size of 425 µm or larger are 30% or more of the whole particulate composition. The criterion of judgement was made as 30% because the dissolution of a particulate composition and the mixing or kneading thereof with other particulate composition(s) will generally be affected when the ratio of particles with a particle size of 425 µm or larger in the particulate composition exceeds 30%. The results are in Table 5.

[0138]

<Experiment 5-2: Test for solubility in water>

Each test sample was weighed by 0.25 g and placed in "FALCON TUBE 2059", a product name of a 14-ml polypropylene cylindrical tube having a hemispherical bottom shape and a cap, commercialized by Becton, Dickinson and Company, New Jersey,

USA. To each tube with each test sample was added five milliliters of deionized water, and the tubes were incubated for 30 min in a 50°C constant temperature water bath, upset two times, and then kept at 50°C for 15 min to examine the solubility under the conditions. It was judged as "Passable" when a particulate composition is macroscopically judged to be completely dissolved, while it was judged as "Impassable" when an insoluble residue is macroscopically observed. The results are in Table 5 in parallel.

10 [0139]

Table 5

Test sample	Storage stability	Solubility in water
A	-	Impassable
B	+	Passable
1	+	Passable
2	+	Passable
3	+	Passable
4	+	Passable
5	+	Passable
6	+	Passable
7	+	Passable
8	+	Passable
9	+	Passable
1c	+	Passable
2c	+	Passable
3c	+	Passable
4c	+	Passable
5c	-	Passable

(Continued)

6c	-	Passable
7c	-	Passable
8c	-	Passable

[0140]

As shown in the column of "Storage stability", in the storage stability test where each test sample was stored for 60 days under a circumstance free of a relatively high temperature and humidity, test samples 1 to 9, and test samples 1c to 4c, which had a degree of crystallinity for trehalose of less than 90.0% and an average crystallite diameter of 2,850 Å or smaller, were judged as "Caked" (+), while test sample A and test samples 5c to 9c, which had a degree of crystallinity of 91.0% or more but not more than 96.0% and an average crystallite diameter of 3,210 Å or larger, were judged as "Not caked" (-). The results indicate that the test samples that were judged as "Caked" (+) or "Slightly caked" (±) in the caking tests conducted in Experiments 2-2 and 3-2, etc., are judged as "Caked" (+) in this storage test, while test samples that were judged as "Not caked" (-) in the caking tests conducted in Experiments 2-2 and 3-2, etc., are judged as "Not caked" (-) in this storage test. The fact indicates that the caking test conducted in Experiments 2-2 and 3-2, etc., is proper as a test for evaluating the cakeability of particulate compositions containing crystalline trehalose dihydrate under their actual storage circumstances.

[0141]

As shown in the column of "Solubility in water" in Table 5, the solubility in water of test sample A, which

had a degree of crystallinity of 100% and an average crystallite diameter of 3,910 Å, was judged as "Impassable", while those of test samples 1 to 9 and test samples 1c to 8c, which had a degree of crystallinity of 96.0% or lower and an average crystallite degree of 3,580 Å or lower, were all judged as "Passable". The result indicates that, when the degree of crystallinity and the average crystallite diameter of a particulate composition containing crystalline trehalose dihydrate are increased to the levels of test sample A, and in other words, when they are increased to the levels of a reagent-grade powder containing crystalline trehalose dihydrate, the solubility in water becomes worse as a different problem from cakeability.

[0142]

<Experiment 6: Partial amino acid sequences common in CGTases more suitable for producing trehalose>

To characterize a more suitable CGTase for producing trehalose, the amino acid sequences (SEQ ID NOs: 1 to 3) of the aforesaid CGTases, derived from microorganisms of the genus *Paenibacillus* having an improved effect of increasing the trehalose content in enzymatic reaction solutions, i.e., which are respectively derived from *Paenibacillus illinoisensis* NBRC15379 strain, *Paenibacillus pabuli* NBRC13638 strain, and *Paenibacillus amylolyticus* NBRC15957 stain, were compared with the amino acid sequences (SEQ ID NOs: 4 to 6) of the CGTases, which are respectively derived from the aforesaid *Geobacillus stearothermophilus* Tc-91 strain and microorganisms of the species *Bacillus macerans* and *Thermoanaerobacter thermosulfurigenes*, which

have a lower effect of increasing the trehalose content in an enzymatic reaction solution than those of the microorganisms of the genus *Paenibacillus*. All the amino acid sequences represented by SEQ ID NOs: 1 to 3, which were used in the above amino acid sequence comparison, are those which are encoded by the base sequences determined by the present applicant's independent cloning for the respective CGTase genes derived from *Paenibacillus illinoisensis* NBRC15379 strain, *Paenibacillus pabuli* NBRC13638 strain, and *Paenibacillus amylolyticus* NBRC15957 stain. The amino acid sequences of SEQ ID NOs: 4 and 5 are of the CGTases derived from *Geobacillus stearothermophilus* (*Bacillus stearothermophilus* as the old classification) Tc-91 strain, disclosed in Japanese Patent Kokai No. 135581/86 and determined independently by the same applicant as the present invention, and from a microorganism of the species *Bacillus macerans*. For comparison, although the amino acid sequence of SEQ ID NO: 5 is not for "CONTIZYME", a product name of a CGTase derived from a microorganism of the species *Bacillus macerans*, commercialized by Amano Enzyme Inc., Aichi, Japan, used in Experiment 1, it was used as a substitution because it is an amino acid sequence of a CGTase derived from a microorganism belonging to the same species *Bacillus macerans*. As the amino acid sequence of a CGTase derived from a microorganism of the species *Thermoanaerobacter thermosulfurigenes*, the one registered in "GenBank", a gene database, under the accession number of 35484 was used.

[0143]

In the above-mentioned comparison of amino acid sequences, the following partial amino acid sequences of (a)

to (d) were observed in CGTases that have a superior effect of increasing the trehalose content in an enzymatic reaction solution, i.e., such partial amino acid sequences commonly exist in the CGTases derived from the above microorganisms of the genus *Paenibacillus* but do not exist in CGTases, whose trehalose-content-increasing effects in enzymatic reaction solutions are not so high, namely CGTases derived from respective *Geobacillus stearothermophilus*, *Bacillus macerans*, and *Thermoanaerobacter thermosulfurigenes*:

- (a) Gly-Ser-X₁-Ala-Ser-Asp;
- (b) Lys-Thr-Ser-Ala-Val-Asn-Asn;
- (c) Lys-Met-Pro-Ser-Phe-Ser-Lys; and
- (d) Val-Asn-Ser-Asn-X₂-Tyr.

(Wherein X₁ means Ala or Ser and X₂ means Ala or Thr, respectively.)

[0144]

Based on the above results, CGTases which are more suitable for the process of producing trehalose of the present invention, namely CGTases, which can increase the trehalose content to over 86.0% in an enzymatic reaction solution, can be characterized to have the above-identified partial amino acid sequences of (a) to (d).

[0145]

The present invention will be explained in more detail based on the following Examples but it should never be restricted thereby.

Example 1

[0146]

<Production of particulate composition containing crystalline

trehalose dihydrate>

Corn starch was suspended in water to give a 30% suspension, admixed with calcium carbonate to give a final concentration of 0.1%, and adjusted to pH 6.0. To the resulting solution was added "TERMAMEAL 60L", a product name of a thermostable α -amylase specimen commercialized by Novozymes Japan Ltd., Tokyo, Japan, in an amount equal to 0.2% of the weight, d.s.b., of the starch, and subjected to an enzymatic reaction at 98 to 100°C for 15 min to gelatinize and liquefy the starch. The resulting liquefied starch solution was autoclaved at 125°C for 15 min, cooled to 51°C, admixed with a partially purified enzyme solution containing an α -glycosyltrehalose-forming enzyme and a trehalose-releasing enzyme, prepared by the method in Experiment 1-1, in respective amounts of 2 and 10 units/g starch, further admixed with an isoamylase produced by Hayashibara Co., Ltd., Okayama, Japan, in an amount of 300 units/g starch and a CGTase derived from *Paenibacillus illinoisensis* NBRC15959 strain, prepared by the method in Experiment 1-2, in an amount of two units/g starch, and further enzymatically reacted for about 70 hours. Thereafter, the enzymatic reaction solution was heated at 97°C for 30 min to inactivate the remaining enzymes, adjusted to pH 4.5, admixed with "GLUCOZYME #20000", a product name of a glucoamylase specimen commercialized by Nagase ChemteX Corp., Osaka, Japan, in an amount of 10 units/g starch, and enzymatically reacted for 24 hours to obtain an enzymatic reaction solution with a trehalose purity or a trehalose content of 87.4%, d.s.b. The enzymatic reaction solution thus obtained was heated to inactivate the remaining enzyme and,

in usual manner, decolorized and filtered with an activated charcoal. The filtrate was desalted with a cation-exchange resin (H^+ -form) and an anion-exchange resin (OH^- -form), concentrated *in vacuo* into a concentrate with a solid content of about 85%. The concentrate was placed in a crystallizer, admixed with "TREHALOSE 999" (Code No.: TH224, trehalose purity: 99.9% or higher), a product name of a reagent-grade powder containing crystalline trehalose dihydrate, commercialized by Hayashibara Co., Ltd., Okayama, Japan, as a seed crystal, in an amount equal to two percent of the solid contents, adjusted to 55°C, and unforcedly cooled to 15°C over 24 hours under gentle stirring conditions to precipitate crystalline trehalose dihydrate. The crystals were collected by a basket-type centrifuge, spayed with refined water in an amount equal to about five percent of the weight of a massecuite, aged and dried at 50°C for two hours, cooled by blowing 20°C air for 10 min, and pulverized to obtain a particulate composition containing crystalline trehalose dihydrate, which contained, on a dry solid basis, 99.4% trehalose, 0.3% D-glucose, 0.06% 4-O- α -glucosyltrehalose, and 0.09% 6-O- α -glucosyltrehalose, in a production yield against starch of about 42%.

[0147]

According to the production process of this example, a particulate composition containing crystalline trehalose dihydrate can be produced at a high production yield against starch of about 42%. The degree of crystallinity for crystalline trehalose dihydrate, the average crystallite diameter, and the reducing power of the whole particulate

composition of the particulate composition containing crystalline trehalose dihydrate produced by the process of this example were respectively 88.4%, 2,850 Å, and 0.4%. For comparison, the measurement for the above degree of crystallinity was determined on the Hermans' method using the analytical values H_{100} and H_0 obtained in Experiment 4-2. The measurement of the particle size distribution of the product revealed that it contained particles with a particle size of 53 µm or larger but smaller than 425 µm in an amount of 73.1%, those with a particle size of 53 µm or larger but smaller than 300 µm in an amount of 68.6%, and those with a particle size of 425 µm or larger in an amount of 8.2%. The product can be used as a material for food products, cosmetics, quasi-drugs, and pharmaceuticals similar to a conventional food-grade powder containing crystalline trehalose dihydrate.

Example 2

[0148]

<Production of particulate composition containing crystalline trehalose dihydrate>

An enzymatic reaction solution with a trehalose purity or a trehalose content of 87.6%, d.s.b., was obtained by conducting a trehalose-forming reaction and a glucoamylase treatment by a similar method as in Example 1, except for setting an enzymatic reaction of 40 hours by using an α-glycosyltrehalose-forming enzyme and a trehalose-releasing enzyme in respective amounts of 3 units and 15 units per g starch and using a CGTase derived from *Paenibacillus illinoisensis* NBRC15379 strain obtained by the method in Experiment 1-2. The enzymatic reaction solution thus obtained was heated to

inactivate the remaining enzymes and, in usual manner, decolored and filtered with an activated charcoal. The filtrate was desalted with a cation-exchange resin (H^+ -form) and an anion-exchange resin (OH^- -form), concentrated *in vacuo* into a concentrate with a solid content of about 85%. The concentrate was placed in a crystallizer, admixed with "TREHALOSE 999" (Code No.: TH224, trehalose purity: 99.9% or higher), a product name of a reagent-grade powder containing crystalline trehalose dihydrate, commercialized by Hayashibara Co., Ltd., Okayama, Japan, as a seed crystal, in an amount equal to one percent of the solid contents, and adjusted to 60°C. Thereafter, the resulting trehalose-containing solution was cooled up to 15°C over a total time of 24 hours by a semi-controlled cooling method of successively cooling from 60°C to 50°C over 12 hours, from 50°C to 40°C over six hours, and then from 40°C to 15°C over six hours under gentle stirring conditions to precipitate crystalline trehalose dihydrate. The crystals were collected by a basket-type centrifuge, spayed with refined water in an amount equal to about 5% of the weight of a massecuite, aged and dried at 50°C for two hours, cooled by blowing 20°C air for 20 min, and pulverized to obtain a particulate composition containing crystalline trehalose dihydrate, which contained, on a dry solid basis, 99.6% trehalose, 0.07% D-glucose, 0.04% 4-O- α -glucosyltrehalose, and 0.06% 6-O- α -glucosyltrehalose, in a production yield against starch of about 45%.

[0149]

The degree of crystallinity for crystalline trehalose dihydrate, the average crystallite diameter, and the

reducing power of the whole particulate composition of the particulate composition containing crystalline trehalose dihydrate produced were respectively 95.6%, 3,520 Å, and 0.15%. For comparison, the measurement for the above degree of crystallinity was determined on the Hermans' method using the analytical values H_{100} and H_0 obtained in Experiment 4-2. The measurement of the particle size distribution of the product revealed that it contained particles with a particle size of 53 µm or larger but smaller than 425 µm in an amount of 83.3%, those with a particle size of 53 µm or larger but smaller than 300 µm in an amount of 72.5%, and those with a particle size of 425 µm or larger in an amount of 6.9%. When subjected to a caking test by the same method as in Experiments 2-2, 3-2, etc., the product was judged as "Not caked" (-). Also, the product was judged as "Passable" when tested for solubility in water by the same method as in Experiment 5.

[0150]

According to the production process of this example, a particulate composition containing crystalline trehalose dihydrate can be produced in a production yield against starch of as high as about 45%. Although, in terms of the purity of trehalose, the particulate composition containing crystalline trehalose dihydrate produced by the process of this example is not so different from "TREHA", a product name of a conventional food-grade powder containing crystalline trehalose dihydrate, commercialized by Hayashibara Co., Ltd., Okayama, Japan, as a food material or the like, it is a significantly, hardly cakeable particulate composition compared to the conventional food-grade powder, as well as being easily stored and handled. The product

is similar to the conventional food-grade powder in that it is a particulate composition containing crystalline trehalose dihydrate; the more easily stored and handled, the more preferably used as a material for food products, cosmetics, quasi-drugs, pharmaceuticals, etc.

Example 3

[0151]

<Production of particulate composition containing crystalline trehalose dihydrate>

When a trehalose-forming reaction was carried out similarly as in Example 1 except for using, as a CGTase, the one derived from *Paenibacillus pabuli* NBRC13638 strain prepared by the method in Experiment 1-2, the trehalose content in the resulting enzymatic reaction solution after glucoamylase treatment was 87.2%, d.s.b. The enzymatic reaction solution thus obtained was heated to inactivate the remaining enzyme and, in usual manner, decolored and filtered with an activated charcoal. The filtrate was desalted with a cation-exchange resin (H⁺-form) and an anion-exchange resin (OH⁻-form), concentrated *in vacuo* into a concentrate with a solid content of about 85%. The concentrate was placed in a crystallizer, admixed with "TREHALOSE 999" (Code No.: TH224, trehalose purity: 99.9% or higher), a product name of a reagent-grade powder containing crystalline trehalose dihydrate, commercialized by Hayashibara Co., Ltd., Okayama, Japan, as a seed crystal, in an amount equal to one percent of the solid contents, adjusted to 60°C, and cooled over 24 hours in such a manner of cooling from 60°C to 45°C over 15 hours and from 45°C to 20°C over 9 hours under gentle stirring

conditions by a two-step semi-controlled cooling method to precipitate crystalline trehalose dihydrate. The crystals were collected by a basket-type centrifuge, spayed with refined water in an amount equal to about 5% of the weight of a massecuite, 5 aged and dried at 50°C for two hours, cooled by blowing 20°C air for 10 min, and pulverized to obtain a particulate composition containing crystalline trehalose dihydrate, which contained, on a dry solid basis, 99.2% trehalose, 0.4% D-glucose, 0.06% 4-O- α -glucosyltrehalose, and 0.10% 10 6-O- α -glucosyltrehalose, in a production yield against starch of about 44%.

[0152]

The degree of crystallinity for crystalline trehalose dihydrate, the average crystallite diameter, and the 15 reducing power of the whole particulate composition of the particulate composition containing crystalline trehalose dihydrate were respectively 92.6%, 3,130 Å, and 0.5%. For comparison, the measurement for the above degree of crystallinity was determined on the Hermans' method using the 20 analytical values H_{100} and H_0 obtained in Experiment 4-2. The measurement of the particle size distribution of the product revealed that it contained particles with a particle size of 53 μm or larger but smaller than 425 μm in an amount of 75.2%, those with a particle size of 53 μm or larger but smaller than 25 300 μm in an amount of 69.3%, and those with a particle size of 425 μm or larger in an amount of 7.8%. When subjected to a caking test by the same method as in Experiments 2-2, 3-2, etc., the product was judged as "Not caked" (-). Also, the product was judged as "Passable" when tested for solubility in water

by the same method as in Experiment 5.

[0153]

According to the production process of this example, a particulate composition containing crystalline trehalose dihydrate can be produced in a high production yield against starch of about 44%. Although, in terms of the purity of trehalose, the particulate composition containing crystalline trehalose dihydrate produced by the process of this example is not so different from "TREHA", a product name of a conventional food-grade powder containing crystalline trehalose dihydrate, commercialized by Hayashibara Co., Ltd., Okayama, Japan, as a food material or the like, it is a significantly, hardly cakeable particulate composition compared to the conventional food-grade powder, as well as being easily stored and handled. The product is similar to the conventional food-grade powder in that it is a particulate composition containing crystalline trehalose dihydrate; the more easily stored and handled, the more preferably used as a material for food products, cosmetics, quasi-drugs, pharmaceuticals, etc.

20 Example 4

[0154]

<Production of particulate composition containing crystalline trehalose dihydrate>

An enzymatic reaction solution with a trehalose purity or a trehalose content of 86.6%, d.s.b., was obtained by conducting a trehalose-forming reaction and a glucoamylase treatment similarly as the method in Example 1, except for using tapioca starch as a material starch and a CGTase derived from *Paenibacillus amylolyticus* NBRC15957 strain, as a CGTase,

obtained by the method in Experiment 1-2. The enzymatic reaction solution thus obtained was heated to inactivate the remaining enzyme and, in usual manner, decolored and filtered with an activated charcoal. The filtrate was desalted with
5 a cation-exchange resin (H^+ -form) and an anion-exchange resin (OH^- -form), concentrated *in vacuo* into a concentrate with a solid content of about 86%. The concentrate was placed in a crystallizer, admixed with "TREHALOSE 999" (Code No.: TH224, trehalose purity: 99.9% or higher), a product name of a
10 reagent-grade powder containing crystalline trehalose dihydrate, commercialized by Hayashibara Co., Ltd., Okayama, Japan, as a seed crystal, in an amount equal to one percent of the solid contents, adjusted to 60°C, and cooled to 15°C over 24 hours in total in such a manner of cooling from 60°C
15 to 50°C over eight hours, from 50°C to 35°C over eight hours, and from 35°C to 15°C over eight hours under gentle stirring conditions by a three-step semi-controlled cooling method to precipitate crystalline trehalose dihydrate. The crystals were collected by a basket-type centrifuge, spayed with refined
20 water in an amount equal to about 5% of the weight of a massecuite, aged and dried at 50°C for two hours, cooled by blowing 20°C air for 20 min, and pulverized to obtain a particulate composition containing crystalline trehalose dihydrate, which contained, on a dry solid basis, 99.4% trehalose, 0.06%
25 D-glucose, 0.04% 4-O- α -glucosyltrehalose, and 0.06% 6-O- α -glucosyltrehalose, in a production yield against starch of about 43%.

[0155]

The degree of crystallinity for crystalline

trehalose dihydrate, the average crystallite diameter, and the reducing power of the whole particulate composition of the particulate composition containing crystalline trehalose dihydrate were respectively 93.3%, 3,280 Å, and 0.13%. For
5 comparison, the measurement for the above degree of crystallinity was determined on the Hermans' method using the analytical values H_{100} and H_0 obtained in Experiment 4-2. The measurement of the particle size distribution of the product revealed that it contained particles with a particle size of
10 53 µm or larger but smaller than 425 µm in an amount of 80.7%, those with a particle size of 53 µm or larger but smaller than 300 µm in an amount of 74.4%, and those with a particle size of 425 µm or larger in an amount of 7.1%. When subjected to a caking test by the same method as in Experiments 2-2, 3-2, etc.,
15 the product was judged as "Not caked" (-). Also, the product was judged as "Passable" when tested for solubility in water by the same method as in Experiment 5.

[0156]

According to the production process of this example,
20 a particulate composition containing crystalline trehalose dihydrate can be produced in a production yield against starch of as high as about 43%. Although, in terms of the purity of trehalose, the particulate composition containing crystalline trehalose dihydrate produced by the process of this example is
25 not so different from "TREHA", a product name of a conventional food-grade powder containing crystalline trehalose dihydrate, commercialized by Hayashibara Co., Ltd., Okayama, Japan, as a food material or the like, it is a significantly, hardly cakeable particulate composition compared to the conventional food-grade

powder, as well as being easily stored and handled. The product is similar to the conventional food-grade powder in that it is a particulate composition containing crystalline trehalose dihydrate; the more easily stored and handled, the more preferably used as a material for food products, cosmetics, quasi-drugs, pharmaceuticals, etc.

Example 5

[0157]

<Preparation of recombinant CGTase and mutant CGTase and production of particulate composition containing crystalline trehalose dihydrate by using the same>

A production of a particulate composition containing crystalline trehalose dihydrate was conducted by using, in place of the CGTase derived from *Paenibacillus illinoisensis* NBRC15379 strain used in Example 2, two types of enzymes of a recombinant (wild type) CGTase obtained by expressing a CGTase gene derived from the above microorganism in *E. coli* as a host, and a mutant CGTase, having a replacement of one amino acid residue in the amino acid sequence with other amino acid residue, prepared by introducing a site-specific mutagenesis into the above wild-type CGTase.

[0158]

<Preparation of recombinant CGTase>

By using a CGTase gene having the base sequence of SEQ ID NO:7, derived from *Paenibacillus illinoisensis* NBRC15379 strain, which had been cloned from the microorganism and possessed by the present inventors, a recombinant DNA for expression, which contains a gene encoding a natural (wild type) CGTase, was constructed by mutating the above CGTase gene

without altering the amino acid sequence encoded by the CGTase gene to introduce or delete a restriction enzyme site(s), etc., and recombining the resultant into an expression plasmid vector "pRSET-A", produced by Invitrogen Corporation, CA, USA. The structure of the obtained recombinant DNA "pRSET-iPI" is shown in FIG. 6. *E. coli* BL21 (DE3), produced by Stratagene, CA, USA, was transformed in usual manner with the recombinant DNA "pRSET-iPI" to obtain a transformant "BL21-RSET-iPI" having the recombinant DNA. Thereafter, the transformant was aerobically cultured at 37°C for 24 hours in T medium (containing 12 g bacto-tryptone, 24 g bacto-yeast extract, 5 ml of glycerol, 17 mM potassium phosphate, and 72 mM dipotassium phosphate per liter of the medium) containing 100 µl/ml of ampicillin (Na-salt). The resulting culture was centrifuged, and the obtained cells were subjected to a disruption treatment with "ULTRA SONIC HOMOGENIZER UH-600", a product name of an ultrasonic disruptor, commercialized by MST Co., Ltd., Tokyo, Japan, and centrifuged, followed by assaying the supernatant for CGTase activity (starch decomposing activity) to have an enzymatic activity of about 12.8 units/ml when converted into the activity per one milliliter of the culture liquid. The supernatant of the disrupted solution was in usual manner salted out with ammonium sulfate and dialyzed to obtain a crude enzyme solution of a recombinant CGTase, followed by purifying the crude enzyme solution by subjecting it to an anion-exchange column chromatography using DEAE-TOYOPEARL 650S GEL, produced by Tosoh Corp., Tokyo, Japan, and a hydrophobic column chromatography using BUTYL-TOYOPEARL 650M GEL commercialized by Tosoh Corp., Tokyo, Japan, into a partially purified

specimen of a recombinant CGTase.

[0159]

<Preparation of mutant CGTase>

Two types of mutant CGTases with one amino acid substitution was prepared by introducing a site specific mutation into a natural (wild type) CGTase gene derived from the above-identified *Paenibacillus illinoisensis* NBRC15379 strain in usual manner, and expressing the obtained mutant CGTase gene in *E. coli*. When in introducing the amino acid substitution into the CGTase, any amino-acid substitution mutation is avoided from the following sites and a mutation site is selected from those other than the following sites: The amino acid residues from the 133rd aspartic acid residue to the 138th histidine residue (Asp 133 to His 138), from the 223rd glycine residue to the 231st histidine residue (Gly 223 to His 231), from the 255th glutamic acid residue to the 258th leucine residue (Glu 255 to Leu 258), and from the 321st phenylalanine residue to the 326th aspartic acid residue (Phe 321 to Asp 326) in the amino acid sequence of SEQ ID NO: 1 corresponding to the amino acid sequence of a CGTase derived from *Paenibacillus illinoisensis* NBRC15379 strain, i.e., amino acid sequences corresponding to four conserved regions commonly conserved in the enzyme group classified as α -amylase family; and the amino acid residues from the 259th glycine residue to the 264th aspartic acid residue (Gly 269 to Asp 264), from the 331st lysine residue to the 337th asparagine residue (Lys 331 to Asp 337), from the 375th lysine residue to the 381st lysine residue (Lys 375 to Lys 381), and from the 567th valine residue to the 572nd tyrosine residue (Val 567 to Tyr 572) in

the amino acid sequence of SEQ ID NO: 1, i.e., the above-identified partial amino acid sequences of (a) to (d) which are characteristic to CGTases derived from microorganisms of the genus *Paenibacillus*.

5 [0160]

Based on the above guideline, the following two types of mutant CGTases were decided to prepare; a mutant CGTase (G178R) with the amino acid sequence of SEQ ID NO: 1 wherein the 178th glycine residue was replaced with arginine residue, and a mutant CGTase (Y454H) with the amino acid sequence of SEQ ID NO: 1 wherein the 454th tyrosine residue was replaced with histidine residue. A recombinant DNA "pRSET-iPI (G178R)" encoding a mutant CGTase (G178R) was obtained by using as a genetic template a recombinant DNA "pRSET-iPI" having a natural (wild type) CGTase gene derived from *Paenibacillus illinoisensis* NBRC15379 strain and using synthetic oligonucleotides having the base sequences of SEQ ID NOs: 8 and 9 as a sense- and anti-sense-primers, respectively; and introducing a site specific mutation into the CGTase gene by conventional PCR and DpnI methods using a commercialized "QuickChange Site-Directed Mutagenesis Kit" produced by Stratagene, CA, USA. A DNA "pRSET-iPI (Y454H)" encoding the mutant CGTase (Y454H) was obtained similarly as above except for using synthetic oligonucleotides having the base sequences of SEQ ID NOs: 10 and 11 as a sense- and anti-sense-primers, respectively.

[0161]

E. coli BL21 (DE3), produced by Stratagene, CA, USA, was transformed in usual manner by using the recombinant

DNA "pRSET-iPI (G178R)" or "pRSET-iPI (Y454H)", which had a mutant CGTase gene, to obtain transformants of "BL21-RSET-iPI (G178R)" and "BL21-RSET-iPI (Y454H)", which had the above respective recombinant DNAs. Similarly as the above
5 "BL21-RSET-iPI", these transformants were respectively cultured, followed by disrupting the cells and partially purifying the resultants to obtain partially purified specimens of the mutant CGTases, respectively. By the way, the supernatants of each cell disruption solutions were assayed
10 for CGTase activity (starch hydrolyzing activity) and converted into enzyme activities per milliliter of the culture solutions, revealing that they had about 10.3 units/ml for "BL21-RSET-iPI (G178R)" and about 13.7 units/ml for "BL21-RSET-iPI (Y454H)".

15 [0162]

<Production of particulate composition containing crystalline trehalose dihydrate>

A particulate composition containing crystalline trehalose dihydrate was produced by the method similarly as
20 in Example 2 except for using the recombinant (wild type) CGTase, and, as a mutant CGTase, G178R, a CGTase having the amino acid sequence of SEQ ID NO: 12; or Y454H, a CGTase having the amino acid sequence of SEQ ID NO: 13, both of which were all obtained in the above. The trehalose contents in the enzymatic reaction
25 solutions obtained by using the respective CGTases, saccharide compositions of the obtained particulate compositions containing crystalline trehalose dihydrate, production yields against starch, degrees of crystallinity for crystalline trehalose dihydrate, average crystallite diameters, reducing

powders of the whole powders, and particle size distributions were determined; and the particulate compositions were subjected to both a caking test by the same method as in Experiments 2-2, 3-2, etc., and a test for solubility in water
5 by the same method as in Experiment 5. The results are tabulated in Table 6.

Table 6

Item	CGTase			
	Recombinant enzyme (wild type)	Mutant enzyme G178R	Mutant enzyme Y454H	
Trehalose content in enzymatic reaction solution* (% by weight)	87.2	87.0	87.6	
Saccharide composition (% by weight**)	Trehalose	99.3	99.4	
	D-Glucose	0.07	0.07	
	4-O- α -Glucosyltrehalose	0.05	0.03	
	6-O- α -Glucosyltrehalose	0.06	0.08	
Production yield against starch (% by weight)	45	44	45	
Degree of crystallinity (%)	94.4	94.9	95.1	
Average crystallite diameter ($\text{\AA}$)	3380	3430	3550	
Reducing power of the whole powder (%)	0.16	0.15	0.16	
Particle size distribution (% by weight)	53 μm or larger but smaller than 425 μm	82.6	84.4	
	53 μm or larger but smaller than 300 μm	74.7	71.5	
	425 μm or larger	6.2	6.6	
Caking test	-	-	-	
Solubility in water	Passable	Passable	Passable	

* : After glucoamylase treatment

** : On a dry solid basis

[0164]

As shown in Table 6, even in the case of using the recombinant CGTase and the mutant CGTases with one amino acid substitution, the trehalose contents in the enzymatic reaction solutions are substantially the same level of 87.0% or more as in the case of natural CGTase; and particulate compositions, containing crystalline trehalose dihydrate having substantially the same trehalose purity, degree of crystallinity, particle size distribution, etc., can be produced in a production yield against starch of as high as about 44% to about 45% according to the same production process. Similarly as the particulate compositions containing crystalline trehalose dihydrate produced with the natural CGTases in Examples 1 to 4, although the particulate compositions containing crystalline trehalose dihydrate produced in the production process of this example are not so different from "TREHA", a conventional food-grade powder containing crystalline trehalose dihydrate, commercialized by Hayashibara Co., Ltd., Okayama, Japan, which has been commercialized as a food material, etc., in terms of trehalose purity, they are significantly, hardly cakeable particulate compositions compared to the conventional food-grade powder, as well as being easily stored and handled.

Example 6

[0165]

A particulate composition containing crystalline trehalose dihydrate, containing, on a dry solid basis, 99.7% trehalose, 0.05% D-glucose, 0.03% 4-O- α -glucosyltrehalose, and 0.05% 6-O- α -glucosyltrehalose, was obtained in a

production yield against starch of about 46% by the method similarly as in Example 2 except for precipitating crystalline trehalose dihydrate by applying a controlled cooling method of cooling the contents over 24 hours by a 20-step cooling profile approximated to the aforesaid Equation [2] in such a manner of cooling the contents from 60°C to 20°C by using, in the crystallization step for crystalline trehalose dihydrate, a conventional programmed-constant-temperature-circulator for crystallization system and flowing a temperature-controlled heat medium to a jacket of a crystallizer.

[0166]

The particulate composition containing crystalline trehalose dihydrate had the degree of crystallinity for crystalline trehalose dihydrate of 96.8%, an average crystallite diameter of 3,680 Å, and a reducing power of the whole powder of 0.13%. For comparison, the determination of the above degree of crystallinity was carried out by the Hermans' method using the analytical values H_{100} and H_0 determined in Experiment 4-2. The measurement of particle size distribution of the particulate composition revealed that it contained particles with a particle size of 53 μm or larger but smaller than 425 μm in an amount of 84.5%, those with a particle size of 53 μm or larger but smaller than 300 μm in an amount of 76.2%, and those with a particle size of 425 μm or larger in an amount of 6.4%. When subjected to a caking test by the same method as in Experiments 2-2, 3-2, etc., the particulate composition was judged as "Not caked" (-). Also, the particulate composition was judged as "Passable" when tested for solubility in water by the same method as in Experiment 5.

[0167]

According to the production process of this example, a particulate composition containing crystalline trehalose dihydrate is produced in a production yield against starch of as high as about 46%. Although the particulate composition containing crystalline trehalose dihydrate produced by the process of this example is not so different from "TREHA", a product name of a conventional food-grade powder containing crystalline trehalose dihydrate, commercialized by Hayashibara Co., Ltd., Okayama, Japan, which has been commercialized as a food material, etc., in terms of trehalose purity, it is a significantly, hardly cakeable particulate composition compared to the conventional food-grade powder, as well as being easily stored handled. The product is similar to the conventional food-grade powder in that it is a particulate composition containing crystalline trehalose dihydrate; the more easily stored and handled, the more preferably used as a material for food products, cosmetics, quasi-drugs, pharmaceuticals, etc.

20 Example for Reference

[0168]

<Production of particulate composition containing crystalline trehalose dihydrate>

When conducting a trehalose-forming reaction and a glucoamylase treatment similarly as in Example 1 except for using, as a CGTase, a CGTase enzyme specimen derived from *Geobacillus stearothermophilus* Tc-91 strain, produced by Hayashibara Co., Ltd., Okayama, Japan, an enzymatic reaction solution after glucoamylase treatment had a trehalose content

of 85.2%, d.s.b. The enzymatic reaction solution was in usual manner decolored and filtered with an activated charcoal, and the filtrate was desalted with a cation-exchange resin (H^+ -form) and an anion-exchange resin (OH^- -form), concentrated
5 *in vacuo* into a concentrate with a solid content of about 84%. The concentrate was placed in a crystallizer, admixed with "TREHALOSE 999" (Code No.: TH224, trehalose purity: 99.9% or higher), a product name of a reagent-grade powder containing crystalline trehalose dihydrate, commercialized by
10 Hayashibara Co., Ltd., Okayama, Japan, as a seed crystal, in an amount equal to one percent of the solid contents, adjusted to 55°C, and unforcedly cooled from 55°C to 15°C over 20 hours under gentle stirring conditions to precipitate crystalline trehalose dihydrate. The crystals were collected by a
15 basket-type centrifuge, spayed with refined water in an amount equal to about 5% of the weight of a massecuite, aged and dried at 50°C for two hours, cooled by blowing 20°C air for 20 min, and pulverized to obtain a particulate composition containing crystalline trehalose dihydrate, which contained, on a dry
20 solid basis, 98.5% trehalose, 0.8% D-glucose, 0.07% 4-O- α -glucosyltrehalose, and 0.1% 6-O- α -glucosyltrehalose, in a production yield against starch of about 38%.

[0169]

The degree of crystallinity for crystalline
25 trehalose dihydrate, the average crystallite diameter, and the reducing power of the whole powder of the particulate composition containing crystalline trehalose dihydrate were respectively 88.3%, 2,580 Å, and 1.0%. For comparison, the measurement for the above degree of crystallinity was

determined on the Hermans' method using the analytical values H_{100} and H_0 obtained in Experiment 4-2. The measurement of the particle size distribution of the product revealed that it contained particles with a particle size of 53 μm or larger but smaller than 425 μm in an amount of 74.4%, those with a particle size of 53 μm or larger but smaller than 300 μm in an amount of 69.4%, and those with a particle size of 425 μm or larger in an amount of 12.6%. When subjected to a caking test by the same method as in Experiments 2-2, 3-2, etc., the product was judged as "Slightly caked" ($\pm$). Also, the product was judged as "Passable" when tested for solubility in water by the same method as in Experiment 5.

Industrial Applicability

[0170]

As described above, according to the production process for producing particulate compositions containing anhydrous crystalline trehalose dihydrate, those which are relatively high in purity similarly as in conventional food-grade powder containing crystalline trehalose dihydrate and are hardly cakeable, can be produced in a high production yield against starch. In particular, when a controlled cooling method or semi-controlled cooling method is applied in the crystallization step for crystalline trehalose dihydrate, particulate compositions containing a higher purity crystalline trehalose dihydrate are produced in a higher production yield against starch. As described above, the production process according to the present invention enables to more efficiently produce particulate compositions

containing crystalline trehalose dihydrate on an industrial scale by using starch, as a material, which is present abundantly but a restricted source, and thus it has a particular industrial utility. The particulate compositions containing
5 crystalline trehalose dihydrate produced by the production process of the present invention, which employs a controlled cooling method or semi-controlled cooling method, are significantly, hardly cakeable particulate compositions compared to the conventional food-grade powders containing
10 crystalline trehalose dihydrate, and they have a superior industrial availability in that they can be used in various uses as more readily handleable powdered materials for food products, cosmetics, quasi-drugs, or pharmaceuticals. Thus, the present invention, which has such an outstanding functions
15 and effects, has distinct industrial utilities.

Explanation of Symbols

[0171]

In FIG. 1, the symbols "a" to "e" mean as follows:

- 20 a: a diffraction peak at a diffraction angle (2θ) of 13.7° (Miller's index (hkl):101) for calculating crystallite diameter;
- b: a diffraction peak at a diffraction angle (2θ) of 17.5° (Miller's index (hkl):220) for calculating crystallite
25 diameter;
- c: a diffraction peak at a diffraction angle (2θ) of 21.1° (Miller's index (hkl):221) for calculating crystallite diameter;
- d: a diffraction peak at a diffraction angle (2θ) of 23.9°

(Miller's index (hkl):231) for calculating crystallite diameter; and

e: a diffraction peak at a diffraction angle (2θ) of 25.9° (Miller's index (hkl):150) for calculating crystallite diameter.

In FIG. 5, the symbols "a" to "c" mean as follows:

a : Controlled cooling curve;

b : Linear cooling; and

c : Unforced cooling curve.

In FIG. 6, the following symbols mean as follows:

pUC ori : Replication origin derived from plasmid pUC;

T7 : T7 Promotor;

White arrow (Amp) : Ampicillin-resistant gene; and

Black arrow : CGTase Gene.

Claims

1. A process for producing a particulate composition comprising crystalline α,α -trehalose dihydrate with an α,α -trehalose content of 98.0% by weight or more, on a dry solid basis, and a degree of crystallinity for crystalline α,α -trehalose dihydrate of 90.0% or higher, when calculated based on its powder X-ray diffraction profile, from a saccharide solution with an α,α -trehalose content of over 86.0% by weight, on a dry solid basis, said process comprising the step of precipitating crystalline by a controlled cooling method or semi-controlled cooling method;

wherein said controlled cooling method is a cooling method, where the liquid temperature "T" at the time "t" is basically expressed by the formula:

$$T = T_0 - (T_0 - T_f) \cdot (t/\tau)^3,$$

wherein " τ " is the operation time established for a crystallization step, " T_0 " is the liquid temperature at the initiation of crystallization, " T_f " is the targeted liquid temperature at the termination of crystallization; and

wherein said semi-controlled cooling method is a cooling method, where the liquid temperature "T" is allowed to linearly or stepwisely decrease against the time "t" in order to keep the variation $(T_0 - T_m)$ of the liquid temperature "T" at the point of " $t=\tau/2$ " to be at least 5% but less than 30% of the total temperature change $(T_0 - T_f)$, wherein " T_m " is the liquid temperature at time " $t=\tau/2$ ".