

DESCRIPTION

FLUX FOR SUBMERGED ARC WELDING

5 Technical Field

[0001]

The present invention relates to a flux for use in submerged arc welding. More specifically, the present invention relates to a high-temperature sintered flux.

10

Background Art

[0002]

15

Fluxes for use in submerged arc welding are mainly classified into a fused flux and a sintered flux in terms of the form of flux. The fused flux is manufactured by melting various materials in an electric furnace and the like and crushing them. Whereas, the sintered flux is manufactured by bonding various raw materials with a binder, such as alkaline silicate, granulating them, and sintering the granules.

20

[0003]

25

In general, the sintered fluxes are further classified, depending on the sintering temperature, into a low-temperature sintered flux produced by sintering at 400 to 600°C and a high-temperature sintered flux produced by sintering at 600 to 1,200°C. The low-temperature sintered flux has been

conventionally studied from various aspects to reduce the diffusion of hydrogen into a weld metal (see Patent Documents 1 to 3). For example, Patent Documents 1 to 3 disclose a technique in which the ratio of carbonates to the flux is set in a specific range, thereby generating CO₂ gas during welding, thus reducing a partial pressure of H₂ gas.

[0004]

To improve moisture absorption properties without using carbonates, another means is proposed to reduce a hydrogen content in the weld metal by specifying an A value, which is a characteristic value mainly derived from a flux component, as well as the maximum value of a specific surface area of the flux (see Patent Document 4). Whereas, in the high-temperature sintered flux, a technique is proposed to decrease the content of diffused hydrogen by specifying the kind of material, such as a basic oxide, an alkali metal fluoride and an acid oxide, as well as a content thereof (see Patent Document 5).

[Prior Art Document]

[Patent Document]

[0005]

Patent Document 1: JP 49-70839 A

Patent Document 2: JP 53-95144 A

Patent Document 3: JP 51-87444 A

Patent Document 4: JP 9-99392 A

Patent Document 5: JP 62-68695 A

Disclosure of the Invention

Problems to be Solved by the Invention

[0006]

5 However, the above-mentioned technique for reducing the diffusion hydrogen content in the sintered flux has the following problems. First, in the low-temperature sintered flux with the carbonates added, as mentioned in Patent Documents 1 to 3, the use of a DC welding power source increases the consumed amount
10 of the flux, promotes the decomposition of the carbonates, compared to the use of an AC welding power source, and coarsens the surfaces of beads because of large amounts of CO gas and CO₂ gas generated during the welding. Further, such a flux has the problem that pockmarks are generated, thereby degrading the outer
15 appearance and shape of beads.

[0007]

 The technique disclosed in Patent Document 4 handles MnO as a hydrate component, regarding the A value which is an index of the hydration properties. However, MnO can become
20 non-hydrated component, in combination with other flux components. In the technique disclosed in Patent Document 4, the specific surface area of the flux is reduced. However, the specific surface area of the flux drastically affects the shield properties of a slag during welding. Specifically, when the specific surface
25 area of the flux is reduced, the shield properties of the slag

might be degraded, thus increasing a nitrogen content in the weld metal, reducing the toughness of the weld metal.

[0008]

Whereas, in the technique disclosed in Patent Document 5
5 regarding the high-temperature sintered flux, flux components are designed mainly to be compatible with the AC welding power source. However, this technique does not take into consideration the degradation in welding workability that would be most afraid of in the use of the DC welding power source. That is, in the flux
10 disclosed in Patent Document 5, the use of the DC welding power source does not gain the substantially same effects as that in use of the AC welding power source.

[0009]

Accordingly, it is a main object of the present invention
15 to provide a flux for submerged arc welding that has good welding workability and can reduce the diffusion hydrogen content in a weld metal in the use of either the AC or DC welding power source.

Means for Solving the Problems

20 [0010]

A flux for submerged arc welding according to the present invention includes: Al_2O_3 : 15 to 35% by mass; SiO_2 : 10 to 30% by mass; MgO : 10 to 25% by mass; F (in terms of CaF_2): 10 to 25% by mass; Mn (in terms of MnO): 3 to 20% by mass; Na (in terms of Na_2O)
25 and/or K (in terms of K_2O): 0.5 to 4.5% by mass in total; and Fe

(in terms of FeO): 0.5 to 8% by mass, in which a CaO content is restricted to 6% by mass or less, a water-soluble SiO₂ is restricted to less than 1% by mass, and the flux satisfies the following formula 1:

5 [0011]

[Formula 1]

$$0.2 \leq [\text{MgO}] / ([\text{Al}_2\text{O}_3] + [\text{MnO}]) \leq 0.8$$

where [Al₂O₃] is an Al₂O₃ content, [MgO] is an MgO content, and [MnO] is an Mn content (in terms of MnO).

10 [0012]

The flux for submerged arc welding further includes:TiO₂: 8% by mass or less, in which the flux can have the composition that satisfies the following formula 2:

[0013]

15 [Formula 2]

$$0.2 \leq [\text{MgO}] / ([\text{Al}_2\text{O}_3] + [\text{MnO}] + [\text{TiO}_2]) \leq 0.8$$

where [TiO₂] is a TiO₂ content.

[0014]

20 In the flux for submerge arc welding in the present invention, a C content may be restricted to 0.2% by mass or less.

The flux for submerge arc welding in the present invention is sintered, for example, at a temperature of 800°C or higher.

Effects of the Invention

25 [0015]

According to the present invention, since the contents of respective components are specified, and the ratio of the Mg content to the total contents of Al and Mn is set in a specific range, the flux for submerged arc welding can have good welding workability and reduce the diffusion hydrogen content in the weld metal in the use of either the AC or DC welding power source.

Brief Description of the Drawings

[0016]

Fig. 1 is a diagram showing the shape of a groove in a test specimen used at a welding test in Examples.

Mode for Carrying Out the Invention

[0017]

Embodiments for carrying out the present invention will be described in detail below. The present invention is not limited to the embodiments mentioned below.

[0018]

The inventors have diligently studied by experiments to solve the above-mentioned problems and found out the following. When using the DC welding power source, to keep the slag removability adequate, the content of SiO_2 in the flux should be reduced as much as possible. Regarding MgO , unless the amount of added MgO is set more than that in the flux mentioned in Patent Document 5, the slag removability cannot be improved.

[0019]

A flux for submerged arc welding according to the embodiment of the present invention (hereinafter simply referred to as a "flux") is restricted such that a SiO_2 content is in a range of 10 to 30% by mass, an MgO content is in a range of 10 to 25% by mass, and a hydrate SiO_2 content is less than 1% by mass. In the flux of the present embodiment, each components are adjusted to satisfy the formula 3 below:

[0020]

10 [Formula 3]

$$0.2 \leq [\text{MgO}] / ([\text{Al}_2\text{O}_3] + [\text{MnO}]) \leq 0.8$$

where $[\text{Al}_2\text{O}_3]$ is an Al_2O_3 content, $[\text{MgO}]$ is an MgO content, and $[\text{MnO}]$ is an Mn content (in terms of MnO).

[0021]

15 The reason for restricting the composition of the flux in the present embodiment will be described below. The content of each component in the flux of the present embodiment is a value obtained by converted a value quantified by a method defined by JIS Z 3352, in terms of oxide or fluoride, unless otherwise
20 specified.

[0022]

$[\text{Al}_2\text{O}_3]$: 15 to 35% by mass]

Al_2O_3 is a component for adjusting the viscosity and melting point of molten slag and has an effect of improving the shape of
25 a bead during welding. However, when the Al_2O_3 content is less

than 15% by mass, the above-mentioned effect cannot be sufficiently obtained. Whereas, when the Al_2O_3 content exceeds 35% by mass, the melting point of the molten slag becomes excessively high, thus degrading the shape of the bead in welding.

5 Therefore, the Al_2O_3 content is set at 15 to 35% by mass.

[0023]

From the perspective of adjusting the viscosity and melting point of the molten slag, the Al_2O_3 content is preferably 20% by mass or more, and more preferably 23% by mass or more. Furthermore,
10 from the perspective of the appropriate melting point of the molten slag, the Al_2O_3 content is preferably 30% by mass or less, and more preferably 28% by mass or less. This restriction can further improve the shape of the bead.

[0024]

15 Here, the term " Al_2O_3 content" as used herein means a value obtained by expressing, in terms of Al_2O_3 , the whole Al content in the flux that is determined by analysis with a method defined by JIS Z 3352 (e.g., JIS M 8220 and the like). The whole Al content measured by this method sometimes contains other components, such
20 as AlF_3 , in addition to Al_2O_3 . However, the contents of these other components are very little. Thus, the Al_2O_3 content (the whole Al content in terms of Al_2O_3) set in the above-mentioned range does not affect the effects of Al_2O_3 .

[0025]

25 [SiO_2 : 10 to 30% by mass]

SiO₂ has the effect of mainly improving the outer appearance and shape of the bead by imparting the appropriate viscosity to the molten slag. However, when the SiO₂ content is less than 10% by mass, the above-mentioned effect is not sufficiently obtained, thus degrading the outer appearance and shape of the bead. When the SiO₂ content exceeds 30% by mass, which means that the SiO₂ content becomes excessive, the slag removability is degraded, and burning of the slags onto a weld bead becomes severe. Therefore, the SiO₂ content is set at 10 to 30% by mass.

[0026]

From the perspective of improving the outer appearance and shape of the bead, the SiO₂ content is preferably 15% by mass or more, and more preferably 18% by mass or more. Furthermore, in view of the appropriate viscosity of the molten slag, the SiO₂ content is preferably 25% by mass or less, and more preferably 22% by mass or less.

[0027]

Here, the term "SiO₂ content" as used herein means a value obtained by expressing, in terms of SiO₂, the whole Si content in the flux that is determined by analysis with the method defined by JIS Z 3352 (e.g., JIS M 8214 and the like). The whole Si content measured by this method sometimes contains other components in addition to SiO₂, including a Si added in the form of an alloy, such as a Fe-Si alloy. However, the SiO₂ content (the whole Si content in terms of SiO₂) set in the above-mentioned range does

not affect the effects of SiO_2 mentioned above.

[0028]

[MgO: 10 to 25% by mass]

MgO is a component that significantly contributes to
5 improving the slag removability, and thus is essential for
ensuring the adequate slag removability regardless of the type
of a welding power source. However, when the MgO content is less
than 10% by mass, the effect of MgO cannot be sufficiently obtained.
Whereas, when the MgO content exceeds 25% by mass, the shape of
10 the bead is degraded, whereby defects, including slag inclusion,
lack of fusion, and undercut, are more likely to occur, depending
on the type of the welding power source. In particular, in the
AC welding power source, the welding defects, such as the slag
inclusion and the lack of fusion, mentioned above, occur
15 remarkably. Therefore, the MgO content is set at 10 to 25% by
mass.

[0029]

From the viewpoint of improving the slag removability, the
MgO content is preferably 13% by mass or more, and more preferably
20 15% by mass or more. Furthermore, from the perspective of
suppression of occurrence of the defects, the MgO content is
preferably 25% by mass or less, and more preferably 22% by mass
or less.

[0030]

25 Here, the term "MgO content" as used herein means a value

obtained by expressing, in terms of MgO, the whole Mg content in the flux that is determined by analysis with the method defined by JIS Z 3352 (e.g., JIS M 8222 and the like). The whole Mg content measured by this method sometimes contains other components, such as MgF_2 , in addition to MgO. However, the contents of these other components are very little. Thus, the MgO content (the whole Mg content in terms of MgO) set in the above-mentioned range does not affect the effects of MgO mentioned above.

[0031]

10 [F (in terms of CaF_2): 10 to 25% by mass]

A fluoride, such as CaF_2 , has the effect of enhancing the electric conductivity and fluidity of the molten slag. The fluoride is one of components that affect the high-temperature viscosity of the molten slag. This effect is in proportion to the F content, like CaO to be mentioned later. Specifically, the F content (in terms of CaF_2) of less than 10% by mass cannot sufficiently exhibit the above-mentioned effect, and cannot also expect another effect of promoting exhaust of CO gas from the molten slag to improve resistance to pockmark.

20 [0032]

Whereas, when the F content (in terms of CaF_2) exceeds 25% by mass, the fluidity of the molten slag becomes excessively high, thereby degrading the shape of the bead. Thus, the F content (in terms of CaF_2) is set at 10 to 25% by mass. From the viewpoint of improving the resistance to pockmark, the F content (in terms

of CaF_2) is preferably 13% by mass or more, and more preferably 15% by mass or more. Furthermore, from the viewpoint of improving the shape of the bead, the F content (in terms of CaF_2) is preferably 22% by mass or less, and more preferably 20% by mass or less.

[0033]

Here, the term "F content" as used herein means a value obtained by expressing, in terms of CaF_2 , the whole F content in the flux that is determined by analysis with the method defined by JIS Z 3352 (e.g., JISK 1468-2 and the like). The fluoride component in the flux of the present embodiment is mainly CaF_2 , but sometimes includes AlF_3 , MgF_2 , etc., in addition thereto. The F content (the whole F content in terms of CaF_2) in the above-mentioned range does not affect the aforesaid effect of the fluoride.

[0034]

[Mn (in terms of MnO): 3 to 20% by mass]

Mn is a component affecting the viscosity and solidification temperature of the molten slag, while improving the resistance to pockmark. Mn is added, mainly in the form of oxide, such as MnO , MnO_2 , and Mn_2O_3 . Among various forms, particularly, the addition of Mn in the form of manganese monoxide (MnO) exhibits the effectiveness of Mn. When the Mn content (in terms of MnO) is less than 3% by mass, the effects of the Mn cannot be sufficiently exhibited. When the Mn content exceeds 20% by

mass, the slag becomes brittle, degrading the slag removability.
Thus, the Mn content (in terms of MnO) is set at 3 to 20% by mass.
[0035]

In view of improving the resistance to pockmark, the Mn
5 content (in terms of MnO) is preferably 6% by mass or more, and
more preferably 8% by mass or more. Furthermore, from the
viewpoint of improving the slag removability, the Mn content (in
terms of MnO) is preferably 15% by mass or less, and more preferably
12% by mass or less. Here, the term "Mn content" as used herein
10 means a value obtained by expressing, in terms of MnO, the whole
Mn content in the flux that is determined by analysis with the
method defined by JIS Z 3352 (e.g., JIS M 8232 and the like).
[0036]

[Na (in terms of Na₂O) and/or K (in terms of K₂O): 0.5 to 8.5%
15 by mass in total]

Na and K are components that mainly affect the arc stability
and moisture absorption properties of the flux in welding. Na
and K are added, mainly in the form of oxide, such as Na₂O and
K₂O. However, when the total of the Na content (in terms of Na₂O)
20 and the K content (in terms of K₂O) is less than 0.5% by mass,
the arc voltage in welding becomes unstable, thus degrading the
outer appearance and shape of the bead.
[0037]

Whereas, when the total of the Na content (in terms of Na₂O)
25 and the K content (in terms of K₂O) exceeds 8.5% by mass, the

moisture absorption properties of the flux are degraded, and the arc becomes too strong and unstable, which degrades the outer appearance and shape of the bead. Thus, the total of the Na content (in terms of Na_2O) and the K content (in terms of K_2O) is set at 0.5 to 8.5% by mass. The flux of the present embodiment may have at least one of Na and K added thereto.

[0038]

From the perspective of stabilizing the arc voltage, the total of the Na content (in terms of Na_2O) and the K content (in terms of K_2O) is preferably 1.5% by mass or more, and more preferably, 2.5% by mass or more. Furthermore, in view of the moisture absorption properties of the flux, the total of Na content (in terms of Na_2O) and the K content (in terms of K_2O) is preferably 6.5% by mass or less, and more preferably 5.5% by mass or less.

[0039]

Here, the term "Na content and K content" as used herein means a value obtained by expressing, in terms of NaO and K_2O , respectively, the whole Na content and whole K content in the flux that are determined by analysis with the method defined by JIS Z 3352 (e.g., JIS M 8852 and the like). The Na component and K component of the flux in the present embodiment are mainly Na_2O and K_2O , respectively, but sometimes include $\text{NaAlSi}_3\text{O}_8$, KAlSi_3O_8 , and the like in addition thereto.

[0040]

[Fe (in terms of FeO): 0.5 to 8% by mass]

Fe has the effect of promoting deoxidation phenomenon to enhance the resistance to pockmark, and is added, mainly in the form of metal powder made of Fe-Si and the like. When the Fe content (in terms of FeO) is less than 0.5% by mass, particularly, in the use of the DC welding power source, the above-mentioned effect cannot be sufficiently obtained in proportion to the amount of presence of Fe. Whereas, the Fe content (in terms of FeO) exceeding 8% by mass affects the solidification temperature of the slag, thus degrading the outer appearance and shape of the bead and the slag removability. Therefore, the Fe content (in terms of FeO) is set at 0.5 to 8% by mass.

[0041]

In view of the resistance to pockmark, the Fe content (in terms of FeO) is preferably 1% by mass or more, and more preferably 2% by mass or more. Taking into consideration the influence on the solidification temperature of a slag, the Fe content (in terms of FeO) is preferably 6% by mass or less, and more preferably 4% by mass or less.

[0042]

Here, the term "Fe content" as used herein means a value obtained by expressing, in terms of FeO, the whole Fe content in the flux that is determined by analysis with the method defined by JIS Z 3352 (e.g., JIS M 8202 and the like). The Fe content sometimes covers, in addition to the Fe content added as the metal

powder, the content of FeO, Fe₂O₃, Fe₃O₄, etc., that is added as inevitable impurities.

[0043]

[CaO (corresponding value): 6% by mass or less]

5 CaO is a component that increases the basicity of the slag, thereby enhancing the cleaning degree of weld metal, and also affects the fluidity of the molten slag. CaO exhibits the aforesaid effects in proportion to the amount of presence of CaO. However, when the CaO content exceeds 6% by mass, the fluidity
10 of the molten slag becomes excessive to degrade the outer appearance and shape of the bead. Therefore, the CaO content is restricted to 6% by mass or less.

[0044]

 From the perspective of the fluidity of the molten slag,
15 the CaO content is preferably 4% by mass or less, and more preferably 3% by mass or less.

[0045]

 The flux in the present embodiment includes CaF₂ mentioned above, as a Ca component, in addition to CaO. Here, the term "CaO
20 content" as used herein means a corresponding value determined from the whole Ca content and the whole F content that are obtained by analysis with the method defined by JIS Z 3352. Thus, if the CaF₂ content is very large, a CaO content can be zero (0) according to JIS Z 3352 in some cases.

25 [0046]

[Water-soluble SiO₂: less than 1% by mass]

As the content of water-soluble SiO₂ is 1% by mass or more, the resistance to moisture absorption of the flux is degraded, and the diffusion hydrogen content of the weld metal is increased.

5 Therefore, the water-soluble SiO₂ content is restricted to less than 1% by mass. From the perspective of improving the resistance to moisture absorption and reducing the diffusion hydrogen content, the water-soluble SiO₂ content is preferably 0.8% by mass or less, and more preferably 0.6% by mass or less.

10 [0047]

The water-soluble SiO₂ is derived mainly from a binder, such as liquid glass. To reduce its content, it is effective to sinter the flux at a temperature equal to or higher than a temperature at which the binder is less likely to absorb moisture.

15 Specifically, the sintering temperature is most preferably set at 800°C or higher.

[0048]

The water-soluble SiO₂ content in the flux can be measured by the following method. First, the flux was crushed into a
20 particle size of 300 μm or less by a vibrational mill, followed by sampling about 0.2g of each specimen for measurement therefrom (step 1). Then, the above-mentioned specimen and 100 ml of distilled water were charged into a conical flask made of quartz, and boiled for 4 hours, thereby extracting a soluble component
25 (step 2). After leaving the extracted solution for 12 hours or

to drastically degrade the slag removability. Here, the slag removability can be improved by addition of MgO.

[0052]

However, since MgO has excellent hydration properties, the addition of MgO into the flux degrades the moisture absorption properties, thereby increasing the diffusion hydrogen content in the weld metal. Whereas, Al_2O_3 and Mn are non-hydrous components, and have the great effect of improving the moisture absorption properties if being added. Unlike the technical knowledge in the related art, it is found out that among them, Mn is used in combination with Al_2O_3 to exhibit the effect of improving the moisture absorption properties of the flux to contribute to decreasing the diffusion hydrogen content.

[0053]

When $[\text{MgO}]/([\text{Al}_2\text{O}_3] + [\text{MnO}])$ is less than 0.2, the slag removability is drastically degraded during welding by the DC welding power source. When $[\text{MgO}]/([\text{Al}_2\text{O}_3] + [\text{MnO}])$ exceeds 0.8, the moisture absorption properties are degraded, thus increasing the diffusion hydrogen content in the weld metal. The amount of each component added is adjusted such that the ratio of $[\text{MgO}]/([\text{Al}_2\text{O}_3] + [\text{MnO}])$ is in a range of 0.2 to 0.8. Thus, the degradation in moisture absorption properties can be suppressed.

[0054]

[TiO_2 : 8% by mass or less]

The flux of this embodiment may contain TiO_2 , in addition

to the above-mentioned components. TiO_2 is a component that is effective in improving the slab removability and has the effect of making the shape of the bead better. Part of TiO_2 is converted into Ti by a reduction reaction in welding, and this Ti is added into the weld metal, contributing to improving the toughness of the flux.

[0055]

The above-mentioned effect is in proportion to the amount of presence of TiO_2 (TiO_2 content). When the upper limit of TiO_2 content exceeds 8% by mass, the shape of the bead is degraded. The lower limit of TiO_2 content is not specifically limited, but is preferably 1% by mass or more from the viewpoint of the slag removability and the bead shape.

[0056]

When TiO_2 is added to the flux, the following formula 4 is preferably satisfied. Thus, the addition of TiO_2 in this way can enhance the effect of further improving the welding workability by the DC welding power source while reducing the diffusion hydrogen content in the weld metal. $[\text{TiO}_2]$ in the following formula 4 is a TiO_2 content.

[0057]

[Formula 4]

$$0.2 \leq [\text{MgO}] / ([\text{Al}_2\text{O}_3] + [\text{MnO}] + [\text{TiO}_2]) \leq 0.8$$

[0058]

Here, the term " TiO_2 content" as used herein means a value

obtained by expressing, in terms of TiO_2 , the whole Ti content in the flux that is determined by analysis with the method defined by JIS Z 3352 (e.g., JIS M 8219 and the like).

[0059]

5 [C: 0.2% by mass or less]

C is derived from a carbonate included as an impurity in each raw material of the flux, and inevitably introduced thereinto. Whereas, in the use of the DC welding power source as mentioned above, the consumption of the flux is increased, and the
10 decomposition of the carbonate is further promoted, compared to the use of the AC welding power source. Thus, even if the C content is very small, a large volume of CO gas and CO_2 gas is generated during welding, leading to degradation in the resistance to pockmark and the outer appearance and shape of the bead. Thus,
15 to prevent the degradation in welding workability, the C content in the flux is preferably reduced to 0.2% by mass or less.

[0060]

In particular, from the perspective of improving the resistance to pockmark, the C content is preferably restricted
20 to 0.1% by mass or less, and more preferably 0.05% by mass or less. To keep the resistance to pockmark adequate, the C content is preferably as small as possible. The term "C content" as used herein means a value determined by analysis with the method defined by JIS Z 2615 (e.g., JIS M 8219 etc.)

25 [0061]

[Other components]

Other components except for the above-mentioned components in the flux of the present embodiment include Zr, Ba, Li, P and S. Among these inevitable impurities, each of Zr, Ba and Li is preferably restricted to 1.0% by mass or less, and particularly,
5 each of P and S that affect the quality of weld metal is preferably restricted to 0.05% by mass or less.

[0062]

[Manufacturing Method]

10 When manufacturing the flux in the present embodiment, for example, the raw material powder is blended to have the above-mentioned composition, then mixed and kneaded together with a binder, granulated, and sintered. At this time, for example, aqueous solutions, such as polyvinyl alcohol, and liquid glass
15 can be used as bonding agents (binders). Granulation methods are not specifically limited, but may preferably include method using a rolling granulator, an extrusion granulator and the like.

[0063]

Further, the granulated flux is preferably subjected to
20 grain-size regulation, including dust removal and crushing of coarse grains, to have grains with a grain size of 2.5 mm or less. Whereas, the sintering process after the granulation can be performed by a rotary kiln, a stationary batch furnace, a belt baking furnace and the like. The sintering temperature at this
25 time can be set, for example, at 600 to 1,200°C. From the

viewpoint of making the binder less likely to absorb moisture as mentioned above, the sintering temperature is preferably set at 800°C or higher.

[0064]

5 As mentioned above in detail, the flux of the present embodiment sets the content of each component in a corresponding specific range, and adjusts the contents of the respective components such that the ratio of the Mg content to the total of the Al content and Mn content falls within a specific range. Thus,
10 even if the welding power source is of either the AC or DC type, it is possible to make the welding workability better and to reduce the diffusion hydrogen content in the weld metal.

Examples

15 [0065]

 The effects of the present invention will be specifically described by way of Examples and Comparative Examples of the present invention. In Examples, submerged arc welding tests were performed using steel plates shown in Table 1 below and wires shown
20 in Table 2 while the steel plates have the shape of a groove shown in Fig. 1, under welding conditions (A or B) shown in Table 3 below. The performances of the fluxes in Examples shown in Table 4 below and in Comparative Examples shown in Table 5 below were evaluated. In Examples, raw materials were blended to have the composition
25 shown in Tables 4 and 5, then mixed and kneaded together with a

binder (liquid glass), granulated, and further sintered using a rotary kiln at the temperatures shown in Table 4 and 5 below, followed by the grain-size regulation, whereby the fluxes having the grain size of 2.5 mm or less were obtained.

5 [0066]

[Table 1]

Plate thickness (mm)	Composition (% by mass)				
	C	Si	Mn	P	S
25	0.16	0.35	1.32	0.007	0.001

[0067]

[Table 2]

Composition (% by mass)				
C	Si	Mn	P	S
0.14	0.01	1.93	0.012	0.005

10

[0068]

[Table 3]

No.	Polarity	Welding current (A)	Arc voltage (V)	Welding speed (cpm)	Wire extension (mm)	Interpass temperature (°C)
A	DC-EP	550	30	42	30	≤ 150
B	AC	550	30	42	30	≤ 150

[0069]

[Table 4]

		Flux composition (% by mass)													M (I)	M (II)	Sintering temperature (°C)
		Al ₂ O ₃	SiO ₂			MgO	F	Mn	Na+ K	Fe	CaO	Water-soluble SiO ₂	TiO ₂	C			
			Alloy-derived	Mineral-derived	Total												
Examples	1	26	4	16	20	15	20	10	2.5	3	2	0.4	2	0.013	0.42	0.39	850
	2	35	4	7	11	17	19	10	2.6	3	1	0.4	2	0.016	0.38	0.36	850
	3	16	4	25	29	19	18	9	2.4	3	2	0.4	2	0.025	0.76	0.70	850
	4	34	4	15	19	10	18	10	2.4	3	2	0.4	2	0.023	0.23	0.22	850
	5	16	4	15	19	25	17	13	2.4	3	2	0.5	3	0.019	0.86	0.78	850
	6	34	4	14	18	19	11	9	2.4	3	2	0.4	2	0.018	0.44	0.42	850
	7	15	4	16	20	20	24	12	2.5	3	2	0.4	2	0.015	0.74	0.69	850
	8	35	4	14	18	19	16	3	2.5	3	2	0.4	2	0.020	0.50	0.48	850
	9	16	4	13	17	20	18	20	2.4	3	2	0.4	2	0.015	0.56	0.53	850
	10	24	4	25	29	10	17	11	2.5	3	2	0.4	2	0.018	0.29	0.27	850
	11	27	4	7	11	24	16	13	2.5	3	2	0.4	2	0.022	0.60	0.57	850
	12	25	4	26	30	16	10	10	2.5	3	2	0.4	2	0.030	0.46	0.43	850
	13	26	4	7	11	18	24	11	2.6	3	2	0.4	3	0.025	0.49	0.45	850
	14	26	4	25	29	16	17	3	2.6	3	2	0.4	2	0.032	0.55	0.52	850
	15	25	4	6	10	17	19	19	2.5	3	3	0.4	2	0.013	0.39	0.37	850
	16	23	5	16	21	25	12	10	2.3	4	2	0.4	1	0.046	0.76	0.74	850

[Table 4] (continued)

		Flux composition (% by mass)													M (I)	M (II)	Sintering temperature (°C)
		Al ₂ O ₃	SiO ₂			MgO	F	Mn	Na+ K	Fe	CaO	Water-soluble SiO ₂	TiO ₂	C			
			Alloy-derived	Mineral-derived	Total												
Examples	17	25	4	16	20	11	25	11	2.4	3	2	0.4	1	0.014	0.31	0.30	850
	18	27	4	15	19	24	17	4	2.3	3	2	0.4	2	0.024	0.77	0.73	850
	19	26	4	14	18	10	18	19	2.3	3	2	0.4	2	0.019	0.22	0.21	850
	20	25	4	15	19	20	25	3	2.4	3	2	0.4	1	0.032	0.71	0.69	850
	21	26	4	14	18	18	11	19	2.6	3	2	0.4	1	0.028	0.40	0.39	850
	22	27	4	18	22	16	19	10	0.6	3	2	0.5	1	0.015	0.43	0.42	800
	23	28	4	17	21	18	11	9	8.3	3	0	0.6	2	0.016	0.43	0.41	800
	24	26	1	20	21	18	17	11	2.5	0.6	2	0.5	2	0.025	0.49	0.46	800
	25	24	10	9	19	18	15	11	2.6	8	2	0.6	1	0.021	0.51	0.50	800
	26	26	4	16	20	16	20	11	2.5	3	2	0.4	0	0.019	0.43	0.43	850
	27	21	4	14	18	23	16	10	2.5	3	2	0.5	5	0.015	0.74	0.64	800
	28	20	4	13	17	22	17	9	2.6	3	2	0.5	8	0.028	0.76	0.59	800
	29	27	4	16	20	14	19	10	2.5	3	3	0.1	2	0.032	0.38	0.36	900
	30	28	4	16	20	14	18	10	2.5	3	3	< 0.1	2	0.022	0.37	0.35	1,000
	31	19	4	22	26	16	17	9	2.4	3	6	0.4	2	0.031	0.57	0.53	850
	32	26	4	16	20	15	20	10	2.5	3	2	0.4	2	0.18	0.42	0.39	850

[0070]

[Table 5]

		Flux composition (% by mass)													M (I)	M (II)	Sintering temperature (°C)
		Al ₂ O ₃	SiO ₂			MgO	F	Mn	Na+ K	Fe	CaO	Water-soluble SiO ₂	TiO ₂	C			
			Alloy-derived	Mineral-derived	Total												
Comparative Examples	1	38	3	14	17	13	16	9	2.4	2	2	0.4	1	0.019	0.28	0.27	850
	2	13	4	23	27	19	20	11	2.4	3	3	0.5	2	0.024	0.79	0.73	850
	3	18	4	28	32	15	15	10	2.6	3	3	0.4	2	0.027	0.54	0.50	850
	4	28	4	2	6	20	24	13	2.5	3	2	0.4	2	0.016	0.49	0.47	850
	5	21	4	12	16	29	16	9	2.4	3	2	0.4	2	0.018	0.97	0.91	850
	6	28	4	24	28	7	12	12	2.6	3	6	0.4	2	0.032	0.18	0.17	850
	7	22	4	13	17	15	28	9	2.5	3	2	0.5	2	0.028	0.48	0.45	850
	8	27	5	14	19	23	8	12	2.4	4	2	0.6	3	0.016	0.59	0.55	850
	9	22	4	11	15	15	14	24	2.5	3	3	0.5	2	0.017	0.33	0.31	850
	10	28	4	16	20	22	20	1	2.6	3	2	0.6	2	0.025	0.76	0.71	850
	11	27	4	14	18	19	17	11	0.1	3	2	0.5	3	0.041	0.50	0.46	800
	12	26	4	15	19	17	14	10	9.5	3	0	0.4	2	0.027	0.47	0.45	800
	13	26	0	21	21	19	17	11	2.5	0.2	2	0.5	2	0.015	0.51	0.49	800
	14	24	13	6	19	18	15	9	2.6	10	2	0.6	1	0.019	0.55	0.53	800
	15	21	4	14	18	21	14	9	2.5	3	2	0.5	10	0.018	0.70	0.53	800
	16	27	4	16	20	14	19	10	2.5	3	3	1.5	2	0.028	0.38	0.36	600
	17	16	4	17	21	24	21	8	2.5	3	3	0.6	2	0.026	1.00	0.92	850
	18	34	4	7	11	10	11	19	2.4	3	3	0.4	7	0.029	0.19	0.17	850
	19	23	4	18	22	16	15	9	2.4	3	8	0.4	2	0.015	0.28	0.27	850
	20	26	4	16	20	15	20	10	2.5	3	2	0.4	2	0.43	0.42	0.39	850

[0071]

The balance of the steel plate composition shown in the above Table 1 and of the wire composition shown in the above Table 2 is Fe and inevitable impurities. "M(I)" shown in the above Tables 4 and 5 indicates a value of $[MgO]/([Al_2O_3] + [MnO])$, and "M(II)" indicates a value of $[MgO]/([Al_2O_3] + [MnO] + [TiO_2])$.

[0072]

The respective fluxes in Examples and Comparative Examples were evaluated for the diffusion hydrogen content in the weld metal, the bead outer appearance, the bead shape, the slag removability, and the welding defect (intrinsic and extrinsic defects).

[0073]

<Diffusion Hydrogen Content>

A diffusion hydrogen content in the weld metal was measured based on the method defined by JIS Z 3118 in principle.

[0074]

<Bead Outer Appearance>

The outer appearance of a bead, mainly regarding the waved shape and luster of the bead, was evaluated by visually observing a welded part. As a result, samples having beads with metallic luster without any disturbed part of the bead waved shape were rated "A"; samples having beads with metallic luster and one disturbed part of the bead waved shape per unit welding length (1 m) were rated "B"; samples having beads without any metallic

luster and with two to four disturbed parts of the bead waved shape per unit welding length (1 m) were rated "C"; and samples having beads without any metallic luster and with five or more disturbed parts of the bead waved shape per unit welding length (1 m) were rated "D".

[0075]

<Bead Shape>

The shape of a bead, mainly regarding uneven part of the bead and wettability to the base metal, was evaluated by visually observing the welded part of each sample. As a result, samples having beads with a very good shape were rated "A"; samples having beads with a good shape were rated "B"; samples having beads with a slightly defective shape were rated "C"; and samples having beads with a defective shape were rated "D".

[0076]

<Slag Removability>

The slag removability was evaluated based on the easiness of slag removal and the presence or absence of slag burning. Specifically, samples from which the slag was naturally removed with no burning were rated "A"; samples from which the slag was naturally removed with three or less burned parts per unit welding length (1 m) were rated "B"; samples from which the slag was not naturally removed with four to nine burned parts per unit welding length (1 m) were rated "C"; and samples from which the slag was not naturally removed with ten or more burned parts per unit

welding length (1 m) were rated "D".

[0077]

<Arc Stability>

The arc stability was evaluated based on the amplitude of
5 voltage and current oscillations during welding. Specifically,
samples having the welding current of ± 50 A and the arc voltage
of ± 2 V were rated "A"; samples having the welding current of ± 100
A and the arc voltage of ± 2 V were rated "B"; samples having the
welding current of ± 100 A and the arc voltage of ± 4 V were rated
10 "C"; and samples in which welding was difficult to perform were
rated "D".

[0078]

<Welding Defects>

Welding defects (intrinsic defects) generated in the weld
15 metal, mainly regarding a pore defect, a slag inclusion, lack of
fusion, and the like, were evaluated. Samples with no welding
defects were rated "A"; samples having a rate of occurrence of
the welding defects per unit welding length (1 m) of 0.5% or less
were rated "B"; samples having a rate of occurrence of the welding
20 defects per unit welding length (1 m) exceeding 0.5% and of 1.0%
or less were rated "C"; and samples having a rate of occurrence
of the welding defects per unit welding length (1 m) exceeding
1.0% were rated "D".

[0079]

25 Whereas, the welding defects (extrinsic defects), mainly

regarding welding defects generated at the surface of the weld metal, such as an undercut part and a pockmark, were evaluated. Samples with no welding defects were rated "A"; samples having a rate of occurrence of the welding defects per unit welding length (1 m) of 0.5% or less were rated "B"; samples having a rate of occurrence of the welding defects per unit welding length (1 m) exceeding 0.5% and of 1.0% or less were rated "C"; and samples having a rate of occurrence of the welding defects per unit welding length (1 m) exceeding 1.0% were rated "D".

10 [0080]

The above-mentioned evaluation results are collectively shown in Tables 6 and 7 below.

[0081]

[Table 6]

		Evaluation results												
		Diffusion hydrogen content (ml/100g)	Welding conditions A						Welding conditions B					
			Bead outer appearance	Bead shape	Slag removability	Arc stability	Welding defect (intrinsic)	Welding defect (extrinsic)	Bead outer appearance	Bead shape	Slag removability	Arc stability	Welding defect (intrinsic)	Welding defect (extrinsic)
Examples	1	2.3	A	A	A	A	A	A	A	A	A	A	A	A
	2	2.1	A	B	A	A	A	A	A	B	A	A	A	A
	3	2.6	A	B	B	A	A	A	A	B	B	A	A	A
	4	2.5	A	B	B	A	A	A	A	B	B	A	A	A
	5	3.4	A	B	A	A	A	B	A	B	A	A	A	B
	6	3.3	B	B	A	A	A	B	B	B	A	A	A	B
	7	2.4	A	B	A	A	A	A	A	B	A	A	A	A
	8	2.3	A	B	B	A	A	B	A	B	B	A	A	B
	9	2.3	A	B	B	A	A	A	A	B	B	A	A	A
	10	2.5	A	A	B	A	A	A	A	A	B	A	A	A
	11	3.5	B	B	A	A	B	B	B	B	A	A	B	B
	12	2.3	A	A	B	A	A	B	A	A	B	A	A	B
	13	2.4	B	B	A	A	A	A	B	B	A	A	A	A
	14	2.2	A	A	B	A	A	B	A	A	B	A	A	B
	15	2.4	B	B	B	A	A	A	B	B	B	A	A	A
	16	3.4	A	B	A	A	B	B	A	B	A	A	B	B

[Table 6] (continued)

		Evaluation results												
		Diffusion hydrogen content (ml/100g)	Welding conditions A						Welding conditions B					
			Bead outer appearance	Bead shape	Slag removability	Arc stability	Welding defect (intrinsic)	Welding defect (extrinsic)	Bead outer appearance	Bead shape	Slag removability	Arc stability	Welding defect (intrinsic)	Welding defect (extrinsic)
Examples	17	2.1	A	B	B	A	A	A	A	B	B	A	A	A
	18	3.2	A	B	A	A	A	B	A	B	A	A	A	B
	19	2.4	A	A	B	A	A	A	A	A	B	A	A	A
	20	2.2	A	B	A	A	A	A	A	B	A	A	A	A
	21	2.2	A	A	B	A	A	B	A	A	B	A	A	B
	22	2.5	B	B	A	B	A	A	B	B	A	B	A	A
	23	3.1	B	B	A	B	A	A	B	B	A	B	A	A
	24	2.8	A	A	A	A	A	B	A	A	A	A	A	B
	25	2.7	B	B	B	A	A	A	B	B	B	A	A	A
	26	2.3	A	A	A	A	A	A	A	A	A	A	A	A
	27	2.9	A	A	A	A	A	A	A	A	A	A	A	A
	28	3.0	A	B	A	A	A	A	A	B	A	A	A	A
	29	1.7	A	A	A	A	A	A	A	A	A	A	A	A
	30	1.5	A	A	A	A	A	A	A	A	A	A	A	A
	31	2.5	B	B	A	A	A	A	B	B	A	A	A	A
	32	2.6	A	A	A	A	A	B	A	A	A	A	A	A

[0082]

[Table 7]

		Evaluation results												
		Diffusion hydrogen content (ml/100g)	Welding conditions A						Welding conditions B					
			Bead outer appearance	Bead shape	Slag removability	Arc stability	Welding defect (intrinsic)	Welding defect (extrinsic)	Bead outer appearance	Bead shape	Slag removability	Arc stability	Welding defect (intrinsic)	Welding defect (extrinsic)
Comparative Examples	1	2.2	B	D	B	B	B	B	B	D	B	B	B	B
	2	2.6	B	C	B	B	B	B	B	C	B	B	B	B
	3	2.2	B	B	D	B	B	B	B	B	C	B	B	B
	4	2.7	C	C	B	B	B	B	C	C	B	B	B	B
	5	3.7	B	C	B	B	C	C	B	C	B	B	D	D
	6	1.8	B	B	D	B	B	B	B	B	C	B	B	B
	7	2.3	B	D	B	B	B	B	B	D	B	B	B	B
	8	3.4	B	B	B	B	B	C	B	B	B	B	B	C
	9	2.5	B	B	D	B	B	B	B	B	C	B	B	B
	10	3.1	B	B	B	B	B	C	B	B	B	B	B	C
	11	-	difficult-to-weld											
	12	3.8	C	C	B	B	B	B	C	C	B	B	B	B
	13	2.8	B	B	B	B	B	D	B	B	B	B	B	C
	14	2.7	C	C	D	B	B	B	C	C	C	B	B	B
	15	2.9	B	C	B	B	B	B	B	C	B	B	B	B
	16	5.5	A	A	A	A	A	A	A	A	A	A	A	A
	17	4.9	A	A	A	A	A	A	A	A	A	A	A	A
	18	1.9	B	B	D	B	B	B	B	B	C	B	B	B
	19	2.5	D	D	B	B	B	B	D	D	B	B	B	B
	20	2.3	A	A	A	A	A	D	A	A	A	A	A	C

[0083]

In the flux of Comparative Example No. 1 shown in Table 7, an Al_2O_3 content exceeded 35% by mass, resulting in defective bead shape. Whereas, in the flux of Comparative Example No. 2, an Al_2O_3 content was less than 15% by mass, resulting in inferior bead shape. In the flux of Comparative Example No. 3, a SiO_2 content exceeded 30% by mass, resulting in inferior slag removability. Whereas, in the flux of Comparative Example No. 4, a SiO_2 content was less than 10% by mass, resulting in inferior bead outer appearance and bead shape.

[0084]

In the flux of Comparative Example No. 5, an MgO content exceeded 25% by mass, resulting in inferior bead shape, further generating welding defects inside and at the surface of the weld metal. Whereas, in the flux of Comparative Example No. 6, an MgO content was less than 10% by mass, causing burning, resulting in inferior slag removability. In the flux of Comparative Example No. 7, an F content exceeded 25% by mass, resulting in inferior bead shape. Whereas, in the flux of Comparative Example No. 8, an F content is less than 10% by mass, thus generating welding defects, including undercut parts and pockmarks.

[0085]

In the flux of Comparative Example No. 9, an Mn content (in terms of MnO) exceeded 20% by mass, causing burning, resulting in inferior slag removability. Whereas, in the flux of

Comparative Example No. 10, an Mn content (in terms of MnO) was less than 3% by mass, causing welding defects at the surface of the weld metal, including the undercut parts and pockmarks. In the flux of Comparative Example No. 11, the total of a Na content (in terms of Na₂O) and a K content (in terms of K₂O) was less than 0.5% by mass, so that the arc stability was drastically reduced, and both the bead outer appearance and the bead shape were degraded. As a result, the welding was difficult to perform. Whereas, in the flux of Comparative Example No. 12, the total of a Na content (in terms of Na₂O) and a K content (in terms of K₂O) exceeded 8.5% by mass, resulting in inferior bead outer appearance and bead shape.

[0086]

In the flux of Comparative Example No. 13, an Fe content (in terms of FeO) was less than 0.5% by mass, generating welding defects, such as the undercut parts and pockmarks, at the surface of the weld metal. Whereas, in the flux of Comparative Example No. 14, an Fe content (in terms of FeO) exceeded 8% by mass, resulting in inferior bead outer appearance and bead shape, further degrading the slag removability. In the flux of Comparative Example No. 15, a TiO₂ content exceeded 8% by mass, thereby degrading the bead shape. Whereas, in the flux of Comparative Example No. 16, the water-soluble SiO₂ content was equal to or more than 1.0% by mass, increasing the diffusion hydrogen content in the weld metal.

[0087]

In the flux of Comparative Example No. 17, since $M(II)$ ($= [MgO] / ([Al_2O_3] + [MnO] + [TiO_2])$) exceeded 0.8, the diffusion hydrogen content in the weld metal was increased. Whereas, in the flux of Comparative Example No. 18, since $M(II)$ was less than 0.2, a number of burned parts were generated, thus drastically degrading the slag removability. In the flux of Comparative Example No. 19, since a CaO content exceeded 6% by mass, the welding defects, including the undercut parts and pockmarks, were generated at the surface of the weld metal. Further, in the flux of Comparative Example No. 20, since a C content in the flux exceeded 0.2% by mass, pockmarks were generated.

[0088]

In contrast, the fluxes in Examples Nos. 1 to 32 shown in Table 6 satisfied the scope of the present invention, and thus had excellent bead outer appearance, bead shape, slag removability, and arc stability, resulting in no welding defects (intrinsic and extrinsic defects). As can be confirmed from the result mentioned above, the use of the flux in the present invention can improve the welding workability and reduce the diffusion hydrogen content in the weld metal in the use of either AC welding or DC welding.

CLAIMS

1. A flux for submerged arc welding, comprising:

Al₂O₃: 15 to 35% by mass;

SiO₂: 10 to 30% by mass;

MgO: 10 to 25% by mass;

F (in terms of CaF₂): 10 to 25% by mass;

Mn (in terms of MnO): 3 to 20% by mass;

Na (in terms of Na₂O) and/or K (in terms of K₂O): 0.5 to 4.5% by mass in total; and

Fe (in terms of FeO): 0.5 to 8% by mass, wherein
a CaO content is restricted to 6% by mass or less,
a water-soluble SiO₂ content is restricted to less than 1% by mass,
and

the flux satisfies the following formula (I):

$$0.2 \leq [\text{MgO}] / ([\text{Al}_2\text{O}_3] + [\text{MnO}]) \leq 0.8 \quad (\text{I})$$

where [Al₂O₃] is an Al₂O₃ content, [MgO] is an MgO content, and [MnO] is an Mn content (in terms of MnO).

2. The flux for submerged arc welding according to claim 1, further comprising: TiO₂: 8% by mass or less, wherein the flux satisfies the following formula (II):

$$0.2 \leq [\text{MgO}] / ([\text{Al}_2\text{O}_3] + [\text{MnO}] + [\text{TiO}_2]) \leq 0.8 \quad (\text{II})$$

where [TiO₂] is a TiO₂ content.

3. The flux for submerged arc welding according to claim 1, wherein a C content is 0.2% by mass or less.

4. The flux for submerged arc welding according to claim 2, wherein a C content is 0.2% by mass or less.

5. The flux for submerged arc welding according to any one of claims 1 to 4, wherein the flux is sintered at a temperature of 800°C or higher.