[CLAIMS]

[Claim 1]

An adhesive resin composition comprising a dicyclopentadiene-based hydrogenated resin and a thermoplastic resin,

wherein the dicyclopentadiene-based hydrogenated resin is prepared by hydrogenating a dicyclopentadiene-based resin prepared by copolymerizing a monomer composition including a dicyclopentadiene-based monomer and a vinylamide-based monomer, and

the adhesive resin composition has a mixed methylcyclohexane aniline cloud point of 60°C or lower and a diacetone alcohol cloud point of 60°C or lower.

[Claim 2]

The adhesive resin composition of claim 1, further comprising an oil.

[Claim 3]

The adhesive resin composition of claim 2, wherein the oil includes any one or two or more selected from the group consisting of paraffin-based oils, naphthene-based oils, and aromatic-based oils.

[Claim 4]

The adhesive resin composition of claim 1, wherein 50 to 90 wt% of the dicyclopentadiene-based hydrogenated resin and 10 to 50 wt% of the thermoplastic resin are included, based on a total weight of the adhesive resin composition.

[Claim 5]

The adhesive resin composition of claim 2, wherein 1 to 60 parts by weight of the oil is included, based on 100 parts by weight of the dicyclopentadiene-based hydrogenated resin and the thermoplastic resin.

[Claim 6]

The adhesive resin composition of claim 1, wherein the dicyclopentadiene-based monomer and the vinylamide-based monomer are included at a weight ratio of 99:1 to 50:50.