

Our Ref.: OP-34
EH-9028

- 1 -

PIGMENT-ATTACHED BLUE-EMITTING PHOSPHOR AND COLOR
CATHODE-RAY TUBE

The present invention relates to a pigment-attached blue-emitting phosphor suitable for a fluorescent layer of e.g. a color cathode-ray tube and to a color cathode-ray tube provided, on the inner surface of a face plate, a fluorescent layer containing such a pigment-attached blue-emitting phosphor, or a color cathode-ray tube provided with a blue pigment layer disposed between the inner surface of a face plate and a blue phosphor picture element.

To improve the contrast of images of color cathode-ray tubes, fluorescent display tubes, etc., there have been known a method which employs a pigment-attached phosphor wherein filter particles capable of absorbing the reflection of an exterior light at a fluorescent screen, are attached to the phosphor surface (USP 3,886,394 and USP 4,307,320), and a method which employs colored glass as the face plate of a cathode-ray tube.

In the method which employs colored glass as the face



- 2 -

plate of a cathode-ray tube, the transmittance of glass is reduced, whereby the contrast can be selected relatively readily within a practical range, but, the absorption of not only the exterior light but also the emission from the fluorescent layer increases, whereby the reduction of brightness is substantial.

Whereas, the method which employs the pigment-attached phosphor having filter particles attached, is a method effective for improving the contrast without reducing the brightness of a screen as far as possible.

The above filter particles are used sometimes for sharpening the emission spectrum of a phosphor. Such filter particles are required to have a transmittance high in the emission wavelength region of the phosphor and low in other wavelength regions. By this characteristic of the transmittance, light components which do not correspond to the emission of the phosphor itself will be absorbed, whereby the contrast under a bright exterior light can be improved.

With respect to the blue-emitting phosphor, it is suitable to use a pigment which has an absorption as small as possible at about 450 nm which is the emission peak of the phosphor, and an absorption as large as possible within the other wavelength regions.

As blue pigments of this type, there have been proposed ultramarine ($3\text{NaAl}\cdot\text{SiO}_2\cdot\text{Na}_2\text{S}_2$), prussian blue ($\text{Fe}_4[\text{Fe}(\text{CN})_6]_3\cdot n\text{H}_2\text{O}$), cobalt aluminate ($\text{CoO}\cdot n\text{Al}_2\text{O}_3$),



- 3 -

cerulean blue ($\text{CoO} \cdot n\text{SnO}_2$), copper sulfide (CuS), etc. in Japanese Unexamined Patent Publication No. 28784/1979.

However, from researches by the present inventors, it has been found that the body color of cobalt aluminate
5 commonly employed, does not correspond to the emission spectrum of the blue-emitting phosphor. The reflectance of the cobalt aluminate is especially high at around 490 nm, such being ineffective to improve the contrast.

The ultramarine practically used to some extent has
10 excellent properties as compared with the cobalt aluminate, but its chemical stability is very poor, whereby a problem of fading in the attaching step to the phosphor or in the coating step to the cathode-ray tube is brought about.

15 To prevent the fading, it has been known to employ a method wherein the ultramarine pigment is covered with a silicic compound. However, when it is coated on a cathode-ray tube, there is a problem that its body color is remarkably changed by irradiation of electron beams,
20 whereby a shift of the peak in the emission spectrum of the fluorescent screen is likely to occur.

On the other hand, the $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type blue pigment of Japanese Patent Application No. 148636/1991 proposed earlier by the present inventors, are superior to the
25 cobalt aluminate and the ultramarine in the color tone and fastness of the pigment-attached phosphor. However, the inorganic oxide pigment of this type is



- 4 -

produced by a method wherein starting materials of oxides or carbonates or chlorides are mixed in a dry system and fired at a temperature above 900°C, followed by cooling and pulverization, and with the phosphor having this

5 CoO·ZnO·SiO₂ type blue pigment attached thereon, the color stability in the baking step (at about 500°C for about one hour) for the production of a cathode-ray tube is not necessarily adequate. Accordingly, for cathode-ray tubes, for which high image qualities have been

10 increasingly demanded in recent years, it has been required to improve the heat resistance of the pigment-attached phosphors to improve the qualities of the cathode-ray tubes.

Under these circumstances, it is an object of the

15 present invention to solve the above problems and to provide a pigment-attached blue-emitting phosphor by attaching a blue pigment excellent in the heat resistance so that excellent blue-emission can be obtained even when subjected to the baking step for the production of a

20 cathode-ray tube, to provide a color cathode-ray tube provided with a fluorescent layer containing such a pigment-attached blue-emitting phosphor, and to provide a color cathode-ray tube having a layer of such a blue pigment disposed between a face plate and a blue phosphor

25 picture element.

The present invention provides a pigment-attached blue-emitting phosphor comprising a blue-emitting



- 5 -

phosphor and a blue pigment attached to the surface of the blue-emitting phosphor, said blue pigment being a $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type pigment containing Mo.

5 The present invention also provides a color cathode-ray tube comprising a face plate having, on the inner surface thereof, a fluorescent layer containing such a pigment-attached blue-emitting phosphor.

Further, the present invention provides a color cathode-ray tube comprising a face plate, a blue phosphor picture element and a layer of a $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type blue pigment containing Mo, said layer being disposed between the inner surface of the face plate and the blue phosphor picture element.

15 Here, the $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type pigment containing Mo is the one obtained by firing raw materials containing Co, Zn, Si and Mo usually at a temperature of at least 800°C for several tens minutes to several tens hours, followed by cooling and pulverization. This pigment includes a mixture of oxides of the respective elements or a
20 composite oxide thereof, a mixture of cobalt silicate and zinc silicate or a solid solution of both, and a mixture thereof. The raw material containing Mo is considered to function mainly as a flux or mineralizer during the formation of the pigment.

25 The compositional ratio of the $x\text{CoO} \cdot y\text{ZnO} \cdot z\text{SiO}_2$ type pigment is preferably within ranges of $0.05 \leq x/z \leq 1.5$ and $0.1 \leq y/z \leq 2.0$, particularly preferably within ranges of




- 6 -

0.2 $\leq$ x/z $\leq$ 1.0 and 0.3 $\leq$ y/z $\leq$ 1.7. If the ratio is outside the ranges, the color tone tends to change, such being sometimes not suitable for the blue pigment to be combined with the blue-emitting phosphor. The content of Mo is preferably within a range of from 0.01 to 10% by weight, more preferably from 0.1 to 2% by weight. If the content is less than this range, improvement in the heat resistance tends to be inadequate. If it exceeds this range, the color tone tends to change, such being undesirable.

It is possible to incorporate various fluxes and other elements at the time of firing the above pigment, if necessary. More specifically, it is possible to incorporate Li, Na, K, Ca, Mg, Ba, Fe, Ni, Cu, Mn, Ti, V, Al, Sn, Sb, Cr, Pr, etc. These elements may be added within a range of not more than about 5% by weight in total. If the amount exceeds this limit, it becomes impossible to obtain a desirable color tone as the blue pigment.

The blue-emitting phosphor useful for the present invention includes those having a main part of the emission spectrum within the range of from 380 to 500 nm, more specifically, a silver-activated zinc sulfide type phosphor [ZnS:Ag,X (wherein X is halogen or Al), ZnS:Ag,M,X (wherein M is Ga, In, etc., and X is halogen or Al)], Y₂SiO₅:Ce, Ca₂B₅O₉Cl:Eu, (Ba_xMg_{1-x})O·nAl₂O₃:Eu (0 $\leq$ x $\leq$ 1, 7 $\leq$ n $\leq$ 8), SrSi₃O₈Cl₄:Eu, CaWO₄, CaWO₄:Pb, BaFCl:Eu,



- 7 -

$\text{Gd}_2\text{O}_2\text{S:Tb}$ and ZnS:Zn .

The amount of the above blue pigment attached to the blue-emitting phosphor is preferably within the range of from 0.3 to 15 wt%. If the attached amount is below the
5 lower limit, the filter effect tends to be too small, and if it exceeds the upper limit, the luminescence brightness tends to be insufficient.

In the course of various studies of $x\text{CoO}\cdot y\text{ZnO}\cdot z\text{SiO}_2$ type pigment-attached blue-emitting phosphors, the
10 present inventors have found that the heat resistance of the above pigment containing Mo is improved, that the color stability of the phosphor having such a pigment attached thereon, is improved, and that it is possible to obtain a fluorescent screen having a high contrast while
15 maintaining brightness by coating such a pigment-attached phosphor on a face plate, or by coating such a pigment in the form of a layer disposed between the face plate and the blue-emitting phosphor layer, and it is thereby possible to provide a color cathode-ray tube which can be
20 easily viewed even under a bright exterior light.

The reason for the improvement in the heat resistance of the above pigment is not clearly understood. However, it is considered that by using Mo, the crystal structure of the pigment is made firm and hardly susceptible to a
25 deterioration of the crystal surface during the pulverization step after firing the pigment.

In the accompanying drawings:



- 8 -

Figure 1 is a partially cutaway side view of the color cathode-ray tube of the present invention having pigment layers and phosphor picture elements laminated on a face plate.

5 Figure 2 is an enlarged sectional view of a main part of the fluorescent screen of Figure 1.

 The formation of a pigment layer on the face plate is carried out by a photolithography technique like the formation of the fluorescent layer. Firstly, a first
10 pigment slurry, for example, a slurry composed of a mixture of a green pigment and a photosensitive binder comprising ammonium dichromate and polyvinyl alcohol, is coated on the inner surface of a face plate 1 previously having a black matrix 2 formed thereon, and dried to form
15 a layer. This layer is exposed to a light through a shadow mask, and developed to form a green pigment layer 3 into a predetermined pattern. Then, a second pigment slurry, for example, a blue pigment slurry composed of a mixture of a blue pigment and a photosensitive binder, is
20 used to form a blue pigment layer 4 into a predetermined pattern in the same manner as in the above at a position other than the above green pigment layer 3. Further, a third pigment slurry, for example, a red pigment slurry is used to form a red pigment layer 5 into a
25 predetermined pattern in the same manner as in the above at a position other than the green pigment layer 3 and the blue pigment layer 4.



- 9 -


Then, a green phosphor, a blue phosphor and a red phosphor are coated on the pigment layers of the respective colors by a photolithography technique to form a green phosphor picture element 6, a blue phosphor picture element 7 and a red phosphor picture element 8. Further, an aluminium layer is vapor-deposited thereon to form a metal back 9, whereby a fluorescent screen is completed on the face plate 1. A panel 10 provided with this face plate 1 is sealed with a funnel 11, and an electron gun 12 is mounted thereon to complete a color cathode-ray tube.

The color cathode-ray tube employing the pigment-attached blue-emitting phosphor of the present invention, can be prepared by attaching the pigment-attached blue-emitting phosphor picture element directly on the face plate omitting the pigment layer of Figure 1.

Now, the present invention will be described in further detail with reference to Examples. However, it should be understood that the present invention is by no means restricted by such specific Examples. In the following Examples, "parts" means "parts by weight".

Preparation of a Mo-containing blue pigment

60 Parts of cobalt oxide, 103 parts of zinc oxide, 64 parts of silicon oxide and 19 parts of $\text{Na}_6(\text{Mo}_7\text{O}_{24}) \cdot 22\text{H}_2\text{O}$ were mixed and fired in air at 900°C for 2 hours, then cooled and pulverized to obtain a $x\text{CoO} \cdot y\text{ZnO} \cdot z\text{SiO}_2$ pigment ($x=0.8$, $y=1.3$, $z=1.0$) having a Mo content of 0.5% by



- 10 -

weight and an average particle size of 0.5 μm .

EXAMPLE 1

100 Parts of distilled water was added to 100 parts
of a silver-activated zinc sulfide blue-emitting phosphor
5 to obtain a slurry, and 5 parts of the above blue pigment
and 0.3 part of a SBR emulsion (the amount of the resin
per 100 parts of the phosphor) were added thereto and
mixed. The pH of the mixed slurry was adjusted to attach
the pigment to the phosphor, followed by filtration and
10 drying at 120°C for 15 hours to obtain a pigment-attached
blue-emitting phosphor.

EXAMPLE 2

Using a pigment slurry comprising 5 parts of the
above blue pigment, 2 parts of polyvinyl alcohol
15 (polymerization degree: 2400, saponification degree:
88%), 0.15 part of sodium dichromate, 0.03 part of a
surfactant and the rest being water, a blue pigment layer
having an average thickness of 1 μm was formed on the
inner surface of a face plate by photolithography.

20 Then, using a ZnS:Ag,Cl blue-emitting phosphor, a
blue phosphor picture element was formed on the above
blue pigment layer in accordance with a conventional
method.

25 Example for the preparation of a conventional blue pigment

60 Parts of cobalt oxide, 103 parts of zinc oxide and
64 parts of silicon oxide were mixed and fired in air at



- 11 -

1300°C for 2 hours, then cooled and pulverized to obtain a $x\text{CoO} \cdot y\text{ZnO} \cdot z\text{SiO}_2$ pigment ($x=0.8$, $y=1.3$, $z=1.0$) having an average particle size of $0.6 \mu\text{m}$.

COMPARATIVE EXAMPLE 1

- 5 A pigment-attached blue-emitting phosphor was prepared in the same manner as in Example 1 except that in Example 1, the above conventional blue pigment was used instead of the Mo-containing blue pigment.

COMPARATIVE EXAMPLE 2

- 10 A blue pigment layer and a blue-emitting phosphor picture element were formed on the inner surface of a face plate in the same manner as in Example 2 except that in Example 2, the above conventional blue pigment was used instead of the Mo-containing blue pigment.

15 COMPARATIVE EXAMPLE 3

A blue-emitting phosphor picture element was formed in the same manner as in Example 2 except that in Example 2, the Mo-containing blue pigment layer was omitted.

Heat resistance test

- 20 To the pigment-attached phosphors of Example 1 and Comparative Example 1, baking treatment was applied at 500°C for one hour, and the powder reflectance (%) at 450 nm was measured before and after the treatment, whereupon the change $[(\text{before} - \text{after})/\text{before} \times 100\%]$ was
- 25 determined. The results are shown in Table 1.

It is evident from Table 1 that by the addition of Mo, the change in the powder reflectance before and after



- 12 -

the baking treatment becomes extremely small, which indicates that the heat resistance of the pigment-attached phosphor is improved.

Table 1

	Powder reflectance (%)		
	Before baking	After baking	Change (%)
Example 1	79.0	78.8	0.3
Comparative Example 1	74.5	62.0	16.8

Test on luminance and contrast

The surface of the face plates of Example 2 and Comparative Examples 2 and 3, was irradiated with an exterior light, and the white luminance of the highlight parts (white-emitting parts under mounted condition) and the luminance of the shadow parts (non-emitting parts under mounted condition) were measured, and their ratio was calculated. The white luminance and the ratio as the contrast are shown in Table 2.

It is evident from Table 2 that with the fluorescent screen of Example 2, the reduction of the white luminance is little as compared with Comparative Example 2, which indicates that a high contrast is maintained.



- 13 -

Table 2

	White luminance	Contrast
Example 2	96	128
Comparative Example 2	90	120
Comparative Example 3	100	100

10

According to the present invention, by adopting the above construction, it has been made possible to improve the heat resistance of a pigment-attached blue-emitting phosphor and to provide a blue-emitting phosphor excellent in the color stability, which is useful for the production of a color cathode-ray tube. Further, a fluorescent screen having a high contrast can be obtained while maintaining the brightness either by forming the above-mentioned blue pigment layer between the inner surface of a face plate and a blue phosphor picture element, or by forming the blue pigment-attached blue-phosphor picture element on the inner surface of a face plate, whereby it has been made possible to provide a color cathode-ray tube which can be easily viewed even under bright lightning.



- 14 -

CLAIMS:

1. A pigment-attached blue-emitting phosphor comprising a blue-emitting phosphor and a blue pigment attached to the surface of the blue-emitting phosphor, said blue pigment being a $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type pigment containing Mo.
2. The pigment-attached blue-emitting phosphor according to Claim 1, wherein the blue pigment is represented by the formula $x\text{CoO} \cdot y\text{ZnO} \cdot z\text{SiO}_2$ wherein the compositional ratio is within the ranges of $0.05 \leq x/z \leq 1.5$ and $0.1 \leq y/z \leq 2.0$.
3. The pigment-attached blue-emitting phosphor according to Claim 1, wherein the Mo content in the blue pigment is within a range of from 0.01 to 10% by weight.
4. The pigment-attached blue-emitting phosphor according to Claim 1, wherein the blue pigment contains at most about 5% by weight in total of Li, Na, K, Ca, Mg, Ba, Fe, Ni, Cu, Mn, Ti, V, Al, Sn, Sb, Cr and Pr.
5. The pigment-attached blue-emitting phosphor according to Claim 1, wherein the blue-emitting phosphor is at least one member selected from the group consisting of ZnS:Ag,X wherein X is halogen or Al, ZnS:Ag,M,X wherein M is Ga or In, and X is halogen or Al, $\text{Y}_2\text{SiO}_5\text{:Ce}$, $\text{Ca}_2\text{B}_5\text{O}_9\text{Cl:Eu}$, $(\text{Ba}_x\text{Mg}_{1-x})\text{O} \cdot n\text{Al}_2\text{O}_3\text{:Eu}$ ($0 \leq x \leq 1$, $7 \leq n \leq 8$), $\text{SrSi}_3\text{O}_8\text{Cl}_4\text{:Eu}$, CaWO_4 , $\text{CaWO}_4\text{:Pb}$, BaFCl:Eu , $\text{Gd}_2\text{O}_2\text{S:Tb}$ and ZnS:Zn .
6. The pigment-attached blue-emitting phosphor according to Claim 1, wherein the blue pigment is attached to the



- 15 -

blue-emitting phosphor in an amount within a range of from 0.3 to 15% by weight.

7. A color cathode-ray tube comprising a face plate having, on the inner surface thereof, a fluorescent layer
5 containing a pigment-attached blue-emitting phosphor as defined in Claim 1.

8. A color cathode-ray tube comprising a face plate, a blue phosphor picture element and a layer of a $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type blue pigment containing Mo, said layer
10 being disposed between the inner surface of the face plate and the blue phosphor picture element.



- 16 -

ABSTRACT

A pigment-attached blue-emitting phosphor comprising a blue-emitting phosphor and a blue pigment attached to the surface of the blue-emitting phosphor, said blue pigment being a $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type pigment containing Mo.



1/1

FIGURE 1





FIGURE 2



- 1 -

PIGMENT-ATTACHED BLUE-EMITTING PHOSPHOR AND COLOR
CATHODE-RAY TUBE

The present invention relates to a pigment-attached blue-emitting phosphor suitable for a fluorescent layer of e.g. a color cathode-ray tube and to a color cathode-ray tube provided, on the inner surface of a face plate, a fluorescent layer containing such a pigment-attached blue-emitting phosphor, or a color cathode-ray tube provided with a blue pigment layer disposed between the inner surface of a face plate and a blue phosphor picture element.

To improve the contrast of images of color cathode-ray tubes, fluorescent display tubes, etc., there have been known a method which employs a pigment-attached phosphor wherein filter particles capable of absorbing the reflection of an exterior light at a fluorescent screen, are attached to the phosphor surface (USP 3,886,394 and USP 4,307,320), and a method which employs colored glass as the face plate of a cathode-ray tube.

In the method which employs colored glass as the face

25 JUL 1996

Date

- 2 -

plate of a cathode-ray tube, the transmittance of glass is reduced, whereby the contrast can be selected relatively readily within a practical range, but, the absorption of not only the exterior light but also the emission from the fluorescent layer increases, whereby the reduction of brightness is substantial.

Whereas, the method which employs the pigment-attached phosphor having filter particles attached, is a method effective for improving the contrast without reducing the brightness of a screen as far as possible.

The above filter particles are used sometimes for sharpening the emission spectrum of a phosphor. Such filter particles are required to have a transmittance high in the emission wavelength region of the phosphor and low in other wavelength regions. By this characteristic of the transmittance, light components which do not correspond to the emission of the phosphor itself will be absorbed, whereby the contrast under a bright exterior light can be improved.

With respect to the blue-emitting phosphor, it is suitable to use a pigment which has an absorption as small as possible at about 450 nm which is the emission peak of the phosphor, and an absorption as large as possible within the other wavelength regions.

As blue pigments of this type, there have been proposed ultramarine ($3\text{NaAl-SiO}_2\text{-Na}_2\text{S}_2$), prussian blue ($\text{Fe}_4[\text{Fe}(\text{CN})_6]_3\cdot n\text{H}_2\text{O}$), cobalt aluminate ($\text{CoO}\cdot n\text{Al}_2\text{O}_3$),

- 3 -

cerulean blue ($\text{CoO} \cdot n\text{SnO}_2$), copper sulfide (CuS), etc. in Japanese Unexamined Patent Publication No. 28784/1979.

However, from researches by the present inventors, it has been found that the body color of cobalt aluminate commonly employed, does not correspond to the emission spectrum of the blue-emitting phosphor. The reflectance of the cobalt aluminate is especially high at around 490 nm, such being ineffective to improve the contrast.

The ultramarine practically used to some extent has excellent properties as compared with the cobalt aluminate, but its chemical stability is very poor, whereby a problem of fading in the attaching step to the phosphor or in the coating step to the cathode-ray tube is brought about.

To prevent the fading, it has been known to employ a method wherein the ultramarine pigment is covered with a silicic compound. However, when it is coated on a cathode-ray tube, there is a problem that its body color is remarkably changed by irradiation of electron beams, whereby a shift of the peak in the emission spectrum of the fluorescent screen is likely to occur.

On the other hand, the $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type blue pigment of Japanese Patent Application No. 148636/1991 proposed earlier by the present inventors, are superior to the cobalt aluminate and the ultramarine in the color tone and fastness of the pigment-attached phosphor. However, the inorganic oxide pigment of this type is

- 4 -

produced by a method wherein starting materials of oxides or carbonates or chlorides are mixed in a dry system and fired at a temperature above 900°C, followed by cooling and pulverization, and with the phosphor having this $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type blue pigment attached thereon, the color stability in the baking step (at about 500°C for about one hour) for the production of a cathode-ray tube is not necessarily adequate. Accordingly, for cathode-ray tubes, for which high image qualities have been increasingly demanded in recent years, it has been required to improve the heat resistance of the pigment-attached phosphors to improve the qualities of the cathode-ray tubes.

Under these circumstances, it is an object of the present invention to solve the above problems and to provide a pigment-attached blue-emitting phosphor by attaching a blue pigment excellent in the heat resistance so that excellent blue-emission can be obtained even when subjected to the baking step for the production of a cathode-ray tube, to provide a color cathode-ray tube provided with a fluorescent layer containing such a pigment-attached blue-emitting phosphor, and to provide a color cathode-ray tube having a layer of such a blue pigment disposed between a face plate and a blue phosphor picture element.

The present invention provides a pigment-attached blue-emitting phosphor comprising a blue-emitting

- 5 -

phosphor and a blue pigment attached to the surface of the blue-emitting phosphor, said blue pigment being a $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type pigment containing Mo.

The present invention also provides a color cathode-ray tube comprising a face plate having, on the inner surface thereof, a fluorescent layer containing such a pigment-attached blue-emitting phosphor.

Further, the present invention provides a color cathode-ray tube comprising a face plate, a blue phosphor picture element and a layer of a $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type blue pigment containing Mo, said layer being disposed between the inner surface of the face plate and the blue phosphor picture element.

Here, the $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type pigment containing Mo is the one obtained by firing raw materials containing Co, Zn, Si and Mo usually at a temperature of at least 800°C for several tens minutes to several tens hours, followed by cooling and pulverization. This pigment includes a mixture of oxides of the respective elements or a composite oxide thereof, a mixture of cobalt silicate and zinc silicate or a solid solution of both, and a mixture thereof. The raw material containing Mo is considered to function mainly as a flux or mineralizer during the formation of the pigment.

The compositional ratio of the $x\text{CoO} \cdot y\text{ZnO} \cdot z\text{SiO}_2$ type pigment is preferably within ranges of $0.05 \leq x/z \leq 1.5$ and $0.1 \leq y/z \leq 2.0$, particularly preferably within ranges of

- 6 -

$0.2 \leq x/z \leq 1.0$ and $0.3 \leq y/z \leq 1.7$. If the ratio is outside the ranges, the color tone tends to change, such being sometimes not suitable for the blue pigment to be combined with the blue-emitting phosphor. The content of Mo is preferably within a range of from 0.01 to 10% by weight, more preferably from 0.1 to 2% by weight. If the content is less than this range, improvement in the heat resistance tends to be inadequate. If it exceeds this range, the color tone tends to change, such being undesirable.

It is possible to incorporate various fluxes and other elements at the time of firing the above pigment, if necessary. More specifically, it is possible to incorporate Li, Na, K, Ca, Mg, Ba, Fe, Ni, Cu, Mn, Ti, V, Al, Sn, Sb, Cr, Pr, etc. These elements may be added within a range of not more than about 5% by weight in total. If the amount exceeds this limit, it becomes impossible to obtain a desirable color tone as the blue pigment.

The blue-emitting phosphor useful for the present invention includes those having a main part of the emission spectrum within the range of from 380 to 500 nm, more specifically, a silver-activated zinc sulfide type phosphor [ZnS:Ag,X (wherein X is halogen or Al), ZnS:Ag,M,X (wherein M is Ga, In, etc., and X is halogen or Al)], $\text{Y}_2\text{SiO}_5\text{:Ce}$, $\text{Ca}_2\text{B}_5\text{O}_9\text{Cl:Eu}$, $(\text{Ba}_x\text{Mg}_{1-x})\text{O} \cdot n\text{Al}_2\text{O}_3\text{:Eu}$ ($0 \leq x \leq 1$, $7 \leq n \leq 8$), $\text{SrSi}_3\text{O}_8\text{Cl}_4\text{:Eu}$, CaWO_4 , $\text{CaWO}_4\text{:Pb}$, BaFCl:Eu ,

- 7 -

$\text{Gd}_2\text{O}_2\text{S:Tb}$ and ZnS:Zn .

The amount of the above blue pigment attached to the blue-emitting phosphor is preferably within the range of from 0.3 to 15 wt%. If the attached amount is below the lower limit, the filter effect tends to be too small, and if it exceeds the upper limit, the luminescence brightness tends to be insufficient.

In the course of various studies of $x\text{CoO} \cdot y\text{ZnO} \cdot z\text{SiO}_2$ type pigment-attached blue-emitting phosphors, the present inventors have found that the heat resistance of the above pigment containing Mo is improved, that the color stability of the phosphor having such a pigment attached thereon, is improved, and that it is possible to obtain a fluorescent screen having a high contrast while maintaining brightness by coating such a pigment-attached phosphor on a face plate, or by coating such a pigment in the form of a layer disposed between the face plate and the blue-emitting phosphor layer, and it is thereby possible to provide a color cathode-ray tube which can be easily viewed even under a bright exterior light.

The reason for the improvement in the heat resistance of the above pigment is not clearly understood. However, it is considered that by using Mo, the crystal structure of the pigment is made firm and hardly susceptible to a deterioration of the crystal surface during the pulverization step after firing the pigment.

In the accompanying drawings:

- 8 -

Figure 1 is a partially cutaway side view of the color cathode-ray tube of the present invention having pigment layers and phosphor picture elements laminated on a face plate.

Figure 2 is an enlarged sectional view of a main part of the fluorescent screen of Figure 1.

The formation of a pigment layer on the face plate is carried out by a photolithography technique like the formation of the fluorescent layer. Firstly, a first pigment slurry, for example, a slurry composed of a mixture of a green pigment and a photosensitive binder comprising ammonium dichromate and polyvinyl alcohol, is coated on the inner surface of a face plate 1 previously having a black matrix 2 formed thereon, and dried to form a layer. This layer is exposed to a light through a shadow mask, and developed to form a green pigment layer 3 into a predetermined pattern. Then, a second pigment slurry, for example, a blue pigment slurry composed of a mixture of a blue pigment and a photosensitive binder, is used to form a blue pigment layer 4 into a predetermined pattern in the same manner as in the above at a position other than the above green pigment layer 3. Further, a third pigment slurry, for example, a red pigment slurry is used to form a red pigment layer 5 into a predetermined pattern in the same manner as in the above at a position other than the green pigment layer 3 and the blue pigment layer 4.

- 9 -

Then, a green phosphor, a blue phosphor and a red phosphor are coated on the pigment layers of the respective colors by a photolithography technique to form a green phosphor picture element 6, a blue phosphor picture element 7 and a red phosphor picture element 8. Further, an aluminium layer is vapor-deposited thereon to form a metal back 9, whereby a fluorescent screen is completed on the face plate 1. A panel 10 provided with this face plate 1 is sealed with a funnel 11, and an electron gun 12 is mounted thereon to complete a color cathode-ray tube.

The color cathode-ray tube employing the pigment-attached blue-emitting phosphor of the present invention, can be prepared by attaching the pigment-attached blue-emitting phosphor picture element directly on the face plate omitting the pigment layer of Figure 1.

Now, the present invention will be described in further detail with reference to Examples. However, it should be understood that the present invention is by no means restricted by such specific Examples. In the following Examples, "parts" means "parts by weight".

Preparation of a Mo-containing blue pigment

60 Parts of cobalt oxide, 103 parts of zinc oxide, 64 parts of silicon oxide and 19 parts of $\text{Na}_6(\text{Mo}_7\text{O}_{24}) \cdot 22\text{H}_2\text{O}$ were mixed and fired in air at 900°C for 2 hours, then cooled and pulverized to obtain a $x\text{CoO} \cdot y\text{ZnO} \cdot z\text{SiO}_2$ pigment ($x=0.8$, $y=1.3$, $z=1.0$) having a Mo content of 0.5% by

- 10 -

weight and an average particle size of 0.5 μm .

EXAMPLE 1

100 Parts of distilled water was added to 100 parts of a silver-activated zinc sulfide blue-emitting phosphor to obtain a slurry, and 5 parts of the above blue pigment and 0.3 part of a SBR emulsion (the amount of the resin per 100 parts of the phosphor) were added thereto and mixed. The pH of the mixed slurry was adjusted to attach the pigment to the phosphor, followed by filtration and drying at 120°C for 15 hours to obtain a pigment-attached blue-emitting phosphor.

EXAMPLE 2

Using a pigment slurry comprising 5 parts of the above blue pigment, 2 parts of polyvinyl alcohol (polymerization degree: 2400, saponification degree: 88%), 0.15 part of sodium dichromate, 0.03 part of a surfactant and the rest being water, a blue pigment layer having an average thickness of 1 μm was formed on the inner surface of a face plate by photolithography.

Then, using a ZnS:Ag,Cl blue-emitting phosphor, a blue phosphor picture element was formed on the above blue pigment layer in accordance with a conventional method.

Example for the preparation of a conventional blue pigment

60 Parts of cobalt oxide, 103 parts of zinc oxide and 64 parts of silicon oxide were mixed and fired in air at

- 11 -

1300°C for 2 hours, then cooled and pulverized to obtain a $x\text{CoO} \cdot y\text{ZnO} \cdot z\text{SiO}_2$ pigment ($x=0.8$, $y=1.3$, $z=1.0$) having an average particle size of $0.6 \mu\text{m}$.

COMPARATIVE EXAMPLE 1

A pigment-attached blue-emitting phosphor was prepared in the same manner as in Example 1 except that in Example 1, the above conventional blue pigment was used instead of the Mo-containing blue pigment.

COMPARATIVE EXAMPLE 2

A blue pigment layer and a blue-emitting phosphor picture element were formed on the inner surface of a face plate in the same manner as in Example 2 except that in Example 2, the above conventional blue pigment was used instead of the Mo-containing blue pigment.

COMPARATIVE EXAMPLE 3

A blue-emitting phosphor picture element was formed in the same manner as in Example 2 except that in Example 2, the Mo-containing blue pigment layer was omitted.

Heat resistance test

To the pigment-attached phosphors of Example 1 and Comparative Example 1, baking treatment was applied at 500°C for one hour, and the powder reflectance (%) at 450 nm was measured before and after the treatment, whereupon the change $[(\text{before} - \text{after}) / \text{before} \times 100\%]$ was determined. The results are shown in Table 1.

It is evident from Table 1 that by the addition of Mo, the change in the powder reflectance before and after

- 12 -

the baking treatment becomes extremely small, which indicates that the heat resistance of the pigment-attached phosphor is improved.

Table 1

	Powder reflectance (%)		
	Before baking	After baking	Change (%)
Example 1	79.0	78.8	0.3
Comparative Example 1	74.5	62.0	16.8

Test on luminance and contrast

The surface of the face plates of Example 2 and Comparative Examples 2 and 3, was irradiated with an exterior light, and the white luminance of the highlight parts (white-emitting parts under mounted condition) and the luminance of the shadow parts (non-emitting parts under mounted condition) were measured, and their ratio was calculated. The white luminance and the ratio as the contrast are shown in Table 2.

It is evident from Table 2 that with the fluorescent screen of Example 2, the reduction of the white luminance is little as compared with Comparative Example 2, which indicates that a high contrast is maintained.

- 13 -

Table 2

	White luminance	Contrast
Example 2	96	128
Comparative Example 2	90	120
Comparative Example 3	100	100

According to the present invention, by adopting the above construction, it has been made possible to improve the heat resistance of a pigment-attached blue-emitting phosphor and to provide a blue-emitting phosphor excellent in the color stability, which is useful for the production of a color cathode-ray tube. Further, a fluorescent screen having a high contrast can be obtained while maintaining the brightness either by forming the above-mentioned blue pigment layer between the inner surface of a face plate and a blue phosphor picture element, or by forming the blue pigment-attached blue-phosphor picture element on the inner surface of a face plate, whereby it has been made possible to provide a color cathode-ray tube which can be easily viewed even under bright lightning.



CLAIMS:

1. A pigment-attached blue-emitting phosphor comprising a blue-emitting phosphor and a blue pigment attached to the surface of the blue-emitting phosphor, said blue pigment being a $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type pigment containing Mo.
2. The pigment-attached blue-emitting phosphor according to Claim 1, wherein the blue pigment is represented by the formula $x\text{CoO} \cdot y\text{ZnO} \cdot z\text{SiO}_2$ wherein the compositional ratio is within the ranges of $0.05 \leq x/z \leq 1.5$ and $0.1 \leq y/z \leq 2.0$.
3. The pigment-attached blue-emitting phosphor according to Claim 1, wherein the Mo content in the blue pigment is within a range of from 0.01 to 10% by weight.
4. The pigment-attached blue-emitting phosphor according to Claim 1, wherein the blue pigment contains at most about 5% by weight in total of Li, Na, K, Ca, Mg, Ba, Fe, Ni, Cu, Mn, Ti, V, Al, Sn, Sb, Cr and Pr.
5. The pigment-attached blue-emitting phosphor according to Claim 1, wherein the blue-emitting phosphor is at least one member selected from the group consisting of ZnS:Ag,X wherein X is halogen or Al, ZnS:Ag,M,X wherein M is Ga or In, and X is halogen or Al, $\text{Y}_2\text{SiO}_5\text{:Ce}$, $\text{Ca}_2\text{B}_5\text{O}_9\text{Cl:Eu}$, $(\text{Ba}_x\text{Mg}_{1-x})\text{O} \cdot n\text{Al}_2\text{O}_3\text{:Eu}$ ($0 \leq x \leq 1$, $7 \leq n \leq 8$), $\text{SrSi}_3\text{O}_8\text{Cl}_4\text{:Eu}$, CaWO_4 , $\text{CaWO}_4\text{:Pb}$, BaFCl:Eu , $\text{Gd}_2\text{O}_2\text{S:Tb}$ and ZnS:Zn .
6. The pigment-attached blue-emitting phosphor according to Claim 1, wherein the blue pigment is attached to the



- 15 -

blue-emitting phosphor in an amount within a range of from 0.3 to 15% by weight.

7. A color cathode-ray tube comprising a face plate having, on the inner surface thereof, a fluorescent layer containing a pigment-attached blue-emitting phosphor as defined in Claim 1.

8. A color cathode-ray tube comprising a face plate, a blue phosphor picture element and a layer of a $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type blue pigment containing Mo, said layer being disposed between the inner surface of the face plate and the blue phosphor picture element.

- 16 -

ABSTRACT**PIGMENT-ATTACHED BLUE EMITTING PHOSPHOR AND
COLOR CATHODE-RAY TUBE**

A pigment-attached blue-emitting phosphor comprising a blue-emitting phosphor and a blue pigment attached to the surface of the blue-emitting phosphor, said blue pigment being a $\text{CoO} \cdot \text{ZnO} \cdot \text{SiO}_2$ type pigment containing Mo.

Figure 2.

- 1 -

FIGURE 1




FIGURE 2

