



\*G00002\*



\*159159\*

## Catalysts for the purification of ethylene

- The present invention relates to catalysts for the purification  
5 of ethylene comprising copper and zinc and, if desired, one or  
more promoters and supports and produced by precipitation,  
drying, calcination and pressing, with or without addition of  
additives, wherein the pressed catalyst particles are subjected  
to further calcination at from 300 to 700°C.
- 10 Ethylene is an important raw material for the production of  
polyethylene. The industrial-scale preparation of ethylene, e.g.  
by cracking of naphtha in a steam cracker, gives impure ethylene  
from which catalyst poisons which adversely affect the  
15 performance of polymerization catalysts such as organoaluminum  
Ziegler-Natta catalysts or chromium-containing Phillips  
catalysts have to be removed (Industrielle organische Chemie, K.  
Weißermel and H.-J. Arpe, Verlag Chemie, 1976, pages 57, 58, 59,  
65, 66, and Ziegler-Natta Catalysts and Polymerisations, J.  
20 Boor, Academic Press 1979, pages 1, 2, 280 to 285).

- Petrochemical Technology Quarterly (PTQ), pages 103 to 107  
(1997) discloses Cu/ZnO catalysts for the purification of  
feedstock for polymerizations. The performance of these  
25 catalysts at low temperatures is in need of improvement and they  
are sensitive to acetylene impurities.

It is an object of the present invention to remedy the  
abovementioned disadvantages.

- 30 We have found that this object is achieved by new and improved  
catalysts for the purification of ethylene comprising copper and  
zinc and, if desired, one or more promoters and supports and  
produced by precipitation, drying, calcination and pressing,  
35 with or without addition of additives, wherein the pressed  
catalyst particles are subjected to further calcination at from  
300 to 700°C.

- The catalysts of the present invention can be produced, for  
40 example, as follows:

- Using conventional methods, nitrate solutions of copper and zinc  
can be precipitated, for example by means of sodium hydrogen  
carbonate solution at from 20 to 80°C, preferably from 25  
45 to 70°C, particularly preferably from 30 to 60°C, in particular  
from 40 to 55°C, and these precipitates can be mixed with an  
Al<sub>2</sub>O<sub>3</sub> suspension, washed, slurried and spray dried, calcined and

shaped (with or without addition of additives such as graphite, talc, stearates, Walocel, starch, boron trifluoride).

The shaped catalysts obtained in this way are subjected to an after-treatment by calcination at from 300 to 700°C, preferably from 350 to 650°C, particularly preferably from 400 to 600°C, in particular from 450 to 580°C, for generally from 0.5 to 10 hours, preferably from 1 to 3 hours, particularly preferably from 1 to 2 hours, in particular from 1 to 1.5 hours. In a particularly preferred embodiment, the temperature increases during the residence time.

The novel catalysts obtained in this way generally have a BET surface area of from 10 to 100 m<sup>2</sup>/g, preferably from 30 to 90 m<sup>2</sup>/g, particularly preferably from 40 to 80 m<sup>2</sup>/g, in particular from 50 to 75 m<sup>2</sup>/g.

In the production of the catalysts of the present invention, they are generally obtained in "oxidized" form, i.e. the copper is present in the catalyst in the form of copper oxide. These catalysts of the invention can be converted into their "reduced" form by means of hydrogen, preferably in a hydrogen atmosphere at from 80 to 180°C, preferably from 100 to 160°C, particularly preferably from 120 to 140°C, and a pressure of from 1 to 50 bar, so that the copper in them is at least partly present in metallic form. In a particular embodiment, the "reduced" form of the catalysts can also be obtained in situ, i.e. by mixing sufficient amounts of hydrogen into the ethylene stream to be purified.

The composition of the catalysts in "oxidized" form can be varied within a wide range. In general, suitable catalysts comprise from 30 to 50% by weight, preferably from 35 to 45% by weight, particularly preferably from 40 to 45% by weight, of CuO, from 30 to 50% by weight, preferably from 35 to 45% by weight, particularly preferably from 40 to 45% by weight, of ZnO, from 5 to 40% by weight, preferably from 10 to 30% by weight, particularly preferably from 20 to 30% by weight, of Al<sub>2</sub>O<sub>3</sub>, SiO<sub>2</sub>, TiO<sub>2</sub>, MgO, iron oxides or mixtures thereof and from 0 to 5% by weight, preferably from 0 to 2% by weight, particularly preferably from 0 to 1% by weight, of promoters, and preferably consist of these except for trace components which are associated with the abovementioned components.

Suitable promoters are potassium, sodium, manganese, chromium, cobalt, tungsten, molybdenum, nickel, iron, magnesium, calcium or mixtures thereof, preferably potassium, manganese, chromium,

## 3

molybdenum or mixtures thereof, particularly preferably potassium, chromium, molybdenum or mixtures thereof.

The size and shape of the catalysts of the invention can be  
5 chosen freely, for example tablets, rings, stars, wagon wheels, extrudates such as cylinders or pellets; preference is given to annular tablets or tablets.

The purification of ethylene using the catalysts of the present  
10 invention can be carried out as follows:

The ethylene to be purified can, in a two-stage process, be reacted

- 15 a) in the presence of hydrogen over the catalysts of the present invention in the reduced state at from 70 to 110°C, preferably from 75 to 100°C, particularly preferably from 80 to 95°C, and a pressure of from 5 to 80 bar, preferably from 10 to 70 bar, particularly preferably from 20 to 60 bar, and  
20 subsequently
- b) over the catalysts of the present invention in the oxidized state at from 70 to 110°C, preferably from 75 to 100°C, particularly preferably from 80 to 95°C, and a pressure of  
25 from 5 to 80 bar, preferably from 10 to 70 bar, particularly preferably from 20 to 60 bar.

The catalysts of the present invention have a higher resistance to acetylenes than catalysts which have not undergone an  
30 after-treatment according to the invention by subsequent calcination of the shaped bodies. The catalysts of the present invention can be operated at a content of acetylenes of up to 200 ppm in the ethylene to be purified.

35 This two-stage process can be preceded by a hydrogenation step in which the ethylene to be purified is passed together with a sufficient amount of hydrogen over a hydrogenation catalyst, e.g. a noble metal hydrogenation catalyst, for example 0.3% by weight of Pd on an Al<sub>2</sub>O<sub>3</sub> support. This is generally appropriate  
40 when large amounts of acetylenes, i.e. amounts of more than 200 ppm, are present in the ethylene to be purified.

## Examples

## Example 1

## 5 Production of the comparative catalyst

A mixed metal nitrate solution is prepared from 54% strength nitric acid, copper metal and zinc oxide, with the Cu/Zn ratio having to be 100:103. Using this solution, a precipitation with  
10 20% strength sodium carbonate solution is carried out in an aluminum hydroxide slurry. The precipitate slurry produced in this way is subsequently filtered in a filter press and washed. After filtration and washing of the filtercake, the filtercake was slurried, filtered again and washed [electrical  
15 conductivity: less than 150 microsiemens; nitrate content: less than 25 ppm]. The filtercake was slurried with water to produce a 20% strength by weight suspension and this was spray dried to give a powder which was calcined for 1 hour at 525°C in a rotary tube. [The loss on ignition determined by the measurement method  
20 GV 900 (loss on ignition at 900°C) was 12% by weight.] The powder obtained in this way was mixed with 1% by weight of graphite and pressed to form cylindrical tablets having a diameter of 5 mm and a thickness of 3 mm. These contained 40% by weight of CuO, 40% by weight of ZnO, 19.9% by weight of Al<sub>2</sub>O<sub>3</sub>  
25 and 0.1% by weight of K<sub>2</sub>O as promoter. The bulk density was 1.2 kg/l, the porosity was 0.3 ml/g, and the BET surface area was 125 m<sup>2</sup>/g.

## Example 2

30

## Production of the catalyst of the present invention

The conventional catalyst obtained as described above was calcined in a rotary tube at 490°C in the inlet zone and 550°C  
35 in the outlet zone, i.e. at a temperature which increased during the residence time, for 1.2 hours. The bulk density was 1.24 kg/l, the porosity was 0.34 ml/g, and the BET surface area was 64 m<sup>2</sup>/g.

## 40 Example 3

## Preparation of carbon dioxide from carbon monoxide

A gas mixture comprising 1125 standard l/h of nitrogen and 0.1%  
45 by volume of carbon monoxide was passed through a test apparatus comprising an adiabatically operated reactor containing a catalyst charge of 450 ml at a space velocity of 2500 standard

## 5

liters of gas per liter of catalyst and hour at from 90 to 120°C. At the outlet, the remaining unreacted carbon monoxide was measured. The conversion and the temperature required are a measure of the effectiveness.

5 The results are reported below.

Catalyst as described in Example 1

At a reaction temperature of 91°C, relatively no oxidation took  
10 place; all the CO broke through, i.e. it was found again at the outlet of the test apparatus. At 120°C, the conversion was greater than 99% only during the first minutes; after 15 minutes, 90 ppm of CO were present in the tailgas (conversion: 91%), while after 10 hours large amounts broke through and the  
15 content was 360 ppm (conversion: 36%).

Catalyst as described in Example 2

At a reaction temperature of 91°C, the gas at the outlet of the  
20 test apparatus contained only 9 ppm of CO both after 10 hours and after 18 hours. The conversion was thus 99.1% after both 10 hours and 18 hours.

25

30

35

40

45

We claim:

1. A catalyst for the purification of ethylene, comprising  
5 copper and zinc and, if desired, one or more promoters and supports and produced by precipitation, drying, calcination and pressing, with or without addition of additives, wherein the pressed catalyst particles are subjected to further calcination at from 300 to 700°C.
- 10 2. A catalyst for the purification of ethylene, consisting of copper and zinc, if desired partly in oxidic form, and if desired, one or more promoters and supports and produced by precipitation, drying, calcination and pressing, with or  
15 without addition of additives, wherein the pressed catalyst particles are subjected to further calcination at from 300 to 700°C.
- 20 3. A catalyst as claimed in claim 1 or 2 which has a BET surface area of from 10 to 100 m<sup>2</sup>/g.
4. A process for the purification of ethylene using a catalyst as claimed in any of claims 1 to 3, which comprises
  - 25 a) operating the catalyst in the reduced state in the presence of hydrogen at from 70 to 110°C and a pressure of from 5 to 80 bar and subsequently
  - b) in the oxidized state at from 70 to 110°C and a pressure  
30 of from 5 to 80 bar.
5. The use of a catalyst as claimed in any of claims 1 to 3 for the purification of ethylene.
- 35 6. The use of a catalyst as claimed in any of claims 1 to 3 for the purification of ethylene at from 70 to 110°C.

40

45