

SOLID CATALYST COMPONENT FOR OLEFIN POLYMERIZATION,
COMPRISING TITANIUM ATOMS, MAGNESIUM ATOMS, HALOGEN
ATOMS AND HYDROCARBYLOXY GROUPS

5 Field of the Invention

 The present invention relates to a process for producing
a solid catalyst component for olefin polymerization, a
process for producing an olefin polymerization catalyst, and
a process for producing an olefin polymer.

10

Background of the Invention

 JP 10-212319A (corresponding to US 6,187,883B)
discloses a highly stereoregular olefin polymer produced by
polymerizing an olefin in the presence of a polymerization
15 catalyst, the catalyst being formed according to a process
comprising the steps of (1) reducing a titanium compound with
an organomagnesium compound in the presence of a combination
of an organosilicon compound with an ester compound, thereby
producing a solid product, (2) contacting the solid product
20 with a halogenation compound, an internal electron donor and
an organic acid halide, thereby producing a solid catalyst
component containing trivalent titanium atoms, and (3)
contacting the solid catalyst component containing trivalent
titanium atoms, an organoaluminum compound and an external
25 electron donor.

Summary of the Invention

However, the above highly stereoregular olefin polymer is not sufficient in stiffness of its injection-molded article, namely, is not sufficient in its stereoregularity, whereas
5 injection-molded articles having superior stiffness are particularly required.

In view of the above circumstances, the present invention has an object to provide:

(i) a solid catalyst component for olefin
10 polymerization capable of producing a highly stereoregular olefin polymer, which can be molded into an injection-molded article having superior stiffness;

(ii) a process for producing the above solid catalyst component (i);

15 (iii) a process for producing an olefin polymerization catalyst using the above solid catalyst component (i); and

(iv) a process for producing an olefin polymer using an olefin polymerization catalyst produced according to the above process (iii).

20 The present invention is a solid catalyst component for olefin polymerization, comprising titanium atoms, magnesium atoms, halogen atoms and hydrocarbyloxy groups, wherein the following filtrate contains titanium atoms in a concentration of 0.08 mg-Ti/ml-filtrate or lower, measured according to a
25 method comprising the steps of:

(1) preparing a suspension of the solid catalyst

component for olefin polymerization in heptane having a concentration of 0.1 g-solid catalyst component/ml-suspension;

(2) heating the suspension at 70°C for 30 minutes under stirring;

(3) filtering the suspension, thereby obtaining a filtrate; and

(4) measuring a concentration of titanium atoms contained in the filtrate.

Also, the present invention is a process for producing the above solid catalyst component for olefin polymerization, comprising the following steps (1) and (4) in this order, or comprising the following step (1), one or more repetitions of a combination of the following steps (2) and (3) in this order, and the following step (4), in this order:

(1) contacting a solid material containing magnesium atoms and hydrocarbyloxy groups, a halogenation compound and an internal electron donor and/or organic acid halide with one another, thereby obtaining a solid component;

(2) washing the solid component with a hydrocarbon solvent;

(3) contacting the washed solid component, a halogenation compound, and an internal electron donor and/or organic acid halide with one another; and

(4) washing the solid component with a hydrocarbon solvent at 70°C or higher four or more times.

Further, the present invention is a process for producing an olefin polymerization catalyst, comprising the step of contacting a solid catalyst component for olefin polymerization produced according to the above production process, an organoaluminum compound and an external electron donor with one another.

Furthermore, the present invention is a process for producing an olefin polymer, comprising the step of contacting an olefin with an olefin polymerization catalyst produced according to the above production process.

Detailed Description of the Invention

As explained above, the process of the present invention for producing a solid catalyst component for olefin polymerization has two embodiments. The first embodiment comprises the above steps (1) and (4), and those steps are carried out in this order. The second embodiment comprises the above step (1), one or more repetitions of a combination of the above steps (2) and (3), and the above step (4), and those steps are carried out in this order. In case that the second embodiment has two repetitions of a combination of the above steps (2) and (3), all the steps are carried out in the following order:

step (1) → step (2) → step (3) → step (2) → step (3)
→ step (4).

It should be noted that both embodiments have the step (4) after the step (1) in case of the first embodiment, or after the final

step (3) in case of the second embodiment.

Regarding the step (1):

The solid component obtained in the step (1) may be known
 5 in the art, which is disclosed in prior arts such as JP
 10-212319A corresponding to US 6,187,883B and JP 7-216017A
 corresponding to US 5,608,018A.

Examples of the solid material used in the step (1) are
 the following solid materials (i) to (iii), and the solid
 10 material (iii) is preferable among them:

(i) dihydrocarbyloxymagnesiums represented by the
 formula, $Mg(OR^1)(OR^2)$, wherein R^1 and R^2 is independently of each
 other a hydrocarbyl group having 1 to 20 carbon atoms;

(ii) hydrocarbyloxymagnesium halides represented by
 15 the formula, $Mg(OR^3)X^1$, wherein R^3 is a hydrocarbyl group having
 1 to 20 carbon atoms, and X^1 is a halogen atom; and

(iii) solid materials containing trivalent titanium
 atoms, magnesium atoms and hydrocarbyloxy groups.

Examples of the dihydrocarbyloxymagnesiums
 20 represented (i) by the above formula, $Mg(OR^1)(OR^2)$, are
 dimethoxymagnesium, diethoxymagnesium, dipropoxymagnesium,
 dibutoxymagnesium, dipentoxymagnesium, dihexyloxymagnesium,
 dioctoxymagnesium, diphenoxymagnesium,
 dicyclohexyloxymagnesium, methoxyethoxymagnesium,
 25 methoxypropoxymagnesium, methoxybutoxymagnesium,
 ethoxypropoxymagnesium, and ethoxybutoxymagnesium. Among

them, preferred is dimethoxymagnesium, diethoxymagnesium or dipropoxymagnesium, and more preferred is diethoxymagnesium.

A process for producing dihydrocarbyloxymagnesiums (i) represented by the above formula, $Mg(OR^1)(OR^2)$, is not limited. Preferable examples thereof are (1) a process comprising the step of reacting a magnesium metal, an alcohol and a small amount of a halogen-containing compound and/or halogen, with one another, and (2) a process comprising the step of reacting a dialkylmagnesium compound with an alkoxy silicon compound.

Examples of the hydrocarbyloxymagnesium halides (ii) represented by the above formula, $Mg(OR^3)X^1$, are methoxymagnesium chloride, ethoxymagnesium chloride, propoxymagnesium chloride, butoxymagnesium chloride, pentoxymagnesium chloride, hexyloxymagnesium chloride, octoxymagnesium chloride, phenoxy magnesium chloride, and cyclohexyloxymagnesium chloride, and compounds obtained by replacing the chlorine atom contained in the above-exemplified compounds with a fluorine atom, a bromine atom or a iodine atom. Among them, preferred is methoxymagnesium chloride, ethoxymagnesium chloride or propoxymagnesium chloride, and more preferred is ethoxymagnesium chloride.


A process for producing hydrocarbyloxymagnesium halides (ii) represented by the above formula, $Mg(OR^3)X^1$, is not limited. Preferable examples of the process are (1) a process comprising the step of reacting a Grignard compound

with an alkoxysilicon compound, and (2) a process comprising the step of reacting a Grignard compound with alcohol.

Examples of the hydrocarbyloxy group contained in the above solid materials (iii) are hydrocarbyloxy groups having
5 1 to 20 carbon atoms. Among them, preferred is a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, or a hexoxy group.

The solid material used in the step (1) is preferably the above solid material (iii), which contains the trivalent
10 titanium atoms in an amount of preferably 50% or more, and more preferably 90% or more, provided that the total amount of titanium atoms contained in the solid material (iii) is 100%, and contains the hydrocarbyloxy groups in an amount of preferably 20% by weight or more, and more preferably 25% by
15 weight or more, provided that the amount of the solid material (iii) is 100% by weight.

A process for producing the solid material (iii) comprises, for example, the step of reducing a titanium compound represented by the following formula [I] with an
20 organomagnesium compound in the presence of an organosilicon compound containing a Si-O bond, or in the presence of a combination of the organosilicon compound with an ester compound in view of improving an activity of a polymerization catalyst:



wherein R^4 is a hydrocarbyl group having 1 to 20 carbon atoms;
 X^2 is independently of one another a halogen atom or a
 5 hydrocarbyloxy group having 1 to 20 carbon atoms; and a is a
 number of 1 to 20, and preferably a number satisfying $1 \leq a$
 ≤ 5 .

Examples of R^4 in the above formula [I] are an alkyl group
 such as a methyl group, an ethyl group, a propyl group, an
 10 isopropyl group, a butyl group, an isobutyl group, an amyl group,
 an isoamyl group, a hexyl group, a heptyl group, an octyl group,
 a decyl group and a dodecyl group; an aryl group such as a phenyl
 group, a cresyl group, a xylyl group and a naphthyl group; a
 cycloalkyl group such as a cyclohexyl group and a cyclopentyl
 15 group; an allyl group such as a propenyl group; and an aralkyl
 group such as a benzyl group. Among them, preferred is an alkyl
 group having 2 to 18 carbon atoms, or an aryl group having 6
 to 18 carbon atoms, and particularly preferred is a linear alkyl
 group having 2 to 18 carbon atoms.

20 Examples of the halogen atom of X^2 in the above formula
 [I] are a chlorine atom, a bromine atom and an iodine atom. Among
 them, particularly preferred is a chlorine atom.

Examples of the hydrocarbyloxy group having 1 to 20




carbon atoms of X^2 in the above formula [I] are those derived from the above-exemplified hydrocarbyl groups as R^4 , such as a methoxy group derived from a methyl group, an ethoxy group derived from an ethyl group, etc. Among them, particularly
5 preferred is an alkoxy group derived from the above-exemplified linear alkyl group having 2 to 18 carbon atoms as R^4 , such as an ethoxy group derived from an ethyl group, etc.

Examples of the titanium compound represented by the
10 above formula [I] are tetramethoxytitanium, tetraethoxytitanium, tetra-n-propoxytitanium, tetraisopropoxytitanium, tetra-n-butoxytitanium, tetraisobutoxytitanium, n-butoxytitanium trichloride, di-n-butoxytitanium dichloride, tri-n-butoxytitanium
15 chloride, di-n-tetraisopropylpolytitanate which is a mixture of compounds having "a" of 2 to 10 in the above formula [I], tetra-n-butylpolytitanate which is a mixture of compounds having "a" of 2 to 10 in the above formula [I], tetra-n-hexylpolytitanate which is a mixture of compounds
20 having "a" of 2 to 10 in the above formula [I], and tetra-n-octylpolytitanate which is a mixture of compounds having "a" of 2 to 10 in the above formula [I], and a condensate obtained by reacting tetraalkoxytitanium with a small amount of water. Among them, preferred is a titanium compound having
25 "a" of 1, 2 or 4 in the above formula [I], and particularly preferred is tetra-n-butoxytitanium, tetra-n-butyltitanium

dimer, or tetra-n-butylyltitanium tetramer. Those titanium compounds may be used in a combination of two or more thereof.

Examples of the above organosilicon compound are those represented by the following respective formulas:

5



10 wherein R^5 is a hydrocarbyl group having 1 to 20 carbon atoms; R^6 , R^7 , R^8 , R^9 and R^{10} are independently of one another a hydrocarbyl group having 1 to 20 carbon atoms, or a hydrogen atom; t is an integer satisfying $0 < t \leq 4$; u is an integer of 1 to 1,000; and v is an integer of 2 to 1,000.


15 Examples of the organosilicon compound are

tetramethoxysilane,	dimethyldimethoxysilane,
tetraethoxysilane,	triethoxyethylsilane,
diethoxydiethylsilane,	ethoxytriethylsilane,
tetraisopropoxysilane,	diisopropoxydiisopropylsilane,
20 tetrapropoxysilane,	dipropoxydipropylsilane,
tetrabutoxysilane,	dibutoxydibutylsilane,
dicyclopentoxydiethylsilane,	diethoxydiphenylsilane,
cyclohexyloxytrimethylsilane,	phenoxytrimethylsilane,
tetraphenoxysilane,	triethoxyphenylsilane,
25 hexamethyldisiloxane,	hexaethyldisiloxane,
hexapropyldisiloxane,	octaethyltrisiloxane,

dimethylpolysiloxane, diphenylpolysiloxane,
methylhydropolysiloxane and phenylhydropolysiloxane.

Among them, preferred is an alkoxyasilane compound represented by the above formula, $\text{Si}(\text{OR}^5)_t\text{R}^{6}_{4-t}$, wherein t is
5 preferably an integer satisfying $1 \leq t \leq 4$, and more preferably 4 (namely, tetraalkoxyasilane compound). Tetraethoxyasilane is the most preferable compound.

The above organomagnesium compound may be any compound containing a magnesium-carbon bond therein. The organomagnesium
10 compound is preferably a Grignard compound represented by the following first formula, or a dihydrocarbylmagnesium represented by the following second formula:



wherein R^{11} is a hydrocarbyl group having 1 to 20 carbon atoms; X^3 is a halogen atom; and R^{12} and R^{13} are independently of each other a hydrocarbyl group having 1 to 20 carbon atoms. Among
20 them, more preferred is a Grignard compound, and particularly preferred is a solution of a Grignard compound in an ether, in order to obtain a polymerization catalyst having a good shape.

Examples of R^{11} , R^{12} and R^{13} are an alkyl group having 1 to 20 carbon atoms, an aryl group, an aralkyl group and an alkenyl
25 group, such as a methyl group, an ethyl group, a propyl group, an isopropyl group, a butyl group, a sec-butyl group, a tert-butyl

group, an isoamyl group, a hexyl group, an octyl group, a 2-ethylhexyl group, a phenyl group and a benzyl group.

The organomagnesium compound may be used as its complex soluble in a hydrocarbon solvent, which complex can be obtained
5 by reacting the organomagnesium compound with an organometal compound such as that of Li, Be, B, Al or Zn.

Examples of the above ester compound are monocarboxylic acid esters and polycarboxylic acid esters. Among them, preferred are unsaturated aliphatic carboxylic acid esters
10 such as methacrylic acid esters and maleic acid esters, or aromatic carboxylic acid esters such as phthalic acid esters, and particularly preferred are phthalic acid dialkyl esters. Specific examples thereof are saturated aliphatic carboxylic acid esters, unsaturated aliphatic carboxylic acid esters,
15 alicyclic carboxylic acid esters, and aromatic carboxylic acid esters. More specific examples thereof are methyl acetate, ethyl acetate, phenyl acetate, methyl propionate, ethyl propionate, ethyl butyrate, ethyl valerate, ethyl acrylate, methyl methacrylate, ethyl benzoate, butyl benzoate, methyl
20 toluate, ethyl toluate, ethyl anisate, diethyl succinate, dibutyl succinate, diethyl malonate, dibutyl malonate, dimethyl maleate, dibutyl maleate, diethyl itaconate, dibutyl itaconate, monoethyl phthalate, dimethyl phthalate, methyl ethyl phthalate, diethyl phthalate, di-n-propyl phthalate,
25 diisopropyl phthalate, di-n-butyl phthalate, diisobutyl phthalate, dipentyl phthalate, di-n-hexyl phthalate,

di-n-heptyl phthalate, di-n-octyl phthalate,
di(2-ethylhexyl) phthalate, diisodecyl phthalate,
dicyclohexyl phthalate and diphenyl phthalate.

Each of the above organosilicon compound, titanium
5 compound and ester compound is preferably combined with a
solvent. Examples of the solvent are aliphatic hydrocarbons
such as hexane, heptane, octane and decane; aromatic
hydrocarbons such as toluene and xylene; alicyclic
hydrocarbons such as cyclohexane, methylcyclohexane and
10 decalin; and ether compounds such as diethyl ether, di-n-butyl
ether, diisoamyl ether and tetrahydrofuran.

A temperature of the above reduction reaction is usually
-50 to 70°C, preferably -30 to 50°C, and particularly preferably
-25 to 35°C. A time thereof is not particularly limited, and
15 it is usually about 30 minutes to about 6 hours. The reduction
reaction may be followed by heating at 0 to 120°C.

The solid material prepared in the above reduction
reaction may be supported on a carrier such as a porous inorganic
oxide and a porous organic polymer. The carrier may be known
20 in the art. Examples of the carrier are inorganic oxides such
as SiO₂, Al₂O₃, MgO, TiO₂ and ZrO₂; and polymers such as
polystyrene, a styrene-divinylbenzene copolymer, a
styrene-ethylene glycol dimethacrylate copolymer,
polymethyl acrylate, polyethyl acrylate, a methyl
25 acrylate-divinylbenzene copolymer, polymethyl methacrylate,
a methyl methacrylate-divinylbenzene copolymer,

polyacrylonitrile, an acrylonitrile-divinylbenzene copolymer, polyvinyl chloride, polyethylene and polypropylene. Among them, preferred is an organic polymer, and particularly preferred is a styrene-divinylbenzene
5 copolymer or an acrylonitrile-divinylbenzene copolymer.

In order to support effectively the solid material on a carrier, the carrier has a pore volume of preferably $0.3 \text{ cm}^3/\text{g}$ or more, and more preferably $0.4 \text{ cm}^3/\text{g}$ or more, in a pore radius of 20 to 200 nm. A ratio of the above pore volume is preferably
10 35% or more, and more preferably 40% or more, provided that a pore volume in a pore radius of 3.5 to 7,500 nm is 100%.

The above organosilicon compound is used in an amount of usually 1 to 500 mol, preferably 1 to 300 mol, and particularly preferably 3 to 100 mol, in terms of an amount of
15 silicon atoms contained in the organosilicon compound, per mol of titanium atoms contained in the titanium compound used.

The above organomagnesium compound is used in an amount of usually 0.1 to 10 mol, preferably 0.2 to 5.0 mol, and particularly preferably 0.5 to 2.0 mol in terms of the amount
20 of magnesium atoms contained in the organomagnesium compound used, per mol of the total of the amount of silicon atoms contained in the organosilicon compound used, and the amount of titanium atoms contained in the titanium compound used.

Also, the organosilicon compound, the titanium
25 compound and the organomagnesium compound are respectively used such that a solid catalyst component contains magnesium


atoms in an amount of usually 1 to 51 mol, preferably 2 to 31 mol, and particularly preferably 4 to 26 mol, per mol of titanium atoms contained in the solid catalyst component.

The above ester compound is used in an amount of usually
5 0.05 to 100 mol, preferably 0.1 to 60 mol, and particularly preferably 0.2 to 30 mol, per mol of titanium atoms contained in the titanium compound used.

The solid material obtained by the above reduction reaction is usually separated from a reaction mixture, and then,
10 is washed several times with an inert hydrocarbon solvent such as hexane, heptane and toluene. The thus obtained solid material contains trivalent titanium atoms, magnesium atoms and hydrocarbyloxy groups. The solid material generally has an amorphous structure, or a very weak crystalline structure, and
15 the former structure is particularly preferred.

The halogenation compound used in the above step (1) means a compound capable of replacing the hydrocarbyloxy group contained in the solid material with a halogen atom. The halogenation compound is preferably a halogen compound of
20 Group 4, 13 or 14 elements in the Periodic Table of the elements, and more preferably a halogen compound of Group 4 or 14 elements. When the solid material contains no titanium atom, at least a halogen compound of a titanium atom is used as the halogenation compound.

25 The above halogen compound of Group 4 elements is preferably a compound represented by the following formula:



wherein M^1 is an atom of Group 4; R^{14} is a hydrocarbyl group having
 5 1 to 20 carbon atoms, and when plural R^{14} s exist, they are the
 same as, or different from one another; X^4 is a halogen atom;
 and b is a number satisfying $0 \leq b < 4$, preferably $0 \leq b \leq$
 2, and particularly preferably $b = 0$.

Examples of the above M^1 are a titanium atom, a zirconium
 10 atom and a hafnium atom. Among them, preferred is a titanium
 atom.


Examples of the above R^{14} are an alkyl group such as a
 methyl group, an ethyl group, a propyl group, an isopropyl group,
 a butyl group, an isobutyl group, a tert-butyl group, an amyl
 15 group, an isoamyl group, a tert-amyl group, a hexyl group, a
 heptyl group, an octyl group, a decyl group and a dodecyl group;
 an aryl group such as a phenyl group, a cresyl group, a xylyl
 group and a naphthyl group; an allyl group such as a propenyl
 group; and an aralkyl group such as a benzyl group. Among them,
 20 preferred is an alkyl group having 2 to 18 carbon atoms, or an
 aryl group having 6 to 18 carbon atoms, and particularly
 preferred is a linear alkyl group having 2 to 18 carbon atoms.

Examples of X^4 are a chlorine atom, a bromine atom and
 an iodine atom. Among them, particularly preferred is a
 25 chlorine atom.

Examples of the halogen compound of Group 4 elements

represented by the above formula are a titanium tetrahalide such as titanium tetrachloride, titanium tetrabromide and titanium tetraiodide; an alkoxytitanium trihalide such as methoxytitanium trichloride, ethoxytitanium trichloride, butoxytitanium trichloride, phenoxytitanium trichloride and ethoxytitanium tribromide; and a dialkoxytitanium dihalide such as dimethoxytitanium dichloride, diethoxytitanium dichloride, dibutoxytitanium dichloride, diphenoxytitanium dichloride and diethoxytitanium dibromide; and hafnium compounds obtained by replacing the titanium atom contained in the above-exemplified titanium compounds with a hafnium atom. Among them, most preferred is titanium tetrachloride.

The above halogen compound of Group 13 or 14 elements is preferably a compound represented by the following formula:



wherein M^2 is an atom of Group 13 or 14; R^{15} is a hydrocarbyl group having 1 to 20 carbon atoms; X^5 is a halogen atom; m is the valence of M^2 ; and c is a number satisfying $0 < c \leq m$.

Examples of the atom of Group 13 are a boron atom, an aluminum atom, a gallium atom, an indium atom and a thallium atom. Among them, preferred is a boron atom or an aluminum atom, and more preferred is an aluminum atom.

Examples of the atom of Group 14 are a carbon atom, a silicon atom, a germanium atom, a tin atom and a lead atom. Among

them, preferred is a silicon atom, a germanium atom or a tin atom, and more preferred is a silicon atom or a tin atom.

For example, when M^2 is a silicon atom, m is 4, and c is preferably 3 or 4.

5 Examples of X^5 are a fluorine atom, a chlorine atom, a bromine atom and an iodine atom. Among them, preferred is a chlorine atom.

10 Examples of the above R^{15} are an alkyl group such as a methyl group, an ethyl group, a n-propyl group, an isopropyl group, a n-butyl group, an isobutyl group, an amyl group, an isoamyl group, a hexyl group, a heptyl group, an octyl group, a decyl group and a dodecyl group; an aryl group such as a phenyl group, a tolyl group, a cresyl group, a xylyl group and a naphthyl group; a cycloalkyl group such as a cyclohexyl group and a cyclopentyl group; an allyl group such as a propenyl group; 15 and an aralkyl group such as a benzyl group. Among them, preferred is an alkyl group or an aryl group; and more preferred is a methyl group, an ethyl group, a n-propyl group, a phenyl group or a p-tolyl group.

20 Examples of the above halogen compound of Group 13 elements are trichloroborane, methyldichloroborane, ethyldichloroborane, phenyldichloroborane, cyclohexyldichloroborane, dimethylchloroborane, methylethylchloroborane, trichloroaluminum, 25 methyldichloroaluminum, ethyldichloroaluminum, phenyldichloroaluminum, cyclohexyldichloroaluminum,

dimethylchloroaluminum, diethylchloroaluminum,
 methylethylchloroaluminum, ethylaluminum sesquichloride,
 gallium chloride, gallium dichloride, trichlorogallium,
 methyldichlorogallium, ethyldichlorogallium,
 5 phenyldichlorogallium, cyclohexyldichlorogallium,
 dimethylchlorogallium, methylethylchlorogallium, indium
 chloride, indium trichloride, methylindium dichloride,
 phenylindium dichloride, dimethylindium chloride, thallium
 chloride, thallium trichloride, methylthallium dichloride,
 10 phenylthallium dichloride and dimethylthallium chloride; and
 compounds obtained by replacing the chlorine atom contained in
 the above-exemplified compounds with a fluorine atom, a
 bromine atom or an iodine atom.

Examples of the above halogen compound of Group 14
 15 elements are tetrachloromethane, trichloromethane,
 dichloromethane, monochloromethane, 1,1,1-trichloroethane,
 1,1-dichloroethane, 1,2-dichloroethane,
 1,1,2,2-tetrachloroethane, tetrachlorosilane,
 trichlorosilane, methyltrichlorosilane,
 20 ethyltrichlorosilane, n-propyltrichlorosilane,
 n-butyltrichlorosilane, phenyltrichlorosilane,
 benzyltrichlorosilane, p-tolyltrichlorosilane,
 cyclohexyltrichlorosilane, dichlorosilane,
 methyldichlorosilane, ethyldichlorosilane,
 25 dimethyldichlorosilane, diphenyldichlorosilane,
 methylethyldichlorosilane, monochlorosilane,

- | | | |
|----|--|--------------------------|
| | trimethylchlorosilane, | triphenylchlorosilane, |
| | tetrachlorogermane, | trichlorogermane, |
| | methyltrichlorogermane, | ethyltrichlorogermane, |
| | phenyltrichlorogermane, | dichlorogermane, |
| 5 | dimethyldichlorogermane, | diethyldichlorogermane, |
| | diphenyldichlorogermane, | monochlorogermane, |
| | trimethylchlorogermane, | triethylchlorogermane, |
| | tri-n-butylchlorogermane, | tetrachlorotin, |
| | methyltrichlorotin, | n-butyltrichlorotin, |
| 10 | dimethyldichlorotin, | di-n-butyldichlorotin, |
| | di-isobutyldichlorotin, | diphenyldichlorotin, |
| | divinyldichlorotin, methyltrichlorotin, phenyltrichlorotin, | |
| | dichlorolead, methylchlorolead and phenylchlorolead; and | |
| | compounds obtained by replacing the chlorine atom contained in | |
| 15 | the above-exemplified compounds with a fluorine atom, a | |
| | bromine atom or an iodine atom. Among them, preferred is | |
| | tetrachlorosilane, | methyltrichlorosilane, |
| | ethyltrichlorosilane, | n-propyltrichlorosilane, |
| | n-butyltrichlorosilane, | phenyltrichlorosilane, |
| 20 | tetrachlorotin, methyltrichlorotin or n-butyltrichlorotin. | |

The halogenation compound is preferably titanium tetrachloride, methyldichloroaluminum, ethyldichloroaluminum, tetrachlorosilane, phenyltrichlorosilane, methyltrichlorosilane, ethyltrichlorosilane, n-propyltrichlorosilane or tetrachlorotin, or a combination of two or more thereof, and


particularly preferably titanium tetrachloride or tetrachlorosilane, from a viewpoint of an activity of a polymerization catalyst.

Use of the above internal electron donor in the step (1)
5 may improve an activity or copolymerizability of a polymerization catalyst in the present invention. Examples of the internal electron donor are oxygen-containing electron donors such as ethers, ketones, aldehydes, carboxylic acids, organic acid esters, inorganic acid esters, organic acid amides,
10 inorganic acid amides and acid anhydrides; and nitrogen-containing electron donors such as ammonia, amines, nitriles and isocyanates. Among them, preferred are organic acid esters and/or ethers, and more preferred are carboxylic acid esters and/or ethers.

15 Examples of the above carboxylic acid esters of the internal electron donor are monocarboxylic acid esters and polycarboxylic acid esters. More specific examples thereof are saturated aliphatic monocarboxylic acid esters, saturated aliphatic polycarboxylic acid esters, unsaturated aliphatic
20 monocarboxylic acid esters, unsaturated aliphatic polycarboxylic acid esters, alicyclic monocarboxylic acid esters, alicyclic polycarboxylic acid esters, aromatic monocarboxylic acid esters, and aromatic polycarboxylic acid esters. Preferred are unsaturated aliphatic carboxylic acid
25 esters such as methacrylic acid esters and maleic acid esters, or aromatic carboxylic acid esters such as benzoic acid esters

and phthalic acid esters. Specific examples thereof are methyl acetate, ethyl acetate, phenyl acetate, methyl propionate, ethyl propionate, ethyl butyrate, ethyl valerate, ethyl acrylate, methyl methacrylate, ethyl benzoate, butyl benzoate, 5 methyl toluate, ethyl toluate, ethyl anisate, diethyl succinate, dibutyl succinate, diethyl malonate, dibutyl malonate, dimethyl maleate, dibutyl maleate, diethyl itaconate, dibutyl itaconate, and phthalic acid esters represented by the following formula [II]:

10



wherein R¹⁶, R¹⁷, R¹⁸ and R¹⁹ are independently of one another a hydrogen atom or a hydrocarbyl group; and X⁶ and X⁷ are 15 independently of each other a group consisting of hydrogen atoms and carbon atoms, or a group consisting of hydrogen atoms, carbon atoms and one or more oxygen atoms contained in ether bonds.

R¹⁶, R¹⁷, R¹⁸ and R¹⁹ are preferably a hydrogen atom or a 20 hydrocarbyl group having 1 to 10 carbon atoms, and two or more hydrocarbyl groups of R¹⁶, R¹⁷, R¹⁸ and R¹⁹ may be linked to one another to form a ring; X⁶ and X⁷ are preferably a hydroxyl group or an alkoxy group having 1 to 20 carbon atoms; and when an

aromatic ring exists other than the R^{16} - R^{19} carrying-benzene ring, the aromatic ring may be partially or totally hydrogenated.

The phthalic acid derivatives represented by the above formula are preferably phthalic acid dialkyl esters; and particularly preferably phthalic acid dialkyl esters, whose
 5 two alkyl groups have 8 or less carbon atoms in total. Examples of the phthalic acid derivatives are dimethyl phthalate, methyl ethyl phthalate, diethyl phthalate, di-n-propyl phthalate, diisopropyl phthalate, di-n-butyl phthalate,
 10 diisobutyl phthalate, dipentyl phthalate, di-n-hexyl phthalate, di-n-heptyl phthalate, diisoheptyl phthalate, di-n-octyl phthalate, di(2-ethylhexyl) phthalate, di-n-decyl phthalate, diisodecyl phthalate, dicyclohexyl phthalate, diphenyl phthalate, and phthalic dichloride, and a
 15 combination of two or more thereof. Among them, preferred is diethyl phthalate, di-n-propyl phthalate, diisopropyl phthalate, di-n-butyl phthalate, or diisobutyl phthalate.


Examples of the above ethers of the internal electron donor are dialky ethers, cyclic ethers which are heterocyclic
 20 compounds having at least one ether bond ($-C-O-C-$) in their rings, and 1,3-diethers.

Examples of the above dialky ethers are dimethyl ether, diethyl ether, di-n-propyl ether, diisopropyl ether, di-n-butyl ether, diisobutyl ether, methyl-n-propyl ether,
 25 methyl-n-butyl ether, ethyl-n-propyl ether, ethyl-n-butyl ether, and methyl cyclohexyl ether. Among them, preferred is

di-n-butyl ether, which is hereinafter referred to as "dibutyl ether" or "butyl ether".

Examples of the above cyclic ethers are ethylene oxide, propylene oxide, trimethylene oxide, tetrahydrofuran, 2,5-dimethoxytetrahydrofuran, tetrahydropyran, hexamethylene oxide, 1,3-dioxepane, 1,3-dioxane, 1,4-dioxane, 1,3-dioxolane, 2-methyl-1,3-dioxolane, 2,2-dimethyl-1,3-dioxolane, 4-methyl-1,3-dioxolane, 2,4-dimethyl-1,3-dioxolane, furan, 2,5-dimethylfuran and s-trioxane. Among them, preferred are cyclic ethers containing at least one -C-O-C-O-C- bond in their rings.

Examples of the above 1,3-diethers are those represented by the following formula [III]:



wherein R^{20} , R^{21} , R^{22} and R^{23} are independently of one another a C_{1-20} linear alkyl group, a branched alkyl group, an alicyclic alkyl group, an aryl group or an aralkyl group, and R^{20} and R^{21} may be independently of each other a hydrogen atom, and may be linked to each other to form a ring.

Examples of the 1,3-diethers represented by the above formula [III] are 2,2-diisobutyl-1,3-dimethoxypropane, 2-isopropyl-2-isopentyl-1,3-dimethoxypropane,

- 2,2-bis(cyclohexylmethyl)-1,3-dimethoxypropane,
 2-isopropyl-2-3,7-dimethyloctyl-1,3-dimethoxypropane,
 2,2-diisopropyl-1,3-dimethoxypropane,
 2-isopropyl-2-cyclohexylmethyl-1,3-dimethoxypropane,
 5 2,2-dicyclohexyl-1,3-dimethoxypropane,
 2-isopropyl-2-isobutyl-1,3-dimethoxypropane,
 2,2-diisopropyl-1,3-dimethoxypropane,
 2,2-dipropyl-1,3-dimethoxypropane,
 2-isopropyl-2-cyclohexyl-1,3-dimethoxypropane,
 10 2-isopropyl-2-cyclopentyl-1,3-dimethoxypropane,
 2,2-dicyclopentyl-1,3-dimethoxypropane, and
 2-heptyl-2-pentyl-1,3-dimethoxypropane, and a combination of
 two or more thereof.

The organic acid halide used in the step (1) is
 15 preferably monocarboxylic acid halides or polycarboxylic acid
 halides. Examples thereof are aliphatic carboxylic acid
 halides, alicyclic carboxylic acid halides, and aromatic
 carboxylic acid halides. Specific examples thereof are acetyl
 chloride, propionic acid chloride, butyric acid chloride,
 20 valeric acid chloride, acrylic acid chloride, methacrylic acid
 chloride, benzoic acid chloride, toluic acid chloride, anisic
 acid chloride, succinic acid chloride, malonic acid chloride,
 maleic acid chloride, itaconic acid chloride, and phthalic
 acid chloride. Among them, preferred are aromatic
 25 monocarboxylic acid chlorides such as benzoic acid chloride
 and toluic acid chloride, or aromatic dicarboxylic acid

dichlorides such as phthalic acid dichloride, further preferred are aromatic dicarboxylic acid dichlorides, and particularly preferred is phthalic acid dichloride.

5 The step (1) is carried out usually in an atmosphere of an inert gas such as nitrogen and argon. Examples of an order of contacting the solid material with the halogenation compound and the internal electron donor and/or organic acid halide are the following (1) to (10):

(1) adding a halogenation compound and an internal
10 electron donor to a solid material in an optional order;

(2) adding a halogenation compound and an organic acid halide to a solid material in an optional order;

(3) adding a mixture of a halogenation compound, an internal electron donor and an organic acid halide to a solid
15 material;

(4) adding a mixture of a halogenation compound and an internal electron donor, and an organic acid halide, in an optional order, to a solid material;

(5) adding an internal electron donor to a solid
20 material, and then, adding a halogenation compound thereto;

(6) adding an internal electron donor to a solid material, and then, adding a halogenation compound and an internal electron donor thereto, in an optional order, wherein the former internal electron donor or the latter internal
25 electron donor is additionally added;

(7) adding an internal electron donor to a solid

material, and then, adding a mixture of a halogenation compound and an internal electron donor thereto, wherein the former internal electron donor or the latter internal electron donor is additionally added;

5 (8) adding a solid material and an internal electron donor to a halogenation compound in an optional order;

 (9) adding a solid material and an organic acid halide to a halogenation compound in an optional order; and

 (10) adding a solid material, an internal electron donor
10 and an organic acid halide to a halogenation compound in an optional order.

The above orders (1) to (10) may be followed by one or more steps of adding a halogenation compound or a mixture of a halogenation compound and an internal electron donor.

15 Among them, preferred is the order (2); the order (4); the order (4) followed by one or more steps of adding a mixture of a halogenation compound and an internal electron donor; or the order (7), wherein the second step of adding a mixture of a halogenation compound and an internal electron donor may be
20 repeated. More preferred is the order (4); the order (4) followed by one or more steps of adding a mixture of a halogenation compound and an internal electron donor; or the order (7), wherein the second step of adding a mixture of a halogenation compound and an internal electron donor may be
25 repeated. Particularly preferred is the order (4) using an ether as an internal electron donor, followed by the step of

adding a mixture of a halogenation compound and an internal electron donor, wherein the internal electron donor is a combination of a carboxylic acid ester and an ether, and further followed by one or more steps of adding a mixture of a
5 halogenation compound and an internal electron donor, wherein the internal electron donor is an ether; or the order (7) using a carboxylic acid ester as the first internal electron donor, and using a combination of a carboxylic acid ester with an ether as the second internal electron donor, followed by one or more
10 steps of adding a mixture of a halogenation compound and an internal electron donor, wherein the internal electron donor is an ether.

A method for contacting the solid material, the halogenation compound, the internal electron donor and/or
15 organic acid halide with one another is not particularly limited. Examples of the method are conventional methods such as a slurry method, and a mechanically pulverizing method using a ball mill. The mechanically pulverizing method is preferably carried out in the presence of a diluent, in order to suppress
20 production of fine powders, thereby obtaining a solid component having a narrow particle size distribution.

The above diluent is preferably inert to the solid material, the halogenation compound, the internal electron donor and the organic acid halide. Examples of the diluent are
25 aliphatic hydrocarbons such as pentane, hexane, heptane and octane; aromatic hydrocarbons such as benzene, toluene and

xylene; licyclic hydrocarbons such as cyclohexane and cyclopentane; and halogenated hydrocarbons such as 1,2-dichloroethane and monochlorobenzene. Among them, preferred are aliphatic hydrocarbons or aromatic hydrocarbons, more preferred are aromatic hydrocarbons, and further preferred is toluene or xylene.

The above diluent is used in an amount of usually 0.1 to 1,000 mL, and preferably 1 to 100 mL, per one g of the solid material, per one contact.

A time for the above contact is not particularly limited, and is preferably 0.5 to 8 hours, and more preferably 1 to 6 hours. Its temperature is usually -50 to 150°C, preferably 0 to 140°C, and further preferably 60 to 135°C.

The above contact is carried out preferably under agitation, in order to maintain a homogeneous slurry state. Too weak agitation may result in insufficient contact, and therefore, the finally obtained polymerization catalyst may be insufficient in its stereoregularity or activity. Too strong agitation may break the solid component obtained.

The halogenation compound is used in an amount of usually 0.5 to 1,000 mmol, preferably 1 to 200 mmol, and further preferably 2 to 100 mmol, per one gram of the solid material. The halogenation compound is used preferably in combination with the internal electron donor, which is used in an amount of usually 1 to 100 mol, preferably 1.5 to 75 mol, and further preferably 2 to 50 mol, per one mol of the halogenation compound.

The internal electron donor is used in an amount of usually 0.01 to 100 mmol, preferably 0.05 to 50 mmol, and further preferably 0.1 to 20 mmol, per one gram of the solid material.

5 The organic acid halide is used in an amount of usually 0.1 to 100 mmol, preferably 0.3 to 50 mmol, and further preferably 0.5 to 20 mmol, per one gram of the solid material, and is used in an amount of usually 0.01 to 1.0 mol, and preferably 0.03 to 0.5 mol, per one mol of magnesium atoms contained in the solid material.

10 When the internal electron donor or organic acid halide is used in an amount of larger than 100 mmol per one gram of the solid material, the obtained solid component having a particulate form may be broken.

15 Regarding the step (2):

The step (2) washes away from the solid component such compounds as titanium compounds unfavorable in view of the object of the present invention.

20 Examples of the hydrocarbon solvent used in the step (2) are aliphatic hydrocarbons such as pentane, hexane, heptane, octane and decane; and aromatic hydrocarbon solvents such as benzene, toluene, ethylbenzene and xylene. Among them, preferred is an aromatic hydrocarbon, and more preferred is toluene or xylene.

25 Examples of the hydrocarbon solvent used in the step (2) are aromatic hydrocarbon solvents such as benzene, toluene,

ethylbenzene and xylene. Among them, preferred is toluene or xylene.

The hydrocarbon solvent is used in an amount of usually 0.1 to 1,000 mL, and preferably 1 to 100 mL, per one g of the solid component, per one washing.

A washing temperature in the step (2) is usually -50 to 150°C, preferably 0 to 140°C, and further preferably 60 to 135°C. A washing time therein is not particularly limited, and is preferably 1 to 120 minutes, more preferably 2 to 60 minutes, and further preferably 5 to 40 minutes. The number of the washing is usually one to five times, and six or more times if needed.

The washing is carried out preferably under agitation, in order to maintain a homogeneous slurry state. Too weak agitation may result in insufficient washing, and therefore, the finally obtained polymerization catalyst may be insufficient in its stereoregularity or activity. Too strong agitation may break the solid component.

Regarding the step (3):

Contact conditions in the step (3) are the same as those in the step (1), except that the solid material in the step (1) is replaced with the washed solid component.

Regarding the step (4):

Examples of the hydrocarbon solvent used in the step (4) are aliphatic hydrocarbons such as pentane, hexane, heptane,

octane and decane; aromatic hydrocarbons such as benzene, toluene, ethylbenzene and xylene. Among them, preferred is an aromatic hydrocarbon, and more preferred is toluene or xylene.

5 An amount of the hydrocarbon solvent used for washing, and a washing time are similar to those in the step (2) mentioned above.

A washing temperature is 70°C or higher, generally 70 to 150°C, preferably 90 to 140°C, and more preferably 100 to 135°C.

10 A washing is carried out four or more times, preferably five or more times, and more preferably six or more times.

The step (4) washes away from the solid component such compounds as titanium compounds unfavorable in view of the object of the present invention, more strongly than the step
15 (2), to the extent that the following filtrate contains titanium atoms in a concentration of 0.08 mg-Ti/ml-filtrate or lower, measured according to a method comprising the steps of:

(1) preparing a suspension of the finally-obtained solid catalyst component for olefin polymerization in heptane
20 having a concentration of 0.1 g-solid catalyst component/ml-suspension;

(2) heating the suspension at 70°C for 30 minutes under stirring;

(3) filtering the suspension using, for example, a G4
25 filter, thereby obtaining a filtrate; and

(4) measuring a concentration of titanium atoms

contained in the filtrate, according to an analytical method known in the art such as an UV-optical density method and an ICP emission method.


5 The solid catalyst component for olefin polymerization in the present invention contains preferably chlorine atoms as the halogen atoms, and contains preferably ethoxy groups and/or butoxy groups as the hydrocarbyloxy groups.

The solid catalyst component for olefin polymerization in the present invention comprises titanium atoms in an amount
10 of 0.1 to 3.0% by weight and preferably 0.5 to 2.5% by weight, magnesium atoms in an amount of 5 to 30% by weight and preferably 10 to 25% by weight, halogen atoms in an amount of 40 to 70% by weight and preferably 45 to 65% by weight, and hydrocarbyloxy groups in an amount of 0.1 to 3.5% by weight and preferably 0.5
15 to 3.0% by weight, the total weight of the solid catalyst component being 100% by weight.

The solid catalyst component for olefin polymerization may be used for polymerization in a form of its slurry in an inert solvent, or may be used for polymerization in a form of
20 its fluid dry powder. Examples of a drying method for obtaining the fluid dry powder are a reduced-pressure drying method, and a method comprising the step of removing volatile matters contained in the solid catalyst component under a flow of an inert gas such as nitrogen and argon. The drying is carried out
25 at preferably 0 to 200°C, and more preferably 50 to 100°C, and for preferably 0.01 to 20 hours, and more preferably 0.5 to 10

hours.

The organoaluminum compound used in the present invention is a compound having one or more aluminum-carbon bonds in its molecule, and may be a compound known in the art.
 5 Examples thereof are compounds represented by the following formulas, respectively:



10

wherein R^{24} to R^{28} are independently of one another a hydrocarbyl group having 1 to 20 carbon atoms; X^8 is a halogen atom, a hydrogen atom or an alkoxy group; and w is a number satisfying $2 \leq w \leq 3$.

15 Examples of the organoaluminum compound are trialkylaluminums such as triethylaluminum, triisobutylaluminum and trihexylaluminum; dialkylaluminum hydrides such as diethylaluminum hydride and diisobutylaluminum hydride; dialkylaluminum halides such as
 20 diethylaluminum chloride; mixtures of trialkylaluminums and dialkylaluminum halides such as a mixture of triethylaluminum and diethylaluminum chloride; and alkylalumoxanes such as tetraethyldialumoxane and tetrabutylldialumoxane. Among them, preferred are trialkylaluminums, mixtures of
 25 trialkylaluminums with dialkylaluminum halides, or alkylalumoxanes; and particularly preferred is


triethylaluminum, triisobutylaluminum, a mixture of triethylaluminum with diethylaluminum chloride, or tetraethyldialumoxane.

5 Examples of the external electron donor used in the present invention are oxygen-containing compounds, nitrogen-containing compounds, phosphorus-containing compounds and sulfur-containing compounds. Among them, preferred are oxygen-containing compounds or nitrogen-containing compounds.

10 Examples of the oxygen-containing compounds are alkoxy silicon compounds, ethers, esters and ketones. Among them, preferred are alkoxy silicon compounds or ethers.

Examples of the alkoxy silicon compounds are compounds represented by the following formula:

15



wherein R^{29} is a hydrocarbyl group having 1 to 20 carbon atoms, a hydrogen atom, or a hetero atom-containing group, and when plural R^{29} s exist, they are the same as, or different from one another; R^{30} is a hydrocarbyl group having 1 to 20 carbon atoms, and when plural R^{30} s exist, they are the same as, or different from one another; and r is a number satisfying $0 \leq r < 4$.

20

Examples of the above hydrocarbyl group of R^{29} are a linear alkyl group such as a methyl group, an ethyl group, a propyl group, a butyl group and a pentyl group; a branched-chain

25

alkyl group such as an isopropyl group, a sec-butyl group, a tert-butyl group and a tert-amyl group; a cycloalkyl group such as a cyclopentyl group and a cyclohexyl group; a cycloalkenyl group such as a cyclopentenyl group; and an aryl group such as
 5 a phenyl group and a tolyl group.

The compounds represented by the above formula are preferably compounds having at least one hydrocarbyl group of R^{29} , which contains a secondary or tertiary carbon atom linked to the silicon atom.

10 Examples of the hetero atom contained in the above hetero atom-containing group of R^{29} are an oxygen atom, a nitrogen atom, a sulfur atom and a phosphorus atom. Examples of the hetero atom-containing group are a dimethylamino group, a methylethylamino group, a diethylamino group, an
 15 ethyl-n-propylamino group, a di-n-propylamino group, a pyrrolyl group, a pyridyl group, a pyrrolidinyl group, a piperidyl group, a perhydroindolyl group, a perhydroisoindolyl group, a perhydroquinolyl group, a perhydroisoquinolyl group, a perhydrocarbazolyl group, a
 20 perhydroacridinyl group, a furyl group, a pyranyl group, a perhydrofuryl group and a thienyl group. Among them, preferred are hetero atom-containing groups, whose hetero atom is directly linked to the silicon atom.

Examples of the above alkoxysilicon compounds as the
 25 oxygen-containing compounds are diisopropyldimethoxysilane, diisobutyldimethoxysilane,

- di-tert-butylmethoxysilane,
tert-butylmethyldimethoxysilane,
tert-butylethyldimethoxysilane,
tert-butyl-n-propyldimethoxysilane,
5 tert-butyl-n-butyldimethoxysilane,
tert-amylmethyldimethoxysilane,
tert-amylethyldimethoxysilane,
tert-amyl-n-propyldimethoxysilane,
tert-amyl-n-butyldimethoxysilane,
10 isobutylisopropyldimethoxysilane,
tert-butylisopropyldimethoxysilane,
dicyclobutyldimethoxysilane,
cyclobutylisopropyldimethoxysilane,
cyclobutylisobutyldimethoxysilane,
15 cyclobutyl-tert-butyldimethoxysilane,
dicyclopentyldimethoxysilane,
cyclopentylisopropyldimethoxysilane,
cyclopentylisobutyldimethoxysilane,
cyclopentyl-tert-butyldimethoxysilane,
20 dicyclohexyldimethoxysilane,
cyclohexylmethyldimethoxysilane,
cyclohexylethyldimethoxysilane,
cyclohexylisopropyldimethoxysilane,
cyclohexylisobutyldimethoxysilane,
25 cyclohexyl-tert-butyldimethoxysilane,
cyclohexylcyclopentyldimethoxysilane,

- cyclohexylphenyldimethoxysilane, diphenyldimethoxysilane,
 phenylmethyldimethoxysilane,
 phenylisopropyldimethoxysilane,
 phenylisobutyldimethoxysilane,
 5 phenyl-tert-butyldimethoxysilane,
 phenylcyclopentyldimethoxysilane,
 diisopropyldiethoxysilane, diisobutyldiethoxysilane,
 di-tert-butyldiethoxysilane, tert-butylmethyldiethoxysilane,
 tert-butylethyldiethoxysilane,
 10 tert-butyl-n-propyldiethoxysilane,
 tert-butyl-n-butyldiethoxysilane,
 tert-amylmethyldiethoxysilane,
 tert-amylethyldiethoxysilane,
 tert-amyl-n-propyldiethoxysilane,
 15 tert-amyl-n-butyldiethoxysilane,
 dicyclopentyldiethoxysilane, dicyclohexyldiethoxysilane,
 cyclohexylmethyldiethoxysilane,
 cyclohexylethyldiethoxysilane, diphenyldiethoxysilane,
 phenylmethyldiethoxysilane,
 20 2-norbornanemethyldimethoxysilane,
 bis(perhydroquinolino)dimethoxysilane,
 bis(perhydroisoquinolino)dimethoxysilane,
 (perhydroquinolino)(perhydroisoquinolino)dimethoxysilane,
 (perhydroquinolino)methyldimethoxysilane,
 25 (perhydroisoquinolino)methyldimethoxysilane,
 (perhydroquinolino)ethyldimethoxysilane,

(perhydroisoquinolino)ethyldimethoxysilane,
 (perhydroquinolino)(n-propyl)dimethoxysilane,
 (perhydroisoquinolino)(n-propyl)dimethoxysilane,
 (perhydroquinolino)(tert-butyl)dimethoxysilane,
 5 (perhydroisoquinolino)(tert-butyl)dimethoxysilane,
 diethylaminodimethoxysilane, and
 diethylaminodiethoxysilane.

Examples of the ethers of the above oxygen-containing
 compounds are those exemplified above as the cyclic ethers or
 10 the 1,3-diethers of the internal electron donor.

Examples of the nitrogen-containing compounds of the
 above external electron donor are 2,6-substituted piperidines
 such as 2,6-dimethylpiperidine and
 2,2,6,6-tetramethylpiperidine; substituted methylene
 15 diamines such as 2,5-substituted piperidines,
 N,N,N',N'-tetramethylmethylene diamine and
 N,N,N',N'-tetraethylmethylene diamine; and substituted
 imidazolidines such as 1,3-dibenzylimidazolidine. Among them,
 preferred are 2,6-substituted piperidines.

20 The external electron donor is particularly preferably
 cyclohexylmethyldimethoxysilane,
 cyclohexylethyldimethoxysilane,
 diisopropyldimethoxysilane,
 tert-butylethyldimethoxysilane,
 25 tert-butyl-n-propyldimethoxysilane, phenyldimethoxysilane,
 diphenyldimethoxysilane, dicyclobutyldimethoxysilane,

dicyclopentyldimethoxysilane, 1,3-dioxolane, 1,3-dioxane,
2,6-dimethylpiperidine, 2,2,6,6-tetramethylpiperidine,
2-isopropyl-2-isobutyl-1,3-dimethoxypropane,
2-isopropyl-2-isopentyl-1,3-dimethoxypropane,
5 2,2-diisobutyl-1,3-dimethoxypropane,
2,2-diisopropyl-1,3-dimethoxypropane or
2,2-dicyclohexyl-1,3-dimethoxypropane.

A method for contacting the solid catalyst component for
olefin polymerization with the organoaluminum compound and the
10 external electron donor is not limited. Examples of the method
are (1) a method comprising the steps of (1-1) contacting the
solid catalyst component with the organoaluminum compound and
the external electron donor in the presence or absence of a
solvent, and then (1-2) feeding the obtained mixture to a
15 polymerization reactor, (2) a method comprising the step of
feeding the solid catalyst component, the organoaluminum
compound and the external electron donor separately to a
polymerization reactor, thereby contacting those components
with one another in the polymerization reactor, and (3) a method
20 comprising the steps of (3-1) contacting any two of the solid
catalyst component, the organoaluminum compound and the
external electron donor with each other, thereby obtaining a
mixture, and (3-2) feeding the mixture and the remaining
component to a polymerization reactor, thereby contacting them
25 with each other in the polymerization reactor. The above
feeding to a polymerization reactor is carried out preferably

in a water-free state and in an atmosphere of an inert gas such as nitrogen and argon.

The olefin in the present invention means ethylene or α -olefins having three or more carbon atoms. Examples of the α -olefins are linear mono-olefins such as propylene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene and 1-decene; branched mono-olefins such as 3-methyl-1-butene, 3-methyl-1-pentene and 4-methyl-1-pentene; and vinylcyclohexane. Those olefins may be used in combination of two or more thereof, and may be used in combination with monomers containing plural unsaturated bonds such as conjugated dienes and non-conjugated dienes.

The olefin polymer in the present invention is preferably a propylene homopolymer, a 1-butene homopolymer, a 1-pentene homopolymer, a 1-hexene homopolymer, an ethylene-propylene copolymer, an ethylene-1-butene copolymer, an ethylene-1-hexene copolymer, a propylene-1-butene copolymer, a propylene-1-hexene copolymer, an ethylene-propylene-1-butene copolymer, an ethylene-propylene-1-hexene copolymer, or a hetero-block copolymer; more preferably a propylene homopolymer or a propylene copolymer containing mainly propylene units; further preferably a propylene homopolymer or a propylene copolymer containing 50% by weight or more of a propylene unit, the total of the propylene copolymer being 100% by weight; and particularly preferably a stereoregular propylene

homopolymer. The above "hetero-block copolymer" means a mixture of two or more kinds of polymers, such as a mixture of a propylene homopolymer with an ethylene-propylene copolymer, which is produced according to a process comprising the steps
5 of (i) homopolymerizing propylene, thereby forming a propylene homopolymer, and (ii) copolymerizing ethylene with propylene in the presence of the propylene homopolymer.

Stereoregularity of a propylene homopolymer or a propylene copolymer containing mainly propylene units can be
10 represented by an amount of soluble parts in xylene at 20°C (CXS) of the homopolymer or the copolymer. The smaller the CXS value is, the higher the stereoregularity is. A CXS of a propylene homopolymer is preferably 0.6% by weight or smaller, and more preferably 0.5% by weight or smaller, the total of the propylene
15 homopolymer being 100% by weight.

Prior to polymerizing an olefin in the presence of the above catalyst for olefin polymerization, which is referred to as "real polymerization", the following "pre-polymerization" can be carried out.

20 The pre-polymerization is carried out using a combination of the above solid catalyst component for olefin polymerization with a monomer such as an olefin, in order to make a pre-polymerized catalyst component whose surface is covered by a polymer such as a polyolefin formed by pre-polymerizing
25 the monomer such as an olefin. The real polymerization uses the solid catalyst component for olefin polymerization without

modification, or uses the above pre-polymerized catalyst component.

The pre-polymerized catalyst component is preferably produced by slurry polymerization of a small amount of an olefin
5 in the presence of the above solid catalyst component for olefin polymerization and organoaluminum compound. Examples of a solvent used for the slurry polymerization are inert hydrocarbon solvents such as propane, butane, isobutane, pentane, isopentane, hexane, heptane, octane, cyclohexane,
10 benzene and toluene. A partial or total amount of the inert hydrocarbon solvents may be replaced with liquid olefins.

The organoaluminum compound in the pre-polymerization is used in an amount of usually 0.5 to 700 mol, preferably 0.8 to 500 mol, and particularly preferably 1 to 200 mol, per one
15 mol of titanium atoms contained in the solid catalyst component for olefin polymerization used.

An amount of an olefin pre-polymerized is usually 0.01 to 1,000 g, preferably 0.05 to 500 g, and particularly preferably 0.1 to 200 g, per 1 g of the solid catalyst component
20 for olefin polymerization used.

A slurry concentration of the above slurry polymerization is preferably 1 to 500 g-solid catalyst component/liter-solvent, and particularly preferably 3 to 300 g-solid catalyst component/liter-solvent.

25 The pre-polymerization is carried out at preferably -20 to 100 °C, and particularly preferably 0 to 80°C. A partial

pressure of an olefin contained in a gas phase of the pre-polymerization is preferably 1 kPa to 2 MPa, and particularly preferably 10 kPa to 1 MPa, except an olefin having a liquid state under a pre-polymerization pressure and
5 temperature. A pre-polymerization time is not particularly limited, and is preferably 2 minutes to 15 hours.

Examples of a method for feeding the solid catalyst component, the organoaluminum compound and an olefin to a pre-polymerization reactor are (1) a method comprising the
10 steps of (1-1) feeding the solid catalyst component and the organoaluminum compound, and then (1-2) feeding an olefin, and (2) a method comprising the steps of (2-1) feeding the solid catalyst component and an olefin, and then (2-2) feeding the organoaluminum compound. Examples of a method for feeding an
15 olefin to a pre-polymerization reactor are (1) a method comprising the step of feeding an olefin one after another while keeping an inner pressure of a pre-polymerization reactor at a predetermined pressure, and (2) a method comprising the step of feeding the predetermined total amount of an olefin at the
20 beginning. In order to control a molecular weight of an obtained pre-polymer, a chain transfer agent such as hydrogen may be added to a pre-polymerization reactor.

The pre-polymerization may use a partial or total amount of the external electron donor to be used in the above-mentioned
25 production of the polymerization catalyst. An amount of an external electron donor used in the pre-polymerization is

usually 0.01 to 400 mol, preferably 0.02 to 200 mol, and particularly preferably 0.03 to 100 mol, per one mol of titanium atoms contained in the solid catalyst component, or is usually 0.003 to 5 mol, preferably 0.005 to 3 mol, and particularly preferably 0.01 to 2 mol, per 1 mol of the organoaluminum compound used.

In the pre-polymerization, a method for feeding the organoaluminum compound and the external electron donor to a pre-polymerization reactor is not particularly limited. Examples of the method are (1) a method comprising the step of feeding the external electron donor thereto separately from the organoaluminum compound, and (2) a method comprising the steps of (i) contacting the external electron donor with the organoaluminum compound, thereby forming a mixture, and then (ii) feeding the mixture to the pre-polymerization reactor. An olefin used for the pre-polymerization is the same as, or different from that used for the real polymerization.

The organoaluminum compound in the real polymerization is used in an amount of usually 1 to 1,000 mol, and particularly preferably 5 to 600 mol, per one mol of titanium atoms contained in the solid catalyst component used.

The external electron donor in the real polymerization is used in an amount of usually 0.1 to 2,000 mol, preferably 0.3 to 1,000 mol, and particularly preferably 0.5 to 800 mol, per one mol of titanium atoms contained in the solid catalyst component used, or is used in an amount of usually 0.001 to 5

mol, preferably 0.005 to 3 mol, and particularly preferably 0.01 to 1 mol, per one mol of the organoaluminum compound used.

The real polymerization is carried out:

(1) at usually -30 to 300°C , and preferably 20 to 180°C ;

5 (2) under a pressure, which is not particularly limited, of usually an atmospheric pressure to 10 MPa , and preferably 200 kPa to 5 MPa , from an industrial and economical point of view;

(3) according to a batchwise method or a continuous
10 method; and

(4) according to (4-1) a slurry or solution polymerization method with an inert hydrocarbon solvent such as propane, butane, isobutane, pentane, hexane, heptane and octane, (4-2) a bulk polymerization method using an olefin as
15 a solvent, which olefin is liquid at a polymerization temperature, or (4-3) a gas-phase polymerization method.

The real polymerization may be a hetero-block copolymerization carried out according to two or more polymerization steps.

20 In order to control a molecular weight of an olefin polymer produced, a chain transfer agent such as hydrogen may be used.

According to the present invention, there can be provided (i) a solid catalyst component for olefin
25 polymerization capable of producing a highly stereoregular olefin polymer, which can be molded into an injection-molded

article having superior stiffness, (ii) a process for producing the above solid catalyst component (i), (iii) a process for producing an olefin polymerization catalyst using the above solid catalyst component (i); and (iv) a process for producing an olefin polymer using an olefin polymerization catalyst produced according to the above process (iii).

Example

The present invention is explained in more detail with reference to the following Examples, which do not limit the present invention.

Example 1

1. Preparation of a solid catalyst component

A reactor equipped with a stirrer was purged with nitrogen gas, and then 800 liters of hexane, 6.8 kg of diisobutyl phthalate, 350 kg of tetraethoxysilane and 38.8 kg of tetra-n-butoxytitanium were put into the reactor. The resultant mixture was stirred. To the mixture, 900 liters of a dibutyl ether solution (concentration: 2.1 mol/liter) of butylmagnesium chloride were added dropwise at 7°C over 5 hours under stirring. After completion of the dropwise addition, the mixture was stirred at 20°C for one hour. The obtained reaction mixture was filtered to separate a solid. The separated solid was washed three times at room temperature with each 1,100 liters of toluene to obtain a washed solid. Toluene was added

to the washed solid, thereby obtaining 625 liters of a toluene slurry of the solid. The toluene slurry was heated at 70°C for one hour under stirring, and then was cooled down to the room temperature, thereby obtaining a toluene slurry of a solid material.

A part of the toluene slurry was dried under a reduced pressure, thereby obtaining a dried solid material. The dried solid material was found to contain 2.1% by weight of titanium atoms, 38.9% by weight of ethoxy groups, and 3.4% by weight of butoxy groups, the total weight of the dried solid material being 100% by weight, and the above titanium atoms were found to be trivalent.

Step (1):

A 100 mL-flask equipped with a stirrer, a dropping funnel and a thermometer was purged with nitrogen gas. There was put into the flask the above solid material-containing toluene slurry, the total of the toluene slurry used containing 8 g of the dried solid material. Supernatant toluene in the flask was taken out till the total volume of the toluene slurry was decreased to 26.5 mL. To the slurry, a mixture of 16.0 mL of titanium tetrachloride with 0.8 mL of dibutyl ether was added at 40°C, and further, a mixture of 2.0 mL of phthalic acid dichloride with 2.0 mL of toluene was added dropwise over five minutes. After completion of the dropwise addition, the resultant reaction mixture was stirred at 115°C for four hours.

The obtained reaction mixture was filtered at 115°C to separate a solid component.

Step (2):

- 5 The above-separated solid component was washed three times at 115°C with each 40 mL of toluene.

Step (3):

- 10 Toluene was added to the above-washed solid component, thereby obtaining 26.5 mL of a toluene slurry. To the toluene slurry, a mixture of 0.8 mL of dibutyl ether, 0.45 mL of diisobutyl phthalate, and 6.4 mL of titanium tetrachloride was added. The resultant mixture was stirred at 105°C for one hour. The obtained reaction mixture was filtered to separate a solid
15 component.

Step (2) repeated:

- 20 The above-separated solid component was washed two times at 105°C with each 40 mL of toluene.

Step (3) repeated:

- 25 Toluene was added to the above-washed solid component, thereby obtaining 26.5 mL of a toluene slurry. To the toluene slurry, a mixture of 0.8 mL of dibutyl ether with 6.4 mL of titanium tetrachloride was added. The resultant mixture was stirred at 105°C for one hour. The obtained reaction mixture

was filtered to separate a solid component.

Step (2) further repeated:

5 The above-separated solid component was washed two times at 105°C with each 40 mL of toluene.

Step (3) further repeated:

10 Toluene was added to the above-washed solid component, thereby obtaining 26.5 mL of a toluene slurry. To the toluene slurry, a mixture of 0.8 mL of dibutyl ether with 6.4 mL of titanium tetrachloride was added. The resultant mixture was stirred at 105°C for one hour. The obtained reaction mixture was filtered to separate a solid component.

15 Step (4):

The above-separated solid component was washed six times at 105°C with each 40 mL of toluene, and was further washed three times at a room temperature with each 40 mL of hexane. The washed solid component was dried under a reduced pressure, 20 thereby obtaining a solid catalyst component for olefin polymerization.

The above-obtained solid catalyst component for olefin polymerization was found to contain 1.6% by weight of titanium 25 atoms, 0.06% by weight of ethoxy groups, 0.15% by weight of butoxy groups, 7.6% by weight of diethyl phthalate, 0.8% by

weight of ethyl-n-butyl phthalate, and 2.5% by weight of diisobutyl phthalate, the total weight of the solid catalyst component being 100% by weight.

5 There was added 5.07 g of the above solid catalyst component for olefin polymerization to 51 mL of heptane maintained at 70°C, thereby preparing a suspension of the solid catalyst component for olefin polymerization in heptane having a concentration of 0.1 g-solid catalyst
10 component/mL-suspension. The prepared suspension was stirred at 70°C for 30 minutes, and was filtered with G4 filter. The obtained filtrate was found to contain titanium atoms in a concentration of 0.023 mg/mL, measured according to the following method comprising the steps of:

15 (1) putting 40 mL of the filtrate into a 50 mL measuring flask;

 (2) evaporating the total amount of heptane contained in the filtrate with a nitrogen gas flow;

 (3) decomposing the solid catalyst component with about
20 30 mL of 2 normal (2 N) dilute sulfuric acid;

 (4) adding 3 mL of hydrogen peroxide water having a concentration of 3% by weight, thereby preparing a liquid sample;

 (5) measuring a characteristic absorption of the liquid
25 sample at 410 nm with a double-beam spectrophotometer, U-2001, manufactured by Hitachi, Ltd.; and

(6) finding a concentration of titanium atoms in the filtrate, based on the characteristic absorption, with a calibration curve prepared in advance.

5 2. Polymerization of propylene

A stainless steel autoclave having a 3-liter inner volume was made vacuum, and hydrogen gas was added thereto till its partial pressure reached 0.15 MPa. There were put into the autoclave 7.81 mg of the above-obtained solid catalyst component, 2.6 mmol of triethylaluminum (organoaluminum compound) and 0.52 mmol of tert-butyl-n-propyldimethoxysilane (external electron donor), and then 780 g of liquid propylene was put therein. The autoclave was heated up to 70 °C, and propylene was polymerized at 70 °C for one hour, thereby obtaining 319 g of a powdery propylene homopolymer.

A yield of the propylene homopolymer per one g of the solid catalyst component was 40,800 g/g. The propylene homopolymer had 0.48% by weight of soluble parts in xylene at 20 °C (CXS), the total weight of the propylene homopolymer being 100% by weight; an intrinsic viscosity ($[\eta]$) of 1.71 dl/g; and a bulk density of 0.448 g/mL.

The above titanium atom content (% by weight) was measured according to a method comprising the steps of:

(1) decomposing about 20 mg of a sample with about 30

mL of 2 normal (2 N) dilute sulfuric acid;

(2) adding 3 mL (excess amount) of hydrogen peroxide water having a concentration of 3% by weight, thereby preparing a liquid sample;

5 (3) measuring a characteristic absorption of the liquid sample at 410 nm with a double-beam spectrophotometer, U-2001, manufactured by Hitachi, Ltd.; and

(4) finding a titanium atom content, based on the characteristic absorption, with a calibration curve prepared
10 in advance.

The above alkoxy group content (% by weight) was measured according to a method comprising the steps of:

(1) decomposing about 2 g of a sample with 100 mL of water
15 to obtain a liquid sample;

(2) measuring an amount of an alcohol (corresponding to an alkoxy group) contained in the liquid sample according to a gas chromatography internal standard method; and

(3) converting the obtained amount of an alcohol to an
20 alkoxy group content.

The above carboxylic acid ester content (% by weight) was measured according to a method comprising the steps of:

(1) dissolving 30 mg of a sample in 100 mL of
25 N,N-dimethylacetamide, thereby preparing a solution; and

(2) measuring a content of a carboxylic acid ester in

the solution according to a gas chromatography internal standard method.

The above valence of titanium atoms (trivalent titanium
5 atoms) was measured according to a method comprising the steps
of:

(1) dissolving about 70 mg of a solid material in about
30 mL of an aqueous solution consisting of 240 mL of purified
water, 113 g of tartaric acid and 260 mL of two normal (2 N)
10 sulfuric acid, thereby preparing a solution; and

(2) measuring a valence of titanium atoms contained in
the solution with a polarographic analyzer, P-1100,
manufacture by Yanagimoto Corporation according to a DC
(direct-current) electricity method.

15

The above amount of soluble parts in xylene at 20°C (CXS)
was measured according to a method comprising the steps of:

(1) dissolving 1 g of a polymer in 200 mL of boiling
xylene;

20 (2) cooling the solution gradually down to 50°C,

(3) further cooling the solution under stirring in an
ice-water bath down to 20°C,

(4) allowing the solution to stand at 20°C for 3 hours,
thereby precipitating a polymer,

25 (5) filtering off the precipitated polymer, thereby
obtaining a filtrate, and

(6) measuring the amount of the polymer dissolved in the filtrate, which polymer is the above soluble parts in xylene at 20°C.

The smaller the CXS value is, the larger stereoregularity the polymer has.

The above intrinsic viscosity ($[\eta]$) was measured at 135 °C using an Ubbelohde viscometer in TETRALINE (tetrahydronaphthalene) as a solvent.

10

The above bulk density was measured according to JIS K 6721 (1966), "JIS" being Japanese Industrial Standard.

Example 2

15 1. Preparation of a solid catalyst component

Example 1 was repeated except that "washing six times at 105°C with each 40 mL of toluene, and further washing three times at a room temperature with each 40 mL of hexane" in the step (4) of Example 1 was changed to "washing five times at 105°C with each 40 mL of toluene, and further washing three times at a room temperature with each 40 mL of hexane", thereby obtaining a solid catalyst component.

The above-obtained solid catalyst component was found to contain 1.7% by weight of titanium atoms, 0.07% by weight of ethoxy groups, 0.16% by weight of butoxy groups, 7.6% by weight of diethyl phthalate, 0.76% by weight of ethyl-n-butyl

25

phthalate, and 2.5% by weight of diisobutyl phthalate, the total weight of the solid catalyst component being 100% by weight.

There was added 4.98 g of the above solid catalyst
5 component to 49.8 mL of heptane maintained at 70°C, thereby preparing a suspension of the solid catalyst component in heptane having a concentration of 0.1 g-solid catalyst component/mL-suspension. The prepared suspension was stirred at 70°C for 30 minutes, and was filtered with G4 filter. The
10 obtained filtrate was found to contain titanium atoms in a concentration of 0.029 mg/mL, measured according to the above method.

2. Polymerization of propylene

15 Example 1 was repeated except that 7.81 mg of the solid catalyst component was changed to 4.48 mg of the above-obtained solid catalyst component, thereby obtaining 203 g of a powdery propylene homopolymer.

A yield of the propylene homopolymer per one g of the
20 solid catalyst component was 45,300 g/g. The propylene homopolymer had 0.55% by weight of soluble parts in xylene at 20°C (CXS), the total weight of the propylene homopolymer being 100% by weight; an intrinsic viscosity ($[\eta]$) of 1.68 dL/g; and a bulk density of 0.450 g/mL.

25

Example 3

1. Preparation of a solid catalyst component

Example 1 was repeated except that "washing six times at 105°C with each 40 mL of toluene, and further washing three times at a room temperature with each 40 mL of hexane" in the
5 step (4) of Example 1 was changed to "washing four times at 105°C with each 40 mL of toluene, and further washing three times at a room temperature with each 40 mL of hexane", thereby obtaining a solid catalyst component.

The above-obtained solid catalyst component was found
10 to contain 1.8% by weight of titanium atoms, 0.07% by weight of ethoxy groups, 0.18% by weight of butoxy groups, 7.8% by weight of diethyl phthalate, 0.8% by weight of ethyl-n-butyl phthalate, and 2.5% by weight of diisobutyl phthalate, the total weight of the solid catalyst component being 100% by
15 weight.

There was added 4.83 g of the above solid catalyst component to 48 mL of heptane maintained at 70°C, thereby preparing a suspension of the solid catalyst component in heptane having a concentration of 0.1 g-solid catalyst
20 component/mL-suspension. The prepared suspension was stirred at 70°C for 30 minutes, and was filtered with G4 filter. The obtained filtrate was found to contain titanium atoms in a concentration of 0.074 mg/mL, measured according to the above method.

25

2. Polymerization of propylene

Example 1 was repeated except that 7.81 mg of the solid catalyst component was changed to 5.82 mg of the above-obtained solid catalyst component, thereby obtaining 292 g of a powdery propylene homopolymer.

5 A yield of the propylene homopolymer per one g of the solid catalyst component was 50,200 g/g. The propylene homopolymer had 0.56% by weight of soluble parts in xylene at 20°C (CXS), the total weight of the propylene homopolymer being 100% by weight; an intrinsic viscosity ($[\eta]$) of 1.60 dl/g; and
10 a bulk density of 0.442 g/mL.

Comparative Example 1

1. Preparation of a solid catalyst component

Example 1 was repeated except that "washing six times
15 at 105°C with each 40 mL of toluene, and further washing three times at a room temperature with each 40 mL of hexane" in the step (4) of Example 1 was changed to "washing three times at 105°C with each 40 mL of toluene, and further washing three times at a room temperature with each 40 mL of hexane", thereby
20 obtaining a solid catalyst component.

The above-obtained solid catalyst component was found to contain 2.1% by weight of titanium atoms, 0.06% by weight of ethoxy groups, 0.19% by weight of butoxy groups, 7.7% by weight of diethyl phthalate, 0.8% by weight of ethyl-n-butyl
25 phthalate, and 2.5% by weight of diisobutyl phthalate, the total weight of the solid catalyst component being 100% by

weight.

There was added 4.55 g of the above solid catalyst component to 46 mL of heptane maintained at 70°C, thereby preparing a suspension of the solid catalyst component in
5 heptane having a concentration of 0.1 g-solid catalyst component/mL-suspension. The prepared suspension was stirred at 70°C for 30 minutes, and was filtered with G4 filter. The obtained filtrate was found to contain titanium atoms in a concentration of 0.085 mg/mL, measured according to the above
10 method.

2. Polymerization of propylene

Example 1 was repeated except that 7.81 mg of the solid catalyst component was changed to 8.21 mg of the above-obtained
15 solid catalyst component, thereby obtaining 432 g of a powdery propylene homopolymer.

A yield of the propylene homopolymer per one g of the solid catalyst component was 52,600 g/g. The propylene homopolymer had 0.62% by weight of soluble parts in xylene at
20 20°C (CXS), the total weight of the propylene homopolymer being 100% by weight; an intrinsic viscosity ($[\eta]$) of 1.66 dl/g; and a bulk density of 0.443 g/mL.

CLAIMS

1. A solid catalyst component for olefin polymerization, comprising titanium atoms, magnesium atoms, halogen atoms and hydrocarbyloxy groups, wherein the following filtrate contains titanium atoms in a concentration of 0.04 mg-Ti/ml-filtrate or lower, measured according to a method comprising the steps of:
- (1) preparing a suspension of the solid catalyst component for olefin polymerization in heptane having a concentration of 0.1 g-solid catalyst component/ml-suspension;
 - (2) heating the suspension at 70° for 30 minutes under stirring;
 - (3) filtering the suspension, thereby obtaining a filtrate; and
 - (4) measuring a concentration of titanium atoms contained in the filtrate,
- wherein the solid catalyst component is the one produced by a process comprising the following steps (1) and (4) in this order, or comprising the following step (1), one or more repetitions of a combination of the following steps (2) and (3) in this order, and the following step (4), in this order:
- (1) contacting a solid material containing magnesium atoms and hydrocarbyloxy groups, a halogenation compound and an internal electron donor and/or organic acid halide with one another, thereby obtaining a solid component;
 - (2) washing the solid component with a hydrocarbon solvent;

(3) contacting the washed solid component, a halogenation compound, and an internal electron donor and/or organic acid halide with one another; and

(4) washing the solid component with a hydrocarbon
5 solvent at 70°C or higher four or more times.

2. The solid catalyst component for olefin polymerization according to claim 1, wherein the filtrate

contains titanium atoms in a concentration of 0.03 mg-Ti/ml-filtrate or lower.

3. The solid catalyst component for olefin
5 polymerization according to claim 1, wherein the solid catalyst component comprises 0.1 to 3.0% by weight of titanium atoms, 5 to 30% by weight of magnesium atoms, 40 to 70% by weight of halogen atoms and 0.1 to 3.5% by weight of hydrocarbyloxy groups, the total weight of the solid catalyst
10 component being 100% by weight.

4. The solid catalyst component for olefin
polymerization according to claim 1, wherein the halogen atom
is a chlorine atom.

15

5. The solid catalyst component for olefin
polymerization according to claim 1, wherein the
hydrocarbyloxy group is an ethoxy group and/or butoxy group.